Reversible and reusable compartmentalized thermoplastic chip for coculture of dorsal root ganglion neurons

Solène Moreau, Raul Flores-Berdines, Anne Simon, Tatiana El Jalkh, Guillaume Taret, Anna Fomina,

Céline Dargenet-Becker, André Estevez-Torres, Sophie Bernard and Hugo Salmon**

* Contributed equally

E-mail: sophie.bernard@u-paris.fr; hugo.salmon@u-paris.fr

S. Moreau, C. Dargenet-Becker, A. Simon, A. Fomina, G. Taret, S. Bernard, H. Salmon
Université Paris Cité, INSERM UMR-S 1124, HEALTHFEX, Paris, France

R. Flores-Berdines, H. Salmon
Laboratoire NABI NAnomédecine, Biologie Extracellulaire, Intégratome et Innovations, CNRS
UMR8175, INSERM U1334, Université Paris Cité, 45 rue des Saints Pères, 75006 Paris, France

T. El Jalkh
IMRB INSERM U955 Université Paris-Est
51, avenue du Maréchal de Lattre de Tassigny 94010 Créteil, France

A. Estevez-Torres
LASIRE UMR CNRS 8516 Université de Lille
Avenue Paul Langevin 59650 Villeneuve-d'Ascq, France

Abstract

Compartmentalized microfluidic chips play an important role in understanding the cellular mechanisms involved in neurodegenerative disorders. Dorsal root ganglia are a well-established model for modelling the peripheral nervous system (PNS), but their development on a chip remains limited. Furthermore, it would be beneficial for the devices to be openable in order to access the biological material inside for analyses. Easy to prototype and biocompatible, styrenic block copolymers (SBC) are an alternative to polydimethylsiloxane (PDMS) that offer both reversible and permanent bonding properties. This paper presents a fast and straightforward method to produce compartmentalized SBC chips. The study validates the culture of murine dorsal root ganglia explants, comparing it to the standard methods, to obtain a model of the PNS. Moreover, the reversible bonding properties of the SBC permit the reuse of the chip with a quick and easy cleaning protocol. It provides direct access to the cells, opening the way for imaging and molecular biology analysis. The comparison of the resources required to produce PDMS and SBC chips highlights the importance of moving to reusable devices. These detachable, easy-to-manufacture and sustainable all-thermoplastic platforms provide an alternative way of prototyping compartmentalized devices *for in vitro* PNS modeling.

Keywords: Microfluidic chip, Dorsal root ganglia, sensory neurons, compartmentalized culture, styrenic bloc copolymers, soft thermoplastic elastomers

1. Introduction

The reduction of animal numbers and their replacement by alternative experimental methods are two of the 4R principles (reduction, replacement, refinement, and responsibility) and constitute a major strategic ethical challenge, prompting the development of *in vitro* models that can be used instead of *in vivo* studies involving animal models. Despite the rise of microphysiological systems, in neuropharmacology, the complexity of the physiological processes and the long time scales might explain why only few neurological conditions have been modeled to date.[1] While industrial sectors have played a role in democratizing these tools, reducing their demand on laboratory resources and broadening their applications in neurobiology could further advance this effort.[2]

Microfluidic devices for compartmentalized culture have offered the possibility to study the neuronal functions and structures in a highly controlled way.[3,4] Robert Campenot was the first to develop a device that enabled local control of axons and somas.[5] The aim was to physically separate the cell bodies from the axons to mimic the diverse microenvironments that a neuron might encounter. Subsequently, a variety of microfluidic devices have been developed for neuronal studies. Taylor initiated a two-compartment microfluidic device connected by straight microchannels [6] for the study of axonal injury, regeneration and transport. Samson *et al.* employed a five-parallel culture chamber configuration to circumvent cross-contamination and to establish an environmentally isolated neuronal population with synaptically interconnected cells.[7] Courte *et al*. designed a microchip with arc-shaped microchannels to control the orientation and filtering of axonal growth.[8] Sharma *et al.* proposed a keyhole design to model human nerves,[9] while Park *et al.* developed central circular chamber designs to promote axon growth in microchannels and the formation of a denser axonal network layer.[10,11] Electrospun aligned nanofiber-integrated compartmentalized microfluidic neuron culture systems have been developed by Luo *et al.* to improve axon alignment, length and stability.[12] Two-dimensional (2D) and three-dimensional (3D) compartmentalized co-culture systems on microdevices have been developed to analyze the interactions between neurons and glial cells in both the central nervous system (CNS)[11,13] and in the peripheral nervous system (PNS).[9,11,14–16]

Most of the PNS models focus on motor neurons, while there are only a few studies on sensory neurons on chip.[17–20] However, these studies focus on co-cultures of sensory neurons and oligodendrocytes, a glial cell that is specific to the central nervous system. Dorsal root ganglia (DRGs) represent a well-established model for PNS modeling, but their development on a chip remains limited. They mainly focus on pain signaling[21] and therapeutics[22] as well as on "nerve-on-chip".[23,24] In 2023, Mutschler *et al*.[25] proposed the first co-culture of neurons from dissociated DRGs and Schwann cells on a

76   compartmentalized microfluidic device. They highlighted the challenge of culturing DRGs as explants

77   in microfluidic chips. Notably, Park *et al.* were the only group to successfully culture a chick DRG ex-

78   plant in a compartmentalized microfluidic device.[26] To facilitate the seeding of the explant, they de-

79   signed a device with an open-top chamber.

80   Compartmentalized systems and organ-on-chip devices are becoming more widespread in the

field of Biology, requiring a re-evaluation of their sustainability and of the materials used in their man-

ufacture for specific applications. Currently, polydimethylsiloxane (PDMS) is predominantly used due

to its high oxygen permeability, while polystyrene (PS) is favored for large-scale production and align-

ment with biological standards.[27] However, there are no neurobiological applications that uses mate-

rials combining the advantages of PDMS and PS, such as styrenic block copolymers (SBCs).[28] Reversible

bonding of SBCs would be an advantage for accessing tissues during culture and for reusing devices.[29–

31] Moreover, as the organ-on-chip industry is expanding rapidly and access and production costs are

becoming critical for laboratory resources and carbon footprint,[32] there is no known comprehensive

assessment or methodology to evaluate the resources involved.

Here, we describe a fast and straightforward method for the fabrication of compartmentalized SBC

chips and demonstrate their reversible bonding and reusability for the culture of compartmentalized

peripheral nervous system model. We first propose a simple process for fabricating SBC chips with an

axisymmetric design adapted to anisotropic compartmentalized culture, particularly suitable for pri-

mary DRG explants. We confirm the theoretical compatibility of the design with neuron culture using

analytical and finite element models. The viability and axonal growth of $E13.5$ mouse embryonic DRGs

within SBC and equivalent PDMS chips were then compared. We present a rapid and reliable cleaning

procedure for SBC chips and evaluate their reusability. We also demonstrate the potential of reversible

bonding chips for direct imaging using electron microscopy, as well as for biological analysis techniques

(immunostaining, Western blot, RT-qPCR). Finally, we discuss the resources (energy, time, cost and

CO_2 equivalent emission) involved in the production of a PDMS compared to an SBC chip.

2. Results & discussion

2.1. Development of a compartmentalized SBC chip for coculture of DRG neurons

We developed a design and a workflow to produce axisymmetric compartmentalized 6-plexed

SBC devices. With the exception of the photolithography step, which is necessary for wide channels,

the fabrication process of SBC microfluidic chips **(Figure 1A)** is an out-of-the-cleanroom process. The

first phase was to replicate the SU-8 mold in an epoxy mold, which is more compatible with hot em-

bossing. It was used for 2 years, embossing more than 200 chips without any visible damage. The rep-

lication of the molds was confirmed by profilometry *(**Figure SI.1***). These open-top devices are made of

two layers that are simple to assemble thanks to the adhesive properties of SBC. A first $1\ mm$-thick layer containing the structures and a $2\ mm$-thick reservoir layer to increase the volume capacity and prevent rapid evaporation of the culture media (**Movie SI.1**) as well as shear stress during pipetting. The central chamber without the reservoir can only hold 7 μL, whereas it reaches a volume of 63 μL when the second layer is added. Due to the radial growth of axons in the DRGs, we designed a circular central chamber with a diameter of $4\ mm$ to facilitate the penetration of axons into the microchannels **(Figure 1B)**. The dimensions of the microchannels have been chosen to enable compartmentalization of somas in the central chamber and axons in the peripheral chambers.[6,33] Treatments can be added in the outer chambers without flowing back to the central chamber. The high fluidic resistance of the microchannels creates a small but sustained flow between the chambers, thereby counteracting the diffusion (**Figure SI.3**). This fluidic isolation allowed 6 independent peripheral chambers to be created. The sTPE devices bond easily to polystyrene (PS) **(Figure 1C)**, making them adaptable to already exist-ing basic culture plates. The Young's modulus of the SBC polymer is $1.15\ MPa$[28] which is in the same range as PDMS ($0.5 - 3\ MPa$). In addition, this material is biocompatible, gas permeable, optically transparent and exhibits reversible bonding that can withstand $1\ bar$ even after 10 sealing/unsealing cycles,[34] making it a suitable candidate for cell culture. The air plasma hydrophilization remains stable in time for at least one week for the SBC chips. The culture of peripheral neurons was demonstrated using either explants or dissociated embryonic DRGs harvested from $E13.5$ mouse embryos.

The device was also compatible with dissociated DRGs. It has been described that the radial flow pressure resulting from the circular fluidic design facilitates the positioning of cells in close prox-imity to the microchannels inlet.[10,11,35] Moreover, the circular design allows for axon coverage that is more than 3.5 times higher than that of square designs.[10] It allows the cultivation of both dissociated DRGs and explants while most of the DRGs cultured on chips are dissociated. Overall, this model pro-vides an experimental framework to study different aspects of Schwann cell development such as pro-liferation, migration, differentiation, and myelination of axons.[36] These co-cultures of neurons, Schwann cells and fibroblasts were placed directly into the central chambers and cultured within the SBC chips bonded to 6-well PS plates. The cultures could be maintained for one month within the de-vices, and no leakage or contamination was observed.

2.2. A shear stress compatible with DRG culture on a chip

In order to assess the shear stress experienced by the DRG in the chip, we performed a Finite Elements Method (FEM) analysis and particle velocimetry. As demonstrated by Liu *et al.*, it is essential to quantify the shear stress forces generated within the microchannels in order to evaluate the suita-bility of the device for biological studies. We used the FEM to visualize the speed v and the shear rate σ in a microchannel cross section **(Figure 2A)**, the two physical quantities being intrinsically linked by

$\sigma = \mu \nabla v$. The following values were obtained for a pressure gradient of 30 Pa, which represents the

theoretical maximum pressure that can be applied within the microfluidic device under study, given

the finite volume of the reservoirs. The maximum shear stress inside the cross section is 0.8 dyn. cm^{-2}.

A pressure gradient of 30 Pa is achieved when the central chamber is full and the peripheral chambers

are empty. However, this extreme case never occurs in practice when cells are in the chips. During the

media change, the pressure reached a maximum of 25 Pa for a few seconds, due to the presence of a

small volume of media within the chambers. Experimental validation was performed by measuring the

time required for 0.2 μm microbeads to cross the microchannels **(Figure 2B)**. The experiment was

started with a pressure of 25 Pa and stopped after 9 h, when the pressure had reached 0 Pa. The flow

rate (Q) inside the microchannels was calculated from the velocity of the microbeads and the area of

the cross section of a microchannel (A): $Q = v \times A$. An exponential regression was fitted to the exper-

imental results, with $v_{max} = 132.5$ $\mu m. s^{-1}$ and a time constant of $\tau = 3.18\ h$. It was then possible to

derive the shear stress inside the microchannels based on the following equation: $\sigma = \frac{6\eta Q}{h^2 w}$, where η

was fixed as the viscosity of water in Pa.s. For a maximum pressure of 25 Pa, the mean shear stress

obtained was 2.73 dyn.cm^{-2}.

2.3. Viability and axonal growth of DRG culture on a chip

In order to validate the DRG culture on our devices, we assessed the viability and the axonal

growth over time and according to the material. For viability, the dissociated cells formed a rather

uniform distribution of cells, thereby facilitating the Live/Dead staining. For axonal growth, the axisym-

metric growth of the explant is directional, thereby facilitating the segmentation and the quantification

of the network. DRGs at E13.5 are at a stage at which we can obtain a high yield of sensory neurons

and Schwann cells. Both exhibit high viability and plasticity.[36] After the DRGs were picked from the

extracted spinal cord, dissociated and seeded in PDMS and SBC chips, or in well plates as a control.

Their viability was assessed at day *in vitro* (DIV) $DIV3$ and $DIV7$. Comprehensive tiles of each culture

enable exhaustive quantification and better visualization **(Figure 3A)**. All the cells were segmented and

counted exhaustively (**Figure SI.6**). At $DIV3$, the cell density was below the expected seeding cell den-

sity due to the low survival rate of the primary cells during the seeding step. The number of live cells

was significantly higher in the control than in the chips (**Figure 3B**), with more than 1800 cells.mm^{-2} in

the 96-well plate against 600 cells.mm^{-2} in the PDMS chips, 880 cells.mm^{-2} in the SBC chips and 930

cells.mm^{-2} in the reused SBC chips at DIV7. However, there was no significant difference in the number

of dead cells between all the conditions. The overall number of cells increased by 13 % in the control

group between $DIV3$ and $DIV7$, compared to 64% in the PDMS chips. This rate was found to be similar

between SBC and reused SBC chips, at 31 % and 35 % respectively. Similarly, DRG explants were fixed

at $DIV3$, before the axons reached the microchannels, and at $DIV7$, after the axons had crossed the

microchannels **(Figure 3C)**. The growth speed was deduced from the axonal length (**Figure SI.7**). Due to the fluidic isolation, the antibodies were unable to diffuse from the peripheral chambers into the microchannels. As the axons started to cross the microchannels around $DIV4$, it was necessary to detach the SBC chips at $DIV7$ before staining the cells to fully observe them in the peripheral chambers (**Movie SI.2***)*. However, due to the irreversible bonding of the PDMS, it was not possible to obtain the length of the axon at $DIV7$ inside them. No significant difference was observed between the axonal length in 4-well control and the axonal length in the chips **(Figure 3D)**. From DIV0 to DIV3, the axonal growth speed was $443 \pm 33\ \mu\text{m}.\,\text{day}^{-1}$ and decreased to a speed of $324 \pm 36\ \mu\text{m}.\,\text{day}^{-1}$ from DIV3 to DIV7.

This design enables a uniform treatment in the central chamber and a gradient treatment in the peripheral chambers, due to the high resistance of the microchannels. This feature can be useful for drug treatments; however it prevents antibodies to reach the microchannels during immunostaining constraining us to open the chip to observe the entirety of the axons. In addition, the open-top device facilitates media changes and the CO2 exchange, while minimizing mechanical stress and shear stress compared to a closed-compartment device.[20] The stable hydrophilization was especially convenient for transport and long-term use compared to PDMS. We compared the maximum shear stress value obtained in our device to the maximum shear stress value that is sustainable for cortical neurons. We considered the value of $5\ \text{dyn}.\,\text{cm}^{-2}$ which was measured for a $24\ \text{h}$ exposure[37] as a reference, as to our knowledge there are no data on the effect of shear stress on sensory neurons. The maximum experimental shear stress obtained in our device is 1.25 times higher than the maximum theoretical shear stress. However, it is almost 2 times lower than the cell viability limit for cortical neurons. The maximum shear stress in our device is only reached for a few seconds, when the cells are inside, during the change of medium. An experimental study of the effect of the shear stress on the cell viability would help identify the limit in the context of peripheral nervous system (i.e. sensory neurons) but it would require a controlled flow rate. We numerically confirmed that the axonal growth rate is not impacted by the microfluidic chip, assuming a comparable threshold in our biological context. We made tiled images of the central chambers of the chips and of the wells of the controls to confirm the viability of the cells and ensure that our microfluidic architecture does not affect them. The tiles enabled us to monitor viability over time and confirm the homogeneous spatial distribution of dead cells in the chips. In contrast, in a standard well plate, cells tended to accumulate on the walls.

We had to adjust the number of cells seeded for each material to ensure the targeted seeding density remained consistent. Even when using the same 3 mm puncher to open the central chamber of the SBC and PDMS chips, the diameters of the holes obtained are not the same (**Figure SI.2**). This is a consequence of the elongation at break of the SBC (720 %) compared to the PDMS (76 %) one.[27,34]

As the diameters are different, the seeding area is different for both materials. We have a surface area of 7.1 mm^2 for SBC devices and 3.14 mm^2 for PDMS ones. However, only the open top parts are different in size, the central chamber is still 4 mm in diameter for both materials, which explains why there are fewer cells per mm^2 in the PDMS devices than in the SBC devices.

The consistently high viability (>80%) across conditions indicates that the cells generally survive well under all tested conditions, which is critical for biological relevance and assay reliability. The axonal growth rate in the chips is comparable to that of the control, indicating that the presence of microchannels has no effect on axonal growth. It is also similar to that observed in the literature, with a rate of around 400µm/day.[38] The lower cell density in the chips compared to well plates may reflect differences in culture environment, such as nutrient availability or surface interactions, which can influence cell proliferation behavior. The SBC material exhibits denser cell growth at DIV3 and DIV7 in comparison to the PDMS, suggesting that it may offer a better support for cell proliferation. The fact that the reuse of SBC material does not affect viability is encouraging for reproducibility and material stability. In case of in vitro preclinical study, the viability remains relatively high for all three conditions and networks neuron networks develop normally. Further phenotyping would be required to assess advanced structural features such as myelination (Ki67 proliferation marker, c-fos stress marker, MBP and MPZ myelin markers).

2.4. SBC chips can be cleaned and re-used up to 3 times

A rapid, simple and reproducible protocol was developed to clean and reuse the chip **(Figure 4A)**. We validated the regeneration of the chip using immunofluorescence, profilometry and electron microscopy. We validated the compatibility of re-used chips using axonal growth assays. The process was completed in less than 3 min per device and required only milliQ water, soap, ethanol 70 % and a toothbrush. Chips were sterilized again by UV-sterilization prior to culture. DRGs were grown up to one month in reused chips. It was confirmed that there was no noticeable difference in the surface of the SBC device before and after cleaning. Epifluorescence and SEM images were taken before use, after use and after the cleaning **(Figure 4B)**. Due to the sensitivity of the sTPE to electron beam, cracks appeared during SEM imaging. Using these two microscopy techniques, we confirmed that all the cellular debris present after culture had been removed by the cleaning protocol. After the third cleaning, it was observed that the axons were unable to enter the microchannels **(Figure 4C)**, suggesting that they were obstructed at the entrance. This finding was confirmed by optical profilometry measurement **(Figure 4D)**, which revealed that the microchannels were clogged. The clogging can be readily observed with a brightfield microscope (**Figure SI.9**) and is therefore easily detected. Consequently, each chip can be used up to 3 times before exhibiting irreversible deformation and becoming inoper-

able. The SBC material also has intrinsic advantages for cell culture compared to the PDMS in our context: the hydrophilization of SBC remains steady, allowing longer storage and reduced risk of cells detachment. The tendency of PDMS to leach and absorb other material can also result in issues when used in conjunction with other materials, particularly 3D printed materials or hydrogels.[39] The use of SBC materials would facilitate the production of composite devices for more complex applications.

2.5. The reversible bonding of the SBC provides direct access to the cells

The reversible bonding properties and detachment of the SBC microfluidic chips also allowed direct access to the cells (**Movie SI.2**). Immunostaining of the cells was performed after the detachment of the device without damaging the cells **(Figure 5A)**. We can clearly observe axons and nuclei of Schwann cells and fibroblasts that had grown and migrated inside the microchannels. NFH is an anti-neurofilaments-heavy chain while SMI312 is staining the neurofilaments-medium chains (NFM) and NucRed the nuclei. Similar images were obtained on fixed cells by SEM after opening of the chips **(Figure 5B)**. The cells were not damaged by the detachment or the drying process required prior to metallization. The reversible bonding properties also allowed direct access to the cells, which could then be scraped in order to realize WB and RT-qPCR (see **Figure 5C-D**). WB was performed after 11 days of culture by scraping DRGs either from a 4-well plate or from a 6-well plate after detaching the SBC chips. Four DRGs were pooled together, and the results showed no significant difference in the expression of SOX10, a protein expressed in Schwann cells, between the DRGs extracted from the control and the SBC devices (**Figure 5C**). RT-qPCR was conducted on a single DRG explant scraped from a well or a chip after 7 days of culture. The comparison of the amount of RNA recovered in control wells and that recovered in the reversibly bonded chips revealed that the SBC chips provide more material under equivalent culture conditions – see **Figure SI.14**. The expression levels of *Krox20*, *Mbp* and *Dhh*, which are markers of the Schwann cell lineage, were found to be comparable in the control and SBC chips (**Figure 5D**). Dhh and Mbp are expressed at the precursor level of Schwann whereas *Krox20* specifically confirms the transition to immature Schwan Cells (prior to myelinating Schwann Cells).[36]

Many reversible bonding strategies have recently been reported, for applications beyond cell culture.[30] Most of them require the intervention of an external help, a change in the design or the addition of an interlayer between the chip and the substrate. PDMS can be reversibly bonded in the absence of plasma treatment, but it is not easily reproducible and leakage occurs rapidly. In this case, axons can grow under the microchannels rather than inside them and the hydrophobicity of the PDMS, which is usually made hydrophilic by plasma bonding, prevents liquid from easily entering the device.[29] The self-adhesive properties of thermoplastic elastomers have also been used for reversible bonding[40] and their reported maximum working pressure without plasma bonding is 3.4 times higher than that of PDMS one.[41] Recent studies have shown that PDMS can exhibit reversible bonding properties after

plasma activation of the substrate, 0,1% APTES treatment and overnight bonding at 75°C[42]. However,

the SBC we use has self-adhesive properties that do not require any chemical treatments or design

changes. We have shown that it can be reused without impacting the cell culture and no leakage was

observed. Axons grew inside the microchannels and the SBC chips were hydrophilized by using plasma

treatment without impacting their reversible bonding. Cleaning the chips after use has been suggested

before,[43] but to our knowledge, has never been described. We proposed a fast and simple detailed

protocol for cleaning the devices after use, thus enabling them to be reused. However, the reusability

of the chips is limited in this particular context. After 3 uses, the microchannels were repeatedly

clogged, completely blocking the flow between compartments. We hypothesize that this could be due

to the uniform repetition of the different thermal cycles and plasma treatments, as the microchannels

clogging was identical and regularly distributed. For chips with thicker channels (in this case the

clogged channels were 2.8 μm thick), it is possible to exceed the $n = 3$ limit.

Axons are not only growing inside the central chamber, but also in the reservoirs (**Figure SI.12**).

When the chip is detached, these axons are torn at the same time. However, most of the axons present

in the microchannels remain attached. The samples can be immunostained after fixation. The resulting

images were more contrasted, with a more uniform background than with the devices, due to the

contribution of the autofluorescence of the polymer chip. This direct access also allowed to achieve

direct collection for biological analysis of proteins (western blot), which has already been performed

using a detachable substrate device,[14] or nucleic acids (RT-qPCR), which has been carried out directly

on the chip.[44] The detachment of the chips allowed easy scraping of the cells to collect most of the

biological material. WB was performed on 4 DRGs pooled, experiments have been conducted on 1, 4

and 8 DRGs in controls to assess the number of DRGs necessary to extract sufficient proteins (**Figure**

SI.13). The results showed that there was no significant difference by using 4 or 8 DRGs. However,

there is almost 40% of signal intensity difference between the 1 DRG and 4 DRGs experiments, sup-

porting our choice to pull 4 explants together. RT-qPCR was performed by pulling 1 or 2 DRGs explants

and similar results were obtained, confirming that enough RNA was collected by scrapping 1 DRG to

perform an experiment. Moreover, around $20\ ng/\mu L$ of RNA was extracted from 1 DRG which would

be sufficient to test approximatively 30 genes.

2.6. Comparison of carbon footprint of SBC and PDMS chips fabrication process

The energy and time needed to assemble an SBC and a PDMS device were calculated at each

stage of the fabrication process **(Figure 6A-B)**. The total energy required to fabricate an SBC chip was

$289.3\ kJ$, almost 2 times less than the molding step of a PDMS chip alone, which required $556.8\ kJ$.

PDMS chip fabrication took more time and consumed more supplies, resulting in more waste than an

SBC chip. Moreover, an SBC device could be cleaned and reused 2 times before disposal. The cleaning

step required no energy and took only 3 min, thereby reducing the time and energy needed for the

fabrication process, as well as the cost and kg of CO2 generated **(Figure 6C** and **Table SI.1**). Compared

to a PDMS chip, a reused SBC device took 4 times less energy and time to manufacture. The overall

price for a single PDMS chip is €2.83, while the price of an SBC chip is €3.10. However, the price of

the SBC device decreased to €1.72 when it was reused. To determine the carbon footprint generated

by the SBC raw material production, we assumed that it was the average of the carbon footprint of

polystyrene, polybutadiene and polyethylene production. The resulting value for one SBC chip is

$0.013 \, kg$ CO_2e while for a PDMS chip it is $0.025 \, kg$ CO_2e. When an SBC device is reused, as there is no

need for new SBC there is no more carbon footprint generated by the material fabrication. The overall

carbon footprint has been calculated by considering the mass of CO_2 equivalent generated per chip for

electricity consumption, polymer for chip and 6-well plate production, washing of the chip and disposal

of the wastes by incineration. Most of the carbon footprint was attributed to the disposal and washing

protocols and was similar for the three types of chips. However, the reused SBC devices produced

$0.05 \, kg$ CO_2e less than the PDMS ones because they consumed less electricity and didn't require the

production of polymer.

Time, energy and carbon footprint generated for SBC and re-used SBC chips fabrication were

lower than for PDMS ones fabrication. PDMS required more material and thus generated more waste

and cost. Thermoplastics were cheaper to produce[45] but because PDMS is produced in larger quanti-

ties, its final price is lower. It should be noted that the calculations are based on low carbon electricity,

coming mostly from nuclear power plants. Depending on the country of reference, electricity can affect

both the price and the carbon footprint. Costs and carbon footprint could be lowered for both SBC and

PDMS devices fabrication by reducing the amount of waste generated as they cause half of the mass

of CO_2e produced. The quantities of ethanol and milliQ water could be minimized, and increasing the

density of chips per mold would also reduce the amount of energy and time necessary to produce

them. However, the amount of wasted SBC is easier to reduce than for PDMS because the SBC can be

cut to the desired size whereas PDMS must be poured over the entire surface of the mold. When com-

paring all the environmental impacts from cradle to grave, normalized to those of PDMS, SBC and re-

used SBC chips appeared to be lower for all impacts, in particular for marine eutrophication and min-

eral resource scarcity (**Table SI.2**), confirming the interest of using SBC as an alternative to PDMS. In

our work, we choose to focus only on the manufacturing process for comparison purposes, we did not

take into account the labor cost and the equipment maintenance as they are similar, in our case, for

both materials. However, the total energy required to produce one chip can be considered negligible

when compared to the energy consumed in the lab or the energy required to produce and transport

the material.[46-48] If we considered the fabrication of 300 chips over a year, the carbon footprint asso-

ciated with chip fabrication corresponded to 1/60th of the mean carbon footprint of one researcher in

one year ($6t_{eq\ CO2}$).[46] In summary, the SBC already shows a very interesting reduction in time and cost

for the prototyping phase and could have a significant impact on the environmental impact of a prod-

uct on an industrial scale. This analysis underlines the importance of quantifying and optimizing the

environmental impact of microfluidic devices, especially in a field where there is an ongoing industrial

scale-up that should intensify with the growing rationalization of animal models.

3. Conclusion

We introduced a detachable, reusable, easy to produce and equivalent in cell culture perfor-

mance SBC device for an original application to DRGs culture in the context of peripheral nervous sys-

tem study. We proposed a new design adapted to DRGs explants and their radial growth with 6 pe-

ripheral compartments. We estimated the shear stress in the chip using simulations and particle veli-

cometry and experimentally confirmed its ability to perform axonal growth and viability assays of a

murine peripheral nervous system model. Based on the above biological assays, the PDMS devices,

used as a control, showed equivalent performance to the SBC devices. The demonstration of growth

and maintenance of a primary co-culture of nerves, which are particularly sensitive to stress, in an SBC

chip paves the way for tissue diversification and species growth in SBCs for the neurofluidic commu-

nity, but more generally for the microphysiological systems community. The reversible bonding of the

chips has been exploited both for direct access to different contact imaging microscopy and biological

analysis techniques such as SEM, WB and RT-qPCR. The possibility to recycle our chips led us to de-

velop an original workflow to evaluate the resources (time, energy, financial costs and CO2) involved

in the production and recycling of the chip, which could be used by the microfluidic community in

general to initiate a deeper rethinking. Switching to a reusable SBC chip allowed a significant reduction

in all these resources, more than 4 times in time and energy compared to PDMS, contributing to more

sustainable research. The carbon footprint assessment methodology can be reused for other devices.

In the field of the microphysiological systems, the paradigm to move away from PDMS toward soft

thermoplastics makes it possible to reduce the amount of resources used and to overcome the usual

limitations for cell culture. This could help minimize the environmental impact of a rapidly growing

industry. It also contributes directly to efforts in microfluidics to accelerate the clinical translation of

therapeutics for neuropathologies.[49,50] From an animal ethics perspective, the development of alter-

native *in vitro* models has the potential to significantly reduce the animal use, in alignment with the

4Rs commitment. In the case of DRGs, the number of embryos in a pregnant mouse is typically be-

tween five and seven, with an average of 40 DRGs per embryo. This yields a potential 250 experiments

to be conducted from a single mouse, depositing one dorsal root ganglion per chip. This approach

allows for the testing of up to 1,500 conditions using the proposed design, rendering it highly valuable

for drug screening and mechanistic investigation studies. Finally, the demonstration of viable DRG cul-

ture on our chip paves the way toward myelinating coculture in the PNS, which would provide 2D

myelin models for neuropharmacological explorations. This could be used to study of the processes of

myelination, demyelination, and remyelination, but also to select *in vitro* drugs that could be used for

regenerative treatments by stimulating the production of new myelin.

4. Experimental Section

4.1. Chip design and fabrication

a) Molds fabrication

The photomask designs were drawn using CleWin 5.2.4 version and printed on a SodaLime substrate

with a resolution of 128k dpi (JD Photo Data, UK). A first layer of 2.8 μm thick microchannels was

structured with SU-8 2002 (Chimietech, France) on a 4-inch diameter silicon wafer $1\ mm$ thick using

soft lithography. This was followed by the addition of a second layer of 100 μm thick chambers made

with SU-8 2050 (Chimietech, France). The Epoxym Kit (EdenTech, France) was used to create a negative

replica in $1\!:10$ Sylgard 184 PDMS (Neyco, France), followed by an epoxy positive replica of the SU-8

mold with Gallon KIT Conapoxy FR-1080 (Ellsworth Adhesives, USA).

b) Thermomolding and assembly of SBC chips

The microfluidic chips were embossed from styrene block copolymer (SBC) foils (EdenTech, France) at

$160\ °C$ for $3\ min$ ($0.07 - 0.08\ MPa$) using the Sublym hot press machine (EdenTech, France) and the

previously fabricated epoxy mold. The central chamber was punched with a $3\ mm$ punch to obtain an

open top device. A second layer of SBC embossed on a flat epoxy mold was added to each chip with a

$6\ mm$ diameter reservoir for the central chamber. The outer chambers were punched simultaneously

in the patterned layer and the reservoir layer using a $4\ mm$ puncher. Finally, each chip was die-cut

with a $26\ mm$ puncher. The two-layer devices were then placed in a 6-well plate (VWR, USA) for hy-

drophilization by plasma treatment for $10\ min$ in a plasma cleaner/sterilizer (Harrick Scientific Prod-

ucts, USA). They were baked at $80\ °C$ for $2\ h$ to increase the bonding strength.

c) Fabrication and assembly of PDMS chips

Polydimethylsiloxane (PDMS) chips and reservoirs were respectively molded with 1:10 Sylgard 184

from the SU-8 mold and a basic silicon wafer, and baked at $80\ °C$ for $2\ hours$. The patterned layer and

the reservoir layer were punched with the same punchers used for the SBC chips and both were plasma

treated for $10\ min$ prior to assembly. 6-well plates were pre-treated with $1\ \%$ (3-aminopropyl)trieth-

oxysilane (APTES, Sigma-Aldrich, Germany) in milliQ water. Finally, the devices were treated with

plasma again for $10\ min$ and were bonded in the 6-well plates.

d) Sterilization and coating of the chip

The same protocol was used on the SBC and PDMS chips. The plates containing the devices were placed

in a UV/Ozone ProCleaner™ Plus (BioForce Nanosciences, USA) for $10\ min$ for sterilization. The chips

were then rinsed with EtOH 70 % and three times with Dulbecco's phosphate buffered saline 1X (D-

PBS 1X, Gibco, USA) before being incubated with 5 % Poly-L-lysine (Sigma-Aldrich, Germany) in a so-

lution of boric acid (Sigma-Aldrich, Germany) and sodium hydroxide for $30\ min.$ at 37°C. After washes

with Neurobasal medium (Gibco, USA), they were coated with a solution of $130\ \mu g.ml-1$ rat tail

collagen I (Clinisciences, France) in $17.5 mM$ acetic acid for 1 h at room temperature. Finally, the chips

were rinsed again and placed at $37\ °C$ and 10 % CO_2 overnight before cell seeding. The same coating

procedure was followed for the 4-well and 96-well plates, which were used as controls.

e) Detachment and cleaning of the chip

The wells were filled with $1\ mL$ of D-PBS to immerge the chips before to progressively detach them

with a tweezer. After $10\ min$ of incubation at room temperature, the chips were carefully removed

from the wells. If cells observation was not needed, the devices were detached directly without the

incubation step. To clean them, they were first bathed in a solution of milliQ water and soap solution

(disinfectant Dermanios Scrub CG, Laboratoire Anios, France) and gently brushed with a toothbrush,

then rinsed successively with milliQ water, EtOH 70 % and with milliQ water again. Finally, they were

either dried in a laminar flow hood for $1\ h$ before storage or dried with compressed air and directly

reused following the usual protocol of sterilization and coating. Optical profilometry was performed

with a WykoNT9100 optical profilometer (Veeco, USA) on a new chip and a chip that had been used

up to 4 times and cleaned each time.

4.2 Dorsal Root Ganglia (DRG) Cell Culture

a) Cells harvesting, seeding and maintenance

Dorsal root ganglia (DRGs) were harvested from embryos at $E13.5$ surgically removed from pregnant

C57BL/6 J mice (Janvier, France) following a previously described protocol.[51] For explant culture, the

devices were filled with DRG plating media (DMEM high glucose (Gibco, USA), Glutamax 1X (Gibco,

USA), 10% Heat Inactivated Horse Serum (Gibco, USA), 2.5S NGF (R&D Systems, USA), Antibiotic/Anti-

mycotic 1X (Gibco, USA)). One DRG was placed in the central chamber of each microfluidic chip or in

the center of a well of a 4-well plate. For dissociated cell culture, the DRGs were trypsinized with a

solution of 0.25 Trypsin in Hanks' Balanced Salt Solution 1X (HBSS 1X, Gibco, USA) for = at $37\,°C$ and

$5\,\%$ CO_2. Trypsinization was stopped with L-15 media (Gibco, USA) containing 10% horse serum. DRGs

were then spun down at $1,500\,rpm$ for $5\,min$. The cells were resuspended in DRG plating medium

and seeded at a targeted density of $275\,000\,cells.cm^{-2}$ inside the central chambers or in a well from

a 96-well plate, as a control. The dissociated cells were seeded in a volume of 7 μL in the central cham-

ber and incubated $2\,h$ prior to fill the reservoir, to allow them to adhere to the surface of the culture

plate. DRGs were incubated at $37\,°C$ and $10\,\%$ CO_2. 18 to $20\,h$ after the seeding, the medium was

replaced with Neurobasal medium supplemented with Glutamax 1X, 2.5S NGF, B27 Supplement

(Gibco, USA) and Antibiotic/Antimycotic 1X. The medium was changed every $2\,days$. To prevent evap-

oration, $3\,mL$ of D-PBS was added in between the wells of the plates. All aspects of animal care and

animal experimentation were performed in accordance with the relevant guidelines and regulations

of INSERM and Université Paris Cité (authorization APAFIS#7405-2016092216181520).

b) Live and dead cell assays

Viability was assessed at day *in vitro* $DIV3$ and $DIV7$ using a LIVE/DEAD Viability/Cytotoxicity Assay Kit

(Invitrogen, USA). Cells were incubated for $30\,min$ at $37\,°C$ and $10\,\%$ CO_2 and rinsed with L15 medium

without red phenol (Gibco, USA). Cells were observed using the Cy5 and EGFP channels on a ZEISS

Axio Observer Z1 microscope (Zeiss, Germany) incubated at $37\,°C$ and $10\,\%$ CO_2 and the images were

processed using ImageJ 1.54j.[52] The data obtained were analyzed using R and tidyverse and the graphs

were plotted on GraphPad Prism 8 (GraphPad Software, USA). The full R markdown script is available

as supplementary information (*Script SI.1*). Sidak's multiple comparison tests were performed. The al-

pha value threshold was set at $5\,\%$ and the *P*-values are presented as follows: $* P < 0.05, ** P <$

$0.01, *** P < 0.001$.

c) Immunostaining

Cell cultures at $DIV3$ and $DIV7$ were fixed with 4% paraformaldehyde (PFA, Electron Microscopy Sci-

ences, USA) for $10\,min$ at room temperature. At $DIV7$, the SBC chips were detached to facilitate the

staining. The cells were then permeabilized (0.25 % Triton X100 (Sigma-Aldrich, Germany) and 0.1 %

Tween20 (Thermo Fischer Scientific, USA) in D-PBS) for $10\,min$. After washes with D-PBS and incuba-

tion for $45\,min$ in a blocking solution (0.5 % Triton X100, 0.1 % Tween20, 2 % bovine serum albumin

(BSA, Sigma-Aldrich, Germany), 3 % Mouse on Mouse blocking reagent (Bio-Techne, USA) and 5 %

Normal Donkey Serum (Sigma-Aldrich, Germany), the cells were incubated overnight at $4\,°C$ with the

primary antibodies: rabbit anti-NFH ($1\!:\!1000$, Merck Millipore Ref. AB1989, Germany) and mouse anti-

SMI312 ($1\!:\!250$, BioLegend Ref. AB_2566782, USA). The cultures were again rinsed with D-PBS and

incubated for 1h at room temperature with the secondary antibodies: donkey anti-rabbit Alexa Fluor™

488 ($1\!:\!1000$, Invitrogen Ref. A-21206, USA) and donkey anti-mouse Cyanine3 ($1\!:\!165$, Jackson Ref.

AB_2340813, USA). For nuclear staining, the devices were incubated $30\ min$ in a solution of NucRed

(Invitrogen, USA) in HBSS. To reduce the amount of antibody and staining required for chip detach-

ment, rings were 3D printed in polylactic acid and placed in each well to reduce the surface area (**Figure**

SI.1-2). Images were captured on a ZEISS Axio Observer Z1 microscope and processed on ImageJ using

the *NeuriteJ* plug-in*. The resulting data were processed in RStudio (Posit, USA) and graphs plotted on

GraphPad Prism 8. The full R markdown script is available as supplementary information (**Script SI.2**)

Sidak's multiple comparison tests were performed.

d) Western Blot

Western blots (WB) were performed on DRGs explant cultures at $DIV\,11$. The chips were detached,

and the proteins were extracted by scraping the DRGs in RIPA buffer ($50\ mM$ Tris Base, $150\ mM$ NaCl,

$1\ mM$ MgCl$_2$, 1 % NP-40 (Sigma-Aldrich, Germany), 0.1 % sodium dodecyl sulfate SDS (EU0660, Eu-

romedex, France), 0.5 % sodium deoxycholate (D6750, Sigma-Aldrich, Germany), Protease Inhibitor

Complete mini EDTA free (11836170001, Roche, Switzerland), Pyrophosphate ($10\ mM$, S9515, Sigma-

Aldrich, Germany), Phosphate Inhibitor Cocktail 2 ($10\ \mu L/ml$, P5726, Sigma-Aldrich, Germany), Phos-

phate Inhibitor Cocktail 3 ($10\ \mu L/ml$, P0044, Sigma-Aldrich, Germany) and sodium fluoride ($10\ mM$,

S7920, Sigma-Aldrich, Germany). The protein quantification was determined using a Bio-Rad DC Pro-

tein Assay (Bio-Rad, USA) with BSA as the standard. A total of $15\ \mu g$ of protein was loaded into a $4-$

20 % TGX 10-wells gel (Bio-Rad, USA) and the transfer step was performed using a Trans-Blot Turbo

transfer system (Bio-Rad, USA) on polyvinylidene difluoride membranes (Bio-Rad, USA). Non-specific

binding sites were blocked with blocking solution (5 % BSA in Tris Buffered Saline (TBS, Euromedex,

France)) and then incubated with primary antibodies rabbit anti-Sox10 ($1\!:\!1000$, ab155279, Abcam,

UK) and rabbit anti-Actin ($1\!:\!2\,000$, ab8227, Abcam, UK), followed by a goat anti-rabbit Horseradish

Peroxidase (HRP) coupled secondary antibody ($1\!:\!20\,000$, 111-035-144, Jackson IR, UK). Finally, spe-

cific bands were detected with the Pierce®ECL 2 Western Blotting substrate kit (RPN2209, Thermo

Fischer Scientific, USA), using the ImageQuant LAS 4000 ECL imaging system (GE Healthcare, USA). The

images were analyzed using the gel tool analyzer of ImageJ (1.54g). The integrated densities of Sox10

were normalized to β-actin expression and plotted using GraphPad Prism 10. A t-test was performed

for statistical analysis.

e) RT-qPCR

509 RT-qPCR was performed on explants at $DIV\,7$. The chips were detached and the DRGs were scraped in

510 Trizol (15596018, Invitrogen, USA). The RNA was precipitated and resuspended in water prior to quan-

511 tification with a Nanodrop (Thermo Fischer Scientific, USA). The SuperScript III Reverse Transcriptase

512 (18080085, Invitrogen, USA) was used following the manufacturer's instructions to realize the reverse

transcriptase of $90\ ng$ of RNA. qPCR was performed on a CFX384 biorad qPCR machine ($15\ s$ of dena-turation at $95\ °C$, $30\ s$ of elongation at $60\ °C - 40$ times) by using Sybr Green Rox kit (AB-1162/B, Thermo Fischer Scientific, USA) containing $300\ nM$ of selected primers (**Table 1**). The quality of the qPCR was tested by checking the dissociation curve. Each qPCR reaction was performed in triplicates. Relative expression of target genes was normalized to Ppia and Rpl13a mRNA levels and calculated using the ΔΔCt. Results are expressed as fold changes with respect to the controls and the data were plotted using GraphPad Prism 10.

Gene	Sequence 3'-> 5'	Sequence 5'->3'
Ppia	GGCAAATGCTGGACCAAAC	CATTCCTGGACCCAAAACG
Rpl13a	TACGCTGTGAAGGCATCAAC	TTGGTATTCATCCGCTTCCG
Krox20	TGCACCTAGAAACCAGACCTTC	TGCCCGCACTCACAATATTG
Mbp	ACTCACACACGAGAACTACCC	GGTGTTCGAGGTGTCACAATG
Dhh	ATCCACGTATCGGTCAAAGC	AGTCACCACGATGTAGTTCCC
B-actin	ATGGTGGGAATGGGTCAGAAG	TGCCATGTTCAATGGGGTAC
Pgk1	ACGGTGTTGCCAAAATGTCG	TTGGAACAGCAGCCTTGATC
Gapdh	GTGGACCTCATGGCCTACAT	TGTGAGGGAGATGCTCAGTG

Table 1: qPCR primers used in this study

f)   Scanning Electron Microscopy

After $21\ days$ of culture, the cells were rinsed with D-PBS and fixed in $4\ \%$ PFA. The bottom of each well was then laser-cut using a Universal Laser Systems VLS 4.60 (Universal Laser Systems, Inc., USA) to obtain circular slides suitable for scanning electron microscope. The chips were detached according to the previous protocol and the biological samples were dried using an automated critical point dryer Leica EM CPD300 (Leica Microsystems, France). The samples were then metallized with platinum in a Cressington 208HR metallizer (Cressington Scientific Instruments, UK) and observed in a Zeiss Gemini SEM 360 scanning electron microscope (Zeiss, Germany).

g)   Finite Element Method (FEM)

COMSOL Multiphysics software was used to perform diffusion-convection simulations on the micro-fluidic device. The *creeping flow* and *transport of diluted species* modules were implemented for this study. In the diffusion-convection experiment, a pressure gradient of 5 and $20\ Pa$ between the inlet and the outlet was used for the convective flow, and an inflow of 0.5 mM of water (diffusion coefficient $D = 10^{-9}\ m^2.s^{-1}$) was used for diffusion, by keeping the inlet and outlet the same (transport) or

opposite (isolation). The system comprises two identical blocks of size $1 \times 1 \times 0.1\ mm^3$, merged

with a smaller block of size $0.5 \times 1 \times 0.028\ mm^3$. This geometry represents the junction between

the central and peripheral chambers, which is of particular relevance for the study. Approximate solu-

tions of the following equations were numerically calculated by the FEM software:

$\rho \frac{\partial u}{\partial t} = \nabla \cdot [-pI + \mu(\nabla u + (\nabla u)^T)] + F$ (1)

$\rho \nabla \cdot u = 0$ (2)

$\frac{\partial c_i}{\partial t} + \nabla \cdot J_i + u \cdot \nabla c_i = R_i$ (3)

$J_i = -D_i \nabla c_i$ (4)

Equation (1) is the Navier-Stokes equation, (2) is the incompressibility of the flow, (3) is the diffusion-

convection equation, and equation (4) is Fick's law of diffusion with ρ the fluid density, u the fluid

velocity, p the fluid pressure, I the identity matrix, T the temperature, μ the fluid dynamic viscosity, F

the external forces applied to the fluid, and where, for species i, c_i is the concentration, J_i is the molar

flux, R_i is a net volumetric source for c and D_i is the diffusion coefficient.

h) Particle image velocimetry

The devices were first coated with 5% BSA in D-PBS1X for 10 min to reduce collision impact with the

walls. FluoSpheres^{TM} amine (0.2 μm diameter) (Invitrogen, USA) were diluted 1/40000 in the same

solution. To obtain a flow of $25\ Pa$, 60 μL of the microbead solution was injected into the central

chamber and 5 μL of the solvent solution was injected into the peripheral chambers. D-PBS was added

in between the wells to prevent evaporation and the plate was sealed with parafilm. Microbeads were

observed using the Cy5 channel on a ZEISS Axio Observer Z1 microscope. Images were analyzed directly

using the Zeiss Zen software and data were plotted using GraphPad Prism 8.

i) Time, cost, carbon footprint and energy consumption calculations

The estimated times, costs, carbon footprint and energy consumption were calculated for one chip.

Power consumption was measured using a wattmeter Primera-Line PM 231 E (Lextronic, France). The

measurements were converted to energy by multiplying the power by the time of use of each piece of

equipment. Whenever an equipment was used for several devices at the same time, the amount of

energy and time were divided by the number of chips to estimate the amount required for one device.

Material prices were based on supplier prices. Electricity prices were based on the French electricity

price in June 2024 (€0.2516/kWh). The carbon footprint was calculated based on the direct emissions

of products manufactured in Europe, using the Ecoinvent 3.5 database, required for the fabrication of

one chip. PDMS production was assimilated to silicone using the Ecoinvent process 'product produc-tion | silicone product | APOS, S RER', while SBC manufacture was modeled as an average of 25 % polyethylene, 25 % polybutadiene and 50 % polystyrene using the processes 'polyethylene produc-tion, high density, granulate | polyethylene, high density, granulate | APOS, S, RER', 'polybutadiene production | polybutadiene | APOS, S, RER' and 'polystyrene production, general purpose | polysty-rene, general purpose | APOS, S, RER'. In addition, the impact calculations included electricity con-sumption, 6-well plate production, washing protocol and waste disposal by incineration. Impacts were calculated using the ReCiPe 2016 Midpoint (H) method.

Data availability

The data for this article plots can be found on https://github.com/HugoSalmon/25Moreau.

Supporting Information

Supporting Information is available from the Wiley Online Library.

Author Contributions

H.S., S.B., S.M., A.S. and A.E-T conceptualized the study. H.S., A.S. and C.D-B. provided the resources. S.M., H.S, A.S. and A.E-T made data curation. S.M., A.S. and A.E-T realized the formal analysis. H.S. and S.B. supervised the study. H.S. acquired the fundings. H.S., T.EJ., A.S. and S.B. validated the study. In-vestigation was conducted by H.S., S.M., R.F-B., A.S. and C.D-B.. S.M. wrote the original draft and H.S., T.EJ., A.S., C.D-B. and S.B. review and edited the paper. H.S., S.B., S.M., T.EJ., R.F-B., A.S. and C.D-B. designed the methodology of the study. H.S. and S.B. handled the project administration.

Acknowledgements

S.B. and H.S. contributed equally to this work. This research was funded by the French National Re-search Agency (ANR-23-CE19-0007-01) and the Université Paris Cité via the Initiative d'Excellence Idex Emergence (IDXD7-MOCHI). The motorized microscope and the motorized macroscope were funded by DIM BIOCONVS Région Ile de France (HCS-Mochi and MisoSoup projects, respectively). RFB was funded by DIM ELICIT Région Ile de France (FOMO project). We thank L. Réa from UMR 7057 MSC for prototyping the microscope adaptor.

The parts were fabricated at the mechanical workshop core facility of BioMedTech Facilities Université Paris Cité (https://biomedicale.u-paris.fr/biomedtech-facilities/) INSERM US36 | CNRS UAR2009 by T. Bastien and V. Pierrat.. The authors thank the staff of UMR 7162 MPQ clean room, the IPGG platform from PSL university for the easy access to the platform and ITODYS platform from Université Paris Cité

for the SEM images. Finally, the authors thank V. Sundaram and C. Massaad for the discussions regarding the peripheral nerve modeling, J-M Di Meglio and Dimitri Ayollo for discussions on microscopy. The authors thank the Mathematics and IT department of Université Paris Cité for the access to https://pleiade.mi.parisdescartes.fr/. The large language model "athene-v2" was used for improving the English of the manuscript.

Conflict of Interest

The authors declare no conflict of interest.

Received:

Revised:

Published online:

List of abbreviations

4R: Reduction, Replacement, Refinement and Responsibility

CNS: Central Nervous System

DIV: Days *in vitro*

DRG: Dorsal Root Ganglia

PDMS: PolyDiMethylSiloxane

PNS: Peripheral Nervous System

RT-qPCR: Reverse Transcription quantitative Polymerase Chain Reaction

SBC: Styrenic Block Copolymer

SEM: Scanning Electron Microscope

sTPE: soft Thermoplastic Elastomer

WB: Western Blot

References

G. S. Offeddu, Y. Shin and R. D. Kamm, *Curr. Opin. Biomed. Eng.*, 2020, **13**, 119–126.

A. D. Jadhav, L. Wei and P. Shi, *Curr. Neuropharmacol.*, 2016, **14**, 72–86.

F. M. Pramotton, S. Spitz and R. D. Kamm, *Adv. Sci.*, 2024, **11**, 2403892.

T. Osaki, Y. Shin, V. Sivathanu, M. Campisi and R. D. Kamm, *Adv. Healthc. Mater.*, 2018, **7**, 1700489.

R. B. Campenot, *Proc. Natl. Acad. Sci.*, 1977, **74**, 4516–4519.

A. M. Taylor, M. Blurton-Jones, S. W. Rhee, D. H. Cribbs, C. W. Cotman and N. L. Jeon, *Nat. Methods*, 2005, **2**, 599–605.

A. J. Samson, G. Robertson, M. Zagnoni and C. N. Connolly, *Sci. Rep.*, 2016, **6**, 33746.

J. Courte, R. Renault, A. Jan, J.-L. Viovy, J.-M. Peyrin and C. Villard, in *Methods in Cell Biology*, eds. D. A. Fletcher, J. Doh and M. Piel, Academic Press, 2018, vol. 148, pp. 71–95.

A. D. Sharma, L. McCoy, Elizabeth Jacobs, E. R. Jacobs, H. E. Willey, J. Q. Behn, H. P. T. Nguyen, Brad Bolon, B. Bolon, J. L. Curley and M. J. Moore, *Sci. Rep.*, 2019, **9**, 8921–8921.

J. Park, H. Koito, J. Li and A. Han, *Biomed. Microdevices*, 2009, **11**, 1145–1153.

J. Park, H. Koito, J. Li and A. Han, *Lab. Chip*, 2012, **12**, 3296–3304.

B. Luo, A. P. Tiwari, N. Chen, S. Ramakrishna and I. H. Yang, *ACS Appl. Bio Mater.*, 2021, **4**, 8424–8432.

M. Shi, D. Majumdar, Y. Gao, B. M. Brewer, C. R. Goodwin, J. A. McLean, D. Li and D. J. Webb, *Lab. Chip*, 2013, **13**, 3008–3021.

S. Hyung, S.-R. Lee, J. Kim, Y. Kim, S. Kim, H. N. Kim and N. L. Jeon, *Sci. Adv.*, 2021, **7**, eabd9749.

S. Hyung, B. Yoon Lee, J.-C. Park, J. Kim, E.-M. Hur and J.-K. Francis Suh, *Sci. Rep.*, 2015, **5**, 15122.

R. M. Huval, O. H. Miller, J. L. Curley, Yuwei Fan, Y. Fan, B. J. Hall and M. J. Moore, *Lab. Chip*, 2015, **15**, 2221–2232.

I. H. Yang, Devin S. Gary, D. S. Gary, M. Malone, M. Malone, S. Dria, T. Houdayer, Thierry Houdayer, Visar Belegu, V. Belegu, J. W. McDonald and N. V. Thakor, *Neuromolecular Med.*, 2012, **14**, 112–118.

M. Malone, D. Gary, I. H. Yang, A. Miglioretti, T. Houdayer, N. Thakor and J. McDonald, *Glia*, 2013, **61**, 843–854.

H. U. Lee, A. Blasiak, D. R. Agrawal, D. T. B. Loong, N. V. Thakor, A. H. All, J. S. Ho and I. H. Yang, *PLOS ONE*, 2017, **12**, e0179642.

M. Ristola, L. Sukki, M. M. Azevedo, A. I. Seixas, J. B. Relvas, S. Narkilahti and P. Kallio, *J. Micromechanics Microengineering*, 2019, **29**, 065009.

N. Vysokov, S. B. McMahon and R. Raouf, *Sci. Rep.*, 2019, **9**, 12915.

S. M. Caparaso, A. L. Redwine and R. A. Wachs, *J. Biomed. Mater. Res. B Appl. Biomater.*, 2023, **111**, 1903–1920.

L. Kramer, *ALTEX*, DOI:10.14573/altex.2001181.

P. Khoshakhlagh, A. Sivakumar, L. A. Pace, D. W. Sazer and M. J. Moore, *J. Neural Eng.*, 2018, **15**, 064001.

C. Mutschler, S. V. Fazal, N. Schumacher, A. Loreto, M. P. Coleman and P. Arthur-Farraj, *J. Cell Sci.*, 2023, **136**, jcs261557.

J. W. Park, H. J. Kim, J. H. Byun, H. R. Ryu and N. L. Jeon, *Biotechnol. J.*, 2009, **4**, 1573–1577.

E. Berthier, E. W. K. Young and D. Beebe, *Lab. Chip*, 2012, **12**, 1224–1237.

J. Lachaux, C. Alcaine, B. Gomez-Escoda, C. M. Perrault, D. O. Duplan, P.-Y. J. Wu, I. Ochoa, L. Fernández, O. Mercier, D. Coudreuse and E. Roy, *Lab. Chip*, 2017, **17**, 2581.

J. Harris, H. Lee, B. Vahidi, C. Tu, D. Cribbs, C. Cotman and N. L. Jeon, *JoVE J. Vis. Exp.*, 2007, e410.

Y. Zhang, K. Sun, Y. Xie, K. Liang, J. Zhang and Y. Fan, *Rev. Sci. Instrum.*, 2023, **94**, 061501.

H. Salmon, M. R. Rasouli, N. Distasio and M. Tabrizian, *Eng. Rep.*, 2021, **3**, e12361.

M. D. Paepe, L. Jeanneau, J. Mariette, O. Aumont and A. Estevez-Torres, *PLOS Sustain. Transform.*, 2024, **3**, e0000116.

33 B. G. C. Maisonneuve, A. Batut, C. Varela, J. Vieira, M. Gleyzes, J. Rontard, F. Larramendy and T.
Honegger, *Neurite growth kinetics regulation through hydrostatic pressure in a novel triangle-*
shaped neurofluidic system, Bioarxiv, 2021.
34 H. Salmon, M. R. Rasouli, N. Distasio and M. Tabrizian, *Eng. Rep.*, **n/a**, e12361.
35 S. Hosmane, I. H. Yang, A. Ruffin, N. Thakor and A. Venkatesan, *Lab. Chip*, 2010, **10**, 741–747.
36 V. K. Sundaram, T. El Jalkh, R. Barakat, C. J. I. Fernandez, C. Massaad and J. Grenier, *Front. Cell.*
Neurosci., 2021, **15**, 590537.
37 M. Liu, W. Song, P. Li, Y. Huang, X. Gong, G. Zhou, X. Jia, L. Zheng and Y. Fan, *PLOS ONE*, 2013, **8**,
e63473.
38 A. M. Conti, S. Brimijoin, L. J. Miller and A. J. Windebank, *Neurobiol. Dis.*, 2004, **15**, 106–114.
39 M. de Almeida Monteiro Melo Ferraz, J. B. Nagashima, B. Venzac, S. Le Gac and N. Songsasen, *Sci.*
Rep., 2020, **10**, 994.
40 D. Brassard, L. Clime, K. Li, M. Geissler, C. Miville-Godin, E. Roy and T. Veres, *Lab. Chip*, 2011, **11**,
4099–4107.
41 B.-U. Moon, K. Morton, K. Li, C. Miville-Godin and T. Veres, *Processes*, 2021, **9**, 54.
42 X. Feng, Z. Wu, L. K. W. Cheng, Y. Xiang, R. Sugimura, X. Lin and A. R. Wu, *Lab. Chip*, 2024, **24**,
3546–3555.
43 M. Samandari, L. Rafiee, F. Alipanah, A. Sanati-Nezhad and S. H. Javanmard, *Sci. Rep.*, 2021, **11**,
10310.
44 X. M. Spijkers, S. Pasteuning-Vuhman, J. C. Dorleijn, P. Vulto, N. R. Wevers and R. J. Pasterkamp,
Sci. Rep., 2021, **11**, 2080.
45 E. Roy, M. Geissler, J.-C. Galas and T. Veres, *Microfluid. Nanofluidics*, 2011, **11**, 235–244.
46 A. Estevez-Torres, F. Gauffre, G. Gouget, C. Grazon and P. Loubet, *ChemRxiv*, 2023, preprint, DOI:
10.26434/chemrxiv-2023-6tt1w.
47 A.-L. Ligozat, C. Brun, B. Demirdjian, G. Gouget, E. Jardé, A. Mialon, A.-S. Mouronval, L. Pagani and
L. Vieu, *bioRxiv*, 2024, preprint, DOI: 10.1101/2024.03.11.584380.
48 O. Ragueneau and A. Sabbagh, *One Earth*, 2024, **7**, 747–750.
49 J. Kajtez, S. Buchmann, S. Vasudevan, M. Birtele, S. Rocchetti, C. J. Pless, A. Heiskanen, R. A.
Barker, A. Martínez-Serrano, M. Parmar, J. U. Lind and J. Emnéus, *Adv. Sci.*, 2020, **7**, 2001150.
50 S. Bang, S. Na, J. M. Jang, J. Kim and N. L. Jeon, *Adv. Healthc. Mater.*, 2016, **5**, 159–166.
51 C. Taveggia and A. Bolino, in *Myelin: Methods and Protocols*, ed. A. Woodhoo, Springer, New York,
NY, 2018, pp. 115–129.
52 J. Schindelin, I. Arganda-Carreras, E. Frise, V. Kaynig, M. Longair, T. Pietzsch, S. Preibisch, C.
Rueden, S. Saalfeld, B. Schmid, J.-Y. Tinevez, D. J. White, V. Hartenstein, K. Eliceiri, P. Tomancak
and A. Cardona, *Nat. Methods*, 2012, **9**, 676–682.
709
710

Figure 1: Fabrication and design of the thermoplastic chip. A. Fabrication process of the two-layer microfluidic chip in styrenic bloc copolymers (SBC). B. Scheme of the design of the chip. Somas are compartmentalized in the central chamber, while axons grow through the 292 microchannels. C. Image of the device filled with food dyes. Scale bar = $1\ cm$.

718
719
Figure 2: Estimation of the shear stress inside microchannels. A. Shear stress field induced by a 30Pa flow over
a microchannel cross-section calculated by Finite Element Methods (FEM), with associated analytical plots of the
velocity (in black) and shear stress along the y-axis (dashed red line) and along the z-axis (dashed blue line). **B.**
Particle image velocimetry in the styrenic bloc copolymers (SBC) chip of 200 nm fluorescent polystyrene particles.
Scale bar $= 100\ \mu m$ **C.** Evolution of the flow average speed inside the microchannels (blue curve), fitted expo-
nential model for the average flow speed (dotted blue line), and associated shear stress (red curve) over time for
initial pressure conditions of $25\ Pa$.

727
Figure 3: Comparison of viability and axonal growth of Dorsal Root Ganglia (DRG) explants within the chips A.
Viability test for a control well from a 96-well plate and a central chamber of a Styrenic Block Copolymer (SBC)
and a PolyDiMethylSiloxane (PDMS) chip at $DIV3$ and $DIV7$. The images show all cells (white) and dead cells
(magenta). Miniature tiles (bottom left of each image), scale bars $= 1.2\ mm$, and its representative frame cor-
responding to the region in the yellow square, scale bars $= 150\ \mu m$. **B.** The number of living and dead cells per
mm² inside the control wells, PDMS chips, SBC chips and reused SBC chips at $DIV3$ and $DIV7$. DRG $n = 6 - 24$,
embryos $e = 6 - 12$. Results are represented as the mean ± SEM. Two-way ANOVA were performed. The alpha
value threshold was set at 5% and the P-values are represented as follows: $* p < 0.05$, $** p < 0.01$, $*** p <$
0.001. **C.** Tiles of DRG explants inside the controls wells, PDMS chips, SBC chips and reused SBC chips at $DIV3$
and $DIV7$. Nuclei (blue), neurofilaments H (green), SMI312 (red), scale bars $= 500\ \mu m$ **D.** Axonal length inside
the control wells, PDMS chips, SBC chips and reused SBC chips at $DIV3$ and $DIV7$. No data is available for PDMS
chips at DIV7, as it was not possible to measure the axonal length. $n = 6 - 15$, $e = 6 - 12$. Results are repre-
sented as the mean ± SEM.
741
742
743

744
Figure 4: Reusability of Styrenic Block Copolymer (SBC) chips A. Cleaning process of the two-layer microfluidic
chip in SBC. **B.** Hoechst staining (scale bar $= 100 \ \mu m$) and SEM (scale bar $= 10 \ \mu m$) imaging on a new, a used
and a cleaned SBC chip. **C.** Axonal length of Dorsal Root Ganglia (DRGs) at DIV7 depending on the number of uses
of the SBC chip. DRG $n = 3 - 6$, embryos $e = 3 - 6$. The results are presented as the mean±SEM. A Tukey's
multiple comparison test was conducted. The alpha value threshold was set at $5 \ \%$, and the *P*-values are repre-
sented as follows: $* \ p < 0.05, ** \ p < 0.01, *** \ p < 0.001$. **D.** Optical profilometry of the microchannels of a
new SBC chip and a SBC chip used four times.
752

Figure 5: Direct accessibility to cells A. Immunostaining of the neurofilaments of a Dorsal Root Ganglia (DRG) at $DIV7$ after opening of the chip. Nuclei (blue), neurofilaments H (green), SMI312 (red). **B.** SEM image of the neurofilaments of a DRG at $DIV21$. Scale bars represent 20 µm **C.** Western blot analysis of 4 explants DRGs at DIV11 in control wells from a 96-well plate and in Styrenic Block Copolymer (SBC) opened chips and corresponding graph representing Sox10 expression. Actin was used as a loading control. Results represent the mean ± SEM of three independent experiments ($n = 5 - 8$, embryo $e = 3$). A t-test was performed for statistical analysis (ns=non-significant). **D.** RT-qPCR analysis of *Krox20*, *Mbp* and *Dhh* genes of one DRG at $DIV7$ in controls and in SBC chips. Results represent the mean ± SEM of three independent experiments ($n = 6 - 10$, embryo $e \geq 5$). A Mann-Whitney-test was performed for statistical analysis (ns=non-significant).

Figure 6: Assessment of the resources used and CO2 emissions generated to produce a Styrenic Block Copoly-

mer (SBC) chip and a PolyDiMethylSiloxane **(PDMS) chip.** Energy consumption of the different steps of a fabri-
cation process for **A.** a SBC-based chip and **B.** PDMS-based chip. **C.** Comparison of the time, energy, cost and
carbon footprint associated to the fabrication of a PDMS chip, a SBC chip and a reused SBC chip. Note that we
did not take into account the labor cost and the equipment maintenance, as these are similar in our context for
both materials.
769

Reversible and reusable compartmentalized microfluidic chip for coculture of dorsal root ganglion neurons

Solène Moreau[1,2], Raul Flores-Berdines[1,2], Anne Simon[1], Tatiana El Jalkh[3], Guillaume Taret[1], Anna Fomina[1], Céline Dargenet-Becker[1], André Estevez-Torres[4], Sophie Bernard[1,*], and Hugo Salmon[1,2,*]

[1]Université Paris Cité, Inserm, HEALTHFEX, F-75006 Paris, France, 45, rue des Saints Pères, 75006 Paris, France
[2]Université Paris Cité, CNRS, Inserm, NABI, F-75006 Paris, France, 45, rue des Saints Pères, 75006 Paris, France
[3]IMRB INSERM U955, Université Paris-Est, 51, avenue du Maréchal de Lattre de Tassigny, 94010 Créteil, France
[4]LASIRE, UMR CNRS 8516, Université de Lille, Avenue Paul Langevin, 59650 Villeneuve-d'Ascq, France

Contributed equally
E-mail: sophie.bernard@u-paris.fr; hugo.salmon@u-paris.fr

Contents

1 Code

R markdown code for automated data treatment can be found here.

- **Script SI.1**: R markdown script for live-dead data treatments.

- **Script SI.2**: R markdown script for axonal growth data treatments.

The github depot also contains a data set to run the markdown code on example datasets. Script SI.1 requires 'LiveDead_Noise_NucGreen.csv", "LiveDead_Noise_NucRed.csv", "LiveDead_NucGreen.csv" and "LiveDead_NucRed.csv". Script SI.2 requires "AxGrowth.csv".

2   Profilometry

We controlled our mold and replica using a mechanical profilometer - see **Figure SI.1**. The SU-8 on silicon primary mold and the epoxy mold are the most rigid and offer the best contrast. They confirm the thickness of the microchannels is $2.70 - 2.80 \mu m$. It is in good agreement with the PDMS and SBC replicas which are $2.65 - 2.78 \mu m$ thick. The parabolic baseline of the PDMS profile is most likely due to the curvature of the 4 inch PDMS replica ($S = 157.0 mm^2$) which have thicker edges. The SBC does not display deformation because the replicas are smaller ($S = 12.3 mm^2$). The apparent roughness of the SBC hills might be due to the adhesion forces of the polymer (SBC is a pressure sensitive adhesive) which might generate instability. This was not observed when doing optical profilometry (**Figure 4D**).

Figure SI.1: Mechanical profilometry of microchannels of the SU-8, PDMS and epoxy molds and SBC chips. The irregularities observed on the PDMS and SBC profilometers are due to the elasticity of the materials. The height of the microchannels is similar for each replicate.

The punching quality varies greatly between a handpunch on PDMS and a manual cutting press on a flexdym reservoir layer- see **Figure SI.2**.

Figure SI.2: Differences in hole size after punching an SBC and a PDMS chip with a 3 mm puncher. Scale bar represents 500 µm.

3 Volume effect on pressure

Figure SI.3: **Model of the flow generated inside a microfluidic chip.** **(A)** CAO perspective view of the central chamber (left) and a peripheral chamber (right) connected by one microchannel (in red). **(B)** Schematic illustration of the flow between two chambers using one-cylinder approximation. **(C)** Photography of microfluidic chip (left) and schematic illustration of the model used (right). The chambers are shown in purple, and the microchannels in green. **(D)** Evolution of liquid volume and height inside central chamber and peripheral chamber with respective initial volumes of 60 µL and 5 µL.

Evaluating the evolution of the hydrostatic pressure-induced flow Our mathematical model provides an estimation of the flow time inside a microfluidic device. To model the pressure-gradient induced flow between chambers, we simplified the overall geometry of the problem (**Figure SI.3.A**, **3.B**). The hydrodynamic resistance of the equivalent microchannel was

calculated using electrical circuit analogy of n microchannels of resistance R_h in parallel. Using the conservation of flow rate inside the system, we obtained the following simple differential equation governing the volume of fluid inside a given chamber over time :

$$\frac{dV}{dt} = -\frac{V}{\tau} + \frac{V_{eq}}{\tau}$$

For one cylindrical central chamber of section S_0 and N peripheral chambers of same section S_1, the time constant of our model is :

$$\tau = \frac{R_h S_0 S_1}{\rho g n N \left(S_0 + S_1 N \right)}$$

From this formula, we conclude that the time scale depends on the geometry of the device and the density of the fluid, but not on the initial volume conditions. We calculated the numerical solution using water parameters for the fluid, $n = 27$, $N = 6$, $S_0 = 2.1 \times 10^{-5}$ m^2 and $S_1 = 1.3 \times 10^{-5}$ m^2 (**Figure SI 3.C, SI 3.D**). For these values, $\tau \approx 16$h, meaning it takes each chamber about 50 hours to reach 95% of its final volume.

The following values were obtained for a pressure gradient of 30Pa, which is the theoretical maximum pressure that can be applied inside the studied microfluidic device given the finite volume of the reservoirs (**Figure SI.4**). The maximum shear stress inside the cross section is 0.8 dyn/cm^2. This is lower than the cell viability limit for cortical neurons (5 dyn/cm^2) which was measured for a 24h exposition time [1], meaning the fluid flow has no degrading effect on the studied axons.

Figure SI.4: 2D graph of the pressure within the chip depending on the volume of fluid in the central chamber and in the peripheral chambers.

Cylindrical approximation According to Pascal's law, a pressure-gradient force is applied when two compartments of the same liquid have different altitudes. To obtain the volume as a

linear function of the altitude ($V = hS$) and thus facilitate calculations, we used a one-cylinder approximation for the chambers. In reality, the microfabrication process requires that the chambers be composed of three juxtaposed cylinders. The simplified chambers were calculated by conserving the same height and volume than those of the original ones.

Equivalent circuit theory   Microchannels act as hydraulic resistors. The hydrodynamic resistance of a microchannel can be obtained thanks to a well-known approximation for rectangular cross-section channels [2] :

$$R_h = \frac{12\mu L}{1 - 0,63\frac{h}{w}}\frac{1}{h^3 w}$$

Given the small dimensions $h = 2.8$ µm, $w = 10$ µm and $L = 500$ µm, the obtained value $R_h = 3.3 \times 10^{16}$ Pa.s.m^{-3} is very high compared to that of the chambers (about 10^{11} higher). Considering this the only source of flow resistance is therefore a reasonable assumption. Using the conservation of flow rate in the parallel coupling of n microchannels, the inverse-additive law gives us the total resistance as $R_{tot} = R_h/n$ (**Figure SI.5**). This approximation is true in the case of small Reynolds numbers, which is verified inside our microfluidic device due to the small length and slow speed rate : $Re = \frac{\rho v L}{\eta} \approx 10^{-3}$.

Figure SI.5:   Equivalent circuit theory for two chambers

System equations   The definition of the flow rate Q between the central chamber (volume V_0) and one of the N identical peripheral chambers (volume V_1) can be written as :

$$-\frac{dV_0}{dt} = NQ = Nn\frac{\Delta P}{R_h} = \frac{Nn\rho g}{R_h}\left(\frac{V_0}{S_0} - \frac{V_1}{S_1}\right) \tag{1}$$

In addition, the total volume of fluid is constant over time :

$$V_{0,i} + NV_{1,i} = V_{tot} = V_0 + NV_1 \tag{2}$$

Injecting (2) into (1) gives us the desired differential equation on the volume of either the central or one of the peripheral chambers. This equation was numerically solved using the solve_ivp

function from the python library `scipy.integrate` using Runge-Kutta method. The average flow speed inside the microchannels can be deduced since $v = Q/hw$.

4 Image analysis workflow

The overall study relies on a defined workflow to avoid inconstitency and user dependent analysis. It also aims at quantifying exhaustively in a high content manner the overall information available on the chip regarding viability **Figure SI.6** and axonal growth **Figure SI.7**.

Figure SI.6: Image treatment for total live-dead analysis. i. Workflow: The entire chip is scanned as a single tile. The background is removed and the particles are first threshold and counted on the NucRed channel. The white intensity is then compared between the NucGreen and the NucRed channels. From this data, a dotplot ii. and a histogram iii. are plotted with the intensity of NucRed compared to the intensity of NucGreen. The number of living and dead cells is calculated based on the results with a count of living cells ranging from 0 to $10000UI$ for NucGreen intensity.

As observed in the **Figure SI.9**, the flower design displays a gradient in each arm that is visible when doing an immunostaining. Any treatment to the axons displays this gradient distribution.

The recycling process after several use demonstrate occlusion next to the central part specifically. Though we did not perform any composition analysis of these occlusion, one hypothesis is that the thermal history of the polymer (long term incubation, cleaning and reconditioning 3 times) lead to a deformation of the smallest patterns.

Figure SI.7: Image treatment for axonal growth analysis. The image is first converted to an 8-bit format prior to being processed with Neurite-J plugin. The plugin counts the number of intersections with axons at 25 µm intervals. The maximum distance is fixed when the number of intersections is below 10.

Figure SI.8: Schematic of the concentration gradient (C) close to the microchannels (right) the image was captured using an epifluorescence microscope and illustrate the difficulty of staining the axons. NFH (green) and SMI312 (red). Scale bar represents $100\mu m$.

5 Manufacturing processes estimation

In **Table SI.1**, we detail the requirements of the SBC and PDMS manufacturing processes.

In **Table SI.2**, we compare the environmental impacts of the products, from production to disposal, normalized against the impacts of PDMS. We compare it in a histogram - see **Figure SI.10**, 0.5 meaning the impact is equivalent for both polymer. A value > 0.5 indicates SBC is more impactful than PDMS and reciprocally.

Figure SI.9: Brightfield image of the microchannels after four uses of the chip, indicating that they are no longer linked to the central chamber. Scale bar represents $100\mu m$.

Figure SI.10: Ratio percentage of impact of SBC compared to PDMS.

6 Immunostaining volume optimization

Movie SI.1 shows the chip detachment with a fixed DRG at DIV15. Once detached, a green printed part is added to each well of the plates to minimize the volue used for immunostaining - see **Figure SI.11**.

The detachment of the chip tears the axons growing on top of the central reservoir - see **Figure SI.12**.

Figure SI.11: Picture of rings 3D printed and placed inside a 6-well plate to reduce the volume. Scale bar = $1cm$.

Figure SI.12: Scheme of the axons growing on top of the reservoir layer and the tearing of these axons when detaching the chip. B. Image captured using an epifluorescence microscope of the axons on top of the reservoir. NFH (green) and nuclei (NucRed). Scale bar represents $200\mu m$.

7 Protein and RNA extraction

The extraction of the proteins were attempted varying the number of DRG pulled after extraction from 4-well plates. The advantage of pulling 8 DRG is a reduced standard deviation of the sample, though the $DRG = 1$ condition displays a reasonable one. The proportion of SOX10 protein detected seems also reasonaby higher between 1 and 8, indicating that pulling strategies can be relevant for rare protein samples - see **Figure SI13**.

Figure SI.13: Comparison of Sox10 expression normalized by actin in 1, 4 and 8 DRGs cultivated for 11 days in 4-well plates. β-Actin was used as a loading control. Results represent the mean $\pm$ SEM of three independent experiments ($n = 5 - 9$, embryos $e = 3$). A one-way ANOVA following by a Tukey's multiple comparisons test was performed for statistical analysis. The alpha value threshold was set at 5% and the p-values are represented as follows: ns = non-significant, $*p < 0.05$, $**p < 0.01$.

The comparison of the amount of RNA recovered in control against reversibly bonded chips revealed that the SBC chips provide more material in equivalent culture conditions – see **Figure SI14**. The quantification was performed on a Nanodrop (Thermo Fischer Scientific, USA).

Figure SI.14: Comparison of Sox10 expression normalized by actin in 1, 4 and 8 DRGs cultivated for 11 days in 4-well plates. β-Actin was used as a loading control. Results represent the mean $\pm$ SEM of three independent experiments ($n = 5 - 9$, embryos $e = 3$). A one-way ANOVA following by a Tukey's multiple comparisons test was performed for statistical analysis. The alpha value threshold was set at 5% and the p-values are represented as follows: ns = non-significant, *$p < 0.05$, **$p < 0.01$.

References

[1] Liu, M, Song, W, Li, P, Huang, Y, Gong, X, Zhou, G, Jia, X, Zheng, L, & Fan, Y. (2013) Galanin Protects against Nerve Injury after Shear Stress in Primary Cultured Rat Cortical Neurons. *PLOS ONE* **8**, e63473. Publisher: Public Library of Science.

[2] Panigrahi, P. K. (2015) *Transport phenomena in microfluidic systems*. (Wiley, Singapore).