1
2

Blood Vessels Bioengineered from Induced Pluripotent Stem Cell Derived Mesenchymal Stem Cells and Functional Scaffolds

Short Title: Bioengineered Blood Vessels Derived from hiPSCs

Luis Larrea Murillo [a], Zhongda Chen [b], Jun Song [b], Adam Mitchel [a], Jiashen Li [b], Yi Li [b], Tao Wang [a]

[a] School of Biological Sciences, Faculty of Biology, Medicine and Health, The University of Manchester M13, 9PL, United Kingdom

[b] Department of Materials, School of Natural Sciences, The University of Manchester, Manchester M13 9PL, United Kingdom

Corresponding author: tao.wang@manchester.ac.uk

Word Count: 7379 (excluding abstract and figure ledges)
(Maximum 7,500 words references included)

Abstract

Background:

The development of small-diameter vascular grafts poses a significant challenge in tissue engineering. Despite advances in biofabrication, current vessel mimics lack remodelling and regenerative capabilities. Here, we sought to fabricate patient-specific bioengineered vessels using induced pluripotent stem cells (iPSCs) and functionalised biodegradable scaffolds to produce patient-specific bioengineered vessels.

Methods:

Human iPSCs were differentiated into mesenchymal stem cells (iMSCs) using SB431542, a TGF-β1 pathway inhibitor. iMSCs were further differentiated into vascular smooth muscle cells (VSMCs) with PDGF-BB and TGF-β1. Human bone marrow derived mesenchymal stem cells (hBM-MSC) from a commercial source were used for optimising differentiation protocols and quality control of iMSCs. Electrospun poly-L-lactide (PLLA) scaffolds coated with silk fibroin were developed for cell adhesion and growth. Both hBM-MSCs and iMSCs were seeded on these scaffolds for in-scaffold differentiation into VSMCs. The cell-laden scaffolds were rolled into tubular structures to scaffolds with ~3 mm inner diameters and ~20 mm in length.

Results:

Over 34-36 days, iPSCs were differentiated into cells with fibroblast-like morphology (iMSCs) expressing MSC markers CD73, CD90, and CD105, confirmed via immunofluorescence and flow cytometry. Thereafter, hBM-MSCs and iMSCs were successfully differentiating into VSMCs by supplementing media with PDGF-BB and TGF-β1 media over 9 days. Differentiated VSMCs expressed of *α-SMA*, *CNN1*, *SM22*, and *MYH-11*. Silk fibroin-coated PLLA scaffolds enhanced MSC adhesion and proliferation compared to uncoated scaffolds. The engineered tubular grafts displayed VSMC markers and mechanical properties akin to autologous coronary artery bypass grafting (CABG) grafts.

Conclusion:

This study developed a versatile method to fabricate tissue-engineered blood vessels using stem cells and silk fibroin-coated scaffolds. The resulting grafts exhibited tunica media-like structures and mechanical properties comparable to autografts used in CABG, showing strong potential for clinical application.

Highlights

- Human iPSCs were successfully differentiated into mesenchymal stem cells (iMSCs) over 34–36 days, expressing key markers like CD73, CD90, and CD105. The iMSCs were further differentiated into vascular smooth muscle cells (VSMCs) using PDGF-BB and TGF-β1 within 9 days, demonstrating efficient differentiation protocols.
- The study presents a versatile method to fabricate tissue-engineered vascular grafts (TEVGs) using induced pluripotent stem cell-derived mesenchymal stem cells (iMSCs) and silk fibroin-coated electrospun scaffolds. This approach enables the creation of patient-specific vascular grafts with tunica media-like structures and mechanical properties comparable to autologous grafts used in coronary artery bypass grafting (CABG).
- This method demonstrates potential as an "off-the-shelf" solution due to the immunoregulatory properties of MSCs, enabling allogenic applications. Alternatively, it offers patient-specific customisation using iPSCs, highlighting its adaptability and promising clinical applicability in addressing the shortage of viable autologous vascular grafts

Introduction

Cardiovascular disease (CVD) remains the leading global cause of death, with coronary artery disease (CAD) responsible for more than 9 million fatalities each year [1]. Revascularisation techniques have significantly improved the prognosis and quality of life for patients with vascular conditions, particularly in coronary artery disease (CAD) [2]. Restoring coronary blood flow is essential for survival, and while percutaneous coronary intervention (PCI) has become more common as a less invasive non-surgical procedures, coronary artery bypass grafting (CABG) remains the preferred treatment for patients with extensive atherosclerosis, complex lesions, or comorbidities like diabetes [3,4]. CABG requires vascular grafts to bypass occluded coronary arteries, with saphenous veins being the most commonly used autologous vessels [5]. However, these grafts have a high failure rate, with 40-50% of grafts failing within 10 years due to intimal hyperplasia and associated complications. In contrast, arterial grafts such as the internal mammary artery and radial artery have better long-term patency (failure rates ≤10%), but require more invasive harvesting techniques and are prone to vasospasm [6,7]. Additionally, many patients may not have suitable autologous vessels due to factors like frailty or advanced age, leaving up to 30% of CABG-eligible patients without an appropriate graft. This highlights the need for alternative graft materials [8].

Over the last two decades, tissue engineering has advanced significantly in developing
vascular grafts that mimic the mechanical and physiological properties of native vessels. [9,10].
To address the shortage of autologous grafts, acellular synthetic materials, such as Dacron
and expanded polytetrafluoroethylene (ePTFE), have been clinically applied as alternatives,
yet have fallen short in patency compared to autologous grafts, particularly in small-diameter
applications [11]. Small-diameter (<6 mm) tissue-engineered vascular grafts (TEVGs) have
demonstrated success as arteriovenous shunts in hemodialysis patients, but their application
in coronary artery bypass remains limited [12]. Decellularized allogenic saphenous veins
repopulated with autologous endothelial cells (ECs) have reached the clinical setting for CAD
treatment, but with a low degree of success [13].

An essential aspect of vascular tissue engineering is the scaffold, which provides structural
support for growing tissue. Electrospinning, a low-cost and versatile method, has been used
to create fibrous meshes from synthetic polymers like poly(L-lactic acid) (PLLA) or
polycaprolactone (PCL) and has demonstrated to be a good candidate for fabricating scaffolds
for vascular grafts [14,15]. While several electrospun TEVGs have shown promising results *in
vivo*, none have reached the clinic to treat CAD. This has been attributed to elastic modulus
differences observed in electrospun TEVGs which greatly exceed those observed in native
vessels and have been identified as a significant cause of graft failure [16,17]. To improve
biocompatibility, electrospun scaffolds have been coated with natural biomaterials such as silk
fibroin. Silk fibroin coatings have shown to not only improve cell function due to the cell
adhesive motifs it possesses but degradation can be easily tunned for optimal tissue growth
and formation [18]. Furthermore, modifications to surface topography have also shown to further
enhance biocompatibility of these scaffolds as porous/rougher surfaces can improve cell
attachment and migration of various vascular cell types [19,20].

Another key aspect in vascular tissue engineering lies in sourcing appropriate cells for graft
construction. Currently, most TEVGs that have reached clinical trials have been derived from
autologous primary vascular cells such as fibroblasts, vascular smooth muscle cells (VSMCs),
and ECs. However, these primary cells have limited regenerative capacity due to the donor's
age, with poor proliferative ability and a high risk of senescence. Moreover, harvesting and
culturing these cells is both time-consuming and expensive [16,21]. These challenges have driven
interest in stem cell technologies, particularly the use of induced pluripotent stem cells (iPSCs)
and mesenchymal stem cells (MSCs). IPSCs offer an attractive solution due to their self-
renewal capacity and pluripotency, akin to embryonic stem cells (ESCs) but without associated
ethical concerns [21,22]. MSCs, although more limited in differentiation potential, exhibit excellent
genomic stability and have well-established clinical safety. Additionally, MSCs have

immunosuppressive properties, making them suitable for both autologous and allogenic therapies [22,23].

In this study, we present a viable method to fabricate tissue engineered blood vessels by seeding human iPSCs (hiPSCs)-derived MSCs (iMSCs) onto silk fibroin fuctionalised biodegradable electrospun scaffolds and allowing in-situ differentiation of VSMCs. The fabricated vessels exhibited tunica media-like features and mechanical properties similar to autologous CABG grafts. Their simplicity suggests potential as an "off-the-shelf" solution.

Materials and Methods

Culture of iPSCs

E1PL1 (donor SAMEA2536417), SERU7 (donor SAMEA3965165) from HipSci (Wellcome Genome Campus, UK) and SW171A (provided by the Kimber Lab, University of Manchester, UK) wildtype hiPSC cell-lines were maintained in Essential 8™ Medium (Gibco, A1517001, USA) and seeded on Matrigel coated 6-well plates. Once thawed, they were passaged when 70-80% confluency was reached. Cells were passaged at least two times by dissociating with 0.5 µM EDTA (ThermoFisher, 15575020, USA) to remove any differentiated cells present after thaw prior to conducting characterisation and differentiation experiments. All cell-lines were maintained at 37°C with 5% CO2 incubation conditions.

Culture of hBM-MSCs

Human bone marrow derived mesenchymal stem cells (hBM-MSC) (C-12974) harvested from normal human bone marrow from individual donors were cultured with Mesenchymal Stem Cell Growth Medium 2 (C-28009) purchased from PromoCell (Germany). Culture medium was changed every 2-3 days and passaged once until ~90% confluence was reached for further expansion or experimental use.

Generation of MSCs from iPSCs

Generation of hiPSC derived MSCs (iMSCs) were obtained via a monolayer-directed approach by Chen et al. [24] with significant modifications. Briefly, hiPSCs were seeded on Matrigel (Corning, 354230, USA) coated plates at a 25,000 cells/cm^2 density and cultured with a 10uM ROCK inhibitor supplemented Essential 8™ Medium for the first 16-24 hrs. Thereafter, ROCK inhibitor was removed from the Essential 8™ Medium and maintained for another 48-72 hrs until a ~70-80% confluence was reached. To initiate differentiation (Day 0) medium was changed to a Dulbecco's Modified Eagle's medium F-12 (DMEM F-12) by Gibco (11320-074,

USA) supplemented with 1mM L-Glutamine, 1% (x1) MEM Non-essential Amino Acid Solution, 1% Penicillin-Streptomycin, 10μM, SB431542 in DMSO and 20% knockout serum replacement (KOSR). After 10 days, cells were disassociated with TrypLE Express (Gibco, 12604021, USA), resuspended on Mesenchymal Stem Cell Growth Medium 2 (Promocell, C-28009, Heidelberg, Germany) and seeded on uncoated plates at a density of 80,000 cells/cm^2. When cells reached 80-90% confluence, they were first passaged at a density of 120,000 cells per cm^2. Thereafter, cells were passaged at 1:3 or 1:2 ratios for the remaining of the culture period. At days 34-36, iMSCs positive for common MSCs markers were generated and maintained with the Mesenchymal Stem Cell Growth Medium 2

Osteogenic differentiation of hBM-MSCs and iMSCs

HBM-MSCs and iMSCs maintained in Mesenchymal Stem Cell Growth Medium 2 were dissociated with TrypLE Express once ~ 90% confluence and seeded on 10 μg/ml human fibronectin (Promocell, C-43050, Heidelberg, Germany) coated plates at a density of ~120,000 cells/well. When cells reached a 100% confluence, culture medium was changed to the Mesenchymal Stem Cell Osteogenic Differentiation Medium (C-28013) by PromoCell (Heidelberg, Germany) to induce osteogenic differentiation. Osteogenic differentiation medium over a 28-day differentiation period. At day 28, Cells were fixed and stained with Alizarin Red S to detect extracellular calcium deposits and mineralisation in osteogenic differentiated cells.

Generation of VSMCs from hBM-MSCs and iMSCs

HBM-MSC derived VSMCs (hBM-MSC-VSMCs) and iMSC derived VSMCs (iMSC-VSMCs) were generated using the following protocol. HBM-MSCs or iMSCs resuspended on Mesenchymal Stem Cell Growth Medium 2 were seeded on plates at a density of ~300,000 cells/well. After allowing cells to attach overnight, Medium was changed to VSMC induction medium consisting of Dulbecco's Modified Eagle's medium (DMEM) (Sigma-Aldrich, D6429-500ML, United Kingdom), 10% fetal bovine serum (FBS) and 1% Penicillin-Streptomycin. Medium was further supplemented with Transforming growth factor beta 1 (TGF-β1) (HEK293 derived) and Platelet-derived growth factor (PDGF-BB) from PeproTech (Rocky Hill, United States) at a concentration of 2ng/ml each. Cells were cultured under the differentiation medium for 9 days with medium being changed every 2-3 days.

Immunocytochemistry

Cells were fixed with 4% paraformaldehyde (PFA) and permeabilised with 0.1% triton X-100 in PBS for detecting intracellular makers. Subsequently, cells were incubated with primary

antibodies overnight at 4ºC and secondary antibodies for 1 hr at room temperature thereafter.
To determine successful differentiation of iMSCs, cells were stained with common MSC
membrane markers CD44, CD73, CD90 and CD105. Generated VSMCs from either hBM-
MSC or iMSCs were stained with intracellular markers α-SMA, CNN1, SM22 to determine its
successful differentiation. Furthermore, hBM-MSC-VSMCs and iMSCs-VSMCs we stained
with CACNA1C to assess their contractile function. Finally, all cells were counterstained with
DAPI (Sigma-Aldrich, D9542, USA) to stain the nucleus and cells assessed for morphology
had actin filaments stained with Phalloidin-iFluor 488 (Abcam, ab176753, UK).

Flow Cytometry

To prepare samples for flow cytometry, cells were disassociated with acutase (Thermofisher,
00-4555, USA) and suspensions were first stained with fixable viability dye eFluor 780
(eBioscience, 65-0865-14, USA) for 30 minutes at 4°C. Thereafter, cells were fixed with 4%
PFA and stained with antibody against cell surface protein markers in accordance with
manufacturers recommendations. For intracellular markers, permiabilisation was conducted
with 2% FBS in PBS and 0.1% Triton X-100 for 20 minutes before incubation with antibodies.
Compensations were performed using unstained cells, viability dye stained cells and
UltraComp ebeads by eBioscience (San Diego, CA, USA) conjugated with each antibody.
Compensation and flow cytometry experiments and analysis was performed on the
LSRFortessa SORP cytometer (BD Biosciences, USA). Cells were stained for pluripotent
markers SSEA4, TRA-1-60 and Oct 3/4. Differentiating cells were also stained for positive
MSC makers CD73, CD90 and CD105 as well as negative MSC markers HLA-DR, CD34 and
CD14 to determine their multipotency

Quantitative Real-Time Reverse Transcription-Polymerase Chain Reaction

Quantitative Reverse Transcription Polymerase Chain Reaction (qRT-PCR) was performed
on hiPSC to MSC and iMSC/hBM-MSC to VSMC differentiating cells at different time-points.
Total RNA extraction was performed using the RNeasy mini kit by Qiagen (Venlo,
Netherlands) according to the manufacturer's instructions. Reverse transcription for cDNA
synthesis was performed using the High-Capacity RNA-to-cDNA™ Kit (4387406,
Thermofisher, USA). The cDNA was added to a master mix composed of PowerUp™ SYBR™,
primers for specific genes assessed and DEPC-Treated water. Mix was aliquoted (20 µl) into
each well of a 96-well plate and transferred onto the StepOne™ Real-Time PCR System to
run a Comparative Ct (ΔΔCt) experiment. House-keeping gene Glyceraldehyde 3-phosphate
dehydrogenase (GAPDH) and genes of interest were evaluated using the $2^{-\Delta\Delta CT}$ to analyse
fold gene expression changes amongst the samples.

Fabrication of electrospun scaffolds and functionalisation

Electrospun scaffolds were fabricated using a protocol previously described [19]. Briefly, 2 wt%
Poly-L-lactide acid (PLLA, PL 65) in Dichloromethane (DCM):N,N-Dimethylformamide (DMF)
(19:1) solutions were loaded onto Luer plastic syringes with 21-gauge needles. Loaded
syringes were placed on a nanofibre electrospinning unit (TL-Pro, Tongli Tech, China) and
PLLA solutions were expelled at a controller flow rate of 5 mL/h. Fibres were spun using a
voltage supply of 23 kV and at a walking distance of 30 cm from the collectors. After 4 hrs,
Pristine fibrous scaffolds were removed from the collector and immersed in ≥ 99.8% acetone
for 5 min to produce porous fibre scaffolds. Scaffolds were then further functionalised by
covering the surface with a 1 wt% silk fibroin solution diluted in ethanol (EtOH) and dH_20 (Silk
fibroin:EtOH / 2:1). Scaffolds were left to air dry after adding the silk fibroin solutions and via
cross-linking inactions between EtOH and silk fibroin, a solid silk fibroin coat was left on the
surface of fibrous scaffolds.

Seeding hBM-MSC and iMSCs on Electrospun Scaffolds

Pre-seeding, scaffolds were pre-conditioned by incubating the with 10% FBS supplemented
DMEM by incubating at standard cell culture conditions of 37°C 5% CO^2 for 4-6 hrs to aid cell
attachment. Thereafter, when hBM-MSC and iMSCs reached ~90% confluence, cells were re-
suspended and seeded on ~15 mm diameter scaffolds at a density of 150,000 cells/scaffold.
Cells were cultured with Mesenchymal Stem Cell Growth Medium 2 during the first 24 hours
of attachment and subsequently switched to the VSMC differentiation medium detailed above
for the next 9 days. Thereafter, medium was switched to a 10% FBS supplemented DMEM
maintenance medium for the Remainer of the time depending on the experiment with medium
changed every 2-3 days.

Alama Blue Assay

Cells seeded on ~15 mm diameter scaffolds were used to assess the biocompatibility of
pristine, porous and silk fibroin coated scaffolds. The metabolic activity of cells laden on
scaffolds was measured using an AlamarBlue™ (Invitrogen, DAL1025, USA) assay.
Absorbance of AlamarBlue™ at 570 nm, using 600 nm as a reference wavelength (normalized
to the 600 nm value) was measured using the FLUOstar® Omega microplate reader by BMG
LABTECH (Offenburg, Germany). Reduction of AlamarBlue™ was calculated to determine
metabolic activity of cells. To assess proliferation, cells were disassociated with TrypLE
Express, resuspended and stained with Trypan Blue Solution, 0.4% (Gibco, 15250061, USA).
Cell susoensions were then placed on Cell Counting Chamber Slides and inserted on a

279 Countess II FL Automated Cell Counter (Invitrogen, USA) to measure changes in cell numbers
280 throughput culture. AlamarBlue™ and cell count measurements were taken at different time-
281 points (Day 1, 4, 7 and 10) to assess metabolic activity and proliferation of cell-laden scaffolds.
282

Fabrication of Tissue Engineered Blood Vessels

HBM-MSC and iMSCs were seeded on 2.5 x 5.5 cm silk fibroin coated sheets using the same
cell seeding protocol detailed above at a density of 150,000/cm^2. After the 9-day VSMC
induction period, hBM-MSC-VSMCs and iMSCs-VSMCs were cultured with the 10% FBS
supplemented DMEM maintenance medium for 21 days (3 weeks total). After 3 weeks, the
cell-laden sheets were wrapped around a 3 mm diameter stainless steel rod and from a tubular
structure. For the tube to maintain its shape, an alginate sealing was applied using a modified
rapid-casting method published by Ghanizadeh Tabriz et al. [25]. Briefly, the cell-laden sheets
were wrapped around the rod were dipped in 4% (w/v) alginate solutions for 3 sec.
Subsequently, alginate coated constructs were dipped in a 100mM CaCl2 cross-linking
solution for 3 min. Thereafter, the construct with the solidified alginate seal was removed from
the rod leaving a hollow space in the middle of the cylindrical structure with similar dimensions
to that of a small-diameter artery. Constructs using silk fibroin coated sheets without cells were
also produced via the same method for mechanical analysis comparisons.
297

Mechanical Properties Assessment of Tubular Constructs

To assess the mechanical properties of Tubular constructs, a tensile test experiment was
conducted. The mechanical tensile test was performed on constructs approximately 20 mm in
length, 3 mm in inner diameter and 4 mm of outer diameter with an Instron 3344 (MA, USA)
static tensile test equipped. Tubes were connected distally and proximally onto plugs with flat
ends that were fixed on the upper and lower grips of the instrument. The Instron instrument
ran with a 10 Newton cell load and a deforming rate of 5 mm/min to extend tube constructs
until fracture. Data collected to measure the ultimate tensile strength (UTS) was used calculate
the theoretical burst pressure (P) using the following equation where (T) represents the UTS,
(do) the outer diameter and (di) the inner diameter of constructs.

308
$$P = \frac{T(do^2 - di^2)}{di^2(1 + \frac{do^2}{di^2})}$$

Statistical Analysis

311 Statistical analysis was conducted and values were analysed using the GraphPad Prism
312 software and Microsoft Excel 2016. One-way ANOVA test and a Tukey's multiple comparisons

313   test was applied to assess for statistical differences in experiments containing more than two
314   groups. When p-values were <0.05, differences were considered significant. Data is presented
315   as mean ± standard mean error (SEM).

Results

Producing iMSCs from iPSCs

To take the advantages of iPSCs that are able to provide inexhaustible source of autologous
MSCs that have great regeneration potential and are easy to culture and differentiate into
vascular cell types, we first established a robust protocol to produce MSCs from iPSCs. This
protocol was based on Chen et al. [24] with modifications as illustrated in **Figure 1A**. Prior to
differentiation, the pluripotency of hiPSCs was re-confirmed for hiPSC markers including
SOX2, SEEA4, Oct3/4 and TRA1-60 via immunofluorescence staining and flow cytometry
(**Figure S1A-B**). During differentiation, the expression of *NT5E* (CD73) and *ENG (*CD105*)* and
ENG (CD105) steadily increased during the 34 days of iMSC differentiation as determined by
RT-qPCR. By day 34, the expression of *NT5E* (CD73) and *ENG (CD105)* increased ~170-fold
and ~26-fold, respectively, compared to the start of hiPSC differentiation (day 0) (**Figure 1B**).
This was further validated by the flow cytometry data showing that the percentage of cells
positive for CD73 and CD105 increased from 12.7% and 0.25% on day 0 to 75.55% and
50.75% on day 36, respectively (**Figure C**). The MSC marker CD90, in the other hand, did not
increase further from the iPSCs during the differentiation (**Figure 1B and C**), however, the
percentage of iMSCs positive for CD90 were comparable to those observed in hBM-MSCs
(92.60%). The increase in MSC markers was also accompanied with a decrease in of
pluripotent factors SEEA4 and TRA-1-60 (**Figure S2**). Moreover, iMSCs lacked key MSC
negative marker CD34 and low levels for CD14 and HLA-DR, which were also similar to those
of hBM-MSCs (**Figure S3**). Lastly, differentiated iMSC were observed to display a spindle-
shaped and elongated morphology as well as positively exhibited MSC markers including
CD44, CD105, CD73 and CD90 by immunofluorescent staining. Morphology and positive
markers were comparable to those of hBM-MSCs (**Figure 2D**).

iMSCs were then functionally verified by their ability to differentiate into osteogenic cells, a
hallmark characteristic of the multipotency for MSCs. The iMSCs derived from 3 independent
iPSC lines proved to be able to undergo osteogenic differentiation as evidenced by Alizarin
Red S staining 28 days after differentiation (**Figure 2 a-i**), similarly to that of the parallel control
hBM-MSCs (**Figure 2 j-l**).

Differentiation of iMSC into VSMCs

To produce VSMCs from iMSCs (the iMSC-VSMCs), we optimised a protocol where TGF-β1 and PDGF-BB induced iMSCs to form VSMCs in nine days as illustrated in **Figure 3A**. The hBM-MSCs ran in parallel with the iMSCs as controls. During the differentiation, VSMC-specific maker genes including *ACTA2, CNN1, TAGLN* and *MYH11* were gradually increased and reached a highly significant level by day 6 (**Figure 3B**). On day 9, the expression of these marker genes increased by around 5 to 50-folds between the iMSC-VSMCs and hBM-MSC-VSMCs depending on specific gene, comparing to that of the MSCs on day 0 (**Figure 3B**). Immunofluorescent staining showed a homogenous population of cells positive for VSMC-specific makers α-SMA, calponin, and SM22α in both iMSC-VSMCs and hBM-MSC-VSMCs by day 9 as compared to the undifferentiated iMSCs and hBM-MSCs (day 0) (**Figure 3C**). Both iMSC-VSMCs and hBM-MSC-VSMCs were positive for the calcium channel, voltage-dependent, L type, alpha 1C subunit (Cav1.2) (**Figure 3C**) that is usually highly expressed in the contractile VSMCs. The expressions of most VSMC marker genes did not further increase after day 9 (**Figure 3B**), therefore, the cells were switched to the VSMC maintenance medium at this time point and the expressions of VSMC marker genes were maintained on day 12 (**Figure 3B**). As anticipated, the expression of the pluripotent markers *Oct 3/4* and *SOX2* in the iMSC-VSMCs was significantly downregulated when compared to the undifferentiated iPSCs (**Figure S4**).

VSMC Differentiation in Silk Fibroin Coated Porous Electrospun Vascular Scaffolds

We have previously reported the development of a silk fibroin coated highly porous electrospun poly(L-lactic acid) (PLLA) fibrous vascular scaffold that was compatible to grow rat aortic smooth muscle cells [19]. The production method and morphology changes throughout modifications cand be observed in (**Figure 4A, 4B**). Changes fibre topography and mechanical properties was also further analysed in this study (**Figure S5**). The scaffolds in this study were served for in-scaffold differentiation of iMSC-VSMCs to create cell laden TEVGs. To assess its suitability to manufacture TEVGs, we first assessed the biocompatibility of the scaffold to the iMSCs and hBM-MSCs, and particularly evaluated the effect of the silk fibroin coating on cell growth. After 10 days cell culture, the silk fibroin coated porous scaffold significantly favoured cell proliferation as shown by cell counting and the cellular metabolic activity as measured using alamar blue (**Figure 4C**) for both iMSCs and hBM-MSCs. Fluorescence staining with phalloidin showed that the iMSCs and hBM-MSCs growing in the silk fibroin coated porous scaffolds appeared to have better morphologies with a more spreading feature than the prestine and porous-only Scaffolds (**Figure 4D**). Thus, the silk fibroin coated porous electrospun scaffolds were chosen for fabricating the cell-laden TEVGs.

Prior to the production of cell-laden TEVGs, In-scaffold differentiation of iMSCs and hBM-
MSCs was carried out using the optimised method as mentioned above on 2.5 x 5.5 cm silk
fibroin coated electrospun sheets. After 9 days, cell attachment was first assessed via
phalloidin staining (**Figure 5A**) and differentiation of iMSC-VSMCs and hBM-MSC-VSMCs
was assessed thereafter by positive staining of α-SMA and calponin (**Figure 5B**).
Differentiated iMSC-VSMCs and hBM-MSC-VSMCs exhibited similar characteristic VSMC
markers to those differentiated in the conventional tissue culture conditions described above
(**Figure 3C**).

Production and Characterisation of Tissue Engineered Blood Vessels

The overall approach to produce tissue engineered blood vessels in our study is illustrated in
Figure 6A, where MSCs differentiated into VSMCs in a scaffold sheet that was then rolled into
a tubular structure with a desired diameter, which was sealed with alginate **(Figure 6A)**. Based
on the in-scaffold VSMC differentiation parameters optimised, the iMSCs and hBM-MSCs
were seeded on rectangular silk fibroin coated electrospun scaffold sheets (2.5 x 5.5 cm)
mentioned above and differentiated for 9 days, as previously detailed, and then switch to the
VSMC maintenance medium. Once maintenance media was added, VSMCs were further
expanded over a 3-week culture period. The VSMC-laden sheet scaffolds were rolled on a 3
mm diameter stainless steel rod to generate multiple tubular shaped vessel constructs. The
vessels were then dipped in a 3.5% alginate solution and cross-linked with calcium chloride to
seal the constructs and maintain a vessel-like shape. The vessel mimics measured ~3mm
inner diameters, 0.51 mm wall thickness and ~20 mm in length, similar to those of a coronary
artery of similar calibre (**Figure 6B**). Longitudinal cross-sections were made, and
immunofluorescence stained for VSMC markers. Images showed that both of the iMSC-
VSMCs and hBM-MSC-VSMCs maintained their VSMC phenotype in the maintenance
medium conditions as evident by the α-SMA and calponin positive cells observed across the
length of the tube constructs (**Figure 6C**).

The tissue engineered cell-laden vascular constructs were further assessed for their
mechanical characteristics. Measurement of stress and strain mechanical properties showed
that the hBM-MSC-VSMCs had a higher ultimate tensile stress (UTS) (0.655 ± 0.123 Mpa)
and burst pressure (1408 ± 265.400 mmHg) compared to those from without cells (UTS 0.397
± 0.098 Mpa, burst pressure 852.500 ± 211.800 mmHg) although no statistical differences
were observed (**Figure 6D, 6E**). However more pronounced differences were observed in
vessel mimics derived from iMSC-VSMCs with the UTS (1.017 ± 0.151 Mpa) and burst
pressure (2184 ± 325.300 mmHg) significantly higher than the cell-free grafts (**Figure 6D, 6E**).

Young's modulus and strain were also measured which were similar between scaffolds with

and without cells, although there is a trend of increase of the Young's modules for the cell-

laden grafts (**Figure 6F, 6G**). Overall, the mechanical properties of UST, burst pressure,

young's modules and strains of the tissue engineered grafts were all similar to autologous

vascular grafts used in CABG to treat CAD [10,26,27].

426　**Discussion**

In this study, we presented a new, rapid and simple method to fabricate tissue engineered

blood vessels. The method demonstrated its capability to fabricate small diameter tubular

constructs laden with in-scaffold production of VSMCs from iPSC-derived MSCs, and

possessing native like mechanical properties. Thus, this strategy provided a potential

approach to generate "off-the-shelf" TEVGs that are currently in urgent need due to scarcity

of autologous donor vessels and poor synthetic alternatives currently available for CABG [10].

Various electrospun strategies have been applied to fabricate TEVGs with promising results

in vivo including their performance in large animal models like sheep carotid arterial models

[17,28,29]. However, currently no electrospun TEVG has reached the clinic for CABG. The majority

of the TEVGs reported to date were either not cell-laden but relied on host-cell infiltration post-

implantation to remodel the grafts, or pre-seeded primary vascular cells during the fabrication

process prior to implantation [16,30]. This have been the approaches used for all TEVGs that

have reached the clinic at present to treat occluded small-diameter vessels [12,13,31,32]. However,

these methods are confronted with significant downsides. Most noticeably, the use of primary

cells requires an autologous source to avoid immunogenicity. The donor age or disease can

significantly affect the functionality including the proliferation or remodelling ability of harvested

cells. Primary cells usually have significantly limited lifespan *in vitro* as they become rapidly

senescent [21,33,34]. Stem cells have greater regenerative potential due to their infinite renewal

capacity and the ability to differentiate into various cell types upon environmental stimuli, which

provides an excellent source for fabricating TEVGs [21,35,36]. MSCs are particular appealing

among other stem cell types, like ESCs or iPSCs, despite limited plasticity, as they have

immunosuppressive features which been extensively investigated clinically and have shown

to prevent immunogenic responses upon implantation[23,37,38]. Although iPSCs have remarkable

potential to generate various types of tissue due to their plasticity, they lack the same

immunosuppressive features and undifferentiated iPSCs have significant tumorigenic

potential upon implantation [39]. Thus, scaffolds used to bioengineer blood vessels in this study

were seeded with hBM-MSCs or hiPSCs that were first derived in iMSCs prior to seeding or

differentiating into VSMCs to minimize the risk of tumorigenicity.

VSMCs, as the most abundant cell type in arteries, play a critical role in providing mechanical support and controlling the constant circulation of blood flow in vasculature [40,41]. Their contractile functions are key to the regulation of the vascular tone of blood vessels by buffering the pulsatile flow and maintain blood circulation [42,43]. Due to their important roles, various tissue engineering strategies have focused in mimicking the tunica media of native vasculature when fabricating blood vessels [44–46]. In this study, we demonstrated a viable method to derive VSMCs from hiPSCs via a MSC intermediate. A monolayer defemination method was used to produce VSMCs in part to provide a more reproducible protocol with well-defined chemical factors to direct it towards an MSC intermediate stage. SB431542, a TGF-β1 pathway inhibitor, was used to induces an EMT-like process and an MSC maintenance media was later introduced to promote maturation of these cells towards and MSC phenotype. This strategy offers significant clinical advantages as it couples key beneficial features of both MSCs and iPSCs. One of these features are their ability of MSCs to prevent immunogenic responses by host tissue post-implantation. In various studies, the expression of MHC class I, TLRs and PD-L1 in MSCs has demonstrated to aid in escaping attacks from activated natural killers and avoid an immunogenic response [37,47]. This particular characteristic can enable grafts generated from MSC intermediates to have an allogenic clinical approach apart from the general patient-specific approach iPSCs can provide. Furthermore, MSCs have been also shown to secrete TGF-β1 and hepatocyte growth factor (HGF) in response to inflammation to inhibit the activation and functions of T Cells which can further reduce the chances of immunogenic responses [23,48]. Therefore, although a patient-specific approach is viable using patients own reprogramed iPSCs, our approach also enables a potential for an "of-the-shelf" TEVG application using these key immunosuppressive characteristics MSCs possess by going through that intermediate stage. Moreover, Previous studies have shown that hiPSC derived MSCs could not only generate cells with a rejuvenated phenotype compared to adult MSCs but also enhance vascular regeneration and healing [49–51]. Our derived iMSCs had yields of 50-89% depending on the MSC-specific marker (CD73, CD105 and CD90) without requiring a cell-sorting step and were largely absent for phenotypical MSC negative markers (≤18% positive cells). These measurements were comparable to those in hBM-MSCs and iMSCs were also undergo osteogenic differentiation like hBM-MSCs. While yield of subsequently derived VSMCs was not measured, VSMC marker genes significantly increased by the end of differentiation with homogenous populations positive for VSMC markers observed via immunostaining.

In a previous study, we assessed the biocompatibility of our electrospun scaffolds on A7r5 rat smooth muscle embryonic aorta cells [19]. In this study we aimed to further validate these results with human cells and assess their biocompatibility over an extended culture period. Moreover,

this study evaluated the suitability of these scaffolds to generate vascular tissue like constructs derived from stem cells. Our previous study demonstrated that cells laden on all electrospun scaffold conditions could support proliferation from day 1 to 4. Our present results with hBM-MSCs and iMSCs showed similar outcomes and up to 10 days. However, a clear improvement in proliferation was observed in cell-laden porous scaffolds compared to pristine scaffolds and further enhanced by the silk fibroin coating due to it well known RGD binding sites present. Albeit cell dependent, porous or rough surfaces have shown to improve cell attachment, proliferation, migration and viability as observed in this study [52,53]. Silk fibroin, which demonstrated to also enhance cell function in this study, is a widely available biomaterial derived from silk and unlike other natural based biomaterials with mammalian cell adhesive motifs like collagen, gelatin or fibrin, it possesses remarkable mechanical strength. As a result, it has been extensively used for clinical applications such as biodegradable suturing materials or surgical meshes for wound healing [54–56]. Therefore, due to their superior biocompatibility, silk fibroin coated scaffolds were used for further hBM-MSCs/iMSC to VSMC differentiation experiments and fabrication of tissue engineered blood vessels.

Like those cultured in conventional tissue culture conditions, iMSCs and hBM-MSCs were able to successfully differentiate in VSMCs when seeded on the elctrospun silk fibroin coated scaffolds. As a result, they were used to fabricate blood vessel mimics using sheet wrapping method. One common method used to fabricate tube scaffolds via electrospinning is to spin fibres onto a conductive mandrel that acts as a subtractive mould. When the mandrel is removed, a tube-shaped fibrous mesh is left [57,58]. However, other methods like those that use electrospinning to fabricate fibrous sheet-like meshes and wrap them around a rod also exist. While both are viable methods, sheet-based strategies may be advantageous due to its simplicity and ability to generate multiple concentric layers like the tunica media in vessels as it wraps around the rod [19,59–61]. Further, it may also be advantageous as the calibre of tube constructs can be easily adjusted during the fabrication process to best match comply with anastomosed vasculature if used for bypass for an "off-the-shelf. This was demonstrated during the optimisation of the fabrication process of the bioegineered blood vessels in this study (**Figure S6**). The bioengineered blood vessels in this study not only showed to possess tunic-medial like features with densely populated iMSC-VSMCs or hBM-MSC-VSMCs but those derived from iMSC-VSMCs had similar mechanical properties to common autografts used in CABG. Moreover, the burst pressure calculated for these blood vessels (2184 ± 325.300 mmHg) was significantly greater than similar strategies using hiPSC-VSMC derived electrospun blood vessels like those by Sundaram et al. [36] (600-800 mmHg) which are well below those of autologous vessels used for CABG.

While this study successfully demonstrates a viable method to fabricate TEVGs with mechanical properties comparable to autologous grafts, limitations should be acknowledged. The study was conducted entirely *in vitro*, and no *in vivo* testing was performed. Although the TEVGs showed promising structural, mechanical and biocompatible characteristics, their long-term performance, integration, and remodelling capabilities in a physiological environment remain to be evaluated. Nevertheless, based on the robust mechanical properties and biological characterisation outcomes observed, we believe the TEVGs developed in this study are ready for *in vivo* testing in animal models to assess their functional performance in a more clinically relevant setting. Future studies should focus on validating these constructs in preclinical models to further determine their suitability for clinical translation.

In conclusion, a viable and versatile method to fabricate tissue engineered blood vessels derived from different stem cell types was developed in the present study. A protocol successful at generating hiPSCs derived MSCs and subsequent iMSC derived MSCs was reported in this study that could also be applied to derive VSMCs for hBM-MSCs. Derivation of VSMCs from iMSCs and hBM-MSCs was also shown in electrospun scaffolds coated with silk fibroin to demonstrate stem cell derived vascular constructs could be generated. These vascular constructs included a bioengineered blood vessel with tunica-media like features after 3 weeks of culture. The VSMC-laden tunica media-like bioengineered vessels also demonstrated to possess similar mechanical properties to those of common autografts used in CABG making it a potential candidate for TEVG application although further evaluation *in vivo* would be required to assess its suitability. Lastly, our simple yet versatile approach has shown it has the potential to fabricate "off-the-shelf TEVGs that can potentially be used universally as allogenic sources due to immunoregulatory appeal MSCs possess or via a patient-specific approach using hiPSCs. Therefore, showing significant potential for clinical application.

Acknowledgements

The Author would like to gratefully acknowledge Dr Peter March for his help in the bioimaging facilities at the University of Manchester and Michael Jackson at the University of Manchester core facilities for his contribution on training and using the flow cytometry equipment.

Funding

The work is supported by the EPSRC & MRC PhD studentship and the Centre for Doctoral Training (CDT) program in Regenerative Medicine.

References

1. Townsend N, Bhatnagar P, Wilkins E, Kremlin Wickramasinghe K, Rayner M. *Cardiovascular Disease Statistics 2015 - BHF*.; 2015.

2. Diodato M, Chedrawy EG. Coronary Artery Bypass Graft Surgery: The Past, Present, and Future of Myocardial Revascularisation. *Surg Res Pract*. 2014;2014:1-6. doi:10.1155/2014/726158

3. Singh AK. Percutaneous coronary intervention vs coronary artery bypass grafting in the management of chronic stable angina: A critical appraisal. *J Cardiovasc Dis Res*. 2010;1(2):54-58.

4. Redfors B, Volz S, Angeras O, Ioanes D, Odenstedt J, Haraldsson I, Dworeck C, Myredal A, Hirlekar G, Ramunddal T, Petursson P. Comparative Effectiveness of CABG versus PCI in Patients with Ischemic Heart Disease : insights from SWEDEHEART Registry. *Eur Heart J*. 2020;41(Supplement_2):ehaa946-2521.

5. Alexander J., Smith P. Coronary-Artery Bypass Grafting. *N Engl J Med*. 2016;374(20):1954-1964. doi:10.1056/NEJMra1406944

6. Caliskan E, Souza DR De, Böning A, Liakopoulos OJ, Choi Y, Pepper J, Gibson CM, Perrault LP, Wolf RK, Kim K, Emmert MY. Saphenous vein grafts in contemporary coronary artery bypass graft surgery. *Nat Rev Cardiol*. 2020;17(3):155-169. doi:10.1038/s41569-019-0249-3

7. Audisio K, Halbreiner MS, Chadow D, Gaudino M. Radial artery or saphenous vein for coronary artery bypass grafting. *Trends Cardiovasc Med*. 2022;32(8):479-484. doi:10.1016/j.tcm.2021.09.007

8. Jouda H, Larrea Murillo L, Wang T. Current Progress in Vascular Engineering and Its Clinical Applications. *Cells*. 2022;11(3):493.

9. Yang L, Li X, Wang D, Mu S, Lv W, Hao Y, Lu X, Zhang G, Nan W, Chen H, Xie L, Yang L, Li X, Wang D, Mu S, Lv W, Hao Y. Improved mechanical properties by modifying fibrin scaffold with PCL and its biocompatibility evaluation. *J Biomater Sci Polym Ed*. 2020;31(5):658-678. doi:10.1080/09205063.2019.1710370

10. Heureux NL, Dusserre N, Konig G, Victor B, Keire P, Wight TN, Chronos NAF, Kyles AE, Gregory CR, Hoyt G, Robbins RC, Mcallister TN. Human tissue-engineered blood vessels for adult arterial revascularization. *Nat Med*. 2006;12(3):361-365. doi:10.1038/nm1364

11. Kannan RY, Salacinski HJ, Butler PE, Hamilton G, Seifalian AM. Current Status of Prosthetic Bypass Grafts : A Review. *J Biomed Mater Res Part B Appl Biomater An Off J Soc Biomater Japanese Soc Biomater Aust Soc Biomater Korean Soc Biomater*.

2005;74(1):570-581. doi:10.1002/jbm.b.30247

12. Lawson JH, Glickman MH, Ilzecki M, Jakimowicz T, Peden EK, Pilgrim AJ, Prichard
HL, Guziewicz M, Przywara S, Szmidt J, Turek J, Witkiewicz W, Zapotoczny N.
Bioengineered human acellular vessels for dialysis access in patients with end stage
renal disease: two phase 2 single-arm trials. *Lancet*. 2016;387(10032):2026-2034.
doi:10.1016/S0140-6736(16)00557-2.Bioengineered

13. Herrmann FE., Lamm P, Wellmann P, Milz S, Hagl C, Juchem G. Autologous
endothelialized vein allografts in coronary artery bypass surgery–Long term results.
Biomaterials. 2019;212(June 2018):87-97. doi:10.1016/j.biomaterials.2019.05.019

14. Awad NK, Niu H, Ali U, Morsi YS, Lin T. Electrospun fibrous scaffolds for small-
diameter blood vessels: A review. *Membranes (Basel)*. 2018;8(1):1-26.
doi:10.3390/membranes8010015

15. Ju YM, San Choi J, Atala A, Yoo JJ, Lee SJ. Bilayered scaffold for engineering
cellularized blood vessels. *Biomaterials*. 2010;31:4313–4321.

16. Rickel AP, Deng X, Engebretson D, Hong Z. Electrospun nanofiber scaffold for
vascular tissue engineering. *Mater Sci Eng C*. 2021;129:112373.
doi:10.1016/j.msec.2021.112373

17. Ju YM, Ahn H, Arenas-Herrera J, Kim C, Abolbashari M, Atala A, Yoo JJ, Lee SJ.
Electrospun vascular scaffold for cellularized small diameter blood vessels: A
preclinical large animal study. *Acta Biomater*. 2017;59:58-67.
doi:10.1016/j.actbio.2017.06.027

18. Umuhoza D, Yang F, Long D, Hao Z, Dai J, Zhao A. Strategies for Tuning the
Biodegradation of Silk Fibroin-Based Materials for Tissue Engineering Applications.
Biomater Sci Eng. 2020;6(3):1290-1310. doi:10.1021/acsbiomaterials.9b01781

19. Song J, Chen Z, Murillo LL, Tang D, Meng C, Zhong X, Wang T, Li J. Hierarchical
porous silk fibroin/poly(L-lactic acid) fibrous membranes towards vascular scaffolds.
Int J Biol Macromol. 2021;166:1111-1120. doi:10.1016/j.ijbiomac.2020.10.266

20. Jeong SI, Kim SY, Cho SK, Chong MS, Kim KS, Kim H, Lee SB, Lee YM. Tissue-
engineered vascular grafts composed of marine collagen and PLGA fibers using
pulsatile perfusion bioreactors. *Biomaterials*. 2007;28(6):1115-1122.
doi:10.1016/j.biomaterials.2006.10.025

21. Atchison L, Zhang H, Cao K, Truskey GA. A Tissue Engineered Blood Vessel Model
of Hutchinson-Gilford Progeria Syndrome Using Human iPSC-derived Smooth Muscle
Cells. *Sci Rep*. 2017;7(1):1-12. doi:10.1038/s41598-017-08632-4

22. Zomer HD, Vidane AS, Goncales NN, Ambrïsio CE. Mesenchymal and induced
pluripotent stem cells: General insights and clinical perspectives. *Stem Cells Cloning*
Adv Appl. 2015;8:125-134. doi:10.2147/SCCAA.S88036

23. Chen Q, Wu F, Liu L, Chen H, Zheng R, Wang H, Yu L. Mesenchymal stem cells
regulate the Th17 / Treg cell balance partly through hepatocyte growth factor in vitro.
Stem Cell Res Ther. 2020;11(1):1-11.

24. Chen YS, Pelekanos R, Ellis R, Horne R, Wolvetang E, Fisk N. Small Molecule
Mesengic Induction of Human Induced Pluripotent Stem Cells to Generate
Mesenchymal Stem/Stromal Cells. *Stem Cells Transl Med*. 2012;(1):83-95.

25. Ghanizadeh Tabriz A, Mills CG, Mullins JJ, Davies JA, Shu W. Rapid Fabrication of
Cell-Laden Alginate Hydrogel 3D Structures by Micro Dip-Coating. *Front Bioeng*
Biotechnol. 2017;5(February):1-10. doi:10.3389/fbioe.2017.00013

26. Schneider KH, Rohringer S, Kapeller B, Grasl C, Kiss H, Heber S, Walter I, Teuschl
AH, Podesser BK, Bergmeister H. Riboflavin-me diate d photooxidation to improve the
characteristics of decellularized human arterial small diameter vascular grafts. *Acta*
Biomater. 2020;116:246-258. doi:10.1016/j.actbio.2020.08.037

27. Patel B, Wonski BT, Saliganan DM, Rteil A, Kabbani LS, Lam MT. Decellularized
dermis extracellular matrix alloderm mechanically strengthens biological engineered
tunica adventitia-based blood vessels. *Sci Rep*. 2021;11(1):1-16.

28. Zhao L, Li X, Yang L, Sun L, Mu S, Zong H, Li Q, Wang F, Song S, Yang C, Zhao C,
Chen H, Zhang R. Materials Science & Engineering C Evaluation of remodeling and
regeneration of electrospun PCL / fibrin vascular grafts in vivo. *Mater Sci Eng C*.
2021;118(August 2020):111441. doi:10.1016/j.msec.2020.111441

29. Hu Y, Pan X, Zheng J, Ma W, Sun L. In vitro and in vivo evaluation of a small-caliber
coaxial electrospun vascular graft loaded with heparin and VEGF. *Int J Surg*.
2017;44:244-249. doi:10.1016/j.ijsu.2017.06.077

30. Hasan A, Memic A, Annabi N, Hossain M, Paul A, Dokmeci MR, Dehghani F,
Khademhosseini A. Electrospun scaffolds for tissue engineering of vascular grafts.
Acta Biomater. 2014;10(1):11-25. doi:10.1016/j.actbio.2013.08.022

31. McAllister TN, Maruszewski M, Garrido SA, Wystrychowski W, Dusserre N, Marini A,
Zagalski K, Fiorillo A, Avila H, Manglano X, Antonelli J, Kocher A, Zembala M,
Cierpka L, de la Fuente LM, L'Heureux N. Effectiveness of haemodialysis access with
an autologous tissue-engineered vascular graft: a multicentre cohort study. *Lancet*.
2009;373(9673):1440-1446. doi:10.1016/S0140-6736(09)60248-8

32. Lamm P, Juchem G, Milz S, Schuffenhauer M, Reichart B. Autologous
Endothelialized Vein Allograft. 2001;104(Suppl_1):108-114.

33. Heath CA. Cells for tissue engineering. *Trends Biotechnol*. 2000;18(1):17-19.

34. Hughes P, Marshall D, Reid Y, Parkes H, Gelber C. The costs of using
unauthenticated, over-passaged cell lines: how much more data do we need?
Biotechniques. 2007;43(5):575-586. doi:10.2144/000112598

35.   Luo J, Qin L, Zhao L, Gui L, Ellis MW, Huang Y, Kural MH, Clark JA, Ono S, Wang J,
672   Yuan Y, Zhang SM, Cong X, Li G, Riaz M, Lopez C, Hotta A, Campbell S, Tellides G,
673   Dardik A, Niklason LE, Qyang Y. Tissue-Engineered Vascular Grafts with Advanced
674   Mechanical Strength from Human iPSCs. *Cell Stem Cell*. 2020;26(2):251-261.e8.
675   doi:10.1016/j.stem.2019.12.012
676   36.   Sundaram S, One J, Siewert J, Teodosescu S, Zhao L, Dimitrievska S, Qian H,
677   Huang AH, Niklason L. Tissue-Engineered Vascular Grafts Created From Human
678   Induced Pluripotent Stem Cells. *Stemcells Transl*. 2014;3(12):1535-1543.
679   doi:doi/10.5966/sctm.2014-0065
680   37.   Sotiropoulou P., Perez S., Gritzapis A., Baxevanis C., Papamichail M. Interactions
681   between human mesenchymal stem cells and natural killer cells. *Stem Cells*.
682   2006;24(1):74-85. doi:10.1634/stemcells.2004-0359
683   38.   Kalimuthu S, Gangadaran P, Li XJ, Oh JM, Lee HW, Jeong SY, Lee SW, Lee J, Ahn
684   BC. In Vivo therapeutic potential of mesenchymal stem cell-derived extracellular
685   vesicles with optical imaging reporter in tumor mice model. *Sci Rep*.
686   2016;6(February):1-11. doi:10.1038/srep30418
687   39.   Lee AS, Tang C, Rao MS, Weissman IL, Wu JC. Tumorigenicity as a clinical hurdle
688   for pluripotent stem cell therapies. *Nat Med*. 2013;19(8):998-1004.
689   doi:10.1038/nm.3267
690   40.   Scott D, Tan Y, Shandas R, Stenmark KR, Tan W. High pulsatility flow stimulates
691   smooth muscle cell hypertrophy and contractile protein expression. *AJP Lung Cell Mol
692   Physiol*. 2013;304(1):L70-L81. doi:10.1152/ajplung.00342.2012
693   41.   Tykocki NR, Boerman EM, Jackson WF. Smooth muscle ion channels and regulation
694   of vascular tone in resistance arteries and arterioles. *Compr Physiol*. 2017;7(2):485-
695   581. doi:10.1002/cphy.c160011
696   42.   Wanjare M, Kuo F, Gerecht S. Derivation and maturation of synthetic and contractile
697   vascular smooth muscle cells from human pluripotent stem cells. *Cardiovasc Res*.
698   2013;97(2):321-330. doi:10.1093/cvr/cvs315
699   43.   Brozovich F V., Nicholson CJ, Degen C V., Gao YZ, Aggarwal M, Morgan KG.
700   Mechanisms of Vascular Smooth Muscle Contraction and the Basis for
701   Pharmacologic Treatment of Smooth Muscle Disorders. *Pharmacol Rev*.
702   2016;68(2):476-532. doi:10.1124/pr.115.010652
703   44.   L'Heureux N, Pâquet S, Labbé R, Germain L, Auger FA. A completely biological
704   tissue-engineered human blood vessel. *FASEB J*. 1988;12(1):47-56.
705   doi:10.1096/fasebj.12.1.47
706   45.   Dahl S., Kypson A., Lawson J., Blum J., Strader J., Li Y, Manson R., Tente W.,
707   DiBernardo L, Hensley M., Carter R. Readily available tissue-engineered vascular

708   grafts. *Sci Transl Med*. 2011;3(68):68ra9-68ra9.

709 46. Elsayed Y, Lekakou C, Labeed F, Tomlins P. Fabrication and characterisation of

710   biomimetic, electrospun gelatin fibre scaffolds for tunica media-equivalent, tissue

711   engineered vascular grafts. *Mater Sci Eng C*. 2016;61:473-483.

712   doi:10.1016/j.msec.2015.12.081

713 47. Giuliani M, Bennaceur-Griscelli A, Nanbaksh A, Oudrihiri N, Chouaib S, Durrbach A,

714   Lataillade J-J. TLR Ligands Stimulation Protects MSC from NK Killing. *Stem Cells*.

715   2014;32(88):290-300.

716 48. Niu J, Yue W, Le-le Z, Bin L, Hu X. Mesenchymal stem cells inhibit T cell activation by

717   releasing TGF-β1 from TGF-β1 / GARP complex. *Oncotarget*. 2017;8(59):99784-

718   99800.

719 49. Lian Q, Zhang Y, Zhang J, Zhang HK. Functional Mesenchymal Stem Cells Derived

720   From Human Induced Pluripotent Stem Cells Attenuate Limb Ischemia in Mice.

721   *Circulation*. 2010;121(9):1113-1123. doi:10.1161/CIRCULATIONAHA.109.898312

722 50. Spitzhorn LS, Megges M, Wruck W, Rahman MS, Otte J, Degistirici Ö, Meisel R, Sorg

723   RV, Oreffo ROC, Adjaye J. Human iPSC-derived MSCs (iMSCs) from aged

724   individuals acquire a rejuvenation signature. *Stem Cell Res Ther*. 2019;10(1):1-18.

725   doi:10.1186/s13287-019-1209-x

726 51. Zhang J, Guan J, Niu X, Hu G, Guo S, Li Q, Xie Z, Zhang C, Wang Y. Exosomes

727   released from human induced pluripotent stem cells-derived MSCs facilitate

728   cutaneous wound healing by promoting collagen synthesis and angiogenesis. *J Transl*

729   *Med*. 2015;13(1):1-14. doi:10.1186/s12967-015-0417-0

730 52. Vassaux M, Milan J. Stem cell mechanical behaviour modelling : substrate ' s

731   curvature influence during adhesion. *Biomech Model Mechanobiol*. 2017;16(4):1295-

732   1308. doi:10.1007/s10237-017-0888-4

733 53. Cai S, Wu C, Yang W, Liang W, Yu H, Liu L. Recent advance in surface modification

734   for regulating cell adhesion and behaviors. *Nanotechnol Rev*. 2020;9(1):971-989.

735 54. Yan S, Li Y, Jiang Y, Xu Y, Wang D. Expanded polytetrafluoroethylene / silk fibroin /

736   salicin vascular graft fabrication for improved endothelialization and anticoagulation.

737   *Appl Surf Sci*. 2021;542(15 March (2021) 148610):1-11.

738   doi:10.1016/j.apsusc.2020.148610

739 55. Marcolin C, Draghi L, Tanzi M, Faré S. Electrospun silk fibroin–gelatin composite

740   tubular matrices as scaffolds for small diameter blood vessel regeneration. *J Mater*

741   *Sci Mater Med*. 2017;28(5):1-12. doi:10.1007/s10856-017-5884-9

742 56. Wang Y, Kim H, Vunjak-novakovic G, Kaplan DL. Stem cell-based tissue engineering

743   with silk biomaterials. 2006;27:6064-6082. doi:10.1016/j.biomaterials.2006.07.008

744 57. Fukunishi T, Best CA, Sugiura T, Opfermann J, Ong CS, Shinoka T, Breuer CK,

Krieger A. Preclinical study of patient-specific cell-free nanofiber tissue-engineered vascular grafts using 3-dimensional printing in a sheep model. *J Thorac Cardiovasc Surg*. 2017;153(4):924-932. doi:10.1016/j.jtcvs.2016.10.066

58. Connor RAO, Cahill PA, Mcguinness GB. Effect of electrospinning parameters on the mechanical and morphological characteristics of small diameter PCL tissue engineered blood vessel scaffolds having distinct micro and nano fibre populations – A DOE approach. *Polym Test*. 2021;96(April):107119. doi:10.1016/j.polymertesting.2021.107119

59. Woods I, Molloy EJ, Jockenhoevel S, Flanagan TC. Fabrication of blood-derived elastogenic vascular grafts using electrospun fibrinogen and polycaprolactone composite scaffolds for paediatric applications. *J Tissue Eng Regen Med*. 2020;14(9):1281-1295. doi:10.1002/term.3100

60. Mun CH, Jung Y, Ph D, Kim S, Ph D, Lee S. Three-dimensional electrospun poly (lactide-co-ε-caprolactone) for small-diameter vascular grafts. *Tissue Eng Part A*. 2012;18(15-16):1608-1616. doi:10.1089/ten.tea.2011.0695

61. Hu J, Chao W, Lee P, Huang C. Construction and characterization of an electrospun tubular scaffold for small-diameter tissue-engineered vascular grafts : A scaffold membrane approach. *J Mech Behav Biomed Mater*. 2012;13(September):140-155. doi:10.1016/j.jmbbm.2012.04.013

Figure 1 hiPSC differentiate in to cells with an MSC phenotype exhibiting common MSC markers. A schematic of the MSC differentiation protocol is shown (**A**). Fold gene expression increases in MSC marker-genes *THY1 (CD90)*, *NT5E (CD73)* and *ENG (CD105)* was observed throughout differentiation of hiPSC-iMSCs (**B**). Histograms for common MSC positive markers are displayed (**C**) and increase of the percentage of cells positive for CD90, CD73 and CD105 after 36 days could also be noticed via flow cytometry (**C-i to C-iii**) after 36 days when iMSCs were derived. Data significance is presented as *** P ≤ 0.001 and **** p ≤ 0.0001 (n = 3).

Figure 2 Characterisation of iMSC and hBM-MSCs via alizarin red staining. Both iMSCs and hBM-MSCs underwent osteogenic differentiation with noticeable mineralisation nodules being produced by the end of differentiation (day 28) as displayed by alizarin red staining. Images were collected on an Olympus IX83 inverted microscope and captured through MMI CellTools software at 10x magnification. Scale bars shown at 200 μm.

Figure 3 Detection of common VSMC markers in hBM-MSC-VSMCs and iMSC-VSMCs. A schematic of the VSMC differentiation protocol is shown (**A**). Fold gene expression increases in VSMC marker-genes *α-SMA*, *CNN1*, *SM22* and *MYH11* was also noticed throughout differentiation of hBM-MSC-VSMCs and iMSC-VSMCs (**B**) More homogenous population positive for contractile VSMC markers α-SMA and CACNA1C (green) as well as CNN1 and SM22 (red) could be observed by day 9 of differentiation via Immunofluorescence staining in hBM-MSC-VSMCs (C) and iMSC-VSMCs (**C**). Scale bars shown at 100 µm. Data significance is presented as *p < 0.05, ** P ≤ 0.01 *** P ≤ 0.001 **** p ≤ 0.0001 (n = 3).

Figure 4 Proliferation and metabolic activity of hBM-MSC and iMSCs. A diagram of the modifications made to the pristine (1) by immersing in acetone ≥ 99.8% acetone to porous (2) fibres and covered with a 1% w/v silk fibroin solution to coat scaffolds (3)(**A**). Three different types of scaffolds were visualised under SEM imaging. Pristine scaffolds produced by electrospinning without any post-electrospinning modification (**B**). Cells count differences in iMSCs and hBM-MSCs seeded on pristine, porous and silk fibroin coated scaffolds after and reduction of AlamarBlue™ differences in iMSCs and hBM-MSCs seeded on pristine, porous and silk fibroin coated scaffolds after 10 days of culture (**C**) Density and morphological differences between the scaffold conditions were also observed via immunofluorescence staining with Phalloidin-iFluor 488 (A). Scale bars shown at 100 μm (**D**). Data significance is presented as *p < 0.05, ** P ≤ 0.01, *** P ≤ 0.001 (n =3).

Figure 5 Detection of common VSMC markers in hBM-MSC-VSMC and iMSC-VSMC ladens electrospun scaffolds. Electrospun sheets coated with silk fibroin were seeded with hMSCs-BM (**Ai**). After 9 days, hMSCs-BM stained with phalloidin 488 showed to have adhered and spread throughout the scaffolds (**Aii and Aiii**). Scale bars shown at 2 mm for the wide view and 100 μm in the zoomed images. Images were aquired on an Olympus BX63 upright microscope using a using an DP80 camera (Olympus) through CellSens software. Homogenous population positive for contractile VSMC markers α-SMA (green) and CNN1 (red) could be observed in hBM-MSC-VSMCs and iMSC-VSMCs laden scaffolds after 9 days of differentiation. Scale bars shown at 50 μm at 20x magnification (**B**).

Figure 6 Vessel-like constructs derived from hMSCs-BM and iMSCs. Diagram of the fabrication process of tissue engineered blood vessels (**A**). The tube construct post-production can be seen next to the steel rod used to fabricate next and next to a penny for scale comparison (**Bi**). Length dimensions (**Bii**), wall thickness, and inner diameter dimensions (**Biii**) are also displayed. Immunofluorescence images of longitudinal cross-sections of tube constructs (B). Vessel mimics fabricated using both hBM-MSC-VSMCs and iMSC-VSMCs can be observed to be densely-populated with cells positive for α-SMA (green) and CNN1 (red). DAPI was counterstained to show nuclei. Scale bars shown at 100 μm. The representation of the scale is displayed in (**C**) Mechanical property differences in UTS (**D**), burst strength (**E**), young's modulus (**F**) and strain (**G**) were also measured. Data significance is presented as *p < 0.05 (n =3).