Poly-L-Ornithine Coated Plant Scaffolds Support Motor Recovery in Rats after Traumatic Spinal Cord Injury

Lauren J. Couvrette[1], Krystal L. A. Walker[2], Arman Bayat[2], Daniel J. Modulevsky[1,2], Alex Laliberté[1], Charles M. Cuerrier[1,2,3], Maxime Leblanc-Latour[2,3], Ryan J. Hickey[2], Rose Boudria[1], Ruthie Monty[2], Ras-Jeevan K. Obhi[2], Isabel Shore[2,3], Ahmad Galuta[4], Eve C. Tsai[4,5,6], Tuan Bui[1], and Andrew E. Pelling[1,2,3,7*]

[1]Department of Biology, Gendron Hall, 30 Marie Curie, University of Ottawa, Ottawa, ON, K1N5N5 Canada
[2]Department of Physics, STEM Complex, 150 Louis Pasteur Pvt., University of Ottawa, Ottawa, ON, K1N5N5 Canada
[3]Spiderwort Inc., 7, Bayview Station Road, Ottawa, ON, K1K4R3 Canada
[4]Program in Neuroscience, Ottawa Hospital Research Institute, Ottawa, ON, K1Y 4E9 Canada
[5]Division of Neurosurgery, Department of Surgery, The Ottawa Hospital, Ottawa, ON, K1Y 4E9 Canada
[6]Department of Cellular and Molecular Medicine, Faculty of Medicine, University of Ottawa, Ottawa, ON, K1H 8M5 Canada
[7]Institute for Science Society and Policy, Simard Hall, 60 University, University of Ottawa, Ottawa, ON, K1N5N5 Canada

*Author for correspondence: Andrew E. Pelling, University of Ottawa, Tel. +1 613 562 5800, Email: apelling@uottawa.ca

ABSTRACT

Spinal cord injury (SCI) is a debilitating neurological condition with far-reaching consequences for patients, including loss of motor function and significant limitations to quality of life. Implantable biomaterials have emerged as a therapeutic strategy to modulate the SCI microenvironment and facilitate regeneration of axons. In this study, plant-derived cellulose scaffolds coated with poly-L-ornithine (PLO) are shown to support locomotor recovery and neural tissue repair in a rat model of spinal cord injury. Upon complete transection of the spinal cord, animals were implanted with a plant-derived scaffold coated in poly-L-ornithine, a positively charged amino acid chain that is known to promote neural stem cell differentiation into neurons and enhance myelin regeneration. Recovery of motor function was evaluated by the Basso, Beattie and Bresnahan (BBB) locomotor scale as well as the Karolinska Institutet Swim Assessment Tool (KSAT). Retrograde tracing of ascending sensory tracts revealed enhanced regeneration in animals that received the PLO-coated scaffold. Numerous β-III tubulin and neurofilament 200 positive fibers may indicate axonal sprouting within the cellulose scaffold and LFB staining highlights myelination around the PLO-coated scaffold. These results demonstrate the potential of plant-based biomaterials in a rat model of acute spinal cord injury and highlight their enhancement after PLO functionalization.

Introduction

The mammalian spinal cord has limited regenerative capacity after spinal cord injury (SCI). Failure of the adult central nervous system to regenerate can be attributed in part to the limited capacity of injured neurons to re-establish functional axons across the lesion[1]. Mechanical trauma to the tissue elicits a range of cell responses, including increased proliferation of ependymal cells that line the central canal[2]. Upon activation, ependymal cells re-express neural stem cell properties and migrate to the site of injury, where they spontaneously differentiate into oligodendrocytes and astrocytes[3]. Although ependymal cells can differentiate into neurons *in vitro*, the same has not been demonstrated following SCI in vivo[4], though mature oligodendrocytes have been observed[5,6]. After SCI, complex pathological mechanisms create a hostile microenvironment at the injury epicenter, which inhibits the regrowth of axons and damages surrounding tissue[7]. For instance, SCI-induced death of oligodendrocytes leads to an accumulation of myelin breakdown products at the injury site [8–10]. Molecules such as Nogo-A and myelin-associated glycoprotein are released from damaged myelin into the extracellular matrix after SCI and represent an important group of axonal growth inhibitors[11]. Many therapeutic strategies aim to establish a more permissive environment for regeneration by removing inhibitory molecules[12,13], providing trophic support[14,15], directing stem cell fate[16], remyelinating axons[17,18], or implanting biomaterial scaffolds that can guide axonal growth[19,20]. In recent years, multimodal therapies have generated much attention since they address multiple aspects of SCI pathology and often produce greater benefit than their individual components[21,22]. Such therapeutic strategies have combined cell transplants, biomaterials, locomotor training, and neurotrophic factors with the goal of modulating the injury microenvironment to promote repair.

Developing biocompatible scaffolds to bridge the SCI has been at the forefront of tissue engineering strategies.
Implantable biomaterials not only provide structural scaffolding to guide cell attachment and migration but can also be used
to regulate the inflammatory response or deliver other therapeutics such as stem cells and growth factors. Regenerative
biomaterials for SCI are designed to replicate the properties of spinal cord tissue and should therefore have the mechanical
strength, porosity and internal microstructures that are suitable for neurite extension across the injury site[23,24]. Moreover,
the surface chemistry of biomaterials is of particular importance, as it can be utilized to influence cell migration and
differentiation [25,26].

Both degradable and non-degradable biomaterials have been investigated for SCI repair. In order for degradable
scaffolds to act as extracellular matrix substitutes, it is essential that their rate of degradation aligns with the regeneration
rate of axons[27]. Synthetic materials are attractive candidates for spinal cord tissue engineering due to their controllable
mechanical properties and high batch-to-batch consistency. For example, polyethylene glycol is a synthetic polymer that can
be cross-linked to form injectable hydrogels that provide a framework for regenerating tissue and were shown to promote
motor recovery in a rat model of SCI[28]. In addition, poly(lactic-co-glycolic acid)-based scaffolds have produced significant
motor improvements and increased tissue remodelling in African green monkeys with an incomplete SCI[29]. However, many
synthetic biomaterials are limited by their hydrophobicity, which can impair cell attachment, or by their potential to release
toxic by-products during degradation. By contrast, natural materials such as collagen, fibrin, alginate, chitosan and hyaluronic
acid are widely studied as regenerative scaffolds for SCI due to their excellent biocompatibility and cell adhesion properties.
In particular, collagen-based scaffolds are a promising SCI treatment that has been explored in diverse forms including
collagen hydrogels[30], sponges or scaffolds that deliver therapeutics to the injury[31]. Ongoing human clinical trials have
reaffirmed the therapeutic potential of collagen scaffolds, notably in their ability to promote tissue regeneration and
functional recovery[32]. One common issue with scaffolds made from natural polymers is insufficient mechanical strength and
durability in vivo, which multiple studies have aimed to resolve by adding cross-linkers[33] or combining natural and synthetic
biomaterials.

Recently, plant-derived scaffolds have been investigated in vivo for various biomedical applications including skin[34],
tendon[35], nerve[36] and bone[37] tissue engineering. Many different plant species can be decellularized with the help of
detergents, sonication, enzymatic digestion, or freeze-thawing methods to produce cellulose-based scaffolds[38] composed of
β(1→4) linked D-glucose units. Plant cellulose scaffolds were shown to be biocompatible in vivo and supported extracellular
matrix deposition when implanted subcutaneously[39]. In addition, these scaffolds became vascularized as early as one week
post-implantation. Since cellulose is not biodegradable in humans, scaffolds made from this material are poised to offer long-
term durability in vivo[40]. Moreover, plant cellulose has proven to be a versatile material that can be combined with hydrogels
to generate customizable macroscopic structures[41]. Some groups have shown that cellulose scaffolds can be functionalized
with chemical coatings to promote cell adhesion[42]. For example, we have previously demonstrated that poly-L-ornithine-
coated cellulose scaffolds produced from stalks of Asparagus officinalis can support attachment and proliferation of neural
stem cells in vitro[43]. In culture, rat neural stem cells form neurospheres that attach to the cellulose biomaterial and readily
infiltrate its channels. Increased expression of neuron-specific beta-III tubulin and glial fibrillary acidic protein in cells grown
on these scaffolds suggests they may promote differentiation of NSCs towards neurons and astrocytes, respectively, *in vitro*.

Here we investigate the ability of poly-L-ornithine-coated cellulose biomaterials to support neural tissue repair and
functional recovery after traumatic SCI. We implanted poly-L-ornithine-coated scaffolds or uncoated scaffolds acutely
following a complete spinal cord transection in rats housed in an enriched environment. Motor recovery was monitored by
the Basso, Beattie and Bresnahan (BBB) open field assessment and Karolinska Institutet Swim Assessment Tool (KSAT).
Sprouting and regeneration of the dorsal columns were analyzed by neural tract tracing with the retrograde tracer CTb
injected into the sciatic nerve. The results of this experiment point to enhanced regeneration of the sensory tracts in animals
that received PLO-coated implants compared to controls. In addition, the descending fibers of the corticospinal tracts were
visualized with dextran amine injections in the motor cortex, which revealed CST axons projecting along the cellulose
biomaterial. Finally, histological analysis showed host tissue integration with the scaffold and neural cell migration along its
channels, which was enhanced by the PLO coating. In sum, we demonstrate the ability of PLO-modified plant-derived
scaffolds to promote axonal sprouting in the lesion and induce motor recovery after SCI.

Results

Cellulose Scaffold Production and Implantation in Rodent Spinal Cord Injury

Stalks of Asparagus officinalis were cut into cylindrical sections with a biopsy punch and decellularized to produce cellulose scaffolds (Fig 1A). Naturally occurring vascular bundles (VBs) cross the length of the cellulose scaffold, which has parenchyma with an average pore diameter of 39±15μm (Fig 1B). The aligned channels within the scaffold were characterized by scanning electron microscopy and the Young's modulus was measured parallel to the long axis as 128±20 kPa (n=5). In animals with a complete T8-T9 spinal cord transection, scaffolds were implanted into the gap between the stumps of the cord with the long axis of the VBs parallel to the spinal cord (Fig 1D). The control group (n=8) did not receive a scaffold, while the PLO group (n=11) was implanted with a cellulose scaffold coated with a 100μg/ml solution of poly-L-ornithine (PLO) and the ASP group (n=9) received an uncoated cellulose scaffold. After 12 weeks in vivo, spinal cord tissue was collected, and histological analysis was performed to assess tissue integration with the scaffold. Immunohistochemistry staining for CD31 was performed to assess biomaterial vascularization (Fig 1F and G). CD31 positive blood vessels were identified in the tissue surrounding the scaffold, including the dorsal, rostral, and caudal interfaces. As well, CD31 positive blood vessels were found inside the vascular bundles within the biomaterial. Hematoxylin & eosin staining revealed nuclei migrating along the channels of the cellulose biomaterial (Fig 1E), which is consistent with our previous in vitro study[43]. In particular, nuclei were observed within the vascular bundles of the biomaterial (Fig 1C) and completely crossed the lesion. The scaffolds retained their structure and dimensions throughout the study and no signs of chronic foreign body reaction were observed, which aligns with the findings of previous studies[39,44]. Prior to testing the biomaterial in a rat model of SCI, we examined its biocompatibility by subcutaneously implanting PLO-coated scaffolds in immunocompetent Sprague Dawley rats. Histological analysis performed at 1-, 4-, and 12-weeks post-implantation showed a gradual decrease in immune cell presence in the scaffold and surrounding dermis tissue (Supplementary Fig 1). By the 12-week timepoint, low levels of foreign body multinucleated cells were observed at the periphery of the scaffold.

Hindlimb locomotor recovery after complete SCI

BBB Locomotor Assessment

Hindlimb motor function was assessed weekly using the Basso, Beattie and Bresnahan (BBB) locomotor scale, which ranges from 0 (complete hindlimb paralysis) to 21 (normal locomotion) points. Two weeks after complete transection of the spinal cord, the BBB assessment was performed to confirm total hindlimb paralysis. At this initial assessment, there were no significant differences in locomotor ability amongst the experimental groups: No Tx (transection with no scaffold, n=8), ASP treated (cellulose implant only, n=9), and PLO treated (PLO-coated cellulose implant, n= 11). Any animal that achieved a BBB score of above 5 at the 2-week post-operative timepoint was excluded from further locomotor evaluation. Out of 29 animals, a single rat was identified as an outlier, with a BBB score of 5.5 (average of 3 examiners) and was therefore excluded from the BBB motor recovery assessment. Over the 11-week recovery period, BBB scores increased significantly in animals that received PLO-coated scaffolds (p<0.0001) as well as those implanted with uncoated scaffolds (p=0.0158) (Fig 2A). This was determined by comparing the average score at week 2 with the average score at week 11 for each experimental group. Whereas significant functional recovery was achieved in scaffold treated groups, animals that did not receive a scaffold had no significant change (p=0.3128) in BBB scores throughout the recovery period. At week 11, the mean BBB score of rats treated with the PLO-coated scaffold was 5.6±0.87 points, corresponding to slight movement in 2 joints and extensive movement of a third. The group receiving uncoated scaffolds had a mean score of 4.3±0.96, indicating slight movement of all three joints of the hindlimb. By contrast, controls that did not receive a scaffold had a mean score of 3.35±1.0, reflecting extensive movement in 2 joints. Importantly, no animals from the No Tx group attained scores of 6 or above, whereas several animals from the PLO and ASP groups achieved BBB scores of 7 (extensive movement of all three joints), 8 (plantar placement of the paw without weight support), and 9 (plantar placement of the paw with weight support in stance only).

KSAT Swimming Assessment

Motor recovery as assessed by the BBB can be influenced by the retraining effect[45–47], whereby spontaneous "self-training" occurring in the cage contributes to functional recovery. Factors such as cage size and housing density can influence the activity level of the animals, which may impact the recovery of overground walking. By contrast, swimming performance is not affected by the retraining effect[48], since animals are not normally exposed to swimming in a laboratory setting. Another

potential confounding factor that may affect BBB scores is sensory feedback from below the injury, which can contribute to
motor recovery during overground walking after SCI[49–52]. During swimming, there is an important reduction in sensory
feedback from the hindlimbs compared to overground walking[48,53] since rats rely on buoyancy to support their bodyweight.
The Karolinska Institutet Swim Assessment Tool (KSAT) evaluates swimming parameters including hindlimb movement,
forelimb usage, trunk instability, and body angle. In this assessment, healthy animals achieve a maximum score of 19, based
on intensity and frequency of limb and tail movement. At the first post-operative swim assessment, there were no
differences amongst the experimental groups. After 11 weeks of recovery, rats with the PLO-coated scaffold showed
significant improvements in swimming performance compared to their first post-operative assessment (p=0.0001) (Fig 2B).
By contrast, the animals treated with uncoated scaffolds (p=0.0609) and those without scaffolds (p=0.3361) did not achieve
statistically significant improvement over the course of the study. At the final swimming assessment, the average KSAT score
of rats implanted with PLO-coated scaffolds was 3.79± 0.58 compared to 3.18±0.64 with the uncoated scaffold (ASP group)
and 2.25±0.68 for those without scaffolds (No Tx group). Overall, animals from the PLO and ASP groups showed improvement
in hindlimb movement and trunk stability. Interestingly, the best performing animal from the PLO group attained a KSAT
score of 8, while the highest score achieved in the ASP group was 6 and the highest score in the No Tx group was 5.
159
Inclined Plane test
Before the spinal cord injury, all animals were trained to perform the inclined plane test as described by Rivlin et al[54]. Animals
were placed on an inclined plane and the slope was adjusted to determine the maximum angle at which the animal could
maintain its position without falling. Every 2 weeks after the spinal cord injury, the inclined plane test was performed to
examine sensorimotor recovery. At the final week, there were no significant differences (p= 0.7915) in the performance of
the three experimental groups (Fig 2C). On average, animals reached a maximum angle of 26±1 degrees in the PLO group
(PLO-coated scaffolds), 28±1 degrees in the ASP group (uncoated scaffolds), and 23±3 degrees in the No Tx group (No
scaffold).
168
Retrograde tract tracing of ascending sensory fibers
To elucidate possible mechanisms that may facilitate the observed motor recovery, retrograde tracing was performed on
rats from each experimental group. Neuroanatomical tract tracing is commonly used to visualize sprouting or regeneration
of axons after injury[55–58]. After the recovery period of 11 weeks, Cholera Toxin subunit B (CTb) conjugated to Alexa Fluor 647
was injected into the sciatic nerve to label sensory axons projecting along the dorsal column of the spinal cord. Cross sections
of T10 spinal cord tissue caudal to the injury were imaged by confocal laser scanning microscopy and revealed a distinct CTb-
positive signal in the dorsal column (Fig 3B) which was not found in T6 sections rostral to the injury. Sagittal sections of spinal
cord tissue showed CTb-labelled axons projecting into the caudal side of the scaffold towards the injury epicenter (Fig 3C, D
& E). Compared to animals without a scaffold, those with PLO-coated scaffolds had on average a significantly smaller distance
(p=0.0264) between the furthest rostral CTb-traced axons and the injury epicenter (Fig 3A). This result suggests that the PLO-
coated scaffold enhanced regeneration of axons and/or reduced axon retraction. In animals treated with PLO-coated
scaffolds (Fig 3E), the furthest rostral CTb-labelled axons were identified at an average of 3.2±0.2 mm from the injury
epicenter. By contrast, control animals that did not receive a scaffold had CTb-traced axons at an average distance of 4.8±0.4
mm from the epicenter (Fig 3C). In animals treated with the uncoated scaffold, the average distance of CTb-traced axons
from the epicenter was 3.2±0.3 mm. This tract tracing experiment reveals that sensory axons extend further rostrally in
animals with PLO-coated scaffolds compared to those without a scaffold. However, it is unclear whether those sensory fibers
are regenerated axons or spared fibers that may result from reduced cystic cavitation after injury.
186
Anterograde labeling of the corticospinal tract
Another tract tracing experiment was performed to investigate the regeneration of the hindlimb corticospinal tract (CST),
which is involved in the control of voluntary movement in mammals[59,60]. After the recovery period of 11 weeks, stereotaxic
injections of dextran amine (DA) conjugated to Alexa Fluor 488 were made into the hindlimb motor cortex, which has
descending projections in the spinal cord. Successful tracer uptake was confirmed by confocal laser scanning microscopy of
T6 spinal cord cross-sections rostral to the injury, which showed strong positive dextran amine labelling of axons in the
corticospinal tract (Fig 4B). In sagittal sections, dextran amine-labeled axons were identified at the rostral interface between
the biomaterial and spinal cord (Fig 4D & E), though none were present in T10 cord sections caudal to the injury. The most
caudal DA-labelled axons were identified at an average distance of 0.33±0.4 mm from the epicenter for animals with PLO-
coated scaffolds (Fig 4E), 0.45±0.3 mm from the epicenter for those with the uncoated scaffold (Fig 4D), and 1.6±0.1 mm
from the epicenter for animals without a scaffold (Fig 4C). Although no significant difference in CST axon extension was found
between the experimental groups, DA-traced axons were seen projecting along the dorsal side of the PLO-coated cellulose
biomaterial towards the caudal spinal cord (Fig 4E).
200
201

Neural cell infiltration and axonal sprouting inside cellulose biomaterial

Histological analysis of spinal cord tissue revealed host cell infiltration into the scaffolds from the rostral and caudal interface. Within the scaffold, both cell bodies and axonal projections expressing β-III tubulin, an early neuronal marker, were identified (Fig 5A & B). This finding suggests that endogenous adult neural stem cells infiltrated the biomaterial and initiated differentiation towards neural lineages. In addition, a substantial number of NF200-positive cells were observed inside the scaffold and surrounding tissue (Fig 5C). In both PLO-coated and uncoated scaffolds, NF200-positive cells densely clustered at the outermost edge of the scaffold and some NF200-positive neurites extended into its channels. To determine the effect of PLO coating on infiltration of NF200-positive cells, the distance of infiltration into the channels was measured from the scaffold edge towards the injury epicenter in NF200-stained sagittal sections. NF200-positive cells penetrated significantly further into the channels of PLO-coated scaffolds compared to those without the coating (p=0.0286, Fig 5F). On average, the longest distance of NF200-positive cell infiltration was 388.8±154.5µm into the PLO-coated scaffolds and 215.6±22.3µm in the uncoated scaffolds. However, the percentage of channels infiltrated by cells did not differ between the two conditions (p=0.8286). In PLO coated scaffolds, 93±0.8% of the channels were infiltrated by NF200-positive cells, on average, and uncoated scaffolds had 93±2% of their channels infiltrated. Interestingly, at the rostral and caudal interfaces of the biomaterial we observed a cluster of neurofilament-positive projections branching from the dorsal to ventral aspect of the spinal cord, perpendicular to the axis of the tracts (Fig 5D).

Finally, tissue sections from each experimental group were stained with luxol fast blue (LFB) to evaluate axon myelination in the injury site (Fig 6 and Supplementary Figure 2). As expected with a traumatic spinal cord injury, severe degeneration of myelin was observed in the perilesional tissue, consistent with Wallerian degeneration. However, in animals that received a PLO-coated scaffold, dark blue bands of LFB staining were consistently observed at the rostral and caudal interface of the PLO-coated scaffold and tissue, indicating possible remyelination induced by the poly-L-ornithine (Fig 6A). Although we did not quantify this observation, several images from different animals are provided in Supplementary Figure 2.

Discussion

Complete SCI leads to the loss of both sensorimotor and autonomic function distal to the injury site due to the interruption of ascending and descending pathways. Regrowth of axons and restoration of appropriate synaptic connectivity after SCI remains a major medical challenge. Various therapeutic strategies have attempted to induce sprouting of the corticospinal tract or to establish relay neural circuits that can mediate functional recovery[61,62]. Neural circuits in the injured spinal cord are known to exhibit plasticity after treadmill training[63] or electrical epidural stimulation[64] that can produce some degree of motor recovery. However, irregular synaptic connectivity after SCI can be maladaptive and lead to spasticity or neuropathic pain[65]. In recent decades, biomaterial-based therapeutic strategies for SCI have been explored as a means to support axonal growth and deliver cells or pharmaceuticals locally to modulate the inhibitory milieu of the lesion. For instance, some groups have produced bioactive scaffolds that use cell signaling molecules to enhance axonal regrowth, myelination, and functional recovery[20] while others have 3D printed scaffolds with microarchitectures that mimic the structures in the spinal cord to support the formation of neural relays[19]. As well, several scaffolds have been used as carriers to deliver various types of stem cells to the injured cord to promote repair[66].

In the present study, we investigated the ability of naturally occurring microarchitectures found in plant-derived scaffolds to provide physical support to regenerating axons and guide their extension across a lesion in the spinal cord. Our results show that plant cellulose can become vascularized after implantation into the spinal cord and that endogenous neural cells expressing β-III tubulin and NF200 readily migrate into the channels of the scaffold in a linear orientation along the rostral-to-caudal axis. Aside from directing the extension of regenerating axons, the biomaterial may have contributed to motor recovery by its interaction with astrocytes, which are known to play a key role in SCI pathology. After SCI, activated microglia induce changes in the gene expression and morphology of astrocytes surrounding the lesion. The process of reactive astrogliosis is controlled by complex signaling pathways, notably NFκB or TGF-β signaling[67], and eventually leads to the formation of a dense glial scar. We found positive immunostaining for glial fibrillary acidic protein (GFAP) in sagittal spinal cord sections from each experimental group (Supplementary Figure 3). In all animals, GFAP expression was observed in the tissue rostral and caudal to the injury, with little to no GFAP visible in the injury epicenter. By occupying space in the injury site, the cellulose scaffold may have reduced the number of reactive astrocytes migrating into the lesion and interfered with signaling mechanisms involved in the propagation of reactive astrogliosis, thereby attenuating tissue damage and enhancing motor ability. In addition, the presence of channels at the surface of the cellulose scaffolds may have affected the alignment and morphology of astrocytes in the injury site, as previous reports have shown that cytoskeletal modulation in astrocytes can be induced by microgrooves[68].

We tested the ability of plant-derived cellulose scaffolds to support repair in combination with a coating of poly-L-
ornithine, a positively charged synthetic amino acid that adheres to cellulose by electrostatic interactions. PLO is commonly
used in neural stem cell culture and previous studies have demonstrated its ability to improve cell attachment and
migration[69,70]. Specifically, PLO was shown to promote filopodia formation in neural progenitors in vitro[70] by increasing the
expression of α-Actinins 4, a critical effector of structural plasticity. Based on this, we hypothesized that PLO may have a
similar effect in vivo after SCI and that increased sprouting of severed axons could assist in establishing neural relays across
the scaffold, thereby mediating functional recovery.
264
We found that animals implanted with the uncoated cellulose scaffold had a modest recovery of motor function in
the BBB assessment and this recovery was enhanced by the addition of the poly-L-ornithine coating. By contrast, no
significant recovery of motor function was observed amongst the No Tx animals during the recovery period. Despite the
motor improvements seen in biomaterial-treated animals, we did not find evidence of serotonergic activity below the injury.
Immunohistochemistry staining for 5-HT revealed some sprouting of serotonergic axons, though positive 5-HT staining was
limited to tissue on the rostral side of the complete transection in all experimental groups (Supplementary Figure 4). To
investigate possible axon regeneration which may contribute to the observed motor recovery, we performed retrograde
tract tracing by injecting CTb into the sciatic nerve. This neural tract tracing experiment demonstrated that sensory axons
extended a greater distance into the injury site in animals with PLO-coated scaffolds compared to those without a scaffold.
Our findings are consistent with those of Schackel et al, who found that PLO/laminin-coated hydrogels implanted in animals
with a cervical hemisection had increased host cell migration and a slight increase in neurite growth[69]. Further experiments
may elucidate the mechanism by which the PLO-coated scaffold produced this effect. It is unclear whether the CTb-traced
sensory fibers in the injury site are regenerated axons or spared fibers that may result from reduced axonal retraction after
injury. We speculate that the presence of the cellulose scaffold in the injury site may slightly reduce cystic cavitation, thereby
mitigating further axon retraction after injury. In addition, it is possible that the PLO coating promoted neurite extension, as
demonstrated by other works[69–71]. Similarly, the immunostaining experiments we performed on sagittal sections of the
scaffold after 12-weeks in vivo revealed NF200-positive cells migrating further into the channels of scaffolds with the PLO
coating compared to the uncoated biomaterial. Taken together, our results highlight the potential of plant-derived scaffolds,
though further work is necessary to optimize therapeutic strategies using these biomaterials with PLO or other peptides to
further enhance neural cell infiltration to potentially enable communication between circuits below and above the injury.
285
The differences we identified in the sensory axons in PLO-treated animals could possibly have contributed to their
recovery in motor ability, given the importance of sensory feedback in motor function after SCI[49,50,72,73]. To test whether
these axons serve as the substrate for functional recovery, further experiments could be performed to assess the
functionality of theses regenerated sensory fibers and to identify whether they have relevant synaptic contacts. In addition
to sprouting of sensory axons, we found enhanced myelination in the injury site of animals with PLO-coated scaffolds, as
evidenced by the luxol fast blue staining showing myelin in the scaffold periphery. In a recent study, the ability of PLO to
enhance myelin repair was demonstrated in an animal model of focal demyelination[74]. We speculate that myelin repair may
be a contributing mechanism underlying PLO-induced motor recovery in our SCI model. Further, the positive effect of PLO
on myelination in the injury site may be two-fold, as myelin breakdown products are known to be inhibitors of neuronal
plasticity. Hence, by enhancing remyelination, PLO may also be creating a more permissive environment for axonal sprouting,
consistent with our observations. In future experiments, plant cellulose scaffolds could be seeded with stem cells,
functionalized with neurotrophins or axon guidance molecules such as netrins or ephrins to further promote regeneration
of axons through the scaffold.
299
Environmental enrichment (EE) was included as part of our multifaceted neurorehabilitation strategy due to its
ability to enhance neuroplasticity and attenuate SCI-induced neuropathic pain [75–77]. Environmental enrichment is a housing
manipulation that includes novel toys, tunnels, nesting materials, puzzles, and running wheels along with opportunities for
socialization with conspecifics. By enhancing plasticity, enriched environments support functional improvements in animal
models of stroke and SCI[75–82]. Studies have indicated that EE promotes plasticity through various mechanisms including
increased production of neurotrophic factors and changes in dendritic-spine density [83]. In rodent SCI models, enrichment
potentiates the regenerative ability of neurons via Creb-binding protein-mediated histone acetylation, which increases
expression of regeneration-associated genes[81]. Many groups have reported that environmental enrichment substantially
improves sensory and motor recovery after contusive SCI[75,77]. Similarly, in animal models of stroke, exposure to an enriched
environment causes neuroanatomical changes including dendritic remodeling, axonal sprouting, and the release of growth
factors [84]. It has also been reported that environmental enrichment may promote white matter recovery after stroke by
reducing microglia activation[85]. Altogether, environmental enrichment shows great promise as part of a multimodal SCI
therapeutic strategy. In the present study, all animals were housed with EE and no standard housing (SH) controls were
included, since SH is an impoverished environment that is not representative of the conditions of human SCI patients. In

addition to improving animal welfare throughout the study, we speculate that the enriched environment may have
contributed to the growth of axons after SCI by expanding the regenerative ability of sensory neurons, as previously
reported[76]. Enrichment has been explored as a therapeutic modality for stroke and traumatic brain injury, with results
suggesting it may act synergistically with other treatments to enhance functional outcomes[86]. However, it is possible that
enrichment in our study overshadowed the benefits of the PLO-coated scaffold alone.
319
This study demonstrated the potential of plant-derived cellulose scaffolds to be functionalized with peptides and
used in a multimodal SCI therapeutic strategy that includes environmental enrichment. We found that coating the
biomaterial with poly-L-ornithine supported hindlimb motor recovery and neural tissue repair in a rat model of complete
transection. The biomaterial was infiltrated by endogenous neural cells, which migrated along the linearly oriented channels
of the plant scaffold. Retrograde neural tracing highlighted regeneration of sensory tracts in the spinal cord after treatment
with PLO-coated scaffolds. Overall, our results point to exciting potential patient-treatment strategies that use plant-derived
scaffolds in combination with other therapeutics.
327

Methods

Biomaterial production: Cellulose scaffolds were prepared using a 4 mm diameter biopsy punch to cut Asparagus officinalis
sections which were then placed into a 50ml Falcon tube containing 0.1% sodium dodecyl sulphate (SDS) (Sigma-Aldrich).
Samples were shaken for 72 hours at 180 RPM at room temperature. The resulting cellulose scaffolds were then transferred
into new sterile microcentrifuge tubes, washed and incubated for 12 hours in phosphate-buffered saline (PBS). Following the
PBS washing steps, the asparagus were then incubated in 100 mM $CaCl_2$ for 24 hours at room temperature and washed 3
times with dH_2O. Samples were then sterilized in 70% ethanol overnight. Finally, scaffolds were washed 12 times in a sterile
saline solution before incubating overnight in a 100μg/ml solution of poly-L-ornithine (30-70kDa, Sigma-Aldrich, P3655).
337

Animal Housing and Environmental Enrichment: All procedures described were approved and performed in accordance with
standards set out by the University of Ottawa Animal Care and Veterinary Services ethical review committee. Juvenile female
Sprague Dawley rats were purchased from Charles River. Rat tickling was performed with the juvenile rats as a habituation
technique to improve welfare. Experimenters followed the Panksepp method[87] of rat tickling which consists of 15 sec rest
followed by 15 sec of dorsal contacts and pins for a total of 2 minutes for 4 days of training. Upon completing tickle training,
every rat was tickled before every procedure. Clicker training was performed with the juvenile rats to encourage cooperation
in all behavioral assays and to develop positive affect with experimenters. Briefly, rats were encouraged to step onto a plastic
platform and given food rewards upon successful completion, accompanied by a 'click'. Clicker training was done for 5 days
(4 mins daily). All rats were housed in pairs throughout the study and got 20 minutes of daily group play with conspecifics.
During group play, up to 10 rats were placed in a 1-meter diameter arena with climbing structures, tunnels, foraging toys,
food enrichment and nesting material. Enrichment was provided in all rats' home cages, including a wooden block, nylon
bone (Bio-Serv, K3580), bunny block (Bio-Serv, F05274) and metal swing. In addition to a diet of standard rat chow, all rats
were given daily food enrichment including mini yogurt drops (Cedarlane Bio-Serve, F7577), banana chips (Cedarlane Bio-
Serve F7161), fruity bites (Cedarlane Bio-Serve F6038), ABC fruit blend (Cedarlane Bio-Serve F7228), Mealworms (Cedarlane
Bio-Serve 9264), veggie-bites (Cedarlane Bio-Serve F5158) and pumpkin (E.D. Smith).

Spinal Cord Transection Surgical Procedure: Once rats reach a weight of 250-300g, they are anesthetized with isoflurane
USP-PPC and injected subcutaneously with normal saline (Baxter) and enrofloxacin (Baytril). Laminectomies were performed
at the T8-T9 level to expose the spinal cord, followed by a dorsal midline durotomy. The entire cord was gently lifted by a
hook before cutting with micro scissors. Surgifoam 1972 (Ethicon) was used to establish hemostatic control, then the gap
was measured after 10 minutes to select the appropriately sized cellulose implant. Prior to surgery, animals were be split
into four groups: sham (laminectomy only, n=2), No Tx (full transection only, no scaffold, n=8), ASP treated (cellulose implant
only, n=9), and PLO treated (PLO-coated cellulose implant, n= 11). PLO-coated scaffolds were rinsed twice with sterile water
before implantation. While implanting the scaffold, ARTISS fibrin sealant (Baxter) was be applied into the cavity. The muscle
and adipose tissue are reapproximated with 3-0 Vicryl sutures (Johnson & Johnson) and the skin was closed with Michel clips
(Fine Science Tools). Rats received post-operative care including bladder expressions 4 times daily, pain monitoring and
management with buprenorphine HCl, when necessary, weight loss and dehydration tracking.

BBB Locomotor Assessment: Functional recovery of the hindlimbs was assessed by a weekly BBB open field assessment.[88]
Each rat was placed in a 1-meter diameter arena covered with a non-slippery floor and recorded by 5 cameras. The 4-minute
videos were then scored by three blinded observers and the average of three examiners was calculated for each animal at

each timepoint. Spasticity and movement occurring simultaneously with urination was ignored and confirmed with repeated views of the videos. Two weeks after receiving the spinal cord injury, one animal was excluded based on their BBB score, which was above 5.

KSAT Swim Assessment: Before SCI, all rats were acclimatized to the pool daily (up to 5 minutes) for 5 days. During this pre-training, each rat was placed into a clear acrylic swim tank (depth 20cm, length 150cm) filled with water (27-30℃) and encouraged to swim via clicker training. Animals with poor performance were excluded from the study before the SCI surgery. After rats sustained a SCI, the swim assessment was performed every 2 weeks to assess functional recovery. Each animal was allowed three runs across the swim tank with 20 second rests between runs. Swimming was recorded by 4 cameras and videos were scored by 3 blind observers using the Karolinska Institutet Swim Assessment Tool (KSAT).[53]

Inclined Plane Assessment: Before the spinal cord injury, all animals were trained to perform the inclined plane test as described by Rivlin et al[54]. Each rat was placed on an inclined plane while adjusting the slope to determine the maximum angle at which the animal can maintain its position without falling. Every 2 weeks after the spinal cord injury, the inclined plane test was performed to examine sensorimotor recovery.

Retrograde Tract Tracing of Ascending Sensory Afferents: Animals also received 2uL of Cholera Toxin Subunit B conjugated to Alexa Fluor 647 (CTb, ThermoFisher, cat. C34778, 1% solution in sterile PBS) injected bilaterally into their sciatic nerves (4uL total per rat). Rats were anesthetized with 3% isoflurane, a linear incision was made along the femur, and the gluteus maximus was separated from the gluteus medius to expose the sciatic nerve. Using a surgical microscope, a nick was made in the proximal portion of the exposed nerve. The CTb solution was loaded into a Hamilton syringe, and the needle was inserted 5mm into the sciatic nerve. CTb was injected in increments of 0.5μL, waiting 30 seconds and withdrawing the needle by 1mm per injection. Once the injection was complete, a sterile Q-tip was used to remove any CTb that was expelled from the nerve and the incision was sutured using 4-0 Prolene sutures. Post-operatively, 2% bupivacaine was applied topically and animals were given buprenorphine (0.05mg/kg subcutaneously) and Gabapentin (Chiron, 50mg/kg subcutaneously) for analgesia. Pain was assessed TID and additional buprenorphine was administered as necessary. To prevent infections, Enrofloxacin (Bayer, 10mg/kg subcutaneously) was administered daily for 3 days peri-operatively.

Anterograde Labeling of the Corticospinal Tract: 11 weeks post-operatively, rats from each group were injected with neural tracers to visualize axons in and around the injury site. Animals were anesthetized with 3% isoflurane and placed into a stereotactic frame. After a surgical scrub, a sagittal incision was made to expose the top of the skull and the periosteum was scraped off. Using a Zeiss surgical microscope, the skull was levelled by measuring the Dorsal-Ventral axis at 4 random points and ensuring they are within 0.05mm of each other. Bregma was located and its coordinates were used to calculate the target location of each injection. Using a surgical drill (Micro Drill, Harvard Apparatus) attached to the stereotactic frame, 8 holes were drilled into the cranium. Stereotactic injections were made into the right and left motor cortex at coordinates: Injection 1: Anterior-posterior (AP) -0.5mm, Medial-lateral (ML) ±2mm, Dorsal-Ventral (DV) 1.5mm. Injection 2: Anterior-posterior (AP) -1mm, Medial-lateral (ML) ±2.5mm, Dorsal-Ventral (DV) 1.5mm. Injection 3: Anterior-posterior (AP) -1.5mm, Medial-lateral (ML) ±2mm, Dorsal-Ventral (DV) 1.5mm. Injection 4: Anterior-posterior (AP) -2mm, Medial-lateral (ML) ±2.5mm, Dorsal-Ventral (DV) 1.5mm. Injections were made using a 5uL Hamilton syringe. After a 2-minute delay, a volume of 0.5μL of 10% Dextran Amine Alexa Fluor 488 (ThermoFisher, cat. D22910, 10,000 MW) was injected into each location at a rate of 250nl/min for a total injection volume of 4μL per rat. Each injection was followed by a 2-minute delay to ensure diffusion into the tissue. Once all 8 injections were complete, the scalp was sutured with 4-0 Prolene sutures and 2% transdermal bupivacaine was applied to the incision. Animals had 2 weeks of recovery time before euthanasia to allow for transport of neural tracers. For tissue collection, animals were deeply anesthetized with isoflurane USP-PPC and euthanized by cardiac perfusion with 500ml of 1xPBS followed by 500ml of 4% paraformaldehyde. The brain and spinal cord were dissected out and fixed overnight in 4% paraformaldehyde at 4°C, then stored in 70% ethanol at 4°C until embedding and sectioning.

Quantification of neuroanatomical tract tracing: Cross-sections of spinal cord tissue above and below the injury site were imaged by confocal laser scanning microscopy to confirm successful tracer uptake. For retrograde tracing, CTb-traced axons were seen in the dorsal columns of T10 cross-sections. For anterograde tracing, dextran amine labelled axons were identified within the corticospinal tract of T6 cross-sections. For each animal, 3 sagittal sections in the middle of the cord were imaged by confocal laser scanning microscopy and the distance between the tracers and the injury epicenter was measured using ImageJ (See supplementary Figure 5). For retrograde tracing with CTb (n= 4 PLO animals, n=2 ASP animals, n=3 No Tx animals), the distance (mm) was measured between the furthest rostral CTb-traced axon and the injury epicenter. For anterograde tracing with dextran amine (n=4 PLO animals, n=4 ASP animals, n=3 No Tx animals), the distance (mm) was

measured between the furthest caudal dextran amine-traced axon and the injury epicenter. In animals implanted with a scaffold, the injury epicenter was deemed to be at the mid-point of the scaffold (½ the total length of the scaffold). In 'no scaffold' control animals, the injury epicenter was deemed to be at the mid-point of the syrinx at the lesion site (½ the total length of the cyst). Averages were calculated for each group and a one-way ANOVA was performed.

GFAP Immunostaining: Paraformaldehyde-fixed paraffin-embedded tissue sections (5μm thick) were deparaffinized and pre-treated using heat-mediated antigen retrieval with Sodium Citrate buffer (pH 6.0). Slides were then rehydrated in 1X TBST buffer and blocked for 30 minutes with Rodent Block R (Biocare RBR962H). Sections were then incubated with Rabbit GFAP (1:3000, Sigma AB5804) at room temperature for 1.5 hours. Sections were washed with 1XTBST and then incubated with the Goat anti-Rabbit-488 antibody for 2 hours in the dark at room temperature. This was followed by incubation with a quencher (Vector TrueView Autofluorescence Quenching Kit #SP-8400, Vector Labs) to decrease autofluorescence. Sections were then washed, incubated with 5 ug/ml of DAPI (ThermoScientific #62248) and coverslipped.

β-III Tubulin Immunostaining: Paraformaldehyde-fixed paraffin-embedded tissue sections (5μm thick) were deparaffinized and tissue was permeabilized at room temperature (5 mins) the following buffer: 0.5% Triton-X, 20mM HEPES, 300mM Sucrose, 50mM NaCl, 3mM $MgCl_2$, 0.05% sodium azide. Sections were incubated in blocking buffer (6% Normal Goat Serum in 1xPBS) for 10 minutes. Sections were rinsed twice in 1xPBS before incubation at 4℃ overnight in mouse anti-β-III tubulin antibody (10ug/ml, MAB1195, R&D systems). The following day, after 2 washes of 1xPBS, sections were incubated at room temperature (2.5 hours) in goat anti-mouse alexa Fluor 594 polyclonal antibody (1:200, A11005, Thermofisher) and counterstained with Hoescht (1:2000).

Neurofilament 200 Immunostaining: Paraformaldehyde-fixed paraffin-embedded tissue sections (5μm thick) were deparaffinized and tissue was permeabilized at room temperature (3x 5 minutes) in 1X TBST. Sections were incubated in blocking buffer (5% Normal Goat Serum in 1X TBST) for 30 minutes followed by 3 washes in 1X TBST. Tissue was incubated at 4℃ overnight in rabbit anti-NF200 (1:3000 dilution in 1X PBS, cat. N4142 Sigma). The following day, after 2 washes of 1X PBS, sections were incubated at room temperature (2 hours) in goat anti-rabbit alexa fluor 488 (cat. A11008 Thermofisher) and counterstained with Hoescht (1:2000).

5-HT Immunohistochemistry: Paraformaldehyde-fixed paraffin-embedded tissue sections (5μm thick) were deparaffinized and incubated in rabbit anti-serotonin antibody (1:2500 dilution in 1X PBS, Sigma S5545) for 2 hours. Immunohistochemistry was performed using DAB as the chromogen and counterstained with Hoescht (1:2000).

Statistical Analysis: Experimental data were analyzed using GraphPad Prism. For the distance of infiltration of NF200-positive cells, the differences between two groups were compared utilizing the Student's t-test at a significance level of $P < 0.05$ & the Mann Whitney test was performed. Differences between multiple groups were compared by one way ANOVA followed by Tukey's multiple comparisons test (for neuroanatomical tract tracing) or the uncorrected Fisher's LSD (for BBB locomotor assessment) at a significance level of $P < 0.05$.

References

1. Zheng, B. & Tuszynski, M. H. Regulation of axonal regeneration after mammalian spinal cord injury. *Nat Rev Mol Cell Biol* (2023) doi:10.1038/s41580-022-00562-y.

2. Johansson, C. B. *et al.* Identification of a Neural Stem Cell in the Adult Mammalian Central Nervous System. *Cell* **96**, 25–34 (1999).

3. Lacroix, S. *et al.* Central Canal Ependymal Cells Proliferate Extensively in Response to Traumatic Spinal Cord Injury but Not Demyelinating Lesions. *PLoS One* **9**, e85916 (2014).

4. Li, J. *et al.* Recent advances in endogenous neural stem/progenitor cell manipulation for spinal cord injury repair. *Theranostics* **13**, 3966–3987 (2023).

5.　Barnabé-Heider, F. *et al.* Origin of New Glial Cells in Intact and Injured Adult Spinal Cord. *Cell Stem Cell* **7**, 470–482
(2010).

6.　Meletis, K. *et al.* Spinal Cord Injury Reveals Multilineage Differentiation of Ependymal Cells. *PLoS Biol* **6**, e182
(2008).

7.　Hachem, L. D. & Fehlings, M. G. Pathophysiology of Spinal Cord Injury. *Neurosurg Clin N Am* **32**, 305–313 (2021).

8.　McKerracher, L. & Rosen, K. M. MAG, myelin and overcoming growth inhibition in the CNS. *Front Mol Neurosci* **8**,
(2015).

9.　Lee, J. K. & Zheng, B. Role of myelin-associated inhibitors in axonal repair after spinal cord injury. *Exp Neurol* **235**,
33–42 (2012).

10.　Chambel, S. S. & Cruz, C. D. Axonal growth inhibitors and their receptors in spinal cord injury: from biology to
clinical translation. *Neural Regen Res* **18**, 2573–2581 (2023).

11.　Wang, J. *et al.* Nogo-A expression dynamically varies after spinal cord injury. *Neural Regen Res* **10**, 225 (2015).

12.　Hyatt, A. J. T., Wang, D., Kwok, J. C., Fawcett, J. W. & Martin, K. R. Controlled release of chondroitinase ABC from
fibrin gel reduces the level of inhibitory glycosaminoglycan chains in lesioned spinal cord. *Journal of Controlled*
Release **147**, 24–29 (2010).

13.　Karimi-Abdolrezaee, S., Schut, D., Wang, J. & Fehlings, M. G. Chondroitinase and Growth Factors Enhance Activation
and Oligodendrocyte Differentiation of Endogenous Neural Precursor Cells after Spinal Cord Injury. *PLoS One* **7**,
(2012).

14.　Díaz-Galindo, M. del C., Calderón-Vallejo, D., Olvera-Sandoval, C. & Quintanar, J. L. Therapeutic approaches of
trophic factors in animal models and in patients with spinal cord injury. *Growth Factors* **38**, 1–15 (2020).

15.　Bregman, B. S. *et al.* Chapter 18 Transplants and neurotrophic factors increase regeneration and recovery of
function after spinal cord injury. in 257–273 (2002). doi:10.1016/S0079-6123(02)37020-1.

16.　Liu, Q. *et al.* Electric field stimulation boosts neuronal differentiation of neural stem cells for spinal cord injury
treatment via PI3K/Akt/GSK-3β/β-catenin activation. *Cell Biosci* **13**, 4 (2023).

17.　Sasaki, M., Lankford, K. L., Zemedkun, M. & Kocsis, J. D. Identified Olfactory Ensheathing Cells Transplanted into the
Transected Dorsal Funiculus Bridge the Lesion and Form Myelin. *The Journal of Neuroscience* **24**, 8485–8493
(2004).

18.　Keirstead, H. S. *et al.* Human Embryonic Stem Cell-Derived Oligodendrocyte Progenitor Cell Transplants
Remyelinate and Restore Locomotion after Spinal Cord Injury. *The Journal of Neuroscience* **25**, 4694–4705 (2005).

19.　Koffler, J. *et al.* Biomimetic 3D-printed scaffolds for spinal cord injury repair. *Nat Med* **25**, 263–269 (2019).

20.　Álvarez, Z. *et al.* Bioactive scaffolds with enhanced supramolecular motion promote recovery from spinal cord
injury. *Science (1979)* **374**, 848–856 (2021).

21.   Meshkini, A. *et al.* Combined treatment with Minocycline and methylprednisolone in acute traumatic spinal cord
492   Injury: A pilot study. *Interdisciplinary Neurosurgery* **36**, 101883 (2024).

493   22.   García, E. *et al.* Recent advances in the combination of cellular therapy with stem cells and nanoparticles after a
494   spinal cord injury. *Front Neurol* **14**, (2023).

495   23.   Liu, S., Xie, Y.-Y. & Wang, B. Role and prospects of regenerative biomaterials in the repair of spinal cord injury.
496   *Neural Regen Res* **14**, 1352 (2019).

497   24.   Shen, H. *et al.* Advances in Biomaterial-Based Spinal Cord Injury Repair. *Adv Funct Mater* **32**, (2022).

498   25.   Flanagan, L. A., Rebaza, L. M., Derzic, S., Schwartz, P. H. & Monuki, E. S. Regulation of human neural precursor cells
499   by laminin and integrins. *J Neurosci Res* **83**, 845–856 (2006).

500   26.   Joseph, G., Orme, R. P., Kyriacou, T., Fricker, R. A. & Roach, P. Effects of Surface Chemistry Interaction on Primary
501   Neural Stem Cell Neurosphere Responses. *ACS Omega* **6**, 19901–19910 (2021).

502   27.   Kubinová, Š. & Syková, E. Nanotechnologies in regenerative medicine. *Minimally Invasive Therapy & Allied*
503   *Technologies* **19**, 144–156 (2010).

504   28.   Estrada, V. *et al.* Long-lasting significant functional improvement in chronic severe spinal cord injury following scar
505   resection and polyethylene glycol implantation. *Neurobiol Dis* **67**, 165–179 (2014).

506   29.   Slotkin, J. R. *et al.* Biodegradable scaffolds promote tissue remodeling and functional improvement in non-human
507   primates with acute spinal cord injury. *Biomaterials* **123**, 63–76 (2017).

508   30.   Breen, B. A. *et al.* Therapeutic Effect of Neurotrophin-3 Treatment in an Injectable Collagen Scaffold Following Rat
509   Spinal Cord Hemisection Injury. *ACS Biomater Sci Eng* **3**, 1287–1295 (2017).

510   31.   Li, X. *et al.* A collagen microchannel scaffold carrying paclitaxel-liposomes induces neuronal differentiation of neural
511   stem cells through Wnt/β-catenin signaling for spinal cord injury repair. *Biomaterials* **183**, 114–127 (2018).

512   32.   Xiao, Z. *et al.* Significant Improvement of Acute Complete Spinal Cord Injury Patients Diagnosed by a Combined
513   Criteria Implanted with NeuroRegen Scaffolds and Mesenchymal Stem Cells. *Cell Transplant* **27**, 907–915 (2018).

514   33.   Davidenko, N. *et al.* Control of crosslinking for tailoring collagen-based scaffolds stability and mechanics. *Acta*
515   *Biomater* **25**, 131–142 (2015).

516   34.   Peng, W. *et al.* Recent progress of collagen, chitosan, alginate and other hydrogels in skin repair and wound
517   dressing applications. *Int J Biol Macromol* **208**, 400–408 (2022).

518   35.   Contessi Negrini, N., Toffoletto, N., Farè, S. & Altomare, L. Plant Tissues as 3D Natural Scaffolds for Adipose, Bone
519   and Tendon Tissue Regeneration. *Front Bioeng Biotechnol* **8**, (2020).

520   36.   Chen, F. *et al.* Natural *Flammulina velutipes* -Based Nerve Guidance Conduit as a Potential Biomaterial for
521   Peripheral Nerve Regeneration: In Vitro and In Vivo Studies. *ACS Biomater Sci Eng* **7**, 3821–3834 (2021).

522   37.   Lee, J., Jung, H., Park, N., Park, S.-H. & Ju, J. H. Induced Osteogenesis in Plants Decellularized Scaffolds. *Sci Rep* **9**,
523   20194 (2019).

38.   Bilirgen, A. C. *et al.* Plant-Based Scaffolds in Tissue Engineering. *ACS Biomater Sci Eng* **7**, 926–938 (2021).

39.   Modulevsky, D. J., Cuerrier, C. M. & Pelling, A. E. Biocompatibility of Subcutaneously Implanted Plant-Derived
Cellulose Biomaterials. *PLoS One* **11**, e0157894 (2016).

40.   Hickey, R. J. & Pelling, A. E. Cellulose Biomaterials for Tissue Engineering. *Front Bioeng Biotechnol* **7**, (2019).

41.   Hickey, R. J., Modulevsky, D. J., Cuerrier, C. M. & Pelling, A. E. Customizing the Shape and Microenvironment
Biochemistry of Biocompatible Macroscopic Plant-Derived Cellulose Scaffolds. *ACS Biomater Sci Eng* **4**, 3726–3736
(2018).

42.   Fontana, G. *et al.* Biofunctionalized Plants as Diverse Biomaterials for Human Cell Culture. *Adv Healthc Mater* **6**,
1601225 (2017).

43.   Couvrette, L. J., Walker, K. L. A., Bui, T. V. & Pelling, A. E. Plant Cellulose as a Substrate for 3D Neural Stem Cell
Culture. *Bioengineering* **10**, 1309 (2023).

44.   Toker-Bayraktar, M., Erenay, B., Altun, B., Odabaş, S. & Garipcan, B. Plant-derived biomaterials and scaffolds.
Cellulose **30**, 2731–2751 (2023).

45.   Burke, D. A., Morehouse, J. R., Saraswat Ohri, S. & Magnuson, D. S. K. Unintentional Effects from Housing
Enhancement Resulting in Functional Improvement in Spinal Cord–Injured Mice. *Neurotrauma Rep* **4**, 71–81 (2023).

46.   Starkey, M. L. *et al.* High-Impact, Self-Motivated Training Within an Enriched Environment With Single Animal
Tracking Dose-Dependently Promotes Motor Skill Acquisition and Functional Recovery. *Neurorehabil Neural Repair*
28, 594–605 (2014).

47.   Battistuzzo, C. R., Callister, R. J., Callister, R. & Galea, M. P. A Systematic Review of Exercise Training To Promote
Locomotor Recovery in Animal Models of Spinal Cord Injury. *J Neurotrauma* **29**, 1600–1613 (2012).

48.   Smith, R. R. *et al.* The Louisville Swim Scale: A Novel Assessment of Hindlimb Function following Spinal Cord Injury
in Adult Rats. *J Neurotrauma* **23**, 1654–1670 (2006).

49.   Takeoka, A. Proprioception: Bottom-up directive for motor recovery after spinal cord injury. *Neurosci Res* **154**, 1–8
(2020).

50.   Takeoka, A., Vollenweider, I., Courtine, G. & Arber, S. Muscle Spindle Feedback Directs Locomotor Recovery and
Circuit Reorganization after Spinal Cord Injury. *Cell* **159**, 1626–1639 (2014).

51.   Bouyer, L. J. G. & Rossignol, S. Contribution of Cutaneous Inputs From the Hindpaw to the Control of Locomotion. I.
Intact Cats. *J Neurophysiol* **90**, 3625–3639 (2003).

52.   Park, H. *et al.* Cutaneous sensory feedback from paw pads affects lateral balance control during split-belt
locomotion in the cat. *Journal of Experimental Biology* (2019) doi:10.1242/jeb.198648.

53.   Xu, N., Åkesson, E., Holmberg, L. & Sundström, E. A sensitive and reliable test instrument to assess swimming in
rats with spinal cord injury. *Behavioural Brain Research* **291**, 172–183 (2015).

54.   Rivlin, A. S. & Tator, C. H. Objective clinical assessment of motor function after experimental spinal cord injury in
the rat. *J Neurosurg* **47**, 577–581 (1977).

55.   Hellenbrand, D. J. *et al.* Basic techniques for long distance axon tracing in the spinal cord. *Microsc Res Tech* **76**,
1240–1249 (2013).

56.   Kim, D. *et al.* Inosine Enhances Axon Sprouting and Motor Recovery after Spinal Cord Injury. *PLoS One* **8**, e81948
(2013).

57.   Saleeba, C., Dempsey, B., Le, S., Goodchild, A. & McMullan, S. A Student's Guide to Neural Circuit Tracing. *Front
Neurosci* **13**, (2019).

58.   Reiner, A. *et al.* Pathway tracing using biotinylated dextran amines. *J Neurosci Methods* **103**, 23–37 (2000).

59.   Schieber, M. H. Chapter 2 Comparative anatomy and physiology of the corticospinal system. in 15–37 (2007).
doi:10.1016/S0072-9752(07)80005-4.

60.   Ueno, M. *et al.* Corticospinal Circuits from the Sensory and Motor Cortices Differentially Regulate Skilled
Movements through Distinct Spinal Interneurons. *Cell Rep* **23**, 1286-1300.e7 (2018).

61.   Jin, D. *et al.* Restoration of skilled locomotion by sprouting corticospinal axons induced by co-deletion of PTEN and
SOCS3. *Nat Commun* **6**, 8074 (2015).

62.   Lai, B.-Q. *et al.* Stem cell-derived neuronal relay strategies and functional electrical stimulation for treatment of
spinal cord injury. *Biomaterials* **279**, 121211 (2021).

63.   Shah, P. K. *et al.* Use of quadrupedal step training to re-engage spinal interneuronal networks and improve
locomotor function after spinal cord injury. *Brain* **136**, 3362–77 (2013).

64.   Ichiyama, R. M., Gerasimenko, Yu. P., Zhong, H., Roy, R. R. & Edgerton, V. R. Hindlimb stepping movements in
complete spinal rats induced by epidural spinal cord stimulation. *Neurosci Lett* **383**, 339–344 (2005).

65.   West, S. J., Bannister, K., Dickenson, A. H. & Bennett, D. L. Circuitry and plasticity of the dorsal horn – Toward a
better understanding of neuropathic pain. *Neuroscience* **300**, 254–275 (2015).

66.   Gong, Z. *et al.* Bioactive Elastic Scaffolds Loaded with Neural Stem Cells Promote Rapid Spinal Cord Regeneration.
ACS Biomater Sci Eng **6**, 6331–6343 (2020).

67.   Li, X. *et al.* Reactive Astrogliosis: Implications in Spinal Cord Injury Progression and Therapy. *Oxid Med Cell Longev*
2020, 1–14 (2020).

68.   Singh, A. V. *et al.* Astrocytes Increase ATP Exocytosis Mediated Calcium Signaling in Response to Microgroove
Structures. *Sci Rep* **5**, 7847 (2015).

69.   Schackel, T. *et al.* Peptides and Astroglia Improve the Regenerative Capacity of Alginate Gels in the Injured Spinal
Cord. *Tissue Eng Part A* **25**, 522–537 (2019).

70.   Ge, H. *et al.* Poly-L-ornithine enhances migration of neural stem/progenitor cells via promoting α-Actinin 4 binding
to actin filaments. *Sci Rep* **6**, 37681 (2016).

71.   Setien, M. B. *et al.* Differentiation and characterization of neurons derived from rat iPSCs. *J Neurosci Methods* **338**,
590   108693 (2020).

591   72.   Takeoka, A. & Arber, S. Functional Local Proprioceptive Feedback Circuits Initiate and Maintain Locomotor Recovery
592   after Spinal Cord Injury. *Cell Rep* **27**, 71-85.e3 (2019).

593   73.   Courtine, G. *et al.* Transformation of nonfunctional spinal circuits into functional states after the loss of brain input.
594   *Nat Neurosci* **12**, 1333–1342 (2009).

595   74.   Xiong, Y.-J. *et al.* Poly-L-ornithine blocks the inhibitory effects of fibronectin on oligodendrocyte differentiation and
596   promotes myelin repair. *Neural Regen Res* **18**, 832 (2023).

597   75.   Koopmans, G. C. *et al.* Functional Recovery, Serotonergic Sprouting, and Endogenous Progenitor Fates in Response
598   to Delayed Environmental Enrichment after Spinal Cord Injury. *J Neurotrauma* **29**, 514–527 (2012).

599   76.   De Virgiliis, F. *et al.* Enriched conditioning expands the regenerative ability of sensory neurons after spinal cord
600   injury via neuronal intrinsic redox signaling. *Nat Commun* **11**, 6425 (2020).

601   77.   Berrocal, Y. *et al.* Social and Environmental Enrichment Improves Sensory and Motor Recovery after Severe
602   Contusive Spinal Cord Injury in the Rat. *J Neurotrauma* **24**, 1761–1772 (2007).

603   78.   Tai, W. L. *et al.* Additive Effects of Environmental Enrichment and Ketamine on Neuropathic Pain Relief by Reducing
604   Glutamatergic Activation in Spinal Cord Injury in Rats. *Front Neurosci* **15**, (2021).

605   79.   Clemenson, G. D., Deng, W. & Gage, F. H. Environmental enrichment and neurogenesis: from mice to humans. *Curr
606   Opin Behav Sci* **4**, 56–62 (2015).

607   80.   McDonald, M. W., Hayward, K. S., Rosbergen, I. C. M., Jeffers, M. S. & Corbett, D. Is Environmental Enrichment
608   Ready for Clinical Application in Human Post-stroke Rehabilitation? *Front Behav Neurosci* **12**, (2018).

609   81.   Hutson, T. H. *et al.* Cbp-dependent histone acetylation mediates axon regeneration induced by environmental
610   enrichment in rodent spinal cord injury models. *Sci Transl Med* **11**, (2019).

611   82.   Neves, L. T. *et al.* Environmental Enrichment in Stroke Research: an Update. *Transl Stroke Res* (2023)
612   doi:10.1007/s12975-023-01132-w.

613   83.   Rossi, C. *et al.* Brain-derived neurotrophic factor (BDNF) is required for the enhancement of hippocampal
614   neurogenesis following environmental enrichment. *European Journal of Neuroscience* **24**, 1850–1856 (2006).

615   84.   Johansson, B. B. & Belichenko, P. V. Neuronal Plasticity and Dendritic Spines: Effect of Environmental Enrichment on
616   Intact and Postischemic Rat Brain. *Journal of Cerebral Blood Flow & Metabolism* **22**, 89–96 (2002).

617   85.   Guo, Y.-S. *et al.* Effects of enriched environment on microglia and functional white matter recovery in rats with post
618   stroke cognitive impairment. *Neurochem Int* **154**, 105295 (2022).

619   86.   Maegele, M. *et al.* Multimodal early onset stimulation combined with enriched environment is associated with
620   reduced CNS lesion volume and enhanced reversal of neuromotor dysfunction after traumatic brain injury in rats.
621   *European Journal of Neuroscience* **21**, 2406–2418 (2005).

87. Burgdorf, J. & Panksepp, J. Tickling induces reward in adolescent rats. *Physiol Behav* **72**, 167–173 (2001).

88. BASSO, D. M., BEATTIE, M. S. & BRESNAHAN, J. C. A Sensitive and Reliable Locomotor Rating Scale for Open Field Testing in Rats. *J Neurotrauma* **12**, 1–21 (1995).

Acknowledgements

The authors would like to thank the Animal Care and Veterinary Service staff and the University of Ottawa Louise Pelletier Histology Core (RRID: SCR_021737) for their continuous support in this project. We would like to thank Dr. Rafay Azhar for advising on histopathological interpretation. This work was supported by the Li Ka Shing Foundation (AEP), the Natural Sciences and Engineering Research Council (TB and AEP), Canada Research Chairs Program (AEP), the Canada Foundation for Innovation (AEP), the Canadian Institutes of Health Research (TB), the Canada Graduate Scholarship Program (LJC) and the Ontario Graduate Scholarship Program (LJC).

Author contributions statement

LJC, KLAW, DJM, CMC, ECT, TB and AEP conceived the experiment(s). LJC, KLAW, AB, DJM, CMC, MLL, RJH, RB and RM conducted the experiment(s), LJC, KLAW, DJM, CMC, MLL, RJH, R-JKO, IS, AG, TB and AEP authors analysed the results. All authors reviewed the manuscript.

Competing Interests Statement

LJC, KLAW, AB, DJM, CMC, RJH, MLL, RB and AEP are listed inventors on several patents on the topic of plant-derived cellulose biomaterials for various applications. DJM, CMC, RJH, MLL, IS, and AEP are former or current employees of Spiderwort Inc., which is leading the clinical translation of these biomaterials. ET is a member of Spiderwort's CelluBridge clinical advisory board. All other authors declare no other competing interests.

Figure 1. Plant-derived cellulose biomaterial in rodent model of complete transection spinal cord injury.

A. A cross sectional view of decellularized plant-derived scaffold consisting of vascular bundles and parenchyma (scale bar = 1 mm). B. SEM of cellulose scaffold microarchitecture (scale bar = 100μm). C. Hematoxylin & eosin staining of cross section of cellulose scaffold after 12 weeks in vivo. The scaffold's vascular bundles are infiltrated with host cells. (Scale bar = 200 μm). D. An exposed fully transected spinal cord (left box) and a scaffold after implantation (right box). E. Hematoxylin & eosin staining of sagittal section of spinal cord tissue with cellulose scaffold (outlined) after 12 weeks in vivo (Scale bar = 2mm). F. Immunohistochemistry staining for CD31 (brown) in a sagittal section at the caudal biomaterial-tissue interface (representative image from the ASP group). CD31 positive blood vessels denoted by arrow (Scale bar = 200μm). G. Immunohistochemistry staining for CD31 (brown) in a sagittal section at the caudal biomaterial-tissue interface (representative image from the PLO group). CD31 positive blood vessels denoted by arrow (Scale bar = 200μm).

Figure 2. Locomotor assessments after complete spinal cord transection

A. Average BBB score of each experimental group at week 2 (purple bars) after SCI compared to week 11 (blue bars) after SCI (2way ANOVA Uncorrected Fisher's LSD; ****$P<0.0001$, *$P=0.0158$; mean ± s.e.m, n = 11 PLO animals, n = 9 ASP animals, n = 8 No Tx animals). B. Average KSAT swim assessment score of each experimental group at week 2 after SCI compared to week 11 after SCI (2way ANOVA Uncorrected Fisher's LSD; ***$P=0.0001$; mean ± s.e.m, n = 11 PLO animals (green bar), n = 9 ASP animals (red bar), n = 8 No Tx animals (yellow bar)). C. Average maximum angle achieved by each experimental group in inclined plane assessment at final week (mean ± s.e.m, n = 11 PLO animals, n = 9 ASP animals, n = 8 No Tx animals)

728
729
Figure 3. Retrograde tract tracing of ascending sensory afferents by CTb injection into sciatic nerve
A. Furthest rostral CTb-traced axons. Each point represents the distance (mm) between the injury epicenter and the furthest
rostral CTB-traced axon in one animal. Bar represents the mean ± s.e.m of each group (One-way ANOVA; *P=0.0264, n = 4
PLO animals, n = 2 ASP animals, n = 3 No Tx animals). B. Hoescht (cyan) stained cross section of spinal cord at T10 (caudal to
the injury) confirms presence of CTb (magenta) in dorsal column and lamina 4 (Scale bar 300 μm). C. Hoescht (cyan) stained
sagittal section of spinal cord from SCI animal with no scaffold at T9 (caudal side of the injury). CTb-traced axons (magenta)
can be seen in the dorsal collumn (Scale bar 500 μm). D. Hoescht (cyan) stained sagittal section of spinal cord from SCI animal
with uncoated scaffold at T9 (caudal side of the injury). CTb-traced axons (magenta) can be seen in the dorsal collumn (Scale
bar 500 μm). E. Hoescht (cyan) stained sagittal section of spinal cord from SCI animal implanted with PLO-coated cellulose
scaffold at T9 (caudal side of the injury). CTb-traced axons (magenta) can be seen in the dorsal column (Scale bar 500 μm)

Figure 4. Anterograde labeling of the corticospinal tract by injection of dextran amine into hindlimb motor cortex

A. Furthest caudal dextran amine-traced axons. Each point represents the distance (mm) between the injury epicenter and the furthest caudal DA-traced axon in one animal. Bar represents the mean ± s.e.m of each group (One-way ANOVA; P=0.0903, n = 4 PLO animals, n = 4 ASP animals, n = 3 No Tx animals). B. Hoescht (cyan) stained cross section of spinal cord at T6 (rostral to the injury) confirms presence of dextran amine (yellow) in corticospinal tract (Scale bar 300 µm). C. Hoescht (cyan) stained sagittal section of spinal cord from SCI animal with no scaffold. DA-traced axons (yellow) can be seen in the corticospinal tract (rostral aspect on the left, scale bar 500 µm). D. Hoescht (cyan) stained sagittal section of spinal cord from SCI animal implanted with uncoated cellulose scaffold (outlined by white dotted line). DA-traced axons (yellow) can be seen in the corticospinal tract (rostral aspect on the left, scale bar 500 µm). E. Hoescht (cyan) stained sagittal section of spinal cord from SCI animal implanted with PLO-coated cellulose scaffold (outlined by white dotted line). DA-traced axons (yellow) can be seen in the corticospinal tract (rostral aspect on the left, scale bar 500µm).

Figure 5. Immunostaining for ß-III tubulin and neurofilament-200 reveals neural cells attaching to scaffold and migrating along channels

A. ß-III tubulin (red) and Hoescht (blue) staining of sagittal section within PLO-coated biomaterial. Cell bodies (identified by arrow) can be seen inside the scaffold (scale bar 50µm). B. ß-III tubulin (red) and Hoescht (blue) staining of sagittal section within PLO-coated biomaterial. Axons (identified by arrow) can be seen sprouting inside the scaffold (scale bar 50µm). C. Neurofilament 200 (green) and Hoescht (blue) staining of sagittal section at the interface (dashed line) between PLO-coated biomaterial and spinal cord (scale bar 200µm). D. Neurofilament 200 (green) and Hoescht (blue) staining of sagittal section at the interface (dashed line) between PLO-coated biomaterial and spinal cord. NF200 positive cells can be seen infiltrating the biomaterial (asterisk) & NF200 axon projections extend from the dorsal to ventral aspect of the biomaterial (arrow) (scale bar 50µm). E. Neurofilament 200 (green) and Hoescht (blue) staining of sagittal section at the interface (dashed line) between uncoated biomaterial and spinal cord (scale bar 200µm). F. Longest distance of infiltration of NF200-cells into the scaffold for each experimental group. The mean ± SD of each group is shown (Unpaired T-test Mann Whitney; P=0.0286, n = 4 PLO animals, n = 4 ASP animals)

811
812
813 **Figure 6. Luxol fast blue (LFB) staining of sagittal tissue sections for assessment of myelin at the site of spinal cord injury**
814 A. Representative LFB staining at scaffold-tissue interface in animals implanted with PLO coated cellulose scaffold. Outline
815 denotes cellulose scaffold (Scale bar = 200μm). B. LFB staining at scaffold-tissue interface in animals implanted with uncoated
816 cellulose scaffold (outlined) (Scale bar = 200μm). C. LFB staining at cyst-tissue interface in animals with no scaffold (Scale bar
817 = 200μm).