1   Crystal growth and design Main Manuscript for

2   Ultrastructural features of bacterial calcite unveil ubiquitous

3   organics occlusion and clues on biomineralization

Franco Grosso Giordano[1,2,3] *, Martín Purino[4], Nico Boon[1], Nele De Belie[2] and Carlos

Rodriguez-Navarro[3*]

[1] Ghent University, Center for Microbial Ecology and Technology (CMET), Frieda

Saeysstraat 1, 9052, Ghent, Belgium.

[2] Ghent University, Magnel-Vandepitte Laboratory, Dept. of Structural Engineering

and Building Materials, Technologiepark Zwijnaarde 60, B-9052, Ghent, Belgium.

[3] University of Granada, Department of Mineralogy and Petrology, 18002, Granada,

Spain.

[4] Ghent University, Department of Organic and Macromolecular Chemistry, Krijgslaan

281 S4, B-9000 Ghent, Belgium.

*Corresponding authors: Franco.GrossoGiordano@UGent.be; CarlosRN@Ugr.es.

Keywords: Bacteria, biomineralization, organics occlusion, amorphous calcium

carbonate, calcite.

This PDF file includes:

Title page (title, author list, classification, keywords)

Abstract

Main Text

Figures 1 to 6

References

Abstract

Microbially-induced calcium carbonate precipitation is a widespread natural

phenomenon with numerous technical applications. Recent advances have shown

that bacterial calcium carbonates (BCC) form non-classically via amorphous calcium

carbonate (ACC) precursors in the presence of organics, but the role of organics in

the formation and nanostructural features of BCCs is not fully understood. Here we

show that two bacterial strains produce BCCs with diverse textural and structural

features at the macroscale but similar at the micro and nanoscale. We show that

bacterial organics guide precipitation of calcite, stabilizing ACC to produce

nanogranular crystals and these organics are then trapped within the crystal, rather

than being released as previously suggested. These organics are N-rich and create

regions of low Z-contrast aligned perpendicular to the *c*-axis of the crystal, yielding a

"Swiss cheese-like" mesostructure. Moreover, it is these occluded organics that lead

to the distinctive biosignatures observed in BCC. Finally, we also observe crystalline

2D-films, possibly proteins, templating the oriented crystallization of calcite. These

ultrastructural features help to disclose how microbial $CaCO_3$ biomineralization takes

place leading to improved technical applications and may provide fingerprints for

their identification in nature.

Introduction

Biomineralization is a widespread, cross-kingdom phenomenon whereby organisms

induce or control the formation of a variety of minerals in or around them [1]. A widely

occurring biomineralization process is the precipitation of calcium carbonate. It forms

the basis of many current biominerals structures – including shells of molluscs, the

cell wall of coralline algae, and the cystolith of plants [1-3] – and ancient – it is the

main mineral fraction in microbialites, some of the oldest fossils in the world [4]. The

bioprecipitation of calcium carbonate is also a common occurrence in the present day

microbial world [5-7], usually denominated as microbially-induced carbonate

precipitation (MICP). While calcium carbonate biominerals in eukaryotes is

considered to be tightly controlled by genetic and biochemical factors, MICP,

generally an extracellular phenomenon, has long been considered uncontrolled with

no specific purpose or functionality [8]. However, recent evidence is questioning this

notion [9]. For example, calcium carbonates have been reported to lead to an

evolutionary benefit by increasing the pathogenic capacity of strains [10], facilitating

biofilm formation [11], and providing survival strategies in extreme conditions [12].

Certain aspects of the biochemical understanding of MICP are well agreed upon. For

instance, the metabolic pathways of bacterial calcium carbonate (BCC) production

are in general well-known and include sulphate reduction [13], photosynthesis [2],

denitrification [14] ureolysis and ammonification [15] and metabolism of organic acids

[16,17]. They all result in alkalinization, thereby fostering the formation of CO_3^{2-} ions

and enabling precipitation of $CaCO_3$ in the presence of Ca^{2+} ions. Moreover,

researchers recognize that there is a role of extracellular polymeric substances (EPS)

- which include polysaccharides, proteins and nucleic acids - in the formation of

precipitates, acting as a Ca^{2+} adsorption template [18]. Besides their role in

concentrating Ca^{2+}, there is growing evidence showing that the organic-mediated

formation of amorphous calcium carbonate (ACC) by prokaryotes prior to

crystallization of anhydrous $CaCO_3$ crystals appears to be a general phenomenon [19-

22]. Recently, Enyedi et al. [23], showed that bacterial EPS led to long-term stabilization

of ACC, and suggested that the stabilized ACC eventually led to the formation of

calcite through non-classical crystallization. However, the MICP crystallization

mechanisms are still poorly understood, specifically when the role of organics is

involved, while structural aspects of these biocrystals have not been fully

characterised. This is an important research gap given MICP occurs with a wide

range of organisms and it has attracted a large amount of research in bio-

engineering applications [7].

In this work, we aim to shed light on the formation mechanism of MICP and study

the elemental, compositional and (ultra)structural characteristics of BCCs at multiple

scales. To achieve this goal we have performed crystallographic, compositional,

textural and (nano)structural analyses of BCCs (calcite) from two bacterial species,

using inorganic calcite as control. Differences between BCCs and inorganic calcite

were starker than between BCCs of the two species and were attributed to the

presence of (N-rich) organic biosignatures. Furthermore, BCCs formed through non-

classical ACC-to-calcite precipitation and produced mesocrystals with a Swiss-cheese

like structure with regions of occluded intracrystalline organic matter. In addition, a

bacterially-derived 2D crystalline film was identified which enabled the oriented

nucleation of bacterial calcite, supporting the role of organic molecules in BCC

formation.

Materials and Methods

Synthetic calcite preparation

Calcite was produced synthetically in order to act as an abiotic control. A reaction

pathway was chosen as proxy to that expected in the bacterial cultures, whereby

calcite precipitated by the dissolution of CO_2 from bacterial respiration. A saturated

calcium hydroxide solution was prepared by adding 5 g $Ca(OH)_2$ to 100 ml of distilled

water, stirring for 30 min at 50 RPM and letting sit for 2 h. The supernatant (i.e., a

saturated solution of Ca^{2+} and OH^- (equation 1) was poured into a clean container.

CO_2 was then purged through this solution. This enabled the fast dissolution and

hydration of CO_2, creating bicarbonate (equation 2) and carbonate ions (equation 3).

Subsequently, $CaCO_3$ spontaneously precipitated through the reaction of carbonate

ions with Ca^{2+} (equation 4) in the absence of any background electrolyte. The

precipitates were filtered using a vacuum pump and polycarbonate filters ($\varphi = 0.22$

μm). The filter with the precipitates was placed at room temperature (T) and dried

overnight. The dry solids were stored in plastic vials for further analysis.

$Ca(OH)_2 \rightarrow Ca^{2+} + 2OH^-$ (1)

$OH^- + CO_2 \rightarrow HCO_3^-$ (2)

$HCO_3^- + OH^- \rightarrow CO_3^{2-} + H_2O$ (3)

$Ca^{2+} + CO_3^{2-} \rightarrow CaCO_3$ (4)

Selection and cultivation of bacterial strains

Two bacterial strains were used in this study, *Lynsinobacillus fusiformis* (LMG 9816)

and a recently isolated strain, *Shouchella clausii* (registered at the Belgian

Coordinated Collection of Microorganisms as LMG 33400). *S. clausii* was isolated

from a lime mortar wall in Ghent, Belgium by selecting morphologically distinct

colonies from a Horikoshi medium. Its capacity for carbonate precipitation was tested

on pH 8-adjusted B4-medium (0.4 % yeast extract, 0.5 % dextrose, 0.265 % Ca-

acetate hydrate, 1.4 % agar, adjust pH to 8 using 0.1M NaOH), a standard medium

used to study precipitation of calcium carbonate crystals [5,23–25]. Importantly, Ca-

acetate was filter sterilized as doing otherwise would lead to precipitation of calcium

carbonate either through too high pH or through heating of the Ca-acetate. Finally,

the strain was selectively adapted to high pH tolerance by repeated inoculation in

TSB adjusted to pH 11 with CAPS buffer. An alkaliphile was desirable as MICP

commonly occurs in alkaline environments. The bacteria were grown and kept in TSA

at 28 °C.

Culture and precipitation media, and precipitate extraction

Due to the alkaliphilic nature of both bacteria, carbonate precipitation experiments

were carried out on pH 8-adjusted B4-medium. For the inoculation of B4 plates,

bacteria were inoculated in TSB and grown for 48 h. Subsequently, 10 µL of a fully

grown culture was drop-inoculated onto 9 spots on B4 plates. The cultures were

grown for 4 weeks at 28 °C. At this point, precipitates were visible on the plate and

were extracted. Briefly, the B4 agar was cut into pieces and placed in a glass

container and melted in a microwave oven. 100 mL of warm deionized water were

added to the beaker to dilute the melted agar. The dilute agar was centrifuged at

5000 rpm for 1 min while still warm. The pellet was then microwaved again, warm

water was added, and centrifuged again. This was performed a third time but

centrifuged at 7000 rpm. The sample was warmed up once more, and the suspension

was filtered using a vacuum pump and polycarbonate filters (φ = 0.22 µm). The

filter with the precipitates was placed at room temperature and dried overnight.

Once dried, the solids were placed in a plastic vial for further analysis.

Bleaching of precipitates

A fraction of the bacterial precipitates was bleached to remove any potential organic

matter on their surfaces [26]. Bleaching was done using commercial bleach and

deionized water (1:1 dilution) poured in an Eppendorf tube (1.5 mL) filled with 0.1 g

solids, followed by incubation for 2 h in a shaking table. The samples were then

centrifuged for 1 min at 5000 RPM and the supernatant discarded. Bleached solids

were resuspended in MilliQ water, vortexed for 1 min, and centrifuged again.

Washing was performed thrice. The precipitates were dried at 50 °C overnight.

FTIR spectroscopy

Fourier Transform Infrared Spectroscopy (FTIR) spectra of the precipitate were

recorded on a NICOLET 20SXB FTIR (400–4000 cm^{-1} spectral range; resolution of 2

cm^{-1}). Baseline and smoothing corrections to the FTIR spectra was performed using

Spectragryph v1.2.16.1.

X-ray diffraction (XRD)

The crystallographic features of the synthetic (control) and bacterial precipitates

were analysed with a Xpert Pro X-ray powder diffractometer (Panalytical, The

Netherlands) in reflection mode using copper radiation to determine $\theta-2\theta$ scans

(measurement parameters: Cu Kα radiation λ = 1.5405 Å, 45 kV, 40 mA, 3 to 70°

exploration range, with 0.00418° step size and 29.8 s integration time per step).

Bacterial precipitates were analysed in zero-background Si sample holders. XRD

patterns were analysed using the computer program HighScore Plus Version 3.0d.

TG analysis

Thermogravimetric analysis (TGA) was performed using a TGA 2 (Mettler-Toledo,

Switzerland) with a large furnace and an autosampler, using 70 μL alumina crucibles.

Samples (12 mg) were heated at 20 °C/min from 25 to 950 °C under air atmosphere

(80 mL/min).

Synchrotron High-Resolution Powder X-Ray Diffraction (HRXRD)

HRXRD analyses were performed at beamline CRYSTAL of the SOLEIL synchrotron

(Paris, France). The wavelength 0.672356 Å (18.44024 keV) was selected with a

double-crystal Si (111) monochromator and determined by using Si640d NIST

standard (a = 5.43123 Å). The CRYSTAL beamline is equipped with a high-

throughput position sensitive detector (PSD) MYTHEN, optimal for time-resolved

experiments. Borosilicate glass capillaries of 0.3 mm diameter were loaded with

powder samples and rotated during data collection to improve diffracting particle

statistics. Isochronous annealing (10°C min^{-1}; 30 s stabilization time at target T,

tolerance ± 5°C) was performed using a Cyberstar hot gas blower with a Eurotherm

T controller (Eurotherm, Worthing, UK), collecting diffraction data each 50°C during

the heating ramps (50° to 400°C). Once the maximum T was reached, the samples

were cooled to room T, and a final measurement was taken. The data acquisition

time was ~5 min per pattern, with up to two iterations per measurement to obtain a

good signal-to-noise ratio over the 0-55.34 °2θ angular range. To calibrate the

equipment and reduce possible shifts during experimental analysis, a LaB6 standard

was used. An instrumental resolution factor analysis was performed in each case.

Under these data acquisition conditions, the angular resolution was better than

0.006° FWHM. As opposed to conventional XRD, such an angular resolution enables

to detect lattice strains of 10^{-3} to 10^{-4} associated with intracrystalline organics.

The Rietveld refinement method [27] was used to extract lattice parameters of calcite

matching the experimental diffraction peaks with those included in Markgraf and

Reeder [28] using Topas software. Optical quality (highly pure) geologic calcite (Iceland

spar, from Chihuahua, Mexico) was used as standard to compare XRD data from

BCC.

To investigate the microstructural variations due to organic (macro)molecule

incorporation in the calcite structure, the Thompson-Cox-Hastings pseudo-Voigt

function was used to fit the profile of the experimental diffraction patterns.

Refinement cycles were performed to ensure reproducibility of each analysis,

selecting a Goodness of Fit of <9. Note that, as opposed to BCC, in the case of the

Iceland spar control no changes in Bragg peak position or broadening (FWHM) were

observed after annealing, i.e., after returning to room T following heating up to

400°C. These results show that the selected geogenic calcite is a proper reference to

compare the results of BCC HRXRD analysis.

FESEM and TEM analysis

Field Emission Scanning electron microscopy (FESEM) images were collected using

an Auriga (Zeiss, Germany) microscope with field emission gun operated at 5 kV. All

samples were carbon coated prior to imaging.

Nanoscale features and elemental composition of the precipitates were studied using

TEM on a Titan (FEI) with acceleration voltage of 300 kV. The TEM was equipped

with a high angle annular dark field (HAADF) detector for Z-contrast imaging and

energy dispersive X-ray spectroscopy (EDS) for microanalysis (performed in STEM

mode). Right before TEM analysis the solids were dispersed in ethanol, sonicated for

2 min and fished with carbon-coated TEM Cu grids. Imaging was performed using a

20 µm objective aperture, which is a good compromise for amplitude and phase

contrast (high resolution, HRTEM) imaging. Selected area electron diffraction (SAED)

patterns were collected from areas ~200 nm in diameter.

Solid-state NMR (ssNMR)

The 1D experiments were recorded on a Bruker Ascend 500.13MHz Avance III spectrometer equipped with a Bruker broadband 4 mm 1H/X dual channel CP-MAS smartprobe probe head, equipped with Z-gradients, a MAS III pneumatic unit and running Topspin 3.6.5. For each measurement, the spinning frequency was set to 12000Hz, all measurements were performed at room temperature (25°C) and controlled with a Eurotherm 2000 BVT controller and a BCU-I.

All samples were prepared by filling the 4mm Bruker K1910 ZrO2 rotors with an appropriate amount of dry and finely grained sample material (25-30 mg per sample). Using subsequent rounds of filling and packing the rotor led to a tightly filled rotor sample for each material under study. Following the packing of the rotors, each of them was sealed with a Kel-F insert, a Kel-F rotor cap and visually checked for any leftover voids or air pockets.

The spectra recorded on the samples included 1D ^{1}H and 1D ^{13}C measurements. For the 1D ^{1}H 'onepulse' experiments, the spectral width used was 200.00 ppm with 4 scans of 4K data points each being accumulated, preceded by 2 dummy scans and a relaxation delay of 2 seconds. Finally, the spectrometer excitation frequency was set on resonance with the frequency (5 ppm) of the most intense signal. Processing consisted of one order of zero filling to 16K real data points, followed by Fourier transformation, phase correction and a base-line correction.

For ^{13}C measurements a 'hpdec' measurement type was used for non-cross-polarization and 'hX.cp' for measurements with cross-polarization (CP) with ^{1}H. The spectral width used was 300.00 ppm with 2048 scans of 4K data points each being

accumulated, preceded by 4 dummy scans and a relaxation delay of 5 seconds.

Finally, the spectrometer excitation frequency was set on resonance with the

frequency (100 ppm) of the most intense signal. Processing consisted of one order of

zero filling to 16K real data points, followed by Fourier transformation, phase

correction and a base-line correction.

Chemical shifts were indirectly referenced by adapting the magnet 'field' value -by

measuring an adamantane reference sample-, and adapting the magnet field until

one of the adamantane signals is at the right chemical shift value (37.77 ppm). All

spectra were processed using TOPSPIN 4.1.3.

Results

BCCs have distinctive biosignatures associated with organics and ACC

The calcium carbonate precipitating capacity of two bacterial species was studied.

Lynsinobacillus fusiformis (LMG 9816) strain was selected as it has been commonly

used in other studies of MICP [29,30]. To test whether nanoscale characteristics between

BCCs were similar, a recently isolated strain producing morphologically distinct BCC,

Shouchella clausii (previously known as *Alkalohalobacillus clausii*) LMG 33400, was

used. No previous *Shouchella* (or *Alkalohalobacillus)* strain has been reported to

precipitate calcium carbonate.

Optical microscopy imaging (Figure 1a,e) disclosed morphological differences

between mineral precipitates produced by *L. fusiformis* and *S. clausii*. *L. fusiformis*

mainly produced irregular precipitates with spherical incrustations, while *S. clausii*

induced the formation of spherical or oval-shape precipitates. A detailed observation

of the latter shows that they display elongated disphenoidal forms, or spindle- and/or

dumbbell-shaped structures, as also observed in other bacterial species [31]. Such

diverse precipitate morphologies have been observed for different bacteria in studies

using the same standard culture medium used here (B4) [24]. Both bacteria produced

precipitates associated with the bacterial colonies as well as in the surrounding

media. Field emission scanning electron microscopy (FESEM) analysis showed the

presence of carbonate precipitates closely-associated with organic matter (Figure 1b,

f). At the microscale all precipitates had an overall rhombohedral morphology,

consistent with the presence of calcite (see XRD results below) and were better

developed in the case of *S. clausii* samples (Figure 1d vs g and h). All of them

showed a nanogranular texture, implying formation through particle attachment

(PA). In PA, ACC particles 100 – 400 nm in size [32] in the presence of organics [33] or

crystalline $CaCO_3$ nanoparticles [34], attach forming a single crystallographic unit and

this is typically observed in carbonate biominerals produced by a range of organisms

(e.g., molluscs, barnacles, echinoderms, cnidaria) [26,35–37], including other bacteria [23].

The precipitates were bleached to remove any organics on the precipitate surface

and study possible crystallographic and compositional changes. After bleaching,

organic matter was not observable anymore on the precipitates (Figure 1c, d and h),

calcified bacterial casts could be spotted (Figure 1c), and the crystallographic faces

were more obvious (Figure 1h). Note that we performed bleaching tests with

increasing reaction time from 10 up to 480 min, observing (using FTIR) that the

removable fraction of organics could not be detected after 10 min (see Supporting

Information and Supporting Figure 1 and Supporting Figure 2).

Figure 1. Optical and scanning electron microscopy photomicrographs of

bacterial calcium carbonate. Calcium carbonate structures precipitated by *L.*

fusiformis (a - d) and *S. clausii* (e - h). Orange outlined images are samples treated

with bleach (c, d, h). Different morphologies of calcium carbonate precipitates were

produced by both bacteria. (**a**) *L. fusiformis* produced irregular precipitates. (**b**)

Bacteria and biofilm associated with precipitated calcium carbonate. (**c**) Bleached *L.*

fusiformis precipitates showing the calcified bacterial casts. (**d**) Bleached *L.*

fusiformis precipitates (showing rhombohedral vicinal faces) made up of ordered

nanoparticles. (**e**) *S. clausii* produced ovoidal (black arrow), disphenoidal (white

arrow with black outline) and dumbbell (white arrows) shaped precipitates. (**f**) *S.*

clausii cells associated with precipitated calcium carbonate (calcite rhombohedra).

(**g**) Detail of the mesostructured CaCO$_3$ crystals. (**h**) Bleached calcium carbonate

showing the orderly arrangement of calcium carbonate nanoparticles. In all cases the

shapeless precipitate subunits varying between 100 – 200 nm in size are

distinguishable within calcite mesocrystals. All SEM micrograph scale bars are 1.2

µm.

XRD confirmed the precipitation of calcite rather than any other calcium carbonate

polymorphs. The humps at 10 and 20 - 30 °2θ in the XRD patterns of both *S. clausii*

and *L. fusiformis* carbonates pointed to the presence of two distinct amorphous

phases (Figure 2a). Note that no humps were present in the XRD pattern of abiotic

calcite (control). Changes in the relative intensity of Bragg peaks were observed for

BCCs, as compared with synthetic calcite. Notably, the intensity of the 110 Bragg

reflection increased drastically (as compared to the main 104 Bragg reflection). The

(11.0) plane is associated with crystals elongated along the *c*-axis [38] and consistent

with the crystal morphology observed in Figure 1. Overdevelopment of {11.0} faces,

or more exactly, pseudo-faces composed of (01.2) and (11.0) forms [39], is common in

- although not exclusive to - other calcite biominerals and abiotic calcite formed via

ACC-to-calcite crystallization in the presence of organics (see Supporting

Information). After bleaching, both humps at 10 °2θ and 20-30 °2θ disappeared.

The bleaching of precipitates also led to changes in the intensity of Braggs peaks of

both bacterial crystals, most starkly non-(104) planes, with 110 and 113 Bragg

reflections being the strongest (Supporting Table 1). We observed better

development of crystal faces after bleaching (Figure 1c, d and h) which would explain

the XRD changes.

Figure 2. Analysis of synthetic (c, purple) and bacterial crystals (*L. fusiformis* (*lf*, red) and *S. clausii* (*sc*, brown)). Both bacterial calcites were bleached to remove organic matter from the surface (*L. fusiformis* (*lf* b, light red) and *S. clausii* (*sc* b, light brown)) **(a)** XRD patterns of the studied calcium carbonates. Bragg peaks correspond to calcite in all cases and the main *hkl* reflections are indicated. **(b)** FTIR spectra of synthetic, *L. fusifomis* and *S. clausii* calcites. Blue shaded bands indicate organic and/or ACC wavenumber regions. **(c)** FTIR spectra of the calcites after bleaching **(d)** TGA of *L. fusifomis* bleached calcite (light red) vs synthetic calcite (purple).

FTIR spectroscopy showed distinctive spectral features among the different precipitates. All precipitates displayed the characteristic v_2, v_3 and v_4 bands of calcite

at 873, 1407 and 711 cm^{-1}, respectively, however with some differences. Bacterial

calcites showed a slightly red-shifted v_2 band at 869 cm^{-1} (with a broad tail spanning

to lower wavenumbers) and a v_3 band at 1402 cm^{-1}. The red-shift of the v_2 band can

be caused by ACC which has a characteristic band at 860 cm^{-1} also seen in ACC

producing bacterial strains [3,40–43]. There were also variations in the absorbance of the

v_2 and v_4 bands. Synthetic calcite had the sharpest and strongest absolute v_4

absorbance followed by *S. clausii* and finally by *L. fusiformis* (Figure 2b). Besides the

differences in the vibrational modes, certain bands were evident in biogenic

precipitates but absent in synthetic calcite: namely between 950 – 1150 cm^{-1}, at

1500 – 1550 cm^{-1}, and between 1570 – 1700 cm^{-1}. A last band became apparent at

1190 - 1350 cm^{-1}, characteristic of amides [23], when subtracting the synthetic calcite

with the BCC spectra (Supporting Figure 3). Similar spectra have been previously

reported on bacterial calcites [23,43,44], attributed to overlapping signatures of organics

(general organics at 950 – 1150 cm^{-1} and amides at > 1500 cm^{-1}) and ACC (v_1-mode

1060-1080 cm^{-1}; a v_3 asymmetric vibration at 1470 cm^{-1}; and O-H bending at 1650

cm^{-1} from structural H_2O in ACC) (for details see Supporting Information). As such,

Mehta and colleagues [43] concluded that it is difficult to infer the presence of ACC

from the bands at > 900 cm^{-1} alone.

Following the bleaching process used to remove organic matter, BCCs produced

almost matching FTIR spectra (Figure 2c). No shift was observed in the carbonate v-

modes, yet all three modes experienced an increase in absorbance. This is important

as changes in calcite v-mode absorbance, most notably the increase in intensity of

the 712 cm^{-1} band, is associated with an increase in crystallinity of the carbonates [41].

However, the lack of shift in the v_2 band, and in particular the persistence of the

right broad tail, suggests that some ACC was still present, most likely structurally

bound to the BCC calcite structure. Conversely, the increase in v_4 absorption after

bleaching suggests that a fraction of ACC, likely the superficially exposed (see TEM

results below), was transformed into calcite via dissolution-precipitation in the bleach

solution, and/or was removed after rinsing of the bleach. Moreover, the bleaching

process leads to removal of bands at higher wavenumbers (bands at 1500 – 1550

cm^{-1} and 1570 – 1700 cm^{-1}), previously linked to organics. On the contrary, the

bands at 950 – 1150 cm^{-1} and 1190 – 1350 cm^{-1} also corresponding to organics and

ACC were conserved after bleaching, with a reduction in absorbance, especially in *L.*

fusiformis. Interestingly, the amide-specific band at 1190 – 1350 cm^{-1} in *L.*

fusiformis BCC experienced a shift to higher wavenumber after bleaching. Given that

we can associate the wavenumber to the bond strength, a higher wavenumber

means that a stronger bond exists between the remaining organics and the crystal

structure [45]. It follows that bleaching removed the material more weakly associated

with the BCC crystals (e.g. adsorbed organics and ACC), and the subsequent rinsing

of the bleach led to dissolution of precursor ACC and recrystallization of calcium

carbonate on certain preferential faces of the crystals. This would be responsible for

the disappearance of the two humps in the XRD patterns and the changes in Bragg

peak intensities. Nevertheless, a fraction of organics (and likely ACC) were not

affected by the bleaching process, as a signal of organics remains in the FTIR

spectra. Duplicates of the BCCs before and after bleaching show consistent FTIR

bands (see Supporting Information and Supporting Figure 4).

Thermogravimetric analysis (TGA) was performed on the bleached BCCs of *L.*

fusiformis and synthetic calcite to further disclose the compositional nature of the

biominerals (Figure 2e). The calcite control shows a weight loss of 42.3 % starting

from 650 °C, close to the theoretical 44 % due to the decarbonation of calcite. The

bleached BCC of *L. fusiformis*, showed a continuous and step-wise mass loss at $T <$ 100 °C, 150 – 500 °C, 500 – 600 °C and 600 – 950 °C. The initial mass loss is from adsorbed water. The second loss can be from ACC dehydration and/or thermal decomposition of the remaining organic matter. The dehydration of ACC occurs at 100 – 350 °C [42,46] and the decomposition of organic matter starts at 250 °C and continues up to 400 or 600 °C for intracrystalline matter [42,47]. Although there is an overlap between both decompositions, the continuous mass loss after 350 °C distinguishes the presence of organics. Finally, unlike the control, the weight loss of BCC from 650 - 950 °C (33.9 %) does not match the value corresponding to the theoretical mass loss of $CaCO_3$ following release of CO_2, but rather the weight loss from 550 – 950 does (44.1 %). A lower decomposition temperature in $CaCO_3$ is associated with lower crystallinity [48], which corresponds to the lower crystallinity of BCCs observed with FTIR.

Overall, it becomes apparent that BCCs produced by the two bacteria studied, when formed, are associated with bacterially-derived organic matter and ACC, with distinctive biosignatures in all tests. FTIR confirmed that bleaching removes a non-calcite fraction, seemingly composed of organics and ACC loosely bound to the crystal surfaces, as seen on the SEM micrographs. But FTIR and TGA results show that there is a non-removable organic/ACC fraction that is more permanently associated with the BCC crystals. Overall this produces biomineralized calcite with non-perfect crystal lattice (i.e. lower crystallinity).

Organics lead to the formation of a distinctive nanostructural Swiss-cheese like structure

433 To further disclose how the organics were associated with the precipitates, TEM and

434 HRTEM analyses were performed, complemented with HAADF-EDS. Under the TEM

435 we observed that unbleached *L. fusiformis* precipitated crystalline (calcite) and

436 amorphous (ACC) phases as confirmed by selected area electron diffraction (SAED)

437 patterns (Figure 3a, Supporting Figure 5a). Conversely, we could not find individual

438 or aggregated ACC particles in the case of *S. clausii* which only showed single crystal

439 SAED patterns of calcite (Figure 3c). Additionally, SAED patterns with calcite single

440 crystal features were frequently arced, with spots displaying an angular spread of ~4

441 to 12° on both BCCs (Figure 3c, Supporting Figure 5a). Angular spreading is a

442 distinctive feature of mesocrystals reflecting a slight misorientation among the

443 different nanocrystals making up a mesocrystal [49] and commonly associated with the

444 presence of organic matter in biominerals [50]. The elemental composition of the

445 unbleached precipitates was confirmed with EDS mapping. Ca, O and C were

446 ubiquitous in all samples. Moreover, it was possible to correlate the presence of

447 organic-related elements such as, N, S and P – the latter two in trace amounts – in

448 the crystals produced by both bacteria (Figure 3b, d, Supporting Figure 5b,

449 Supporting Figure 6).

Figure 3. TEM and EDS analysis of bacterial calcium carbonates. (**a**) HAADF

image of ACC precipitated by *L. fusiformis*. Inset: SAED pattern showing the

amorphous nature of the particle. (**b**) In clockwise order: EDS elemental maps of

precipitates in (a) (calcium, oxygen, nitrogen and carbon, respectively). (**c**) HAADF

image of calcite crystals precipitated by S. clausii. Note the nanoporous structure of

the crystals. Inset: $[2\bar{2}1]$ zone axis SAED pattern of the calcite particle on the left

with diffraction spots showing an angular spreading of 6°; (**d**) In clockwise order:

EDS elemental maps of precipitates in (d) (calcium, oxygen, nitrogen and carbon,

respectively).

EDS line-scans from the edge to the interior of the unbleached BCC crystals showed

that N was not only present within the crystals but also adsorbed on their surface as

the intensity did not drop to zero outside the crystal (Figure **4**a-d). Point scans

showed a lower N:Ca ratio in the centre of the crystals than in the rim (Figure **4**e).

This implies that the internal areas of the precipitate include a lower relative amount

of organics than the rim. HRTEM was used to observe the precipitate rim more in

detail. In the case of *S. clausii*, lattice fringe images and corresponding FFT showed

that, generally, the outermost layer of the bacterial calcite crystals was amorphous,

confirming previous observations [23] (Figure **4**f-h, more examples in Supporting

Figure 7). Moreover, here we also observed amorphous areas, interwoven within the

crystalline lattice (Figure **4**f). This occurred in a region of intermediate contrast and a

few nanometers in thickness at the edge of the crystal, which was N-enriched

according to EDS analysis (N:Ca ratio of 0.53 Figure **4**e). The latter points to

occlusion of organics and/or amorphous calcium carbonate, consistent with the

relatively high Ca content (Figure **4**e).

Figure 4. HRTEM, HADDF-EDS and ss-NMR analysis of bacterial calcium

carbonates. (a) HAADF image of calcite crystal precipitated by *L. fusiformis*. The

porous -Swiss-cheese like- structure of the calcite crystal is visible and the location

of the EDS line scan is indicated (green arrow). **(b)** Brightfield TEM imagae of the

crystal in (a). **(c)** [0$\bar{1}$0] zone axis SAED pattern of the crystal shown in (a) and (b).

Note the marked arcing of diffraction spots (showing an angular spreading of ~9°).

(d) Line scan in (a) showing that N concentration (light blue line) is uncoupled (after

40 nm) to that of Ca (dark blue line), and the increase in N can be traced to the

pores on the calcite crystal (corresponding to the darker areas in (a)). **(e)** *S. clausii*

calcium carbonate structure showing different N/Ca ratios in different areas. **(f)**

HRTEM image of the edge of the precipitate in (e) (Area #2) with FFT of the blue

squared area **(g)** demonstrating it is an amorphous external layer, and the FFT of

the orange squared area **(h)** showing it is a crystallized (calcite) internal zone. The

red outline demarcates the end of the lattice fringes, showing amorphous areas

trapped within the crystalline zone at the rim of the precipitate. **(i)** CP–MAS ^{13}C NMR

spectra of bleached *L. fusiformis* calcite (light red) and synthetic calcite (purple).

The peak at 172 ppm is associated with calcite while the remaining peaks are due to

the presence of amides. Referenced to the signal of DSS (δ = 0 ppm).

Furthermore, an uncoupling of N and Ca was observed on the line-scans in the inner

region of the crystals (> 40 nm from the edge), i.e. when Ca increased, N decreased

(Figure **4**d), albeit with a slight phase-shift. Upon close inspection of HAADF images,

it was clear that the crystals did not show a homogenous surface (Figure **4**a).

Rather, a Swiss cheese-like structure could be observed, with elongated generally

parallel low Z-contrast pore-like areas present within the bacterial calcite single

crystals (more examples in Supporting Figure 8). A direct association of these low Z-

contrast nanoporous-looking areas with an increase in N content was systematically

observed. It could be argued that this porous structure is the result of beam

damage. However, this is ruled out here because the HAADF images were collected

before EDS analysis and the porous structure was already present. Pioneering work

by Towe and Thompson [51], and many other subsequent studies [52] have also shown

that beam damage does not produce such features, but organics do. Moreover, this

structure was also observed in many other BCCs during brightfield TEM analysis and

subsequent SAED analysis showed no CaO diffraction spots/rings which are standard

features of beam damage in calcite [53]. Note also that we have not observed such

Swiss-cheese structure in any studied synthetic calcite crystal. Although a Swiss-

cheese-like structure has never been reported in the case of BCC, similar features

have been observed in other calcium carbonate biominerals, such as mollusc shells

[52,54], and their biomimetic counterparts [55]. The pore-like areas have been usually

identified as intracrystalline organic matter and recently with ACC (see Supporting

Information).

CP-MAS ^{13}C NMR (ss-NMR) and HRXRD were used to confirm the nature of those

observed here, utilizing bleached precipitates. The CP-MAS ^{13}C NMR spectra of

bleached BCC primarily consist of broad peaks, with a notable exception at 168 ppm

attributed to calcite (Figure *4*i), as confirmed by the MAS ^{13}C of synthetic calcite

(Supporting Figure 9). The broad peaks are indicative of amorphous content yet no

well-defined peak was observed closely associated downwards of calcite (167 ppm),

where ACC is typically present [56]. The remaining option for amorphous content must

then be organic in nature. Many broad peaks are present in the 20 - 80 ppm range

and a peak at 172 ppm suggests the presence of carbonyl groups. These shifts are

linked to amino acids which have peaks at 20-60 ppm (CH), and 170-180 ppm

(carbonyl) [57]. Overall, the spectra closely resembles that of eggshells [58] and protein-

including calcite biominerals [59]. The CP-MAS ^{13}C of the synthetic calcite does not

show any bands, as expected (Figure *4*i; see also Supporting Figure 9). This means

that the calcite peak present in the *L. fusiformis* BCC is associated with hydrogen

atoms, only available from either organics or water [56.] Because the presence of

water, such as in monohydrocalcite [56,] should broaden and shift to higher ppm values

the calcite carbonyl bond, we conclude that the hydrogen is from amine or carboxyl

groups from the organics. Lastly, the broadness of the peaks further suggests that

the structure is internal [56]. This suggests that the observed Swiss cheese-like

structure must be present through the whole crystal and not superficially as

seemingly observed on TEM.

To further disclose whether these regions are internal, and related to the organic

signatures ubiquitously observed, we performed HRXRD analyses at the CRYSTAL

beamline of the Soleil synchrotron (Paris, France). HRXRD analysis showed that the

104 and 006 Bragg peaks of bleached BCC produced by *L. fusiformis* were left-

shifted (i.e., to higher *d*-spacings) as compared with geogenic calcite (optical quality

Iceland spar) (Figure 5a, b). The shifting was more marked for the 00*l* reflections,

implying anisotropic lattice distortion. Rietveld full profile fitting analysis [27] yielded

the following refined cell parameters for BCC calcite: a = 4.98900(4) Å; c =

17.08345(5) Å; cell volume = 368.24(4) Å^3, demonstrating a clear anisotropic lattice

distortion as compared with reference geogenic calcite (a = 4.98970(2) Å; c =

17.05900(4) Å; cell volume = 367.82(2) Å^3). Maximum lattice strain was observed

along the [001] direction ($\Delta c/c$=0.0014). This lattice strain fluctuation is within the

range reported for biogenic (e.g., mollusc shell) and biomimetic calcite [60–63]. HRXRD

analysis during *in situ* isochronous heating (annealing) from room T up to 400 °C at

50 °C intervals (see Materials and Methods), showed little changes in $\Delta a/a$ and a

significant $\Delta c/c$ reduction at T > 200 °C (Figure 5c). Reanalysis of the BCC after

annealing at maximum T and subsequent cooling to room T showed permanent

lattice contraction and peak broadening (Figure 5). Pokroy et al. [60,61] observed

exactly the same features following similar (isochronous annealing) HRXRD analysis

of calcite in mollusc shells, demonstrating intracrystalline occlusion of organics (as

solutes) in such biominerals. The preferential expansion along the *c*-axis was

associated with interaction/replacement of carbonate groups placed along (00.1)

planes of calcite by acidic proteins, although interaction with other polar planes such

as (01.2) should also be favoured [60,63]. The authors also stated that thermal

decomposition of occluded organics at T > 200 °C results in strain relaxation and

reduction in $\Delta c/c$, with a parallel increase in peak broadening due to reduction in

crystallite size and increase in microstrain fluctuations, as we have observed here.

Interestingly, we also observed an increase in $\Delta c/c$ of BCC between 100 °C and 200

°C. The latter, also observed in other calcite biominerals such as sea-urchin spicules,

has been associated with the presence of ACC and its thermal-induced

transformation into calcite, which leads to expansion [64]. Altogether, our HRXRD

results confirm that intracrystalline organic occlusions also occur in bacterial calcite,

with very similar anisotropic lattice distortion as in other calcite biominerals such as

mollusc shells. Our HRXRD results also suggest that intracrystalline ACC is present in

the BCC structures, as supported by TEM and ss-NMR results.

Figure 5. Synchrotron HRXRD analysis of *L. fusiformis* calcite. (a) 104 Bragg

peaks and **(b)** 006 Bragg peaks of bacterial calcite before (red) and after annealing

at 400 °C and cooling to room T (light brown). The dashed (purple) profiles show the

reference Iceland spar calcite; **(c)** T-dependent variation of lattice distortion ($\Delta c/c$)

along the c-axis as compared with reference geogenic calcite. The red squared

symbol marks the residual lattice distortion after annealing at 400 °C and cooling to

room *T*.

Role of crystalline 2D organic films in BCC formation

During TEM imaging of *L. fusiformis* biogenic precipitates we unexpectedly observed

layered structures containing areas of amorphous and crystalline carbonates (Figure

6a). HRTEM imaging showed that these film-like structures were crystalline

displaying lattice fringes oriented in different directions. SAED analysis of the film-

like structures revealed diffraction spots with *d*-spacings 3.7 − 4.5 nm aligned in

rows with different orientations corresponding to the multiple orientations of the

lattice fringes visualized in the HRTEM image (Figure 6a,b yellow and green lines),

along with diffraction spots corresponding to (at least two non-oriented) calcite

crystals (Figure 6c). The *d*-spacings of the films is at the scale of those measured in

protein crystalline structures [65] but full characterization of these structures to confirm

if they were made up of proteins was not possible. HRTEM images showed the

carbonates closely associated with these 2D crystalline films. The crystalline films

were less visible on higher density patches indicating that they were placed at the

"bottom" of calcite. However, as shown in Supporting Figure 10a, we could observe

in other examples a close relationship between the film and an overlying

nanogranular structure, with a SAED pattern corresponding to a calcite single crystal

(Supporting Figure 10b). These results suggest that the formation of oriented calcite

after particle attachment of ACC is templated by the film underneath, in a similar

fashion as that reported on S-layers [66] or carbonic anhydrase films [67] (see

Supporting Information).

Figure 6. HRTEM analysis of *L. fusiformis* calcite formed on an organic crystalline 2D template. (a) A polycrystal showing different amorphous and crystalline phases, alongside crystalline 2D film showing lattice fringes. **(b)** Zoom-in of the blue squared area in (a) showing lattice fringes in the 2D films. The yellow and green lines show the direction of the lattice fringes. **(c)** SAED pattern of the red circled area in (a) showing different diffraction spots corresponding to calcite ($[0\bar{1}0]$ zone axis, calculated using the most intense diffraction spots: note that additional orientations are present) overprinted with diffraction spots of the (organic) films (the green and yellow lines mark the three aligned spots corresponding to the films in (b) with lattice fringes oriented along the green and yellow lines).

Discussion

FESEM showed that the bacteria were closely associated with the BCC crystals and that a nanogranular texture was present, suggesting the formation through an ACC precursor. XRD indicated that all carbonates were calcite, while amorphous and organic signatures were detected with FTIR and TGA in both bleached and unbleached samples. TEM analysis showed the presence of both crystalline and amorphous calcium carbonate, the latter being more predominant in *L. fusiformis*, in

agreement with FTIR spectra. In the individual crystals, amorphous areas were

present at the rim of the BCCs, likely the growth front of the crystal, in both

bacteria. TEM-EDS mapping unveiled the presence of organic-related elements in the

bacterial crystals, including N, (and S and P to a lesser extent) associated with both

crystalline and amorphous regions of calcium carbonate precipitates. Importantly, we

observed low Z-contrast pore areas that resembled a Swiss cheese-like structure

thoroughly reported in calcifying metazoans [26,54], and a strong correlation with N was

detected in the low Z-contrast regions. CP-MAS C^{13} NMR pointed at the presence of

amino acids in a strikingly similar way as in other protein-including calcite

biominerals [59]. TEM-EDS and ss-NMR results helped clarify that the observed FTIR

bands correspond to amide bonds (Amide I band (1600 – 1700 cm^{-1}); Amide II:

1540 cm^{-1} likely attributed to a C=N bond [68] and C-N-C=O bonds at 1499 cm^{-1} [69];

Amide III band 1250 – 1350 cm^{-1} [69]). The overall strong indication of amides points

to peptides having a role in the biomineralization process, although no particular

macromolecule was determined.

The detection of organic signatures by FTIR and TGA after bleaching suggests that

an organic fraction remained bound to the BCCs. Three possibilities exists for this

explanation: (i) the bleaching is not sufficient to remove all organics from the

precipitate surface, (ii) the organics can also be structurally bound and protected

from the bleaching by being occluded in the precipitates, or (iii) both. The presence

of organic occlusions in BCCs is as of yet unreported and could have important

practical implications while changing our understanding of how biomineralization in

bacteria works (see below). While ss-NMR supports the second hypothesis, HRXRD

unambiguously shows that this fraction was (in part), intracrystalline organic

occlusions. HRXRD shows that the amino acids/peptides are intracrystalline, as there

was a marked lattice strain (expansion) along the *c*-axis, and a lattice contraction

was observed along the *c*-axis direction after annealing (up to 400 °C). Similar

behaviour has been observed using HRXRD in the case of calcite biominerals

produced by eukaryotes and their biomimetic counterparts [60–62]. Note that the

nanometer-sized porous areas filled with N-rich organics forming the Swiss-cheese

structure are, however, too large to account for the lattice strain fluctuations

determined by HRXRD. Apparently, organics are occluded in BCCs at two scales: the

atomic scale (as solutes in the calcite crystal lattice) resulting in the observed lattice

strain, and the mesoscale (as nanometer-sized clusters) as observed here with TEM.

This latter nanometer size occlusion could be responsible for the angular spreading

observed in SAED patterns and become occluded as the crystal grows at the rim.

This is consistent with the amorphous phases occluded inside the crystal lattice

observed in HRTEM analysis. Similar organic occlusion occurs in several calcium

carbonate biominerals produced by eukaryotes [52]. Note that foreign nanoparticle

occlusion results in peak broadening due to microstrain contributions associated with

the creation of intracrystalline boundaries acting as a source of inhomogeneous

deformation fields but without necessarily contributing to macrostrain, i.e., lattice

distortion [61]. These results are consistent with the ss-NMR results as the broad peaks

of the CP–MAS ^{13}C NMR spectra point to intracrystalline presence of the amino

signatures. Finally, the confirmed role of organics in the crystallization process,

explain the preferential growth of BCC calcite along the *c*-axis, with overdeveloped

{110} (pseudo)faces, which are typically formed during calcite growth following

adsorption of organics on acute steps [70]. Besides the organic signatures, we also

report strong indications of ACC presence throughout the whole study, even after

bleaching. If the organics remain occluded, then this suggests that ACC is also

occluded, and likely stabilized by the organics as observed elsewhere[37]. However,

further analysis is needed to unambiguously prove this such as that presented by De

Frutos et al. [26].

The evidence presented here supports the mechanism of precipitation originally

alluded to by Enyedi et al. [23], where ACC is stabilized by EPS, and calcite forms

through PA. However, we clarify several missing aspects after ACC stabilization.

Firstly, we propose that BCC grows by aggregation of protein-stabilized ACC, rather

than the more broadly assigned EPS. This is consistent with the intracrystalline

occlusion in BCC calcite crystals of both peptides and ACC. Moreover, we observed

that larger crystalline 2D films structures, not only stabilize, but act as a template for

crystal formation. This film had *d*-spacings in the range of those observed in

crystalline protein films, although the molecular features of the films could not be

fully characterized. The stabilized ACC then undergoes an amorphous-to-crystalline

conversion, at which point the intracrystalline occlusion of a fraction of the organics

associated with ACC occurs. This closely resembles the current model of

biomineralization of calcite biominerals in eukaryotes [26]. Our proposition is in

contrast to what was previously suggested for bacteria, where organics were

assumed to be completely ejected [23]. Biomineralization through the eukaryotic model

involving an ACC precursor commonly produces a nanogranular structure and results

in a Swiss cheese-like structure, as observed here. Even more remarkable, de Frutos

and colleagues proposed a model for calcite biomineralization in animals wherein

pellicle-like regions of concentrated organics are formed [26]. These are starkly similar

to the orderly fashion in which the pore-like N-rich structures were observed in our

bacteria biominerals. Moreover, the transformation of ACC nanoparticles into calcite

occurs in crystallographic register with the core calcite, which explains the single

crystal features of the SAED patterns. Still, some miss-orientation occurs, resulting

in the observed angular spreading and the mesocrystal features described above,

which are also observed in calcite biominerals produced by eukaryotes, as it is the

case of sea-urchin spicules [71]. This could point towards a shared biomineralization

process, but future research needs to explore such hypothesis.

On top of other calcium carbonate biominerals, similar structures as those observed

for the BCCs in this work form in biomimetic *in vitro* models [55]. This might not be

surprising given that many processes proposed for the formation of calcite

biominerals have been shown to be thermodynamically favourable (i.e., down-hill

energy landscape) [36]. Yet, critically, in these models the carbonate crystals do not

display the highly organized organic-inorganic nanostructure observed in

biominerals, in general, and in our BCCs, in particular. Thus, the organization of the

BCCs mesocrystals and the hierarchy in organic occlusions observed in this work

could contradict the common idea that calcium carbonate biomineral precipitation by

microorganisms - in contrast $CaCO_3$ biominerals produced by eukaryotes - is a

spontaneous and uncontrolled phenomenon [8]. Furthermore, other authors are

already scrutinizing the idea that calcium carbonate biomineralization in prokaryotes

is functionless [72]. Some recent work points to real adaptive benefits for MICP. For

example, Botusharova et al. [12] showed that bacterial spores could survive

entombment in carbonate precipitates, being autoclaved and then reactivated. More

recently, it was shown that the precipitation of calcium carbonate had a central role

in the effective formation of biofilm in pathogenic bacteria with genetic inhibition of

carbonate biomineralization leading to a reduced pathogenicity and biofilm formation

[10]. On the other hand, control over the precipitation process could provide protection

to the bacteria from unfavourable conditions by controlling the rate and location on

the cell where precipitates form, for example to prevent unwanted entombment [66],

or reduce damage from toxic metals by removing these from the surrounding

environment through (co)precipitation in carbonates [73]. Although the work remains

limited, investing energy in producing organics that will create a controlled process

of biomineralization might contribute to the inclusive fitness of the organism.

Aside from the evolutionary standpoint, there is technical applicability to these

results. The observations of intracrystalline organics and possibly also ACC, implies

that there might be improved mechanical properties for BCCs. Intracrystalline

organic matter that occurs in other calcium carbonate biominerals such as mollusk

shells, lead to improved mechanical properties (e.g. increased toughness) [52].

Moreover, stabilized ACC as a precursor prior to transitioning to calcite has been

shown in different biomineral composites to lead to improved structural properties [74].

This observations can have implications in the technical applications of microbial

biominerals, such as in bioengineering applications of MICP, like self-healing cements

or the consolidation of stone built heritage. Moreover, identification of these

biosignatures could pave the way for determining biogenicity of carbonate samples in

the geologic record, which is not always straight forward. As such, understanding

how these mechanisms work and are controlled can open up the door for novel

biomaterial applications with purposely designed structure-function.

Supporting information

Additional experimental details and results including Supporting Figures 1 – 10 and

Supporting Table 1.

Acknowledgments

We thank the personnel of the Centro de Instrumentación Científica (CIC) of the

University of Granada for helping with FESEM and TEM analyses and the Inorganic

Chemistry department for access to their FTIR. Additional thanks go to the personnel

of the Department of Mineralogy and Petrology of the University of Granada for their

help with the instrumentations, including Teodora Ilić, Sarah Bonilla Correa, Aurélie

Pace and Miguel Burgos Ruiz. Special thanks go to Kerstin Elert for her help with the

SEM imaging and Fadwa Jroundi Mesbahi for allowing to grow our bacterial cultures

at her facilities. HRXRD experiments were performed at CRYSTAL beamline at SOLEIL

Synchrotron with the help of this beamline staff (E. Elkaim). We also thank Julia

Atienzar, Aurelie Pace, and Nuria Pujol Solà for their help during HRXRD analyses at

SOLEIL synchrotron and Alejandro Rodriguez-Navarro for his help during Rietveld

analysis of HRXRD results.

Author Contributions:

FGG contributed Conceptualization, Methodology, Investigation, Visualization,

Supervision, Writing (original draft), Writing (review and editing)

MP contributed Conceptualization, Investigation, Visualization, Writing (original

draft), Writing (review and editing)

NB contributed Conceptualization, Supervision, Writing (review and editing), Funding

acquisition

NDB contributed Conceptualization, Supervision, Writing (review and editing),

Funding acquisition

CR-N contributed Conceptualization, Methodology, Investigation, Visualization,

Supervision, Writing (original draft), Writing (review and editing), Funding acquisition

Competing Interest Statement: The authors declare no competing interest.

Funding: This work was funded by Spanish Government grant

PID2021.125305NB.I00 funded by MCIN/ AEI /10.13039/501100011033 and by

ERDF A way of making Europe (to C.R.-N.); Junta de Andalucía and ERDF grant B-

RNM-574-UGR20 and research group RNM-179 (to C.R.-N.); University of Granada,

Unidad Científica de Excelencia UCE-PP2016-05 (to C.R.-N.). Funding was also

provided by the European Union's Horizon 2020 research and innovation programme

under Marie Sklodowska-Curie project SUBLime [Grant Agreement n∘955986]. 500

MHz CP-MAS ssNMR was funded by Hercules foundation AUGE/09/2006 and FWO

I006920N.

References

(1)   Lowestam, H. A.; Weiner, S. *On Biomineralization*, 1st ed.; Oxford University

796   Press: New York, 1989.

797   (2)   Raven, J. A.; Giordano, M. Biomineralization by Photosynthetic Organisms:

798   Evidence of Coevolution of the Organisms and Their Environment? *Geobiology*

799   **2009**, *7* (2), 140–154. https://doi.org/10.1111/j.1472-4669.2008.00181.x.

800   (3)   Addadi, L.; Raz, S.; Weiner, S. Taking Advantage of Disorder: Amorphous

801   Calcium Carbonate and Its Roles in Biomineralization. *Adv. Mater.* **2003**, *15*

802   (12), 959–970. https://doi.org/10.1002/adma.200300381.

803   (4)   Schopf, J. W. Solution to Darwin's Dilemma: Discovery of the Missing

804   Precambrian Record of Life. *Proc. Natl. Acad. Sci. U. S. A.* **2000**, *97* (13),

805   6947–6953. https://doi.org/10.1073/pnas.97.13.6947.

806   (5)   Boquet, E.; Boronat, A.; Ramos-Cormenzana, A. Production of Calcite (Calcium

807   Carbonate) Crystals by Soil Bacteria Is a General Phenomenon. *Am. J. Med.*

Sci. **1973**, *242* (2), 527. https://doi.org/10.1097/00000441-196108000-

00035.

(6)   Fujita, Y.; Grant Ferris, F.; Daniel Lawson, R.; Colwell, F. S.; Smith, R. W.

Calcium Carbonate Precipitation by Ureolytic Subsurface Bacteria.

Geomicrobiol. J. **2000**, *17* (4), 305–318. https://doi.org/10.1080/782198884.

(7)   Seifan, M.; Berenjian, A. Microbially Induced Calcium Carbonate Precipitation:

A Widespread Phenomenon in the Biological World. *Appl. Microbiol. Biotechnol.*

2019, *103* (12), 4693–4708. https://doi.org/10.1007/s00253-019-09861-5.

(8)   Frankel, R. B.; Bazylinski, D. Biologically Induced Mineralization by Bacteria.

Rev. Mineral. Geochemistry **2003**, *54* (1), 95–114.

https://doi.org/10.2113/0540095.

(9)   Cosmidis, J.; Benzerara, K. Why Do Microbes Make Minerals? *Comptes Rendus*

- Geosci. **2022**, *354* (1), 1–39. https://doi.org/10.5802/CRGEOS.107.

(10)   Cohen-Cymberknoh, M.; Kolodkin-Gal, D.; Keren-Paz, A.; Peretz, S.;

Brumfeld, V.; Kapishnikov, S.; Suissa, R.; Shteinberg, M.; McLeod, D.; Maan,

H.; Patrauchan, M.; Zamir, G.; Kerem, E.; Kolodkin-Gal, I. Calcium Carbonate

Mineralization Is Essential for Biofilm Formation and Lung Colonization.

iScience **2022**, *25* (5), 104234. https://doi.org/10.1016/j.isci.2022.104234.

(11)   Oppenheimer-Shaanan, Y.; Sibony-Nevo, O.; Bloom-Ackermann, Z.; Suissa,

R.; Steinberg, N.; Kartvelishvily, E.; Brumfeld, V.; Kolodkin-Gal, I. Spatio-

Temporal Assembly of Functional Mineral Scaffolds within Microbial Biofilms.

npj Biofilms Microbiomes **2016**, *2*, 15031. https://doi.org/10.1038/npjbio.

(12)   Botusharova, S.; Gardner, D.; Harbottle, M. Augmenting Microbially Induced

Carbonate Precipitation of Soil with the Capability to Self-Heal. *J. Geotech.*

Geoenvironmental Eng. **2020**, *146* (4), 04020010.

https://doi.org/10.1061/(asce)gt.1943-5606.0002214.

(13) Baumgartner, L. K.; Reid, R. P.; Dupraz, C.; Decho, A. W.; Buckley, D. H.;

Spear, J. R.; Przekop, K. M.; Visscher, P. T. Sulfate Reducing Bacteria in

Microbial Mats: Changing Paradigms, New Discoveries. *Sediment. Geol.* **2006**,

185 (3-4 SPEC. ISS.), 131–145.

https://doi.org/10.1016/j.sedgeo.2005.12.008.

(14) Erşan, Y. Ç.; De Belie, N.; Boon, N. Microbially Induced CaCO3 Precipitation

through Denitrification: An Optimization Study in Minimal Nutrient

Environment. *Biochem. Eng. J.* **2015**, *101*, 108–118.

https://doi.org/10.1016/j.bej.2015.05.006.

(15) Stocks-Fischer, S.; Galinat, J. K.; Bang, S. S. Microbiological Precipitation of

CaCO3. *Soil Biol. Biochem.* **1999**, *31* (11), 1563–1571.

https://doi.org/10.1016/S0038-0717(99)00082-6.

(16) Rivadeneyra, M. A.; Delgado, R.; Moral, A.; Ferrer, M. R.; Ramos-

Cormenzana, A. Precipatation of Calcium Carbonate by Vibrio Spp. from an

Inland Saltern. *FEMS Microbiol. Ecol.* **1994**, *13* (3), 197–204.

https://doi.org/10.1111/j.1574-6941.1994.tb00066.x.

(17) Ehrlich, H. L. *Ehrlich's Geomicrobiology*, Sixth.; Ehrlich, H. L., Newman, D. K.,

Kappler, A., Eds.; Taylor & Francis, 2016.

(18) Tourney, J.; Ngwenya, B. T. The Role of Bacterial Extracellular Polymeric

Substances in Geomicrobiology. *Chem. Geol.* **2014**, *386*, 115–132.

https://doi.org/10.1016/j.chemgeo.2014.08.011.

(19) Benzerara, K.; Menguy, N.; López-García, P.; Yoon, T. H.; Kazmierczak, J.;

Tyliszczak, T.; Guyot, F.; Brown, G. E. Nanoscale Detection of Organic

Signatures in Carbonate Microbialites. *Proc. Natl. Acad. Sci. U. S. A.* **2006**,

103 (25), 9440–9445. https://doi.org/10.1073/pnas.0603255103.

(20) Lyu, J.; Li, F.; Long, H.; Zhu, X.; Fu, N.; Guo, Z.; Zhang, W. Bacterial

Templated Carbonate Mineralization: Insights from Concave-Type Crystals

Induced by Curvibacter Lanceolatus Strain HJ-1. *RSC Advances*. 2024, pp

353–363. https://doi.org/10.1039/d3ra06803j.

(21) Lyu, J.; Qin, W.; Zhang, C.; Li, F. Nanoparticle Accumulation in Microbial

Induced Carbonate Precipitation: The Crucial Role of Extracellular Polymeric

Substance. *Geomicrobiol. J.* **2020**, *0* (0), 837–847.

https://doi.org/10.1080/01490451.2020.1786866.

(22) Chen, L.; Shen, Y.; Xie, A.; Huang, B.; Jia, R.; Guo, R.; Tang, W. Bacteria-

Mediated Synthesis of Metal Carbonate Minerals with Unusual Morphologies

and Structures. *Cryst. Growth Des.* **2009**, *9* (2), 743–754.

https://doi.org/10.1021/cg800224s.

(23) Enyedi, N. T.; Makk, J.; Kótai, L.; Berényi, B.; Klébert, S.; Sebestyén, Z.;

Molnár, Z.; Borsodi, A. K.; Leél-Őssy, S.; Demény, A.; Németh, P. Cave

Bacteria-Induced Amorphous Calcium Carbonate Formation. *Sci. Rep.* **2020**,

10 (1), 1–12. https://doi.org/10.1038/s41598-020-65667-w.

(24) Marvasi, M.; Gallagher, K. L.; Martinez, L. C.; Molina Pagan, W. C.; Rodríguez

Santiago, R. E.; Castilloveitía Vega, G.; Visscher, P. T. Importance of B4

Medium in Determining Organomineralization Potential of Bacterial

Environmental Isolates. *Geomicrobiol. J.* **2012**, *29* (10), 916–924.

https://doi.org/10.1080/01490451.2011.636145.

(25) Seifan, M.; Samani, A. K.; Berenjian, A. Induced Calcium Carbonate

Precipitation Using Bacillus Species. *Appl. Microbiol. Biotechnol.* **2016**, *100*

(23), 9895–9906. https://doi.org/10.1007/s00253-016-7701-7.

(26) de Frutos, M.; Rodríguez-Navarro, A. B.; Li, X.; Checa, A. G. Nanoscale

Analysis of the Structure and Composition of Biogenic Calcite Reveals the

Biomineral Growth Pattern. *ACS Nano* **2023**, *17* (3), 2829–2839.

https://doi.org/10.1021/acsnano.2c11169.

(27)   Rietveld, H. M. Line Profiles of Neutron Powder-Diffraction Peaks for Structure

Refinement. *Acta Crystallogr.* **1967**, *22* (1), 151–152.

https://doi.org/10.1107/s0365110x67000234.

(28)   Markgraf, S. A.; Reeder, R. J. High-Temperature Structure Refinements of

Calcite and Magnesite. *Am. Mineral.* **1985**, *70* (5), 590–600.

(29)   Yan, H.; Han, Z.; Zhao, H.; Pan, J.; Zhao, Y.; Tucker, M. E.; Zhou, J.; Yan, X.;

Yang, H.; Fan, D. The Bio-Precipitation of Calcium and Magnesium Ions by

Free and Immobilized Lysinibacillus Fusiformis DB1-3 in the Wastewater. *J.*

Clean. Prod. **2020**, *252*, 119826.

https://doi.org/10.1016/j.jclepro.2019.119826.

(30)   Park, S. J.; Park, Y. M.; Chun, W. Y.; Kim, W. J.; Ghim, S. Y. Calcite-Forming

Bacteria for Compressive Strength Improvement in Mortar. *J. Microbiol.*

Biotechnol. **2010**, *20* (4), 782–788. https://doi.org/10.4014/JMB.0911.11015.

(31)   Chekroun, K. Ben; Rodríguez-Navarro, C.; González-Muñoz, M. T.; Arias, J.

M.; Cultrone, G.; Rodríguez-Gallego, M. Precipitation and Growth Morphology

of Calcium Carbonate Induced by Myxococcus Xanthus: Implications for

Recognition of Bacterial Carbonates. *J. Sediment. Res.* **2004**, *74* (6), 868–

876. https://doi.org/10.1306/050504740868.

(32)   Gilbert, P. U. P. A.; Bergmann, K. D.; Boekelheide, N.; Tambutté, S.; Mass, T.;

Marin, F.; Adkins, J. F.; Erez, J.; Gilbert, B.; Knutson, V.; Cantine, M.;

Hernández, J. O.; Knoll, A. H. Biomineralization: Integrating Mechanism and

Evolutionary History. *Sci. Adv.* **2022**, *8* (10).

https://doi.org/10.1126/sciadv.abl9653.

(33)   Rodriguez-Navarro, C.; Burgos Cara, A.; Elert, K.; Putnis, C. V.; Ruiz-Agudo,

E. Direct Nanoscale Imaging Reveals the Growth of Calcite Crystals via

Amorphous Nanoparticles. *Cryst. Growth Des.* **2016**, *16* (4), 1850–1860.

https://doi.org/10.1021/acs.cgd.5b01180.

(34) De Yoreo, J. J.; Gilbert, P. U. P. A.; Sommerdijk, N. A. J. M.; Penn, R. L.;

Whitelam, S.; Joester, D.; Zhang, H.; Rimer, J. D.; Navrotsky, A.; Banfield, J.

F.; Wallace, A. F.; Michel, F. M.; Meldrum, F. C.; Cölfen, H.; Dove, P. M.

Crystallization by Particle Attachment in Synthetic, Biogenic, and Geologic

Environments. *Science (80-.).* **2015**, *349* (6247).

https://doi.org/10.1126/science.aaa6760.

(35) Wolf, S. E.; Böhm, C. F.; Harris, J.; Demmert, B.; Jacob, D. E.; Mondeshki,

M.; Ruiz-Agudo, E.; Rodríguez-Navarro, C. Nonclassical Crystallization in Vivo

et in Vitro (I): Process-Structure-Property Relationships of Nanogranular

Biominerals. *J. Struct. Biol.* **2016**, *196* (2), 244–259.

https://doi.org/10.1016/j.jsb.2016.07.016.

(36) Rodríguez-Navarro, C.; Ruiz-Agudo, E.; Harris, J.; Wolf, S. E. Nonclassical

Crystallization in Vivo et in Vitro (II): Nanogranular Features in Biomimetic

Minerals Disclose a General Colloid-Mediated Crystal Growth Mechanism. *J.*

Struct. Biol. **2016**, *196* (2), 260–287.

https://doi.org/10.1016/j.jsb.2016.09.005.

(37) Gong, Y. U. T.; Killian, C. E.; Olson, I. C.; Appathurai, N. P.; Amasino, A. L.;

Martin, M. C.; Holt, L. J.; Wilt, F. H.; Gilbert, P. U. P. A. Phase Transitions in

Biogenic Amorphous Calcium Carbonate. *Proc. Natl. Acad. Sci. U. S. A.* **2012**,

109 (16), 6088–6093.

https://doi.org/10.1073/PNAS.1118085109/SUPPL_FILE/SM02.MOV.

(38) DeOliveira, D. B.; Laursen, R. A. Control of Calcite Crystal Morphology by a

Peptide Designed to Bind to a Specific Surface. *J. Am. Chem. Soc.* **1997**, *119*

(44), 10627–10631. https://doi.org/10.1021/ja972270w.

(39)   Teng, H. H.; Dove, P. M. Surface Site-Specific Interactions of Aspartate with

939   Calcite during Dissolution: Implications for Biomineralization. *Am. Mineral.*

940   **1997**, *82* (9–10), 878–887. https://doi.org/10.2138/am-1997-9-1005.

941   (40)   Rodríguez-Navarro, A. B.; Marie, P.; Nys, Y.; Hincke, M. T.; Gautron, J.

942   Amorphous Calcium Carbonate Controls Avian Eggshell Mineralization: A New

943   Paradigm for Understanding Rapid Eggshell Calcification. *J. Struct. Biol.* **2015**,

944   *190* (3), 291–303. https://doi.org/10.1016/j.jsb.2015.04.014.

945   (41)   Beniash, E.; Aizenberg, J.; Addadi, L.; Weiner, S. Amorphous Calcium

946   Carbonate Transforms into Calcite during Sea Urchin Larval Spicule Growth.

947   *Proc. R. Soc. B Biol. Sci.* **1997**, *264* (1380), 461–465.

948   https://doi.org/10.1098/rspb.1997.0066.

949   (42)   Ihli, J.; Wong, W. C.; Noel, E. H.; Kim, Y. Y.; Kulak, A. N.; Christenson, H. K.;

950   Duer, M. J.; Meldrum, F. C. Dehydration and Crystallization of Amorphous

951   Calcium Carbonate in Solution and in Air. *Nat. Commun.* **2014**, *5*, 1–10.

952   https://doi.org/10.1038/ncomms4169.

953   (43)   Mehta, N.; Gaëtan, J.; Giura, P.; Azaïs, T.; Benzerara, K. Detection of Biogenic

954   Amorphous Calcium Carbonate (ACC) Formed by Bacteria Using FTIR

955   Spectroscopy. *Spectrochim. Acta - Part A Mol. Biomol. Spectrosc.* **2022**, *278*,

956   121262. https://doi.org/10.1016/j.saa.2022.121262.

957   (44)   Ryparová, P.; Prošek, Z.; Schreiberová, H.; Bílý, P.; Tesárek, P. The Role of

958   Bacterially Induced Calcite Precipitation in Self-Healing of Cement Paste. *J.*

959   *Build. Eng.* **2021**, *39* (October 2020).

960   https://doi.org/10.1016/j.jobe.2021.102299.

961   (45)   Pavia, D. L.; Lampman, G. M.; Kriz, G. S.; Vyvyan, J. R. Infrared

962   Spectroscopy. In *Introduction to Spectroscopy*; Cengage Learning: Stamford,

963   CT, 2015; pp 14–106. https://doi.org/10.1016/S1460-1567(00)80010-0.

(46) Schmidt, M. P.; Ilott, A. J.; Phillips, B. L.; Reeder, R. J. Structural Changes

upon Dehydration of Amorphous Calcium Carbonate. *Cryst. Growth Des.*

2014, *14* (3), 938–951. https://doi.org/10.1021/cg401073n.

(47) Rodríguez-Navarro, A. B.; Grenier, C.; Checa, A. G.; Jiménez-López, C.;

Sánchez-Sánchez, P.; Bertone, D.; Lagos, N. A. Role of the Organic Matter in

the Structural Organization of Giant Barnacle Austromegabalanus Psittacus

Shell from the Micro- To Nanoscale. *Cryst. Growth Des.* **2021**, *21* (1), 357–

365. https://doi.org/10.1021/acs.cgd.0c01222.

(48) Valverde, J. M.; Perejon, A.; Medina, S.; Perez-Maqueda, L. A. Thermal

Decomposition of Dolomite under CO2: Insights from TGA and in Situ XRD

Analysis. *Phys. Chem. Chem. Phys.* **2015**, *17* (44), 30162–30176.

https://doi.org/10.1039/c5cp05596b.

(49) Cölfen, H.; Antonietti, M. Mesocrystals: Inorganic Superstructures Made by

Highly Parallel Crystallization and Controlled Alignment. *Angew. Chemie - Int.*

Ed. **2005**, *44* (35), 5576–5591. https://doi.org/10.1002/anie.200500496.

(50) Bergström, L.; Sturm née Rosseeva, E. V.; Salazar-Alvarez, G.; Cölfen, H.

Mesocrystals in Biominerals and Colloidal Arrays. *Acc. Chem. Res.* **2015**, *48*

(5), 1391–1402. https://doi.org/10.1021/ar500440b.

(51) Towe, K. M.; Thompson, G. R. The Structure of Some Bivalve Shell Carbonates

Prepared by Ion-Beam Thinning - A Comparison Study. *Calcif. Tissue Res.*

1972, *10* (1), 38–48. https://doi.org/10.1007/BF02012534.

(52) Deng, Z.; Jia, Z.; Li, L. Biomineralized Materials as Model Systems for

Structural Composites: Intracrystalline Structural Features and Their

Strengthening and Toughening Mechanisms. *Adv. Sci.* **2022**, *9*, 2103524.

https://doi.org/10.1002/advs.202103524.

(53) Rodriguez-Navarro, C.; Ruiz-Agudo, E.; Luque, A.; Rodriguez-Navarro, A. B.;

Ortega-Huertas, M. Thermal Decomposition of Calcite: Mechanisms of Formation and Textural Evolution of CaO Nanocrystals. *Am. Mineral.* **2009**, *94* (4), 578–593. https://doi.org/10.2138/am.2009.3021.

(54) Li, H.; Xin, H. L.; Kunitake, M. E.; Keene, E. C.; Muller, D. A.; Estroff, L. A. Calcite Prisms from Mollusk Shells (Atrina Rigida): Swiss-Cheese-like Organic-Inorganic Single-Crystal Composites. *Adv. Funct. Mater.* **2011**, *21* (11), 2028–2034. https://doi.org/10.1002/adfm.201002709.

(55) Li, H.; Xin, H. L.; Muller, D. A.; Estroff, L. A. Visualizing the 3D Internal Structure of Agarose Hydrogels. *Science (80-.).* **2009**, *326* (November), 1244–1247.

(56) Nebel, H.; Neumann, M.; Mayer, C.; Epple, M. On the Structure of Amorphous Calcium Carbonate - A Detailed Study by Solid-State NMR Spectroscopy. *Inorg. Chem.* **2008**, *47* (17), 7874–7879. https://doi.org/10.1021/ic8007409.

(57) Chaloupecká, E.; Tyrpekl, V.; Bártová, K.; Nishiyama, Y.; Dračínský, M. NMR Crystallography of Amino Acids. *Solid State Nucl. Magn. Reson.* **2024**, *130* (November 2023). https://doi.org/10.1016/j.ssnmr.2024.101921.

(58) Pisklak, D. M. I.; Szeleszczuk, Ł.; Wawer, I. 1H and 13C Magic-Angle Spinning Nuclear Magnetic Resonance Studies of the Chicken Eggshell. *J. Agric. Food Chem.* **2012**, *60* (50), 12254–12259. https://doi.org/10.1021/jf304230g.

(59) Kababya, S.; Ben Shir, I.; Schmidt, A. From Molecular Level to Macroscopic Properties: A Solid-State NMR Biomineralization and Biomimetic Exploration. *Curr. Opin. Colloid Interface Sci.* **2022**, *62*, 101630. https://doi.org/10.1016/j.cocis.2022.101630.

(60) Pokroy, B.; Fitch, A. N.; Marin, F.; Kapon, M.; Adir, N.; Zolotoyabko, E. Anisotropic Lattice Distortions in Biogenic Calcite Induced by Intra-Crystalline Organic Molecules. *J. Struct. Biol.* **2006**, *155* (1), 96–103.

https://doi.org/10.1016/j.jsb.2006.03.008.

(61) Pokroy, B.; Fitch, A. N.; Zolotoyabko, E. The Microstructure of Biogenic

Calcite: A View by High-Resolution Synchrotron Powder Diffraction. *Adv.*

Mater. **2006**, *18* (18), 2363–2368. https://doi.org/10.1002/adma.200600714.

(62) Aizenberg, J.; Hanson, J.; Koetzle, T. F.; Weiner, S.; Addadi, L. Control of

Macromolecule Distribution within Synthetic and Biogenic Single Calcite

Crystals. *J. Am. Chem. Soc.* **1997**, *119* (5), 881–886.

https://doi.org/10.1021/ja9628821.

(63) Lang, A.; Mijowska, S.; Polishchuk, I.; Fermani, S.; Falini, G.; Katsman, A.;

Marin, F.; Pokroy, B. Acidic Monosaccharides Become Incorporated into Calcite

Single Crystals**. *Chem. - A Eur. J.* **2020**, *26* (70), 16860–16868.

https://doi.org/10.1002/chem.202003344.

(64) Albéric, M.; Caspi, E. N.; Bennet, M.; Ajili, W.; Nassif, N.; Azaïs, T.; Berner,

A.; Fratzl, P.; Zolotoyabko, E.; Bertinetti, L.; Politi, Y. Interplay between

Calcite, Amorphous Calcium Carbonate, and Intracrystalline Organics in Sea

Urchin Skeletal Elements. *Cryst. Growth Des.* **2018**, *18* (4), 2189–2201.

https://doi.org/10.1021/acs.cgd.7b01622.

(65) Stevenson, H. P.; Makhov, A. M.; Calero, M.; Edwards, A. L.; Zeldin, O. B.;

Mathews, I. I.; Lin, G.; Barnes, C. O.; Santamaria, H.; Ross, T. M.; Soltis, S.

M.; Khosla, C.; Nagarajan, V.; Conway, J. F.; Cohen, A. E.; Calero, G. Use of

Transmission Electron Microscopy to Identify Nanocrystals of Challenging

Protein Targets. *Proc. Natl. Acad. Sci. U. S. A.* **2014**, *111* (23), 8470–8475.

https://doi.org/10.1073/pnas.1400240111.

(66) Schultze-Lam, S.; Beveridge, T. J. Nucleation of Celestite and Strontianite on a

Cyanobacterial S-Layer. *Appl. Environ. Microbiol.* **1994**, *60* (2).

(67) Rodriguez-Navarro, C.; Cizer, Ö.; Kudłacz, K.; Ibañez-Velasco, A.; Ruiz-

1042   Agudo, C.; Elert, K.; Burgos-Cara, A.; Ruiz-Agudo, E. The Multiple Roles of

1043   Carbonic Anhydrase in Calcium Carbonate Mineralization. *CrystEngComm*

1044   **2019**, *21* (48), 7407–7423. https://doi.org/10.1039/c9ce01544b.

1045 (68) Murdock, J. N.; Wetzel, D. L. FT-IR Microspectroscopy Enhances Biological and

1046   Ecological Analysis of Algae. *Appl. Spectrosc. Rev.* **2009**, *44* (4), 335–361.

1047   https://doi.org/10.1080/05704920902907440.

1048 (69) Ji, Y.; Yang, X.; Ji, Z.; Zhu, L.; Ma, N.; Chen, D.; Jia, X.; Tang, J.; Cao, Y.

1049   DFT-Calculated IR Spectrum Amide I, II, and III Band Contributions of N-

1050   Methylacetamide Fine Components. *ACS Omega*. 2020, pp 8572–8578.

1051   https://doi.org/10.1021/acsomega.9b04421.

1052 (70) Kim, Y. Y.; Ganesan, K.; Yang, P.; Kulak, A. N.; Borukhin, S.; Pechook, S.;

1053   Ribeiro, L.; Kröger, R.; Eichhorn, S. J.; Armes, S. P.; Pokroy, B.; Meldrum, F.

1054   C. An Artificial Biomineral Formed by Incorporation of Copolymer Micelles in

1055   Calcite Crystals. *Nat. Mater.* **2011**, *10* (11), 890–896.

1056   https://doi.org/10.1038/nmat3103.

1057 (71) Seto, J.; Ma, Y.; Davis, S. A.; Meldrum, F.; Gourrier, A.; Kim, Y. Y.; Schilde,

1058   U.; Sztucki, M.; Burghammer, M.; Maltsev, S.; Jäger, C.; Cölfen, H. Structure-

1059   Property Relationships of a Biological Mesocrystal in the Adult Sea Urchin

1060   Spine. *Proc. Natl. Acad. Sci. U. S. A.* **2012**, *109* (10), 3699–3704.

1061   https://doi.org/10.1073/pnas.1109243109.

1062 (72) Cosmidis, J.; Benzerara, K. Comptes Rendus Géoscience Why Do Microbes

1063   Make Minerals？ *Comptes Rendus - Géoscience Sci. la Planète* **2022**, *354*, 0–

1064   39. https://doi.org/10.5802/crgeos.107.

1065 (73) Mugwar, A. J.; Harbottle, M. J. Toxicity Effects on Metal Sequestration by

1066   Microbially-Induced Carbonate Precipitation. *J. Hazard. Mater.* **2016**, *314*,

1067   237–248. https://doi.org/10.1016/j.jhazmat.2016.04.039.

1068   (74)   Albéric, M.; Bertinetti, L.; Zou, Z.; Fratzl, P.; Habraken, W.; Politi, Y. The

1069   Crystallization of Amorphous Calcium Carbonate Is Kinetically Governed by Ion

1070   Impurities and Water. *Adv. Sci.* **2018**, *5* (5).

1071   https://doi.org/10.1002/advs.201701000.

1072