1 Nature Communications Main Manuscript for

2 Organics Guide Non-Classical Crystallization Of Bacterial

3 Calcite Which Parallels Eukaryotic Biomineralization

Franco Grosso Giordano[1,2,3] *, Martín Purino[4], Nico Boon[1], Nele De Belie[2] and Carlos

Rodriguez-Navarro[3*]

[1] Ghent University, Center for Microbial Ecology and Technology (CMET), Frieda

Saeysstraat 1, 9052, Ghent, Belgium.

[2] Ghent University, Magnel-Vandepitte Laboratory, Dept. of Structural Engineering

and Building Materials, Technologiepark Zwijnaarde 60, B-9052, Ghent, Belgium.

[3] University of Granada, Department of Mineralogy and Petrology, 18002, Granada,

Spain.

[4] Ghent University, Department of Organic and Macromolecular Chemistry, Krijgslaan

281 S4, B-9000 Ghent, Belgium.

*Corresponding authors: Franco.GrossoGiordano@UGent.be; CarlosRN@Ugr.es.

Keywords: Bacteria, biomineralization, organics occlusion, amorphous calcium

carbonate, calcite.

This PDF file includes:

Title page (title, author list, classification, keywords)

Abstract

Main Text

Figures 1 to 6

Abstract

Microbially-induced calcium carbonate precipitation is a widespread natural

phenomenon with numerous applications. Recent advances have shown that

bacterial calcium carbonates (BCC) form non-classically via amorphous calcium

carbonate (ACC) precursors in the presence of organics, but the role of organics in

the formation and nanostructural features of BCCs is not fully understood. Here we

show that different bacterial strains produce BCCs with diverse textural and

structural features at the macroscale but similar at the micro and nanoscale. We

show that bacterial organics guide precipitation of calcite, stabilizing ACC to produce

nanogranular crystals and these organics are then trapped within the crystal, rather

than being released as previously suggested. These organics are N-rich and create

regions of low Z-contrast aligned perpendicular to the *c*-axis of the crystal, yielding a

"Swiss cheese-like" mesostructure. Moreover, it is these occluded organics that lead

to the distinctive biosignatures observed in BCC. Finally, we also observe crystalline

2D-structures made up of self-assembled bacterial proteins templating the oriented

crystallization of calcite. The formation mechanism and the resulting distinctive

nanostructural biosignatures of BCC are strikingly similar to those of carbonate

biominerals formed by eukaryotic organisms in controlled biomineralization,

suggesting a common origin for this crucial biomineralization process.

Introduction

Biomineralization is a widespread, cross-kingdom phenomenon whereby organisms

induce or control the formation of a variety of minerals in or around them [1]. A widely

occurring biomineralization process is the precipitation of calcium carbonate. It forms

the basis of many current biominerals structures – including shells of molluscs, the

cell wall of coralline algae, and the cystolith of plants [1–3] – and ancient – it is the

main mineral fraction in microbialites, some of the oldest fossils in the world [4]. The

bioprecipitation of calcium carbonate is also a common occurrence in the present day

microbial world [5–7], usually denominated as microbially-induced carbonate

precipitation (MICP). While calcium carbonate biominerals in eukaryotes is

considered to be tightly controlled by genetic and biochemical factors, MICP,

generally an extracellular phenomenon, has long been considered uncontrolled with

no specific purpose or functionality [8]. However, recent evidence is questioning this

notion [9]. For example, calcium carbonates have been reported to lead to an

evolutionary benefit by increasing the pathogenic capacity of strains [10], facilitating

biofilm formation [11], and providing survival strategies in extreme conditions [12].

Formation of intracellular calcium carbonate minerals, a tenant of eukaryote

biomineralization, has also been reported in prokaryotes [13].

Certain aspects of the biochemical understanding of MICP are well agreed upon. For

instance, the metabolic pathways of bacterial calcium carbonate (BCC) production

are in general well-known and include sulphate reduction [14], photosynthesis [2],

denitrification [15] ureolysis and ammonification [16] and metabolism of organic acids

[17,18]. Moreover, researchers recognize that there is a role of extracellular polymeric

substances (EPS) - which include polysaccharides, proteins and nucleic acids - in the

formation of precipitates, acting as a Ca^{2+} adsorption template [19]. Besides their role

in concentrating Ca^{2+}, there is growing evidence showing that the organic-mediated

formation of amorphous calcium carbonate (ACC) by prokaryotes prior to

crystallization of anhydrous $CaCO_3$ appears to be a general phenomena [20–23].

Recently, Enyedi et al. [24], showed that bacterial EPS led to long-term stabilization of

ACC, and suggested that the stabilized ACC eventually led to the formation of calcite

through non-classical crystallization. However, the MICP crystallization mechanisms

are still poorly understood, specifically when the role of organics is involved, while

structural aspects of these biocrystals have not been fully characterised.

In contrast, a large body of knowledge has been generated over the last few decades

on the formation mechanisms and structure-properties of biomineralized calcium

carbonate composites from eukaryotes, mostly of invertebrates such as molluscs

(extensively reviewed in *16*), photosynthetic organisms like phytoplankton [26], and

biomimetic counterparts [27]. These studies have led to the current model of calcium

carbonate biomineralization [28], where most calcium carbonate biominerals form

through (nano)particle attachment of ACC precursors, leading to hierarchical

structures of different calcium carbonate polymorphs with multiple types of

intracrystalline structural modifications including lattice distortions and elemental

differences. In turn, these variations in the organic-inorganic hybrid structure leads

to different physico-mechanical traits such as the fact that $CaCO_3$ biominerals are

often stronger and tougher than geocalcite [25], while they have enhanced abilities to

deflect cracking, different dissolution rates and are selectively precipitated as specific

polymorphs [25].

It is still important to know that even in the profusely studied eukaryotic calcium

carbonates, few studies "have identified the salient nano- and microscale

mechanisms" attributed to the material properties of these bio-composites [29]. As

such, it is of no surprise that there is a clear knowledge gap in MICP, despite MICP's

widespread occurrence, geological significance and bio-engineering applicability [7]. In

this work, crystallographic, compositional, textural and (nano)structural differences

of BCCs from two bacterial species and inorganic calcite are studied in-depth and at

high resolution. The aim is to shed light on the formation mechanism of MICP and

study the elemental, compositional and structural characteristics of BCCs at multiple

scales. Differences between BCCs and inorganic calcite were starker than between

BCCs of the two species and were attributed to the presence of organic

biosignatures. Furthermore, BCCs formed through non-classical ACC-to-calcite

precipitation and produced crystals with a Swiss-cheese like structure with regions of

occluded intracrystalline organic matter. In addition, a bacterially-derived self-

assembled 2D structure was identified supporting the role of organic molecules in

BCC formation. Overall, these features were starkly similar to those of eukaryotic

calcite biominerals. This raises the question whether this precipitation mechanism is

common to all $CaCO_3$ biominerals, regardless of their origin (microbial or from other

organisms). These findings have implications from an evolutionary standpoint and for

technical applications.

Results

BCCs have distinctive biosignatures associated with organics and ACC

The calcium carbonate precipitating capacity of two bacterial species was studied to

elucidate differences in the mechanistic process of biomineralization. *Lynsinobacillus*

fusiformis (LMG 9816) strain was used as it has been commonly used in other

studies of MICP [30,31]. To test whether nanoscale characteristics between BCCs were

similar, a recently isolated strain producing morphologically distinct BCC, *Shouchella*

clausii (previously known as *Alkalohalobacillus clausii*) LMG 33400, was used. No

previous *Shouchella* (or *Alkalohalobacillus)* strain has been reported to precipitate

calcium carbonate.

Optical microscopy imaging (Figure 1a,e) disclosed morphological differences

between mineral precipitates produced by *L. fusiformis* and *S. clausii*. *L. fusiformis*

mainly produced irregular precipitates with spherical incrustations, while *S. clausii*

induced the formation of spherical or oval-shape precipitates. A detailed observation

of the latter shows that they display elongated disphenoidal forms, or spindle- and/or

dumbbell-shaped structures, as also observed in other bacterial species [32].Both

bacteria produced precipitates associated with the bacterial colonies as well as in the

surrounding media. Field emission scanning electron microscopy (FESEM) analysis

showed the presence of carbonate precipitates closely-associated with organic matter

(Figure 1b, f). At the microscale all precipitates had an overall rhombohedral

morphology, consistent with the presence of calcite and were better developed in the

case of *S. clausii* samples (Figure 1d vs g and h). All of them showed a nanogranular

texture, implying formation through particle attachment (PA). In PA, ACC particles

100 – 400 nm in size [28] in the presence of organics [33] or crystalline $CaCO_3$

nanoparticles [34], attach forming a single crystallographic unit and this is typically

observed in carbonate biominerals produced by a range of organisms (e.g., molluscs,

barnacles, echinoderms, cnidaria) [27,35–37], including other bacteria [24]. The precipitates

were bleached to remove any organics on the precipitate surface and study possible

crystallographic and compositional changes. After bleaching, organic matter was not

observable anymore on the precipitates (Figure 1c, d and h), calcified bacterial casts

could be spotted (Figure 1c), and the crystallographic faces were more obvious

(Figure 1h**)**. Note that we performed controls on the sample preparation including

the bleaching test with increasing reaction time from 10 up to 480 min, observing

(using FTIR) that full removal of surface organics was already achieved after 10 min

(see Supplementary Information and Supplementary Figure 1 and Supplementary

Figure 2).

Figure 1. Optical and scanning electron microscopy photomicrographs of

bacterial calcium carbonate. Calcium carbonate structures precipitated by *L.*

fusiformis (a - d) and *S. clausii* (e - h). Orange outlined images are samples treated

with bleach (c, d, h). Different morphologies of calcium carbonate precipitates were

produced by both bacteria. (**a**) *L. fusiformis* produced irregular precipitates. (**b**)

Bacteria and biofilm associated with precipitated calcium carbonate. (**c**) Bleached *L.*

fusiformis precipitates showing the calcified bacterial casts. (**d**) Bleached *L.*

fusiformis precipitates (showing rhombohedral vicinal faces) made up of ordered

nanoparticles. (**e**) *S. clausii* produced ovoidal (black arrow), disphenoidal (white

arrow with black outline) and dumbbell (white arrows) shaped crystals. (**f**) *S. clausii*

cells associated with precipitated calcium carbonate (calcite rhombohedra). (**g**) Detail

of the mesostructured $CaCO_3$ crystals. (**h**) Bleached calcium carbonate crystals

showing the orderly arrangement of calcium carbonate nanoparticles. In all cases the

shapeless crystal subunits varying between 100 – 200 nm in size are distinguishable

within calcite mesocrystals. All SEM micrograph scale bars are 1.2 µm.

XRD confirmed the precipitation of calcite rather than any other calcium carbonate

polymorphs. The humps at 10 and 20 - 30 °2θ in the XRD patterns of both *S. clausii*

and *L. fusiformis* carbonates pointed to the presence of two distinct amorphous

phases (Figure 2a). Note that no humps were present in the XRD pattern of

synthesized calcite. Changes in the relative intensity of Bragg peaks were observed

for BCCs, as compared with synthetic calcite. Notably, the intensity of the 110 Bragg

reflection increased drastically (as compared to the main 104 Bragg reflection). The

(110) plane is associated with crystals elongated along the *c*-axis [38] and consistent

with the crystal observed in Figure 1. Overdevelopment of {11.0} faces, or more

exactly, pseudo-faces composed of (01.2) and (11.0) forms [39], is common in -

although not exclusive to - other calcite biominerals and abiotic calcite formed via

ACC-to-calcite crystallization in the presence of organics (see Supplementary

Information). After bleaching, both humps at 10 °2θ and 20-30 °2θ disappeared.

The bleaching of precipitates also led to changes in the intensity of Braggs peaks of

both bacterial crystals, most starkly non-(104) planes, with 110 and 113 Bragg

reflections being the strongest (Supplementary Table 1) We observed better

development of crystal faces after bleaching (Figure 1c, d and h) which would explain

the XRD changes.

Figure 2. Analysis of synthetic (c, purple) and bacterial crystals (*L. fusiformis* (*lf*, red) and *S. clausii* (*sc,* brown)). Both bacterial calcites were bleached to remove organic matter from the surface (*L. fusiformis* (*lf* b, light red) and *S. clausii* (*sc* b, light brown)) **(a)** XRD patterns of the studied calcium carbonates. Bragg peaks correspond to calcite in all cases and the main *hkl* reflections are indicated. **(b)** FTIR spectra of synthetic, *L. fusifomis* and *S. clausii* calcites. Blue shaded bands indicate organic and/or ACC wavenumber regions. **(c)** FTIR spectra of the calcites after bleaching. **(d)** Raman spectra of the studied unbleached calcites. **(e)** TGA of *L. fusifomis* bleached calcite (light red) vs synthetic calcite (purple).

FTIR spectroscopy showed distinctive spectral features among the different

precipitates. All precipitates displayed the characteristic v_2, v_3 and v_4 bands of calcite

at 873, 1407 and 711 cm^{-1}, respectively, however with some differences. Bacterial

calcites showed a slightly red-shifted v_2 band at 869 cm^{-1} (with a broad tail spanning

to lower wavenumbers) and a v_3 band at 1402 cm^{-1}. The red-shift of the v_2 band can

be caused by ACC which has a characteristic band at 860 cm^{-1} also seen in ACC

producing bacterial strains [3,40–43]. There were also variations in the absorbance of the

v_2 and v_4 bands. Synthetic calcite had the sharpest and strongest absolute v_4

absorbance followed by *S. clausii* and finally by *L. fusiformis* (Figure 2b). Besides the

differences in the vibrational modes, certain bands were evident in biogenic

precipitates but absent in synthetic calcite: namely between 950 – 1150 cm^{-1}, at

1500 – 1550 cm^{-1}, and between 1570 – 1700 cm^{-1}. A last band became apparent at

1190 - 1350 cm^{-1}, characteristic of amides [24], when subtracting the synthetic calcite

with the BCC spectra (Supplementary Figure S3). Similar spectra have been

previously reported on bacterial calcites [24,43,44], attributed to overlapping signatures

of organics (general organics at 950 – 1150 cm^{-1} and amides at > 1500 cm^{-1}) and

ACC (v_1-mode 1060-1080 cm^{-1}; a v_3 asymmetric vibration at 1470 cm^{-1}; and O-H

bending at 1650 cm^{-1} from structural H_2O in ACC) (for details see Supplementary

Information). Nevertheless, Mehta and colleagues [43] concluded that it is difficult to

infer the presence of ACC from the bands at > 900 cm^{-1} alone.

Following the bleaching process used to remove organic matter, BCCs produced

almost matching FTIR spectra (Figure 2c). No shift was observed in the carbonate v-

modes, yet all three modes experienced an increase in absorbance. This is important

as changes in calcite v-mode absorbance, most notably the increase in intensity of

the 712 cm^{-1} band, is associated with an increase in crystallinity of the carbonates [41].

However, the lack of shift in the v_2 band, and in particular the persistence of the

right broad tail, suggests that some ACC was still present, most likely structurally

bound to and/or occluded into the BCC calcite structure. Conversely, the increase in

v_4 absorption after bleaching suggests that a fraction of ACC, likely the superficially

exposed (see TEM results below), was transformed into calcite via dissolution-

precipitation in the bleach solution, and/or was removed after rinsing of the bleach.

Moreover, the bleaching process leads to removal of bands at higher wavenumbers

(bands at 1500 – 1550 cm^{-1} and 1570 – 1700 cm^{-1}), previously linked to organics,

pointing to the removal of organics along with ACC. Conversely, the bands at 950 –

1150 cm^{-1} and 1190 – 1350 cm^{-1} also corresponding to organics were conserved

after bleaching, with a reduction in absorbance, especially in *L. fusiformis*.

Interestingly, the band at 1190 – 1350 cm^{-1} in *L. fusiformis* BCC experienced a shift

to higher wavenumber after bleaching. Given that we can associate the wavenumber

to the bond strength, a higher wavenumber means that there is a stronger bond of

the remaining organics to the crystal structure. It follows that bleaching removed the

material more weakly associated with the BCC crystals (e.g. adsorbed organics) and

the subsequent rinsing of the bleach, led to dissolution of precursor ACC and

recrystallization of calcium carbonate on certain preferential faces of the crystals.

This would be responsible for the disappearance of the two humps in the XRD

patterns and the changes in Bragg peak intensities. Nevertheless, a fraction of

organics (and likely ACC) were not only associated with but structurally bound to the

BCC as a signal remains in the FTIR spectra. We suggest that they correspond to

intracrystalline occlusions (see TEM and HRXRD below). Duplicates of the BCCs

before and after bleaching show consistent FTIR bands (see Supplementary

Information and Supplementary Figure 4).

Raman spectroscopy analysis showed that all precipitates were identified as calcite

with strong fluorescence, but no distinctive spectral feature was identified (Figure

2d).

Thermogravimetric analysis (TGA) was performed on the bleached BCCs of *L.*

fusiformis and synthetic calcite to further disclose the compositional nature of the

biominerals (Figure 2e). The calcite control shows a weight loss of 42.3 % starting

from 650 °C, close to the theoretical 44 % due to the decarbonation of calcite. The

bleached BCC of *L. fusiformis*, showed a continuous and step-wise mass loss at

temperature ($T)$ < 100 °C, 150 – 500 °C, 500 – 600 °C and 600 – 950 °C. The initial

mass loss is from adsorbed water. The second loss can be from ACC dehydration

and/or thermal decomposition of the remaining organic matter. The dehydration of

ACC occurs at 100 – 350 °C [42,45] and the decomposition of organic matter starts at

250 °C and continues up to 400 or 600 °C for intracrystalline matter [42,46]. Although

there is an overlap between both decompositions, the continuous mass loss after 350

°C distinguishes the presence of organics. Finally, unlike the control, the weight loss

of BCC from 650 - 950 °C (33.9 %) does not match the value corresponding to the

theoretical mass loss of $CaCO_3$ following release of CO_2, but rather the weight loss

from 550 – 950 does (44.1 %). A lower decomposition temperature in $CaCO_3$ is

associated with lower crystallinity [47], which corresponds to the lower crystallinity of

BCCs observed with FTIR, and likely related to the possible presence of occluded

organics/ACC.

Overall, it becomes apparent that BCCs produced by the two bacteria studied, when

formed, are associated with bacterially-derived organic matter and ACC, with

distinctive biosignatures in all tests. FTIR confirmed that bleaching removes a non-

calcite fraction, seemingly composed of organics and ACC loosely bound to the

crystal surfaces, as seen on the SEM micrographs. But FTIR and TGA results show

that there is a non-removable organic/ACC fraction that is more permanently

associated with the BCC crystals. Overall this produces biomineralized calcite with

non-perfect crystal lattice (i.e. lower crystallinity) due to organics (and likely ACC)

occlusion as demonstrated by transmission electron microscopy (TEM) and high

resolution synchrotron powder XRD (HRXRD) results (see below).

Organics lead to the formation of a distinctive nanostructural Swiss-cheese

like structure

It could be argued that the bleaching process did not fully eliminate all the organics

adsorbed on the BCC precipitates, thereby contributing to their detection by FTIR

and TGA analyses. This would thus jeopardise any claim for intracrystalline occlusion

of organics, a yet unreported feature of bacterial carbonates. To unambiguously

disclose whether intracrystalline organics occlusion took place in BCC calcite, we

performed TEM, ss-NRM and HRXRD. .

Under the TEM we observed that *L. fusiformis* precipitated crystalline (calcite) and

amorphous (ACC) phases as confirmed by selected area electron diffraction (SAED)

patterns (Figure 3a, Supplementary Figure 5a). Conversely, we could not find

individual or aggregated ACC particles in the case of *S. clausii* which only showed

single crystal SAED patterns of calcite (Figure 3c). Additionally, SAED patterns with

calcite single crystal features were frequently arced, with spots displaying an angular

spread of ~4 to 12° on both BCCs (Figure 3c, Supplementary Figure 5a). Angular

spreading is a distinctive feature of mesocrystals reflecting a slight misorientation

among the different nanocrystals making up a mesocrystal [48] and commonly

associated with the presence of (occluded) organic matter in biominerals [49]. The

elemental composition of the unbleached precipitates was confirmed with EDS

mapping. Ca, O and C were ubiquitous in all samples. Moreover, it was possible to

correlate the presence of organic-related elements such as, N, S and P – the latter

two in trace amounts – in the crystals produced by both bacteria (Figure 3b, d,

Supplementary Figure 5b, Supplementary Figure 6).

Figure 3. TEM and EDS analysis of bacterial calcium carbonates. (**a**) HAADF

image of ACC precipitated by *L. fusiformis*. Inset: SAED pattern showing the

amorphous nature of the particle. (**c**) In clockwise order: EDS elemental maps of

precipitates in (a) (calcium, oxygen, nitrogen and carbon, respectively). (**c**) HAADF

image of calcite crystals precipitated by *S. clausii*. Note the nanoporous structure of

the crystals. Inset: $[2\bar{2}1]$ zone axis SAED pattern of the calcite particle on the left

with diffraction spots showing an angular spreading of 6°; (**d**) In clockwise order:

EDS elemental maps of precipitates in (D) (calcium, oxygen, nitrogen and carbon,

respectively).

EDS line-scans from the edge to the interior of BCC crystals showed that N was not

only present within the crystals but also adsorbed on their surface as the intensity

did not drop to zero outside the crystal (Figure 4a-d). Point scans showed a lower

N:Ca ratio in the centre of the crystals than in the rim (Figure 4e). This implies that

the internal areas of the precipitate include a lower relative amount of organics than

the rim. To further disclose how the organics were associated with the precipitates,

HRTEM analyses were performed, complemented with HAADF-EDS. In the case of *S.*

clausii, lattice fringe images and corresponding FFT showed that, generally, the

outermost layer of the bacterial calcite crystals was amorphous, confirming previous

observations [24] (Figure 4f-h, more examples in Supplementary Figure 7). Moreover,

here we also observed amorphous areas, interwoven within the crystalline lattice

(Figure 4f). This occurred in a region of intermediate contrast and a few nanometers

in thickness at the edge of the crystal, which was N-enriched according to EDS

analysis (N:Ca ratio of 0.53 Figure 4e). The latter points to occluded organics

including amorphous calcium carbonate, consistent with the relatively high Ca

content (Figure 4e).

Figure 4. TEM, EDS and ss-NMR analysis of bacterial calcium carbonates. (a)

HAADF image of calcite crystal precipitated by *L. fusiformis*. The porous -Swiss-

cheese like- structure of the calcite crystal is visible and the location of the EDS line

scan is indicated (green arrow). **(b)** Brightfield TEM image of the crystal in (a). **(c)**

$[0\bar{1}0]$ zone axis SAED pattern of the crystal shown in (a) and (b). Note the marked

arcing of diffraction spots (showing an angular spreading of ~9°). **(d)** Line scan in

(a) showing that N concentration (light blue line) is uncoupled (after 40 nm) to that

of Ca (dark blue line), and the increase in N can be traced to the pores on the calcite

crystal (corresponding to the darker areas in (a)). **(e)** *S. clausii* calcium carbonate

structure showing different N/Ca ratios in different areas. **(f)** HRTEM image of the

edge of the precipitate in (e) (Area #2) with FFT of the blue squared area **(g)**

demonstrating it is an amorphous external layer, and the FFT of the orange squared

area **(h)** showing it is a crystallized (calcite) internal zone. The red outline

demarcates the end of the lattice fringes, showing amorphous areas trapped within

the crystalline zone at the rim of the precipitate. **(i)** CP–MAS ^{13}C NMR spectra of

bleached *L. fusiformis* calcite (light red) and synthetic calcite (purple). The peak at

172 ppm is associated with calcite while the remaining peaks are due to the presence

of amides. Referenced to the signal of DSS (δ = 0 ppm).

Furthermore, an uncoupling of N and Ca was observed on the line-scans in the inner

region of the crystals (> 40 nm from the edge), i.e. when Ca increased, N decreased

(Figure 4d), albeit with a slight phase-shift. Upon close inspection of HAADF images,

it was clear that the crystals did not show a homogenous surface (Figure 4a).

Rather, a Swiss cheese-like structure could be observed, with elongated generally

parallel low Z-contrast pore-like areas present within the bacterial calcite single

crystals (more examples in Supplementary Figure 8). A direct association of these

low Z-contrast nanoporous-looking areas with an increase in N content was

systematically observed. It could be argued that this porous structure is the result of

beam damage. However, this is ruled out here because the HAADF images were

collected before EDS analysis and the porous structure was already present.

Pioneering work by Towe and Thompson [50], and many other subsequent studies [25]

have also shown that beam damage does not produce such features, but organics

do. Moreover, this structure was also observed in many other BCCs during brightfield

TEM analysis and subsequent SAED analysis showed no CaO diffraction spots/rings

which are standard features of beam damage in calcite [51]. Note also that we have not

observed such Swiss-cheese structure in any studied synthetic calcite crystal.

Although a Swiss-cheese-like structure has never been reported in the case of BCC,

similar features have been observed in other calcium carbonate biominerals, such as

mollusc shells [25,52], and their biomimetic counterparts [53]. The pore-like areas have

been usually identified as intracrystalline organic matter (IOM) and recently with ACC

(see Supplementary Information). CP-MAS ^{13}C NMR was used to confirm the nature

of those observed here. The CP-MAS ^{13}C NMR spectra of bleached BCC primarily

consist of broad peaks, with a notable exception at 168 ppm attributed to calcite

(Figure 4i), as confirmed by the MAS ^{13}C of synthetic calcite (Supplementary Figure

9). The broad peaks are indicative of amorphous content yet no well-defined peak

was observed closely associated downwards of calcite (167 ppm), where ACC is

typically present [54]. The remaining option for amorphous content must then be

organic in nature. Many broad peaks are present in the 20 - 80 ppm range and a

peak at 172 ppm suggests the presence of carbonyl groups. These shifts are linked

to amino acids which have peaks at 20-60 ppm (CH), and 170-180 ppm (carbonyl)

[55]. Overall, the spectra closely resembles that of eggshells [56] and protein-including

calcite biominerals [57].The CP-MAS ^{13}C of the synthetic calcite does not show any

bands, as expected (Figure 4i; see also Supplementary Figure 9). This means that

the calcite peak present in the *L. fusiformis* BCC is associated with hydrogen atoms,

only available from either organics or water [54]. Because the presence of water, such

as in monohydrocalcite [54], should broaden and shift to higher ppm values the calcite

carbonyl bond, we conclude that the hydrogen is from amine or carboxyl groups

from the organics. Lastly, the broadness of the peaks further suggests that the

structure is internal [54] in agreement with the fact that the bleaching removed all

adsorbed organic matter, but structurally bound organics remained. As such, the

observed Swiss cheese-like structure must be present through the whole crystal and

not superficially as seemingly observed on TEM.

To further disclose whether BCCs included intracrystalline organics, we performed

HRXRD analyses at the CRYSTAL beamline of the Soleil synchrotron (France). HRXRD

analysis showed that the 104 and 006 Bragg peaks of bleached BCC produced by *L.*

fusiformis were left-shifted (i.e., to higher *d*-spacings) as compared with geogenic

calcite (optical quality Iceland spar) (Figure 5a, b). The shifting was more marked for

the 00*l* reflections, implying anisotropic lattice distortion. Rietveld full profile fitting

analysis [58] yielded the following refined cell parameters for BCC calcite: $a =$

4.98900(4) Å; $c = 17.08345(5)$ Å; cell volume = 368.24(4) Å^3, demonstrating a

clear lattice expansion as compared with reference geogenic calcite ($a = 4.98970(2)$

Å; $c = 17.05900(4)$ Å; cell volume = 367.82(2) Å^3). Maximum lattice strain was

observed along the [001] direction ($\Delta c/c=0.0014$). This lattice strain fluctuation is

within the range reported for biogenic (e.g., mollusc shell) and biomimetic calcite [59–

[62]. HRXRD analysis during *in situ* isochronous heating (annealing) from room *T* up to

400 °C at 50 °C intervals (see Materials and Methods), showed little changes in $\Delta a/a$

and a significant $\Delta c/c$ reduction at *T* > 200 °C (Figure 5c). Reanalysis of the BCC

after annealing at maximum *T* and subsequent cooling to room *T* showed permanent

lattice contraction and peak broadening (Figure 5). Pokroy et al. [59,60] observed

exactly the same features following similar (isochronous annealing) HRXRD analysis

of calcite in mollusc shells, demonstrating intracrystalline occlusion of organics (as

solutes) in such biominerals. The preferential expansion along the *c*-axis was

associated with interaction/replacement of carbonate groups placed along (00.1)

planes of calcite by acidic proteins, although interaction with other polar planes such

as (01.2) should also be favoured [59,62]. The authors also stated that thermal

decomposition of occluded organics at $T > 200$ °C results in strain relaxation and

reduction in $\Delta c/c$, with a parallel increase in peak broadening due to reduction in

crystallite size and increase in microstrain fluctuations, as we have observed here.

Interestingly, we also observed an increase in $\Delta c/c$ of BCC between 100 °C and 200

°C. The latter, also observed in other calcite biominerals such as sea-urchin spicules,

has been associated with the presence of ACC and its thermal-induced

transformation into calcite, which leads to expansion [63]. Altogether, our HRXRD

results confirm that intracrystalline organics occlusion, with very similar anisotropic

lattice distortion as in mollusc shells, also occurs in bacterial calcite. Our HRXRD

results also suggest that intracrystalline ACC is present in the BCC structures, as

supported by TEM and ss-NMR results.

Figure 5. Synchrotron HRXRD analysis of *L. fusiformis* calcite. (a) 104 Bragg

peaks and **(b)** 006 Bragg peaks of bacterial calcite before (red) and after annealing

at 400 °C and cooling to room *T* (light brown). The dashed (purple) profiles show the

reference geologic calcite; **(c)** *T*-dependent variation of lattice distortion ($\Delta c/c$) along

the *c*-axis as compared with reference geogenic calcite. The red squared symbol

marks the residual lattice distortion after annealing at 400 °C and cooling to room *T*.

Role of crystalline 2D organic films in BCC formation

During TEM imaging of *L. fusiformis* biogenic precipitates we unexpectedly observed

layered structures containing areas of amorphous and crystalline carbonates (Figure

6a). HRTEM imaging showed that these film-like structures were crystalline

displaying lattice fringes oriented in different directions and with *d*-spacings of 3.8 –

4.3 nm (Figure 6b). Carbonates were closely associated with these 2D crystalline

films (Figure 6a, b). SAED analysis of the film-like structures revealed diffraction

spots with *d*-spacings 3.7 – 4.5 nm aligned in rows with different orientations

corresponding to the multiple orientations of the lattice fringes visualized in the

HRTEM image (Figure 6a, yellow and green lines), along with diffraction spots

corresponding to (at least two non-oriented) calcite crystals (Figure 6c). The *d*-

spacings of the films is at the scale of those measured in protein crystalline

structures [64]. The crystalline films were less visible on higher density patches

indicating that they were placed at the "bottom" of calcite. However, as shown in

Supplementary Figure 10a, we could observe, in other examples, a close relationship

between the film and an overlying nanogranular structure of calcite, with a SAED

pattern corresponding to a calcite single crystal with a nanogranular structure

(Supplementary Figure 10b). These results suggest that the formation of oriented

calcite after particle attachment of ACC is templated by the protein film underneath,

such as that reported on S-layers [65] or carbonic anhydrase [66] (see Supplementary

Information).

Figure 6. HRTEM analysis of *L. fusiformis* calcite formed on an organic crystalline 2D template. (a) A polycrystal showing different amorphous and crystalline phases, alongside crystalline 2D organic structures showing lattice fringes. **(b)** Zoom-in of the blue squared area in (a) showing lattice fringes in the 2D films. The yellow and green lines show the direction of the lattice fringes. **(c)** SAED pattern of the red circled area in (a) showing different diffraction spots corresponding to calcite ([0$\bar{1}$0] zone axis, calculated using the most intense diffraction spots: note that additional orientations are present) overprinted with diffraction spots of the (organic) films (the green and yellow lines mark the three aligned spots corresponding to the films in (b) with lattice fringes oriented along the green and yellow lines).

Discussion

FESEM showed that the bacteria were closely associated with the BCC crystals and that a nanogranular texture was present suggesting the formation through an ACC precursor. XRD and Raman indicated that all carbonates were calcite, while amorphous and organic signatures were detected with FTIR and TGA, in both bleached and unbleached samples. TEM analysis showed the presence of both crystalline and amorphous calcium carbonate, the latter being more predominant in

L. fusiformis, in agreement with FTIR spectra. In the individual crystals, amorphous

areas were present at the rim of the BCC precipitate, likely the growth front of the

crystal, in both bacteria. TEM-EDS mapping unveiled the presence of organic-related

elements in the bacterial crystals, including N, (and S and P to a lesser extent)

associated with both crystalline and amorphous regions of calcium carbonate

precipitates. Importantly, we observed low Z-contrast pore areas that resembled a

Swiss cheese-like structure thoroughly reported in calcifying metazoans [36,52], and a

strong correlation with N was detected in the low Z-contrast regions. CP-MAS C^{13}

NMR pointed at the presence of amino acid in a strikingly similar way as in other

protein-including calcite biominerals [57]. TEM-EDS and ss-NMR results helped clarify

that the observed FTIR bands correspond to amide bonds (Amide I band (1600 −

1700 cm^{-1}); Amide II: 1540 cm^{-1} likely attributed to a C=N bond [67] and C-N-C=O

bonds at 1499 cm^{-1} [68]; Amide III band 1250 − 1350 cm^{-1} [68]). Nevertheless, the

strong indication of ACC presence throughout the whole study, even after bleaching,

suggests that ACC is also occluded, and likely stabilized by the organics [37]. However

further analysis is needed to unambiguously prove this. Moreover, HRXRD shows

that the amino acids/proteins should be intracrystalline, as there was a marked

lattice strain (expansion) along the *c*-axs, and a lattice contraction was observed

along the *c*-axis direction after annealing (up to 400 °C). A similar features have

been observed using HRXRD in the case of calcite biominerals and their biomimetics

(59-61). Note that the nanometer-sized porous areas filled with N-rich organics

forming the Swiss-cheese structure are, however, too large to account for the lattice

strain fluctuations determined by HRXRD. Apparently, organics are occluded in BCCs

at two scales: the atomic scale (as solutes in the calcite crystal lattice) resulting in

the observed lattice strain, and the mesoscale (as nanometer-sized clusters) as

observed here with TEM as well as in several calcium carbonate biominerals

produced by eukaryotes [25]. Note that foreign nanoparticle occlusion results in peak

broadening due to microstrain contributions associated with the creation of

intracrystalline boundaries acting as a source of inhomogeneous deformation fields

but without necessarily contributing to macrostrain, i.e., lattice distortion [60]. These

results are consistent with the ss-NMR results as the broad peaks of the CP–MAS ^{13}C

NMR spectra point to intracrystalline presence of the amino signatures. Finally, the

confirmed role of organics in the crystallization process, explain the preferential

growth of BCC calcite along the *c*-axis, with overdeveloped {110} (pseudo)faces,

which are typically formed during calcite growth following adsorption of organics on

acute steps [69].

The evidence presented here supports the mechanism of precipitation originally

alluded to by Enyedi et al. [24], where ACC is stabilized by EPS, and calcite forms

through PA. However, we clarify several missing aspects after ACC stabilization.

Firstly, we propose that BCC grows by aggregation of protein-stabilized ACC, rather

than the more broadly assigned EPS. This is consistent with the intracrystalline

occlusion in BCC calcite crystals of both proteins and ACC. Moreover, we observed

that larger crystalline 2D protein structures, not only stabilize, but act as a template

for crystal formation. The stabilized ACC then undergoes an amorphous-to-crystalline

conversion, at which point the intracrystalline occlusion of a fraction of the organics

associated with ACC occurs. This closely resembles the current model of

biomineralization of calcite biominerals in eukaryotes [36]. Our proposition is in

contrast to what was previously suggested for bacteria, where organics were

assumed to be completely ejected [24]. Biomineralization through the eukaryotic model

commonly produces a nanogranular structure and results in a Swiss cheese-like

structure, as observed here. Even more remarkable, de Frutos and colleagues

proposed a model for calcite biomineralization in animals wherein the formation of

pellicle-like regions of concentrated organics are formed [36]. These are starkly similar

to the orderly fashion in which the pore-like N-rich structures were observed in our

bacteria biominerals. Moreover, the transformation of ACC nanoparticles into calcite

occurs in crystallographic register with the core calcite, which explains the single

crystal features of the SAED patterns. Still, some miss-orientation occurs, resulting

in the observed angular spreading and the mesocrystal features described above,

which are also observed in calcite biominerals produced by eukaryotes, as it is the

case of sea-urchin spicules [70].

This conserved mechanism of biomineralization between BCC and that reported in

biomineralizing protists and metazoan might not be surprising given that many

processes proposed for the formation of calcite biominerals have been shown to be

thermodynamically favourable (i.e., down-hill energy landscape) [27]. Similar

structures seem to form in the case of biomimetic *in vitro* models [53], yet, critically, in

these models the carbonate crystals do not display the highly organized organic-

inorganic nanostructure observed in biominerals, in general, and in our BCCs, in

particular. The organization of the BCCs mesocrystals and the hierarchy in organics

occlusion observed in this work contradicts the common idea that calcium carbonate

biomineral precipitation by microorganisms - in contrast $CaCO_3$ biominerals produced

by eukaryotes - is a spontaneous and uncontrolled phenomenon [8]. Furthermore,

other authors are already scrutinizing the idea that calcium carbonate

biomineralization in prokaryotes is functionless [71]. Some recent work points to real

adaptive benefits for MICP. For example, Botusharova et al. [12] showed that bacterial

spores could survive entombment in carbonate precipitates, being autoclaved and

then reactivated. More recently, it was shown that the precipitation of calcium

carbonate had a central role in the effective formation of biofilm in pathogenic

bacteria with genetic inhibition of carbonate biomineralization leading to a reduced

pathogenicity and biofilm formation [10]. On the other hand, control over the

precipitation process could provide protection to the bacteria from unfavourable

conditions by controlling the rate and location on the cell where precipitates form, for

example to prevent unwanted entombment [65], or reduce damage from toxic metals

by removing these from the surrounding environment through (co)precipitation in

carbonates [72]. Although the work remains limited, investing energy in producing

organics that will create a controlled process of biomineralization might contribute to

the inclusive fitness of the organism. Moreover, stabilized ACC as a precursor prior to

transitioning to calcite has been shown in different biomineral composites to lead to

improved structural properties [73]. As such, understanding how these mechanisms

work and are controlled can open up the door for novel biomaterial applications with

purposely designed structure-function.

The similarities between the formation mechanism (via amorphous phases and PA in

the presence of N-rich organics -aminoacids/peptides/proteins-), and the resulting

nanostructural and compositional features of the hybrid organic-inorganic BCCs

studied here, and $CaCO_3$ biominerals produced by eukaryotes [28] are remarkable. In

the case of MICP, the main missing aspect that has been discussed in carbonate

biomineralization of eukaryotes is the presence of a privileged space, a biologically

controlled compartment where biominerals can form [28]. Here, the observed adsorbed

organics on the crystals could act as a rudimentary permeable privileged space

where the process of biomineralization (adsorption of Ca^{2+}, high concentration of

both DIC and DOC from EPS, formation and stabilization of ACC, and crystallization

of calcium carbonate through particle attachment on the growth front) could take

place. At a higher organizational scale, this is similar to what has been described in

the EPS of microbial mats [74], which further stimulates the possibility of organics and

EPS as proto-permeable spaces. Moreover, there is evidence for the intracellular

formation of calcium carbonate biominerals (mostly ACC) in some bacteria [13,75] which

further points to a conserved mechanism for biomineralization. This prompted us to

suggest that there must be a shared "biomineralization pathway" between

prokaryotes and eukaryotes [74].

To open up the debate about whether a conserved process of biomineralization might

exist across prokaryotes and eukaryotes, here we propose two possible evolutionary

paths based on what is currently known on the evolution and mechanisms of calcium

carbonate in other organisms. First, it is the possibility of a eukaryotic-prokaryotic

common ancestor already having the molecular toolkit for the formation of calcium

carbonate biominerals. Work on biomineralizing animals have shown that the

mechanisms of biomineralization emerged independently multiple times through the

co-optation of proteins from other processes, with the last common ancestor of all

biomineralizing clades today not having the capacity to do so [28]. Nevertheless, some

of the currently associated proteins involved in calcium carbonate precipitation - such

as carbonic anhydrase - are also present in bacteria [76] alluding at the possibility that

the last common ancestor between prokaryotes and eukaryotes might have shared

the same ancient co-opted protein toolkit used, for instance, in modern shell

formation [77]. The other possibility is that some eukaryotes acquired the protein

toolkit from prokaryotes at different stages, either at the beginning of the Cambrian

as proposed by [74], or later as supported by the idea of a web of life [78]. This could

have occurred through a horizontal gene transfer (HGT) event such as

endosymbiosis, gene transfer from host-microbiome interactions or other possible

HGT events known to occur between prokaryotes and eukaryotes [79]. For example,

work on sea urchins has shown that ACC-precursor forms intracellularly in vacuoles

[80] and in coccolithophores the Golgi apparatus is heavily involved in the formation of

the calcite coccoliths intracellularly [81]. The endomembrane system in eukaryotes has

long been proposed to have been formed as a remnant of an endosymbiotic event

[82,83], which would link the formation of extracellular calcium carbonate to the

capacity of eukaryotes to develop, at different points in time, the capacity to

precipitate calcium carbonate in a controlled environment. Moreover, in case of HGT,

incorporation of genetic information commonly has neutral or nearly neutral effects

in the recipient [78]. This means that the genes are not expressed or only to a limited

extent and provide peripheral functionality. Only after the acquisitions do these

genes change and provide a novel beneficial phenotype. Acquiring genes through a

HGT event could explain the lack of a biomineralizing common ancestor [84], either

because there were multiple HGT events or an original neutral HGT event. Naturally,

the malleability of the molecular toolkit would have led to the multiple variations in

different marine animals we observe today [85]. The possibility that HGT from bacteria

to eukaryotes could be at the root of carbonate biomineralization in higher order

organisms is consistent with experimental results showing that bacterial precipitation

of calcium carbonates is associated with specific genes [86]. Mutants without such

genes were unable to produce BCC.

Besides the evolutionary standpoint, there is the technical applicability of the results.

The observations of intracrystalline organics implies that there might be improved

mechanical properties for BCC, as occurs with other calcium carbonate biominerals

such as mollusk shells (i.e., increased toughness) [25], which can have implications in

the industrial applications of MICP, like self-healing cements or the consolidation of

stone built heritage. Moreover, identification of these biosignatures could pave the

way for determining biogenicity of carbonate samples in the geologic record, which is

not always straight forward.

Materials and Methods

Synthetic calcite preparation

Calcite was produced synthetically in order to act as an abiotic control. A reaction

pathway was chosen as proxy to that expected in the bacterial cultures, whereby

calcite precipitated by the dissolution of CO_2 from bacterial respiration. A saturated

calcium hydroxide solution was prepared by adding 5 g $Ca(OH)_2$ to 100 ml of distilled

water, stirring for 30 min at 50 RPM and letting sit for 2 h. The supernatant (i.e., a

saturated solution of Ca^{2+} and OH^- (equation 1) was poured into a clean container.

CO_2 was then purged through this solution. This enabled the fast dissolution and

hydration of CO_2 , creating bicarbonate (equation 2) and carbonate ions (equation 3

or 4). Subsequently, $CaCO_3$ spontaneously precipitated through the reaction of

carbonate ions with Ca^{2+} (equation 5) in the absence of any background electrolyte.

The precipitates were filtered using a vacuum pump and polycarbonate filters (φ =

0.22 μm). The filter with the precipitates was placed at room temperature (*T*) and

dried overnight. The dry solids were stored in plastic vials for further analysis.

$Ca(OH)_2 \rightarrow Ca^{2+} + 2OH^-$ (1)

$OH^- + CO_2 \rightarrow HCO_3^-$ (2)

$HCO_3^- + OH^- \rightarrow CO_3^{2-} + H_2O$ (4)

$Ca^{2+} + CO_3^{2-} \rightarrow CaCO_3$ (5)

Selection and cultivation of bacterial strains

Two bacterial strains were used in this study, *Lynsinobacillus fusiformis* (LMG 9816)

and a recently isolated strain, *Shouchella clausii* (registered at the Belgian

Coordinated Collection of Microorganisms as LMG 33400). *S. clausii* was isolated

from a lime mortar wall in Ghent, Belgium by selecting morphologically distinct

colonies from a Horikoshi medium. Its capacity for carbonate precipitation was tested

on B4. Finally, the strain was selectively adapted to high pH tolerance by repeated

inoculation in TSB adjusted to pH 11 with CAPS buffer. An alkaliphile was desirable

as MICP commonly occurs in alkaline environments. The bacteria were grown and

kept in TSA at 28 $^{\circ}$C.

Culture and precipitation media, and precipitate extraction

Due to the alkaliphilic nature of both bacteria, carbonate precipitation experiments

were carried out on pH 8-adjusted B4-medium, a complex medium used to study

precipitation of calcium carbonate crystals [5]. Importantly, Ca-acetate was filter

sterilized as doing otherwise would lead to precipitation of calcium carbonate either

through too high pH or through heating of the Ca-acetate. For the inoculation of B4

plates, bacteria were inoculated in TSB and grown for 48 h. Subsequently, 10 µL of a

fully grown culture was drop-inoculated onto 9 spots on B4 plates. The cultures were

grown for 4 weeks at 28 °C. At this point, precipitates were visible on the plate and

were extracted. Briefly, the B4 agar was cut into pieces and placed in a glass

container and melted in a microwave oven. 100 mL of warm deionized water were

added to the beaker to dilute the melted agar. The dilute agar was centrifuged at

5000 rpm for 1 min while still warm. The pellet was then microwaved again, warm

water was added, and centrifuged again. This was performed a third time but

centrifuged at 7000 rpm. The sample was warmed up once more, and the suspension

was filtered using a vacuum pump and polycarbonate filters (φ = 0.22 μm). The

filter with the precipitates was placed at room temperature and dried overnight.

Once dried, the solids were placed in a plastic vial for further analysis.

Bleaching of precipitates

A fraction of the bacterial precipitates was bleached to remove any potential organic

matter on their surfaces [36]. Bleaching was done using commercial bleach and

deionized water (1:1 dilution) poured in an Eppendorf tube (1.5 mL) filled with 0.1 g

solids, followed by incubation for 2 h in a shaking table. The samples were then

centrifuged for 1 min at 5000 RPM and the supernatant discarded. Bleached solids

were resuspended in MilliQ water, vortexed for 1 min, and centrifuged again.

Washing was performed thrice. The precipitates were dried at 50 °C overnight.

Raman and FTIR spectroscopy

Precipitates were observed under a Horiba XploRA PLUS Raman spectrometer

equipped with a CCD detector (OE., 1024 x 256 pixel, TE deep-air cooled at -60° C,

UV-NIR range), an integrated confocal microscope and a built-in camera. Microscopic

observations were performed simultaneously with micro-Raman spectra acquisition

(excitation with a 4 mW power diode laser operated at 532 nm; frequency range

400–4000 cm^{-1}; spectral resolution of 2 cm^{-1}). Averaged values of three spectra (60

s acquisition time) for each analyzed spot are reported here. Calibration was

performed using the 520.5 cm^{-1} band of silicon in a calibration objective. Samples

were observed with the integrated microscope of Raman.

Fourier Transform Infrared Spectroscopy (FTIR) spectra of the precipitate were

recorded on a NICOLET 20SXB FTIR (400–4000 cm^{-1} spectral range; resolution of 2

cm^{-1}). Baseline and smoothing corrections to the FTIR spectra was performed using

Spectragryph v1.2.16.1.

X-ray diffraction (XRD)

The crystallographic features of the synthetic (control) and bacterial precipitates

were analysed with a Xpert Pro X-ray powder diffractometer (Panalytical, The

Netherlands) in reflection mode using copper radiation to determine θ−2θ scans

(measurement parameters: Cu Kα radiation λ = 1.5405 Å, 45 kV, 40 mA, 3 to 70°

exploration range, with 0.00418° step size and 29.8 s integration time per step).

Bacterial precipitates were analysed in zero-background Si sample holders. XRD

patterns were analysed using the computer program HighScore Plus Version 3.0d.

TG analysis

Thermogravimetric analysis (TGA) was performed using a TGA 2 (Mettler-Toledo,

Switzerland) with a large furnace and an autosampler, using 70 µL alumina crucibles.

Samples (12 mg) were heated at 20 °C/min from 25 to 950 °C under air atmosphere

(80 mL/min).

Synchrotron High-Resolution Powder X-Ray Diffraction (HRXRD)

HRXRD analyses were performed at beamline CRYSTAL of the SOLEIL synchrotron

(Paris, France). The wavelength 0.672356 Å (18.44024 keV) was selected with a

double-crystal Si (111) monochromator and determined by using Si640d NIST

standard (*a* = 5.43123 Å). The CRYSTAL beamline is equipped with a high-

throughput position sensitive detector (PSD) MYTHEN, optimal for time-resolved

experiments. Borosilicate glass capillaries of 0.3 mm diameter were loaded with

powder samples and rotated during data collection to improve diffracting particle

statistics. Isochronous annealing (10°C min^{-1}; 30 s stabilization time at target *T*,

tolerance ± 5°C) was performed using a Cyberstar hot gas blower with a Eurotherm

T controller (Eurotherm, Worthing, UK), collecting diffraction data each 50°C during

the heating ramps (50° to 400°C). Once the maximum *T* was reached, the samples

were cooled to room *T*, and a final measurement was taken. The data acquisition

time was ~5 min per pattern, with up to two iterations per measurement to obtain a

good signal-to-noise ratio over the 0-55.34 °2θ angular range. To calibrate the

equipment and reduce possible shifts during experimental analysis, a LaB6 standard

was used. An instrumental resolution factor analysis was performed in each case.

Under these data acquisition conditions, the angular resolution was better than

0.006° FWHM. As opposed to conventional XRD, such an angular resolution enables

to detect lattice strains of 10^{-3} to 10^{-4} associated with intracrystalline organics.

The Rietveld refinement method [58] was used to extract lattice parameters of calcite

matching the experimental diffraction peaks with those included in Markgraf and

Reeder [87] using Topas software. Optical quality (highly pure) geologic calcite (Iceland

spar, from Chihuahua, Mexico) was used as standard to compare XRD data from

BCC.

To investigate the microstructural variations due to organic (macro)molecule

incorporation in the calcite structure, the Thompson-Cox-Hastings pseudo-Voigt

function was used to fit the profile of the experimental diffraction patterns.

Refinement cycles were performed to ensure reproducibility of each analysis,

selecting a Goodness of Fit of <9. Note that, as opposed to BCC, in the case of the

Iceland spar control no changes in Bragg peak position or broadening (FWHM) were

observed after annealing, i.e., after returning to room *T* following heating up to

400°C. These results show that the selected geogenic calcite is a proper reference to

compare the results of BCC HRXRD analysis.

FESEM and TEM analysis

Field Emission Scanning electron microscopy (FESEM) images were collected using

an Auriga (Zeiss, Germany) microscope with field emission gun operated at 5 kV. All

samples were carbon coated prior to imaging.

Nanoscale features and elemental composition of the precipitates were studied using

TEM on a Titan (FEI) with acceleration voltage of 300 kV. The TEM was equipped

with a high angle annular dark field (HAADF) detector for Z-contrast imaging and

energy dispersive X-ray spectroscopy (EDS) for microanalysis (performed in STEM

mode). Right before TEM analysis the solids were dispersed in ethanol, sonicated for

2 min and fished with carbon-coated TEM Cu grids. Imaging was performed using a

20 µm objective aperture, which is a good compromise for amplitude and phase

contrast (high resolution, HRTEM) imaging. Selected area electron diffraction (SAED)

patterns were collected from areas ~200 nm in diameter.

Solid-state NMR (ssNMR)

The 1D experiments were recorded on a Bruker Ascend 500.13MHz Avance III

spectrometer equipped with a Bruker broadband 4 mm 1H/X dual channel CP-MAS

smartprobe probe head, equipped with Z-gradients, a MAS III pneumatic unit and

running Topspin 3.6.5. For each measurement, the spinning frequency was set to

12000Hz, all measurements were performed at room temperature (25°C) and

controlled with a Eurotherm 2000 BVT controller and a BCU-I.

All samples were prepared by filling the 4mm Bruker K1910 ZrO_2 rotors with an

appropriate amount of dry and finely grained sample material (25-30 mg per

sample). Using subsequent rounds of filling and packing the rotor led to a tightly

filled rotor sample for each material under study. Following the packing of the rotors,

each of them was sealed with a Kel-F insert, a Kel-F rotor cap and visually checked

for any leftover voids or air pockets.

The spectra recorded on the samples included 1D ^{1}H and 1D ^{13}C measurements. For

the 1D ^{1}H 'onepulse' experiments, the spectral width used was 200.00 ppm with 4

scans of 4K data points each being accumulated, preceded by 2 dummy scans and a

relaxation delay of 2 seconds. Finally, the spectrometer excitation frequency was set

on resonance with the frequency (5 ppm) of the most intense signal. Processing

consisted of one order of zero filling to 16K real data points, followed by Fourier

transformation, phase correction and a base-line correction.

For ^{13}C measurements a 'hpdec' measurement type was used for non-cross-

polarization and 'hX.cp' for measurements with cross-polarization (CP) with ^{1}H. The

spectral width used was 300.00 ppm with 2048 scans of 4K data points each being

accumulated, preceded by 4 dummy scans and a relaxation delay of 5 seconds.

Finally, the spectrometer excitation frequency was set on resonance with the

frequency (100 ppm) of the most intense signal. Processing consisted of one order of

zero filling to 16K real data points, followed by Fourier transformation, phase

correction and a base-line correction.

Chemical shifts were indirectly referenced by adapting the magnet 'field' value -by

measuring an adamantane reference sample-, and adapting the magnet field until

one of the adamantane signals is at the right chemical shift value (37.77 ppm). All

spectra were processed using TOPSPIN 4.1.3.

Acknowledgments

We thank the personnel of the Centro de Instrumentación Científica (CIC) of the

University of Granada for helping with FESEM and TEM analyses and the Inorganic

Chemistry department for access to their FTIR. Additional thanks go to the personnel

of the Department of Mineralogy and Petrology of the University of Granada for their

help with the instrumentations, including Teodora Ilić, Sarah Bonilla Correa, Aurélie

Pace and Miguel Burgos Ruiz. Special thanks go to Kerstin Elert for her help with the

SEM imaging and Prof. Fadwa Jroundi Mesbahi for allowing to grow our bacterial

cultures at her facilities. HRXRD experiments were performed at CRYSTAL beamline

at SOLEIL Synchrotron with the help of this beamline staff (E. Elkaim). We also

thank J. Atienzar, A. Pace, and N. Pujol Solà for their help during HRXRD analyses at

SOLEIL synchrotron and Alejandro Rodriguez-Navarro for his help during Rietveld

analysis of HRXRD results.

Author Contributions:

FGG contributed Conceptualization, Methodology, Investigation, Visualization,

Supervision, Writing (original draft), Writing (review and editing)

MP contributed Conceptualization, Investigation, Visualization, Writing (original

draft), Writing (review and editing)

NB contributed Conceptualization, Supervision, Writing (review and editing), Funding

acquisition

NDB contributed Conceptualization, Supervision, Writing (review and editing),

Funding acquisition

CR-N contributed Conceptualization, Methodology, Investigation, Visualization,

Supervision, Writing (original draft), Writing (review and editing), Funding acquisition

Competing Interest Statement: The authors declare no competing interest.

Funding: This work was funded by Spanish Government grant

PID2021.125305NB.I00 funded by MCIN/ AEI /10.13039/501100011033 and by

ERDF A way of making Europe (to C.R.-N.); Junta de Andalucía and ERDF grant B-

RNM-574-UGR20 and research group RNM-179 (to C.R.-N.); University of Granada,

Unidad Científica de Excelencia UCE-PP2016-05 (to C.R.-N.). Funding was also

provided by the European Union's Horizon 2020 research and innovation programme

under Marie Sklodowska-Curie project SUBLime [Grant Agreement n∘955986]. 500

MHz CP-MAS ssNMR was funded by Hercules foundation AUGE/09/2006 and FWO

I006920N.

Data availability: All necessary data to evaluate our conclusions are included within

the manuscript and the Supplementary Information.

References

1.   Lowestam, H. A. & Weiner, S. *On Biomineralization*. (Oxford University Press,

New York, 1989).

2.   Raven, J. A. & Giordano, M. Biomineralization by photosynthetic organisms:

Evidence of coevolution of the organisms and their environment? *Geobiology*

7, 140–154 (2009).

3.   Addadi, L., Raz, S. & Weiner, S. Taking advantage of disorder: Amorphous

calcium carbonate and its roles in biomineralization. *Adv. Mater.* **15**, 959–970

(2003).

4.   Schopf, J. W. Solution to Darwin's dilemma: Discovery of the missing

Precambrian record of life. *Proc. Natl. Acad. Sci. U. S. A.* **97**, 6947–6953

(2000).

5.   Boquet, E., Boronat, A. & Ramos-Cormenzana, A. Production of Calcite

(Calcium Carbonate) Crystals by Soil Bacteria is a General Phenomenon. *Am.*

J. Med. Sci. **242**, 527 (1973).

6. Fujita, Y., Grant Ferris, F., Daniel Lawson, R., Colwell, F. S. & Smith, R. W.

Calcium carbonate precipitation by ureolytic subsurface bacteria. *Geomicrobiol.*

J. **17**, 305–318 (2000).

7. Seifan, M. & Berenjian, A. Microbially induced calcium carbonate precipitation:

a widespread phenomenon in the biological world. *Appl. Microbiol. Biotechnol.*

103, 4693–4708 (2019).

8. Frankel, R. B. & Bazylinski, D. Biologically Induced Mineralization by Bacteria.

Rev. Mineral. Geochemistry **54**, 95–114 (2003).

9. Cosmidis, J. & Benzerara, K. Why do microbes make minerals? *Comptes*

Rendus - Geosci. **354**, 1–39 (2022).

10. Cohen-Cymberknoh, M. *et al.* Calcium carbonate mineralization is essential for

biofilm formation and lung colonization. *iScience* **25**, 104234 (2022).

11. Oppenheimer-Shaanan, Y. *et al.* Spatio-temporal assembly of functional

mineral scaffolds within microbial biofilms. *npj Biofilms Microbiomes* **2**, 15031

(2016).

12. Botusharova, S., Gardner, D. & Harbottle, M. Augmenting Microbially Induced

Carbonate Precipitation of Soil with the Capability to Self-Heal. *J. Geotech.*

Geoenvironmental Eng. **146**, 04020010 (2020).

13. Benzerara, K. *et al.* Intracellular Ca-carbonate biomineralization is widespread

in cyanobacteria. *Proc. Natl. Acad. Sci. U. S. A.* **111**, 10933–10938 (2014).

14. Baumgartner, L. K. *et al.* Sulfate reducing bacteria in microbial mats:

Changing paradigms, new discoveries. *Sediment. Geol.* **185**, 131–145 (2006).

15. Erşan, Y. Ç., De Belie, N. & Boon, N. Microbially induced CaCO3 precipitation

through denitrification: An optimization study in minimal nutrient environment.

Biochem. Eng. J. **101**, 108–118 (2015).

16. Stocks-Fischer, S., Galinat, J. K. & Bang, S. S. Microbiological precipitation of

CaCO3. *Soil Biol. Biochem.* **31**, 1563–1571 (1999).

17. Rivadeneyra, M. A., Delgado, R., Moral, A., Ferrer, M. R. & Ramos-

Cormenzana, A. Precipatation of calcium carbonate by Vibrio spp. from an

inland saltern. *FEMS Microbiol. Ecol.* **13**, 197–204 (1994).

18. Ehrlich, H. L. *Ehrlich's Geomicrobiology*. *Ehrlich's Geomicrobiology* (Taylor &

Francis, 2016).

19. Tourney, J. & Ngwenya, B. T. The role of bacterial extracellular polymeric

substances in geomicrobiology. *Chem. Geol.* **386**, 115–132 (2014).

20. Benzerara, K. *et al.* Nanoscale detection of organic signatures in carbonate

microbialites. *Proc. Natl. Acad. Sci. U. S. A.* **103**, 9440–9445 (2006).

21. Lyu, J. *et al.* Bacterial templated carbonate mineralization: insights from

concave-type crystals induced by Curvibacter lanceolatus strain HJ-1. *RSC*

Advances vol. 14 353–363 at https://doi.org/10.1039/d3ra06803j (2024).

22. Lyu, J., Qin, W., Zhang, C. & Li, F. Nanoparticle Accumulation in Microbial

Induced Carbonate Precipitation: The Crucial Role of Extracellular Polymeric

Substance. *Geomicrobiol. J.* **0**, 837–847 (2020).

23. Chen, L. *et al.* Bacteria-mediated synthesis of metal carbonate minerals with

unusual morphologies and structures. *Cryst. Growth Des.* **9**, 743–754 (2009).

24. Enyedi, N. T. *et al.* Cave bacteria-induced amorphous calcium carbonate

formation. *Sci. Rep.* **10**, 1–12 (2020).

25. Deng, Z., Jia, Z. & Li, L. Biomineralized Materials as Model Systems for

Structural Composites: Intracrystalline Structural Features and Their

Strengthening and Toughening Mechanisms. *Adv. Sci.* **9**, 2103524 (2022).

26. Brownlee, C., Wheeler, G. L. & Taylor, A. R. Coccolithophore biomineralization:

New questions, new answers. *Semin. Cell Dev. Biol.* **46**, 11–16 (2015).

27. Rodríguez-Navarro, C., Ruiz-Agudo, E., Harris, J. & Wolf, S. E. Nonclassical

crystallization in vivo et in vitro (II): Nanogranular features in biomimetic

minerals disclose a general colloid-mediated crystal growth mechanism. *J.*

Struct. Biol. **196**, 260–287 (2016).

28. Gilbert, P. U. P. A. *et al.* Biomineralization: Integrating mechanism and

evolutionary history. *Sci. Adv.* **8**, (2022).

29. Wegst, U. G. K., Bai, H., Saiz, E., Tomsia, A. P. & Ritchie, R. O. Bioinspired

structural materials. *Nat. Mater.* **14**, 23–36 (2015).

30. Yan, H. *et al.* The bio-precipitation of calcium and magnesium ions by free and

immobilized Lysinibacillus fusiformis DB1-3 in the wastewater. *J. Clean. Prod.*

252, 119826 (2020).

31. Park, S. J., Park, Y. M., Chun, W. Y., Kim, W. J. & Ghim, S. Y. Calcite-Forming

Bacteria for Compressive Strength Improvement in Mortar. *J. Microbiol.*

Biotechnol. **20**, 782–788 (2010).

32. Chekroun, K. Ben *et al.* Precipitation and growth morphology of calcium

carbonate induced by Myxococcus xanthus: Implications for recognition of

bacterial carbonates. *J. Sediment. Res.* **74**, 868–876 (2004).

33. Rodriguez-Navarro, C., Burgos Cara, A., Elert, K., Putnis, C. V. & Ruiz-Agudo,

E. Direct Nanoscale Imaging Reveals the Growth of Calcite Crystals via

Amorphous Nanoparticles. *Cryst. Growth Des.* **16**, 1850–1860 (2016).

34. De Yoreo, J. J. *et al.* Crystallization by particle attachment in synthetic,

biogenic, and geologic environments. *Science (80-.).* **349**, (2015).

35. Wolf, S. E. *et al.* Nonclassical crystallization in vivo et in vitro (I): Process-

structure-property relationships of nanogranular biominerals. *J. Struct. Biol.*

196, 244–259 (2016).

36. de Frutos, M., Rodríguez-Navarro, A. B., Li, X. & Checa, A. G. Nanoscale

Analysis of the Structure and Composition of Biogenic Calcite Reveals the

948   Biomineral Growth Pattern. *ACS Nano* **17**, 2829–2839 (2023).

949   37.   Gong, Y. U. T. *et al.* Phase transitions in biogenic amorphous calcium

950   carbonate. *Proc. Natl. Acad. Sci. U. S. A.* **109**, 6088–6093 (2012).

951   38.   DeOliveira, D. B. & Laursen, R. A. Control of calcite crystal morphology by a

952   peptide designed to bind to a specific surface. *J. Am. Chem. Soc.* **119**, 10627–

953   10631 (1997).

954   39.   Teng, H. H. & Dove, P. M. Surface site-specific interactions of aspartate with

955   calcite during dissolution: Implications for biomineralization. *Am. Mineral.* **82**,

956   878–887 (1997).

957   40.   Rodríguez-Navarro, A. B., Marie, P., Nys, Y., Hincke, M. T. & Gautron, J.

958   Amorphous calcium carbonate controls avian eggshell mineralization: A new

959   paradigm for understanding rapid eggshell calcification. *J. Struct. Biol.* **190**,

960   291–303 (2015).

961   41.   Beniash, E., Aizenberg, J., Addadi, L. & Weiner, S. Amorphous calcium

962   carbonate transforms into calcite during sea urchin larval spicule growth. *Proc.*

963   *R. Soc. B Biol. Sci.* **264**, 461–465 (1997).

964   42.   Ihli, J. *et al.* Dehydration and crystallization of amorphous calcium carbonate

965   in solution and in air. *Nat. Commun.* **5**, 1–10 (2014).

966   43.   Mehta, N., Gaëtan, J., Giura, P., Azaïs, T. & Benzerara, K. Detection of

967   biogenic amorphous calcium carbonate (ACC) formed by bacteria using FTIR

968   spectroscopy. *Spectrochim. Acta - Part A Mol. Biomol. Spectrosc.* **278**, 121262

969   (2022).

970   44.   Ryparová, P., Prošek, Z., Schreiberová, H., Bílý, P. & Tesárek, P. The role of

971   bacterially induced calcite precipitation in self-healing of cement paste. *J.*

972   *Build. Eng.* **39**, (2021).

45.   Schmidt, M. P., Ilott, A. J., Phillips, B. L. & Reeder, R. J. Structural changes

upon dehydration of amorphous calcium carbonate. *Cryst. Growth Des.* **14**,

938–951 (2014).

46. Rodríguez-Navarro, A. B. *et al.* Role of the Organic Matter in the Structural

Organization of Giant Barnacle Austromegabalanus Psittacus Shell from the

Micro- To Nanoscale. *Cryst. Growth Des.* **21**, 357–365 (2021).

47. Valverde, J. M., Perejon, A., Medina, S. & Perez-Maqueda, L. A. Thermal

decomposition of dolomite under CO2: Insights from TGA and in situ XRD

analysis. *Phys. Chem. Chem. Phys.* **17**, 30162–30176 (2015).

48. Cölfen, H. & Antonietti, M. Mesocrystals: Inorganic superstructures made by

highly parallel crystallization and controlled alignment. *Angew. Chemie - Int.*

Ed. **44**, 5576–5591 (2005).

49. Bergström, L., Sturm née Rosseeva, E. V., Salazar-Alvarez, G. & Cölfen, H.

Mesocrystals in biominerals and colloidal arrays. *Acc. Chem. Res.* **48**, 1391–

1402 (2015).

50. Towe, K. M. & Thompson, G. R. The structure of some bivalve shell carbonates

prepared by ion-beam thinning - A Comparison Study. *Calcif. Tissue Res.* **10**,

38–48 (1972).

51. Rodriguez-Navarro, C., Ruiz-Agudo, E., Luque, A., Rodriguez-Navarro, A. B. &

Ortega-Huertas, M. Thermal decomposition of calcite: Mechanisms of

formation and textural evolution of CaO nanocrystals. *Am. Mineral.* **94**, 578–

593 (2009).

52. Li, H. *et al.* Calcite prisms from mollusk shells (Atrina rigida): Swiss-cheese-

like organic-inorganic single-crystal composites. *Adv. Funct. Mater.* **21**, 2028–

2034 (2011).

53. Li, H., Xin, H. L., Muller, D. A. & Estroff, L. A. Visualizing the 3D Internal

Structure of Agarose Hydrogels. *Science (80-.).* **326**, 1244–1247 (2009).

54.   Nebel, H., Neumann, M., Mayer, C. & Epple, M. On the structure of amorphous

calcium carbonate - A detailed study by solid-state NMR spectroscopy. *Inorg.*

Chem. **47**, 7874–7879 (2008).

55.   Chaloupecká, E., Tyrpekl, V., Bártová, K., Nishiyama, Y. & Dračínský, M. NMR

crystallography of amino acids. *Solid State Nucl. Magn. Reson.* **130**, (2024).

56.   Pisklak, D. M. I., Szeleszczuk, Ł. & Wawer, I. 1H and 13C magic-angle

spinning nuclear magnetic resonance studies of the chicken eggshell. *J. Agric.*

Food Chem. **60**, 12254–12259 (2012).

57.   Kababya, S., Ben Shir, I. & Schmidt, A. From molecular level to macroscopic

properties: A solid-state NMR biomineralization and biomimetic exploration.

Curr. Opin. Colloid Interface Sci. **62**, 101630 (2022).

58.   Rietveld, H. M. Line profiles of neutron powder-diffraction peaks for structure

refinement. *Acta Crystallogr.* **22**, 151–152 (1967).

59.   Pokroy, B. *et al.* Anisotropic lattice distortions in biogenic calcite induced by

intra-crystalline organic molecules. *J. Struct. Biol.* **155**, 96–103 (2006).

60.   Pokroy, B., Fitch, A. N. & Zolotoyabko, E. The microstructure of biogenic

calcite: A view by high-resolution synchrotron powder diffraction. *Adv. Mater.*

18, 2363–2368 (2006).

61.   Aizenberg, J., Hanson, J., Koetzle, T. F., Weiner, S. & Addadi, L. Control of

macromolecule distribution within synthetic and biogenic single calcite

crystals. *J. Am. Chem. Soc.* **119**, 881–886 (1997).

62.   Lang, A. *et al.* Acidic Monosaccharides become Incorporated into Calcite Single

Crystals**. *Chem. - A Eur. J.* **26**, 16860–16868 (2020).

63.   Albéric, M. *et al.* Interplay between Calcite, Amorphous Calcium Carbonate,

and Intracrystalline Organics in Sea Urchin Skeletal Elements. *Cryst. Growth*

Des. **18**, 2189–2201 (2018).

64.   Stevenson, H. P. *et al.* Use of transmission electron microscopy to identify

nanocrystals of challenging protein targets. *Proc. Natl. Acad. Sci. U. S. A.* **111**,

8470–8475 (2014).

65.   Schultze-Lam, S. & Beveridge, T. J. Nucleation of Celestite and Strontianite on

a Cyanobacterial S-Layer. *Appl. Environ. Microbiol.* **60**, (1994).

66.   Rodriguez-Navarro, C. *et al.* The multiple roles of carbonic anhydrase in

calcium carbonate mineralization. *CrystEngComm* **21**, 7407–7423 (2019).

67.   Murdock, J. N. & Wetzel, D. L. FT-IR microspectroscopy enhances biological

and ecological analysis of algae. *Appl. Spectrosc. Rev.* **44**, 335–361 (2009).

68.   Ji, Y. *et al.* DFT-Calculated IR Spectrum Amide I, II, and III Band Contributions

of N-Methylacetamide Fine Components. *ACS Omega* vol. 5 8572–8578 at

https://doi.org/10.1021/acsomega.9b04421 (2020).

69.   Kim, Y. Y. *et al.* An artificial biomineral formed by incorporation of copolymer

micelles in calcite crystals. *Nat. Mater.* **10**, 890–896 (2011).

70.   Seto, J. *et al.* Structure-property relationships of a biological mesocrystal in

the adult sea urchin spine. *Proc. Natl. Acad. Sci. U. S. A.* **109**, 3699–3704

(2012).

71.   Cosmidis, J. & Benzerara, K. Comptes Rendus Géoscience Why do microbes

make minerals? *Comptes Rendus - Géoscience Sci. la Planète* **354**, 0–39

(2022).

72.   Mugwar, A. J. & Harbottle, M. J. Toxicity effects on metal sequestration by

microbially-induced carbonate precipitation. *J. Hazard. Mater.* **314**, 237–248

(2016).

73.   Albéric, M. *et al.* The Crystallization of Amorphous Calcium Carbonate is

Kinetically Governed by Ion Impurities and Water. *Adv. Sci.* **5**, (2018).

74.   Dupraz, C. *et al.* Processes of carbonate precipitation in modern microbial

mats. *Earth-Science Rev.* **96**, 141–162 (2009).

75. Couradeau, E. *et al.* An Early-Branching Microbialite Cyanobacterium Forms

Intracellular Carbonates. 459–463 (2012).

76. Supuran, C. T. & Capasso, C. An overview of the bacterial carbonic

anhydrases. *Metabolites* **7**, (2017).

77. Kocot, K. M., Aguilera, F., McDougall, C., Jackson, D. J. & Degnan, B. M. Sea

shell diversity and rapidly evolving secretomes: Insights into the evolution of

biomineralization. *Front. Zool.* **13**, 1–10 (2016).

78. Soucy, S. M., Huang, J. & Gogarten, J. P. Horizontal gene transfer: Building

the web of life. *Nat. Rev. Genet.* **16**, 472–482 (2015).

79. Sieber, K. B., Bromley, R. E. & Dunning Hotopp, J. C. Lateral gene transfer

between prokaryotes and eukaryotes. *Exp. Cell Res.* **358**, 421–426 (2017).

80. Kahil, K. *et al.* Cellular pathways of calcium transport and concentration

toward mineral formation in sea urchin larvae. *Proc. Natl. Acad. Sci. U. S. A.*

117, 30957–30965 (2020).

81. Taylor, A. R., Brownlee, C. & Wheeler, G. Coccolithophore Cell Biology:

Chalking Up Progress. *Ann. Rev. Mar. Sci.* **9**, 283–310 (2017).

82. Gould, S. B., Garg, S. G. & Martin, W. F. Bacterial Vesicle Secretion and the

Evolutionary Origin of the Eukaryotic Endomembrane System. *Trends*

Microbiol. **24**, 525–534 (2016).

83. Margulis, L. & Bermudes, D. Symbiosis as a mechanism of evolution: status of

cell symbiosis theory. *Symbiosis* **1**, 101–124 (1985).

84. Gilbert, P. U. P. A. *et al.* Biomineralization by particle attachment in early

animals. *Proc. Natl. Acad. Sci. U. S. A.* **116**, 17659–17665 (2019).

85. Clark, M. S. Molecular mechanisms of biomineralization in marine

invertebrates. *J. Exp. Biol.* **223**, (2020).

86.   Barabesi, C. *et al.* Bacillus subtilis gene cluster involved in calcium carbonate

biomineralization. *J. Bacteriol.* **189**, 228–235 (2007).

87.   Markgraf, S. A. & Reeder, R. J. High-temperature structure refinements of

calcite and magnesite. *Am. Mineral.* **70**, 590–600 (1985).

1082