Multidirectional alignment of collagen fibers to guide cell orientation in 3D-printed tissue

Diya Singhal[1,‡], Fotis Christakopoulos[2,‡], Lucia G. Brunel[1], Suraj Borkar[1], Vanessa M. Doulames[2], David Myung[3,4], Gerald G. Fuller[1] and Sarah C. Heilshorn[2,*]

[1] Department of Chemical Engineering, Stanford University, Stanford, CA, USA
[2] Department of Materials Science and Engineering, Stanford University, Stanford, CA, USA
[3] Department of Ophthalmology, Byers Eye Institute, Stanford University School of Medicine, Palo Alto, CA, USA
[4] VA Palo Alto Healthcare System, Palo Alto, CA, USA
‡ These authors contributed equally to this work

E-mail: `heilshorn@stanford.edu`

Abstract. Natural tissue comprises fibrous proteins with complex fiber alignment patterns. Here, we develop a reproducible method to fabricate biomimetic scaffolds with patterned fiber alignment along multiple orientations. While extrusion-based approaches are commonly used to align fibrous polymers in a single orientation parallel to the direction of flow, we hypothesized that extrusion-based 3D printing could be utilized to achieve more complex patterns of fiber alignment. Specifically, we show control of lateral spreading of a printed filament can induce fiber alignment that is either parallel or perpendicular to the flow direction. Theoretical prediction of the printing parameters that control fiber orientation was experimentally validated using a collagen biomaterial ink. The velocity ratio of the printhead movement relative to the ink extrusion rate was found to dictate collagen fiber alignment, allowing for the informed fabrication of collagen scaffolds with prescribed patterns of fiber alignment. For example, controlled variation of the ink extrusion rate during a single print resulted in scaffolds with specified regions of both parallel and perpendicular collagen fiber alignment. Human corneal mesenchymal stromal cells seeded onto the printed scaffolds adopted a spread morphology that aligned with the underlying collagen fiber patterns. This technique worked well for filaments either printed into air or extruded within a support bath using embedded 3D printing, enabling the fabrication of 3D structures with aligned collagen fibers. Taken together, this work demonstrates a theoretical and experimental framework to achieve the reproducible fabrication of 3D printed structures with controlled collagen fiber patterns that guide cellular alignment.

Keywords: collagen inks, fiber orientation, extrusion-based 3D printing, cell alignment

1. Introduction

Tissues in the body commonly include a fibrous matrix with exquisite fiber alignment along different directions, which guides cell alignment and spreading (1; 2; 3; 4; 5; 6; 7; 8; 9). The most abundant fibrous protein of the native extracellular matrix (ECM) in the human body is collagen, and different, complex patterns of collagen fiber alignment are observed across different tissues, such as the cornea, cartilage, and arteries. (5; 8; 10; 11; 12; 13). For example, in the cornea, the ECM contains orthogonal sheets of collagen fibrils that are able to transmit light while being mechanically resilient (5; 14). In articular cartilage, collagen fibril architecture exhibits depth-dependent organization: fibrils are aligned parallel to the surface in the superficial zone, display a more isotropic distribution in the transitional zone, and orient perpendicular to the surface in the deep zone, where they anchor into the calcified cartilage (12). This zonal arrangement restricts tissue swelling, facilitates osmotic pressurization for load-bearing, and confers both compressive compliance and shear resistance . Arterial collagen fibers are predominantly arranged in a helical pattern, enabling them to reinforce the artery in both the circumferential and axial directions (15; 13).

Collagen fiber alignment can direct many physiological cellular processes, such as migration (16), differentiation (6), and proliferation (17). Thus, a common goal in tissue engineering is to control the orientation of collagen fibers to guide cell behavior (7; 18; 6; 16). To date, several fabrication techniques have been used to create substrates with aligned collagen fibers, including electro-spinning, magnetic flow alignment, microfluidics, mechanical strain devices, and gravity-based fluidic alignment (19; 20; 21; 16; 6). While these aligned collagen constructs have been helpful tools to study cell-matrix interactions such as mechanosensing, cell migration speed, and cell persistence, these techniques are typically limited to unidirectional fiber alignment (22; 16; 23). Creative approaches to overcome this limitation and fabricate radial patterns of collagen fibers have employed Marangoni flow in evaporating, aqueous sessile droplets (24) and microextrusion of discrete filaments in different macroscopic orientations (18). Yet, it remains challenging to achieve larger constructs with controlled fiber alignment in multiple directions.

Recently, 3D printing of biological materials has emerged as a reproducible, scalable, and versatile method to fabricate constructs with clinically relevant dimensions and increased complexity (25; 26; 27; 28; 29; 30; 31; 32). In particular, extrusion-based 3D printing offers ease of use and the potential to produce oriented constructs. Alignment in the extrusion direction has been achieved through different methods for a variety of polymers and fibrous materials. For example, alignment can be induced inside the *print nozzle* by subjecting the material to controlled flow profiles during extrusion; alternatively, alignment can be induced outside of the print nozzle by subjecting the printed filament to extensional deformation (33; 34; 7; 35; 36; 37; 38; 39; 40). For fibrous collagen inks, shear stress-induced fiber alignment has been achieved through extrusion-based 3D printing, resulting in constructs with uniaxially aligned fibers in the

direction of printing (7; 18).

Here, we sought to develop an easy to implement and reproducible 3D printing strategy to create constructs with collagen fibers aligned in multiple directions. Specifically, we demonstrate the ability to pattern collagen fibers both parallel to and perpendicular to the printing direction, enabling the fabrication of constructs with more complex patterns of fiber alignment. To achieve this, we hypothesized that two different printing regimes could be achieved within a single printing setup. The first regime relies primarily on extensional deformation of the collagen ink within a tapered print nozzle to achieve fiber alignment that is parallel to the print direction. In the second regime, we rationalized that controlling the lateral spreading of the printed filament post-printing can be used to induce collagen fiber alignment perpendicular to the printing direction.

To explore this idea, we first theoretically predicted how different printing parameters might impact filament lateral spreading. We then performed a systematic evaluation of the printing parameters for our extrusion-based 3D printer and quantified the collagen fiber alignment patterns for each condition. These experimental observations validated our predictions and allowed us to define the printing parameters for each regime of fiber alignment. We next demonstrated the ability of these parallel and perpendicularly aligned collagen substrates to guide the spreading morphology of cells. Using this new printing strategy, we fabricated specimens with multidirectional collagen fiber alignment in a single print. Taken together, this work introduces a predictable, reproducible, and scalable approach to print biomimetic constructs with complex patterns of collagen fiber directionality to guide cellular alignment.

2. Results and discussion

2.1. Collagen fiber alignment along the printing direction

Collagen inks are widely used in 3D printing, both in the solution and the gel state (10; 41; 42; 7). Collagen gelation is attained through physical assembly and entanglement of collagen fibers at physiological conditions, with the kinetics being dependent on collagen concentration, temperature, and pH (43; 44; 45; 46). Collagen inks have been formulated to form fibers before printing, during printing, or after printing (add references).

We chose to formulate a collagen ink with pre-formed fibers that would become oriented by fluid mechanics, as we reasoned that printing parameters would have a stronger impact on pre-formed fibers as opposed to soluble collagen protein.[ref] Specifically, we selected a neutralized type-I atelocollagen at a relatively high concentration of 35 mg mL^{-1} that is stored and printed at 4 °C. At these conditions, the ink has storage (G') and loss (G'') moduli of about 250 Pa and 150 Pa, respectively (figure 1(A)). Thus, the ink is already a weak gel ($G' > G''$) prior to printing, due to its high concentration and neutral pH. Importantly, the ink at 4 °C displays shear-thinning behavior, making it suitable for extrusion-based 3D printing (figure 1(B)). Additionally,

this ink formulation demonstrates the ability to recover after shear-thinning. After exposure to high shear that disrupts the network structure, the fluid achieves a 80% storage modulus recovery in 30 seconds at 4 °C and recovers its initial stiffness after 240 seconds(figure S1(A). As the ink is deposited on the printbed, which is at room temperature, the physical assembly of the collagen fibers continues to progress, as evident in the ten-fold increase in G', reaching a plateau of 2,000 Pa (figure 1(C)). The presence of fibers in the ink cartridge was confirmed by confocal reflectance microscopy at 4 °C 1(D). As expected, collagen fibers within the ink are initially randomly oriented.

Figure 1. Extrusion-based 3D printing setup for collagen fiber alignment. (A) Time sweep, shear rheology of the collagen ink at 4 °C; (storage modulus, G' , •; loss modulus, G'', ○; temperature: red solid line). (B) Shear-dependent viscosity of the collagen ink at 4 °C. (C) Shear rheology of the collagen ink as temperature increases from 4 to 23 °C; (storage modulus, G' , •; loss modulus, G'', ○; temperature: red solid line). (A-C) Data are mean ± standard deviation; N = 3 independent gel conditions. For (A) and (B), symbol size is larger than the errorbars. (D) Representative confocal reflectance image of the collagen ink prior to extrusion. (E) Schematic of the extrusion-based printing setup showing the different printing parameters; ink cartridge diameter (D, mm), nozzle diameter (d_{nozzle}, mm), translational speed of the printhead (F, mm min^{-1}), speed of ink extrusion (C, mm min^{-1}), plunger displacement per step (E, mm), lateral displacement distance of the printhead per step (Δx, mm), and diameter of the printed filament (d_{print}). An ice pack is positioned around the syringe to keep the ink at 4 °C, which is deposited on a printbed in air at room temperature. (F) Representative confocal reflectance image of the collagen post-printing, showing fiber alignment parallel to the printing direction (black arrow).

To demonstrate that this collagen ink could achieve parallel alignment similar to that reported by others [reference], we employed a standard extrusion-based 3D printing system (figure 1(E)) This setup offers several user-defined parameters including the ink

cartridge diameter, D, which we kept constant through all experiments (7.29 mm), and the diameter of the printing nozzle, d_{nozzle}, which was varied in our studies. In addition to these hardware parameters, the setup also includes a number of user-defined parameters controlled through the software (*e.g.* Gcode). These include the plunger displacement per step, E, the lateral displacement of the printhead per step, Δx, and the translation speed of the printhead, F. Through these hardware- and software-controlled variables, we define further printing parameters such as the speed of ink extrusion from the nozzle, C, and the diameter of the printed filament, d_{print}. Through optimization, we were able to identify a combination of printing parameters (table S1) that results in parallel fiber alignment at within the printed filament at 23 °C (figure 1(F)), similar to results of others (7). Upon further heating of the collagen print to physiological temperature (37 °C), additional collagen fiber formation occurs, as evidenced by a further increase in G' to about 3500 Pa (figure S1(B,C)). To confirm that the heating to 37 °C does not disrupt the achieved fiber alignment, we incubated the sample for 15 minutes and then confirmed that the alignment remains unchanged by confocal reflectance imaging (figure S1(D)). Having been able to replicate the state of the art with our extrusion-based 3D printing setup, we next investigated the ability to achieve fiber alignment in an orientation other than the printing direction, towards the broader goal of fabricating constructs with multidirectional collagen fiber alignment.

2.2. Printed filament spreading dictates fiber alignment orientation

Previously, an interesting correlation between extruded width and fiber alignment has been shown where low extrusion width lead to more fiber aligned in printing direction however as extruded width increases less fibers are aligned in the printing direction (47). We hypothesized that harnessing the lateral spreading of the printed filament post-printing would lead to perpendicular alignment of the collagen fibers. This lateral spreading of the printed filament can be quantified as a ratio of printed filament diameter (d_{print}) to the nozzle diameter (d_{nozzle}), which we define as the diameter ratio, D^*, (figure S2):

$$D^* = \frac{d_{\mathrm{print}}}{d_{\mathrm{nozzle}}} \tag{1}$$

Thus, when $D^* < 1$, the printed filament diameter is smaller than the nozzle diameter, implying less printed filament spreading. In contrast, when $D^* > 1$, the printed filament diameter is higher than the nozzle diameter, denoting more printed filament spreading. To control the lateral spreading of the printed filament, we derived a theoretical expression of D^* by performing a mass balance. For our extrusion-based, piston-controlled, 3D printer, the volumetric flow rate inside the syringe ($\dot{Q}_{\mathrm{syringe}}$) is defined as:

$$\dot{Q}_{\mathrm{syringe}} = \frac{A_{\mathrm{syringe}} E}{\frac{\Delta x}{F}} \tag{2}$$

which, due to mass conservation, is equal to the volumetric flow rate at the end of the nozzle ($\dot{Q}_{\text{nozzle}}$):

$$\dot{Q}_{\text{nozzle}} = \dot{Q}_{\text{syringe}} \tag{3}$$

Similarly, the volumetric flow rate at the end of the nozzle can be equated to that of the printed filament after extrusion from the nozzle:

$$\dot{Q}_{\text{nozzle}} = \dot{Q}_{\text{filament}} \tag{4}$$

We initially assume the printed filament is a cylinder to enable the estimation of $\dot{Q}_{\text{filament}}$ as:

$$\dot{Q}_{\text{filament}} = \frac{F\pi d_{\text{print}}^2}{4} \tag{5}$$

In actuality, the printed filament will not be a perfect cylinder, and to account for this, we introduce the coefficient, β. When $\beta = 1$, then the cross-sectional area of the printed filament would be perfectly circular (*i.e.* the width and height of the printed filament will be similar), and when $\beta > 1$, the filament will undergo lateral spreading.

Using conservation of mass, 2-5 we find:

$$\frac{A_{\text{syringe}}E}{\frac{\Delta x}{F}} = \frac{F\beta\pi d_{\text{print}}^2}{4} \tag{6}$$

giving us a theoretical prediction for d_{print} as:

$$d_{\text{print}} = \sqrt{\frac{4\beta A_{\text{syringe}}E}{\pi\Delta x}} \tag{7}$$

In turn, D^* (*i.e.* the normalized printed filament diameter) can also be correlated to the printing parameters as:

$$D^* = \frac{1}{d_{\text{nozzle}}}\sqrt{\frac{4\beta A_{\text{syringe}}E}{\pi\Delta x}} \tag{8}$$

From eq. 8, it can be duly noted that D^* depends on two of the printing parameters introduced in figure 1(E), namely E (plunger distance per step) and d_{nozzle} (nozzle diameter), with the proportionality given as:

$$D^* \propto \frac{\sqrt{E}}{d_{\text{nozzle}}} \tag{9}$$

To test this theoretical prediction, we conducted a series of controlled experiments wherein either E or d_{nozzle} was independently varied. For each experimental condition, we measured the actual d_{print} (*i.e.* the printed filament width) through confocal imaging to calculate an experimentally observed D^*. First, we kept E constant ($E = 0.007$ mm) and decreased d_{nozzle} from 1.55 mm to 0.16 mm (a ratio of $\simeq$ 9.7:1). Upon microscopy analysis of the resulting printed filaments, we observed that decreasing d_{nozzle} causes D^* to increase from 0.875 to 8.406 (a ratio of $\simeq$ 1:9.6) (Figure 2(A)). Thus, for these

conditions, we found that D^* and d_{nozzle} are inversely proportional, consistent with our theoretical prediction (eq. 9).

Next, we kept d_{nozzle} constant ($d_{\mathrm{nozzle}} = 1.55$ mm) while E was increased from 0.005 mm to 0.040 mm (a ratio of $\simeq$ 1:8) (figure 2(B)). Upon measuring the width of the printed filament for increasing E, we observed that D* increased from 0.875 to 3.019 (a ratio of $\simeq$ 1:3.45). Thus, these experimental results are consistent with our theoretical prediction that D^* is directly proportional to $\sqrt{E}$ (eq. 9).

Figure 2. Diameter ratio correlates with collagen fiber alignment in printed filaments. (A) Representative confocal reflectance images of collagen filaments printed with the same plunger displacement per step ($E = 0.005$ mm) and different nozzle diameters (d_{nozzle}). (B) Collagen filaments printed with the same nozzle ($d_{\mathrm{nozzle}} = 1.55$ mm) and different plunger displacement per step (E). Yellow dotted lines denote the nozzle diameter for easy comparison to the printed filament width. The experimentally determined diameter ratio, D^*, (*i.e.* the width of the printed filament, d_{print}, normalized by the diameter of the printing nozzle, d_{nozzle}) is written above each micrograph along with a qualitative description of the observed collagen fiber orientation. Scalebars correspond to 500 μm.

After validating our ability to predict the printed filament width based on our printing parameters, we then observed the fiber alignment within each filament using confocal reflectance microscopy. To aid in the assessment of fiber alignment direction and to prevent observational bias, we used an automated fiber tracing algorithm (CT-FIRE for Individual Fiber Extraction) that traces and artificially colors individual fibers to enable visualization of fiber orientation (figure S3). We found that at low D^* (*i.e.* the condition where uniaxial filament extension occurs, 0.875 in the left panels in figure 2A,B), the collagen fibers were oriented parallel to the printing direction (figure Sx).

In contrast, for the conditions with $D^* > 1$ (*i.e.* significant lateral filament spreading, 8.406 and 3.019 in the right panels of figure 2(A) and 2(B), respectively) the collagen fibers were observed to orient perpendicular to the filament printing direction (figure Sx). This observation is consistent with our hypothesis that fluid flow that occurs after extrusion while the filament is undergoing uniaxial extension or lateral spreading can be sufficient to induce parallel or perpendicular alignment of embedded collagen fibers, respectively. For experimental conditions with an intermediate value of D^* ($D^* \simeq 1$, middle panels of figure 2A,B), the collagen fibers were randomly oriented (figure S3). This observation suggests that there is an intermediate transition regime where the embedded fibers experience neither sufficient extensional flow to orient in the parallel direction, nor enough lateral flow to orient perpendicularly.

2.3. Quantification of fiber alignment across a broad printing space

We next wanted to identify the relevant values of D^* to achieve parallel or perpendicular collagen fiber alignment across a wide range of printing parameter space. To categorize the prints into different alignment regimes, we developed a technique to quantify the fiber alignment orientation using automated software analysis from the confocal reflectance micrographs (figure 3(A)). From this analysis, we prepared histograms showing the normalized frequency of fiber alignment relative to the total number of fibers versus fiber orientation, where the printing direction is 0 ° (figure 3(B, C) and figure S5(A,B)).

Figure 3. Selection of printing parameters controls the collagen fiber alignment direction. (A) Automated analysis of representative confocal reflectance images for different combinations of plunger displacement per step (E) and nozzle diameter (d_{nozzle}) leads to identification of parallel (blue), random (green) and perpendicular (red) alignment regimes. (B) Histograms of fiber alignment when keeping the plunger displacement constant and changing the nozzle diameter, showing the normalized frequency of fiber alignment relative to the total number of fibers versus fiber orientation, where the printing direction is 0 °. (C) Histograms of fiber alignment when keeping the nozzle diameter constant and changing the plunger displacement. (D) Alignment parameter (AP) plotted for several combinations of E and d_{nozzle} show that the printing parameter space can be divided into three regimes with different fiber alignment directions: parallel (blue, $AP \leq 0.5$), random (green, $0.5 < AP \leq 2$) and perpendicular (red, $AP > 2$). (B,C) Data are mean $\pm$ standard deviation, N = 3 independent printing trials.

From these histograms, we further calculated an Alignment Parameter (AP), which we define as the ratio of the fraction of perpendicular fibers (orientation ranges from $-80°$ to $-60°$ and $60°$ to $80°$) to the fraction of parallel fibers (orientation from $-20°$ to $20°$). To support visual validation of our automated analysis, we also used the aforementioned automated fiber tracing algorithm to artificially color individual fibers (figure 3(A)). With this analytical workflow in place, we systematically varied E and d_{nozzle} and quantified the fiber alignment for three independent printing trials at each of 24 conditions. First, we found that by keeping d_{nozzle} constant ($d_{\mathrm{nozzle}} = 1.55$ mm or 0.84 mm, left and middle columns, respectively, in figure 3(A)), the fiber alignment

direction can be transitioned from parallel to random to perpendicular by increasing the plunger displacement E from 0.003 mm to 0.04 mm (left and middle graph in figure 3(A,B) and supplemental figure S4(X)). Interestingly, for choice of smaller d_{nozzle} (0.16 mm, right-most column, (figure 3(A)), the fiber alignment direction was predominantly perpendicular for all E values tested (right column in figure 3(A) and 3 (B)). These data suggest that careful selection of a single nozzle could be used to print all three different fiber orientations within a single construct.

An alternative method to control the fiber alignment orientation is to keep E constant while varying d_{nozzle}. For lower E values (0.003 or 0.007 mm, top two rows in figure 3(A)), decreasing d_{nozzle} from 1.55 to 0.16 mm resulted in a transition from parallel to perpendicular fiber alignment, respectively (top two graphs in figure 3(C)). For larger E (0.01 mm or 0.04 mm, bottom two rows in figure 3(A)), the alignment direction is predominantly perpendicular for all d_{nozzle} values (bottom graph in figure 3(C)) and figure S5). These data suggest that multinozzle printing systems also could be used to achieve all three different fiber orientations within a single construct.

To synthesize together the information from each histogram into a single quantitative metric, we next calculated and plotted the AP value for each of the 24 tested combinations of printing parameters (figure 3(D)). This allowed us to identify cutoff values of AP that define the three regions of fiber alignment: parallel (blue, $AP \leq 0.5$), random (green, $0.5 < AP \leq 2$) and perpendicular (red, $AP > 2$) (figure 3(D)). At the cutoff value of AP ≤ 0.5 , the number of fibers aligned in the parallel direction is approximately twice that of the perpendicular direction. In the green, random region ($0.5 < $ AP $ < 2$), the proportions of parallel and perpendicular fibers are comparable. Finally, for AP ≥ 2, roughly twice as many fibers are oriented perpendicularly compared to those aligned in the parallel direction. Interestingly, for this particular ink formulation and printer setup, we found that 16 of the 24 tested printing parameter combinations resulted in perpendicular fiber alignment (figure 3(D)). Thus, while most bioprinting studies to date have focused on the parallel alignment of fibers, printing conditions to achieve perpendicular fiber alignment are readily achievable.

2.4. Normalized speed of ink extrusion dictates fiber alignment orientation

Although the exact values of E and d_{nozzle} that result in perpendicular or parallel fibers will be different for each printer setup, we reasoned that more generalizable guidelines could be identified by considering how AP relates to the D^* ratio as defined previously in equation 8. Towards this goal, we first experimentally identified the dependence of E and d_{nozzle} on the printed filament width (d_{print}). As E increases from 0.003 to 0.04 mm, d_{print} increases monotonically due to the increased amount of extruded material. Interestingly, we observed that for a particular E value, d_{print} remains the same irrespective of d_{nozzle} (figure 4(A)), which is consistent with our theoretical prediction (eq. 7). By plotting AP against D^* for our 24 printing conditions, we were able to identify the ranges of D^* for the three fiber alignment regimes using our earlier AP cutoff values (figure 4(B).

Specifically, we found that $D^* \leq 1$ produced filaments in the parallel fiber alignment region ($AP \leq 0.5$), and $D^* > 2$ produced filaments in the perpendicular fiber alignment region (AP $\geq$ 2). For values between these two regions, *i.e.* $1 < D^* \leq 2$, fibers had random alignment.

We then compared the experimentally determined values of D^* to our earlier theoretical prediction (equation 8), where the only fitting parameter is β (figure 4(C). When fitting our experimental data to this equation, we found the same value of $\beta = 4$ for each d_{nozzle} tested across the full range of E. This constant fitting parameter further supports the notion that β is an ink-dependent parameter that does not change with the tested printing conditions, and thus remains unchanged for a given ink system (*e.g.* ink composition and temperature).

Figure 4. Relative speed of ink deposition controls filament spreading and fiber alignment. (A) Experimentally determined printed filament width (d_{print}) plotted as a function of E for different values of d_{nozzle}. (B) Alignment parameter (AP) plotted against D^* across 24 printing conditions, with distinct alignment regimes based on AP. Symbol colors denote d_{nozzle}, while symbol shapes denote E. (C) Experimental data and theoretical fits for D^* as a function of E for different values of d_{nozzle}. (D) Schematic of fiber alignment regimes for different velocity ratios (V^*), where V^* is the ratio of ink extrusion speed from the nozzle (C) to the translational speed of the printbed (F). (E) Alignment parameter (AP) plotted against V^* for 24 printing conditions, with distinct alignment regimes based on AP. (F) Theoretical values of V^* plotted as a function of E for different values of d_{nozzle}. (A,B,C,E,F) Data are mean $\pm$ standard deviation, N = 3 independent printing trials. $^{**}p < 0.01, ^{***}p < 0.001, ^{****}p < 0.0001$.

To reformulate our theoretical prediction into a format that is independent of β, so that it is controlled solely by the experimental printing parameters (*e.g.* E, d_{nozzle}, F,

D, Δx) for a specific ink system, we defined the normalized velocity, V^*:

$$V^* = \frac{C}{F} \tag{10}$$

where C corresponds to the speed of the ink extrusion from the nozzle and F to the translational speed of the printhead. We hypothesized that when $C \gg F$, i.e. the speed at which ink is extruded is higher than the translational speed of the printhead, the ink would experience significant lateral spreading on the printbed, leading to perpendicular fiber alignment relative to the printing direction (figure 4(D)). In contrast, when $C \ll F$, i.e. the speed at which the ink is extruded is lower than the translational speed of the printhead, the filament will become extensionally drawn as it gets extruded, leading to parallel fiber alignment. When $C \leq F$, i.e. the speed at which ink is extruded is comparable to the translational speed of the printhead, the filament does not experience significant lateral spreading or extensional drawing, leading to random alignment of fibers.

This normalized velocity framework enables extension to other extrusion-based systems such as pneumatic-controlled printers, where F is explicitly selected, while C will depend on the pressure drop through the syringe and nozzle, ΔP. The maximum stress, τ_w in capillary flow can be calculated from: (48)

$$\tau_w = \frac{d_{\mathrm{nozzle}}\Delta P}{4L} \tag{11}$$

, where L is the length of the nozzle. For power-law fluids, the shear rate, $\dot{\gamma}_w$, is calculated from:

$$\dot{\gamma}_w = \frac{3n+1}{4n} \cdot \frac{32\dot{Q}}{\pi d_{\mathrm{nozzle}}^3} \tag{12}$$

, where n is the power-law index. Through equation SX and:

$$\tau_w = \eta\dot{\gamma}_w \tag{13}$$

, where η is the apparent shear viscosity, we can get an expression for C:

$$C = \frac{4n}{3n+1} \cdot \frac{d_{\mathrm{nozzle}}^2\Delta P}{32\eta L} \tag{14}$$

For our specific extrusion-based 3D printer, the theoretical equation for V^* is derived using mass conservation by equating the volumetric flow rate inside the syringe to the volumetric flow rate at the tip of the printing nozzle (equation S(x-y)) and can be expressed as:

$$V^* = \frac{4A_{\mathrm{syringe}}E}{\pi d_{\mathrm{nozzle}}^2\Delta x} \tag{15}$$

To confirm that this formulation of V^* can directly predict the direction of fiber alignment without any fitting parameters, we correlated the resulting theoretical V^* values with the experimentally determined alignment parameter (AP) across the range

of E and d_{nozzle} conditions presented earlier (figure 4(E)). As before, we used our AP cutoff values to identify the regimes that correspond to perpendicular, random, and parallel fiber alignment. From this analysis, we observed that a $V^* < 0.5$ results in parallel fibers ($AP \leq 0.5$), intermediate values of V^* ($0.5 \leq V^* \leq 1$) results in randomly aligned fibers ($0.5 < AP \leq 2$), and $V^* \geq 1$, results in perpendicular fibers ($AP > 2$). These results agree with a similar ratio that was identified in earlier studies for an extrusion deposition additive manufacturing system (the ratio of the extrusion speed and print speed), where ratios less than unity resulted in greater fiber alignment in the printing direction (49).

To enable the prediction of fiber alignment with no fitting parameters, we plotted the theoretical curves of $V*$ as a function of E for each d_{nozzle} tested, using equation. 15 (figure 4(F)). For ease of viewing the three different fiber alignment regimes are shown as different color-coded regions, and we overlaid the points corresponding to the 24 specific combinations of E and d_{nozzle} tested out experimentally. Similar plots could be constructed for other printer-ink combinations to enable prediction of printing parameters that result in specific fiber alignment orientations. As extrusion-based printers are generally widely available and easy to use, this framework could be readily adapted to other systems. While the diameter ratio (D^*) included a fitting parameter that is related to the intrinsic ink properties, the velocity ratio (V^*) depends only on the printing parameters programmed into the 3D printer.

2.5. Control of fiber alignment in embedded 3D printing

As our data suggest that fiber alignment is primarily dictated by filament spreading versus filament drawing (and does not depend on interactions between the filament and the printbed), we hypothesized that the same printing parameters that induce parallel or perpendicular fiber alignment when printed in air would also cause fiber alignment when printed in a support bath. Embedded 3D printing into support baths has emerged as a strategy to expand the range of printable materials and the complexity of fabricated structures with intricate features (50; 51; 52). In contrast to printing in air, in embedded 3D printing the ink material is deposited into an aquaeus yield-stress fluid (50). This allows the printed material to remain suspended and supported during the printing process, enabling the creation of complex 3D structures that would otherwise collapse under their own weight and/or aqueous surface tension if printed in air. (ref)

To explore if our fiber alignment strategy could be extended to embedded 3D printing, we prepared a Carbopol support bath material. Carbopol is widely used as a support bath due to its shelf-healing behavior (figure 5(A)) (53). In addition, previous work has demonstrated that a large range of printing speeds are compatible with Carbopol support baths without causing porosity in the final print (54).

Figure 5. Collagen fiber alignment in embedded 3D printing. (A) Shear rheology of Carbopol support bath upon alternating application of high or low shear strain (red line) demonstrates shear-thinning and shelf-healing behavior. Filled symbols correspond to storage moduli, G', and open symbols correspond to loss moduli, G''. (B) Multilayer collagen construct 3D printed in a Carbopol support bath. (C-D) (Left) Representative confocal reflectance images with parallel (C) and perpendicular (D) fiber alignment. (Right) Quantification of the collagen fiber alignment of collagen filaments printed in a Carbopol support bath compared to controls printed in air at the same conditions. (C,D) Data are mean $\pm$ standard deviation; n=3 independent printing experiments.

As a demonstration, we printed a 3D structure having hollow, suspended features (*i.e. windows)* and built up as a multilayered construct in which fiber alignment was be tuned in each individual filament (figure 5(B)). In addition, single filaments, which allow for easier visualization of the collagen fibers after removal from the support bath, were printed with identical printing parameters (figure SI-table). The fiber alignment of the resulting prints was imaged and quantified for comparison to that of filaments printed in air with the same printing conditions (figure 5(C,D)). Collagen fibers were well aligned when filaments were printed into the Carbopol support bath, both for conditions that result in parallel and perpendicular orientations. Furthermore, the degree of fiber alignment was found to be similar for filaments printed in air or within the Carbopol support bath. For example, the AP for parallel alignment printing in air and in the support bath was found to be 0.35 ± 0.044 and 0.30 ± 0.02 respectively. The AP for perpendicular alignment in air and in the support bath was found to be 6.23 ± 0.75 and 9.57 ± 0.017 respectively. While printing in a support bath can produce filaments with both parallel and perpendicular fiber alignment, the inherent limitations and challenges of embedded 3D printing must also be considered when selecting printing parameters.= For example, moving the printhead quickly ($V^* < 0.5$) can result in

parallel fiber alignment, but this speed may also introduce print defects such as filament breakup, "crowning" (*i.e.* upwards flow of the ink material due to a prolonged crevice in the support bath), and extensive porosity (50; 54; 55; 56). Therefore, the printing parameter regimes for each alignment orientation will be affected by the viscosity ratio between the ink material and the support bath, which will need to be tuned for each material system.

2.6. Collagen fiber alignment guides cell orientation

To evaluate if patterned collagen fibers could influence cellular orientation, we seeded human corneal mesenchymal stromal cells (CMSCs) on collagen scaffolds with parallel, perpendicular, and random fiber alignments. The native cornea has multidirectional collagen fiber alignment, which is responsible for imparting its structural and functional properties (57; 58; 5; 59), and CMSCs are one of the regenerative cell types found in these tissues (60; 61; 62). Specimens were printed with parallel or perpendicular collagen fiber alignment, following the printing guidelines identified earlier (parallel: $V^*= 0.22$, $d_{\text{nozzle}}= 1.55$; perpendicular: $V^*= 2.98$, $d_{\text{nozzle}}= 0.42$), and a cast gel, condition with random fiber alignment was included as a negative control. The collagen fibers in the three different conditions were imaged through confocal reflectance on day 0, prior to cell seeding (first column of figure 6(A) and figure S6), and the fiber orientation was determined for each sample. At days 1, 3, and 5 after CMSC seeding, the cell morphology was visualized with a live cell cytoplasmic marker (calcein-AM). Across all timepoints, cells remained highly viable (about 99%, figure S7) and maintained their proliferative phenotype, resulting in increased confluence by day 5. Cell alignment was quantified by calculating orientation histograms from these images on days 1 and 3. Already by day 1, quantified cell orientation matched with the underlying collagen fiber alignment across all three types of fiber patterns (figure 6(B-D)). This agreement in alignment orientation persisted at day 3, as quantitatively evaluated in figure 6(B-D). At day 5, increased cell-cell contact due to cell proliferation prevented automated identification of individual cell borders for orientation analysis; nonetheless, fiber-guided cell alignment was readily observed through qualitative inspection of the confocal fluorescence micrographs. Cell morphology was further analyzed by staining the cell nuclei (DAPI) and filamentous actin (phalloidin) along with the aldehyde dehydrogenase 3 family member A1 (ALDH-3A1), a phenotypic marker for viable CMSCs (figure 6(A)) (63). Across all three cases (perpendicular, parallel, and random fiber alignments), and all timepoints, cells were observed to elongate and align with the underlying substrate while maintaining their positive staining for ALDH-3A1. Thus, similar to reports by others, controlling the orientation of collagen fibers at the microscale allows control of the cell orientation (7; 22; 6), which we uniquely demonstrate here by inducing cells to align in both parallel and perpendicular orientations.

Figure 6. Collagen fiber alignment guides cell orientation. (A) Representative confocal reflectance images of collagen fibers (gray) and confocal fluorescence images of CMSCs grown on the collagen filaments for 5 days and stained for cell bodies (green, calcein-AM), cell nuclei (blue, DAPI), filamentous actin (orange, phalloidin), and ALDH-3A1 (magenta). Printed samples included both perpendicular (top row) and parallel (middle row) collagen fiber alignment, and controls included cast samples (bottom row) with random fiber alignment. (B-D) Orientation of the the collagen fibers and seeded cells on days 1 and 3 were quantified for the prints with perpendicular (B), parallel (C), and random (D) fiber alignments, normalized to the total count of fibers or cells, respectively.

2.7. Multidirectional collagen fiber alignment in a single print

In native tissues, collagen fibers and endogenous cells are aligned in multiple directions within a single tissue (5; 8; 10; 11; 12; 13). Inspired by this, we reasoned that we should be able to modulate the printing conditions (*i.e.* V^*) during the fabrication process to achieve multidirectional collagen fiber alignment and hence different regions of cellular orientation within a single construct. Specimens with three different designs were created to demonstrate multidirectional alignment through either different interfilament or intrafilament fiber orientation patterning (figure 7(A)). In one type of interfilament patterning, sequential filaments can have alternating parallel and perpendicular fiber alignment. This can be achieved either (i) by using the same E but printing through two differently sized nozzles ($d_{nozzle} \neq$ constant, Table S1) (left column, figure 7(A)) or (ii) by printing through the same nozzle ($d_{nozzle} =$ constant) and varying E for sequential filaments (middle column, figure 7(A), Table S1). In intrafilament patterning, alternating regions of parallel and perpendicular fiber alignment are present in the same filament. This can be achieved using a single nozzle by varying E during continuous

printing of a filament (right column, figure 7(A), Table S1).

CMSCs were seeded onto these three different multidirectional fiber alignment prints, and cell morphology was visualized through cytoplasmic calcein staining on day 3. Cellular orientation was digitally analyzed and color coded to identify cells with parallel (blue, -45° to 45°,) or perpendicular alignment (red, -90 to -45° and 45 to 90°) relative to the printing direction (figure 7(B)). Cells appeared to adhere equally well on construct regions with parallel or perpendicular fiber alignment, (figure7(C)). As expected, cells followed the alignment of the underlying collagen fibers, as visualized by automated color coding (figure 7(D)) and by quantitative analysis (figure 7(E)). Thus, this technique offers the flexibility to create multidirectional patterns of fiber alignment using either a multiple nozzle printer (by altering d_{nozzle} and keeping E constant) or a single nozzle printer (by altering E and keeping d_{nozzle} constant). This versatile approach will enable the fabrication of printed constructs with control over different regions of patterned cell orientation to mimic native tissue architecture.

Figure 7. Multidirectional fiber and cell alignment in a single print. (A) Schematic of designs used to achieve multidirectional collagen fiber alignment in a single print, where the blue and red colors refer to regions printed with V^* values shown to result in a parallel and perpendicular alignment, respectively. (B) Color code used for automated analysis of cell orientation, relative to the printing direction (0 °). (C) Representative confocal images of CMSCs cultured on top of the collagen prints, visualized through calcein-AM. (D) Representative images of cell morphology with automated coloring based on their orientation using the legend from panel B. (E) Histograms of cell orientation for the different regions of each design, normalized to the total cell count.

3. Conclusion

Control over fiber alignment in engineered scaffolds is essential to accurately emulate natural tissue. Here, we demonstrate an extrusion-based 3D printing approach to control collagen fiber orientation in multiple directions by tuning the printing parameters. Moreover, CMSCs cultured on the printed collagen scaffolds were found to orient in the direction of the patterned collagen fibers. Even though plunger-controlled printing

3D printing was employed in the present work, the same principles can be applied to other types of extrusion-based 3D printing, such as a pressure-controlled setup (64). Moreover, the findings of this work can be applied to other fibrous materials, such cellulose nanofibers, or composites of fibrous and amorphous collagen inks (65; 66; 67). In addition, the use of different materials will allow for the identification of a material parameter, which in this work is included in the constant β as only one ink is used. Particularly, the accurate identification of such a material parameter can be achieved with inks that have fiber with controlled dimensions and tunable viscoelastic properties (both shear and extensional). Further work may achieve an increase in both biological and architectural complexity, through incorporating the approach presented here together with other printing modalities and by extending it to include bioinks that a living cell component. Taken together this work presents a method to pattern collagen fibers with a pre-defined fiber orientation through tuning the printing parameters in an extrusion-based 3D printing setup. The fabricated have the ability to guide cell orientation when used as scaffolds for tissue engineering as showcased with CMSCs.

4. Materials and methods

4.1. Materials

The collagen ink used was the commercial bovine type I neutralized 35 mg mL^{-1} Lifeink 200 (Advanced Biomatrix). Carbopol ETD2020 powder (Lubrizol) was dissolved by rotating overnight at room temperature at 7 mg mL^{-1} in 100 mL of sterile, ultrapure deionized water (Millipore) with 0.8 mL of 10 M NaOH (Sigma) to balance the pH to 7. Subsequently, the solution was degassed overnight before use.

4.2. Rheometry

The mechanical properties of the collagen and Carbopol were evaluated through rheological characterization. Small-amplitude oscillatory shear and rotational measurements were performed on an ARG2 rheometer (TA Instruments) equipped with a Peltier plate and a solvent trap to prevent evaporation, using a parallel-plate geometry with a diameter of 8 mm. The absence of wall slip was confirmed through measurements at a different measuring gap having excellent agreement with each other. Collagen gelation was examined through time-sweep measurements at an angular frequency of 1 rad s^{-1} and a shear strain amplitude of 1% at a temperature between 4 °C and 37 °C. Frequency-sweep measurements were conducted after the storage modulus (G') had reached a plateau at a shear strain amplitude of 1%, in the linear viscoelastic regime, between an angular frequency of 0.1 and 100 rad s^{-1}. Step-shear measurements were conducted with an alternating shear strain amplitude of 0.1% and 300% using a parallel-plate geometry with a diameter of 8 mm and a measuring gap of 900 μm and at an angular frequency of 6 rad s^{-1}. For Carbopol each shear step lasted 30 s and the measurements took place at room temperature, while for the collagen ink the low-shear

step lasted 300 s and the high-shear step 40 s and the measurements were conducted at 4 °. Three replicates using a fresh sample were conducted for all measurements.

4.3. 3D Printing

3D printing was performed using a custom-built dual-extruder bioprinter modified from a MakerGear M2 Rev E plastic 3D printer, as previously described [8, 58, 59]. Briefly, the thermoplastic extruder of the printer was removed and replaced with a mount designed to hold two Replistruder 4 syringe pumps. Additionally, the control board was replaced with a Duet 2 WiFi board with RepRapFirmware. The syringe was wrapped with Gel Finger Ice Pack (stored at -20 °C) to retain the collagen at 4 °C, as suggested by the manufacturer, to keep the self-assembly kinetics constant during printing. The printing was performed with nozzles having a diameter of 1.55 mm (14G), 0.84 mm (18G), 0.42 mm (22G), and 0.16 mm (30G) and the plunger distance varied from $E = 0.003$ mm to $E = 0.04$ mm. The printing speed (F) was kept constant at 99920 mm min^{-1}, the step distance ($\Delta x = 0.5$ mm) and syringe diameter (D = 7.29 mm) for all samples. The entire printing took place in air at room temperature. Acellular prints were printed as a single 2 cm long filament while the diameter varied depending on the printing parameters ranging from (1 mm to 4.8 mm). The Gcode used were manually written in a text file. For prints that were subsequently seeded with cells, the printing process was carried out in a sterile tissue culture cabinet and each sample consisted of three sequentially printed filaments with a length of 2 cm to increase seeding area. For perpendicular alignment, the sample was printed using a d_{nozzle} of 0.42 mm (22G) with $E = 0.007$ mm and for parallel alignment using a d_{nozzle} of 1.55 mm (14G) with $E = 0.007$ mm.

4.4. Cell culture

Corneal mesenchymal stromal cells (CMSCs) were obtained from a human donor cornea (Lions Eye Institute for Transplant and Research) following established protocols (68). The donor, aged between 30 and 35 years, had no known history of herpes simplex virus, varicella zoster virus, human immunodeficiency virus, or hepatitis. The time from death to preservation was less than 7 days, and the cornea was stored in Optisol corneal storage medium. Cells were cultured in a growth medium containing 500 mL MEM-Alpha (Corning), 50 mL fetal bovine serum (Gibco), 5 mL GlutaMax (Gibco), 5 mL non-essential amino acids (Gibco), and 5 mL antibiotic-antimycotic (Gibco). The growth medium was refreshed every other day, and CMSCs were passaged once they reached 80% confluency. The cells were used in experiments between passages 6 and 10. The cells were seeded on the bottom side of the print as it is more flat than the top part of the print. To achieve this, the prints were flipped in PBS solution followed by pipetting out the PBS solution. Then, CMSCs were trypsinized, counted, pelleted, re-suspended in media, and seeded at an initial cell density of 10^4 cells cm^{-2}.

4.5. In-vitro Characterization

To assess the viability of the CMSCs, a Live/Dead assay was conducted by staining cells with calcein AM and ethidium homodimer-1 (Life Technologies), following the manufacturer's instructions. Imaging for live/dead analysis was performed using a STELLARIS 5 confocal microscope (Leica) with a 10X air objective. At least 5 images were taken in different areas of each print, and image analysis was performed using FIJI (ImageJ2, Version 2.3.0/1.53f). Cell viability was calculated as the number of live cells (calcein AM-positive) divided by the total number of cells.

For immunofluorescence imaging, gels with seeded CMSCs were fixed with 4 % paraformaldehyde (PFA) in PBS for 20 minutes at room temperature (RT) followed by three washes (10 minutes each). Samples were permeabilized for 45 minutes at RT with 0.25 % Triton X-100 (Sigma Aldrich) in PBS (PBST) and then blocked for 2 hours at RT using blocking solution containing PBS with 5 wt % bovine serum albumin (BSA, Roche), 5 % goat serum (Gibco), and 0.5 % Triton X-100. Antibody dilutions were prepared in PBS with 2.5 wt % BSA, 2.5 % goat serum, and 0.5 % Triton X-100. Each sample was first treated with the appropriate primary antibody overnight at 4 °C: for CMSCs, rabbit anti-ALDH-3A1 (Abcam, ab76976, 1:200 dilution). The following day, the samples were washed three times with PBST (20 minutes each). The appropriate dilution of secondary antibodies was prepared in antibody dilution solution: 4',6'-diamidino-2-phenylindole (DAPI, Molecular Probes, 1:900 dilution) and phalloidin-tetramethyl rhodamine B isothiocyanate peptide from Amanita phalloides (Phalloidin-TRITC, Sigma Aldrich, 1:1000 dilution), Alexa Fluor 488 Goat anti-Rabbit Secondary Antibody, 1:500 dilution) and then added to the samples incubated overnight at 4 °C. Finally, samples were washed with PBST three times and imaged with a STELLARIS 5 confocal microscope (Leica) using 40x oil and 10x air objectives. Tile scans were taken at 512 x 512 image format.

4.6. Microscopy and image analysis

Collagen fibers in the acellular prints were imaged with a STELLARIS 5 confocal microscope (Leica) using 40x oil objective. Tile scans were taken at 512 x 512 image format for the entire print. Confocal images were then analyzed to characterize collagen fiber alignment qualitatively and quantitatively. For qualitative analysis, CT-FIRE for Individual Fiber Extraction software was used to enable automated tracing of the collagen fibers by artificially coloring individual fibers to aid in visual assessment of the overall collagen fiber alignment in the sample (69). For quantitative analysis, confocal images were analyzed using theOrientation J plugin in FIJI (Image J) software. The fraction of fibers corresponding to each orientation was obtained as a function of orientation angle (in degrees, °). Using this, histograms of normalized frequency of fibers relative to the total number of fibers versus orientation angle were plotted with bins of 20°. Three independent printing trials were analyzed for each experimental condition

and plotted as mean $\pm$ standard deviation. Cellular alignment of the seeded CMSCs on the gels was analyzed with CellProfiler, an open-source software using confocal images of the cells visualized with calcein-AM (live) stain.

4.7. Statistical analysis

Statistical analyses were performed using GraphPad Prism (Version 10). Details of the sample sizes and statistical tests conducted for each figure are included within the figure captions. In all cases, statistical differences are denoted as follows: not significant (ns $p > 0.05$), $^*p < 0.05$ $^{**}p < 0.01$, $^{***}p < 0.001$, $^{****}p < 0.0001$).

Acknowledgments

The authors thank Betty Cai and Dr. David Kilian for the helpful discussions. The authors acknowledge funding support from the Stanford Graduate Fellowship in Science and Engineering (D.S.), the Swiss National Science Foundation including P500PN210723 (F.C.), the National Institutes of Health including R01-EY035697 (S.C.H., D.M.), F31-EY034785 (L.G.B), and K01-EB033870 (V.M.D.), and the ARCS Foundation Scholarship (L.G.B.).

References

[1] Wang X, Kim H J, Wong C, Vepari C, Matsumoto A and Kaplan D L 2006 *Materials Today* **9** 44–53 ISSN 13697021

[2] Suveges S, Chamseddine I, Rejniak K A, Eftimie R and Trucu D 2021 *Frontiers in Applied Mathematics and Statistics* **7** 680029 ISSN 22974687

[3] Crossley R M, Johnson S, Tsingos E, Bell Z, Berardi M, Botticelli M, Braat Q J, Metzcar J, Ruscone M, Yin Y and Shuttleworth R 2024 *Frontiers in Cell and Developmental Biology* **12** 1354132 ISSN 2296634X

[4] Kirkwood J E and Fuller G G 2009 *Langmuir* **25** 3200–3206 ISSN 07437463

[5] Quantock A J, Winkler M, Parfitt G J, Young R D, Brown D J, Boote C and Jester J V 2015 *Experimental Eye Research* **133** 81–99 ISSN 10960007

[6] Sapudom J, Karaman S, Quartey B C, Mohamed W K E, Mahtani N, Garcia-Sabaté A and Teo J 2023 *Advanced Science* **10** 2301353 ISSN 21983844

[7] Kim H, Jang J, Park J, Lee K P, Lee S, Lee D M, Kim K H, Kim H K and Cho D W 2019 *Biofabrication* **11**(3) ISSN 17585090

[8] Liu J, you Xu M, Wu J, Zhang H, Yang L, xing Lun D, cheng Hu Y and Liu B 2021 *Orthopaedic Surgery* **13** 701–707 ISSN 17577853

[9] Piotrowski-Daspit A S, Nerger B A, Wolf A E, Sundaresan S and Nelson C M 2017 *Biophysical Journal* **113** 702–713 ISSN 15420086 URL `http://dx.doi.org/10.1016/j.bpj.2017.06.046`

[10] Osidak E O, Kozhukhov V I, Osidak M S and Domogatsky S P 2020 *International Journal of Bioprinting* **6** 270 ISSN 24248002

[11] Wang Y, Wang Z and Dong Y 2023 *ACS Biomaterials Science and Engineering* **9** 1132–1150 ISSN 23739878

[12] Peters J R, Hoogenboom M, Abinzano F, Callens S J, Foolen J and Ito K 2024 *Scientific Reports* **14**(1) ISSN 20452322

[13] Dahl S L, Vaughn M E and Niklason L E 2007 *Annals of Biomedical Engineering* **35**(10) 1749–1755 ISSN 00906964

[14] Holmes D F, Gilpin C J, Baldock C, Ziese U, Koster A J and Kadler K E 2001 *Proceedings of the National Academy of Sciences* **98**(13) 7307–7312 URL `www.pnas.orgcgidoi10.1073pnas.111150598`

[15] Shadwick R E 1999 *The Journal of Experimental Biology* **202** 3305–3313

[16] Szulczewski J M, Inman D R, Proestaki M, Notbohm J, Burkel B M and Ponik S M 2021 *Acta Biomaterialia* **129** 96–109 ISSN 18787568

[17] Wu S, Peng H, Li X, Streubel P N, Liu Y and Duan B 2017 *Biofabrication* **9** 044106 ISSN 17585090

[18] Nerger B A, Brun P T and Nelson C M 2019 *Soft Matter* **15** 5728–5738 ISSN 17446848

[19] Kishan A P, Robbins A B, Mohiuddin S F, Jiang M, Moreno M R and Cosgriff-Hernandez E M 2017 *Acta Biomaterialia* **56** 118–128 ISSN 18787568

[20] Builles N, Janin-Manificat H, Malbouyres M, Justin V, Rovère M R, Pellegrini G, Torbet J, Hulmes D J, Burillon C, Damour O and Ruggiero F 2010 *Biomaterials* **31**(32) 8313–8322 ISSN 01429612

[21] Ahmed A, Mansouri M, Joshi I M, Byerley A M, Day S W, Gaborski T R and Abhyankar V V 2022 *Biofabrication* **14**(3) ISSN 17585090

[22] Riching K M, Cox B L, Salick M R, Pehlke C, Riching A S, Ponik S M, Bass B R, Crone W C, Jiang Y, Weaver A M, Eliceiri K W and Keely P J 2015 *Biophysical Journal* **107** 2546–2558 ISSN 15420086 URL http://dx.doi.org/10.1016/j.bpj.2014.10.035

[23] Joshi I M, Mansouri M, Ahmed A, Silva D D, Simon R A, Esmaili P, Desa D E, Elias T M, Brown E B and Abhyankar V V 2024 *Advanced Functional Materials* **34**(13) ISSN 16163028

[24] Nerger B A, Brun P T and Nelson C M 2020 *Science Advances* **6** eaaz7748 ISSN 23752548

[25] Skylar-Scott M A, Uzel S G, Nam L L, Ahrens J H, Truby R L, Damaraju S and Lewis J A 2019 *Science Advances* **5** eaaw2459 ISSN 23752548

[26] Brassard J A, Nikolaev M, Hübscher T, Hofer M and Lutolf M P 2021 *Nature Materials* **20** 22–29 ISSN 14764660 URL http://dx.doi.org/10.1038/s41563-020-00803-5

[27] Imamura T, Shimamura M, Ogawa T, Minagawa T, Nagai T, Silwal Gautam S and Ishizuka O 2018 *Tissue Engineering - Part A* **24** 1574–1587 ISSN 1937335X

[28] Lee A, Hudson A R, Shiwarski D J, Tashman J W, Hinton T J, Yerneni S, Bliley J M, Campbell P G and Feinberg A W 2019 *Science* **365** 482–487 ISSN 10959203

[29] Shiwarski D J, Hudson A R, Tashman J W, Bakirci E, Moss S, Coffin B D and Feinberg A W 2025 *Science Advances* **11** eadu5905

[30] Ricci G, Gibelli F and Sirignano A 2023 *Bioengineering* **10** 1052 ISSN 23065354

[31] Huang M S, Christakopoulos F, Roth J G and Heilshorn S C 2025 *Nature Reviews Bioengineering* **3** 126–142 ISSN 27316092 URL http://dx.doi.org/10.1038/s44222-024-00268-0

[32] Murphy S V and Atala A 2014 *Nature Biotechnology* **32** 773–785 ISSN 15461696

[33] Peterlin A 1987 *Colloid & Polymer Science* **265** 357–382 ISSN 0303402X

[34] Nakayama K and Kanetsuna H 1975 *Journal of Materials Science* **10** 1105–1118 ISSN 15482634

[35] Ghodbane S A, Murthy N S, Dunn M G and Kohn J 2019 *Biofabrication* **11** 045004 ISSN 17585090

[36] Qian X, Zhou X, Mu B and Li Z 2003 *Cement and Concrete Research* **33** 1575–1581 ISSN 00088846

[37] Hoogenkamp H R, Bakker G J, Wolf L, Suurs P, Dunnewind B, Barbut S, Friedl P, Van Kuppevelt T H and Daamen W F 2015 *Acta Biomaterialia* **12** 113–121 ISSN 18787568 URL http://dx.doi.org/10.1016/j.actbio.2014.10.012

[38] Heitkamp T, Kuschmitz S, Girnth S, Marx J D, Klawitter G, Waldt N and Vietor T 2023 *Progress in Additive Manufacturing* **8** 541–559 ISSN 23639520 URL https://doi.org/10.1007/s40964-022-00347-x

[39] Christakopoulos F, Busato S P, Troisi E M, Kong X, Friederichs N and Tervoort T A 2024 *Polymer Engineering & Science* **64** 3606–3616

[40] Lewicki J P, Rodriguez J N, Zhu C, Worsley M A, Wu A S, Kanarska Y, Horn J D, Duoss E B, Ortega J M, Elmer W, Hensleigh R, Fellini R A and King M J 2017 *Scientific Reports* **7** 43401 ISSN 20452322

[41] Li Z, Ruan C and Niu X 2023 *Medicine in Novel Technology and Devices* **17** 100211 ISSN 25900935 URL https://doi.org/10.1016/j.medntd.2023.100211

[42] Moss S P, Shiwarski D J and Feinberg A W 2025 *ACS Biomaterials Science and Engineering* **11** 556–563 ISSN 23739878

[43] Jiang F, Hörber H, Howard J and Müller D J 2004 *Journal of Structural Biology* **148** 268–278 ISSN 10478477

[44] Banos C C, Thomas A H and Kuo C K 2008 *Birth Defects Research Part C - Embryo Today: Reviews* **84** 228–244 ISSN 1542975X

[45] Fang M, Goldstein E L, Matich E K, Orr B G and Banaszak Holl M M 2013 *Langmuir* **29** 2330–2338 ISSN 07437463

[46] Khare E, Yu C H, Gonzalez Obeso C, Milazzo M, Kaplan D L and Buehler M J 2022 *Proceedings of the National Academy of Sciences of the United States of America* **119** 2209524119 ISSN 10916490

[47] Yan J, Demirci E, Ganesan A and Gleadall A 2022 *Additive Manufacturing* **49** 102496 ISSN 22148604 URL https://doi.org/10.1016/j.addma.2021.102496

[48] Macosko C W 1994 *Rheology: Principles, Measurements and Applications* (Wiley-VCH) ISBN 1560815795

[49] Pibulchinda P, Barocio E, Favaloro A J and Pipes R B 2023 *Composites Part B: Engineering* **261** 110793 ISSN 13598368 URL https://doi.org/10.1016/j.compositesb.2023.110793

[50] Brunel L G, Hull S M and Heilshorn S C 2022 *Biofabrication* **14** ISSN 17585090

[51] Becker M, Gurian M, Schot M and Leijten J 2023 *Advanced Science* **10** 2204609 ISSN 21983844

[52] Sakai S and Morita T 2022 *ACS Biomaterials Science & Engineering* **8** 2589–2597 pMID: 35608818

[53] Bhattacharjee T, Zehnder S M, Rowe K G, Jain S, Nixon R M, Sawyer W G and Angelini T E 2015 *Science Advances* **1** e1500655 ISSN 23752548

[54] Brunel L G, Christakopoulos F, Kilian D, Cai B, Hull S M and Heilshorn S C 2024 *Advanced Healthcare Materials* **13** 2303325

[55] Friedrich L M, Gunther R T and Seppala J E 2022 *ACS Applied Materials and Interfaces* **14** 32561–32578 ISSN 19448252

[56] Leblanc K J, Niemi S R, Bennett A I, Harris K L, Schulze K D, Sawyer W G, Taylor C and Angelini T E 2016 *ACS Biomaterials Science and Engineering* **2** 1796–1799 ISSN 23739878

[57] Birk D E and Brückner P 2011 *Collagens, Suprastructures, and Collagen Fibril Assembly* (Berlin, Heidelberg: Springer Berlin Heidelberg) pp 77–115 ISBN 978-3-642-16555-9 URL https://doi.org/10.1007/978-3-642-16555-9_3

[58] Salvatore L, Gallo N, Natali M L, Terzi A, Sannino A and Madaghiele M 2021 *Frontiers in Bioengineering and Biotechnology* **9** 644595 ISSN 22964185

[59] Parfitt G J, Pinali C, Young R D, Quantock A J and Knupp C 2010 *Journal of Structural Biology* **170** 392–397 ISSN 10478477 URL http://dx.doi.org/10.1016/j.jsb.2010.01.019

[60] Basu S, Hertsenberg A J, Funderburgh M L, Burrow M K, Mann M M, Du Y, Lathrop K L, Syed-Picard F N, Adams S M, Birk D E and Funderburgh J L 2014 *Science Translational Medicine* **6** 266ra172 ISSN 19466242

[61] Eslani M, Putra I, Shen X, Hamouie J, Tadepalli A, Anwar K N, Kink J A, Ghassemi S, Agnihotri G, Reshetylo S, Mashaghi A, Dana R, Hematti P and Djalilian A R 2018 *Stem Cells* **36** 775–784 ISSN 15494918

[62] Brunel L G, Cai B, Hull S M, Han U, Wungcharoen T, Fernandes-Cunha G M, Seo Y A, Johansson P K, Heilshorn S C and Myung D 2025 *Bioactive Materials* **48** 414–430 ISSN 2452199X URL https://doi.org/10.1016/j.bioactmat.2025.02.009

[63] Pei Y, Reins R Y and McDermott A M 2006 *Experimental Eye Research* **83** 1063–1073 ISSN 00144835

[64] Zhang Y S, Haghiashtiani G, Hübscher T, Kelly D J, Lee J M, Lutolf M, McAlpine M C, Yeong W Y, Zenobi-Wong M and Malda J 2021 *Nature Reviews Methods Primers* **1** 75 ISSN 26628449

[65] Moohan J, Stewart S A, Espinosa E, Rosal A, Rodríguez A, Larrañeta E, Donnelly R F and Domínguez-Robles J 2020 *Applied Sciences (Switzerland)* **10** 65 ISSN 20763417

[66] Mamidi N, García R G, Martínez J D H, Briones C M, Martínez Ramos A M, Tamez M F L, Del Valle B G and Segura F J M 2022 *ACS Biomaterials Science & Engineering* **8** 3690–3716 pMID: 36037103

[67] Brunel L G, Long C M, Christakopoulos F, Cai B, Johansson P K, Singhal D, Enejder A, Myung D and Heilshorn S C 2025 *Acta Biomaterialia* **193** 128–142 ISSN 18787568 URL https://doi.org/10.1016/j.actbio.2025.01.009

[68] Jabbehdari S, Yazdanpanah G, Kanu L N, Anwar K N, Shen X, Rabiee B, Putra I, Eslani M, Rosenblatt M I, Hematti P and Djalilian A R 2020 *Translational Vision Science and Technology* **9** 26 ISSN 21642591

[69] Bredfeldt J S, Liu Y, Pehlke C A, Conklin M W, Szulczewski J M, Inman D R, Keely P J, Nowak R D, Mackie T R and Eliceiri K W 2014 *Journal of Biomedical Optics* **19** 016007 ISSN 1083-3668