1 **Multiscale Mechanics of Granular Biofilms**

2 Lisa K. Månsson[1*], Anna E. Warsaw[2*], Elizabeth G. Wilbanks[2,3], Angela A. Pitenis[1]
3 * These authors contributed equally to this work and are designated as co-first authors.
4
5 [1] Materials Department
6 [2] Department of Ecology, Evolution, and Marine Biology
7 [3] Marine Science Institute
8 University of California, Santa Barbara, Santa Barbara, CA 93106
9

Abstract

Biofilms produce and maintain extracellular polymeric substances (EPS) essential for their form
and function. While biofilms are commonly lamellar and frequently targets of removal, granular
biofilms are increasingly incorporated into water treatment strategies. In both cases, the EPS
(mainly consisting of proteins, polysaccharides, and extracellular DNA) is largely responsible for
their persistence. Unlike many granular biofilms, which are formed in engineered industrial
bioreactors, the "pink berry" consortia is a naturally-occurring and robust granular biofilm of
photosynthetic bacteria, found only in intertidal pools of salt marshes around Woods Hole,
Massachusetts (USA). The pink berry biofilm's unique ecological niche has sparked over three
decades of study, yet their mechanical properties are completely unknown. Here, we
characterized the structural and mechanical landscape of pink berry granules to determine the
extent to which microscale heterogeneity influences macroscale material properties. We
performed microindentation measurements on intact granules and nanoindentation measurements
on thin sections. We report that intact pink berry granules exhibited low reduced elastic moduli
($E^*_{\text{pink berry}} \approx 0.5$–$10$ kPa) and fast stress relaxation times ($\tau_{1/2} \approx$ seconds), consistent with
previous investigations of soft and viscoelastic biofilms. Nanomechanical measurements of thin
pink berry sections revealed two mechanically-distinct domains: a very soft extracellular
polymeric substance (EPS) matrix surrounding stiffer microcolonies of purple sulfur bacteria
(PSB). Light sheet fluorescence microscopy revealed the spatial organization and distribution of
cell-dense PSB microcolonies (34 vol.%) within EPS matrix (66 vol.%), suggesting the
nanomechanical behavior of EPS dominates macroscale pink berry mechanics. Our multiscale
experimental approach combining mechanics and imaging may be broadly applicable to
investigations of complex soft materials, from synthetic hydrogel composites to biologically
heterogeneous spheroids, organoids, and tissues.
34

35 **Keywords**

39 **Corresponding Authors**

40 Prof. Elizabeth G. Wilbanks
41 ewilbanks@ucsb.edu
42
43 Prof. Angela A. Pitenis
44 apitenis@ucsb.edu

1. Introduction

Multicellularity critically depends on the ability to stick together under diverse stressors. Many multicellular systems, from bacterial aggregates to organs, generate an extracellular matrix as a protective binder and conduit for nutrient transport. Light and electron microscopy reveal that the extracellular matrix supports intricate structural complexity, spanning the macro- to nano-scales [1–3]. Nanomechanical measurements of single cells (e.g., atomic force microscopy) provide mechanobiological insights at the cellular and subcellular scales [4–12], yet large multicellular assemblies often exhibit very different force responses to mechanical compression due to spatial heterogeneity [13]. Such mechanical differences from the cellular scale to macroscale capture key emergent properties of multicellular systems – phenotypes that are foundational in the evolution of group-level traits from cellular-level activities [14].

Among the most ancient multicellular assemblies are communities of microorganisms held together by a self-produced extracellular matrix, also known as biofilms [15]. Mechanical measurements of biofilms have typically focused on lamellar biofilms relevant to both biomedical and industrial environments [10–12, 16–27]. However, millimeter-sized roughly spherical "granular" biofilms are observed in both natural and engineered environments and play a critical role in industrial wastewater treatment technologies [28–31]. Dense granules settle quickly, which serves to retain catalytically-valuable biomass within wastewater treatment reactors, and rapid respiration rates depletes oxygen at the granule core, leading to biofilms that can simultaneously catalyze both aerobic and anaerobic processes [28–31]. One of the few well-studied, naturally occurring granular biofilms are the colorfully described "pink berry" microbial consortia [32]. Pink berries are pink-hued granules, millimeters in diameter, found in intertidal salt marsh ponds (**Fig. 1**). Pink berries have enjoyed a long history of observation, leading to a genome-resolved understanding of the microbial community within the consortia [32–36]. Our prior work has established that these granules host a conserved consortia of bacteria (and diatoms), and are primarily composed of a single species of uncultivated phototrophic purple sulfur bacteria (*Thiohalocapsa* PSB1), which forms dense microcolonies within a translucent, supportive matrix of extracellular polymeric substances (EPS). Despite their importance to pink berries' remarkable robustness and persistence in nature [32] and potential for industrial applications, their mechanical properties are completely unknown.

In this study, we present multiscale structure-property relationships of pink berry granular

biofilms. We conducted in situ micromechanical measurements on intact granules as well as in

situ nanomechanical measurements on thin sections to distinguish the respective contributions of

bacterial microcolonies and the EPS matrix to the mechanics of the granular composite. We then

leveraged advanced imaging approaches to correlate granule structure and spatial organization

with quantitative measurements of their mechanical properties.

Figure 1: a) Pink berries settle quickly (left) and maintain integrity during agitation (right). b)
Close-up view of a pink berry granular biofilm, reproduced from reference [35]. c) Fluorescence
micrograph of a thin pink berry slice, with nucleic acid in blue (SYTO 41 Blue Fluorescent
Nucleic Acid Stain) and cyanobacteria and purple sulfur bacteria (PSB) microcolony
autofluorescence in red. d) Higher magnification view of PSB microcolonies (encircled in
dashed line) within a pink berry slice, with nucleic acid in blue (DAPI) and PSB microcolony
autofluorescence in red.

16
2. Materials and Methods

2.1. Sample Collection

Pink berry granular biofilms were sampled in September 2024 from an intertidal pond in the

Little Sippewissett Salt Marsh in Falmouth, MA (N 41.57587, W -70.63923). Pink berries were

collected with a sieve (1 mm mesh size) from the sediment-water interface, stored in water

sampled from the site, and shipped to UC Santa Barbara. The pink berries were maintained as a

concentrated collection in an aquarium with ≈3 cm sediment sampled from the site and ≈6 L

unfiltered seawater.

25
2.2. Microindentation of Pink Berries

Pink berries were collected from the aquarium (never frozen) and washed three times in 0.2 µm

filter-sterilized seawater. The granular biofilms were fully submerged in phosphate-buffered

saline (PBS 3×) and positioned in a rigid transparent dish for unconfined compression using a

custom-built microtribometer [37–43]. Pink berry deformation and recovery were recorded using

an inverted digital microscope (Dino-Lite Edge AF4115ZT, 20–220× magnification) mounted

beneath the dish. Pink berries were compressed at a constant approach and retraction velocity (v

= 1, 10, or 100 µm/s) to a maximum applied normal force between F_N = 500 µN and 1 mN

(contact pressures, P = 80 Pa to 330 Pa) using a hemispherical glass probe (radius of curvature,

R_1 = 2.6 mm) attached to a double-leaf cantilever (normal spring stiffness, K_N = 220 µN/µm).

Each pink berry sample was indented at least three consecutive times (n = 3) with a minute

between each indent to obtain the average elastic modulus.

For calculation of reduced elastic modulus, E^*, the data were fit to the Hertzian contact

mechanics model [44] using Eq. 1.

$$F_N = \frac{4}{3} E^* R^{\frac{1}{2}} d^{\frac{3}{2}} \#(1)$$

16 　　　In this equation, F_N is the applied normal force, d is the microindentation depth, and R is

17 the effective radius determined from the probe radius of curvature, R_1, and the radius of the pink

18 berry sample, approximated as a sphere, R_2 (Eq. 2). The average pink berry diameter for each

19 sample was determined from five measurements across each sample (**Supplementary Fig. A1**).

$$\frac{1}{R} = \frac{1}{R_1} + \frac{1}{R_2} \#(2)$$

To comply with Hertzian contact mechanics model assumptions, all indentation

measurements were analyzed within the small-strain regime (i.e., maximum contact radius

$a < 0.15 R_2$) (**Supplementary Fig. A2**).

2.3. Stress Relaxation Measurements

Pink berry samples were washed and positioned on a rigid dish for unconfined compression

while fully submerged in PBS (3×) as described in Section 2.2. Using a cylindrical glass rod

(radius, R_{cyl} = 0.75 mm), pink berry samples (N = 6) were compressed to an approximate strain

of 5% at an approach velocity of v_{app} = 2 mm/s (strain rate ≈ 20 s^{-1}), held for 20 s, then retracted

at v_{ret} = 0.05 mm/s (motion profile in **Fig. 3b**). The data was smoothed using a Savitzky-Golay

filter in MATLAB, the stress was normalized to the maximum stress, and the characteristic stress

relaxation time constant, $\tau_{1/2}$, was determined at the time the stress had decreased to half of its

maximum value. The average pink berry diameter for each sample was measured from images

taken from below by the inverted digital microscope (**Supplementary Fig. A3**). For each

sample, five diameters across were measured to obtain an average.

Stress relaxation data were fit to common viscoelastic models based on Maxwell

elements where viscous contributions are represented by dashpots and elastic contributions by

springs. The equations used are presented in Supplementary Information, with data fits in

Supplementary Fig. C1.

2.3. Nanoindentation of Pink Berry Slices

To investigate the mechanical properties of distinct biofilm components, pink berries were

prepared for sectioning. A cylindrical disk of agarose was prepared by pouring 4% (w/v) agarose

gel in PBS (3×) into a rigid mold (≈20 mm diameter, ≈10 mm thickness). Prior to gelation of

agarose at room temperature, a single pink berry was embedded live (unfixed) in the center of

the mold. Thereafter, the cylindrical disk was sectioned on a Leica VT1000 S vibratome to

obtain roughly 100 µm thick slices through the entire disk. Pink berry slices were stored in PBS

(3×) in glass-bottom culture dishes at 4°C for up to one week prior to testing. During this time,

negligible sample degradation was observed. To prepare slices for nanoindentation, a glass-

bottom culture dish was coated with 400 µL of Weaver's Gelatin (50 mL DI H_2O, 0.5 g

chromium potassium sulfate dodecahydrate, 0.05 g gelatin type B) and incubated for 10 min at

room temperature. The solution was aspirated, and the glass surface dried for 15 min at room

temperature. Pink berry slices were gently patted with cellulose paper to remove excess liquid,

positioned on the coated glass surface, and equilibrated for 20 min at room temperature. The

culture dish was then filled with PBS (3×) for nanoindentation measurements. The full procedure

is illustrated in **Supplementary Fig. B1**.

Nanoindentation measurements were performed with the Optics11 Life Pavone housed in

the BioPACIFIC MIP user facilities at UC Santa Barbara. Pink berry slices were indented at

room temperature using a spherical glass probe (probe radius of curvature, $R = 26.5$ µm, normal

spring constant, $K_N = 0.021$ N/m) while fully submerged in PBS (3×) at a constant indentation

velocity of $v = 10$ µm/s to an indentation depth of about 5 µm. Multiple positions across each

slice (separated by at least two probe diameters) were selected using the inverted 20× objective

installed in the instrument. Each position across the pink berry slice was indented at least three

consecutive times in the same location to obtain an average elastic modulus. All measurements

were conducted at least two probe diameters from the perimeter of the pink berry, which is near

the interface between the biofilm and the agarose gel matrix. The mechanical properties of the

agarose support were characterized following the procedures above using a probe with

appropriate cantilever spring constant for the material (probe radius of curvature, $R = 48$ µm,

normal force spring constant, $K_N = 3.52$ N/m) (agarose elastic modulus was about 500 kPa, see

Supplementary Fig. B2, in agreement with previous literature [45]). Following nanoindentation

measurements, the full pink berry slices were imaged to correlate micro- to -macro-scale

structure. Slices were imaged using an inverted Leica SP8 confocal microscope. A 10× (0.3 NA)

air objective lens was combined with tile scanning to image entire pink berry slices. Brightfield

images were acquired using 3×3 tiles with 10% overlap.

The reduced elastic modulus (E^*) was calculated for nanoindentation measurements as

described above, with R in Eq. 1 here being the radius of the spherical probe. Statistical analyses

were performed in Python using the *scipy* package, specifically the function *mannwhitneyu* for

performing a Mann-Whitney u-test, as the nanoindentation data from purple sulfur bacteria

(PSB) microcolonies were not normally distributed.

2.5. Fluorescence Light Sheet Microscopy and Analysis

To examine the internal architecture of the pink berry granular biofilms, a pink berry collected

from an intertidal pond in the Great Sippewissett Salt Marsh, Falmouth, MA (N 41.58618, W -

70.64228) was fixed, optically cleared, and imaged on a light sheet microscope. Briefly, the pink

berry was twice washed in 0.2 µm-filtered seawater, fixed in 4% PFA in PBS (1×) for 1 h

agitated at 125 rpm at room temperature, washed three times in PBS (1×), and stored in PBS (1×)

at 4 °C for about one week. The pink berry was incubated in 100% methanol for about 2 h, twice

washed in PBS (1×), and incubated in 500 µL clearing reagent iCBiofilm-H2 (TCI AMERICA)

diluted 4:1 with sterile, de-ionized water for about 7 h. For imaging, the pink berry was

embedded in 1% (w/v) agarose gel in the 4:1 iCBiofilm-H2:water solution. The agarose gelled

within the barrel of a 1 mL plastic disposable syringe modified with a wider inlet to reduce

compressive strains on the pink berry during aspiration. The syringe was stored at 4 °C in the 4:1

iCBiofilm-H2:water solution until imaging.

Light sheet imaging was performed using the Zeiss Lightsheet Z.1 microscope housed in

the NRI-MCDB shared facility using the 20× CLARITY objective lens (refractive index = 1.46)

combined with tile scanning. The sample chamber was filled with iCBiofilm-H2 solution, and

the pink berry embedded in agarose was partially extruded from the syringe and immersed in the

solution. We acquired a Z-stack through 844 µm of the pink berry (670 slices, Z-step = 1.26

µm), spanning roughly half of the granule, and 3×4 tiles were imaged with 10% overlap. A 488

nm laser at 10% intensity was used to excite pink berry autofluorescence, and emission was

collected at 505–545 nm.. The tiles were stitched together in Fiji (ImageJ) using the stitching

plugin Grid/Collection Stitching [46]. Image analysis was conducted using Imaris 10.2.0. Three

surface categories were created from the Z-stack, capturing the intact pink berry surface, bright

abiotic crystals, and PSB microcolonies. These surfaces were created using the machine learning

segmentation tool in Imaris, which trains an AI segmentation model. One of the surface

categories captured bright crystals that appeared in the Z-stack as an artifact of the clearing

protocol and was used to remove these from the images. The microcolony category primarily

captured PSB microcolonies but also included a small number of potential cyanobacterial and

Rhodobacteraceae microcolonies. The volumes computed from the pink berry and microcolony

surfaces were used to calculate the microcolony volume fraction.

3. Results

3.1. Pink Berry Granular Biofilms are Soft and Exhibit Low Elastic Modulus

Microindentation measurements of whole pink berries (i.e., granules) were performed with a

custom-built microindentation platform using the experimental configuration shown in **Fig. 2a**.

A representative force-displacement approach curve for a constant indentation velocity of

$v = 10$ µm/s is shown in **Fig. 2b**. Granules exhibited a range of reduced elastic moduli, from

$0.5 < E^*_{\text{pink berry}} < 11.2$ kPa, with an average of $E^*_{\text{pink berry}} = 4.0 \pm 3.4$ kPa (N = 7). Although there

was no clear correlation with pink berry diameter (**Fig. 2c**), the wide range of elastic modulus

values obtained in this study is consistent with previously observed heterogeneity of biofilms,

even in pure culture of single-species systems [47]. The reduced moduli of granules are within

comparable order of magnitude to lamellar biofilms (see additional discussion in section 4.1)

[17]. Serial force-displacement curves on the same location of the same granule did not reveal

significant adhesion, plastic deformation, or strain-stiffening (**Supplementary Fig. A4)**. The

reduced elastic modulus of pink berry granules was largely insensitive to indentation velocity (*v*

= 1, 10, and 100 µm/s) (**Supplementary Fig. A5**).

Figure 2: Microindentation measurements of whole pink berries. a) Experimental configuration
for microindentation measurements. b) Representative force-displacement curve for a single pink
berry sample with approach and retraction paths indicated. The Hertzian contact mechanics
model (dashed line) was used to fit the approach curve to determine the elastic modulus. c) Pink
berry granules reduced elastic modulus average values are shown with y-error bars indicating
standard deviation from n = 3 indentations per sample, and x-error bars representing the standard
deviation from the average sample diameter (n = 5).

3.2. Pink Berry Granular Biofilms Show Fast Response to Compression during Stress Relaxation

The custom-built microindenter with a modified experimental configuration (flat punch glass

probe) was used to conduct stress relaxation measurements on individual pink berry granules

(**Fig. 3a,b**). Pink berry samples were compressed to an average strain of 5% (N = 6). Normalized

stress relaxation data was used to determine the characteristic relaxation time, $\tau_{1/2}$, the time

required for the applied stress to reach half its initial value (**Fig. 3c**). Stress relaxation time was

on the order of 0.1 to 10 s, with an average stress relaxation time $\tau_{1/2} = 3.7 \pm 4.1$ s (N = 6) (**Fig.**

3c). Stress relaxation time for the small sample size evaluated here does not appear to be

correlated with sample diameter (**Fig. 3d**). Stress relaxation studies performed by compression

testing of dental biofilm (plaque) report similar time scales, $\tau_{1/2} = 11 \pm 12$ s (n = 10), and similar

variability, attributed to heterogeneity associated with biofilms [47]. Collagen biopolymers and

heart tissues under modestly higher strains (10–15%) exhibit similar relaxation times extracted

from indentation measurements [48, 49]. Notably, decellularized heart tissue was found to relax

stress slower than the heart tissue containing cells [49]. This finding suggests an intriguing

possibility that the cell microcolony component in the pink berry may make important

contributions to the granule's fast response to compression. Further studies could include stress

relaxation measurements of decellularized samples to examine this hypothesis.

Figure 3: Pink berry granular biofilms exhibit fast relaxation during compression. a)
Experimental configuration of stress relaxation measurements. b) Microindenter motion profile.
c) Resulting stress relaxation curve from microindentation using the motion profile in b), where
the stress was normalized to the maximum stress indented. Each pink berry was evaluated only
once (N = 6, n = 1). d) Stress relaxation time scale shows no dependence on pink berry sample
size. Error bars in x show standard deviations for each sample's average diameter.

3.4. Nanoindentations Reveal Microscopic Mechanical Heterogeneity in Pink Berries

Pink berry biofilms are composed of tightly packed clusters of coccoid purple sulfur bacterial

cells (PSB microcolonies) supported within an EPS matrix (**Fig. 1**). To separately measure these

distinct structures and examine their contributions to the mechanical properties of the whole

granule, we sectioned pink berry samples (about 100 µm thin) for nanoindentation measurements

on either microcolonies or EPS domains (**Fig. 4a**). Nanoindentation measurements were

conducted using the Optics11 Life Pavone nanoindenter with an integrated inverted 20×

objective and a borosilicate glass probe ($R = 26.5$ µm radius). Imaging through thin sections of

pink berry granules enabled unobstructed observations of purple sulfur bacteria (PSB)

microcolonies surrounded by EPS (**Fig. 4b**), with the location of each nanoindentation

measurement represented by circles (red for microcolonies and blue for EPS). The apparent

contact diameter, $2a$, is represented to scale in the inset (**Fig. 4b**), and indentations were

separated by a minimum distance of 100 µm from neighboring locations. Additionally, each

location was selected such that the projected contact area, as observed by inverted microscope,

was fully bounded by either the microcolony or EPS domains to reduce crosstalk.

Nanoindentation measurements were conducted over two slices from a single pink berry

granule (N = 2). Image maps of pink berry slices with indentation locations marked along with

corresponding reduced elastic modulus values are presented in **Supplementary Fig. B3**.

Nanoindentation measurements revealed significant differences in reduced elastic modulus

between PSB microcolonies ($E^*_{PSB} = 2.1 \pm 1.2$ kPa, n = 14 locations, each location with 3

technical repeats) and the EPS ($E^*_{EPS} = 0.6 \pm 0.1$ kPa, n = 10 locations, each location with 3

technical repeats) (**Fig. 4c,d**). The average reduced elastic modulus between the PSB

microcolonies and EPS matrix domains were determined to be statistically significant based on

the Mann Whitney test (p-value = 0.000002). The reduced elastic modulus determined from

nanoindentation measurements against PSB microcolonies ranged from $E^*_{PSB} = 0.8$ to 5.3 kPa,

and from $E^*_{EPS} = 0.4$ to 0.8 kPa for the EPS matrix. The reported elastic modulus of the EPS

matrix within pink berry granules is on the same order of magnitude as those determined from

the EPS found in lamellar biofilms [50]. The broad spread of reported E^* values associated with

PSB microcolonies (**Fig. 4** and **Supplementary Fig. B3**) may be due to a number of factors,

including: biofilm heterogeneity, microcolony size and density, and depth into the pink berry

slice. Nanoindentation locations were selected using optical microscopy; opaque PSB domains

may have occluded EPS matrix above the microcolony and directly beneath the probe, which

may have led to unintended crosstalk.

Figure 4: Nanoindentations of sliced pink berries reveal heterogeneity in mechanical properties at the micrometer scale. a) Schematic side view of experimental configuration. b) Brightfield image of the pink berry section, showing purple sulfur bacteria (PSB) (dark) and extracellular polymeric substances (EPS) (light) and probe contact radius, *a*, determined at maximum indentation depth. c) Representative force-displacement curves from nanoindentation measurements in positions shown in b). Hertzian contact mechanics model (dashed lines) used to fit approach curves. d) PSB microcolonies exhibited significantly higher elastic moduli than EPS matrix.

3.5. Volume Fraction of Microcolonies Distributed Throughout the EPS Matrix

To examine the internal structure of pink berry biofilms in 3D, we used fluorescence light sheet

microscopy commonly used in neurobiology and developmental biology to image organs and

embryos [51]. This technique images millimeter-sized samples with fast data acquisition, using

tissue clearing and purely optical sectioning [52] and allows us to capture the internal

architecture of an intact, millimeter-scale pink berry biofilm with single cell resolution (**Fig 5a**).

Imaging revealed heterogenous, irregularly-shaped microcolonies distributed throughout the

granule (**Fig. 5a**). The EPS matrix between microcolonies featured occasional diatoms. A

cropped region of the granule shows the microcolonies in greater detail (**Fig. 5b**), which can be

described as roughly tube shaped, about 30 µm in diameter on average, often curved and

sometimes connected into a toroidal-like shape (**Fig. 5b,c**). Representative Z-slices through the

3D image show the spatial organization of PSB microcolonies as well as occasional bright

masses of diatoms or cyanobacteria (e.g., in the upper center part of the second to last slice

shown in **Fig. 5d**).

Figure 5: Light sheet microscopy reveals heterogeneous microcolonies distributed throughout the pink berry granular biofilm. a) Full 3D rendering of a Z-stack through half a pink berry granule. b) Cropped region of 3D rendering ($500 \times 500 \times 100$ µm) showing the structure of PSB microcolonies in green (autofluorescence). c) Orthogonal views of cropped region shown in b) in the XY, XZ, and YZ directions. d) Representative Z slices through Z-stack shown in a), from $Z = 0$ µm at the interior of the pink berry granule to $Z = 756$ µm near the surface. Each slice shown is 126 µm apart.

To further analyze pink berry composition, we used machine learning to obtain volumetric surface renderings capturing different components of the pink berry granular biofilm (**Fig. 6**). Using a surface reconstruction of the granule, we determined the volume to be 1.86 mm^3 (**Fig. 6a, 6b**). Surface reconstruction of each microcolony gave a summed microcolony volume of 0.629 mm^3 (**Fig. 6c, 6d**). In this granule, the volume fraction of microcolonies corresponded to $f_{PSB} \approx 34\%$ of the pink berry volume and the EPS matrix made up a volume fraction of $f_{EPS} \approx 66\%$.

Figure 6: Microcolonies correspond to roughly 34% of the entire pink berry volume. a) Representative slice showing autofluorescent microcolonies (green) and the outline in pink representing the granule surface reconstruction shown in b. b) Granule surface reconstruction from a Z-stack through half a pink berry granule. Imaris was used to obtain the surface via machine learning segmentation. c) Representative slice illustrating autofluorescent microcolonies (green) and circled in pink is the microcolony surface rendering shown in d. d) Microcolony surface reconstruction from the same Z-stack using Imaris machine learning segmentation. e) Enlarged view of c to showcase microcolonies. f) Enlarged view of d.

4. Discussion

4.1 Connecting Structure to Mechanical Properties Across Scales

In this study, we present methods that bridge multiscale mechanical properties and the structural landscape of composite biological samples. We performed mechanical measurements using indentation techniques across nN to µN force scales. Advanced imaging using light sheet fluorescence microscopy allowed us to visualize intact macroscopic specimens with micron-scale resolution, connecting our smaller scale, high-resolution imaging methods and larger-scale visualization of entire macroscopic specimens [53]. Light sheet fluorescence microscopy connected structural visualizations to the same length scales as our mechanical characterization. Previously, to resolve single-celled structures in this system, we relied on physical thin sectioning of an embedded sample, combined with confocal microscopy [33]; given the technical challenges of capturing and aligning serial thin sectioning, this approach was ill-suited to reconstructing finely sampled millimeter-sized structures. Here, we demonstrate a method that can reliably and rapidly (~2 days) generate single-cell resolution images of intact, millimeter-sized granules. While light sheet imaging has occasionally been used to visualize surface-attached biofilms [54–58], this approach is not widespread in microbiology [59]. Our study is the first of its kind to use this approach to reveal the detailed cellular architecture of millimeter scale granular biofilms, and only the second reported application of this technique on marine bacteria [60].

We report reduced elastic moduli of whole pink berry granules in the range of $E^{*}_{\text{pink berry}} \approx$ 0.5–10 kPa, values within the many orders of magnitude wide range of elastic moduli values reported for lamellar biofilms, reviewed by Böl *et al.* [17]. However, it shall be noted that the elastic modulus determined depends on several factors including, for example, instrumentation used, specific experimental setup, biofilm species, and environmental conditions. Focusing only on measurements performed using microcantilever indentation or compression (between which, for example, probe geometries, indentation velocities, and sample strains still varied), elastic moduli for different lamellar biofilms (single-species, and with different cell-cell architecture) ranged from 0.017 kPa [61] up to 2.2 kPa [62]. The range of elastic moduli determined for pink berries is similar, although notably on the stiffer side. It should be noted that the Hertz contact mechanics model used to analyze microindentation measurements assumes indentation of a

spherical sample (reflected in Eqs. 1 and 2) which can influence the reduced elastic modulus.

The equations used imply that for an underestimated sample radius (R_2 in Eq. 2), which may be

the case for more oval-shaped pink berry samples, the estimated reduced elastic modulus E^*

(from Eq.1), would be slightly overestimated.

This research effort attempted to connect the mechanical properties of whole, intact pink

berries to their primary microscale constituents: PSB microcolonies and the EPS matrix. One

pink berry among the samples characterized with microindentation was sectioned and further

investigated via nanoindentation measurements. The largest granule (pictured in **Supplementary**

Fig. A1, sample #5) was chosen for easier experimental handling. This sample was also the

softest among the pink berries examined, with an average reduced elastic modulus of $E^*_{\text{pink berry}} =$

0.5 ± 0.1 kPa (**Fig. 2c**). Bacterial microcolonies, estimated to comprise about 34 vol.% of the

granule, exhibited an average reduced elastic modulus of $E^*_{\text{PSB}} = 2.1 \pm 1.2$ kPa. The predominant

component, EPS (about 66 vol.% of the granule) was significantly softer, with an average

reduced elastic modulus of $E^*_{\text{EPS}} = 0.6 \pm 0.1$ kPa. Our results suggest that the EPS dominates the

overall mechanical response of the pink berry. Interestingly, similar EPS-dominant macroscopic

mechanical properties have been previously reported for distinctly different lamellar biofilms

[63]. The composition of EPS, which has been well characterized in several lamellar biofilms

and includes a suite of polysaccharides, extracellular proteins and extracellular DNA, largely

consists of water (around 95 to 98% water [64]) which consequently drives mechanical and

transport properties of biofilms [65]. We hypothesize that softer EPS enables greater

accommodation of deformation, thus protecting microcolonies from cell damage and preventing

intra-granular fracture, even under moderate compressive strains (about 50% strain, by manual

inspection).

EPS is an essential component of granular biofilms that enables granules to hold together

under flow in bioreactors [31]. The EPS in naturally occurring pink berry biofilms has been

modified by nature over time, and our results demonstrate that the EPS matrix is a key

component in these highly resilient structures. Pink berry EPS and the species that produce it

may be useful in optimizing granules for industrial bioreactors, or for the rational design of

engineered microbial consortia, an ongoing challenge in synthetic biology [66–68]. Ultimately,

this may be useful both in engineering robust and functional industrial systems, as well as

inspiring novel 3D-structured soft materials.

4.2 Pink Berry Permeability

Microcolonies of cells within the pink berry require nutrient supply through fluid flow. Pink

berry granules are estimated to contain about 70% water; the interconnected domains of EPS

may provide channels for fluid flow through the granule [17, 19].

Fluid permeability describes fluid flow through a material in response to an applied

pressure through the square of the limiting length scale to flow. One such limiting length scale

could be the mesh size of EPS matrix filaments, which could be estimated using the scaling in

Eq. 3,

$$E^* \sim \frac{k_B T}{\xi^3} \#(3)$$

where k_B is the Boltzmann constant, T is temperature, and ξ is the correlation length or the mesh

size of the network [69]. Using the calculated value for the EPS reduced elastic modulus (E^*_{EPS}),

the mesh size, ξ, is on the order of 10's of nanometers, resulting in an estimated permeability,

$k \sim \xi^2 \sim 10^{-16}$ m^2 (or 10^{-10} mm^2 or 0.0001 µm^2), on the same order of magnitude as estimated for

high water content aqueous gels [70], including alginate gels (about 95% water) [71].

4.3 Viscoelasticity in Biofilms

Viscoelasticity is common in many biological systems, including biofilms [20, 72]. Fast

viscoelastic responses protect cells within the biofilm from mechanical damage and facilitate the

biofilm's ability to stay intact under high pressures and instant forces [20, 27, 65]. Time scales of

viscoelastic responses have been evaluated in soft, high-water content biological structures, like

brain tissue, where viscoelastic contributions were found to dominate on time scales up to 100's

of seconds [73] (compared to slower diffusion-controlled structural relaxation, time scales ~

1,000's of seconds [73–76]).

Stress relaxation data of pink berry granules were fit to viscoelastic models based on

Maxwell elements, each consisting of two model components connected in series: a spring and a

dashpot, representing elastic and viscous responses, respectively [74–76]. Fitting models were

based on either one- or two-Maxwell elements. The two-Maxwell element model resulted in

improved fits to the data (R^2-values > 0.93 across all samples, N = 6) (Supplementary

Information C and **Supplementary Fig. C1**). This two-element model has previously described

the viscoelastic behavior of other multicomponent biological systems, including brain, breast

cancer tissue, and meniscus extracellular matrix [73, 74]. Overall, our results indicate

viscoelastic contributions to pink berry granule stress relaxation.

4.4 Limitations

In this study, in situ nanoindentation measurements enabled the selection of regions of interest.

However, our samples are opaque unless sectioned into very thin slices. Slices thinner than 100

µm presented significant experimental and handling challenges due to their fragility. Therefore,

nanoindentations were performed using 100 µm thick sections, despite the uncertainty in

knowing where in the Z plane PSB microcolonies were positioned. In contrast, EPS regions were

translucent and easily discernible with available optics. The uncertainty in spatial positioning of

the nanoindenter with respect to microcolony distribution in the Z plane (normal to the sample

holder) may explain the broad spread of E^* measurements associated with PSB microcolonies

and the relatively more consistent results for EPS matrix measurements (**Fig. 4** and

Supplementary Fig. B3). In situ measurements with live cell fluorescent reporters and confocal

microscopy may overcome these experimental challenges in the future.

It is important to note that the average reduced elastic modulus values for the EPS matrix

and microcolonies in the pink berry were obtained from two centrally-located slices within the

granule closest to the core, whereas the microindentation measurements were performed at the

granule surface. Further studies are required to assess potential spatial variations in both density

and stiffness of the components across the granule, as well as EPS composition to allow for

comparative analyses with lamellar biofilms. While it would be ideal to conduct all imaging and

mechanical analyses on the same pink berry samples, light sheet imaging requires fixation and

optical clearing steps that would negatively impact subsequent mechanical characterization. For

this reason, nanoindentations were not conducted on samples prepared for such imaging.

4.5 Future Work

The results presented here are a first approximation of the mechanical properties of pink berry

granular biofilms. We believe there to be seasonal, geographical, and potentially day-night

variability in properties like size and structure of the pink berries. Future studies will investigate

variation in pink berry size, density, structure, and EPS matrix composition and explore how

these variations impact mechanical properties of the biofilms. This work may help inform

granule design and optimal environmental conditions in wastewater treatment systems.

Microscale variation in material properties throughout a granular biofilm can influence

their macroscale properties and overall function. Radially symmetric density variation has been

observed in other granular biofilms, typically with a denser surface and a less dense core [77].

While we did not find radially-symmetric trends from nanoindentations or imaging, a larger set

of nanoindentation measurements positioned to investigate this property could improve our

understanding of how spatial gradients influence overall mechanical properties and function.

EPS matrix variation, including composition and structured layering, have been found in other

biofilms [78, 79]. Future studies will include investigation of EPS matrix composition and

whether composition varies throughout the biofilms, as this could influence the mechanical

properties of the composite.

Our results suggest that pink berry, soft and viscoelastic, pink berry granular biofilms are

well suited for industrial applications. However, pink berries are only known to occur in a

restricted geographic location worldwide and they cannot currently be maintained and cultured in

isolation. This presents significant experimental challenges for detailed studies of component

parts, or direct biotechnological applications. Future prospects include their propagation in

culture or studies of live material using next-generation 3D culture and perfusion techniques

[80].

Pink berry granular biofilms were used here as a model system for methods applicable

across disciplines, integrating imaging and mechanics to construct structure-property

relationships. We hope this study inspires future work on other biological composites and soft

biomaterials and foresee a rich application space ranging from non-moldable synthetic materials

to three-dimensional tissue-mimicking models like cancer spheroids and organoids.

5. Concluding Remarks

In this work, we have developed a sequence of methods bridging the gap between the visual and

mechanical landscapes across length scales of composite soft materials. Using the soft ($E^*_{\text{pink berry}}$

≈ 0.5–10 kPa) pink berry granular biofilm as a model system, we showed that this composite has

viscoelastic mechanical properties and experience fast relaxation times ($\tau_{1/2} \approx$ seconds).

Additionally, our methods revealed that by computing the volume fraction of cell microcolonies

($\approx 34\%$), we could relate microscale mechanical contributions to the macroscopic properties

crucial for pink berry biofilm function, including structural integrity and cell protection. By

studying naturally occurring microbial granules like pink berry biofilms, we can improve the

design of engineered consortia, including for waste management technologies. Continued

investigation of the structural and mechanical properties of biological composites, from biofilms

to cancer spheroids, organoids, and beyond, will allow us to better understand nature and

improve the built environment around us.

Conflicts of Interest

The authors declare no conflict of interest.

Acknowledgements

We gratefully acknowledge the current and former members of the Interfacial Engineering

Laboratory and the Wilbanks Lab for helpful discussions. Special thanks to Dr. Benjamin Lopez

for his assistance with light sheet imaging and image analysis. This work was primarily

supported by the US Army Research Office under Cooperative Agreement No. W911NF-19-2-

0026 for the Institute for Collaborative Biotechnologies. We acknowledge the BioPACIFIC

Materials Innovation Platform of the National Science Foundation (Award No. DMR-1933487)

for the use of their shared user facilities, including the use of the Optics11 Life Pavone

nanoindenter and instrument training and support from specialist Dr. Juan Manuel Urueña during

nanoindentation measurements. We also acknowledge the use of the NRI-MCDB Microscopy

Facility at UC Santa Barbara, including the Leica VT1000S vibratome, the Leica SP8 Resonant

Scanning Confocal supported by the NSF MRI grant DBI-1625770 as well as the Zeiss Z.1

Lightsheet and Hercules computer workstation supported by the NIH Shared Instrumental Grant

1S10OD019969-01A1. We gratefully acknowledge contributions of Dr. Emily N. Junkins to

field sampling of pink berry consortia, work which was supported by a Whitman Fellowship to

E.N.J. from the Marine Biological Laboratory.

References

1. O'Toole G, Kaplan HB, Kolter R (2000) Biofilm Formation as Microbial Development. Annual Review of Microbiology 54:49–79. https://doi.org/10.1146/annurev.micro.54.1.49

2. Claessen D, Rozen DE, Kuipers OP, et al (2014) Bacterial solutions to multicellularity: a tale of biofilms, filaments and fruiting bodies. Nat Rev Microbiol 12:115–124. https://doi.org/10.1038/nrmicro3178

3. Mark Welch JL, Rossetti BJ, Rieken CW, et al (2016) Biogeography of a human oral microbiome at the micron scale. Proceedings of the National Academy of Sciences 113:E791–E800. https://doi.org/10.1073/pnas.1522149113

4. Chen CS (2008) Mechanotransduction – a field pulling together? Journal of Cell Science 121:3285–3292. https://doi.org/10.1242/jcs.023507

5. Tilghman RW, Cowan CR, Mih JD, et al (2010) Matrix Rigidity Regulates Cancer Cell Growth and Cellular Phenotype. PLoS One 5:e12905. https://doi.org/10.1371/journal.pone.0012905

6. Lu P, Weaver VM, Werb Z (2012) The extracellular matrix: A dynamic niche in cancer progression. J Cell Biol 196:395–406. https://doi.org/10.1083/jcb.201102147

7. Rice AJ, Cortes E, Lachowski D, et al (2017) Matrix stiffness induces epithelial–mesenchymal transition and promotes chemoresistance in pancreatic cancer cells. Oncogenesis 6:e352. https://doi.org/10.1038/oncsis.2017.54

8. Sarantis P, Koustas E, Papadimitropoulou A, et al (2020) Pancreatic ductal adenocarcinoma: Treatment hurdles, tumor microenvironment and immunotherapy. World J Gastrointest Oncol 12:173–181. https://doi.org/10.4251/wjgo.v12.i2.173

9. Liu J, Wu J (2024) The Pathogenesis and Impact of Arterial Stiffening in Hypertension: The 2023 John H. Laragh Research Award. American Journal of Hypertension 37:241–247. https://doi.org/10.1093/ajh/hpae006

10. Volle CB, Ferguson M, Aidala K, et al (2009) Physical Properties of Native Biofilm Cells Explored by Atomic Force Microscopy. Biophysical Journal 96:398a. https://doi.org/10.1016/j.bpj.2008.12.2025

11. James SA, Hilal N, Wright CJ (2017) Atomic force microscopy studies of bioprocess engineering surfaces – imaging, interactions and mechanical properties mediating bacterial adhesion. Biotechnology Journal 12:1600698. https://doi.org/10.1002/biot.201600698

12. Pattem J, Davrandi M, Aguayo S, et al (2018) A Multi-scale Biophysical Approach to Develop Structure-Property Relationships in Oral Biofilms. Sci Rep 8:5691. https://doi.org/10.1038/s41598-018-23798-1

13. Schulze KD, Zehnder SM, Urueña JM, et al (2017) Elastic modulus and hydraulic permeability of MDCK monolayers. Journal of Biomechanics 53:210–213. https://doi.org/10.1016/j.jbiomech.2017.01.016

14. Bozdag GO, Zamani-Dahaj SA, Day TC, et al (2023) De novo evolution of macroscopic multicellularity. Nature 617:747–754. https://doi.org/10.1038/s41586-023-06052-1

15. Allwood AC, Walter MR, Kamber BS, et al (2006) Stromatolite reef from the Early Archaean era of Australia. Nature 441:714–718. https://doi.org/10.1038/nature04764

16. Wilking JN, Angelini TE, Seminara A, et al (2011) Biofilms as complex fluids. MRS Bulletin 36:385–391. https://doi.org/10.1557/mrs.2011.71

17. Böl M, Ehret ,Alexander E., Bolea Albero ,Antonio, et al (2013) Recent advances in mechanical characterisation of biofilm and their significance for material modelling. Critical Reviews in Biotechnology 33:145–171. https://doi.org/10.3109/07388551.2012.679250

18. He Y, Peterson BW, Jongsma MA, et al (2013) Stress Relaxation Analysis Facilitates a Quantitative Approach towards Antimicrobial Penetration into Biofilms. PLOS ONE 8:e63750. https://doi.org/10.1371/journal.pone.0063750

19. Safari A, Tukovic ,Zeljko, Walter ,Maik, et al (2015) Mechanical properties of a mature biofilm from a wastewater system: from microscale to macroscale level. Biofouling 31:651–664. https://doi.org/10.1080/08927014.2015.1075981

20. Peterson BW, He Y, Ren Y, et al (2015) Viscoelasticity of biofilms and their recalcitrance to mechanical and chemical challenges. FEMS Microbiol Rev 39:234–245. https://doi.org/10.1093/femsre/fuu008

21. Kundukad B, Seviour T, Liang Y, et al (2016) Mechanical properties of the superficial biofilm layer determine the architecture of biofilms. Soft Matter 12:5718–5726. https://doi.org/10.1039/C6SM00687F

22. Billings N, Birjiniuk A, Samad TS, et al (2015) Material properties of biofilms – key methods for understanding permeability and mechanics. Rep Prog Phys 78:036601. https://doi.org/10.1088/0034-4885/78/3/036601

23. Gordon VD, Davis-Fields M, Kovach K, Rodesney CA (2017) Biofilms and mechanics: a review of experimental techniques and findings. J Phys D: Appl Phys 50:223002. https://doi.org/10.1088/1361-6463/aa6b83

24. Gloag ES, Fabbri S, Wozniak DJ, Stoodley P (2020) Biofilm mechanics: Implications in infection and survival. Biofilm 2:100017. https://doi.org/10.1016/j.bioflm.2019.100017

25. Zhang Y, Young P, Traini D, et al (2023) Challenges and current advances in in vitro biofilm characterization. Biotechnology Journal 18:2300074. https://doi.org/10.1002/biot.202300074

26. Li M, Nahum Y, Matouš K, et al (2023) Effects of biofilm heterogeneity on the apparent mechanical properties obtained by shear rheometry. Biotechnology and Bioengineering 120:553–561. https://doi.org/10.1002/bit.28276

27. Wells MJ, Zhou X, Gordon VD (2024) Viscoelasticity of the Biofilm Matrix. In: Reichhardt C (ed) Biofilm Matrix. Springer Nature Switzerland, Cham, pp 259–282

28. Nicolella C, van Loosdrecht MCM, Heijnen JJ (2000) Wastewater treatment with particulate biofilm reactors. Journal of Biotechnology 80:1–33. https://doi.org/10.1016/S0168-1656(00)00229-7

29. Winkler M-KH, Meunier C, Henriet O, et al (2018) An integrative review of granular sludge for the biological removal of nutrients and recalcitrant organic matter from wastewater. Chemical Engineering Journal 336:489–502. https://doi.org/10.1016/j.cej.2017.12.026

30. Trego AC, Mills S, and Collins G (2021) Granular biofilms: Function, application, and new trends as model microbial communities. Critical Reviews in Environmental Science and Technology 51:1702–1725. https://doi.org/10.1080/10643389.2020.1769433

31. Rosa-Masegosa A, Rodriguez-Sanchez A, Gorrasi S, et al (2024) Microbial Ecology of Granular Biofilm Technologies for Wastewater Treatment: A Review. Microorganisms 12:433. https://doi.org/10.3390/microorganisms12030433

32. Seitz AP, Nielsen TH, Overmann J (1993) Physiology of purple sulfur bacteria forming macroscopic aggregates in Great Sippewissett Salt Marsh, Massachusetts. FEMS Microbiology Ecology 12:225–235. https://doi.org/10.1111/j.1574-6941.1993.tb00035.x

33. Wilbanks EG, Jaekel U, Salman V, et al (2014) Microscale sulfur cycling in the phototrophic pink berry consortia of the Sippewissett Salt Marsh. Environmental Microbiology 16:3398–3415. https://doi.org/10.1111/1462-2920.12388

34. Wilbanks EG, Doré H, Ashby MH, et al (2022) Metagenomic methylation patterns resolve bacterial genomes of unusual size and structural complexity. ISME J 16:1921–1931. https://doi.org/10.1038/s41396-022-01242-7

35. Doré H, Eisenberg AR, Junkins EN, et al (2024) Targeted hypermutation of putative antigen sensors in multicellular bacteria. Proc Natl Acad Sci USA 121:e2316469121. https://doi.org/10.1073/pnas.2316469121

36. Kosmopoulos JC, Campbell DE, Whitaker RJ, Wilbanks EG (2023) Horizontal Gene Transfer and CRISPR Targeting Drive Phage-Bacterial Host Interactions and Coevolution in "Pink Berry" Marine Microbial Aggregates. Applied and Environmental Microbiology 89:e00177-23. https://doi.org/10.1128/aem.00177-23

37. Krick BA, Vail JR, Persson BNJ, Sawyer WG (2012) Optical In Situ Micro Tribometer for Analysis of Real Contact Area for Contact Mechanics, Adhesion, and Sliding Experiments. Tribol Lett 45:185–194. https://doi.org/10.1007/s11249-011-9870-y

38. Urueña JM, Hart SM, Hood DL, et al (2018) Considerations for Biotribometers: Cells, Gels, and Tissues. Tribol Lett 66:141. https://doi.org/10.1007/s11249-018-1094-y

39. Chau AL, Getty PT, Rhode AR, et al (2022) Superlubricity of pH-responsive hydrogels in extreme environments. Front Chem 10:. https://doi.org/10.3389/fchem.2022.891519

40. Chau AL, Edwards CER, Helgeson ME, Pitenis AA (2023) Designing Superlubricious Hydrogels from Spontaneous Peroxidation Gradients. ACS Appl Mater Interfaces 15:43075–43086. https://doi.org/10.1021/acsami.3c04636

41. Atkins DJ, Rosas JM, Månsson LK, et al (2024) Survival-Associated Cellular Response Maintained in Pancreatic Ductal Adenocarcinoma (PDAC) Switched Between Soft and Stiff 3D Microgel Culture. ACS Biomater Sci Eng 10:2177–2187. https://doi.org/10.1021/acsbiomaterials.3c01079

42. Rhode AR, Montes de Oca I, Chabinyc ML, et al (2024) Sliding on Slide-Ring Gels. Tribol Lett 72:121. https://doi.org/10.1007/s11249-024-01920-x

43. Atkins DJ, Rogers AE, Shaffer KE, et al (2025) Pro-Inflammatory Response to Macrotextured Silicone Implant Wear Debris. Tribol Lett 73:30. https://doi.org/10.1007/s11249-025-01965-6

44. Hertz H (1882) Ueber die Berührung fester elastischer Körper. Journal für die reine und angewandte Mathematik 92:156–171

45. Nayar VT, Weiland JD, Nelson CS, Hodge AM (2012) Elastic and viscoelastic characterization of agar. Journal of the Mechanical Behavior of Biomedical Materials 7:60–68. https://doi.org/10.1016/j.jmbbm.2011.05.027

46. Preibisch S, Saalfeld S, Tomancak P (2009) Globally optimal stitching of tiled 3D microscopic image acquisitions. Bioinformatics 25:1463–1465. https://doi.org/10.1093/bioinformatics/btp184

47. Rmaile A, Carugo D, Capretto L, et al (2013) Microbial tribology and disruption of dental plaque bacterial biofilms. Wear 306:276–284. https://doi.org/10.1016/j.wear.2013.02.010

48. Chaudhuri O, Gu L, Klumpers D, et al (2016) Hydrogels with tunable stress relaxation regulate stem cell fate and activity. Nat Mater 15:326–334. https://doi.org/10.1038/nmat4489

49. Gionet-Gonzales M, Gathman G, Rosas J, et al (2025) Stress relaxation rates of myocardium from failing and non-failing hearts. Biomech Model Mechanobiol 24:265–280. https://doi.org/10.1007/s10237-024-01909-4

50. Wloka M, Rehage H, Flemming H-C, Wingender J (2004) Rheological properties of viscoelastic biofilm extracellular polymeric substances and comparison to the behavior of calcium alginate gels. Colloid Polym Sci 282:1067–1076. https://doi.org/10.1007/s00396-003-1033-8

51. Chatterjee K, Pratiwi FW, Wu FCM, et al (2018) Recent Progress in Light Sheet Microscopy for Biological Applications. Appl Spectrosc, AS 72:1137–1169

52. Santi PA (2011) Light Sheet Fluorescence Microscopy: A Review. J Histochem Cytochem 59:129–138. https://doi.org/10.1369/0022155410394857

53. Lazzari G, Vinciguerra D, Balasso A, et al (2019) Light sheet fluorescence microscopy *versus* confocal microscopy: in quest of a suitable tool to assess drug and nanomedicine penetration into multicellular tumor spheroids. European Journal of Pharmaceutics and Biopharmaceutics 142:195–203. https://doi.org/10.1016/j.ejpb.2019.06.019

54. Zhang J, Zhang M, Wang Y, et al (2021) Optically Accessible Microfluidic Flow Channels for Noninvasive High-Resolution Biofilm Imaging Using Lattice Light Sheet Microscopy. J Phys Chem B 125:12187–12196. https://doi.org/10.1021/acs.jpcb.1c07759

55. Šmerdová L, Füzik T, Valentová L, et al (2024) Dynamics of bacterial biofilm development imaged using light sheet fluorescence microscopy. 2024.07.10.602771

56. Vignolini T, Capitanio M, Caldini C, et al (2024) Highly inclined light sheet allows volumetric super-resolution imaging of efflux pumps distribution in bacterial biofilms. Sci Rep 14:12902. https://doi.org/10.1038/s41598-024-63729-x

57. Qin B, Fei C, Bridges AA, et al (2020) Cell position fates and collective fountain flow in bacterial biofilms revealed by light-sheet microscopy. Science 369:71–77. https://doi.org/10.1126/science.abb8501

58. Zhang M, Zhang J, Wang J, et al (2019) 3D Imaging of Single Cells in Bacterial Biofilms using Lattice Light-Sheet Microscopy. Biophysical Journal 116:25a. https://doi.org/10.1016/j.bpj.2018.11.179

59. Parthasarathy R (2018) Monitoring microbial communities using light sheet fluorescence microscopy. Current Opinion in Microbiology 43:31–37. https://doi.org/10.1016/j.mib.2017.11.008

60. Fuchs E, Jaffe JS, Long RA, Azam F (2002) Thin laser light sheet microscope for microbial oceanography. Opt Express, OE 10:145–154. https://doi.org/10.1364/OE.10.000145

61. Paramonova E, Kalmykowa OJ, van der Mei HC, et al (2009) Impact of Hydrodynamics on Oral Biofilm Strength. J Dent Res 88:922–926. https://doi.org/10.1177/0022034509344569

62. Aggarwal S, Hozalski RM (2010) Determination of biofilm mechanical properties from tensile tests performed using a micro-cantilever method. Biofouling 26:479–486. https://doi.org/10.1080/08927011003793080

63. Flemming H-C, van Hullebusch ED, Neu TR, et al (2023) The biofilm matrix: multitasking in a shared space. Nat Rev Microbiol 21:70–86. https://doi.org/10.1038/s41579-022-00791-0

64. Schmitt J, Flemming H-C (1999) Water binding in biofilms. Water Science and Technology 39:77–82. https://doi.org/10.1016/S0273-1223(99)00153-5

65. Saharan BS, Beniwal N, Duhan JS (2024) From formulation to function: A detailed review of microbial biofilms and their polymer-based extracellular substances. The Microbe 5:100194. https://doi.org/10.1016/j.microb.2024.100194

66. Grandel NE, Reyes Gamas K, Bennett MR (2021) Control of synthetic microbial consortia in time, space, and composition. Trends in Microbiology 29:1095–1105. https://doi.org/10.1016/j.tim.2021.04.001

67. Wang L, Zhang X, Tang C, et al (2022) Engineering consortia by polymeric microbial swarmbots. Nat Commun 13:3879. https://doi.org/10.1038/s41467-022-31467-1

68. Solé R, Conde–Pueyo N, Pla–Mauri J, et al (2024) Open problems in synthetic multicellularity. npj Syst Biol Appl 10:151. https://doi.org/10.1038/s41540-024-00477-8

69. Rubinstein M, Colby RH (2003) Polymer Physics. Oxford University Press

70. Dunn AC, Sawyer WG, Angelini TE (2014) Gemini Interfaces in Aqueous Lubrication with Hydrogels. Tribol Lett 54:59–66. https://doi.org/10.1007/s11249-014-0308-1

71. Hu Y, Zhao X, Vlassak JJ, Suo Z (2010) Using indentation to characterize the poroelasticity of gels. Applied Physics Letters 96:121904. https://doi.org/10.1063/1.3370354

72. Shaw T, Winston M, Rupp CJ, et al (2004) Commonality of Elastic Relaxation Times in Biofilms. Phys Rev Lett 93:098102. https://doi.org/10.1103/PhysRevLett.93.098102

73. Su L, Wang M, Yin J, et al (2023) Distinguishing poroelasticity and viscoelasticity of brain tissue with time scale. Acta Biomaterialia 155:423–435. https://doi.org/10.1016/j.actbio.2022.11.009

74. He D, Malu D, Hu Y (2024) A Comprehensive Review of Indentation of Gels and Soft Biological Materials. Applied Mechanics Reviews 76:. https://doi.org/10.1115/1.4065434

75. Tschoegl NW (1989) The Phenomenological Theory of Linear Viscoelastic Behavior. Springer, Berlin, Heidelberg

76. Roylance D (2001) Engineering Viscoelasticity

77. Toh S, Tay J, Moy B, et al (2003) Size-effect on the physical characteristics of the aerobic granule in a SBR. Appl Microbiol Biotechnol 60:687–695. https://doi.org/10.1007/s00253-002-1145-y

78. Lin X, Wang Y (2017) Microstructure of anammox granules and mechanisms endowing their intensity revealed by microscopic inspection and rheometry. Water Research 120:22–31. https://doi.org/10.1016/j.watres.2017.04.053

79. Jia F, Yang Q, Liu X, et al (2017) Stratification of Extracellular Polymeric Substances (EPS) for Aggregated Anammox Microorganisms. Environ Sci Technol 51:3260–3268. https://doi.org/10.1021/acs.est.6b05761

80. Sawyer WG, Marshall SL, McGhee EO, et al (2020) Perfusion enabled bioreactors