A coupled fluorescence assay for high-throughput screening of polyurethane-degrading enzymes

Liujun YANG[1], Xianjun DENG[1], Renju LIU[2], Jianyang LI[2], Junyao ZHAI[1], Xiaoxiao MA[1], Arthur K.L. LIN[3], Zongze SHAO[2], Jiguang WANG[4], Hongyuan LU[1]*

[1] *Thrust of Bioscience and Biomedical Engineering, The Hong Kong University of Science and Technology (Guangzhou), Guangzhou 511400, China*

[2] *Third Institute of Oceanography, Ministry of Natural Resources, Xiamen 361005, China*

[3] *Practice in Engineering Education, The Hong Kong University of Science and Technology (Guangzhou), Guangzhou 511400, China*

[4] *Division of Life Science, Department of Chemical and Biological Engineering, The Hong Kong University of Science and Technology, Clear Water Bay, Kowloon, Hong Kong SAR, China*

Corresponding authors: Hongyuan LU (hongylu@hkust-gz.edu.cn)
First author contact: Liujun YANG (lyang068@connect.hkust-gz.edu.cn)

Abstract

The global accumulation of plastic waste, particularly persistent polymers like polyurethane (PU), demands urgent solutions. Enzymatic depolymerization offers a viable strategy for PU waste valorization. However, progress has been hindered by the lack of reliable high-throughput screening (HTS) assays capable of precise and quantitative evaluation of enzymatic activity. Current enzyme screening assays face significant limitations due to poor substrate relevance and inadequate quantification methods. Here, we present a novel HTS assay featuring a chemically defined, synthetic poly (ethylene adipate)-based PU substrate that enables unambiguous structure-activity analysis and direct quantification of degradation products (adipic acid and ethylene glycol). Coupled with this substrate is a highly sensitive fluorescence-based detection cascade, in which released ethylene glycol is stoichiometrically converted to resorufin via a two-enzyme system (glycerol dehydrogenase and diaphorase). This assay overcomes key limitations of commercial substrates (e.g., Impranil DLN) by providing quantitative, real-time monitoring of PU hydrolysis with molecular precision. Validation with known PU-degrading enzymes demonstrated that the assay can sensitively distinguish differences in enzymatic activity with high reproducibility and quantitative accuracy. Our platform enables rapid, cost-effective screening of enzyme libraries and engineered variants, significantly advancing enzyme discovery and optimization efforts. By bridging the gap between laboratory research and industrial application, this HTS assay accelerates the development of sustainable PU recycling solutions, offering a critical tool against plastic pollution.

Graphical Abstract Legend.

(A) Workflow of the enzymatic degradation assay. Enzymes are incubated with chemically defined PEA-PU films. The resulting hydrolysate is collected and analysed using a fluorescence-based assay in microplate format (Ex/Em = 535/588 nm). **(B)** Fluorescence-based detection mechanism. Assay principle based on ethylene glycol (EG), one of the major degradation products. EG is converted through a two-step enzymatic cascade involving glycerol dehydrogenase (GldA) and diaphorase, leading to the generation of fluorescent resorufin from resazurin.

32 "Keywords: fluorescence; high-throughput screening; polyurethane; enzyme engineering; biodegradation; ethylene glycol"

1. Introduction

Plastic pollution poses a pressing global challenge, threatening ecosystems [1-3] and human health [4–9]. A major contributor to this crisis is polyurethane (PU), a synthetic polymer extensively used in foams (e.g., mattresses, insulation), elastomers (e.g., shoe soles, medical devices), and durable goods (e.g., automotive parts, synthetic leather) [10–12]. Given the low recycling rate of PU waste [12,13], its environmental persistence highlights the urgent need for sustainable solutions [13–15].

Enzymatic depolymerization has emerged as a promising strategy for PU waste valorization, attracting growing research interest [10,13–16]. However, progress in this field remains limited. This is largely due to persistent challenges in identifying, characterizing, and engineering enzymes that can efficiently degrade PU under industrial conditions [14–18].

A major bottleneck lies in current enzyme screening assays, which suffer from limitations in predictive accuracy and practical utility (Table 1). Conventional assays using low-molecular-weight model substrates (e.g., p-nitrophenyl esters or carbamates) often fail to predict enzyme activity against authentic polymeric PU, leading to false positives that misdirect enzyme discovery efforts [14,15,16,19]. In contrast, while industrial PU materials (e.g., foams, films, elastomers) offer greater physiological relevance, their heterogeneity and slow degradation kinetics render them unsuitable for high-throughput screening (HTS) applications [15,18,20,21].

Consequently, many studies have turned to colloidal PU dispersions (e.g., Impranil DLN or Bayhydrol), accessing enzyme activity via clearing zone formation [22] or by monitoring OD reduction in PU emulsions upon enzyme or microbial addition [23]. However, these proprietary mixtures are chemically undefined and only detect bulk esterase activity. These limitations hinder rigorous quantitative analysis, which is crucial for enzyme discovery and mechanistic studies [14,15,20,24].

To overcome these limitations, we developed an HTS assay using a synthetic PU substrate designed to release detectable degradation products upon enzymatic hydrolysis. By coupling this reaction to a detection cascade—where degradation products are enzymatically converted into an optical signal—we enable real-time kinetic measurements and direct activity comparisons.

This assay resolves key ambiguities in existing methods by delivering a quantitative, high-throughput measurement of PU hydrolysis kinetics, enabling rapid and precise enzyme variants screening. Rigorous validation with established PU-degrading enzymes confirms its high sensitivity, reproducibility, and robustness. Beyond serving as a powerful tool for enzyme discovery and engineering, this assay also establishes a foundation for mechanistic studies of PU biodegradation.

Feature	LMW Model Compounds	PU Dispersions	Commercial PU Materials
Representative Examples	p-Nitrophenyl esters, carbamates	Impranil® DLN, Bayhydrol® 110	PU foam, film, elastomer
Chemical Definition	Defined, synthetic molecules	Proprietary formulations	undefined mixtures or composites
Physiological Relevance	Low	Moderate	High
Readout Modality	Colorimetric absorbance	Turbidity clearing, halo formation	Weight loss, SEM, product analysis (e.g., HPLC)
Data Quality	Quantitative (model-limited)	Non-quantitative	Quantitative (method-dependent)
Screening Throughput	High	Moderate	Low
Bond-Type Specificity	Restricted to designed motifs	Ester-biased; limited urethane sensitivity	Broad; structurally diffuse
Mechanistic Insight	Indirect; lacks polymer context	Partial; limited structural resolution	Direct, but labor-intensive

Table 1: Critical limitations of current assay formats for polyurethane (PU) biodegradation.
A Comparative overview of model substrates, colloidal PU dispersions, and commercial PU materials used in PU degradation assays.

2. Results and Discussion

2.1. Synthesis and characterization of PEA-PU

To develop a quantitative assay for PU-degrading enzymes, we designed a novel polymeric substrate that is chemically well-defined and readily synthesizable. The polymer features a soft segment composed of poly (ethylene adipate) (PEA). Hydrolysis of its ester bonds produces two well-defined products: ethylene glycol (EG) and adipic acid (AA). Both can be easily quantified with high reliability. Specifically, the PEA-PU polymer was synthesized via a one-step, solvent-based step-growth polymerization [23,25] (Fig. 1A). The resulting polymer solution was then cast into films exhibiting high optical transparency and uniformity (Fig. 1B). This optical quality reflects excellent macroscopic homogeneity, which is desirable for consistent enzyme-substrate interactions in replicate assays.

To confirm the polymer's chemical composition, we performed ¹H NMR analysis. The ¹H NMR spectrum (Fig. 1B) exhibited three diagnostic regions that unambiguously confirmed the polyester–urethane backbone architecture: (i) the urethane N–H proton at δ 9.63 ppm; (ii) aromatic and bridging methylene protons from the MDI-based hard segment at δ 7.07–7.35 and 3.78 ppm, respectively; (iii) O-linked methylene protons from the ethylene glycol units at δ 4.18–4.29 ppm, and aliphatic methylene protons from the adipate segment at δ ~2.3 and ~1.5 ppm. These clearly assignable signals demonstrate successful formation of both urethane and ester linkages in the polymer structure, providing a structural foundation for precise analysis of enzymatic degradation.

Complementary structural verification was achieved through Fourier-transform infrared (FTIR) spectroscopy
(Fig. 1D). The spectrum displayed all expected characteristic absorptions: (i) a strong ester C=O stretch at 1725
cm^{-1}, (ii) a broad urethane N–H stretch at 3320 cm^{-1}, (iii) an amide II band (C–N stretch) at 1530 cm^{-1}, and (iv)
an ester C–O stretch at 1240 cm^{-1}. These features showed excellent agreement with reference spectra of urethane
and ester groups, supporting the expected chemical structure of the polymer.

To further validate the material's properties, we characterized the thermal behavior of the synthesized PEA-PU
using differential scanning calorimetry (DSC). The DSC results revealed that PEA-PU exhibits amorphous
thermoplastic behavior, with a glass transition temperature (Tg) of approximately –17.6 °C, as determined by
the half-height method (Supplementary Fig. 1). No melting transition was observed up to 200 °C. This thermal
profile confirms the absence of crystalline domains, making the material particularly suitable for enzymatic
degradation studies [15,21].

Taken together, these results demonstrate that PEA-PU is a structurally uniform, chemically well-defined
polymer with straightforward synthesis and characterization. The material is optically transparent and exhibits
distinct spectroscopic signatures, facilitating analytical tracking. More importantly, PEA-PU closely replicates
the structural and chemical properties of post-consumer PU waste, making it a highly representative model
system. These properties establish PEA-PU as an ideal model substrate for enzymatic degradation studies while
also serving as a reproducible, standardized platform for developing robust PU degradation assays.

Figure 1: Synthesis and characterization of PEA-PU.

(A) Synthesis of PEA-PU via step-growth polymerization. PEA-PU was synthesized by reacting pre-dried polyethylene adipate (PEA, Mn ≈ 1000 g/mol) with 4,4′-methylenebis (phenyl isocyanate) (MDI) at an NCO: OH molar ratio of 1:1 in anhydrous DMF at 70 °C under a nitrogen atmosphere for 1 hour. **(B) PEA-PU film**. The polymer solution was cast into a PTFE mold and dried under vacuum at 60 °C for 24 hours, yielding a film approximately 0.2 mm thick. **(C) ¹H-NMR spectrum of PEA-PU**. δ 9.63 (br s, NH, urethane); 7.33 (t, J ≈ 8.6 Hz, 2 H) & 7.08 (d, J ≈ 8.2 Hz, 3 H) = aromatic H of MDI; 4.40–4.15 (m, ≈14 H) = overlapped O-CH₂-CH₂-O and α-CH₂ next to carbonyl/urethane O; 3.78 (br s, Ar-CH₂-Ar bridge, down-field half; up-field partner at ~3.3 ppm is buried in the 2.6–2.3 ppm envelope); 2.60–2.35 (br m) = overlapped Ar-CH₂-Ar partner + urethane α-CH₂ ± minor end groups; 2.30 (br s) = adipate α-CH₂; 1.52 (br s) = internal aliphatic CH₂. **(D) FTIR spectrum of PEA-PU.**The spectrum exhibits characteristic absorption bands, including a composite carbonyl band at 1725 cm⁻¹ (overlapping ester and urethane C=O stretches), a urethane N–H stretch at 3320 cm⁻¹, an amide II band at 1530 cm⁻¹ (N–H bending coupled with C–N stretching), and an amide III/ester C–O–C band at 1240 cm⁻¹, collectively validating the expected urethane and ester functionalities in the polymer backbone.

2.2. Enzymatic degradation of PEA-PU

Following comprehensive characterization of PEA-PU's structure and physicochemical properties, we next evaluated its enzymatic degradability using two well-characterized polyester hydrolases: two well-characterized polyester hydrolases: ICCM (an engineered leaf compost cutinase variant) and BaCut1 (a cutinase from *Blastobotrys* sp. G-9). Although both enzymes demonstrate PU-degrading capability, prior studies have reported that ICCM exhibit greater polyester hydrolytic activity than BaCut1 under their respective optimal conditions[26,27]. We therefore employed PEA-PU as a model substrate to determine whether this well-documented activity difference could be reliably replicated, assessing its potential for standardized enzyme performance comparisons.

PEA-PU films were incubated with each enzyme for 36 hours under their optimal conditions (70 °C for ICCM, 37 °C for BaCut1). Enzymatic treatment induced significant morphological alterations in the films, which transitioned from an initially transparent state to an opaque and fragmented morphology (Fig. 2A). In contrast, control samples exhibited no structural or optical changes, demonstrating that the degradation was exclusively enzyme dependent.

To examine surface-level enzymatic degradation, we analyzed PEA-PU films by scanning electron microscopy (SEM). While untreated films displayed smooth and uniform surfaces, enzyme-treated samples exhibited significant surface erosion (Fig. 2A). ICCM treatment induced pronounced degradation features, including deep pits and porous structures, whereas BaCut1 treatment caused milder surface disruption. These distinct morphological patterns reflect differential catalytic efficiencies between the two enzymes, consistent with previous reports[26,27].

Further structural analysis by FTIR provided additional insights (Fig. 2B). Compared to untreated PEA-PU, enzyme-treated samples exhibited:(i) a broadened and slightly intensified O–H/N–H stretching band (3200–3500 cm^{-1}), suggesting the formation of hydroxyl and amine end-groups resulting from ester and urethane bond cleavage;(ii) a notable decrease in ester carbonyl (~1725 cm^{-1}) and C–O–C stretching (~1100 cm^{-1}) band intensities, confirming the breakdown of polyester segments.

To characterize the soluble degradation products, we performed chromatographic analysis of reaction supernatants. The PU monomer AA was quantified via liquid HPLC, while EG was detected by gas chromatography–mass spectrometry (GC–FID). Both monomers were exclusively present in enzyme-treated samples, with no detectable levels in negative controls. Notably, the observed AA:EG molar ratio (approximately 1:1) matched the theoretical stoichiometry of PEA-PU hydrolysis, wherein each ester bond cleavage generates equimolar AA and EG (Supplementary Table 1). This stoichiometric agreement establishes AA production as a robust quantitative indicator of EG release during enzymatic degradation.

Gel permeation chromatography (GPC) was then employed to quantify changes in polymer molecular weight following enzymatic treatment. Untreated PEA-PU exhibited a high molecular weight distribution, with a main retention time around 8.5 min. After enzymatic degradation, the distribution shifted toward higher retention times. Specifically, the main peak shifted to ~10.0 min after ICCM treatment and to ~9.2 min after BaCut1 treatment (Fig. 2C), consistent with the formation of lower-molecular-weight fragments. ICCM treatment led to a 67.9% reduction in number-average molecular weight (Mn) and a 47.3% reduction in weight-average molecular weight (Mw) (Fig. 2D), indicating substantial fragmentation into smaller oligomers. BaCut1 caused a relatively smaller but still significant decrease in Mn (~28.2%) and Mw (~48.5%). The corresponding

polydispersity index (PDI) values are provided in Supplementary Figure S3. These molecular-level changes
align with the distinct surface erosion patterns observed by SEM.

In addition, to understand how the enzymes interact with the PEA-PU, we performed molecular docking using
representative PEA-PU oligomers. Our analysis revealed that both BaCut1 and ICCM preferentially bind to
adipate ester linkages at their active sites (Fig. 2E–F), highlighting conserved features of ester bond recognition.
Key interactions included hydrogen bonding networks and hydrophobic contacts near the cleavage site. Notably,
ICCM exhibited stronger binding affinity than BaCut1, forming additional hydrogen bonds with scissile
carbonyl oxygens and positioning the substrate deeper within its active site. These structural features—
enhanced binding interactions and optimal substrate alignment—likely contribute to ICCM's higher catalytic
efficiency toward PEA-PU degradation compared to BaCut1.
156
Collectively, our integrated approach—combining microscopic, spectroscopic, chromatographic, and
computational analyses—demonstrates that the chemically defined PEA-PU offers exceptional analytical
tractability during enzymatic degradation. Upon enzymatic treatment, PEA-PU undergoes clear morphological
changes—often visible to the naked eye—and generates well-defined soluble products. These monomers can
be accurately identified and quantified using conventional chromatographic methods. Importantly, by assessing
PEA-PU degradation with two established PU-degrading enzymes, we confirmed that this substrate reliably
recapitulates their differential activities. The degradation profiles reflect enzyme-specific catalytic behaviors,
enabling robust comparative analysis of PU-hydrolyzing activity. Given these attributes, PEA-PU emerges as
an ideal model substrate for comparative enzyme characterization, providing a reliable basis for quantitative
PU assay development.
167

A

B

C

D

E

BaCut1 model PEA-PU Docking

F

ICCM model PEA-PU Docking

Figure 2: Enzymatic degradation of PEA-PU (A) Visual observation of film degradation & **Surface morphology by SEM** PEA-PU films became turbid and fragmented after 36 h of incubation with ICCM (70 °C) or BaCut1 (37 °C), while enzyme-free controls remained optically transparent, indicating enzyme-specific hydrolytic activity. **(B) FTIR spectral changes following degradation**. **(C) GPC chromatograms**. GPC analysis was performed using DMF as the mobile phase after heat-assisted dissolution. **(D) Quantification of molecular weight reduction**. **(E, F) Molecular docking of enzyme–substrate complexes**. Docking simulations using AutoDock Vina showed that ICCM forms more hydrogen bonds with adipate ester linkages and binds substrates more deeply than BaCut1.

2.3. Development of a coupled fluorescence assay for EG detection in PEA-PU degradation

The well-defined chemical composition, transparency, and homogeneity of PEA-PU enable direct observation
and quantification of enzymatic degradation, with breakdown products readily analyzed by chromatography.
However, like conventional substrates, PEA-PU has a critical limitation: while chromatographic analysis offers
precise quantification, its low throughput hinders large-scale enzyme screening applications. To overcome this
bottleneck, we designed an enzymatic cascade that converts the stoichiometric release of EG during PU
hydrolysis into a sensitive fluorescent signal (Fig. 3A).

In this coupled system, we employed an NAD^+-dependent glycerol dehydrogenase (GldA) from *Enterobacter*
aerogenes [28] to oxidize EG to glyoxylic acid while reducing NAD^+ to NADH. The resulting NADH is then used
by diaphorase from *Clostridium kluyveri* [29] to reduce resazurin into resorufin, a highly fluorescent dye. This
two-step enzymatic cascade ensures a direct, molecule-to-molecule correspondence between PU hydrolysis (EG
release) and fluorescence intensity, enabling continuous and quantitative monitoring without extensive sample
processing.

To establish robust performance of the coupled enzymatic fluorescence assay, we systematically optimized its
reaction conditions. We began by evaluating buffer systems to maximize GldA activity. To avoid interference
from downstream enzymes, GldA was assessed independently using EG as the substrate. NADH formation was
monitored at 340 nm as a direct readout of enzymatic activity.

We tested six biological buffers: 50 mM Tris–HCl (pH 8.0 and 7.4), PBS (pH 8.0 and 7.4), HEPES (pH 7.4),
and KH_2PO_4 (pH 8.0). Among these, KH_2PO_4 (pH 8.0) generated the highest NADH signal but exhibited poor
reproducibility with significant inter-experimental variability. In contrast, 50 mM Tris–HCl (pH 8.0) supported
consistently strong and stable NADH production with minimal variability (Fig. 3B). Additionally, Tris–HCl
(pH 8.0) has been commonly used in prior studies involving diaphorase, supporting its suitability for the
downstream coupling reaction. Based on these results, we selected 50 mM Tris–HCl (pH 8.0) as the standard
buffer for all subsequent experiments.

Next, we determined the optimal concentration of the NAD^+ cofactor. Increasing NAD^+ from 1 mM to 3 mM
accelerated NADH production, monitored via 340 nm absorbance (Fig. 3C). As NADH was produced in
micromolar quantities, 3 mM NAD^+ was sufficient to drive the reaction and yield a stable signal; further
increases in NAD^+ provided minimal additional benefit. Therefore, 3 mM was selected as the optimal
concentration for subsequent assays (Fig. 3C).

We next optimized the concentration of diaphorase to ensure efficient signal transduction. Diaphorase activity
was assessed by measuring fluorescence output using 20 μM NADH and 10 μM resazurin in 50 mM Tris–HCl
(pH 8.0). Enzyme concentrations ranging from 0.1 U/mL to 0.5 U/mL were tested. After 30 minutes of
incubation at room temperature, fluorescence (Ex/Em = 535/588 nm) increased with diaphorase concentration,
plateauing at 0.3 U/mL. This suggests that 0.3 U/mL is sufficient for near-maximal signal output, with higher
concentrations offering only marginal gains. Thus, 0.3 U/mL was selected as the optimal diaphorase
concentration (Fig. 3D).

Finally, we evaluated resazurin, the fluorescent reporter, using 0.3 U/mL diaphorase and 20 μM NADH while
varying resazurin (10–50 μM). Following the same incubation and detection protocol, fluorescence intensity
decreased progressively with increasing resazurin concentrations. The highest signal was observed at 10 μM,
suggesting that excess resazurin may induce self-quenching or inner-filter effects. Based on these results, 10 μM
was selected as the standard resazurin concentration (Fig. 3E).

Figure 3: Development the coupled fluorescence assay. (A) Reaction scheme of the EG-coupled fluorescence assay.
Schematic of the enzymatic cascade linking EG oxidation to resorufin fluorescence via GldA and diaphorase. **(B) Identification of the**
optimal buffer for GldA-mediated NADH generation. (C) Optimization of NAD⁺ concentration for maximal EG oxidation. (D)
Optimization of diaphorase dosage for efficient signal conversion. (E) Selection of optimal resazurin concentration to avoid
quenching.

Through systematic optimization, we established a highly sensitive and reliable fluorescence-based assay for
quantifying EG production from PU degradation. Under the finalized conditions (50 mM Tris–HCl, pH 8.0; 3
mM NAD⁺; 10 μM resazurin; 0.3 U/mL diaphorase), the assay delivers a strong, EG-dependent fluorescent
signal across a broad detection range (0.25 – 25 mM EG), effectively capturing expected concentrations from
polymer breakdown. The fluorescence generation rate (RFU) showed excellent linear correlation with EG
concentration ($R^2 > 0.99$ at all-time points from 30–120 minutes, measured at 10-minute intervals;
Supplementary Table S2), demonstrating both precision and temporal stability. This assay enables continuous,
high-throughput monitoring of PU degradation and is ideally suited for enzyme activity screening.

2.4. Validation of the coupled assay for PEA-PU degradation

To evaluate the quantitative performance of our coupled fluorescence assay, we first constructed calibration
curves using EG standards ranging from 0.25 mM to 25 mM. Fluorescence generation rates (RFU/min),
measured between 30 minutes and 120 minutes, exhibited a highly linear response (R^2 = 0.9995; Figure 4A).
We then applied this calibration to quantify EG released from PEA-PU films following enzymatic degradation
by ICCM and BaCut1.

To independently validate these measurements, we used HPLC to quantify AA levels in the same samples,
leveraging the known 1:1 stoichiometric co-release of EG and AA during PEA-PU hydrolysis (Supplementary
Table 1). Because of this relationship, HPLC-measured AA levels serve as both a robust proxy for EG
production (and thus overall polymer degradation) and a direct benchmark for assessing the accuracy of
fluorescence-based EG detection. Notably, fluorescence-derived EG concentrations closely matched HPLC-
measured AA values (Figure 4B), confirming the assay's reliability for monitoring enzymatic degradation.

In addition to accuracy, our fluorescence assay also effectively resolved differences in enzymatic activity. As
shown in Figure 4B (inset), the fluorescence assay detected a 1.37-fold greater EG release by ICCM compared
to BaCut1. This ratio was highly consistent with the 1.40-fold difference measured via HPLC. This concordance
underscores our fluorescence assay's capacity to discriminate subtle variations in enzyme activity, a critical
feature for HTS applications.

Finally, the fluorescence assay offers several practical advantages over HPLC, including reduced analysis time,
lower sample volume requirements, and inherent compatibility with microplate-based high-throughput formats.
These improvements address major limitations of conventional PU degradation assays and may accelerate the
discovery and engineering of enhanced PU-degrading enzymes.

Figure 4: Validation of the coupled fluorescence assay for quantitative EG detection.
(A) Standard curve for EG detection. Fluorescence rates (RFU/min) showed excellent linear correlation with EG concentration from 0.25 to 25 mM (R^2 = 0.9995). **(B) Quantification of EG in enzymatic degradation samples.** Comparison of predicted EG concentrations (blue; derived from the fluorescence assay) and measured AA concentrations (magenta; determined by HPLC) in supernatants from PEA-PU films treated with BaCut1 and ICCM. Values reflect mean ± SD from three independent enzymatic reactions. **Inset,** Fold difference in enzymatic activity between ICCM and BaCut1 as determined by the fluorescence assay (1.37×) and HPLC (1.40×), demonstrating the assay's ability to resolve enzyme-specific activity differences.

3. Conclusion

The development of effective HTS assays for PU-degrading enzymes is essential for discovering and optimizing biocatalysts to combat PU pollution. Here, we present an HTS assay that integrates a chemically defined PEA-PU substrate with an enzymatic cascade, converting stoichiometrically released EG into a sensitive fluorescent signal. Our assay shows excellent correlation with conventional analytical techniques (e.g., HPLC), demonstrating comparable reliability while offering the significant advantages of high-throughput compatibility, overcoming the limitations of traditional labor-intensive methods.

A key innovation of this work lies in our substrate design. Unlike proprietary substrates such as Impranil DLN (with undefined composition and obscure degradation pathways), our PEA-PU system establishes clear structure-activity relationships, directly linking specific polymer bonds to their degradation products (AA and EG). This mechanistic clarity enables a deeper investigation of enzymatic mechanisms, supporting rational enzyme engineering and advanced screening strategies.

Beyond its fundamental advantages, the assay offers practical benefits, including rapid processing, minimal sample requirements, and seamless compatibility with multi-well plate formats. These features significantly reduce time and resource demands, enabling efficient screening of environmental isolations and large mutant libraries. Such capabilities make our assay particularly valuable for large-scale applications, from functional metagenomic discovery to directed evolution campaigns.

Future refinements could further enhance the assay's versatility, such as extending its sensitivity to etherbased PU cleavage markers or incorporating alternative fluorophores, enzymatic cascades, and detection modalities. Integration with emerging technologies—such as artificial intelligence–assisted enzyme design, automated liquid handling, and ultra-high-throughput microfluidics— could further enhance screening efficiency and success rates.

Ultimately, our HTS assay for PEA-PU degradation provides a robust, scalable, and mechanistically precise tool for accelerating the discovery and engineering of PU-degrading enzymes. By utilizing a structurally realistic substrate, the assay ensures that identified hits exhibit industrially relevant depolymerization activity, effectively bridging the gap between laboratory discovery and real-world PU waste degradation. This approach holds significant promise for advancing sustainable PU waste management, a critical step toward achieving a circular plastics economy.

4. Reference

1. R.C. Thompson, Y. Olsen, R.P. Mitchell *et al.*, Twenty years of microplastic pollution research—what have we learned, *Science* 386 (2024) eadl2746.

2. J. Liang, Y. Yang, Q. Zhou *et al.*, Unraveling the threat: microplastics and nanoplastics' impact on reproductive viability across ecosystems, *Sci. Total Environ.* 913 (2024) 169525.

3. V. Nava, A. Berton, A. Boggero *et al.*, Plastic debris in lakes and reservoirs, *Nature* 619 (2023) 317–322.

4. J. Lei, Q. Li, X. Zheng *et al.*, Microplastic environmental behavior and health risk assessment: a review, *Environ. Chem. Lett.* 22 (2024) 1–29.

5. Z. Liu, Y. Luo, Y. Liang *et al.*, Anionic nanoplastic contaminants promote Parkinson's-disease–associated α-synuclein aggregation, *Sci. Adv.* 9 (2023) eadi8716.

6. H. Zha, M. Liu, X. Wu *et al.*, Foodborne and airborne polyethersulfone nanoplastics respectively induce liver and lung injury in mice: comparison with microplastics, *Environ. Int.* 183 (2024) 108350.

7. H. Huang, X. Zhang, W. Li *et al.*, Microplastics in the bloodstream can induce cerebral thrombosis by causing cell obstruction and lead to neurobehavioral abnormalities, *Sci. Adv.* 11 (2025) eadr8243.

8. B. Zhao, H. Wang, J. Liu *et al.*, The potential toxicity of microplastics on human health, *Sci. Total Environ.* 912 (2024) 168946.

9. J. Drzeżdżon, J. Datta, Advances in the degradation and recycling of polyurethanes: biodegradation strategies, MALDI applications, and environmental implications, *Waste Manag.* 198 (2025) 21–45.

10. Z. Li, C. Zhang, J. Chen *et al.*, Structure-guided engineering of a versatile urethanase improves its polyurethane depolymerization activity, *Adv. Sci.* 12 (2025) 2416019.

11. D. Simón, P. Hidalgo, F. Pérez *et al.*, Recycling of polyurethanes from laboratory to industry: a journey towards the sustainability, *Waste Manag.* 76 (2018) 147–171.

12. G. Rossignolo, G. Malucelli, A. Lorenzetti, Recycling of polyurethanes: where we are and where we are going, *Green Chem.* 26 (2024) 1132–1152.

13. N. Gama, A. Ferreira, A. Barros-Timmons, Polyurethane recycling through acidolysis: current status and prospects for the future, *J. Polym. Environ.* 32 (2024) 4777–4793.

14. J. Liu, Y. Li, Y. Zhang *et al.*, Biodegradation and up-cycling of polyurethanes: progress, challenges, and prospects, *Biotechnol. Adv.* 48 (2021) 107730.

15. A. Raczyńska, A. Góra, I. André, An overview on polyurethane-degrading enzymes, *Biotechnol. Adv.* 68 (2024) 108439.

16. S.P. Katnic, F.M. de Souza, R.K. Gupta, Recent progress in enzymatic degradation and recycling of polyurethanes, *Biochem. Eng. J.* 204 (2024) 109363.

17. A. Magnin, E. Pollet, L. Avérous, Characterization of the enzymatic degradation of polyurethanes, *Methods Enzymol.* 648 (2021) 317–336.

18. H. Puetz, D. Yamamoto, L.M. Blank *et al.*, Validated high-throughput screening system for nylon-depolymerizing enzymes, *ACS Sustain. Chem. Eng.* 11 (2023) 15513–15522.

19. C. Acevedo-Rocha, M. Pérez-Gallego, F.H. Arnold *et al.*, Artificial, biomimetic and hybrid enzymes: general discussion, *Faraday Discuss.* 252 (2024) 354–386.

20. A. Magnin, E. Pollet, L. Avérous, Evaluation of biological degradation of polyurethanes, *Biotechnol. Adv.* 39 (2020) 107457.

21. M. Cregut, M. Bedas, M.J. Durand, G. Thouand, New insights into polyurethane biodegradation and realistic prospects for the development of a sustainable waste recycling process, *Biotechnol. Adv.* 31 (2013) 1634–1647.

22. J.C. Biffinger, J.T. Wertz, D.T. Fox *et al.*, The applicability of Impranil DLN for gauging the biodegradation of polyurethanes, *Polym. Degrad. Stab.* 120 (2015) 178–185.

23. J. Liu, X. Wang, Y. Li, Y. Jiang, Y. Zhang, Biodegradation of polyester polyurethane by *Cladosporium* sp. P7: evaluating its degradation capacity and metabolic pathways, *J. Hazard. Mater.* 448 (2023) 130776.

24. A. Magnin, E. Pollet, L. Avérous, Isolation and characterization of different promising fungi for biological waste management of polyurethanes, *Microb. Biotechnol.* 12 (2019) 544–555.

25. W. Sikorska, G. Janowska, W. Musial *et al.*, Synthesis and physicochemical properties of new (bio)degradable poly(ester-urethane)s containing polylactide and poly[(1,4-butylene terephthalate)-co-(1,4-butylene adipate)] segments, *Polymer* 52 (2011) 4676–4685.

26. H. Lu, D.J. Diaz, N.J. Czarnecki *et al.*, Machine learning–aided engineering of hydrolases for PET depolymerization, *Nature* 604 (2022) 662–667.

27. Z. Jiang, Z. Li, L. Wang, H. Lu, Novel polyurethane-degrading cutinase BaCut1 from *Blastobotrys* sp. G-9 with potential role in plastic bio-recycling, *J. Hazard. Mater.* 472 (2024) 134493.

333   28. A.B. Filip, J.E. Hardy, T.H. Jones *et al.*, Accuracy of a glycerol dehydrogenase assay for
334   ethylene glycol detection, *J. Med. Toxicol.* 19 (2023) 362–367.

335   29. M. Gimeno-Pérez, X. Chen, R. Mezzenga, A coupled ketoreductase–diaphorase assay for the
336   detection of polyethylene terephthalate–hydrolyzing activity, *ChemSusChem* 15 (2022)
337   e202102750.

338
339
340

5. **Materials and Methods**

5.1. Materials

Unless otherwise stated, all reagents were of analytical grade and used as supplied. Hydroxyl-terminated poly
(ethylene adipate) (PEA, Mn ≈ 1000 g/mol, CAS 24938-37-2), 4,4′-methylenebis (phenyl isocyanate) (MDI,
CAS 101-68-8), and anhydrous N, N-dimethylformamide (DMF, CAS 68-12-2) were purchased from Aladdin
Industrial Corporation (Shanghai, China).

Resazurin (≥98%, CAS No. 550-82-3) and Diaphorase from *Clostridium kluyveri* (3.0-20.0 units/mg protein,
CAS No. 9001-18-7) were purchased from Sigma-Aldrich (St. Louis, MO, USA). β-Nicotinamide adenine
dinucleotide (NAD$^+$, >98%, CAS No. 53-84-9) was obtained from Roche Diagnostics GmbH (Mannheim,
Germany).

The polyurethane-degrading enzymes ICCM and BaCut1 were constructed as described: ICCM based on
engineered LCC variants (F243I/D238C/S283C/N246M) per Nature 2022 (DOI:10.1038/s41586-022-04599-
z), and BaCut1 based on the reported sequence from *Blastobotrys* sp. G-9
(DOI:10.1016/j.jhazmat.2024.134493), was codon-optimized, synthesized by Tsingke Biotechnology Co., Ltd.
(Beijing, China), and cloned into the pET32a expression vector. Glycerol dehydrogenase (GldA) from
Enterobacter aerogenes was recombinantly expressed in-house in *E. coli* BL21(DE3) using a pET32-based
vector and purified by Ni–NTA affinity chromatography as described in Section 5.2.3.

All other routine chemicals, buffer components (e.g., Tris base, NaCl, imidazole), and consumables were
purchased from Sigma-Aldrich unless otherwise stated. Ultrapure water (18.2 MΩ·cm) was prepared using a
Milli-Q® Integral water purification system (Merck Millipore, USA). Black, flat-bottom, low-volume 96-well
plates were obtained from Corning® (Corning, NY, USA) for fluorescence measurements.

5.2. Methods

5.2.1. Synthesis of PEA-PU Films

PEA was vacuum dried at 120 °C for 1 hour prior to use. In a nitrogen-purged three-neck flask, equimolar
amounts of PEA and MDI (NCO: OH = 1:1) were dissolved in anhydrous DMF (10% w/v). The reaction mixture
was stirred at 70 °C for 1 hour under a dry nitrogen atmosphere. The resulting viscous prepolymer was cast into

a PTFE mold and vacuum-dried at 60 °C for 24 hours, yielding uniform transparent films of approximately 0.2
mm thickness. Films were stored in a desiccator prior to use.

5.2.2. Structural and Thermal Characterization

^{1}H NMR spectra were recorded on a Bruker Avance III 400 MHz spectrometer using DMSO-d_6 as solvent.
Chemical shifts were referenced to the residual solvent peak at δ 2.50 ppm.

ATR-FTIR spectra were obtained using a Bruker Vertex 70V FTIR spectrometer coupled with a Hyperion II
microscope (Bruker, Germany), operated at 4 cm^{-1} resolution with 32 scans per sample.

Differential scanning calorimetry (DSC) measurements were performed on a DSC 2500 (TA Instruments, New
Castle, DE, USA). Approximately 5 mg of each PEA-PU film was sealed in an aluminium Tzero™ pan with a
matching lid. Samples were equilibrated at –50 °C for 1 min, heated to 200 °C at 10 °C min^{-1}, held for 1 min,
cooled to –50 °C at the same rate, and then reheated to 200 °C. Thermograms from the second heating scan
were used for analysis to remove thermal-history effects. The glass-transition temperature (Tg) was determined
from the midpoint of the heat-capacity step in the second heating trace.

SEM analysis was conducted to assess surface morphology before and after enzymatic degradation. Samples
were sputter-coated with a thin layer of platinum to ensure conductivity. Imaging was performed using a Hitachi
SU3900 Scanning Electron Microscope at an accelerating voltage of 10.0 kV, a working distance of 5.4 mm,
and a magnification of ×500 under secondary electron (SE) mode. Scale bars were set to 100 μm.

5.2.3. Protein Expression and Purification

The enzymes GldA, ICCM, and BaCut1 were recombinantly expressed and purified for this study. The
corresponding genes for each enzyme were cloned into the pET32a(+) expression vector, which incorporates
an N-terminal His$_6$-tag for affinity purification. The resulting plasmids were transformed into E. coli BL21
(DE3) host cells.

For protein expression, cultures were grown in Luria-Bertani (LB) medium containing 100 μg/mL ampicillin at
37 °C with vigorous shaking until the optical density at 600 nm (OD$_{600}$) reached 0.6–0.8. Protein synthesis was
then induced with a final concentration of 0.2 mM isopropyl β-D-1-thiogalactopyranoside (IPTG), and the
cultures were further incubated at 16 °C for 16–20 hours.

After incubation, cells were harvested by centrifugation (4,000 × g, 30 min, 4 °C), and the cell pellet was
resuspended in lysis buffer (50 mM Tris-HCl, pH 8.0, 150 mM NaCl). The cells were disrupted by sonication
on ice, and the crude lysate was clarified by high-speed centrifugation (30,000 × g, 30 min, 4 °C) to remove
cell debris.

The clarified supernatant was loaded onto a Ni Sepharose 6 Fast Flow affinity column (Cytiva) pre-equilibrated
with the lysis buffer. The column was washed with the same buffer containing 20 mM imidazole to remove
non-specifically bound proteins. The target His-tagged protein was subsequently eluted using a buffer
containing 300 mM imidazole. The eluted fractions were desalted and concentrated using Amicon® Ultra-15
centrifugal filters (10 kDa MWCO, Merck Millipore). The purity of the final protein samples was confirmed by

SDS-PAGE, and their concentrations were determined spectrophotometrically at 280 nm using a NanoDrop™
2000 spectrophotometer (Thermo Fisher Scientific).

5.2.4. Enzymatic Degradation of PEA-PU Films

405 PEA-PU films were cut into 0.8 cm × 0.8 cm squares. Each film sample was incubated in 1.0 mL of 50 mM
406 Tris–HCl buffer (pH 8.0) containing ICCM (13.95 μg/mL) or BaCut1 (125 μg/mL) at their respective optimal
407 temperatures (70 °C and 37 °C) for 36 hours. Control samples lacked enzyme. Reaction supernatants were
408 collected for product analysis.

5.2.5. Chromatographic Analysis of Degradation Products

To validate the enzymatic degradation of PEA-PU films, the resulting hydrolysis products were detected using
gas chromatography and high-performance liquid chromatography.

Gas Chromatography–Flame Ionization Detection (GC-FID)

Ethylene glycol (EG) in the enzymatic degradation supernatants was analyzed by a third-party analytical
laboratory using a Shimadzu GC system equipped with a flame ionization detector (FID). EG was detected at a
retention time of approximately 4.73 minutes. Quantification was based on an external standard calibration
curve (5–20 ppm), which showed excellent linearity ($R^2 > 0.998$).

High-Performance Liquid Chromatography (HPLC)

Adipic acid (AA) was analyzed using a Thermo Scientific Vanquish Core HPLC system (Thermo Fisher
Scientific, Germany) equipped with a Shim-pack GIST C18 AQ column (3 μm, 150 mm × 4.6 mm; Shimadzu,
Japan). The mobile phase consisted of 0.1% trifluoroacetic acid (TFA) in water (solvent A) and acetonitrile
(solvent B). Gradient elution was performed as follows: 0–20 min, 5–95% B; 20–24 min, held at 95% B; 24–
25 min, ramped back to 5% B; followed by a 5-minute re-equilibration at 5% B. The flow rate was 1.0 mL/min,
the detection wavelength was set at 210 nm, and the injection volume was 10 μL. Quantification was based on
an external calibration curve (1–100 ppm), which showed excellent linearity ($R^2 > 0.999$).

5.2.6. Coupled Fluorescence Assay for EG Detection

A fluorescence-based coupled enzyme assay was developed to quantify ethylene glycol (EG) released from
PEA-PU degradation. Reactions were performed in black 96-well plates with a final volume of 200 μL. Each
reaction contained 50 mM Tris-HCl buffer (pH 8.0), 3 mM NAD^+, 10 μM resazurin, 0.3 U/mL diaphorase, 0.25
mg/mL GldA, and either EG standards or samples.

To construct the standard curve, EG standards (0.25–25 mM) were prepared in assay buffer and incubated at
room temperature. Fluorescence was monitored at Ex/Em = 535/588 nm using a Thermo Scientific Varioskan™
LUX microplate reader in kinetic mode for 180 minutes, with readings collected every 5 minutes. The
fluorescence rate (RFU/min) was plotted against EG concentration, yielding a linear regression with $R^2 \geqslant$
0.9995.

For experimental samples, 20 μL of degradation supernatant was added to 180 μL of assay buffer. Fluorescence
was recorded under identical conditions, and EG concentrations were interpolated from the standard curve. All
measurements were performed in triplicate.