Optimisation and validation of a rapid RP-HPLC method for budesonide quantification

from polymeric nanoparticles with application to stability and drug release studies

Giriprasath Ramanathan* [a][b], Masroora Hassan [a][b], Yury Rochev* [a][b]

[a] School of Physics, University of Galway, Galway, Ireland

[b] CÚRAM, Research Ireland Centre for Medical Devices, University of Galway, Galway *H91*

W2TY, Ireland

23 ***Corresponding authors**

24 Dr. Yury Rochev, yury.rochev@universityofgalway.ie

25 Dr. Giriprasath Ramanathan, giriprasath.ramanathan@universityofgalway.ie

Abstract

A rapid and reliable reversed-phase high-performance liquid chromatography (RP-HPLC) method for quantifying budesonide encapsulated in poly(lactic-co-glycolic acid) (PLGA)-based, layer-by-layer (LbL) coated nanoparticles is developed and validated in this study. Optimization using response surface methodology (RSM) with a central composite design (CCD) identified acetonitrile: water (80:20, v/v) as the optimal mobile phase, enabling efficient separation within 5 minutes at a flow rate of 0.34 mL/min and detection at 244 nm. Consistent with ICH Q2(R2) guidelines, the method demonstrates excellent linearity ($R^2 > 0.999$), precision (% RSD < 2 %), accuracy, specificity, and sensitivity (LOD: 0.04 µg/mL; LOQ: 1.2 µg/mL). The validated method was applied in comprehensive forced degradation studies under diverse stress conditions, including acidic, alkaline, oxidative, thermal, photolytic, and photostatic environments. The LbL coating offered significant protection for budesonide, resulting in less than 20 % degradation under thermal and photostatic stress. In contrast, degradation exceeded 75 % when exposed to alkaline and oxidative conditions, particularly in hydrated environments. These findings underscore the critical importance of nanoparticle design and environmental conditions in ensuring drug stability. Furthermore, in vitro release studies demonstrated a sustained release profile (20.6 % over 48 h), indicating potential for targeted colonic drug delivery. Overall, this study is the first to establish a validated HPLC method for drug-loaded, LbL-coated nanoparticles, providing a robust analytical platform for characterizing and evaluating the stability of nanoparticle-based drug delivery systems for inflammatory bowel disease, facilitating their clinical translation.

Keywords: Budesonide; RP-HPLC method; Method validation; Forced degradation study; Polymeric nanoparticles; Targeted drug delivery

1. Introduction

Inflammatory bowel disease (IBD), encompassing conditions like Crohn's disease and ulcerative colitis, continues to pose a considerable clinical challenge. Its chronic, relapsing course, coupled with persistent difficulties in achieving sustained, targeted drug delivery, makes effective management notably complex [1]. Standard oral formulations often get absorbed too early in the upper gastrointestinal (GI) tract, which can lead to notable side effects [2], This highlights the need for colon-targeted delivery systems that allow for localized drug release and help reduce systemic exposure.[3]. To address these limitations, researchers have widely investigated nanoparticle (NPs)-based drug delivery systems for their capacity to safeguard drugs during GI transit and enable targeted release at inflamed sites. Notably, layer-by-layer (LbL) coated poly(lactic-co-glycolic acid) (PLGA) NPs have emerged as a leading approach for colonic targeting, owing to their customizable architecture, surface charge tunability, and resilience to the pH and enzymatic fluctuations encountered throughout the GI tract [4]. These systems are distinguished by their modular design, which permits surface charge change and incorporating multiple functional layers. Such features enhance both their retention and responsiveness within the colonic environment. [5,6].

Budesonide (BUd) exhibits potent topical anti-inflammatory effects as a glucocorticoid and undergoes significant first-pass metabolism, making it well-suited for localized IBD therapy. Beyond IBD, BUd has also been employed in treating various clinical conditions, including asthma [7], allergic rhinitis [8], and eosinophilic esophagitis [9], owing to its potent local anti-inflammatory action and favourable pharmacokinetic profile. It is subject to premature absorption and degradation in the upper gastrointestinal tract, which restricts its effective delivery to the colon. [10]. The therapeutic success of BUd in ulcerative colitis hinges on overcoming GI barriers through the development of advanced colon-targeted delivery systems that enable localized, controlled release at the site of inflammation [11]. Although

advances have been made in formulation strategies, accurately quantifying BUd in these

complex NPs systems is still quite challenging. Standard reversed-phase high-performance

liquid chromatography (RP-HPLC) methods, which work fine for biological fluids or

conventional dosage forms, are often unsuitable for nanoparticulate matrices. This is mainly

because they rely on buffered mobile phases such as sodium dihydrogen phosphate (pH 3.2;

0.02 M) [10,12], phosphate buffer (pH 3.2–0.02 M) [13–16], ammonium formate buffer (pH

4.2, 5 Mm) in 0.1% formic acid [17], ammonium acetate (pH 3.2, 10 mM) [18,19], gradient

elution [20–24], and extended run time [15], making them inefficient or unsuitable for

analysing polymeric NPs systems. **(Table 1)**. Most of these methods have not been validated

for use with nanoparticle matrices, particularly when subjected to forced degradation or

during in vitro release studies.

From a pharmaceutical development and regulatory standpoint, method validation [25] is far

more than a routine procedure. It is fundamental for ensuring the reliability, specificity, and

reproducibility of analytical results throughout the product lifecycle. Without rigorous

validation, the integrity of data and subsequent decisions regarding product quality would be

compromised [26]. This is especially significant for NPs-based formulations, as they can

experience physical or chemical alterations during processing, storage, or passage through the

GI tract. Without a robust, stability-indicating analytical method [27,28], it becomes

challenging to differentiate between true drug degradation and potential artifacts introduced

by the analysis itself. This ambiguity can undermine the accurate assessment of formulation

performance and the true stability of the product over its shelf-life [29]. The method must not

only quantify total drug content but also effectively monitor in vitro drug release profiles

under simulated GI conditions. In these systems, interfering substances from the release

medium, polymers, or degradation products can impact baseline separation and peak

resolution. Therefore, an analytical method development followed by forced degradation

studies are indispensable tools in pharmaceutical development, enabling the assessment of

manufacturing changes in drug quality and comparability, despite limited regulatory guidance

on their standardized design and interpretation [30,31].

In this study, we designed to validate an RP-HPLC method tailored for quantifying BUd from

LbL-coated PLGA NPs. The approach was kept isocratic, buffer-free, and rapid and fully

validated under ICH Q2(R2) guidelines. The method was evaluated through forced

degradation and applied to in vitro drug release studies to quantify BUd under stress and

release from NPs efficiently for screening formulations in colon-targeted nanoparticle

systems. A schematic overview of the study design, highlighting the RP-HPLC method

optimization, validation, and its application to BUd NPs analysis, is presented in **Fig. 1**.

Accordingly, establishing a robust, validated RP-HPLC method for BUd is not only crucial

for nanoparticle formulations but also for wider analytical and clinical applications where

precise drug quantification is required.

2. Experimental section

2. 1. Materials

High molecular weight hyaluronic acid (HMW-HA) (Mw 1250–1500 kDa) was purchased

from Contipro (Czech Republic). It was produced biotechnologically through the

fermentation of a non-haemolytic *Streptococcus* sp. strain and stored at 2–8 °C. Poly(D,L-

lactide-co-glycolide) (PLGA; Resomer® RG 504 H; 50:50 lactide:glycolide ratio, Mw 38–54

kDa, amorphous) was obtained from Merck (Germany) and stored at 2–8 °C. Polyvinyl

alcohol (PVA; Mw 13–23 kDa), poly-L-lysine (PLL; Mw 150–300 kDa, 0.1% w/v in water,

synthetic origin), dichloromethane (DCM), sodium phosphate monobasic (MW 138.0),

sodium phosphate dibasic (MW 268.0), potassium chloride (MW 74.5), hydrochloric acid,

sodium hydroxide, hydrogen peroxide (H_2O_2), and HPLC grade solvents (acetonitrile

(ACN), methanol (MeOH), ethanol (EtOH), and water (H_2O)) were also sourced from Merck.

PLL was stored at room temperature. Budesonide (BUd) (MW 430.54 g/mol, ≥97 % purity)

was bought from Thermo Scientific Chemicals (USA) and used as the model drug. HPLC-

grade solvents were used for all analytical studies and mobile phase preparation. All other

reagents and chemicals were of analytical grade and purchased from Merck unless otherwise

specified.

2. 2. Instrumentation

Chromatographic analyses were performed using a Shimadzu Prominence-i LC-2023 Plus

HPLC system (Shimadzu, Japan), equipped with a quaternary pump, inline degasser, auto-

sampler, column oven, sample cooler, and UV detector. Data collection, chromatogram

processing, and peak integration were managed through Lab solutions software (version 5.57,

Shimadzu, Japan). Experimental design, response surface modelling, and calculations

involving the desirability function were performed with Design Expert® software (version

13, Stat-Ease Inc., Minneapolis, MN, USA). Particle size, polydispersity index (PDI), and

zeta potential were measured by dynamic light scattering (DLS) using a Lite Sizer 500

(Anton Paar). For microstructural analysis of the particles, scanning electron microscopy

(SEM) was conducted with a Hitachi S-4700 EDX.

2. 3. Chromatographic conditions

Chromatographic separation was performed using a Kinetex® C18 column (100×4.6 mm, 5

µm particle size, 100 Å pore size; Phenomenex, USA) operating under isocratic conditions.

Response surface methodology (RSM) with a central composite design (CCD) was used for

preliminary optimization in phase I: MeOH: H_2O mixtures (70:30, 75:25, and 80:20, v/v)

served as the mobile phase. Flow rates tested included 0.375, 0.400, and 0.425 mL/min, and

the column temperature was maintained at 30 °C. The injection volume was set at 10 µL

throughout. UV detection occurred at a wavelength of 244 nm. Method refinement and

response optimisation phase II: ACN: H_2O (80:20, v/v) was selected as the mobile phase. The

flow rates assessed were 0.34, 0.35, and 0.36 mL/min, while injection volumes of 5, 10, and

15 µL were examined. The column temperature was kept at 40 °C, and UV detection was

performed at 242 nm. Across all experiments, mobile phases were filtered through

polytetrafluoroethylene (PTFE) membrane filters (0.45 µm pore size, 47 mm diameter;

Agilent Technologies, USA) and degassed by ultra-sonication. The auto-sampler temperature

was held at 4 °C for all runs.

2. 4. Preparation of stock solutions, calibration standards, and RSM working solutions

A primary stock solution of BUd (1000 µg/mL) was prepared by accurately weighing the

drug and dissolving it in ACN. Serial dilutions were then performed using ACN and H_2O,

both filtered through 0.45 µm PTFE membranes, to obtain calibration standards at

concentrations of 1 to 200 µg/mL. These standards were used in the calibration curve

required for method validation. For chromatographic method optimization employing RSM-

CCD, a BUd (100 µg/mL) working solution was freshly prepared and utilized in all

experimental runs. To systematically assess the influence of solvent composition as a

categorical factor during optimization, three organic solvents (ACN, MeOH, and EtOH) were

used to dissolve BUd (100 µg/mL) prior to RSM-CCD experiments. All dilutions and

preparations employed freshly prepared, degassed, and membrane-filtered (0.45 µm) to

maintain consistency and ensure analytical reliability.

2. 5. Selection and validation of key chromatographic performance parameters

The accuracy, precision, and reliability of the developed RP HPLC method were thoroughly

assessed under ICH Q2(R2) guidelines [25]. Analytical performance parameters namely, peak

area for quantification, retention time (Rt) for consistent analyte identification, the number of

theoretical plates (N) as a reflection of column efficiency, tailing factor (T) for peak

symmetry, resolution (Rs) for adequate analyte separation, and capacity factor (k') to describe

retention were systematically evaluated. Each parameter was measured against established

criteria grounded in standard chromatographic benchmarks. The method's suitability and

robustness were validated comprehensively under the final chromatographic conditions,

which were optimized via the second phase of RSM-CCD.

2. 6. Experimental design and statistical analysis

2. 6. 1. CCD for method optimisation

A design of experiments (DOE) strategy was utilized to explore the effects of key

chromatographic variables on method performance, conducted in two sequential stages.

These stages, phase I (screening and preliminary optimization) and phase II (method

refinement and response optimization), were performed using a CCD framework within

Design Expert® software (version 13, Stat-Ease Inc., Minneapolis, USA) [32,33].

Throughout both phases, Rt and PA were chosen as the primary response variables to evaluate

the efficiency and sensitivity of the method.

In phase I, the composition of the mobile phase (MeOH:H_2O) and the flow rate (mL/min)

were evaluated as numerical factors, while the solvent used for drug dissolution (ACN,

MeOH, EtOH) was treated as a categorical variable. In phase II, the method was further

refined by adjusting both the flow rate (mL/min) and injection volume (µL), with the same

categorical solvent variable.

2. 6. 2 Model development and statistical evaluation

Each phase involved 42 experimental runs analysed using RSM. Analysis of variance

(ANOVA) was employed to assess statistical significance, model adequacy, and predictive

capability of the final optimised chromatographic conditions. **Table 2** summarises the

independent variables and their levels used in the CCD, and the relationship between coded

and actual factor values was established using the standard equation.

$x_i = \frac{X_i - X_0}{\Delta x}$ (1)

Where x_i is the dimensionless coded value of the i^{th} independent variable, X_i is the actual

value of the independent variable, X_0 is the actual value at the centre point, and Δx is the step

change value of the variable. For each DOE experiment, the relationship between the

independent variables and the responses (R) was modelled using the following general form:

$R_{1,}R_2, = \beta_0 + \beta_1 A + \beta_2 B + \beta_3 C_1 + \beta_4 C_2 + \beta_{12} AB + \beta_{13} AC_1 + \beta_{14} AC_2 + \beta_{23} BC_1 + \beta_{24} BC_2 + \beta_{11} A^2 + \beta_{22} B^2$ **(2)**

(for Phase I) and

$R_{3,}R_4, = \beta_0 + \beta_1 D + \beta_2 E + \beta_3 F_1 + \beta_4 F_2 + \beta_{12} DE + \beta_{13} DF_1 + \beta_{14} DF_2 + \beta_{23} EF_1 + \beta_{24} EF_2 + \beta_{11} D^2 + \beta_{22} E^2$ **(3)**

(for phase II)

Equations (2) and (3) represent the second-order polynomial models developed to predict the

chromatographic responses under different experimental conditions for Phase I and Phase II,

respectively. In these models, $R\square$ and $R\square$ represent Rt, while $R\square$ and $R\square$ correspond to PA,

denoting the predicted responses for the two phases. The coefficients β represent the linear,

interaction, and quadratic effects of the independent variables. For Phase I [Equation (2)], the

independent variables A (mobile phase composition), B (flow rate), and categorical solvent

variables $C\square$ and $C\square$ (ACN, MeOH, and EtOH) were used. Similarly, for Phase II [Equation

(3)], the variables included D (flow rate), E (injection volume), and $F\square$ and $F\square$ (ACN,

MeOH, and EtOH). The detailed levels and coding of these variables are presented in **Table 2**

[33,34].

2. 7. Method validation parameters

2. 7. 1. Specificity

Chromatographic conditions were optimized for specificity and selectivity to ensure

unambiguous analyte quantification in the presence of excipients, degradation products, and

matrix interferences. Two separate experimental strategies were employed: matrix

interference and forced degradation studies.

2. 7. 1. 1. Matrix interference

Specificity was assessed by injecting a series of samples, mobile phase (blank), placebo, NPs

without BUd (Bare NPs), standard BUd solution (BUd), BUd -loaded NPs (BUd NPs), and

BUd NPs subjected to forced degradation. Each sample was analysed under optimized

chromatographic conditions to verify the absence of interfering peaks at the BUd retention

time. Peak purity was evaluated using photodiode array (PDA) detection, and contour plots

(200–300 nm) were generated to confirm spectral homogeneity and rule out co-elution of

degradation products. This ensured the method could selectively quantify BUd in complex

nanoparticle matrices, even under stressed conditions [33,35].

2. 7. 1. 2. Forced degradation study

To assess the stability-indicating properties of the developed RP-HPLC method, forced

degradation studies were conducted in line with the ICH Q1A(R2) guidelines. These

experiments examined the chemical stability of both free BUd and BUd NPs under a range of

stress conditions to identify possible degradation products and validate the specificity of the

method. Stress conditions applied included hydrolytic (acidic and basic), oxidative, thermal,

photolytic, and photostatic degradation. For each condition, the following sample groups

were prepared as untreated BUd NPs as NPs control (NC), BUd NPs at 50 °C subjected to

the respective stress (N50), free BUd at 50 °C subjected to the respective stress (D50), free

BUd at 37 °C subjected to the respective stress (D37), BUd NPs subjected to photolytic and

photostatic (NUV and NDL), and BUd subjected to photolytic and photostatic (DUV and

DDL) as illustrated in **Fig. 7(a)**. Hydrolytic degradation was induced by treating samples

with 0.1 N and 1 N HCl or NaOH at 50 °C for 1 h. Oxidative degradation was performed

using 30 % H_2O_2 at 50 °C for 1 h. For thermal degradation, samples underwent dry

heating at 50 °C for 1 h without additional reagents. BUd and Bud NPs were suspended in

HPLC grade water in transparent glass vials were exposed to UV-C light (254 nm) at an

intensity (13.46 W·h/m²) for 1 h and visible light from an ET17 tube lamp (15.8 million

lux·h) for 1 h for photolytic and photostatic degradation, respectively. Control samples, in

both cases, were protected from light in order to clearly isolate and assess the effects of

illumination. Following stress treatments, all samples were neutralized when necessary,

freeze-dried, redissolved in a defined volume of ACN, filtered through a PTFE membrane

(0.22 µm), and analysed using the validated RP-HPLC method. This systematic approach to

sample preparation enabled precise quantification of BUd and reliable detection of

degradation products across all tested conditions [33,34].

2. 7. 2. Linearity

Linearity was assessed by analysing standard BUd solutions across a concentration range of

1–200 µg/mL. A calibration curve was generated by plotting peak area against concentration,

followed by linear regression analysis to obtain the correlation coefficient (r) and coefficient

of determination (r^2). These results confirmed that the method yields responses directly

proportional to the analyte concentration [35].

2. 7. 3. .Accuracy

Method accuracy was evaluated through recovery studies conducted at three concentration

levels (100, 93.3, and 86.6 %) of the target concentration, which corresponded to theoretical

values of 187.5, 175.0, and 162.5 µg/mL, respectively. These BUd concentrations were

prepared volumetrically by mixing two stock solutions, namely vial A (200 µg/mL) and vial

B (150 µg/mL), in ratios of 750:250, 500:500, and 250:750 µL. Each concentration level was

analysed in triplicate. Accuracy was determined by calculating the mean recovery, standard

deviation (SD), and percent relative standard deviation (% RSD). The acceptance criteria

were set at 98 to 102 % recovery and ≤ 2 % RSD [14,36].

2. 7. 4. .Precision

The precision of the developed RP-HPLC method was assessed by evaluating repeatability

(intra-day) and intermediate precision (inter-day). Repeatability was determined by analysing

six replicates of a BUd (200 µg/mL) standard solution under identical conditions within the

same day. Intermediate precision was evaluated by repeating this procedure on the

subsequent day, using the same instrumentation and methodological parameters. Precision

was reported as the % RSD ($\leq$ 2 %) considered acceptable [33,34].

2. 7. 5. Sensitivity

The limit of detection (LOD) and limit of quantification (LOQ) of the developed method

were established using the signal-to-noise (S/N) approach, with approximate ratios of 3:1 and

10:1, respectively. , A statistical assessment was conducted by employing the standard

deviation of the response (σ) and the slope of the calibration curve (S), utilizing the following

equations:

$\text{LOD} = 3.3 \times \sigma / S$ **(4)**

$\text{LOQ} = 10 \times \sigma / S$ **(5)**

LOD indicates the lowest concentration of BUd that can be reliably detected, and LOQ

corresponds to the minimum concentration that can be quantified with acceptable precision

and accuracy [14,34].

2. 7. 6. Robustness

Robustness was assessed by making small, intentional adjustments to key chromatographic

parameters, in order to determine how well the method withstood typical operational changes.

Parameters examined were flow rate ($\pm$ 0.01 mL/min), injection volume ($\pm$ 5 µL), column

temperature ($\pm$ 10 °C), and detection wavelength ($\pm$ 2 nm). Each modified condition was

analysed twice, and the effects on retention time, peak area, and overall system suitability

were evaluated. Consistency in chromatographic performance across these variations was

used as evidence of the method's robustness [33].

2. 7. 7. System Suitability

System suitability was evaluated to confirm reliable performance of the RP-HPLC system

before analysing samples. Six replicate injections of a standard BUd solution (100 µg/mL)

were performed under the optimized chromatographic conditions. Key chromatographic

parameters as Rt, PA, number of theoretical plates (N), tailing factor (T), resolution (Rs), and

capacity factor (k') were carefully recorded. The % RSD for both peak area and retention

time was calculated to assess repeatability and instrument stability [37].

2. 8. Application of the validated RP-HPLC method to nanoparticle formulation

2. 8. 1. Synthesis of budesonide-loaded nanoparticles (BUd NPs)

The HA-functionalized, BUd NPs were prepared using a previously established co-solvent

and LbL assembly method with minor modifications to incorporate the drug was

schematically illustrated in **Fig. 2(a)** [38]. Briefly, PLGA (2 % w/v) and BUd (5 mg, pre-

dissolved in EtOH)) were dissolved in a 3:1 (v/v) mixture of DCM and EtOH. This organic

phase was added drop-wise into 1 % (w/v) aqueous PVA under probe sonication

(8□/2□s:on/off, 120□s total) to form an oil-in-water emulsion, followed by overnight

stirring at room temperature for solvent evaporation and nanoparticle formation. The

resulting BUd -loaded PLGA NPs (BUd-PLGA NPs) were collected by centrifugation

(10,350 rpm, 15 min), washed, and subjected to sequential surface modification via

electrostatic adsorption. For the first coating step, BUd-PLGA NPs were incubated in PLL

(0.1 % (w/v) solution for 12 h, enabling cationic PLL chains to adsorb onto the negatively

charged PLGA surface, forming BUd-PLGA-PLL NPs. These were subsequently incubated in

HMW-HA (0.2 % (w/v)) solution for 4 h, allowing electrostatic attraction between the

anionic HA and the cationic layer (PLL) to yield the final BUd-PLGA-PLL-HA NPs (BUd

NPs). The completed NPs were lyophilized and stored under desiccated conditions until

further use.

2. 8. 2. Determination of drug loading in nanoparticles

To determine drug loading, approximately 1 mg of lyophilized BUd NPs was dissolved in 1

mL of ACN. The sample was vortexed thoroughly to ensure complete disruption of the NPs

and release of the encapsulated drug into the solvent. The resulting solution was then filtered

using a 0.22 µm syringe filter. The clear filtrate was subsequently analysed using the

validated RP-HPLC method described previously. BUd content in the nanoparticle sample

was quantified by referencing a standard calibration curve. Theoretically, 1 mg of BUd NPs is

expected to contain 200 µg of BUd.

2. 8. 3. In vitro drug release studies from BUd NPs

The in vitro release profile of BUd from BUd NPs was evaluated using a dialysis-based

approach that replicates the sequential pH changes of the GI. For these experiments, Slide-A-

Lyzer® MINI Dialysis Devices (10 kDa MWCO, 50 mL tube) were employed, as outlined in

Fig. 8(a). Precisely 1 mg of lyophilized NPs was weighed, dispersed in 1 mL of HPLC grade

water, and loaded into the sample chamber of each dialysis unit. The devices were immersed

in 45 mL of pre-warmed release medium maintained at 37 □±□0.5 °C, with constant agitation

at 200 rpm. To mimic GI transit, the release study was performed under a stepwise pH

regimen. Initially, the dialysis units were incubated in simulated gastric fluid (SGF, pH 1.2)

for 1 h. This was followed by transfer to fresh, pre-warmed simulated intestinal fluid (SIF, pH

6.8) for 3 h. Subsequently, the medium was replaced with simulated colonic fluid (SCF, pH

7.4), and the release profile was monitored for up to 72 h. At predetermined time intervals (1,

2, 4, 8, 24, and 48 h), 1 mL samples were withdrawn from the external release medium,

immediately frozen, and lyophilized. The dried samples were then reconstituted in a known

volume of ACN to solubilize the released drug. Quantitative determination of BUd was

achieved using a validated RP-HPLC method. To maintain sink conditions, the sampled

volume was replaced with a fresh, pre-warmed buffer of the corresponding pH at each time

point [4].

3. Results and discussion

3. 1. Physicochemical properties of the BUd NPs

The drug (BUd) loaded NPs displayed progressive increases in particle size and stepwise surface charge reversal, confirming successful LbL assembly. The final formulation showed a mean hydrodynamic diameter of (496 ± 30 nm) with a PDI below 0.25 ± 0.02, indicating uniform size distribution. Zeta potential shifted from (-27.4 ± 3.0 mV) (uncoated) to (55.5 ± 3.1 mV) (PLL coated), and back to (−32.0 ± 2.4 mV) after HA deposition **(Fig. 2(b-f))**. The final size remained within the submicron range with a low PDI, indicating colloidal stability of the formulation with distinct surface charge transitions, further support sequential polymer deposition and colloidal stability [4,5,38].

3. 2. Morphological analysis of the BUd NPs

SEM analysis confirmed that BUd NPs exhibited a spherical and uniform morphology across different magnifications, with no signs of aggregation **(Fig. 2(g-i))**. The SEM morphology revealed that the BUd NPs were ranged from around 500 nm with monodisperse colloidal nature and observed particle sizes were consistent with DLS measurements [38,39].

3. 3. Optimization of the method using RSM-CCD

3. 3. 1. Phase I: Screening and preliminary optimization

In the initial phase, RSM-CCD was employed to screen key chromatographic factors influencing BUd quantification, specifically mobile phase composition, flow rate (numerical), and drug dissolution solvent (categorical). While MeOH-based systems provided acceptable retention and peak shape, they consistently caused higher back-pressure at elevated flow rates because of methanol's viscosity and hydrogen bonding with water [40]. Additionally, dissolving BUd in MeOH or EtOH led to variable peak areas and poor reproducibility. In contrast, acetonitrile markedly improved BUd solubility and signal response, attributed to its lower viscosity, weaker hydrogen bonding, and stronger elution strength [41]. These

experimental findings (R_1, R_2, and R_{2a}), summarized in **Table S1**, supported the transition to

an acetonitrile-based system for Phase II optimization. Second-order polynomial models (Eq.

6 and 7) were generated using Design Expert software to predict retention time and peak area

in Phase I.

R_t = 4.77 − 1.14A − 0.32B + 0.04C[1] + 0.02C[2] + 0.07AB − 0.05AC[1] + 0.01AC[2] −

0.01BC[1] + 0.00BC[2] + 0.36A² + 0.018B²   **(6)**

R_a = 4798398.48 + 35788.33A − 305030.07B + 344475.42C[1] − 65612.94C[2] + 2600.47AB −

3270.67AC[1] − 14950.78AC[2] − 19336.59BC[1] + 8951.46BC[2] + 3711.89A² + 21354.56B² **(7)**

Where, A denotes mobile phase ratio, B is flow rate, and C[1] and C[2] represent solvent

categories. ANOVA analysis **(Table S3)** confirmed the model's significance with high F-

values (3919.94 for Rt and 1392.43 for PA) and p-values < 0.0001, indicating robust

predictability [32,33,42].

3. 3. 2. Phase II: Method refinement and response optimization

Building on Phase I findings, Phase II focused on optimizing flow rate and injection volume

under a fixed ACN:H$_2$O (80:20, v/v) mobile phase. The aim was to improve reproducibility,

signal intensity, and system stability while minimizing back-pressure. Lower flow rates

reduced system strain, and a 10 µL injection volume yielded strong, undistorted signals.

These trends aligned with the performance characteristics of the core-shell Kinetex C18

column (100 mm × 4.6 mm), known for high-efficiency separations at reduced pressure

[41]. Using Design Expert software, second-order polynomial models (Eq. 8 and 9) were

developed to predict retention time and peak area in Phase II.

R_t = 3.65 − 0.09D + 0.024E − 0.01F[1] + 0.00F[2] + 0.019DE − 0.00DF[1] − 0.01DF[2] −

0.01EF[1] − 0.01EF[2] + 0.01D² + 0.01E²   **(8)**

$R\square = 4022631.08 - 584187.37D + 1631072.04E + 122305.64F[1] - 167869.31F[2] +$

$89603.28DE - 101813.41DF[1] + 25899.09DF[2] + 83278.63EF[1] - 198018.31EF[2] -$

$202573.18D^2 - 374743.73E^2$ **(9)**

Where, D represents flow rate, E denotes injection volume, and F[1] and F[2] indicate solvent

categories. ANOVA results **(Tables S4)** showed significant model fits, with F-values of 21.17

for retention time and 10.62 for peak area ($p\square<\square0.0001$). These experimental findings (R_3,

R_4, and R_{4a}), were summarized in **Table S2**.

3. 3. 3. Influence of column temperature and PDA-based peak purity assessment

During method refinement, the effect of column temperature on detection wavelength and

spectral behaviour was evaluated. At 30 °C, BUd showed maximum absorbance at 244 nm,

while increasing the temperature to 40 °C caused a hypsochromic shift to 242 nm, likely due

to temperature-induced changes in the chromophore environment, consistent with

solvatochromic effects [41]. PDA-based peak purity analysis at both temperatures confirmed

spectral homogeneity **(Fig. 5d)**, ruling out degradation or co-elution. These results highlight

the importance of temperature and wavelength optimization in RP-HPLC, especially for

thermosensitive or lipophilic analytes.

3. 3. 4. Summary of optimized parameters

The method development and optimization strategy led to a finalized set of RP-HPLC

conditions suitable for the quantification of BUd. The optimized method employed a mobile

phase of ACN:H_2O (80:20, v/v), a flow rate of 0.34 mL/min, and an injection volume of 10

µL. The optimal detection wavelength was determined to be 242 nm at a column temperature

of 40 °C, and ACN was used as the solvent for dissolution of drug, because of its superior

solubilization properties and compatibility with the mobile phase. A Kinetex C18 column

(100 mm × 4.6 mm) was selected for its high efficiency and ability to operate at low back-

pressure.

3. 3. 5. Effect of variables in Phase I and Phase II

The relationship between the independent variables to understand factor interactions to get responses (R_1, R_2, R_3, and R_4) across both phases of method development using RSM-CCD was effectively generated from the empirical models (Equations 6–9). The responses (Rt and PA), for both Phase I and II are presented as two-dimensional contour plots, three-dimensional surface plots, and actual vs. predicted plots, using ACN as the categorical solvent was effectively depicted in **Fig. 3(a–f)** and **Fig. 4(a–f)**, respectively. Corresponding results for MeOH and EtOH as categorical solvents are provided in supplementary **Fig. S1 and S2**.

In Phase I, both flow rate and mobile phase composition significantly affected Rt) and PA. Rt decreased with increasing flow rate and acetonitrile content, while PA peaked at intermediate flow rates with higher acetonitrile ratios. Acetonitrile showed superior solvent compatibility and system stability, supporting its selection for Phase II. The statistical robustness of the models was strong, with R^2/adjusted R^2 values of 0.993/0.991 for Rt (Eq. 6) and 0.998/0.997 for PA (Eq. 7). ANOVA confirmed model significance with a non-significant lack-of-fit, validating the models for prediction and optimization. [32].

In Phase II, flow rate and injection volume were evaluated using an ACN:H□O (80:20, v/v) system. Injection volumes above 10 µL caused minor peak broadening, while reduced flow rates slightly improved resolution without extending runtime. Although the effects on Rt and PA were less pronounced than in Phase I, the design identified an optimal balance between signal intensity and peak shape. The model for Rt (Eq. 8) showed moderate fit ($R^2 = 0.889$; adj $R^2 = 0.847$), while the PA model (Eq. 9) yielded $R^2 = 0.801$ and adj $R^2 = 0.725$. ANOVA confirmed statistical significance, with a non-significant lack-of-fit for Rt. The slightly higher lack-of-fit in the PA model may reflect injection-volume-related variability, as previously reported in low-volume LC systems. [33]. Collectively, the model-driven findings highlighted

the critical influence of mobile phase strength, flow rate, and injection volume on

chromatographic performance. Acetonitrile emerged as the preferred solvent, offering

superior dissolution, consistent elution, and low back-pressure. The validated models provide

confidence in the optimized parameters, supporting their use in method validation and

application to BUd NPs.

3. 5. Validation of RP-HPLC method

3. 5. 1. Specificity

The developed RP-HPLC method exhibited excellent specificity, with no interfering peaks at

the BUd retention time (3.75 ± 0.01 min) in blank and placebo chromatograms **(Fig. 5a).**

BUd consistently eluted as a sharp, symmetrical peak with stable Rt across all conditions.

Under basic and oxidative stress, minor additional peaks indicated degradation products.

PDA-based peak purity analysis confirmed spectral integrity, with purity angles below

threshold and contour plots (200 - 320 nm) showing no spectral overlap, except in stressed

samples, where distinct degradant peaks were observed **(Fig. 5(b) to (k)** [35]

3. 5. 2. Linearity

The method demonstrated excellent linearity over a broad concentration range (1–200

µg/mL) **(Fig. 6(a) and (b))**, covering the expected levels for in vitro release and degradation

studies. The calibration curve followed the equation $y = 20291.68 + 52847.85x$, with a

correlation coefficient (r) of 0.999 and r² of 0.998. All calibration points exhibited % RSD (<

2 %) **(Table S4)**, confirming accurate and reliable quantification across both low and high

concentration ranges. [14].

3. 5. 3. .Accuracy

Accuracy was evaluated through recovery studies at three spiking levels, yielding mean

recoveries between 98.1 to 99.7 % with % RSD values from 0.8 % to 1.4 %, confirming the

method's reliability in the presence of excipients **(Table 3(a))**. These results also demonstrate

that the method accurately quantifies BUd without loss or interference from sample handling

or dilution steps, ensuring recovery of the pure drug even in matrix-containing samples

[14,36].

3. 5. 4. .Precision

The method demonstrated excellent precision, confirmed through intra-day and inter-day

analyses. Intra-day repeatability, assessed from six replicate injections of BUd (200 µg/mL)

within a single day, yielded a concentration of $207 \pm 3\,\square\,\mu g/mL$ with a % RSD of 1.3 %. Inter-

day precision, evaluated over two consecutive days under the same conditions, resulted in

210 ± 3 µg/mL and a % RSD of 1.4 %. Both values fall well below the 2 % threshold

recommended by ICH guidelines, confirming the method's reproducibility for routine use and

long-term studies [33,34].

3. 5. 5. Sensitivity

The sensitivity of the method was established through both signal-to-noise ratio and statistical

calculations, yielding a LOD of 0.04 µg/mL and an LOQ of 1.2 µg/mL. These threshold

levels are also stated in the calibration curve **(Fig. 6(a)).** These values indicate that the

method can detect trace amounts of BUd, a critical requirement for early-stage drug release

studies and degradation profiling, where drug concentrations may fall below standard

detection thresholds. The ability to reliably detect and quantify low concentrations also

enhances the method's utility for pharmacokinetic sampling, drug release kinetics, and

stability-indicating assays [14,34].

3. 5. 6. Robustness

Robustness was established by introducing minor, deliberate variations in flow rate, injection

volume, column temperature, and detection wavelength **(Table 3(b))**. These changes caused

negligible shifts in retention time (% RSD < 0.6%) and peak area (% RSD < 2.0%),

confirming method reliability under typical operational fluctuations. For instance, increasing

the flow rate from 0.34 to 0.35 mL/min resulted in a marginal shift in retention time from

3.75 to 3.65 ± 0.01 min, with corresponding peak area variation within acceptable limits. No

significant changes were observed in peak symmetry or resolution. These results highlight the

method's robustness and operational tolerance, making it suitable for routine use under

standard laboratory conditions without risk of analytical drift [15,33].

3. 5. 7.System Suitability

System suitability testing showed high repeatability at 3.75 ± 0.01 min, with a peak area %

RSD of 0.2 %, confirming analytical repeatability **(Table 3(c))**. The theoretical plate count

(3088 ± 13) exceeded the recommended minimum of 2000, while the tailing factor was 1.22

± 0.00 (≥ 2.0), indicating efficient separation and peak symmetry. Moreover, the resolution

between critical peaks was 8.3 ± 0.7 (≥2.0), and the capacity factor (k') was 3.62 ± 0.01,

both falling within the optimal range for reversed-phase separations. These parameters

confirm the system's operational readiness and the method's reproducibility under optimized

conditions [37].

3. 6. Application of the validated RP-HPLC method to nanoparticle formulation

3. 6. 1. Forced degradation studies

Under acidic conditions **(Fig. 7(b) and (c))**, the BUd NPs retained only 48.7 ± 19.3 µg/mL

from an initial 209.3 ± 10.5 µg/mL, which translates to roughly 77 % degradation. In

comparison, the free drug undergo a moderate degradation labile because of hydrolysis and

maintained 102.3 ± 8.6 µg/mL. The substantial degradation observed in both formulations

was expected, given the documented sensitivity of PLGA esters to acidic environments and

the drug's proneness to hydrolytic degradation [43,44]. Although the Bud NPs degraded more

than the free drug, they still preserved a measurable amount of drug content, implying that

the PLL-HA layered structure provided some degree of buffering and steric protection. The

statistically significant difference between treated and untreated NPs ($p < 0.05$) further

supports the analytical method's capacity to indicate stability.

Exposure to alkaline conditions **(Fig. 7(b) and (d))** resulted in the most pronounced

degradation among all stress tests. Bud-NPs retained only 22.8 ± 15.2 µg/mL from their

initial 118.7 ± 2.8 µg/mL, translating to roughly 80.8 % degradation. However, by

comparison, the free drug underwent severe degradation to retain 59.7 ± 2.6 µg/mL drug,

indicates considerable instability. The pronounced degradation of BUd NPs under alkaline

conditions confirms their base labile nature, primarily because of PLGA hydrolysis that

compromises matrix integrity and accelerates drug release. While some drug persisted, likely

protected by the PLL and HA layers, the overall loss underscores the critical need for strict

pH control during storage and handling [36,44].

Thermal stress **(Fig. 7(b) and (e))** had minimal impact on both the formulation and the drug.

BUd NPs retained 117.9 ± 37.9 µg/mL compared to 118.7 ± 2.7 µg/mL in controls, and free

BUd remained stable at 203.2 ± 7.8 µg/mL versus 201.4 ± 14.8 µg/mL. Both BUd NPs and

free BUd exhibited considerable thermal stability under hydrated conditions, with negligible

drug loss and no apparent compromise to the PLGA matrix. These findings suggest the

formulation is robust and suitable for storage and transport under moderate temperature

conditions [33].

Oxidative degradation **(Fig. 7(b) and (f))** significantly affected BUd-NPs, with only 32.3 ±

20.1 µg/mL remaining from 119.9 ± 23.4 µg/mL (73 % loss), whereas the pure drug retained

190.2 ± 17.1 µg/mL. This differential response reflects the susceptibility of PLGA and

surface polymers to peroxidation and oxidative cleavage. These findings are relevant for IBD,

where reactive oxygen species are abundant, underscoring the need for oxidative stabilizers

in future formulations [33].

Photolytic degradation **(Fig. 7(b) and (g))** resulted in severe loss of BUd from both systems.

BUd NPs retained 20.0 ± 9.3 µg/mL, while free BUd dropped to 34.3 ± 0.2 µg/mL, each

reflecting 81 % degradation. The hydrated nanoparticle state likely increased permeability,

accelerating drug exposure to UV-induced damage. Similarly, photostatic degradation **(Fig.**

7(b) and (h)) under daylight exposure reduced BUd NP content to 29.4 ± 5.0 µg/mL, in

contrast to 112.0 ± 11.1 µg/mL in controls (74 % loss). These results confirm the loss of

photo protective functionality upon hydration and highlight the critical importance of post-

reconstitution handling guidelines and light-protective packaging [45].

3. 6. 2. Determination of drug loading in nanoparticles

Quantification of BUd in BUd NPs yielded a drug content of 169.9 µg/mg of NPs, closely

aligning with the theoretical loading of 200 µg/mg. The chromatographic analysis exhibited a

sharp, well-resolved peak with no interfering signals, confirming the method's selectivity for

accurately detecting the encapsulated drug within the nanoparticle matrix. The minimal

deviation between measured and expected values indicates consistent drug incorporation and

negligible loss during formulation. These findings not only confirm the successful loading of

BUd into the NPs, but also demonstrate that the drug remained chemically stable throughout

the fabrication and lyophilization process, an essential requirement for ensuring therapeutic

integrity during storage and subsequent application.

3. 6. 3. In vitro drug release studies from BUd NPs

The in vitro dissolution/release behaviour of free BUd and BUd encapsulated in NPs (BUd

NPs) was evaluated under simulated gastrointestinal conditions relevant to the IBD

environment. Data **(Fig. 8(b))** indicate that free BUd undergoes an extremely rapid and nearly

complete release, with over 94 % diffusing out in less than 4 h, regardless of pH. This rapid

dissolution and diffusion through the dialysis membrane likely accounts for the swift

systemic absorption, which could limit the drug's therapeutic effectiveness in the colon. In

contrast, the BUd NPs demonstrated a markedly controlled and sustained release profile

throughout the pH transitions, mimicking gastric, intestinal, and colonic environments. Only

about 7.6 % of the encapsulated drug was released in the acidic gastric phase (pH 1.8),

suggesting substantial nanoparticle stability under these conditions. As the medium's pH

increased, cumulative release from the NPs rose gradually, reaching approximately 15.6 % at

24 h and 20.6 % at 48 h. This sustained release aligns with the structural properties of the

PLGA matrix and the surface coatings of PLL and HA, which collectively regulate swelling,

degradation, and drug diffusion in a pH-dependent manner. Such a time-dependent release

mechanism, involving both diffusion and degradation, is characteristic of PLGA-based NPs

and is helpful for localized IBD therapy. By prolonging BUd exposure specifically in the

colon, the formulation enhances anti-inflammatory efficacy while minimizing systemic

corticosteroid side effects. Overall, these findings support the potential of BUd NPs as an

effective oral delivery system for targeted treatment of colonic inflammation in IBD patients

[4,39,46].

4. Conclusion

In this study, a rapid and robust RP-HPLC UV method was established, optimized, and

validated for quantifying BUd encapsulated within PLGA-based, LbL NPs using the RSM-

CCD approach. Notably, to the best of our knowledge, this represents the first validated RP-

HPLC UV method tailored specifically for drug-loaded, LbL-coated NPs. The optimized

method employed an acetonitrile/water mobile phase (80:20, v/v) under isocratic conditions,

achieving efficient separation in 5 minutes at a flow rate of 0.34 mL/min with a 10 μL

injection volume. The approach exhibited excellent drug solubility and a sharp peak response.

All ICH Q2(R2) validation criteria were successfully fulfilled, and the method applied to

forced degradation and in vitro release experiments. Although developed specifically for

LbL-coated nanoparticle formulations, the validated RP-HPLC method that meets all ICH

Q2(R2) criteria also holds strong potential for routine budesonide quantification across a

wide range of pharmaceutical products and clinical matrices owing to its robustness,

sensitivity, and buffer-free composition. Significantly, the LbL-coated nanoparticle matrix

afforded substantial protection to BUd, improving its stability against diverse stressors,

including hydrolytic, thermal, oxidative, photolytic, and photostatic challenges. Sustained

drug release was observed (20.6 % over 48 h) under simulated GI pH conditions, indicating

potential for targeted colonic delivery in inflammatory bowel disease therapy. Overall, this

validated analytical strategy offers a reliable platform for quality control and comprehensive

evaluation of advanced nanoparticulate drug delivery systems

Acknowledgements

This work was supported by a grant from the Science Foundation Ireland (SFI) and the

European Regional Development Fund (ERDF) under Grant number 13/RC/2073_P2. The

authors acknowledge the facilities of the Anatomy Imaging and Microscopy Facility at the

University of Galway and the technical assistance of Dr Éadaoin Timmins

https://imaging.universityofgalway.ie/imaging/).

CRediT authorship contribution statement

Giriprasath Ramanathan: Conceptualisation, Methodology, Investigation, Validation, Data

curation, Software, Formal analysis, Writing - Original Draft, Writing – review & editing,

Visualisation. **Masroora Hassan:** Conceptualisation, Investigation, Formal analysis, Writing

- Review & Editing. **Yury Rochev:** Conceptualisation, Writing – review & editing,

Resources, Supervision, Validation, Funding acquisition, Project administration.

Declaration of Competing Interest

The author declares that they have no conflict of interest.

References

[1] W. Liu, Z. Dong, K. Liu, Y. Lu, W. Wu, J. Qi, Z. Chen, Targeting strategies of oral nano-

delivery systems for treating inflammatory bowel disease, International Journal of

Pharmaceutics 600 (2021) 120461. https://doi.org/10.1016/j.ijpharm.2021.120461.

[2] W. Sun, Z. Li, X. Zhang, Q. Luo, L. Wei, C. Xiao, Biomaterial-based therapeutic

strategies for inflammatory bowel disease, Biomaterials 324 (2026) 123462.

https://doi.org/10.1016/j.biomaterials.2025.123462.

[3] Y. Zhang, K. Liu, Y. Zheng, J. He, Y. Huang, J. Gao, X. Chen, T. Wang, H. Zhou, J.

Wen, Q. Yu, K. Wang, B. Zhang, A dual-polysaccharide (carboxylated chitosan-

carboxymethyl cellulose sodium) gastrointestinal dynamic response in situ hydrogel for

optimized oral targeted inflammatory bowel disease therapy, Carbohydrate Polymers

363 (2025) 123704. https://doi.org/10.1016/j.carbpol.2025.123704.

[4] N.G. Kotla, R. Singh, B.V. Baby, S. Rasala, J. Rasool, S.O. Hynes, D. Martin, L.J. Egan,

P.K. Vemula, V.R. Jala, Y. Rochev, A. Pandit, Inflammation-specific targeted carriers for

local drug delivery to inflammatory bowel disease, Biomaterials 281 (2022) 121364.

https://doi.org/10.1016/j.biomaterials.2022.121364.

[5] N.G. Kotla, I.L.M. Isa, S. Rasala, S. Demir, R. Singh, B.V. Baby, S.K. Swamy, P.

Dockery, V.R. Jala, Y. Rochev, A. Pandit, Modulation of Gut Barrier Functions in

Ulcerative Colitis by Hyaluronic Acid System, Advanced Science 9 (2022) 2103189.

https://doi.org/10.1002/advs.202103189.

[6] S. Zhang, R. Langer, G. Traverso, Nanoparticulate drug delivery systems targeting

inflammation for treatment of inflammatory bowel disease, Nano Today 16 (2017) 82–

96. https://doi.org/10.1016/j.nantod.2017.08.006.

[7] R. Oum, Y. Al Ayoub, F. Haddad, B. Aburas, A. Paradkar, M. Najafzadeh, M.T. Nasim,

R.C. Gopalan, K.H. Assi, Development and evaluation of liquid formulations of chrysin

and budesonide for asthma and COPD; evaluation of the formulations' genotoxicity and

anti-inflammatory activity, Journal of Drug Delivery Science and Technology 105

(2025) 106567. https://doi.org/10.1016/j.jddst.2024.106567.

[8] G. Asadi, P. Feizollahi, M. Rajabinejad, S. Falahi, F. Rezaei Varmaziar, E. Faryadi, A.

Gorgin Karaji, F. Salari, A. Rezaiemanesh, Comparison of the efficacy of combined

budesonide and fexofenadine versus combined fluticasone propionate and fexofenadine

on the expression of class-4 semaphorins and their receptors in the peripheral blood

cells of patients with allergic rhinitis, Heliyon 10 (2024) e22924.

https://doi.org/10.1016/j.heliyon.2023.e22924.

[9] E.S. Dellon, D.A. Katzka, V.A. Mukkada, M.H. Collins, G.W. Falk, C.A. Richmond, B.

Terreri, M. Thakur, M. Boules, B. Goodwin, I. Hirano, Long-term Safety and Efficacy

of Budesonide Oral Suspension for Eosinophilic Esophagitis: A 4-Year, Phase 3, Open-

Label Study, Clinical Gastroenterology and Hepatology (2025).

https://doi.org/10.1016/j.cgh.2024.12.024.

[10] M. Peng, D. Song, X. Ling, W. Jiang, Y. Zhang, Y. Yang, J. Le, Using thermal forced

degradation approach for impurity profiling of budesonide solution-formulated metered

dose inhalation with implementation of LC-QTOFMS and HPLC-UV, Journal of

Pharmaceutical and Biomedical Analysis 208 (2022) 114445.

https://doi.org/10.1016/j.jpba.2021.114445.

[11] H.S. Sardou, M. Abbaspour, A. Akhgari, P. Kesharwani, A. Sahebkar, Colon-targeted

delivery systems of budesonide as second-line therapy in inflammatory bowel disease,

Journal of Drug Delivery Science and Technology 93 (2024) 105472.

https://doi.org/10.1016/j.jddst.2024.105472.

[12] M.E.A. Hammouda, A.A. El-Masry, S.M. El-Ashry, D.R. El-Wasseef, Insights of

different analytical approaches for estimation of budesonide as COVID-19 replication

inhibitor in its novel combinations: green assessment with AGREE and GAPI

approaches, BMC Chemistry 17 (2023) 17. https://doi.org/10.1186/s13065-023-00936-

z.

[13] M. Gupta, H.N. Bhargava, Development and validation of a high-performance liquid

chromatographic method for the analysis of budesonide, Journal of Pharmaceutical and

Biomedical Analysis 40 (2006) 423–428. https://doi.org/10.1016/j.jpba.2005.06.038.

[14] J. Varshosaz, J. Emami, N. Tavakoli, M. Minaiyan, N. Rahmani, F. Ahmadi, F.

Dorkoosh, Development and validation of a rapid HPLC method for simultaneous

analysis of budesonide and its novel synthesized hemiesters in colon specific

formulations, Res Pharm Sci 6 (2011) 107–116.

https://www.ncbi.nlm.nih.gov/pmc/articles/PMC3249773/ (accessed June 30, 2025).

[15] S. Hou, M. Hindle, P.R. Byron, A stability-indicating HPLC assay method for

budesonide, Journal of Pharmaceutical and Biomedical Analysis 24 (2001) 371–380.

https://doi.org/10.1016/S0731-7085(00)00424-6.

[16] A. Cimato, G. Facorro, M. Martínez Sarrasague, Budesonide associated with exogenous

pulmonary surfactant in a novel formulation to improve the delivery to the lung,

Respiratory Physiology & Neurobiology 296 (2022) 103825.

https://doi.org/10.1016/j.resp.2021.103825.

[17] R.B. Gudimitla, L.R. Atmakuri, V.R. Jangala, A Novel Method for the Estimation of

Budesonide in Human Plasma by Using LC-MSMS, (n.d.).

https://www.derpharmachemica.com/pharma-chemica/a-novel-method-for-the-

estimation-of-budesonide-in-human-plasma-by-using-lcmsms-14984.html (accessed

June 30, 2025).

[18] B. Streel, B. Cahay, R. Klinkenberg, Using total error concept for the validation of a

liquid chromatography–tandem mass spectrometry method for the determination of

budesonide epimers in human plasma, Journal of Chromatography B 877 (2009) 2290–2300. https://doi.org/10.1016/j.jchromb.2009.02.004.

[19] Y.A. Salem, M.A. Shaldam, D.T. El-Sherbiny, D.R. El-Wasseef, S.M. El-Ashry, Simultaneous Determination of Formoterol Fumarate and Budesonide Epimers in Metered Dose Inhaler Using Ion-Pair Chromatography, Journal of Chromatographic Science 55 (2017) 1013–1020. https://doi.org/10.1093/chromsci/bmx067.

[20] A. Demurtas, S. Pescina, S. Nicoli, P. Santi, D. Ribeiro de Araujo, C. Padula, Validation of a HPLC-UV method for the quantification of budesonide in skin layers, Journal of Chromatography B 1164 (2021) 122512. https://doi.org/10.1016/j.jchromb.2020.122512.

[21] N.C. do C. Borges, R.B. Astigarraga, C.E. Sverdloff, B.C. Borges, T.R. Paiva, P.R. Galvinas, R.A. Moreno, Budesonide quantification by HPLC coupled to atmospheric pressure photoionization (APPI) tandem mass spectrometry. Application to a comparative systemic bioavailability of two budesonide formulations in healthy volunteers, Journal of Chromatography B 879 (2011) 236–242. https://doi.org/10.1016/j.jchromb.2010.12.003.

[22] M. de L.T. Vieira, RP Singh, H. Derendorf, Simultaneous HPLC analysis of triamcinolone acetonide and budesonide in microdialysate and rat plasma: Application to a pharmacokinetic study, Journal of Chromatography B 878 (2010) 2967–2973. https://doi.org/10.1016/j.jchromb.2010.08.048.

[23] Y. Ke, J. Jiang, X. Mao, B. Qu, X. Li, H. Zhao, J. Wang, Z. Li, Photochemical reaction of glucocorticoids in aqueous solution: Influencing factors and photolysis products, Chemosphere 331 (2023) 138799. https://doi.org/10.1016/j.chemosphere.2023.138799.

[24] B. Tessier, L. Moine, A. Peramo, N. Tsapis, E. Fattal, Poly(malic acid)-budesonide

nanoconjugates embedded in microparticles for lung administration, Drug Deliv. and

Transl. Res. 14 (2024) 2062–2078. https://doi.org/10.1007/s13346-024-01571-4.

[25] ICH, 2023. ICH guideline Q2(R2) on validation of analytical procedures – Step 5.

EMA/CHMP/ICH/82072/2006. European Medicines Agency, Amsterdam, (n.d.).

https://www.ema.europa.eu/en/documents/scientific-guideline/ich-q2r2-guideline-

validation-analytical-procedures-step-5-revision-1_en.pdf.

[26] J. Ermer, H.-J. Ploss, Validation in pharmaceutical analysis: Part II: central importance

of precision to establish acceptance criteria and for verifying and improving the quality

of analytical data, Journal of Pharmaceutical and Biomedical Analysis 37 (2005) 859–

870. https://doi.org/10.1016/j.jpba.2004.06.018.

[27] ICH, 2003. ICH guideline Q1A(R2) on stability testing of new drug substances and

products – Step 5. CPMP/ICH/2736/99. European Medicines Agency, London, (n.d.).

https://www.ema.europa.eu/en/documents/scientific-guideline/ich-q-1-r2-stability-

testing-new-drug-substances-and-products-step-5_en.pdf.

[28] M. Blessy, R.D. Patel, P.N. Prajapati, Y.K. Agrawal, Development of forced degradation

and stability indicating studies of drugs—A review, Journal of Pharmaceutical Analysis

4 (2014) 159–165. https://doi.org/10.1016/j.jpha.2013.09.003.

[29] M. Rambla-Alegre, J. Esteve-Romero, S. Carda-Broch, Is it really necessary to validate

an analytical method or not? That is the question, Journal of Chromatography A 1232

(2012) 101–109. https://doi.org/10.1016/j.chroma.2011.10.050.

[30] T. Tome, N. Žigart, Z. Časar, A. Obreza, Development and Optimization of Liquid

Chromatography Analytical Methods by Using AQbD Principles: Overview and Recent

Advances, Org. Process Res. Dev. 23 (2019) 1784–1802.

https://doi.org/10.1021/acs.oprd.9b00238.

[31] J.M. Campbell, S. Colombo, J.L. Doyle, D.I. Filoti, G. Hübner, L. Magnenat, A.K.

Nowinski, J.A. Pavon, S.M. Singh, L.R. Vo, J.M. Woods, E.S.E. Stokes, An Industry

Perspective on the use of Forced Degradation Studies to Assess Comparability of

Biopharmaceuticals, Journal of Pharmaceutical Sciences 113 (2024) 505–512.

https://doi.org/10.1016/j.xphs.2023.12.011.

[32] S. Miriam Marques, R.K. Shirodkar, L. Kumar, Analytical 'Quality-by-Design'

paradigm in development of a RP-HPLC method for the estimation of cilnidipine in

nanoformulations: Forced degradation studies and mathematical modelling of in-vitro

release   studies,   Microchemical   Journal   193   (2023)   109124.

https://doi.org/10.1016/j.microc.2023.109124.

[33] Salwa, L. Kumar, Quality-by-design driven analytical method (AQbD) development and

validation of HPLC–UV technique to quantify rivastigmine hydrogen tartrate in lipidic

nanocarriers: Forced degradation, and assessment of drug content and in vitro release

studies,   Microchemical   Journal   193   (2023)   108944.

https://doi.org/10.1016/j.microc.2023.108944.

[34] B. Rao Nagulancha, K. Rao Vandavasi, S. Kumar Palugula, Stability indicating RP-

HPLC-UV method for quantitative estimation of isomer and other organic impurities of

atopic dermatitis drug abrocitinib in drug substance and pharmaceutical dosage form

using quality by design (QbD) approach, Microchemical Journal 204 (2024) 111032.

https://doi.org/10.1016/j.microc.2024.111032.

[35] M. Uğur, E. Bellur Atici, S.A. Ozkan, A specific chiral HPLC method for lifitegrast and

determination of enantiomeric impurity in drug substance, ophthalmic product and

stressed samples, Journal of Pharmaceutical and Biomedical Analysis 242 (2024)

116039. https://doi.org/10.1016/j.jpba.2024.116039.

[36] N. Gandhi, S. Ezhava, Stability-Indicating Analytical Method Development Using

Quality by Design (QbD) Approach for Simultaneous Estimation of Budesonide and

Levosalbutamol, Journal of AOAC INTERNATIONAL 105 (2022) 665–674.

https://doi.org/10.1093/jaoacint/qsab172.

[37] S. Levent, A. Elriş, S. Özcan, N.Ö. Can, A novel stability-indicating HPLC method for

determining vorapaxar and conducting high-resolution mass spectroscopic

characterization and molecular docking studies on its novel degradation product,

Microchemical Journal 210 (2025) 113002.

https://doi.org/10.1016/j.microc.2025.113002.

[38] G. Ramanathan, M. Hassan, Y. Rochev, Optimising the viscoelastic properties of

hyaluronic acid hydrogels through colloidal particle interactions: A response surface

methodology approach, Colloids and Surfaces A: Physicochemical and Engineering

Aspects 703 (2024) 135320. https://doi.org/10.1016/j.colsurfa.2024.135320.

[39] Q. Li, W. Liu, K. Liu, Z. Dong, W. Kong, X. Lu, Y. Wei, W. Wu, J. Yang, J. Qi, The Role

of Nanoparticle Morphology on Enhancing Delivery of Budesonide for Treatment of

Inflammatory Bowel Disease, ACS Appl. Mater. Interfaces 16 (2024) 33081–33092.

https://doi.org/10.1021/acsami.4c05214.

[40] N. Zhang, Z. Shen, C. Chen, G. He, C. Hao, Effect of hydrogen bonding on self-

diffusion in methanol/water liquid mixtures: A molecular dynamics simulation study,

Journal of Molecular Liquids 203 (2015) 90–97.

https://doi.org/10.1016/j.molliq.2014.12.047.

[41] X. Subirats, L. Casanovas, L. Redón, M. Rosés, Effect of the solvent on the

chromatographic selectivity in reversed-phase and HILIC, Advances in Sample

Preparation 6 (2023) 100063. https://doi.org/10.1016/j.sampre.2023.100063.

[42] P. Pahade, L.P. Pradhan, S. Chowdhury, D. Bose, A. Durgbanshi, S. Carda-Broch, J.

Peris-Vicente, A study on micellar liquid chromatographic analysis of multivariate

forced degradation of chemotherapeutic drug irinotecan using an experimental design

approach: Response surface methodology, Microchemical Journal 208 (2025) 112349.

https://doi.org/10.1016/j.microc.2024.112349.

[43] F. Zhang, J. Zhou, Y. Shi, P. Tavlarakis, K. Karaisz, Mechanism driven structural

elucidation of forced degradation products from hydrocortisone in solution, Journal of

Pharmaceutical and Biomedical Analysis 128 (2016) 333–341.

https://doi.org/10.1016/j.jpba.2016.06.004.

[44] J. Hansen, H. Bundgaard, Studies on the stability of corticosteroids V. The degradation

pattern of hydrocortisone in aqueous solution, International Journal of Pharmaceutics 6

(1980) 307–319. https://doi.org/10.1016/0378-5173(80)90114-3.

[45] A. Bhutnar, S. Khapare, A. Desai, S. Dsouza, Isolation and Characterization of

Photodegradation Impurity in Budesonide Drug Product Using LC-MS and NMR

Spectroscopy, American Journal of Analytical Chemistry 8 (2017) 449–461.

https://doi.org/10.4236/ajac.2017.87034.

[46] C. Cristelo, J. Viegas, A.S. Barros, H. Almeida, J. das Neves, B. Sarmento, R. Nunes,

Oral delivery of tunable oxidation-responsive budesonide-loaded nanoparticles

enhances inflammation modulation in intestinal colitis, Journal of Controlled Release

384 (2025) 113948. https://doi.org/10.1016/j.jconrel.2025.113948.

Table captions

Table 1. Reported analytical methods for BUd across different matrices, highlighting column

types, mobile phases, conditions, and applications.

Table 2. Independent variables and their corresponding levels used in RSM-CCD

experiments for Phase I and Phase II method optimization.

Table 3. Summary of method validation parameters for BUd by RP-HPLC. (A) Accuracy

(n □ = □ 3). (B) Robustness evaluation (n □ = □ 3). (C) System suitability parameters (n □ = □ 6).

Figure captions

Figure 1. Schematic overview of the RP-HPLC method development for BUd-NPs,

illustrating DOE-based optimization, method validation, and application to in vitro release

and forced degradation studies.

Figure 2. (a) Schematic representation of the sequential electrostatic coating of BUd-PLGA

NPs with PLL and HA to obtain BUd NPs. Physicochemical characterization including (b)

hydrodynamic diameter, (c) zeta potential, (d) PDI, (e) intensity, and (f) frequency (%)

distributions by DLS (n = 3). (g–i) SEM images at 5 □ µm (×10k), 2 □ µm (×20k), and 1 □ µm

(×30k).

Figure 3. Visualization of variable interactions for phase I optimization of the RP-HPLC

method with ACN as the categorical solvent. (a, b) Contour plots; (c, d) 3D surface plots; and

(e, f) actual vs. predicted plots showing the combined effects of MeOH:H_2O composition

(70:30, 75:25, 80:20, v/v) and flow rate (0.375, 0.400, and 0.425 □ mL/min) on retention time

and peak area (n = 3).

Figure 4. Visualization of variable interactions for phase II optimization of the RP-HPLC

method with ACN as the categorical solvent. (a, b) Contour plots; (c, d) 3D surface plots; and

(e, f) actual vs. predicted plots showing the combined effects of flow rate (0.34, 0.35, and

0.36 □ mL/min) and injection volume (5, 10, and 15 □ µL) on retention time and peak area (n =

3).

Figure 5. (a) Representative RP-HPLC chromatograms showing method specificity for

blank, placebo, BUd, BUd NPs, and BUd NPs under stress. PDA contour plots (200–

320 □ nm) for (b) blank, (c) Bare NPs, (d) BUd, (e) BUd NPs, and stressed BUd NPs under (f)

acidic, (g) basic, (h) thermal, (i) oxidative, (j) UV, and (k) visible light conditions.

Figure 6. Calibration and sensitivity assessment for BUd (1–200 µg/mL). (a) Calibration

curve with linear regression and inset showing LOD and LOQ values. (b) Overlaid RP-HPLC

chromatograms demonstrating method sensitivity and linearity (n = 6).

Figure 7. (a) Schematic of forced degradation protocol for BUd and BUd NPs under

hydrolytic (acidic, basic), oxidative, thermal, photolytic (UV), and photostatic (visible light)

stress. (b) Quantitative BUd content analysis in BUd NPs under stress (n = 3). ANOVA with

Tukey's post hoc test: $*p < 0.05$, $**p < 0.01$, $***p < 0.001$, $****p < 0.0001$. Only

$p \geq 0.0001$ comparisons are annotated, all others are statistically significant at $p < 0.0001$. (c–

h) RP-HPLC chromatograms showing degradation profiles under (c) acidic, (d) basic, (e)

thermal, (f) oxidative, (g) UV, and (h) visible light conditions.

Figure 8. (a) Schematic of the in vitro release protocol simulating gastrointestinal pH

transitions using dialysis devices (pH 1.8, 6.8, and 7.4 at 37 °C). (b) Release profile of BUd

from BUd-NPs over 48 h with inset showing segmented x-axis for early-phase visualization.

Data shown as mean ± SD (n = 3).

863   **Figure 1**

865   **Figure 2**

Figure 3

Figure 4

871
872 **Figure 5**

874 **Figure 6**

876 **Figure 7**

878 **Figure 8**

Table 1. Reported analytical methods for budesonide across different matrices, highlighting column types, mobile phases, conditions, and applications

Ref.	Column	Mobile Phase	Flow rate (mL/min)	Temp (°C)	Detection (nm)	Sample	Analysis	IV (µL)
[10]	C18 (150×4.6 mm, 3 µm)	EtOH:ACN:Buffer (2:34:66, pH 3.2)	1	50±2	240	BUd	Impurity and stress degradation	100
[12]	C18 (150×4.6 mm, 5 µm)	ACN:Buffer (40:60, pH 3.5)	2	25±2	230	BUd as nasal sprays	Validation and Green assessment	20
[13]	C8 (150×4.6 mm)	ACN:Buffer (55:45, pH 3.2)	1.1	25±2	244	BUd in pectin microparticles	Stability, quantification and stress degradation	10
[14]	C18 (250×4.6 mm, 5 µm)	ACN:Buffer (55:45, pH 3.2)	1	25±2	244	BUd-colon targeted	Validation, release	50
[15]	C18 (150×4.6 mm, 5 µm)	EtOH:ACN:Buffer (2:30:68, pH 3.4)	1.5	25±2	240	Propylene glycol funtionalized BUd	Validation, Stability, and stress degradation	10
[16]	C8 (150×4.6 mm)	ACN:Buffer (32:68, pH 3.2)	1.1	25±2	244	BUd in rat organs	Quantification	50
[17]	C8 (150×4.6 mm, 3.5 µm)	ACN:Buffer (60:40, pH 4.2)	-	-	-	BUd in human plasma	Analytical validation	5
[18]	C18 (50×4.6 mm, 3 µm)	ACN:Buffer (35:65, pH 3.2)	1	25±2	MS/MS	BUd in human plasma	Pharmacokinetic and quantification.	100
[19]	C18 (100×3 mm, 3.5 µm)	ACN:Buffer (40:60, pH 3.1)	1	25±2	214	BUd	Validation and stress degradation	10–100
[20]	C18 (75×4.6 mm, 3.5 µm)	MeOH:H_2O (69:31)	0.8	25±2	254	BUd in skin layers	Quantification	100
[21]	C18 (50×4.6 mm, 5 µm)	MeOH:H_2O (70:30)	0.8	25±2	MS/MS	BUd in human plasma	Validation, stability and pharmacokinetic	20
[22]	C18 (250×4.6 mm, 5 µm)	MeOH:H_2O (72:28)	0.8	25±2	254	BUd in rat plasma	Pharmacokinetic	10
[23]	C18 (2.1×150 mm, 5 µm)	H_2O:ACN (30:70)	1	30±2	245	BUd in Env. water	Photo and stress degradation	NA
[24]	RP18 (250×4.6 mm, 5 µm)	ACN:H_2O (55:45)	1	35±2	244	BUd microparticles in lung	Quantification and release	5

Table 2. Independent variables and their corresponding levels used in RSM-CCD experiments for Phase I and Phase II method optimization

DOE Exp. No. Phase			Numerical Variables	Levels			Star Point α = 1	
	1.		**Numerical Variables**	**Levels**			**Star Point α = 1**	
				Low (-1)	**Central (0)**	**High (+1)**	**-α**	**+α**
			A: Mobile Phase (MeOH: H₂O)	70:30	75:25	80:20	70:30	80:20
			B: Flow Rate (mL/min)	0.375	0.400	0.425	0.375	0.425
			Categorical Variables	**Levels**			**Star Point α = 1**	
				1	**2**	**3**	**-α**	**+α**
			C: Drug Dissolved (1mL)	ACN	MeOH	EtOH	NA	
	2.		**Numerical Variables**	**Levels**			**Star Point α = 1**	
				Low (-1)	**Central (0)**	**High (+1)**	**-α**	**+α**
			D: Flow Rate (mL/min)	0.34	0.35	0.36	0.34	0.36
			E: Injection Volume (μL)	5	10	15	5	15
			Categorical Variables	**Levels**			**Star Point α = 1**	
				1	**2**	**3**	**-α**	**+α**
			F: Drug Dissolved (1mL)	ACN	MeOH	EtOH	NA	

Table 3. Summary of method validation parameters for budesonide by RP-HPLC. (A) Accuracy (n = 3). (B) Robustness evaluation (n = 3). (C) System suitability parameters (n = 6)

(a) Accuracy

Spiking Ratio (A:B, µL)	Theoretical Value (µg/mL)	Experimental Mean (µg/mL)	Recovery (%)	% RSD
750:250	187.5	186.9 ± 1.5	99.7%	0.8%
500:500	175.0	172.5 ± 1.3	98.6%	0.8%
250:750	162.5	159.4 ± 2.2	98.1%	1.4%

(b) Robustness

Parameter	Level	Retention Time (min) Mean ± SD	RSD (%)	Peak Area Mean ± SD	RSD (%)
Flow rate (mL/min)	0.34	3.7 ± 0.0	0	4847382 ± 22402	0.5
	0.35	3.65 ± 0.01	0.3	4303177 ± 71076	1.7
Injection Volume (µL)	10	3.7 ± 0.0	0.0	4847382 ± 22402	0.5
	15	3.76 ± 0.02	0.5	5311693 ± 37221	0.7
Temperature (°C)	40	3.74 ± 0.0	0.0	4847382 ± 22402	0.5
	30	3.66 ± 0.01	0.3	5942434 ± 37105	0.6
Wavelength (nm)	242	3.7 ± 0.0	0.0	4847382 ± 22402	0.5
	244	3.76 ± 0.02	0.5	5311693 ± 37221	0.7

(c) System suitability

Parameter	Acceptance Criteria	Mean ± SD	RSD (%)
Retention Time (RT)	Consistent (within ±2%)	3.75 ± 0.01	0.3
Peak area	%RSD ≤ 2.0	7775932 ± 15961	0.2
Number of Theoretical Plates (N)	> 2000 (depends on column)	3087 ± 13	0.4
Tailing Factor (T)	≤ 2.0	1.2 ± 0.0	0.0
Resolution (Rs)	≥ 2.0 (between critical peaks)	8.3 ± 0.6	0.9
Capacity Factor (k')	2<k'<10	3.6 ± 0.0	0.3