LipiGo: A Versatile DNA-Lipid Nanoparticle Hybrid for Precision Drug Delivery

Karoline Kadletz*, Ceren Kimna*, Valentin Kenneth Reichenbach, Olga Carofiglio, Denise Jeridi, Sofia Hu, Igor Khalin, Jakub Grzejdak, Ying Chen, Izabela Horvath, David-Paul Minde, Mayar Ali, Taras Sych, Luciano Höher, Eren Aydeniz, Yagmur Ayse Kulcu, Alessio Ricci, Arthur Liesz, Erdinc Sezgin, Siegfried Ussar, Farida Hellal, Markus Elsner, Ali Ertürk

Abstract: Lipid nanoparticles (LNPs) are established carriers for nucleic acid delivery, however, achieving efficient delivery to non-hepatic tissues remains a major challenge. Here, we present LipiGo, a nanocarrier platform engineered by integrating short single stranded DNA molecules into the lipid nanoparticle structure. Using whole body tissue clearing, advanced imaging and AI-based analysis, we show that LipiGo redirects functional mRNA delivery to lymphoid organs, particularly the spleen. Immune cell profiling further reveals enhanced uptake within key immune populations, including antigen-presenting cells, compared to standard LNPs. Beyond passive redistribution, LipiGo leverages DNA hybridization to enable modular attachment of targeting ligands for active targeting as demonstrated by cell-specific delivery to white adipocytes. Overall, the dual-purpose design principle of LipiGo demonstrates high modularity and efficiency, enabling tissue and cell specific delivery beyond hepatic applications.

1. Introduction

Nucleic acid therapeutics offer opportunities for both prophylactic and therapeutic applications with the potential to address targets previously considered undruggable by conventional methods. Their broad clinical translation, however, remains constrained by targeted delivery.

Lipid nanoparticles (LNPs) represent one of the most clinically advanced vehicles for the delivery of nucleic acids as they combine high loading capacity, stability in circulation, and low toxicity. Their impact has become evident in approved medicines, including SARS-CoV-2 vaccines and a therapy for hereditary transthyretin-mediated amyloidosis, with numerous additional candidates currently in clinical trials.

Despite their advantages, intravenously administered LNPs intrinsically accumulate in the liver, which limits their utility in extrahepatic tissues and increases the risk of liver-related toxicity[1,2]. Although alternative administration routes can shift biodistribution toward different organs, precise delivery beyond the liver requires rational strategies to control nanoparticle tropism, which remains one of the central challenges in the field.

Efforts to achieve organ-, tissue-, and cell type-specific delivery with LNPs can be broadly categorized into passive and active strategies[3]. Varying lipid ratios, introducing lipids with distinct chemistries or expanding the number of constituent lipids reshapes the biomolecular corona that forms around LNPs upon exposure to biofluids, and thereby passively modulates interactions with immune receptors, cells, and tissues[4]. Active strategies, in contrast, involve decorating the particle surface with targeting ligands such as antibodies or aptamers[5,6]. Ligands are most commonly attached to LNPs via PEG-lipids, which protrude from the LNP surface[7]. However, PEG-lipids are designed to rapidly shed upon administration to facilitate cellular internalization and endosomal escape[8]. As PEG shedding typically occurs within minutes of administration, together with the strong intrinsic hepatic tropism of LNPs, efficient engagement of targeting ligands with their cognate receptors is often limited[9]. Thus, cell type-specific targeting following systemic delivery with active strategies has not been achieved *in vivo*[10]. Achieving sub-organ level specificity beyond the liver, therefore, requires overcoming dominant hepatic accumulation while simultaneously leveraging active targeting via surface-displayed ligands, highlighting the need for a vehicle design that integrates both passive and active targeting mechanisms.

Here, we introduce LipiGo, a lipid-based hybrid nanoparticles generated by partially substituting cholesterol with cholesterol-modified single-stranded DNA (ssDNA) that protrude from the particle surface. In this base formulation, the DNA strands alter particle physicochemical properties and redirect functional mRNA delivery from the liver toward immune organs. Beyond this intrinsic retargeting, the protruding DNA strands also serve as modular handles for ligand hybridization, thereby combining passive and active targeting in a single design and enabling cell-specific delivery, as demonstrated with a white adipocyte–targeting DNA aptamer.

2. Results and Discussion

Design and characterization of LipiGo nanoparticles

To generate LipiGo, we partially substituted the cholesterol component in standard lipid nanoparticle formulations with a 26-base single stranded DNA (ssDNA) modified with a cholesterol moiety at the 3' end. This modification results in nanoparticles with ssDNA protruding from their surface (**Fig. 1a,b**).

While generating the base LipiGo formulation, lipid ratios were adapted from Cheng et al.[11] for efficient mRNA encapsulation and release. Particles were assembled by mixing an aqueous phase containing EGFP-encoding, fluorescently labeled mRNA with an ethanol phase containing DLin-MC3-DMA (23.8 mol %), PEG2000-C-DMG (4.3 mol %), DSPC (23.8 mol %), DMG-PEG(2000) (0.5 mol %), and cholesterol (47.6 mol %), with partial substitution of cholesterol by cholesterol-modified ssDNA at varying degrees.

Compared to conventional LNPs, LipiGo displayed altered physicochemical properties. Their hydrodynamic size increased slightly from ~50 nm to ~68 nm (**Fig. 1c**). Increasing the degree of cholesterol-ssDNA substitution from 20 to 50 % shifted the zeta potential towards more negative values (-8.2 ± 3 mV and -10.7 ± 7 for 20 % and 50 % LipiGo, respectively) (**Fig. 1d**). A similar change in zeta potential was observed across different DNA sequences and ionizable lipid chemistries (i.e., ALC-1315 and SM1502), indicating that the effect is sequence and lipid chemistry independent (**Fig. S1a**). Across formulations, the polydispersity index (PDI) remained below 0.2 for all variants, indicating narrow and monomodal size distributions and RNA encapsulation efficiency was not significantly affected by addition of the DNA-cholesterol (**Fig. 1e**). Importantly, particles remain stable for at least 24 h in serum-supplemented media (**Fig. 1f**). Together, these results indicate that while preserving uniformity, stability and loading capacity, cholesterol-ssDNA protrusions provide a tunable parameter on nanoparticle features to alter physicochemical characteristics, i.e., size and zeta potential, which are known to influence the interactions with biological material, affecting their biodistribution[4].

Beyond tuning physical characteristics, the surface-exposed DNA handles of LipiGo provide modular sites for ligand attachment through complementary base pairing. To demonstrate this versatility, we conjugated two structurally distinct ligands, i.e., an immunoglobulin G (IgG) antibody and a short DNA aptamer AS1411. The IgG antibody was first conjugated to a complementary DNA strand via maleimide chemistry, followed by hybridization to the LipiGo handle (**Fig. 1a**). The aptamer was extended with a short region complementary to the LipiGo handle strand and therefore could be directly hybridized to the handle DNA. Both ligand-conjugated LipiGo variants retained comparable physicochemical properties within an acceptable size range (**Fig. 1g,h**). Successful aptamer hybridization was confirmed by an increase in double-stranded DNA content together with a decrease in zeta potential (**Fig. S1c**). Importantly, this DNA-mediated conjugation strategy not only ensures controlled orientation and display of targeting ligands but also avoids the altered biodistribution and enhanced toxicity associated with complement activation, a phenomenon recently reported for nanoparticles functionalized with targeting antibodies using conventional chemistries such as dibenzocyclooctyne-mediated coupling[12].

We next assessed the cellular compatibility and intracellular behavior of LipiGo *in vitro*. LipiGo particles

did not induce detectable cytotoxicity within the tested concentration range (1-10 μg mRNA per mouse)

as measured by cell viability assay in HEK cells (**Fig. S2a**). To evaluate endosomal escape and

cytoplasmic delivery, we employed the Gal8 recruitment assay in HeLa cells, which are stably

expressing Galectin8-mRuby3 fusion protein[13]. Upon endosomal membrane rupture, Gal8-mRuby3

binds to the inner lumen of the disrupted endosomes resulting in punctate fluorescent spots, indicating

cytosolic release of the particle remnants and their cargo. We observed a significantly increased

endosomal rupture at 4 h after LipiGo treatment compared to the standard LNPs (**Fig. 1i,j**). By 24 h,

Gal-8 positive puncta in LipiGo treated cells decreased to levels comparable with those observed with

standard LNPs, suggesting that LipiGo promotes more rapid endosomal escape. Consistent with this,

cells incubated with LipiGo showed stronger fluorescent mRNA signal at 24 h relative to standard LNPs

(**Fig. 1k**), indicating enhanced cytoplasmic retention and reduced intracellular degradation. These

results suggest that LipiGo interacts differently with endosomal membranes or trafficking pathways,

leading to more efficient release of its cargo. Since limited endosomal escape remains a key bottleneck

in mRNA delivery, the accelerated endosomal rupture and sustained cytoplasmic mRNA signal with

LipiGo highlights its potential to overcome this challenge.

Following in vitro evaluations, we next evaluated the half-life of LipiGo particles in bloodstream using in

vivo two-photon microscopy. LipiGo exhibited a circulation half-life of ~120 minutes, which was slightly

shorter than that of the parent LNPs, suggesting faster tissue uptake. This finding is consistent with the

enhanced cellular uptake observed *in vitro*, and fall falls within the range reported for other LNP

formulations assessed with alternative techniques[14] (**Fig. 1l-n**).

LipiGo exhibits enhanced biodistribution to lymphatic tissues

To evaluate the *in vivo* biodistribution of LipiGo nanoparticles, we intravenously injected 1 μg

mRNA/mouse (0.067 mg/kg mRNA) and analyzed particle distribution after 1 h using our in-house

developed "Single Cell Precision Nanocarrier Identification (SCP Nano)" pipeline[15]. SCP Nano

integrates whole-body tissue clearing of LNP/LipiGo administered mice, light sheet fluorescence

microscopy (LSFM) imaging, and deep learning-based signal quantification at single cell-resolution for

biodistribution mapping (**Fig. 2a**). As expected, intravenous administration of standard LNPs led to

predominant hepatic accumulation, limiting their ability to effectively target other organs[2]. Using high

resolution whole-body imaging, we observed LipiGo and LNP signals in other major organs including

the spleen, lungs, and heart (**Fig. 2b**, **Fig. S3**). Some of these organ-specific signals would be difficult

to capture using conventional techniques such as bioluminescence imaging (**Fig. S4b**).

Interestingly, LipiGo particles exhibited a pronounced tropism for lymphoid and immune associated

organs, particularly in the spleen and lymph nodes, which are targeted less by conventional LNPs

following intravenous administration (**Fig. 2b,c**). Standard LNPs and LipiGo particles also show

differences in their intra-organ distribution (**Fig. 2c**). For example, liver distribution patterns for LipiGo

particles were found to be more homogeneous and dispersed than for standard LNPs, which showed

perivascular clustering. These differences likely reflect deeper tissue penetration associated with faster

blood clearance as indicated by the lower signal at 60 minutes in the blood that was measured with
intravitreal microscopy (**Fig. 1l-n**).

To test whether the observed shift in biodistribution was independent on the specific LNP formulation,
we generated LipiGo particles using other clinically validated ionizable lipids, i.e., ALC-0315 (used in
BioNTech's COVID-19 vaccine) and SM-102 (used in Moderna's Covid 19 vaccine). Physicochemical
properties were similar across all LipiGo variants (**Fig. S1a**). Notably, incorporation of the DNA-lipid
handle into the base formulation consistently led to a more uniform biodistribution pattern in the liver
and to a substantial shift in tropism towards immune organs (**Fig. 2d, Fig. S3a**), supporting the
compositional flexibility of the LipiGo platform.

We next evaluated whether sequence-level engineering of the DNA handle further modulates the
biodistribution. We designed a DNA handle variant containing a CpG motif known to activate immune
cells via Toll-like receptor (TLR9) [16-18]. While the original LipiGo sequence was designed to be
biologically inert, both sequences were identical in length and total GC content to control for structural
effects. LipiGo particles formulated with the CpG-containing sequence (LipiGo-CpG), exhibited similar
hydrodynamic size and zeta potential, ruling out colloidal effects on biological behavior (**Fig. S1b**).
Following the SCP Nano pipeline, we found that LipiGo-CpG showed even stronger spleen tropism
compared to the LipiGo with non-functional DNA handles, (**Fig. S3e**). These findings demonstrate that
oligonucleotide sequence alone can be leveraged to tune targeting. Together, the findings demonstrate
the modularity of LipiGo across different ionizable lipid backbones in maintaining immune organ
targeting, as well as its tunability through DNA handle sequence level to further refine biodistribution,
highlighting its flexibility for organ tropism.

Quantitative organ and cell type profiling reveals LipiGo-mediated immune tropism despite
residual hepatic distribution
Having qualitatively assessed particle distribution, we next performed deep-learning based
quantification of organ-level targeting using automated segmentation of organs and mRNA signal (**Fig.**
3a). Based on whole-body images, we anticipated the major difference of LipiGo particles to be their
reduced hepatic accumulation and increased localization to lymphatic organs (**Fig. 2a,b**). However,
unbiased organ-by-organ quantification revealed interesting, yet, unexpected, findings. Even though
the preferential accumulation of LipiGo in the spleen was validated, the visually perceived reduction in
liver targeting was not supported quantitatively (**Fig. 3b**). Compared to LNPs, LipiGo particles exhibited
slightly reduced lung accumulation, consistent with previous reports showing that LNPs formulated with
cationic lipids preferentially localize to the lung whereas the more negatively charged formulations
demonstrate spleen tropism[4]. Across all formulations, minimal particle accumulation was quantified in
the brain, heart, and kidneys, and no significant differences were detected among LipiGo variants with
varying degrees of DNA handle modification (**Fig. 3b**).

Revisiting the raw images for a closer inspection provided insight into these observations. In LipiGo-
injected mice, the mRNA signal in the livers appeared more sparsely distributed, whereas in standard

LNP-injected mice, the signal was concentrated in focal regions as distinct patches near blood vessels. This perivascular clustering likely contributed to the apparent overestimation of liver enrichment by visual inspection alone, underscoring the importance of unbiased quantification. The more dispersed distribution pattern observed with LipiGo may reflect differences in particle kinetics. As shown in the circulation half-life experiments (**Fig. 1l-n**), fewer LipiGo particles remained in bloodstream at 60 minutes, suggesting more rapid tissue uptake. It is possible that, by the time of sacrifice, *i.e.*, 60 minutes post injection, LipiGo particles potentially penetrated deeper into liver parenchyma, leading to a more homogeneous and less visually prominent signal compared to the vascular-concentrated standard LNPs. This integrated view, together with the image-based quantification and kinetic data highlights the value of multimodal analysis in revealing subtle but biologically meaningful differences in nanocarrier behavior.

In addition, we generated liver and spleen biodistribution density maps to facilitate direct comparison of accumulation patterns between standard LNP and LipiGo formulations in terms of liver to spleen tropism. These density heat maps further illustrated these differences, with LipiGo-injected animals showing fewer high-density patches in the liver and stronger accumulation in the spleen (**Fig. 3c**). The enhanced spleen targeting of LipiGo was consistently validated by SCP-nano, as demonstrated both in the representative heat maps (**Fig. 3c**) and in corresponding quantitative dot counts at the organ level (**Fig. 3b**).

With LipiGo showing a strong tropism for lymphoid organs, we next investigated the immune cell types targeted across key immune-relevant tissues including blood, lymph nodes, spleen, and liver. Flow cytometric profiling of 20 distinct immune cell subsets revealed a clear shift in cellular tropism compared to standard LNPs (**Fig. 3d, Fig. S5**). Notably, LipiGo demonstrated enhanced uptake across several immune cell types, particularly in secondary lymphoid organs. In the spleen, LipiGo increased the percentage of mRNA homing immune cells from 26.51% to 65.16% with the most prominent contributions from antigen presenting cells such as $CD35^+$ follicular dendritic cells (5.8-fold), $F4/80^+$ macrophages (11.3-fold), and $CD11c^+$ dendritic cells (2.4-fold) (**Fig. 3d,e**). T-cell delivery also improved with higher frequencies of both CD4+ and CD8+ subsets labeled in the spleen and lymph nodes, despite overall lower levels. High targeting rates of both the antigen presenting and effector cells at these critical sites suggests a potential utility of LipiGo particles to trigger and shape specific immune responses. Furthermore, beyond adaptive immunity, LipiGo broadened innate immune engagement with elevated signals observed in $Ly6C^+$ monocytes and $Ly6G^+$ neutrophils across peripheral organs. By contrast, standard LNPs showed substantially lower mRNA delivery to these immune subsets in the spleen, and remained largely confined to liver-resident cells. Notably, even within the liver, LipiGo outperformed standard LNPs for most immune cell subtypes, with strong increases in targeting efficiency in $CD4^+$ T cells and $Ly6C^+$ monocytes and $Ly6G^+$ neutrophils. Together, these results highlight the potential of LipiGo to engage both innate and adaptive immune cells within immunologically active tissues.

Functional delivery of mRNA to the immune cells with reduced hepatic expression

Having demonstrated through whole body mRNA cargo imaging that LipiGo enhances tropism to
lymphatic organs, we next investigated whether these particles enable functional delivery, *i.e.*,
successful cytoplasmic mRNA release and translation to protein. Mice were injected intravenously with
LipiGo particles carrying EGFP mRNA (0.067 mg/kg) and sacrificed 48 h later. EGFP expression was
detected with nanobody staining using the nanoDISCO whole body clearing method [15].

In contrast to the biodistribution data, functionality readout revealed significantly reduced EGFP
expression in LipiGo-administered mouse livers (**Fig. 4a,b, Fig. S4a**). Moreover, we observed different
protein expression distribution pattern within the liver compared to standard LNPs. While LNPs induced
concentrated, perivascular clusters of EGFP, LipiGo-treated livers exhibited minimal and more diffuse
signal (**Fig. 4b**). By contrast, LipiGo still induced robust EGFP expression in lymphoid tissues, with
spleen expression markedly surpassing that of LNPs. In addition to the spleen, higher EGFP-signals
are also seen in thymus and in the lymph nodes when the mRNA is delivered with LipiGo rather than
with standard LNPs. Thus, although LipiGo distributes systemically, efficient mRNA translation is
selectively enriched in immune organs.

To validate this organ tropism with an orthogonal readout, we performed bioluminescence imaging by
loading nanoparticles with FLuc mRNA (0.067 mg/kg). Quantitative analysis of signal in the spleens
and livers confirmed the enhanced expression in the spleen and confirmed the functional liver
detargeting effect in LipiGo-treated animals (**Fig. 4c, Fig. S4b**).

To resolve the expression at the cellular level, we carried out immunofluorescence staining of fresh
frozen tissue sections from the livers and spleens (**Fig. 4d-f**). Consistent with whole-body imaging,
standard LNPs induced strong EGFP expression in the liver, whereas LipiGo-treated livers showed
minimal signal. In the spleen, however, LipiGo exhibited robust and broadly distributed protein
expression (**Fig. 4f**). Notably, unlike the clustered expression patterns seen in standard LNP-treated
livers, LipiGo-mediated expression appeared more diffuse and less concentrated. Immunostaining
confirmed that LipiGo particles were internalized to greater extent by CD45[+] immune cells as compared
to standard LNPs, and resulted in slightly elevated number of cells received functional delivery in these
populations (**Fig. S4c**). These findings again confirm the flow cytometry results, providing a direct
functional readout of protein expression in immune cell subsets.

LipiGo elicits minimal systemic response and forms a Angpt1-rich protein corona
Having established functional delivery of mRNA to immune tissues, we next evaluated the in vivo safety
profile of LipiGo by assessing systemic cytokine responses and serum protein composition. Cytokine
levels were profiled 48 h post-injection (0.168 mg mRNA/kg mouse) using a 13-plex flow-cytometry
based immunoassay.
Except for IL-1α, cytokine concretions remained below the technical limit of quantification for both
standard LNPs and LipiGo, suggesting that no major systemic inflammatory response was triggered
(**Fig. S2b**). Key inflammatory mediators commonly associated with acute nanocarrier toxicity, including
IL-6, TNF- α, and IFN- γ were undetectable in both groups. Notably, the absence of IL-6 induction is

particularly relevant given the presence of ssDNA on the LipiGo surface, which could potentially engage
TRL9 (**Fig. S2b**).
Next, we measured markers for metabolic stress and liver toxicity in mouse serum after 1h of
LNP/LipiGo circulation, injecting a high dose of 0.67 mg mRNA/kg mouse (**Fig. S2c**). LipiGo and LipiGo-
CpG showed a modest but non-significant increase in glucose and lactate compared to standard LNPs
and untreated controls, hinting to a general inflammatory response reaction after the injection of the
particles. However, since the cytokine panel 48h after injection does not show adverse effects, the
inflammatory response seems to be small and of short duration. All liver stress and damage markers
(AST, ALT, KETONE) were similar to the negative control for all particles - indicating that neither of the
particles causes hepatotoxicity (**Fig. S2c**). Together, these findings demonstrate that LipiGo maintains
a favorable safety profile, with minimal systemic immune activation and no signs of acute toxicity, even
at elevated doses.
257
Upon exposure to biological fluids, nanoparticles rapidly adsorb a layer of biomolecules primarily
composed of proteins on their surface, forming a biomolecular corona that critically influences their
colloidal stability, biodistribution, and organ tropism[19-22]. To determine whether an altered corona
composition contributes to the distinct tropism of LipiGo particles, we performed comparative proteomic
profiling of the protein coronas formed on LipiGo and standard LNPs using LC-MS/MS (**Fig. S6a**).
Principal component analysis (PCA) revealed clear separation between the protein corona profiles of
LipiGo and standard LNPs, independent of CpG-rich motif inclusion, suggesting that the DNA-handle
modification consistently alters protein adsorption patterns (**Fig. S6b**).
Interestingly, among the differentially enriched proteins, Angiopoietin-1 (Angpt1) was consistently and
significantly enriched in all LipiGo coronas independent of the ionizable lipid used in formulation (**Fig.**
S6c). The consistent enrichment of Angpt1 in the LipiGo protein corona may contribute to enhanced
immune organ targeting by promoting interactions with Tie2-expressing endothelial cells abundant in
lymphatic tissues, including lymph nodes and spleen[23]. These interactions could facilitate nanoparticle
retention or uptake within these organs. Moreover, Angpt1 is known to regulate endothelial cell stability
and vascular permeability. Its significant enrichment on the nanoparticle surface could modulate
endothelial barrier properties, potentially enabling more efficient nanoparticle extravasation from the
bloodstream into tissues and explaining the faster blood clearance and more tissue distribution of LipiGo
that we observed. These combined effects, *i.e.*, enhanced receptor mediated interactions and altered
vascular permeability may contribute to the observed redistribution of LipiGo nanoparticles toward
lymphatic organs and the faster and deeper tissue penetration.
278
Aptamer functionalization of LipiGo enables cell specific targeting *in vitro* and *in vivo*
So far we showed that the integration of ssDNA into an LNP formulation passively altered their *in vivo*
fate. However, beyond changing the physicochemical characteristics, these DNA strands also provide
a versatile platform for active ligand attachment *via* DNA hybridization, enabling straightforward
conjugation of diverse targeting ligands including antibodies or their fragments, peptides, and DNA/RNA
aptamers.

To demonstrate the utility of DNA handles for active targeting, we functionalized LipiGo particles with
DNA-based aptamers by hybridization to complementary DNA handles pre-incorporated in the
formulation (**Fig 1a**). Upon aptamer hybridization, we observed a remarkable shift towards a more
negative zeta potential (**Fig. S1c**). Although minor non-specific adsorption was detected on control
LNPs lacking the DNA handle, the pronounced changes in these physicochemical properties confirmed
specific and efficient aptamer conjugation.

First, we evaluated the targeting performance of aptamer-functionalized LipiGo *in vitro* using
differentiated white and brown adipocytes. For these experiments, we selected a novel DNA aptamer
AS1 specifically targeting the Asc-1 protein[24], which is highly expressed on white adipocytes but not on
brown adipocytes.

Confocal microscopy revealed substantial internalization of AS1-LipiGo particles carrying fluorescently
labeled mRNA into the cytoplasm of white adipocytes in an incubation period of 40 minutes (**Fig. 5a**).
Cargo mRNA was localized as clusters within intracellular compartments, suggesting endosomal
trafficking. In contrast, untargeted LipiGo particles and control LNPs incubated with free AS1 aptamers
exhibited only weak, non-specific surface association with negligible cellular uptake (**Fig. 5b**, upper
panel). To confirm cell type specificity, the same formulations were incubated with brown adipocytes
lacking the target surface protein. As expected, all formulations including the targeting AS1-LipiGo,
showed minimal cellular uptake (**Fig. 5b**, lower panel). These results collectively demonstrate that
active functionalization of LipiGo particles enables the specific internalization of mRNA into target cells.
Having confirmed specific uptake *in vitro*, we next evaluated whether the active targeting strategy
translates to tissue-specific delivery *in vivo*. Whole body clearing and imaging revealed very strong
accumulation of AS1-LipiGo in the white adipocyte fat tissue (WAT) close to the injection site (**Fig. 5f**).
Next, to assessed the functional delivery. AS1-LipiGo particles encapsulating luciferase-encoding
mRNA were administered subcutaneously into mice. Live animal bioluminescence imaging (**Fig. S7a**)
and subsequent *ex vivo* analysis of harvested organs 24 h post-injection revealed highly localized and
robust luciferase expression predominantly within the white adipose tissue proximal to the injection site
(inguinal WAT) (**Fig. S7b**). Importantly, this expression was significantly higher compared to that from
untargeted LipiGo controls, indicating the tissue target specificity of AS1-LipiGo particles. While minimal
off-target expression was detected in the liver, spleen, and kidneys, the expression in distal WAT depots
(*e.g.*, interscapular) was also negligible (**Fig. 5g**). This biodistribution profile suggests that either most
of the particles were readily taken up by the inguinal WAT already before reaching other parts of the
body, or that biodistribution throughout the body takes longer than 24 h when administered
subcutaneously. In conclusion, these findings demonstrate that the LipiGo platform enables the modular
attachment of functional aptamers for cell-specific delivery and expression of mRNA cargo *in vitro* and
in vivo, establishing a promising and versatile approach for targeted nanomedicine.

Conclusions

The ability to direct nucleic acid nanocarriers to specific organs, tissues and cell types is a central step towards expanding their therapeutic utility. In this study, we demonstrate LipiGo as a flexible platform that combines passive and active ligand-mediated targeting within a single nanocarrier design, By embedding DNA handles into the LNP framework, LipiGo combines altered characteristics driving redistribution from the liver to lymphoid organs with modular functionalization through DNA hybridization. This dual strategy expands the therapeutic reach of LNPs well beyond hepatic applications. LipiGo enabled selective and functional mRNA delivery to immune cell-rich organs while reducing hepatic expression, and further demonstrated utility as active targeting nanocarrier, achieving receptor specific delivery to white adipocytes *in vitro* and *in vivo*. The ability to unite systemic detargeting, lymphoid tropism and customizable ligand attachment highlights LipiGo as a programmable nanocarrier platform. This modular strategy could enable rapid customization of nanocarriers across diverse therapeutic areas - providing a blueprint for programmable drug delivery systems. Future studies will be directed at translating LipiGo-based constructs into therapeutic applications.

Methods

LNP/LipiGo preparation

LNPs/LipiGo particles were prepared using the ethanol dilution method. All lipids with specified molar ratios (Dlin-MC3-DMA/DSPC/cholesterol/PEG-DMG at 47.6:23.8:23.8:4.8 %) were dissolved in ethanol absolute (<99.8%), and mRNA was dissolved in 50 mM acetate buffer (pH 4.0). Those two solutions were mixed at an aqueous-to-ethanol volume ratio of 3:1 to a final N:P ratio of 6 and then incubated for 10 min at room temperature. The final LNP formulations were dialyzed (MWCO 3.5 kDa) against sterile filtered PBS for 1 h per 100 ul LNP volume to remove the ethanol and neutralize the pH. Standard LNPs were formulated using the molar ratios above. For LipiGo particles, a certain molar percentage (10%, 20% or 50%) of the cholesterol was subsidized with cholesterol bound ssDNA (26nt long) and included in the lipid phase before formulation, the particles were then dialyzed with dialysis tubes with a MWCO of 12kDa.

Physicochemical characterizations of LNP/LipiGo particles

DLS and Zeta potential measurements

The hydrodynamic diameter, polydispersity index (PDI) and zeta potential of the LNPs were measured by DLS (Malvern Zetasizer Pro). For measuring the size, the particle solution was diluted 1:50 with sterile filtered PBS and for measuring the zeta potential particles were diluted with nuclease free water. Plots were generated with GraphPad Prism and show the mean size (nm) of triplicates ± SD.

Attachment of targeting ligands to LipiGo particles

Attachment of aptamers: Aptamers with a bridge complementary to the ssDNA protruding from the LipiGo particles was folded by heating at 95°C for 5 min and then cooling down on ice until further use. LipiGo particles and aptamers were mixed at a molar ratio of 1:1 (binding sites on particles: aptamer) in PBS and then hybridized on a temperature ramp in a thermocycler at 37°C-20°C, -1°C per minute. Unbound aptamers (30 kDa) were removed using 50 kDa Amicon filters (Sigma-Aldich, UFC505008), that were pre-wetted with 0.1M PBS and then filled with the LipiGo-aptamer product and spun down at 8000 rcf for 10 minutes. 3 PBS wash steps followed, each for 5 min at 8000rcf, before inverting the filter into a new collection tube and spinning down the purified product

Attachment of protein-based ligands: Protein based ligands, such as antibodies, were attached to the thiolated complementary ssDNA strand of the LipiGo anchored handle. First, antibodies were functionalized with maleimide groups using SMCC chemistry as described in the reference[25]. Briefly, antibodies were dissolved in PBS (pH 7.2) and reacted with a 20-fold molar excess of Sulfo-SMCC (A39268, Thermo Fisher Scientific), dissolved in DMSO (final DMSO with antibody <10% v/v), for 30 min at room temperature. The activated antibody was purified using desalting columns (PD Spintrap-25, GE28-9180-04, Sigma-Aldrich) into PBS containing 1 mM EDTA. Separately, thiol-modified oligonucleotides were reduced by incubation with a 100-fold molar excess of TCEP (T2556, ThermoFisher Scientific) for 20 min at room temperature. Excess TCEP was removed by ethanol precipitation at −80 °C. For conjugation, reduced oligo-SH was added to maleimide-activated antibody at a 10:1 molar ratio (oligo:antibody), and the mixture was incubated overnight at 4 °C. Final conjugates

379   were purified using 50 kDa molecular weight cut-off centrifugal filters (Amicon Ultra) to remove unbound
380   oligo.

381   The antibody-oligonucleotide product was then hybridized to the LipiGo platform the same way as the
382   aptamer as described above.

Single particle profile (SPP) analysis of particles containing mRNA

SPP measurements were carried out as described by Sych et al.[26] To measure the number of particles
carrying mRNA cargo, cargo and lipid shell had to be labeled in different fluorescent wavelengths.
Particle cargo (mRNA) was labeled with AF-647 and the lipid particle core was labeled with Fast-
DiO(D3898, Invitrogen). Single Particle Profiling was performed using the setup for confocal acquisition
(„spot scan") at a Zeiss LSM 780 microscope. A 488 nm argon ion laser was used for FastDiO , whereas
a 633 nm He−Ne laser was used for Alexa 647. A 40×1.2 NA water immersion objective was used to
focus the light. The fluorescence emission was detected by GaAsP spectral detector in integration
mode. The emission detection windows were set as 490 –560 for FastDiO and 650 –700 for AF-647.
Intensity traces were recorded for 10 minutes, in total 5 measurements per sample. Curves were then
analysed using the python program "Py Profiler", from the reference above.

Serum stability

The stability of the particles in serum (from mice) was tested by measuring the intensity of the
fluorescent resonance energy transfer (FRET) pair, DiO/DiI-with whom the particles were labeled. A
1:10 mixture of LNPs : mouse serum or LNP:PBS (control) was incubated at 37°C and samples taken
at certain timepoints to be measured on a spectrometer (Varioskan). The fluorescence intensity
reduction was measured at excitation and emission wavelengths of 480 nm, 530 nm (DiO), and 580 nm
(DiI), respectively, to calculate the FRET efficiency. Plots were generated with GraphPad Prism, n=3,
mean is shown.

Cryo-TEM imaging of particles

The preparation of LNPs was done immediately before examination and stored in the fridge until the
measurements. 4.5ul of a concentrated LNP formulation (lipid concentration 2.3 mg/mL) was placed on
a thin carbon-reinforced copper grid for 6 min. The grid was blotted with a filter paper (blot time 4s, blot
force 0) to remove the excess of liquid to form a thin film. The samples were vitrified rapidly in liquid
ethane at −180 °C. Cryo-TEM measurements were performed using the Glacios TEM from
ThermoFisher.

Immunological profiling of injected LNPs/LipiGo particles

Plasma protein analysis

412   Mouse plasma of particle injected mice was collected after 1h or 48h of injection and stored in -80°C
413   until further analysis with a Thermo Scientific Konelab analyzers to measure the concentration of
414   plasma proteins.

FACS-based cytokine panel analysis

The LegendPlex immune panel (740929, BioLegend) allows for simultaneous quantification of 13 key
targets essential for immune response such as IL-4, IL-2, CXCL10 (IP-10), IL-1β, TNF-α, CCL2 (MCP-
1), IL-17A, IL-6, IL-10, IFN-γ, IL-12p70, CXCL8 (IL-8), and Free Active TGF-β1.6week old female

BALB/c mice were intravenously injected with different formulations (PBS only, std LNP, LipiGo
particles) containing 10 µg mRNA/mouse. After 1 h, the blood serum was obtained and used to
measure the concentration of pro-inflammatory cytokines using the cytokine panel kit. Mouse Cytokine
Panel 2 kit.
423
Protein-corona analysis
Blood serum from wild-type Balb/c mice was collected retro-orbitally (in non-coated microcentrifuge
tubes), the blood was left to clot at room temperature for 30 min and then spun down for 15 min at
2,000 r.p.m. at 4 °C to retrieve the serum (supernatant). LNPs (50 µl total volume each as described
above, encapsulating 1 µg of unlabeled mRNA per formulation) were incubated with mouse serum for
15 min at 37 °C at a 1:1 volumetric ratio. A 0.7-M sucrose solution was prepared by dissolving solid
sucrose in MilliQ water. The LNP/serum mixture was loaded onto a 300-µl sucrose cushion centrifuged
at 15 300g and 4 °C for 1.5 h. The supernatant was removed, and the pellet was washed 3 times with
1× PBS, by spinning at 15 300g and 4 °C for 5 min and carefully removing the supernatant. The protein-
covered LNPs were then kept dry at −20 °C upon mass spectrometry analysis.
To prepare the particles for MS-analysis, they were resuspended in 4% SDS-Tris-HCl buffer (4% SDS,
10 mM TCEP, pH 8.5) and incubated at 95 °C for 5 min, followed by sonication for 15 min at 4 °C.
Subsequently, 2% SDC buffer (10 mM TCEP, 40 mM CAA) was added, and samples were heated again
at 95 °C for 10 min. Proteins were precipitated by adding 3 µl of a 1:1 SpeedBeads mix and ethanol
(final concentration 75%) under agitation for 5 min. Beads were immobilized using a magnetic rack,
washed twice with 80% ethanol, and dried in a SpeedVac. Samples were digested overnight at 37 °C
in 50 µl of 50 mM TEAB containing 0.4 µg Trypsin-LysC and 0.02% LMNG. Peptides were then cleaned
using a modified Evotip PURE protocol in a 96-well format, at the end of which they were dried and
resuspended in 0.1% TFA containing 0.015% DDM for MS analysis. Finally, peptides (50 ng) were
analysed by LC–MS/MS on an EASY-nanoLC 1200 system (Thermo Fisher Scientific) coupled to a
timsTOF SCP mass spectrometer (Bruker Daltonik) via a CaptiveSpray ion source. Data were acquired
in DIA-PASEF mode with 100 ms ramp and accumulation times. For comparative analysis, 50 ng of
peptide was injected onto a 5.5-cm µPAC Neo HPLC column (Thermo Fisher Scientific) and analysed
using an 80-min gradient at a flow rate of 250 nl min^{-1}.
Data were analyzed using scanpy (v. 1.10.2) and anndata (v. 0.10.8) in Python 3.11. All proteins
expressed in less than half of the samples in each group were filtered out, the data was log-transformed
and normalized per sample. The missing values were input using KNNImputer (n_neighbors=5) from
sklearn package (v. 1.5.1). With scanpy's dendrogram function scipy's hierarchical linkage clustering
was calculated on a Pearson correlation matrix over groups which was calculated for 50 averaged
principal components. Differential expression analysis was conducted using Scanpy's method
`rank_genes_groups` with method set to `t-test`. A threshold of $p < 0.05$ and |log fold change| > 1.0
were applied to identify differentially expressed proteins (DEPs). These DEPs were subsequently
visualized using volcano plots.
457
Cellular uptake and endosomal escape experiments

HeLa or HeLa-Gal8-mRuby cells were seeded on µ-Slide 18-well glass bottom plates (81817, ibidi) with

a density of 10000 or 7000 cells/well 1 day prior to particle exposure. LNP/LipiGo particles were added

at an end concentration of 40 nM per well and cells were washed and fixed after 1h/4h or 24h.

For samples where lysosome co-staining was desired, AF488-mRNA containing particles were used.

HeLa cells were stained with lysotracker DeepRed (L12492, ThermoFisher) at an end concentration of

50 nM. 5 min before ending the experiment, cells were stained with Hoechst 33342 (H3570, Invitrogen)

at 5ug/ml in PBS 5 min before ending the experiment. Cells were gently washed 3x with warm DPBS

to remove excess dyes and then imaged live at an SP5 Leica confocal microscope, image analysis was

done with ImageJ.

To study uptake in recycling endosomes, Rab11 stainings were conducted in HeLa cells, who were

subjected to std LNPs/LipiGo particles. After the incubation of particles with cells, cells were gently

washed 3x with DPBS, fixed with 4% PFA-PBS at RT for 10 min and then permeabilized for 5 min with

0.1% Triton X-100. Blocking was done with 3% BSA (Carl Roth, 8076.2) for 30 min at RT, after which

the cells were stained with 5ug/ml Rab11A-Alexa Fluor 488 (clone 3H18L5, ThermoFisher) (in blocking

buffer) at RT for 1h. Dye removal was described as above, before fixing the cells using cold 4% PFA

(1176205000, Morphisto) for 10 min at room temperature. Cells were finally washed again (first wash

step including Hoechst) and then imaged as described above.

To visualize endosomal escape, AF647-mRNA containing particles were incubated with HeLa-mRuby

cells, who emit fluorescence at 592 nm upon endosomal rupture. Cells were washed and fixed as

described above and then imaged on a confocal microscope. Image representation and "puncta per

cell" analysis was done with ImageJ.

Aptamer-guided cell-culture targeting of white adipocytes

Standard LNPs and LipiGo(20) particles, decorated with targeting aptamers, were formulated as

described above. Cells were seeded in 8-chamber slides (LabTek II) 9 days prior to the experiment.

Differention was induced the next day (D0) with induction medium (DMEM, 10% FBS, 1% PenStrep,

IBMX-KOH, Indometacin, Dexamethason, T3, Rosiglitazon and Insulin). At D2, medium was chagend

to differentiation medium (DMEM, FBS, PenStrep, Rosi, T3, Insulin) and at D5 to differentiation medium

without Rosi.

40 min before adding the particles ,medium was changed to 130 uL fresh blocking medium (dif. medium

containing 100 mg/ L yeast tRNA). 50 ul of the particle solution was added to the wells, so that the

resulting concentration of mRNA would be 40 nM in each well. For blank samples, 50 µL of sterile PBS

was added to each well. After 40 minutes of particle incubation at 37°C, cells were washed with ice cold

PBS before being fixed with 4% PFA for 10min at RT. To quench the crosslinking reaction, cells were

incubated 15 min with 0.1 mM Glycine. Unbound particles were then gently washed away 3x with 0.1M

DPBS before conducting the staining steps.

As pretreatment for the staining, slides were placed 1 min in ice cold 1% Triton-X100-PBS, washed 3x

with PBS and then blocked with 1% BSA-PBS at RT for 30 min. Cells were then stained with DAPI

(5mg/mL, 1:5000) and Phalloidin (1:200), before being mounted with anti-fade mounting medium and

then dried for 2h at RT. Slides were imaged with a SP8 Leica confocal using a 60x objective. Image
representation and intracellular dot-based analysis was done with ImageJ.
500

***In vivo* experiments**
Female Balb/c mice were obtained from Charles River Laboratories. The animals were housed under
a 12-h light/dark cycle and had unlimited access to food and water. The temperature was maintained at
18–23 °C, and humidity was at 40–60%. The animals were housed for at least 1 week before entering
any experiments. The animal experiments were conducted according to institutional guidelines of the
German Mouse Facility at Helmholtz Munich and after approval of the Ethical Review Board of the
Government of Upper Bavaria (Regierung von Oberbayern, Munich, Germany) and under European
Directive 2010/63/EU for animal research.
509

Tissue clearing of animals (nanoDISCO)
All experiments were performed in triplicates. Mice were deeply anesthetized using a combination of
ketamine (70mg/kg) and xylazine (20mg/kg) intraperitoneally. Afterwards, the chest cavity of mice was
opened for intracardial perfusion with cold heparinized PBS (10–25 U ml−1 heparin dissolved in 0.01 M
PBS) using 100–125-mmHg pressure for 5–10 min at room temperature until the blood was washed
out. Next, the mice were perfused with cold 4% paraformaldehyde (PFA) to fix the entire mouse body
until stiffness was observed in the tail of the mice. Finally, the skin was carefully removed, and the
bodies were fixed in 4% PFA overnight at 4 °C and then transferred to PBS for further processing or
directly cleared.
The mice were rendered transparent using the nanoDISCO clearing method previously described (Ref
Roger paper). In short, mice were placed in a glass chamber and set up in a transcardial circulatory
system using peristaltic pumps. After fixation (see above), the mice were intracardially perfused with
PBS 3x for 3h, then 2x for 12h with a decolorization solution (1:4 dilution of CUBIC reagent, consisting
of 25 wt% N,N,N,N′-tetrakis (2-hydroxypropyl) ethylenediamine (Sigma-Aldrich, 122262) and 15 wt%
Triton X-100 (Fisher Scientific, 10287923)). After this, the mouse bodies were washed with PBS for
3x4h, and then perfused 2d with a decalcification solution (10 wt/vol% EDTA, pH 8.00). For visualizing
a direct signal (such as AF-labeled mRNA), no additional staining was needed and the clearing protocol
continued as follows: After another three PBS washes lasting 4h each, the mice were transferred to
passive clearing (no transcardial pumping) on a shaker under a hood. We proceeded to incubate the
mice in 70 vol% THF (Carl Roth, CP82.1), 90 vol% THF and 2 × 100 vol% THF. This was followed by a
20-min treatment with DCM (KK47.1 ,Carl Roth) and finally refractive index matching using BABB (2:1
solution containing Benzyl Benzoate (Sigma-Aldrich, W213802) and Benzyl Alcohol(Sigma-Aldrich,
1009812500) until the mouse bodies were transparent.
For visualizing an mRNA-transcribed EGFP signal, the protocol after the decalcification step continues
as follows: After another three PBS washes lasting 4h each, mice were placed in a permeabilization
solution containing 35 ul 0.5 g/L signal-enhancing nanobodies(Alexa Fluor 647–conjugated anti-GFP
signal-enhancing nanobodies, ChromoTek, gb2AF647). The permeabilization solution (0.5% Triton X-
100, 1.5% goat serum (Gibco, 16210072), 0.5 mM methyl-beta-cyclodextrin (Sigma-Aldrich, 332615)

and 0.2% trans-1-acetyl-4-hydroxy-L-proline (441562 ,Sigma-Aldrich) was actively pumped transcardially for 5 d at RT and then passively incubated with the mice for an additional 2d. Washing of unbound nanobodies was done with a washing solution (containing 0.5% Triton X-100 and 1.5% goat serum) that was applied 2x12h and 3x4h PBS wash steps. As described above, mice were then passively cleared at room temperature with gentle shaking under a fume hood by incubation in 70 vol% THF, 90 vol% THF, 100 vol% THF and again 100 vol% THF for 12 h each. Then, the mouse bodies were treated with DCM for 20 min and immersed BABB until the tissue was rendered completely transparent.

Flow cytometry (FACS)-based immune cell type analysis in animals

All experiments were performed with n=5. 1µg mRNA containing particles (LNPs or LipiGo particles) were intravenously injected into wildtype Balb/c mice and circulated for 1h, before sacrificing the mice via Ketamin/Xylazin overdose, administered intraperitoneally. After administering the anaesthesia, antibodies were injected 3 min prior to perfusion to label intravascular CD45+ cells. Before being perfused with 0.1M PBS, blood was taken from the hearts of the mice from which serum was generated for further analysis. After the perfusion, organs (spleen, liver, lymph node, bone marrow (femur)) were taken from the mice and placed directly into PBS on ice. Mononuclear phagocytes were isolated by enzymatic digestion and density gradient centrifugation, adapted from the reference[27].

For processing the liver, organs were transferred into petri dishes for mechanical dissociation with syringe backs until homogenized. The resulting tissue slurry was incubated in digestion buffer containing PBS supplemented with 450 U/mL collagenase I, 125 U/mL collagenase XI, 60 U/mL DNase I, and 60 U/mL hyaluronidase I-S (all from Sigma-Aldrich) at 37 °C for 30 min under agitation. Digested tissues were filtered through a 40 µm cell strainer into 50 mL tubes, followed by centrifugation at 500 g for 7 min at 4 °C. The resulting cell pellets were resuspended in 5 mL of 1× PBS and layered over 5 mL of Histopaque-1077 (Sigma-Aldrich) at room temperature. Samples were centrifuged at 300 g for 20 min (acceleration 3, brake 0), and the mononuclear cell layer at the interphase was collected and washed in FACS buffer (Cell Staining Buffer (420201, BioLegend)).

Lymph nodes and the spleen were treated with a slightly altered protocol, where the tissue was mechanically dissociated through a 40-µm cell strainer into 20 mL of ice-cold PBS. The cell suspension was pelleted (500 × g, 7 min, 4 °C), washed once with 1 mL of FACS buffer, and centrifuged again.

Bone marrow was harvested by removing the femoral epiphyses and flushing the marrow cavity with ice-cold PBS using a 23-gauge needle. The cell suspension was passed through a 40-µm cell strainer, and the cells were pelleted (500 × g, 7 min, 4 °C).

After these pretreatments, a common staining step followed, where isolated cells were centrifuged at 500 g for 7 min at 4 °C and resuspended in 50–80 µL of FACS buffer (Cell Staining Buffer, 420201, BioLegend). To block Fc receptors, 50 µL of buffer containing 0.5 µL Fc-block (CD16/CD32 Monoclonal Antibody (93), eBioscience™, 14-0161-85, Thermo Fischer) and 0.25 µL Zombie NIR viability dye (BioLegend) was added, followed by incubation for 10 min at RT°C. Subsequently, 50 µL of antibody cocktail was added per tube (antibodies listed below), and samples were incubated for 30 min at 4 °C. Cells were washed with 1 mL FACS buffer and centrifuged again at 500 g for 7 min. Final pellets were

resuspended in 250 μL of FACS buffer for acquisition. The cells were measured by a Cytek® Northern
Lights™ 3000.
The following fluorochrome-conjugated antibodies were used for surface staining: CD3 (clone 17A2,
BioLegend), CD45 i.v. (clone 30-F11), CD8a (clone 53-6.7, BD Biosciences), CD11b (clone M1/70,
BioLegend), CD35 (clone 8C12, BD Biosciences), CD62L (clone MEL-14, BD Biosciences), CD5 (clone
53-7.3, BD Biosciences), B220 (clone RA3-6B2, BioLegend), MHC-II (clone M5/114.15.2, Invitrogen),
CD44 (clone IM7, Invitrogen), Ly6G (clone 1A8-Ly6g, Invitrogen), Ly6C (clone AL-21, BD Biosciences),
F4/80 (clone BM8, Invitrogen), CD11c (clone N418, Invitrogen), CD45 (clone 30-F11, BioLegend), and
CD4 (clone GK1.5, BioLegend). Cell viability was determined using ZombieNIR dye (BioLegend).
TX45), anti-MHC-II (FITC, clone M5/114.15.2), anti-Ly6C (PE-eFluor610, clone 1A8-Ly6g), anti-Ly6G
(PerCP/Cy5.5, clone HK1.4), anti-F4/80 (PE/Cy7, clone BM8), anti-SIRPα (AlexaFluor700, clone P84),
and anti-CD45 (APC/Cy7, clone 30-F11). The antibody mix was generated in the buffer BD Horizon™
Brilliant Stain Buffer (566349, BD Biosciences).
590

Bioluminescence imaging
All experiments were performed in triplicates. Mice were injected with LNPs/LipiGo particles
encapsulating FLuc-mRNA 24h before imaging. 10 min before imaging the mice were deeply
anaesthezized with a Ketamin/Xylazin solution and injected with 150ul of a 15mg/ml aqueous Luciferin
solution (VivoGlo luciferin, Promega). intraperitoneally. The animals were then scanned on an IVIS
bioluminescent scanner as a whole, before being terminated via cervical dislocation. The organs from
the sacrificed mice were then quickly collected for an additional, out-of-body scanning. The exposure
time for each scan was set to 60s. The quantifications were assessed of each organ by marking them
as individual ROIs to generate the desired values using the Living Image Software version 4.2 (Caliper
Life Sciences).
601

Multiphoton imaging for particle Half-Life in blood assessments
Multiphoton imaging was performed using an upright Zeiss LSM710 confocal microscope equipped with
a Ti:Sa laser (Coherent, Chameleon Vision II) and two external photomultiplier detectors for red and
green fluorescence channels. Eight-week-old C57BL/6N mice (Charles River Laboratories) were
anesthetized via intraperitoneal injection of a medetomidine ($0.5\,mg\,kg^{-1}$), fentanyl ($0.05\,mg\,kg^{-1}$), and
midazolam ($5\,mg\,kg^{-1}$) mixture (MMF). Body temperature was continuously monitored and maintained
using a rectal probe connected to a feedback-controlled heating pad.
A catheter was inserted into the femoral artery for administration of fluorescent dyes or nanoparticles.
A 4 × 4-mm cranial window was surgically prepared over the right frontoparietal cortex under continuous
saline cooling, as previously described. To visualize brain vasculature and acquire baseline images,
mice were injected intravenously with FITC-dextran ($3\,\mu l\,g^{-1}$). The animal was then positioned on the
multiphoton microscope platform, which was adapted for intravital imaging of small animals.
Mice was anesthetized, and a rectangular 4x4-mm cranial window was drilled over the right
frontoparietal cortex under continuous cooling with saline. After implantation of glass cranial window,
mouse was placed under the microscope and the brain vessels were imaged to obtain a baseline.

Afterwards, the nanoparticles labeled with 0.5 mol % FastDIO (0.067ug/kg in a volume of 100 µl.) were
systemically injected, and serial imaging was immediately started for at least 2 h. Time-lapse imaging
was conducted at an 80-µm tissue depth using 10% laser power at 800 nm. For the FITC channel, a
GAASP detector with a long-pass (<570 nm) filter and master gain of 600 was used. The particle
channel was recorded using a long-pass (>570 nm) filter and the same master gain setting.
Fluorescence signal analysis was performed using ImageJ.
623
Light-sheet imaging and image visualization of whole cleared mice
Whole-body imaging of cleared mice was performed using a light-sheet fluorescence microscope
(Miltenyi Blaze Ultra) equipped with a 4× objective. Mice were mounted ventrally and a z-step size of
6 µm was applied. In the juvenile mice used in this study (<6 weeks of age), a Z-range of 1200–1400 µm
was typically sufficient to capture the entire body. To improve sensitivity for detecting nanoparticles, the
light-sheet width was reduced to 80%. Scanning was conducted in "light speed mode," enabling rapid
acquisition.
Laser settings were adjusted based on fluorophore characteristics: for 647-labelled mRNA, laser power
was set to 100% with an exposure time of 15 s; for background imaging, 80% power and a 5 ms
exposure were used. Prior to full dataset transfer, a subset of image tiles was stitched and assessed
for image quality to ensure suitability for downstream analysis. Tile stitching was performed on high-
performance workstations using a custom Python script. Two-dimensional image stacks were converted
to 3D volumes using Imaris Converter, and image visualization, including snapshot generation, was
carried out in Imaris Viewer.
638
SCP-nano particle quantification
The in-house developed SCP-nano pipeline consists of organ segmentation, optional manual organ
segmentation correction using VR, and subsequent blob detection, and was described in detail in Luo
et al.[15]. In short, for quantifying the particle events per organ, the relative intensity contrast of every
segmented LNP dot compared to the background intensity was calculated. The background intensity
was estimated per organ by the average intensity of voxels inside the organ while excluding voxels
belonging to segmented dots. The relative contrast values of all segmented dots were summed up to
reflect the amount of LNP in a specific area or organ. Density heat maps could then be generated based
on nanoparticle segmentation to visualize nanoparticle distribution in different organs. A sliding window
strategy was employed to compute segmented nanoparticles' local relative intensity contrast values. A
window size of 16 × 16 × 4 voxels was deployed in our experiments. Every voxel in this cube was then
assigned with the sum of relative contrast values. Finally, using a 3D Gaussian filter, we obtained a
smooth and full-resolution density map.
652
653   **Immunostaining of tissues and slide scanner imaging**
654   Fixed tissue pieces of perfused mice were dehydrated in a 30% sucrose solution and then sliced in 10
655   µm slices with a Cryostat and collected on glass slides. 6 slices in per sample were then stained with a
656   classical immunostaining protocol, consisting of 3x 5 min PBS wash, a 15 min permeabilization step

with 0.1% Triton-X100, a 1h blocking step with 3% BSA and an overnight staining step at 4°C with a primary antibody in a buffer containing 0.1% Triton and 3% BSA. Unbound antibody was removed by washing 3x with PBS, before staining with a secondary antibody for 2h at room temperature. Samples were additionally stained with Hoechst (3 min with 7 µM), before being washed 3x with PBS and 1x with ddH$_2$O. After drying, the mounting medium (VECTASHIELD Antifade, VEC-H-1000, Biozol) was used and slides were closed with cover slips, before being scanned with a slide scanner at the Helmholtz Imaging Core Facility. Automated image analysis was done using the Visiopharm software and plots generated with GraphPad Prism.

References

He, Y., Wang, Y., Wang, L., Jiang, W. & Wilhelm, S. Understanding nanoparticle-liver interactions in nanomedicine. *Expert opinion on drug delivery* **21**, 829-843 (2024).

Hosseini-Kharat, M., Bremmell, K. E. & Prestidge, C. A. Why do lipid nanoparticles target the liver? Understanding of biodistribution and liver-specific tropism. *Molecular Therapy Methods & Clinical Development* **33** (2025).

Dilliard, S. A. & Siegwart, D. J. Passive, active and endogenous organ-targeted lipid and polymer nanoparticles for delivery of genetic drugs. *Nature Reviews Materials* **8**, 282-300 (2023).

Cheng, Q. *et al.* Selective organ targeting (SORT) nanoparticles for tissue-specific mRNA delivery and CRISPR–Cas gene editing. *Nature nanotechnology* **15**, 313-320 (2020).

Rurik, J. G. *et al.* CAR T cells produced in vivo to treat cardiac injury. *Science* **375**, 91-96 (2022).

Tarab-Ravski, D. *et al.* Delivery of therapeutic RNA to the bone marrow in multiple myeloma using CD38-targeted lipid nanoparticles. *Advanced Science* **10**, 2301377 (2023).

Grzetic, D. J., Hamilton, N. B. & Shelley, J. C. Coarse-grained simulation of mRNA-loaded lipid nanoparticle self-assembly. *Molecular Pharmaceutics* **21**, 4747-4753 (2024).

Albertsen, C. H. *et al.* The role of lipid components in lipid nanoparticles for vaccines and gene therapy. *Advanced drug delivery reviews* **188**, 114416 (2022).

Wilson, S. C. *et al.* Real time measurement of PEG shedding from lipid nanoparticles in serum via NMR spectroscopy. *Molecular Pharmaceutics* **12**, 386-392 (2015).

Barbier, A. J., Jiang, A. Y., Zhang, P., Wooster, R. & Anderson, D. G. The clinical progress of mRNA vaccines and immunotherapies. *Nature biotechnology* **40**, 840-854 (2022).

Cheng, Q. *et al.* Dendrimer-based lipid nanoparticles deliver therapeutic FAH mRNA to normalize liver function and extend survival in a mouse model of hepatorenal tyrosinemia type I. *Advanced materials* **30**, 1805308 (2018).

Zaleski, M. H. *et al.* Conjugation chemistry markedly impacts toxicity and biodistribution of targeted nanoparticles, mediated by complement activation. *Advanced Materials* **37**, 2409945 (2025).

Yazdi, M. *et al.* In Vivo Endothelial Cell Gene Silencing by siRNA-LNPs Tuned with Lipoamino Bundle Chemical and Ligand Targeting. *Small* **20**, 2400643 (2024).

Mui, B. L. *et al.* Influence of polyethylene glycol lipid desorption rates on pharmacokinetics and pharmacodynamics of siRNA lipid nanoparticles. *Molecular Therapy Nucleic Acids* **2** (2013).

Luo, J. *et al.* Nanocarrier imaging at single-cell resolution across entire mouse bodies with deep learning. *Nature Biotechnology*, 1-14 (2025).

Pohar, J., Kužnik Krajnik, A., Jerala, R. & Benčina, M. Minimal sequence requirements for oligodeoxyribonucleotides activating human TLR9. *The Journal of Immunology* **194**, 3901-3908 (2015).

Campbell, J. D. Development of the CpG adjuvant 1018: a case study. *Vaccine adjuvants: methods and protocols*, 15-27 (2016).

Yoshida, T. *et al.* Introduction of sugar-modified nucleotides into CpG-containing antisense oligonucleotides inhibits TLR9 activation. *Scientific Reports* **14**, 11540 (2024).

Voke, E. *et al.* Protein corona formed on lipid nanoparticles compromises delivery efficiency of mRNA cargo. *bioRxiv*, 2025.2001. 2020.633942 (2025).

20   Swingle, K. L. *et al.* Placenta-tropic VEGF mRNA lipid nanoparticles ameliorate murine pre-
eclampsia. *Nature* **637**, 412-421 (2025).
21   Zhang, R. *et al.* Helper lipid structure influences protein adsorption and delivery of lipid
nanoparticles to spleen and liver. *Biomaterials science* **9**, 1449-1463 (2021).
22   Chen, D., Parayath, N., Ganesh, S., Wang, W. & Amiji, M. The role of apolipoprotein-and
vitronectin-enriched protein corona on lipid nanoparticles for in vivo targeted delivery and
transfection of oligonucleotides in murine tumor models. *Nanoscale* **11**, 18806-18824 (2019).
23   Davis, S. *et al.* Isolation of angiopoietin-1, a ligand for the TIE2 receptor, by secretion-trap
expression cloning. *Cell* **87**, 1161-1169 (1996).
24   Ussar, S. *et al.* ASC-1, PAT2, and P2RX5 are cell surface markers for white, beige, and brown
adipocytes. *Science translational medicine* **6**, 247ra103-247ra103 (2014).
25   Engelen, W., Meijer, L. H., Somers, B., De Greef, T. F. & Merkx, M. Antibody-controlled
actuation of DNA-based molecular circuits. *Nature Communications* **8**, 14473 (2017).
26   Sych, T. *et al.* High-throughput measurement of the content and properties of nano-sized
bioparticles with single-particle profiler. *Nature biotechnology* **42**, 587-590 (2024).
27   Simats, A. *et al.* Innate immune memory after brain injury drives inflammatory cardiac
dysfunction. *Cell* **187**, 4637-4655. e4626 (2024).

Acknowledgements
This work was supported by the European Research Council Consolidator grant (no. GA 865323),
Nomis Heart Atlas project grant (Nomis Foundation) and Helmholtz Association Program Helmholtz IVF,
ZT-I-PF-4-091, FOMIA. S.H. was funded by the Amgen Scholarship program. Additionally, we would
like to thank Prof. J. Cui for the access to dynamic light scattering measurements, the Helmholtz Core
facility for electron microscopy (Dr. Carsten Peters) for the guidance with the Cryo TEM images, the
group of Prof. Ernst Wagner for providing HeLa-Gal8-mRuby3 cells for the endosomal escape assays,
Dr. David Jürgens for running the Cytokine Assay, the Helmholtz Core Facility Imaging (Dr. Annette
Feuchtinger) for helping us with the Slide Scanner imaging and analysis, as well as Dr. Doris
Kaltenecker for serum protein analysis.

Competing Interest Statement
K.Kadletz, C.Kimna and A.Ertürk have filed for intellectual property on the hybrid nanoparticles
described herein. A.Ertürk. is a co-founder of Deep Piction. The other authors declare no competing
interests.

Authors and Affiliations

Institute for Intelligent Biotechnologies (iBIO), Helmholtz Center Munich, Neuherberg, Germany
Karoline Kadletz, Ceren Kimna, Denise Jeridi, Sofia Hu, Jakub Grzejdak, Izabela Horvath, David-Paul
Minde, Mayar Ali, Luciano Höher, Eren Aydeniz, Yagmur Ayse Kulcu, Farida Hellal, Markus Elsner, Ali
Erturk

Institute for Stroke and Dementia Research, Klinikum der Universität München, Ludwig-
Maximilians University Munich, Munich, Germany
Ceren Kimna, Olga Carofiglio, Igor Khalin, Ying Chen, Alessio Ricci, Arthur Liesz, Farida Hellal, Ali
Ertürk

Munich Cluster for Systems Neurology (SyNergy), Munich, Germany
Karoline Kadletz, Ceren Kimna, Olga Carofiglio, Igor Khalin, Ying Chen, Izabela Horvath, Alessio Ricci,
Arthur Liesz, Farida Hellal, Ali Erturk

Deep Piction, Munich, Germany
Karoline Kadletz, Ceren Kimna, Denise Jeridi, Izabela Horvath, Markus Elsner, Ali Ertürk

Faculty of Medicine, Ludwig-Maximilians University Munich, Munich, Germany
Ying Chen

TUM School of Computation, Information and Technology, Technical University of Munich, Munich, Germany
Izabela Horvath

Research Unit Adipocytes & Metabolism (ADM), Helmholtz Diabetes Center, Helmholtz Zentrum München, Neuherberg, Germany
Valentin Kenneth Reichenbach, Siegfried Ussar

German Center for Diabetes Research (DZD), Neuherberg, Germany
Valentin Kenneth Reichenbach, Siegfried Ussar

Graduate School of Neuroscience (GSN), Munich, Germany
Mayar Ali

Institute of Computational Biology, Helmholtz Munich, Neuherberg, Germany
Mayar Ali

Normandie University, UNICAEN, INSERM UMR-S U1237, Physiopathology and Imaging of Neurological Disorders (PhIND), GIP Cyceron, Institute Blood and Brain @Caen-Normandie (BB@C), Caen, France
Igor Khalin

Science for Life Laboratory, Department of Women's and Children's Health, Karolinska Institutet, Solna, Sweden
Taras Sych, Erdinc Sezgin

School of Medicine, Koç University, İstanbul, Turkey
Ali Erturk

Contributions

A.E. conceived the project as a whole, including the sections on particle design, imaging and AI analysis. K.K. conducted the particle design, K.K. and C.K conducted all experiments involving particle production and characterization, light-sheet imaging and analysis. I.H. worked on the organ segmentation, L.H. and E.A. conducted corrections using VR tools. A.L conceptualized and O.C. and A.C. conducted the experiments on immune cell analysis with FACS. K.K. and S.H. planned and S.H. executed experiments involving aptamer decoration of particles. J.G. worked on immunohistology analysis of the particles in tissues. C.K. and K.K conducted protein corona experiments, D.-P.M. performed proteomics sample preparation and mass spectrometry and M.A. conducted the proteomics analysis. S.U. and V.K.R. designed and V.K.R. conducted the adipocyte cell culture experiments. D.Jeridi. conducted all i.v. particle injections and helped with the immunology FACS experiments, clearing and imaging. Y.A.K. contributed to tissue clearing and imaging. I.K. planned and executed experiments involving intravitreal imaging. T.S. and E.S. helped set up and analyze experiments on SPP analysis of the particles. A.E., M.E. and F.H. provided overall supervision for the project. K.K. and C.K. wrote the manuscript; C.K. and M.E. revised the text, F.H. revised the figures.

Fig. 1. Design and characterization of LipiGo nanoparticles. a) Schematic of LipiGo design. Partial substitution of cholesterol with cholesterol-modified ssDNA enables ligand attachment via complementary base pairing. **b)** Representative Cryo-TEM image of LipiGo particle showing protruding DNA strands (arrows). **c)** Hydrodynamic size distribution of standard LNPs and LipiGo variants measured with DLS. **d)** Zeta potential measurements showing increased negative sharge with higher DNA substitution (N=5). **e)** mRNA encapsulation efficiency of LNPs and LipiGo variants (N=5). **f)** Stability of LNPs and LipiGo particles measured in PBS and serum supplemented media measured with FRET. **g,h)** Hydrodynamic size distribution of LipiGo before and after hybridization with IgG antibody (g) or AS1411 DNA aptamer (h). **i)** Representative confocal images of Gal8 recruitment assay in HeLa cells shows enhanced endosomal rupture at 4 h with LipiGo compared to LNPs. **j)** Quantification of Gal9 puncta per cell (N = 50 cell per condition**). k)** Representative confocal images of HeLa cells after 24 h incubation with LNP or LipiGo particles. **l)** Intravital two-photon microscopy images of LNPs and LipiGo in mouse vasculature at indicated time points. **m)** Quantification of circulation profiles showing slightly

shorter half-life of LipiGo compared to standard LNPs. **n)** Summary of measured circulation half-lives comparing standard LNPs, LipiGo particles, and DNA origami particles[15].

Fig. 2. Whole-body mRNA biodistribution assessment of LipiGo particles assessed by SCP-Nano. a) Schematic of the SCP-nano workflow: (1) fluorescently labelled mRNA-loaded nanoparticle administration, (2) whole body tissue clearing, (3) light-sheet fluorescence microscopy (LSFM) imaging and 3D reconstruction, (4) automated organ segmentation with manual refinement, and (5) deep learning-based signal quantification. **b)** Whole-body 3D projection (600 µm slice) of a mouse 1 h after i.v. injection of LipiGo. **c)** Representative LSFM images of spleen, lymph node, bone marrow and liver, comparing biodistribution of standard LNPs and LipiGo formulations. Yellow dashed boxes indicate regions of interest (ROI) with close-up views, with particularly

enhanced accumulation in immune organs for LipiGo. **d)** Comparison of spleen and liver biodistribution of nanoparticles formed with different base ionizable lipids (MC3, ALC0315, and SM-102), showing consistent spleen targeting across LipiGo variants.

Fig. 3. Quantitative profiling of LipiGo biodistribution at the organ and immune cell level. a) Light sheet fluorescence microscopy (LSFM)-based whole-body analysis workflow showing automated organ segmentation and nanoparticle signal prediction. Representative spleen region from a LipiGo-injected mouse is shown as raw (red), predicted (green), and overlay images. **b)** Quantification of relative nanoparticle accumulation across major organs 1 h post administration using SCP-nano analysis (N = 3). **c)** Representative SCP-nano quantified particle distribution density heatmaps for spleen and liver (N=2). **d)** Flow cytometry analysis of immune cells subtypes in the spleen (CD45+ cells) showing the percentage of LNP (mRNA-AF647+) positive cells in the respective immune cell populations (N=5). **e)** Quantification of AF647+ cells among F4/80+ macrophages, B220+ B cells, CD11c+ dendritic cells (DCs) and CD35+ follicular dendritic cells (FDCs) in blood, lymph nodes (LNs), spleen, and liver (N=5). Data are shown as mean ± SD.

Fig. 4. LipiGo enables functional mRNA delivery to immune cell rich organs. a) Whole-body 3D projection (600 µm) of a mouse 48 h post i.v. injection of LipiGo delivering EGFP mRNA. Dashed boxes indicate ROIs in the spleen, liver, lymph node and thymus. **b)** EGFP expression in livers of mice treated with standard LNPs or LipiGo, demonstrating reduced hepatic expression with LipiGo. **c)** Bioluminescence imaging and quantification of FLuc mRNA expression in liver and spleen 24 h post-injection of standard LNP and LipiGo (N=3). **d-g)** Immunofluorescence staining of fresh frozen tissue sections of liver (d,e) and spleen (f,g) (10 µm) showing EGFP expression (green), DAPI nuclear staining (blue), and CD45⁺ immune cells (red).

Fig 5: Specific targeting and functional mRNA delivery to white adipocytes *in vitro* and *in vivo*. a) Representative confocal microscopy image of differentiated white adipocytes after incubation with LipiGo particles conjugated with the Asc1-surface protein-targeting aptamer (AS1-LipiGo). The particles encapsulate labeled mRNA (red) and are functionalized with a FAM-labeled aptamer (green). The image shows significant internalization and co-localization of both components within intracellular compartments. Cell nuclei are stained with DAPI (blue). **b.** *In vitro* specificity assessment. The top row shows white adipocytes incubated with control formulations: non-conjugated AS1 aptamer, untargeted LipiGo, and standard LNPs lacking the DNA handle but unspecifically mixed with AS1. Only the fully conjugated AS1-LipiGo particles show significant uptake. The bottom row shows the same set of experiments performed on brown adipocytes, which lack the insulin receptor. **c-d.** Quantification of the mRNA signal inside the white (c) and brown (d) adipocytes. One-way ANOVA with Tukey's multiple comparison test with a single pooled variance is employed. **e.** Schematic overview of the *in vivo* study design. Mice were subcutaneously (s.c.) injected with either AS1-LipiGo or untargeted LipiGo particles, to evaluate targeted delivery and functional protein expression. **f.** Whole body imaging of a tissue cleared mouse showing the biodistribution of AS1-LipiGo after 1 h circulation (left) with a zoom in to inguinal

WAT (right). **g.** *Ex vivo* quantification of functional mRNA delivery. Bioluminescence signal from luciferase expression was measured in harvested organs 24 hours post-injection. The quantification reveals that AS1-LipiGo particles (**d**) mediate significantly higher luciferase expression in the target inguinal white adipose tissue (WAT) compared to the untargeted LipiGo control particles (**e**), with minimal off-target expression observed in other organs. Data are presented as mean ± s.d. (n=3 mice per group).