Enhancing the biocorrosion resistance and biocompatibility of Aluminium substrates using Graphene Oxide-PEDOT:PSS Hybrid Coating

Sourya Subhra Nasker[1], Ragnhild Elizabeth Aune[2], Amogh K. Ravi[3], Tharangattu N. Narayanan[3], and Sasmita Nayak[1,4]*

[1]School of Biotechnology, Kalinga Institute of Industrial Technology (KIIT), Bhubaneswar, Odisha 751024, India

[2]Department of Materials Science and Engineering, Norwegian University of Science and Technology (NTNU), 7491 Trondheim, Norway

[3]Materials and Interface Engineering Laboratory, Tata Institute of Fundamental Research (TIFR), Hyderabad, Telangana 500046, India

[4]Department of Microbiology, Kalinga Institute of Medical Sciences, Kalinga Institute of Industrial Technology Deemed to be University, Bhubaneswar, Odisha 751024, India

Address all correspondence to Dr. Sasmita Nayak; E-mail: sasmita.n@kiitbiotech.ac.in

Abstract

Biofilm-associated infections on medical devices remain a major clinical challenge due to antimicrobial resistance, biofouling, and biocorrosion, compromising implant longevity and biocompatibility. Conventional biomedical devices utilizing stainless steel and titanium exhibit limited resistance to biofilm-prone physiological environments, necessitating development of next-generation implant materials. While alumina (Al_2O_3) is favored for its bio-inertness, it raises concerns like leaching and systemic toxicity. Aluminum alloy 1050 (AA1050) offers intrinsic corrosion resistance via a passive oxide layer under dry conditions but remains prone to microbiologically influenced corrosion (MIC) under humid conditions. In the recent years, graphene family of materials have emerged as promising surface coating for metals and alloys due to their strong barrier properties and antimicrobial efficacy. Most graphene derivatives like GO require relatively higher concentrations to achieve antimicrobial activity, however compromising biocompatibility, limiting *in vivo* human uses. This study addresses these caveats by exploring GO activity at lower concentrations (50–500 µg/ml) on AA1050 to

achieve a balance between antimicrobial efficiency and cytocompatibility. Additionally, poly(3,4-ethylenedioxythiophene):poly(styrenesulfonate) (PEDOT:PSS, 1 µg/ml) was integrated with GO to form a hybrid coating on Al (Al_GO/P), to improve GO adhesion, and corrosion resistance. Biological evaluations against *Escherichia coli* (*E. coli*), *Staphylococcus aureus* (*S. aureus*), and *Candida albicans* (*C. albicans*) demonstrated superior antifouling and antimicrobial efficacy of Al_GO/P substrates compared to GO-coated Al (Al_GO) and bare Al surfaces. Corrosion rate, FESEM, ICP-MS, and cytotoxicity analyses further confirmed reduced biocorrosion, minimal ion leaching, along with enhanced biocompatibility of the hybrid coated surfaces. Al_GO/P containing GO at 100 and 250 µg/ml concentration achieved the optimal balance between antimicrobial activity and biocompatibility and can be used as *in vivo* implant materials. Hence, this technology can be implemented towards surface modification of biomedical devices to mitigate periprosthetic infections as well as support *ex vivo* applications requiring durable antimicrobial performance.

Keywords: *Microbiologically Influenced Corrosion (MIC); Antifouling properties; GO-PEDOT:PSS Coatings; Aluminium Alloy 1050; Biocompatibility.*

1. Introduction

Biofilms, structured microbial communities embedded within a self-produced extracellular matrix (ECM), pose a persistent clinical challenge due to their resilience to conventional therapies and impact on human health[1]. The ECM, also referred to as extracellular polymeric substances (EPS), not only supports nutrient absorption but also enhances microbial defense mechanisms against both host immune system responses and antimicrobial drugs[2]. Biofilm formation on medical devices such as implants, catheters, and ventilators often leads to chronic infections, which reduce the therapeutic effectiveness of interventions against medical device-associated infections (MDAIs). These infections significantly contribute to healthcare-associated infections (HAIs), a critical public health concern that affects approximately one in

31 hospitalized patients each day[3]. HAIs extend hospitalization periods, increase healthcare

costs and are predominantly linked to invasive medical devices[3,4]. According to the European

Center for Disease Prevention and Control (ECDC), the European Union and European

Economic Area (EU/EEA) report over 4.3 million HAI cases annually, resulting in more than

90,000 deaths, exceeding the mortality burden of both influenza and tuberculosis in the region[5–

7]. HAIs are also prevalent in the United States, where multidrug-resistant (MDR) infections

contribute substantially to high morbidity and mortality rates[8–10]. In India, the burden is

particularly severe, with HAI incidence ranging between 11% and 83% depending on the

infection type, underscoring systemic vulnerabilities in the healthcare infrastructure[11–15].

Previous research demonstrates that MDAIs are typically caused by biofilms comprising mixed

microbial communities, including Gram-negative bacteria (e.g., *Escherichia coli* and

Pseudomonas aeruginosa), Gram-positive bacteria (e.g., *Staphylococcus aureus*,

Staphylococcus epidermidis, and *Enterococcus faecalis*), and fungi, predominantly the

Candida species[16–18]. Microbial adhesion leads to biofouling, which subsequently initiates

biocorrosion through the formation of differential aeration cells. These cells accelerate

electrochemical degradation and pitting corrosion[19]. Unlike uniform corrosion, pitting results

in severe, localized damage that compromises structural integrity and releases cytotoxic metal

ions into the surrounding tissues[20]. The complex interplay between biofouling and biocorrosion

highlights a key limitation of current implant materials, emphasizing the urgent need for

surfaces engineered to resist both microbial colonization and corrosion-induced

degradation[21,22].

These challenges reflect broader limitations to traditional implant materials, including stainless

steel, aluminum, and synthetic polymers[23]. Their clinical use is often limited by cytotoxic

effects, inflammatory host responses, and rapid degradation through either chemical or

microbiologically influenced corrosion (MIC), often worsened by biofilm activity[24,25]. Metals

and alloys such as 316L stainless steel, cobalt-chromium alloys, and titanium-based materials

suffer from long-term performance issues arising from limited biocompatibility and corrosion-

induced failure[26]. In chloride-rich physiological environments, mechanical wear and corrosion

can release harmful ions such as cobalt (Co^{2+}), nickel (Ni^{2+}), aluminum (Al^{3+}), and vanadium

(V^{3+}), raising significant concerns over systemic toxicity and neurotoxic effects[27,28]. Therefore,

there is a clear need for advanced surface engineering strategies to develop materials that

effectively mitigate biocorrosion and cytotoxicity without compromising performance.

Aluminum alloy 1050 (AA1050) is widely used in multiple sectors due to its excellent thermal

and electrical conductivity[29,30]. As a commercially pure alloy with a minimum aluminum

content of 99.5%, AA1050 is particularly attractive for various applications including

packaging, transportation, and electronics[31]. Its relatively lower density further enhances its

suitability for aerospace and automotive components[29]. While alumina (Al_2O_3) serves as a

popular implant material due to its bio-inertness, other aluminum alloys like AA1050, AA1100,

AA2024, and AA6061 have yet to find clinical use in implants[32–35]. However, Al_2O_3 has

limitations, such as potential ion release from wear debris, which can trigger inflammation,

bone resorption, and aseptic loosening at the implant-bone interface, potentially resulting in

long-term Al^{3+} leaching[36–38]. Commonly used aluminum alloys such as AA1100, AA2024, and

AA6061 are unsuitable for biomedical implants due to their composition (high Si content) and

corrosion tendencies that promote tissue damage through ion release[33,39,40]. However, AA1050

demonstrates intrinsic corrosion resistance via the formation of a passive oxide layer under dry

conditions, this protective barrier becomes compromised in humid or chloride-rich

environents[41]. Under such conditions, AA1050 is vulnerable to MIC, as biofilms significantly

alter the electrochemical landscape and promote corrosion [42].

To address such issues, recent advances in nanomaterials have facilitated the development of

hybrid coatings that limit microbial adhesion and reduce the infection rates associated with

devices[43]. Among these, the graphene family of materials (Gfam), especially graphene oxide

(GO), has gained attention due to its high surface area, excellent barrier properties, strong

adhesion to metals, and broad-spectrum antimicrobial properties[44-48]. Moreover, several

studies confirms GO coating on metal surfaces such as stainless steel, titanium, aluminium,

and copper, effectively mitigates biocorrosion and microbial adhesion[49-53]. However, these

coatings typically employ high GO concentrations (0.5-10 mg/ml) to achieve enhanced

antimicrobial activity, which subsequently limits biocompatibility; restricting their applications

for *in vivo* human uses. Even though GO at a concentration of 1 mg/ml on AA1050 has been

shown to form impermeable barriers against corrosive agents (water, oxygen, ions), it poses

risk of systemic toxicity due to inflammatory responses[54-57]. This underscores the need for the

use of lower concentration of GO coating (<1 mg/ml) to balance antimicrobial efficacy while

preserving biocompatibility for safer human applications. Many recent works have reported

the integration of polymers such as Poly(2,3-dihydrothieno-1,4-dioxin)-poly(styrenesulfonate)

(PEDOT:PSS) with GO, with advantages like improved electrical conductivity[58], enhanced

conductive pathways[59], superior electron mobility[60], improving GO adhesion[61], and enhancing

corrosion resistance[62]. These observations led us to explore GO-PEDOT:PSS hybrid coating

on Al (AA1050) containing lower concentrations of GO in order to achieve a balance between

antimicrobial potential and biocompatibility while optimizing corrosion resistance.

However, several key research questions arise: (1) How does the lower concentrations of GO

influence the antifouling efficacy of GO-PEDOT:PSS hybrid coated Al (Al_GO/P) substrates

against broad-spectrum bacterial and fungal pathogens?; (2) Which GO concentration range

provides the optimal balance between antibiofilm activity and biocompatibility?; (3) Whether

the superior antimicrobial efficacy of Al_GO/P can be correlated to known mechanisms such

as higher surface hydrophobicity and ROS production relative to bare Al?; (4) Whether

Al_GO/P surfaces reduce the cytotoxicity by reducing the leaching compared to GO coating

alone on Al (Al_GO)?; and finally (5) Do the Al_GO/P substrates exhibit higher biocorrosion

resistance relative to uncoated aluminum and Al_GO substrates under similar physiological

conditions? Addressing these questions is essential for advancing healthcare-related

applications through the strategic optimization of GO-PEDOT:PSS hybrid coatings on AA1050

substrates[57].

In the present study, a concentration dependent biocompatibility assessment highlighted the

safety of PEDOT:PSS at 1 µg/ml. Next, GO at lower concentrations (50, 100, 250, and

500 µg/ml) was integrated with PEDOT:PSS (1 µg/ml), which was electrochemically deposited

on Al (AA1050) substrates (Al_GO/P). The resulting substrates were designated as Al_GO50P,

Al_GO100P, Al_GO250P, and Al_GO500P. For a comparative assessment, suitable controls

such as glass, bare Al, and GO coated Al substrates (Al_GO) without PEDOT:PSS at respective

GO concentrations (Al_GO50, Al_GO100, Al_GO250, and Al_GO500) were fabricated under

similar deposition conditions. The structural identity and elemental composition of both

Al_GO and Al_GO/P substrates were verified using Raman spectroscopy and X-ray

photoelectron spectroscopy (XPS). Surface wettability and electrical conductivity were

examined through static water contact angle (WCA) measurements and four-point probe

analysis, respectively. Furthermore, FESEM analysis was performed on the Al_GO/P

substrates to examine the uniformity of surface deposition, while porosity measurements were

carried out to evaluate porosity percentage of the Al_GO/P substrates.

The biological performance of Al_GO/P and control substrates were evaluated against

clinically relevant pathogens; Gram-negative; *Escherichia coli* (*E. coli*), Gram-positive;

Staphylococcus aureus (*S. aureus*), and fungus; *Candida albicans* (*C. albicans*), commonly

associated with healthcare-associated infections (HAIs). Initial studies included growth

inhibition assay and viability assay for both control and test Al_GO/P substrates for a

qualitative and quantitative evaluation of antimicrobial efficacy. Antifouling activity of

substrates was further assessed by examining mixed species biofilm formation in presence of control and test Al_GO/P substrates via fluorescence microscopy and crystal-violet staining. Further mechanistic understanding was obtained by evaluating the generation of intracellular and surface reactive oxygen species (ROS) following exposure to various substrates.

A detailed corrosion analysis was conducted by measuring corrosion rates under abiotic and biotic conditions, along with FESEM images showing pre- and post-immersion condition. Further assessment of MIC potential and surface leaching for the test substrates were conducted via pH monitoring and inductively coupled plasma-mass spectroscopy (ICP-MS) analysis. Biocompatibility of the synthesized substrates was monitored via direct-contact and extract (indirect) methods. Overall, this systematic experimental framework underscores the enhanced antifouling, biocorrosion resistance, and biocompatibility characteristics of the Al_GO/P hybrid substrates relative to control surfaces. However, Al_GO100P and Al_GO250P are found to be the most suitable candidates as *in vivo* implant materials, balancing antimicrobial efficacy, and optimal biocompatibility. Al_GO500P may find promising *in vitro* applications due to its excellent biocidal activity. These observations collectively establish selected Al_GO/P substrates as favorable candidates for next-generation biomedical implant materials, water purification systems, and industrial applications, to name a few, where biofilm mitigation and long-term stability are essential.

2. Experimental Procedures

2.1. Substrates synthesis and characterization

2.1.1. Substrate preparation[57,62]

Aluminium plates (AA1050) with 99.5% purity and a thickness of 1.5 mm were obtained from NALCO India Ltd. The pristine graphene oxide (GO, 0.4 wt%) was purchased from Graphenea Inc., and poly(3,4-ethylenedioxythiophene): polystyrene sulfonate (PEDOT:PSS) was obtained from Sigma-Aldrich (Cat. no. #655201). For ease of handling, aluminum sheets were sectioned into 2.5 cm × 2.5 cm and 1.5 cm x 1.5 cm squares using an electric discharge machine (EDM) wire cutter. The aluminum substrates were then polished using silicon carbide emery papers of grit sizes ranging from P320 to P2000 to improve surface suitability for electrochemical deposition.

Subsequently, the substrates underwent ultrasonic cleaning (100W, 40 kHz) in acetone [Cat. no. #31566, SRL] for 30 minutes to eliminate any remaining polishing residues and were dried at room temperature.

A facile electrochemical deposition (ECD) process, involving optimization of an aqueous electrolyte, was used to coat the sterile aluminium substrate with a GO-PEDOT:PSS hybrid layer (Al_GO/P). The GO slurry was prepared by dispersing GO in 0.1 M sodium sulfate (Na_2SO_4) [Cat. no. #59977, SRL] to form a Na_2SO_4-GO suspension. The mixture was probe-sonicated for 1 hour to ensure uniform dispersion.

GO suspensions of 50 µg/ml, 100 µg/ml, 250 µg/ml, and 500 µg/ml were prepared. The pH of each suspension was adjusted to a neutral value of 7.0 by adding 0.1 M sodium hydroxide (NaOH) [Cat. no. #68151, SRL] dropwise under continuous stirring.

At this stage, prior to deposition, PEDOT:PSS was added to the GO suspension at a

concentration of 1 µg/ml (25 µL).

Electrochemical deposition was carried out in a glass beaker using the cleaned aluminum sheet

as the working electrode and a pure copper sheet as the counter electrode. A constant positive

DC voltage of 30 V was applied using a Keithley 2601B source meter for 90 seconds to achieve

a homogenous, uniform deposition. GO coated AA1050 (Al_GO) substrates were also prepared

without PEDOT:PSS, at different GO concentrations, for a comparative analysis.

Before proceeding to biological experiments, all bare and coated substrates were sterilized by

autoclaving at 121°C under 15 lb pressure for 15 minutes, followed by ultraviolet light

irradiation for 30 minutes to ensure sterility. Finally, all samples were washed twice with

phosphate-buffered saline (PBS) and stored under sterile conditions until use.

2.1.2. Spectroscopic analyses: Raman and X-ray photoelectron spectroscopy [57,63]

The structural identity of the GO layer in the Al_GO and Al_GO/P samples was characterized

using a Renishaw inVia^{TM} confocal Raman microscope. The Raman spectra were recorded at

25°C using a 532 nm laser as the excitation source. Spectral data were collected in the range

of 101 cm^{-1} to 3202 cm^{-1} with a resolution of 0.8 cm^{-1}.

XPS measurements were performed using a ULVAC-PHI (PHI 5000 Versa Probe III) system

with nonmonochromatic Al Kα X-rays (1486.70 eV). XPS measurements were carried out in

an ultra-high vacuum (UHV) chamber with a base pressure of < (6.75 x 10−10 Torr). The high-

resolution spectra were recorded at a pass energy of 55 eV and the survey spectra were recorded

at a pass energy of 280 eV. XPS peak fitting was performed using Casa XPS software.

2.1.3. Surface morphological analysis: Field emission scanning electron microscopy

(FESEM)[57]

FESEM analysis was performed to assess the surface morphology and microstructural

variations between the bare aluminum and Al_GO/P-coated substrates. Micrographs were

obtained using a JSM-7200F Schottky FESEM (JEOL Ltd., TIFR Hyderabad Facility). The

samples (2.5 cm × 2.5 cm) were placed in an ultrahigh vacuum chamber (10^{-6} mbar) and

irradiated with high-energy electrons at an accelerating voltage of 5 kV.

To enhance surface conductivity and image resolution, samples were sputter-coated for 2

minutes with a thin layer of gold (1~2 nm) prior to imaging. Observations were conducted

using the secondary electron (SE) detection mode to obtain high-contrast micrographs of

surface features.

2.1.4. Water Contact Angle (WCA)[63,64]

The surface wettability of bare Al, Al_GO, and Al_GO/P substrates was evaluated by

measuring the static water contact angle (WCA) using a VCA Optima contact angle meter

(AST Products Inc.). The sessile drop technique was employed, in which a droplet of ultrapure

water was placed on the surface of each specimen. Images of the droplet were captured and

analyzed to determine the contact angle, thereby indicating the relative hydrophobicity or

hydrophilicity of the surface. The measurements were repeated at three different points per

sample to ensure reproducibility.

2.1.5. Four-probe conductivity measurement [65]

Bulk electrical conductivity of bare Al, Al_GO, and Al_GO/P substrates was measured using

the Van der Pauw method. A four-probe station and Keithley 2450 source meter (delta mode)

were used for this purpose. Electrical contacts were placed at the edges of the substrate, and a

10 mA current was applied to measure the sheet resistance (R_s).

The bulk conductivity (σ) was calculated using the relation:

$$\sigma = \frac{1}{R_S t} \qquad \text{(Eq. 1)}$$

where t is the thickness of the aluminum substrate. For each sample, measurements were

acquired at three different points, and the resulting data were expressed as mean ± standard

deviation computed using GraphPad Prism version 9.0 for Windows. The experiment was

conducted under 25 ± 1°C with 40% relative humidity (non-condensing) conditions, and the

conductivity values were compared across different GO concentrations.

2.1.6. Porosity Evaluation [57,66–68]

The porosity of Al_GO/P substrates were evaluated at standard laboratory temperature (25 ±

1°C) using electrochemical techniques in a 3.5 wt.% NaCl solution,[57,66–68] simulating a

corrosive environment. Due to the low intrinsic internal resistance of the electrolyte solution

(<5 Ω), iR compensation was not necessary. A three-electrode setup was configured using a

VSP-300 multichannel potentiostat/galvanostat (BioLogic, France). The working electrode

was either a bare or coated aluminum substrate, the reference electrode was Ag/AgCl, and the

counter electrode was a platinum mesh.

The active surface area was defined using an epoxy mask, exposing only 1 cm^2 of the sample.

The open circuit potential (OCP) was monitored for 30 minutes until stabilization. Tafel

polarization was carried out at a scan rate of 1 mV/s, over a potential range of ±250 mV relative

to OCP at room temperature. Tafel parameters, i.e., corrosion potential (E_{corr}) and anodic Tafel

slope (β_a) for bare Al and Al_GO/P substrates were extracted using Tafel fit function of EC-

Lab software. Polarization resistance (R_p) for bare Al and Al_GO/P samples were determined

from the same Tafel data using EC-Lab's R_p fit function, as per the approach of Creus *et al.*[69]

Electrochemical impedance spectroscopy (EIS) was performed with an AC amplitude of 10 mV over a frequency range of 100 kHz to 100 mHz, but was not used for quantitative porosity measurements.

The porosity P (%) was calculated using the following equation[69],

$$P = \left(\frac{R_{PS}}{R_P}\right) \times 10^{-\left(\frac{\Delta E_{corr}}{\beta_a}\right)} \qquad \text{(Eq. 2)}$$

where R_{PS} is the polarization resistance of bare aluminium, R_p the polarization resistance of the coated substrates, ΔE_{corr} the difference between the corrosion potential of the coated ($E_{corr,coatings}$) and bare ($E_{corr,Al}$) substrates ($\Delta E_{corr}=E_{corr,coatings} - E_{corr,Al}$), and β_a the anodic Tafel slope of the bare aluminum.

2.2. Antimicrobial and Antibiofilm Assay

2.2.1. Microbial cell culture

Candida albicans (*C. albicans*) [fungus, ATCC 76485] cells were cultivated on Yeast-Peptone Dextrose (YPD) agar [Cat. no. #G038, HiMedia] plates at 30°C for 24 hours. A single colony was selected and inoculated into YPD broth [Cat. no. #M1363, HiMedia], which was then incubated overnight at 25°C with shaking at 200 rpm. From this overnight culture, a secondary culture was initiated at a 1:100 dilution and allowed to grow until it reached the mid-logarithmic phase. The final fungal cell suspension was prepared to achieve a concentration of 10^8 CFU/ml.

Escherichia coli (*E. coli*) [Gram-negative bacterium, ATCC 29425] and *Staphylococcus aureus* (*S. aureus*) [Gram-positive bacterium, ATCC 25923] cells were grown on Luria Bertani (LB) agar [Cat. no. #G1151, HiMedia] plates at 37°C for 24 hours. A single colony was picked and inoculated into LB broth [Cat. no. #G1245, HiMedia], followed by overnight incubation at

37°C with shaking at 200 rpm. From this culture, a secondary inoculum was prepared using a

1:100 dilution, which was then grown to the mid-logarithmic phase. The final bacterial cell

suspension was prepared to achieve concentrations of 10^7 CFU/ml and 10^8 CFU/ml, depending

on the assay.

For mixed *Candida*-bacterial biofilms, a suspension was prepared by mixing 1 ml each of the

C. albicans, *S. aureus*, and *E. coli* cultures in a 1:1:1 ratio [70].

2.2.2. Microbial Growth Inhibition Assay and Cell Viability Assay[63,71]

For growth inhibition assay, Al_GO/P substrates (2.5 cm × 2.5 cm) were sterilized by

autoclaving at 121°C for 15 minutes under 15 lb pressure, followed by ultraviolet light

exposure for 30 minutes. 100 µL of bacterial suspension containing 10^7 CFU/ml was pipetted

onto different Al_GO/P and control substrates (Glass and Bare Al) inside sterile Petri plates.

These were incubated at 37°C for 2 hours under aseptic conditions. After incubation, molten

LB agar (45ºC) was poured over the substrates and allowed to solidify at room temperature.

The plates were then incubated overnight at 37°C, and bacterial colonies were analyzed the

following day. Similarly, 100 µL of *C. albicans* suspension (10^7 CFU/ml) was incubated on

distinct Al_GO/P and control substrates in sterile Petri plates for 10 hours under aseptic

conditions. Following incubation, molten YPD agar (45ºC) was poured over the surfaces and

allowed to solidify. The plates were incubated overnight at 30°C, and fungal colonies were

analyzed after 24 hours.

For cell viability assay, bacterial and fungal cells at 10^7 CFU were incubated on sterilized glass,

bare Al, Al_GO, and Al_GO/P substrates (150 µl/cm^2) in sterile Petri plates at 37°C under

constant 95% relative humidity (maintained via autoclaved deionized water channels in closed

containers to prevent desiccation). Cells were harvested at 0, 5, and 10 h, serially diluted up to

10^5-fold in normal saline, spread-plated on LB agar (bacteria) or YPD agar (fungi), and

incubated overnight at 37°C (bacteria) or 30°C (fungi). Colonies were counted the following

day, and loss of cell viability percentage was calculated using the formula:

$Loss\ of\ cell\ viability\ (\%) = \frac{CFU/ml\ at\ time\ t_0 - CFU/ml\ at\ time\ t}{CFU/ml\ at\ time\ t_0}$ (Eq.3)

The results were plotted using GraphPad Prism version 9.0 for Windows, GraphPad Software,

San Diego, CA, U.S.A. (www.graphpad.com).

2.2.3. Antibiofilm assay[57]

A mixed microbial suspension was incubated on sterilized Al_GO/P substrates (150 μl/cm²)

placed in sterile Petri dishes at room temperature. To maintain constant humidity (95% relative

humidity), the plates were placed in closed containers containing autoclaved deionized water

channels to prevent desiccation stress.

The mixed suspension was seeded onto both control and Al_GO/P-coated substrates and

incubated for 10 hours. Two different inoculum concentrations (10^7 CFU/ml and 10^8 CFU/ml)

were tested in parallel to assess biofilm formation. After incubation, 100 μL of each residual

suspension was transferred to 35mm Petri plates containing a 1:1 mixture of YPD and LB

broth, supplemented with 10% fetal bovine serum (FBS) [Cat. no. # A5256901, Gibco], and

incubated at 37°C for an additional 10 hours.

2.2.4. Fluorescence microscopy to visualize biofilm formation

After 10 hours of incubation under biofilm-stimulating conditions (37°C with 10% FBS),

biofilm-coated substrates were gently washed with sterile distilled water to remove planktonic

cells. The remaining biofilm biomass was sequentially stained using dark conditions with:

- Calcofluor white (4 µg/ml) [Cat. no. #18909, Sigma-Aldrich] for *C. albicans* (blue) [72–74]

- Acridine orange (2% solution in H$_2$O) [Cat. no. #A9231, Sigma-Aldrich] for *S. aureus* (red)[75]

- Sodium fluorescein (0.0001% solution in ethyl alcohol) [Cat. no. #46960, Sigma-Aldrich] for *E. coli* (green)[76]

The dyes were prepared according to established protocols[76]. Fluorescence imaging was performed using an EVOS Cell Imaging Station (Invitrogen) at 40× magnification. The fluorescence images were quantified to calculate mean fluorescence intensity using ImageJ software[77].

2.2.5. Biofilm biomass quantification[78]

Following 10-hour incubation, 100 µL of each suspension was seeded into wells of a 96-well plate containing YPD medium supplemented with 10% FBS and incubated at 37°C under static conditions for an additional 10 hours.

The biofilms were washed three times with Milli-Q water to remove non-adherent cells. Then, 200 µl of 0.1% (w/v) crystal violet solution [Cat. no. #TC510, HiMedia] was added to each well, and the plates were incubated at room temperature for 30 minutes on an orbital shaker at 70 rpm.

Excess stain was removed with three washes using Milli-Q water, and the wells were dried at room temperature for 30 minutes. The retained stain was solubilized with 200 µl of 70% (v/v) ethanol, and absorbance was measured at 595 nm.

- Growth control (GC): Glass substrate (100% biofilm)

- Sterility control (SC): Ultrapure water (0% biofilm)

Percentage biofilm growth was calculated using the following equation:

$$\% \, Biofilm \, growth = \frac{Sample_{A595} - SC_{A595}}{GC_{A595} - SC_{A595}} \, x \, 100 \qquad (Eq.4)$$

where $Sample_{A595}$ is the absorbance of the test substrate, SC_{A595} the absorbance of the sterility

control (0% biofilm), and GC_{A595} the absorbance of the growth control (100% biofilm). The

results were plotted using GraphPad Prism version 9.0 for Windows, GraphPad Software, San

Diego, CA, U.S.A. (www.graphpad.com).

2.2.6. Detection of ROS production[57,79]

Mixed *Candida*-bacterial suspension was seeded on sterile Al_GO/P substrates and incubated

at room temperature for 10 hours under constant humidity (95% relative humidity). 10 μM of

2',7'-dichlorodihydroflourescein diacetate (H$_2$DCF-DA) [Cat. no. #D399, Invitrogen] was

added to the suspension and incubated for 20 minutes in the dark. Imaging was performed

using an in-house fluorescence microscope (Floid cell station, 40×, Invitrogen).

To detect surface-generated ROS, 10 μM of H$_2$DCF-DA was applied directly onto washed

substrates, and green fluorescence was recorded using a Nikon ECLIPSE Ci-E microscope at

40× magnification.

Mixed bacterial cell suspension was seeded on sterile Al_GO/P substrates and incubated at

room temperature for 10 hours under constant humidity (95% relative humidity). A 10 μM

solution of the cytosolic superoxide indicator dye dihydroethidium (DHE) [Cat. no. #D1168,

Invitrogen] was used to stain the suspension for 20 minutes in the dark[80]. Following incubation,

cell imaging was performed using an in-house fluorescence microscope (Floid Cell Station,

40×, Invitrogen).

To detect ROS generated at the material surface, a separate experiment was performed: mixed

bacterial cell suspension was seeded on sterile Al_GO/P substrates and incubated at room

temperature for 10 hours under constant humidity (95% relative humidity). After incubation, the substrates were rinsed and placed under a fluorescence microscope. A 10 μM solution of DHE was then applied directly to the surface of both the control and Al_GO/P substrates. The resulting red fluorescence signal was captured using a Nikon ECLIPSE Ci-E microscope at 40× magnification. All the fluorescence images were quantified to calculate average fluorescence intensity per ROS positive cell using ImageJ software[77]. The results were plotted using GraphPad Prism version 9.0 for Windows, GraphPad Software, San Diego, CA, U.S.A. (www.graphpad.com).

2.2.7. Scanning electron microscopy (SEM)[57,63]

10^7 CFU of the mixed *Candida*-bacterial suspension were incubated over sterilized Al_GO/P substrates (150 μl/cm^2) placed in sterile Petri plates at room temperature for 10 hours under constant humidity (95% relative humidity). Following incubation, the cells were fixed with 2.5% glutaraldehyde and dehydrated through a graded ethanol series (30%, 60%, 70%, 80%, 90%), followed by treatment with 100% ethanol for 30 minutes.

The substrates were then sputter-coated with gold-palladium (1~2 nm) for 2 minutes and imaged using a Gemini SEM 450 (Zeiss, KIIT Central Research Facility).

2.3. Evaluation of Corrosion Resistance

2.3.1. Description of immersion systems [42]

The experiments were carried out in two systems consisting of glass beakers with a usable volume of 300 ml, in which the substrates were fixed to the bottom after prior sterilization. The

medium employed was a 1:1 mixture of LB and YPD broth, sterilized in an autoclave at 121°C

and 15 lb pressure for 15 minutes. Both systems were assembled under aseptic conditions.

The abiotic system (control) contained only the sterile medium along with the following

antibiotics: Fluconazole (antifungal, 15 µg/ml) [Cat. no. #22239, SRL], Chloramphenicol

(antibacterial, 15 µg/ml) [Cat. no. #97686, SRL], and Vancomycin (antibacterial, 15 µg/ml)

[Cat. no. #61078, SRL]. The biotic system included the same sterile medium, supplemented

with 1% (v/v) of the mixed *Candida*-bacterial inoculum. Both the immersion systems were

maintained at 25 ± 1°C over 45 days.

2.3.2. Weight loss measurement of the corroded substrates

After 45 days of exposure in both biotic and abiotic systems, weight loss was calculated

following the chemical cleaning procedure described in ASTM G1-03 standard[81]. After

removal of the biofilm, the samples were immersed in a 69.2 wt% nitric acid solution for

approximately 5 minutes to remove corrosion products, rinsed with distilled water to eliminate

residual acid, and then dried under flowing air.

The specimens were weighed before and after the experiment using an analytical balance, and

the corrosion rate was calculated using the following equation:

$Corrosion\ rate = \frac{(W \times K)}{(A \times T \times D)}\ \mu mpy$ (Eq. 4)

where W is the weight loss, K the unit conversion constant (8.76×10^7), A the exposed area, T

the exposure time, D the material density, and *µmpy* the corrosion rate in micrometer per year.

The measured corrosion rates were classified according to the NACE Standard RP-07-75[82],

which provides validated guidelines for the preparation, analysis, and interpretation of

corrosion measurements. All tests were performed in triplicates. Additionally, the pH of abiotic

and biotic immersion systems were monitored over 45 days. pH values were measured daily, and the average value was determined from two measurements from the same day to minimize experimental error. The results were plotted using GraphPad Prism version 9.0 for Windows, GraphPad Software, San Diego, CA, U.S.A. (www.graphpad.com).

2.3.3. Inductively Coupled Plasma-Mass Spectroscopy (ICP-MS) analysis of immersion medium[83]

After 45 days of incubation of the control and test substrates under abiotic and biotic immersion conditions, the spent media was collected for ICP-MS sample preparation. Samples were acid-digested with concentrated nitric acid (HNO_3, 65%) and incubated overnight at $25 \pm 1°C$ to ensure complete digestion of dissolved and particulate species. The digested solutions were then diluted to a final volume of 50 ml with ultrapure deionized water and filtered through 0.22 μm syringe filters to remove any remaining particulates. The filtrates were subsequently analyzed using an ICP–MS (NexION 5000, PerkinElmer, USA).

2.3.4. FESEM analysis of immersed Al_GO/P substrates

FESEM was used to investigate microstructural variations on bare aluminum, CR steel (positive control), Al_GO and Al_GO/P substrates before and after 45-day immersion in both abiotic and biotic environments.

To observe the corrosion morphology, the substrates were cleaned in accordance with the ASTM G1-03 standard[81]. Micrographs were obtained using a JSM-7200F Schottky FESEM (JEOL Ltd., TIFR Hyderabad Facility), operated at an accelerating voltage of 30 kV. Samples of 2.5 cm × 2.5 cm were placed in an ultrahigh vacuum chamber (10^{-6} mbar). Prior to imaging,

substrates were coated with a thin gold film (1~2 nm) for 2 minutes to enhance surface

conductivity and enable high-resolution image capture.

2.4. Cytotoxicity assay

2.4.1. Mammalian Cell Culture [84–87]

The Human Embryonic Kidney (HEK293T) cell line [ATCC CRL-11268] was used. HEK293T

is a well-established model and is widely employed in cytotoxicity assays, including the

evaluation of new biomaterials[88]. A frozen vial was retrieved from liquid nitrogen storage and

thawed using a standard defrosting protocol. The cells were cultured in Dulbecco's Modified

Eagle Medium (DMEM) [Cat. no. #10564011, Gibco] supplemented with 10% fetal bovine

serum (FBS) [Cat. no. # A5256901, Gibco] and 1X Antibiotic-Antimycotic solution [Cat. no.

#A002, HiMedia]) for three passages prior to experimentation.

Cells were maintained at 37°C in a humidified incubator with 5% CO_2 and 95% air. Upon

reaching approximately 80% confluency, biocompatibility experiments were initiated. Cell

counting was performed using a hemocytometer. Samples were prepared according to Sections

4.2 and 4.3 of ISO 10993-5: Biological Evaluation of Medical Devices - Part 5: Tests for In

Vitro Cytotoxicity, and the experiments were performed in compliance with Section 8 of the

same standard[89].

2.4.2. Indirect (extract) assay

HEK293T cells (passage 3) were seeded into 96-well plates at a density of $1x10^4$ cells per well

and incubated for 24 h. In parallel, extracts of the test materials were prepared. After

sterilization with 70% ethanol and ultraviolet light exposure for 30 minutes, the Al_GO/P

substrates were placed in 35 mm Petri plates containing fresh growth medium. The extraction

procedure was carried out at 37°C for 24 hours to obtain 100% crude extracts.

Once the seeded cells reached approximately 70% confluency, the culture medium was

replaced with the test extracts. Cells were incubated for an additional 24 and 48 hours. Each

condition was tested in triplicate.

Cell viability was assessed by incubating the cells in medium containing 0.5 mg/ml of 3-[4,5-

dimethylthiazol-2-yl]-2,5-diphenyltetrazolium bromide (MTT) [Cat. no. #CCK003, HiMedia]

for 2 hours. The medium was then replaced with isopropanol to solubilize the purple formazan

product, and absorbance was measured at 570 nm. Results are expressed as the percentage of

MTT signal relative to untreated control cells, which were defined as 100% viable.

Experiments were conducted according to Section 8.2 of ISO 10993-5: Biological Evaluation

of Medical Devices - Part 5: Tests for In Vitro Cytotoxicity[89]. The results were plotted using

GraphPad Prism version 9.0 for Windows, GraphPad Software, San Diego, CA, U.S.A.

(www.graphpad.com).

2.4.3. Direct contact assay

HEK293T cells (passage 3) were seeded at 1×10^4 cells per 35 mm Petri dish containing pre-

sterilized substrates (1.5 cm × 1.5 cm; 2.25 cm^2 per 10^4 cells) for direct contact assays.

HEK293T cells were incubated for 24 and 48 hours in the presence of test materials, which

were carefully placed in the center of each plate. Each test material was evaluated in triplicates.

After incubation, cell viability was measured directly by adding 0.5 mg/ml MTT reagent to the

culture medium and incubating for 2 hours. The medium was then replaced with isopropanol

to extract the formazan dye, and absorbance was measured at 570 nm. Results were reported

as percentage MTT signal compared to the control, where untreated cells were set at 100%

viability. All procedures were carried out in compliance with Section 8.3 of ISO 10993-5:

Biological Evaluation of Medical Devices - Part 5: Tests for In Vitro Cytotoxicity[89]. The results

were plotted using GraphPad Prism version 9.0 for Windows, GraphPad Software, San Diego,

CA, U.S.A. (www.graphpad.com).

2.5. Statistical Analyses

All statistical analyses were performed by one-way analysis of variance (ANOVA) using Graph

Pad Prism version 9.0 for Windows, GraphPad Software, San Diego, CA,

U.S.A.(www.graphpad.com). The data are presented as mean ± standard deviation. The

statistical significance (p-value) between the control and experimental groups is denoted by *

$(p < 0.05)$, or ** $(p < 0.01)$, or *** $(p < 0.001)$, or **** $(p<0.0001)$.

3. Results and Discussion

3.1. Material property assessment

3.1.1. Synthesis of Graphene oxide – PEDOT:PSS hybrid coated Aluminium (AA1050)
substrates

The schematic diagram illustrating the facile two-step synthesis process for graphene oxide-

coated Al substrates is presented in Figure 1. The sample preparation parameters for coating

AA1050 substrates using GO (50, 100, 250, and 500 µg/ml) in presence and absence of

PEDOT:PSS are detailed in Table 1. The inherent negative surface charge (zeta potential) of

the aqueous GO dispersion causes anodic deposition at applied potentials of 10 volts or

higher[57]. These electrostatic forces were sufficient to drive GO nanosheets toward the working

electrode – the Al substrate[90]. PEDOT:PSS was used at a concentration of 1 µg/ml in the hybrid

system to preserve biocompatibility and conductivity while enhancing the adhesion of GO to

the underneath metal (Figure S23, Supporting Information). GO coated AA1050 (Al_GO)

substrates were prepared without PEDOT:PSS, at different GO concentrations, for a

comparative analysis.

539 **Figure 1. Facile two-step synthesis process of GO coated AA1050 substrates.** Schematic
540 diagram illustrating the preparation of Al_GO and Al_GO/P substrates, including sequential
541 polishing of aluminum using SiC papers, followed by electrochemical deposition.

542 **Table 1.** The details of sample preparation parameters used for coating Al substrates using
543 varied concentration of graphene oxide sourced from Graphenea Inc.

Sample Code	GO concentration (in μg/ml)	PEDOT:PSS concentration (in μg/ml)	Voltage applied (in Volts)	Duration of deposition (in seconds)
Al_GO50	50	-	30	90
Al_GO100	100	-	30	90
Al_GO250	250	-	30	90
Al_GO500	500	-	30	90

Al_GO50P	50	1	30	90
Al_GO100P	100	1	30	90
Al_GO250P	250	1	30	90
Al_GO500P	500	1	30	90

3.1.2. Raman Spectrophotometry confirmed identity of GO on Al_GO/P and Al_GO substrates

Figure 2. (A) Raman spectra of pristine GO, Al_GO, and Al_GO/P substrates. The figure shows the Raman signatures (D and G peaks) of GO and the fabricated Al_GO and Al_GO/P substrates. **(B) XPS analysis of pristine GO, Al_GO, and Al_GO/P substrates.** Deconvoluted peaks for the C_{1s} spectra attributing to different functional groups in (i) Pristine

GO, (ii) Al_GO50, (iii) Al_GO50P, (iv) Al_GO100, (v) Al_GO100P, (vi) Al_GO250, (vii) Al_GO250P, (viii) Al_GO500, and (ix) Al_GO500P.

Raman spectroscopy serves as a widely employed tool for acquiring structural insights into carbon-based materials. The identity of commercial PEDOT:PSS was confirmed via Raman spectroscopy (Figure S1, Supporting Information). The most prominent Raman band, located around 1437 cm^{-1}, consistently exhibits a well-reproducible symmetric profile with a mixed pseudo-Voigt line shape (Figure S1, Supporting Information). Interestingly, this prominent band also displays the most substantial variation, encompassing a total shift of approximately 10 cm^{-1} within the PEDOT:PSS complex. Furthermore, our observations of the Raman signatures for the PEDOT:PSS utilized in this study are in strong concurrence with the Raman spectrum obtained from previous research[91,92]. This agreement underscores the reliability and consistency of the Raman spectroscopic characteristics of the PEDOT:PSS material used in the coating process.

The Raman spectra of graphitic carbon-based materials primarily manifest the G and D peaks, and their overtones. In Figure 2A, we present the Raman spectra of GO, Al_GO and Al_GO/P substrates. Notably for Al_GO and Al_GO/P substrates, we identified the prominent graphitic Raman peaks, namely G band at 1594 cm^{-1}, and the D band at 1328 cm^{-1}, correlating with prior literature[57,64]. The G peak primarily arises from the bond stretching of sp^2 carbon atom pairs, encompassing both ring and chain structures[93]. In contrast, the D peak is indicative of structural defects within the graphene lattice. Moreover, the variation in intensity ratios of the D and G bands reveal the characteristics of GO deposited on Al_GO/P substrates as shown in Table S1 (Supporting Information). GO exhibited an I_D/I_G ratio of 0.91, which shifted slightly to 0.93 and 0.91 for AlGO50 and AlGO50P, respectively. This ratio increased to 0.97 for AlGO100 but declined to 0.88 for AlGO100P. The I_D/I_G ratio increased to 1.07 and 0.94 for AlGO250 and AlGO500, whereas both AlGO250P and AlGO500P exhibited 0.86 (Table S1, Supporting

Information). These results confirm the successful deposition of GO on various Al_GO and Al_GO/P surfaces as shown in prior literature[57,94].

We have further calculated the full-width at half-maximum (FWHM) values presented in Table S1, Supporting Information. This clearly demonstrates that PEDOT:PSS modifies the structural environment of GO in a meaningful and systematic way. Smaller FWHM values for both D and G bands and consistently lower I_D/I_G ratios in Al_GO/P substrates (Table S1, Supporting Information) point towards more ordered and less defective carbon framework[95]. This improvement can be attributed to the interactions between GO and PEDOT:PSS. Oxygen atoms from the sulfonate groups of PSS may participate in strong electrostatic and hydrogen bond interactions with GO's hydroxyl, epoxy, carbonyl and carboxy functionalities[96]. Likewise, PEDOT provides positively charged sites that interact with the negatively charged functionalities of GO[97]. Such interactions may stabilize the GO sheets, reducing lattice distortions and defects[98]. Thus PEDOT:PSS not only coats the GO surface but also reorganizes the carbon lattice making it more structurally ordered and defect free.

Next, XPS was performed to understand the chemical modifications induced by PEDOT:PSS incorporation into GO across the test concentrations (50, 100, 250 and 500 µg/ml). Survey spectra confirmed the presence of carbon and oxygen as the dominant elements in the Al_GO and Al_GO/P substrates (Figure S2A, Supporting Information). High-resolution C_{1s} spectra were deconvoluted to resolve the contributions from aromatic sp^2 carbon, C-O groups, carbonyl groups and C-S/C-S-O functionalities associated with PEDOT:PSS (Figure 2B).

A systematic distinction is observed between the Al_GO control and the Al_GO/P samples, particularly at lower GO loadings (50 and 100 µg/ml). In the Al_GO substrates (Al_GO50 and Al_GO100), the C_{1s} is dominated by aromatic sp^2 carbon (~ 284.4 eV), reduced aromatic carbon (~ 283.4 – 283.5 eV) and a carbonyl component (~ 287.3 to 287.5 eV)[99]. In contrast,

the corresponding Al_GO/P samples (Al_GO50P and Al_GO100P) exhibited entirely different

chemical signatures. First, the reduced graphitic carbon peak is absent, indicating PEDOT:PSS

disrupts or masks the reduced sp^2 domains present in the Al_GO samples[100]. Second, the

Al_GO/P samples displayed new oxygenated and sulfur-containing groups (C-S/C-S-O peaks

at ~ 285.1 – 285.7 eV)[101] and a distinct C-O (PEDOT ring) contribution (287.0 eV)[102]. These

features are consistent with the chemical structure of PEDOT:PSS and confirm its successful

incorporation into the GO matrix.

At higher GO concentrations (250 and 500 µg/ml), both Al_GO and Al_GO/P samples

exhibited similar sets of functional groups (aromatic sp^2 carbon, C-C/C-H and carbonyl

species), reflecting the dominance of GO associated features at higher mass fractions[99]. Pristine

GO (Figure 2Bi) exhibited the functionalities similar to Al_GO500 substrate. Nevertheless,

even in these higher GO concentrations, the PEDOT:PSS containing Al substrates consistently

shows higher C:O ratios (Table S2 and Figure S2B, Supporting Information), apart from the

lower GO concentrated samples. All these collectively confirm the successful modification of

the surface chemistry of GO by PEDOT:PSS.

3.1.3. FESEM confirmed uniform deposition of GO on Al surfaces

Electrochemical deposition (ECD) of GO on Al surface is expected to produce a smooth and

uniform coating, as the quality of the coating is determined by its homogeneity[62,103]. We

employed an FESEM analysis of the bare Al surface and coated test surfaces (Al_GO/P)

FESEM micrographs of the bare Al and Al_GO/P substrates are shown in Figure 3, providing

visual evidence of GO nano-sheets overlaying on the Al substrate The polished Al surface

exhibits a non-uniform and rough surface morphology characterized by the presence of

potholes and cavities. Accordingly, the FESEM images of Al_GO/P substrates demonstrated

smooth GO sheets with small wrinkles, folded at the edges as evidenced in existing

literature[57,63]. FESEM micrographs, therefore, confirmed the uniform deposition of the GO

coatings on Al_GO/P surface via ECD method.

Figure 3. FE-SEM micrographs of bare Al vs Al_GO/P surfaces. FESEM images display
(i) polished Al, and uniform deposition of GO on Al_GO/P substrates: (ii) Al_GO50P, (iii)
Al_GO100P, (iv) Al_GO250P, and (v) Al_GO500P.

*3.1.4. Hydrophobic and Conductive nature of Al_GO/P surfaces confirmed by water contact
angle (WCA) and four-probe conductivity measurements*

The deposition of GO on Al substrates has been reported to enhance the surface

hydrophobicity[57]. This increase in hydrophobicity is attributed to the uniform GO coating,

which alters the surface energy and reduces wettability[104,105]. Current study evaluated the

wettability of the bare Al, Al_GO, and Al_GO/P substrates, relying on the stationary WCA

measurements (Table 2 and Figure S3, Supporting Information). The water contact angle of

bare Al was 85.1°, but increased to over 90° for Al_GO and Al_GO/P surfaces, showing an

increase in surface hydrophobicity (Table 2 and Figure S3, Supporting Information). Among

the test samples, Al_GO500P had the highest WCA at 120.2°, followed by Al_GO250P

(114.9°), Al_GO100P (106.8°), and Al_GO50P (101.6°). Following the similar trend, the

control substrates, such as Al_GO500 had the highest WCA at 109.5°, followed by Al_GO250

(105.5°), Al_GO100 (103°), and Al_GO50 (94.2°). Taken together, these results indicate that

increasing GO and GO-PEDOT:PSS loading changes the Al surface towards a hydrophobic

state, which is expected to enhance the barrier properties against aqueous electrolyte

penetration while simultaneously promoting closer microbial contact with the substrate

surface[106]. In this work, a stable contact is advantageous, as it promotes a prolonged interaction

of microbial cells to the GO-rich surface, thereby facilitating contact-mediated antimicrobial

activity[57].

However, the role of surface hydrophobicity in microbial attachment is more nuanced and

strongly depends on the interplay between surface chemistry and physicochemical properties

of the microorganisms themselves. Microorganisms generally exhibit stronger attachment on

hydrophobic surfaces due to favorable hydrophobic–hydrophobic interactions and reduced

interfacial free energy at the solid–liquid boundary[107,108]. On the other hand, hydrophilic

surfaces tend to act as a physical and energetic barrier to microbial attachment, thereby

suppressing early-stage colonization. In this context, the higher WCA values measured for the

Al_GO/P substrates suggest that these surfaces may promote stronger microbial adhesion

relative to bare Al, which is moderately hydrophilic.

Additionally, the electrical conductivity measurements for bare Al and Al_GO/P substrates are

detailed in Table 2. It is worth noting that pure aluminum possesses inherently high electrical

conductivity, registering at 3.43×10^7 S/m (equivalent to 59.14% of the International Annealed

Copper Standard, IACS), consistent with previous literature[109]. In the current work,

conductivity of the aluminum alloy AA1050 was determined to be 3.11×10^7 S/m, which is

slightly lower than that of pure aluminum but falls within the same order of magnitude. It was

observed that while the conductivity of the Al_GO and Al_GO/P substrates shows a relative

reduction compared to the bare Al surface used in this study, the values were within the conductivity ranges for known materials [110–112]. Moreover, this reduction in conductivity becomes more obvious with increasing GO concentration as detailed in Table 2. As the GO concentration increases, the conductivity of the Al_GO and Al_GO/P substrates decreases since GO disrupts the continuous sp^2 carbon network needed for efficient electron transport, as in pristine graphene[113]. Higher GO loading introduces more oxygen-containing functional groups, which convert conductive sp^2 regions into insulating sp^3 regions and break up the π-electron pathways. This phenomenon may be attributed to the inherent insulating nature of graphene oxide, as previously documented[114]. It is plausible that the reduction in conductivity is a consequence of the expansion of interlayer spacing among the GO nanosheets due to the presence of functional groups within the basal planes[115].

Table 2. Stationary water contact angle (WCA) and electrical conductivity values of the synthesized Al_GO/P substrates and control surfaces; bare Al, Al_GO50, Al_GO100, Al_GO250, and Al_GO500.

Samples	WCA (in degrees)	Electrical Conductivity (S/m) x 10^7
Bare Al	85.1 ± 0.4	3.1 ± 0.7
Al_GO50	94.2 ± 4.3	1.8 ± 0.5
Al_GO100	103.0 ± 0.7	1.4 ± 0.2
Al_GO250	105.5 ± 1.2	1.4 ± 0.3
Al_GO500	109.5 ± 0.9	1.2 ± 0.2
Al_GO50P	101.6 ± 1.0	2.2 ± 0.5
Al_GO100P	106.8 ± 0.2	1.9 ± 0.2
Al_GO250P	114.9 ± 4.5	1.8 ± 0.2
Al_GO500P	120.2 ± 2.9	1.6 ± 0.4

3.1.5. Porosity evaluation of Al_GO/P substrates

The presence of porosity in coatings directly correlates to lower density and reduced

compactness of the coating than the bulk metal[68]. Moreover, a porous coating decreases their

protective ability as it allows foreign particles, microorganisms, or corrosive ions to reach and

potentially damage the underlying metal, and cause corrosion[57,116]. The corrosion potential

(E_{corr}) and anodic potential (β_a), and polarization resistance (R_p) for bare aluminium and

Al_GO/P substrates were determined through Tafel fit and R_p fit function of EC-Lab software

utilizing the Tafel plot (Figure 4). The R_p fit and Tafel fit parameters are presented in Table S3

(Supporting Information), and the Nyquist impedance plots are displayed in Figure S4,

Supporting Information.

The details for the porosity measurements for GO coatings is described in the Experimental

Procedures and the results are provided in Table 3. The Al_GO/P substrates exhibited

porosities of 89.1% (Al_GO50P), 82.5% (Al_GO100P), 65.4% (Al_GO250P), and 32%

(Al_GO500P), demonstrating a gradual reduction in porosity with increased GO

concentration(s) on the Al surface(s).

Figure 4. Tafel plot analysis. Linear polarization response comparison between bare Al vs Al_GO/P substrates.

Table 3. Electrochemical characteristics of bare Al and Al_GO/P substrates and porosity (%) calculation

Sample	Polarization Resistance, R_{PS}	Polarization Resistance, R_P	Corrosion Potential, $E_{corr,Al}$ (V)	Corrosion Potential, $E_{corr, Coatings}$ (V)	ΔE_{corr}	Anodic Potential, $\beta_{a,Al}$ (mV)	Porosity (%)
Al_GO50P	145	163	-0.47	-0.49	-0.02	32.40	89.10
Al_GO100P	145	176	-0.47	-0.49	-0.02	32.40	82.50
Al_GO250P	145	222	-0.47	-0.49	-0.02	32.40	65.40
Al_GO500P	145	454	-0.47	-0.48	-0.01	32.40	32.00

As per prior literature porosity measurements have also been correlated to the corrosion resistance properties. Coating porosity critically governs corrosion resistance at the microscopic level by controlling electrolyte penetration pathways to the underlying metal[117]. This influence becomes evident when contrasting the effects of large, open pores with small,

isolated ones[118]. In systems with large pores, electrolyte and oxygen can circulate freely,

facilitating stable passivation and improved resistance to corrosion. In contrast, small pores

tend to trap electrolytes and deplete oxygen, promoting aggressive micro-environments for

crevice corrosion. Moreover, coatings with low porosity percentage has been shown to

maximize barrier performance by restricting ion transport pathways[69,119]. Current results

suggest a reduction in porosity percentage with increase in GO concentration for the Al_GO/P

test surfaces (Table 3). The observed porosity percentage reduction is from 89.1% through

32%, corresponding to increased GO concentration from 50 to 500 µg/ml. Therefore, surfaces

with higher GO concentration with lower porosity percentage should improve corrosion

resistance as per earlier literature. The assessment of the corrosion properties for the

synthesized substrates is mentioned later in this manuscript.

3.2. Assessment of antimicrobial potential of Al_GO/P substrates

3.2.1. Al_GO/P inhibited growth of microbial cells

In a preliminary study, growth inhibition assay was conducted to evaluate the antimicrobial

activity of the fabricated Al_GO/P substrates. This is a conventional technique where microbial

cells are exposed to substrates for a specific time, followed by growth on nutrient rich medium

overnight[63]. The antibacterial and antifungal activities of Al_GO/P substrates (Al_GO50P,

Al_GO100P, Al_GO250P, and Al_GO500P) were tested against Gram-positive *S. aureus*,

Gram-negative *E. coli*, and fungus *C. albicans*. Bare Al (uncoated Al sheet) and glass slides

were used as control surfaces.

Figure 5. Growth Inhibition Assay of Al_GO/P substrates. After 10 hour of incubation on different control (glass and bare Al) and Al_GO/P substrates, (**A, B**) bacterial (*E. coli, S. aureus*) and (**C**) fungal (*C. albicans*) cells were cultured overnight on LB and YPD agar plates, respectively. The inhibitory roles of the coated substrates were assessed by examining colony growth the following day. Cells cultivated on glass and bare Al surfaces exhibited abundant bacterial and fungal colonies, indicating a lack of antimicrobial potential. In contrast, cells cultured on Al_GO50P presented minimal colony growth while rest of the Al_GO/P substrates demonstrated no visible colony growth.

Figures 5A, 5B and 5C show the bacterial (Gram-positive *S. aureus* and Gram-negative *E. coli*) and fungal (*C. albicans*) colonies on LB and YPD agar plates, respectively. Control surfaces glass and bare Al displayed rich growth of microbial colonies for both bacterial and fungal species. While significantly low colony growth was observed on Al_GO50P substrate, no bacterial and fungal cell growth were noted on rest of the Al_GO/P substrates. Thus, the growth inhibitory activity of these substrates was conserved across all the microbial species with Al_GO100P, Al_GO250P, and Al_GO500P exhibiting a higher inhibitory potential compared to controls (glass and bare Al), whereas Al_GO50P displayed a moderate inhibitory effect. However, control Al_GO substrates without PEDOT:PSS failed to display significant growth inhibitory activity relative to Al_GO/P test substrates (Figure S5, Supporting Information)

For a comparative analysis, microbial growth inhibition was performed in presence of pristine

GO as shown in Supporting Information (Figure S6A). Relative to the activity of GO, the

fabricated substrates were shown to exhibit superior antimicrobial potential towards both

bacterial and fungal cells. Besides, evaluation of PEDOT:PSS activity revealed no intrinsic

antimicrobial potential over a wide concentration range (1 µg/ml, 50 µg/ml, 100 µg/ml, 250

µg/ml, 500 µg/ml, 1 mg/ml, and 2 mg/ml) (Figure S6B, Supporting Information). Therefore,

the relative efficacy of Al_GO/P substrates could be correlated to varied concentrations of GO

on Al_GO/P substrates correlating to earlier literatures[120,121].

Next, cell viability assay was conducted for a quantitative evaluation of the antimicrobial

nature of Al_GO/P substrates. Percentage loss of cell viability was calculated via spread plate

method following exposure to different control (Glass, bare Al, Al_GO50, Al_GO100,

Al_GO250, and Al_GO500) and test (Al_GO50P, Al_GO100P, Al_GO250P, and Al_GO500P)

substrates for a period of 0, 5, and 10 hours as described in the Experimental Procedures. For

E. coli cells (Figure S7A, Supporting Information), at 5 h, the control surfaces showed minimal

loss of cell viability, with glass at 1.9%, bare Al at 4.4%, Al_GO50 at 4.1%, Al_GO100 at 9%,

Al_GO250 at 17.1%, and Al_GO500 at 20.9%. The corresponding test substrates showed

markedly higher loss in cell viability percentage, with Al_GO100P at 44.1%, Al_GO250P at

94.2%, and Al_GO500P at 95.1%, while Al_GO50P caused only 16.3% loss in cellular

viability. At 10 h, the loss of cell viability when exposed to controls remained low, with glass

at 4.4%, bare Al at 6.4%, Al_GO50 at 8.7%, Al_GO100 at 14.3%, Al_GO250 at 19.6%, and

Al_GO500 at 23.4%. The Al_GO/P substrates gave rise to higher loss in cell viability, with

Al_GO100P at 65.7%, Al_GO250P at 95.1%, and Al_GO500P at 97%. Al_GO50P induced

only a 20.1% loss in cell viability following exposure to *E. coli* cells.

In case of *S. aureus* (Figure S7B, Supporting Information), 5 h exposure caused minor loss in

cell viability on control surfaces, with glass at 1.5%, bare Al at 1.7%, Al_GO50 at 2.6%,

Al_GO100 at 3.6%, Al_GO250 at 5.1%, and Al_GO500 at 4.8%. In contrast, the Al_GO/P

surfaces showed higher loss in cell viability percentage, with Al_GO250P at 96.1% and

Al_GO500P at 96.6%, while Al_GO50P at 7.8% and Al_GO100P at 27.9% displayed

drastically low loss in cell viability percentages. After 10 h, negligible loss in cell viability

were displayed by control substrates: glass at 2.4%, bare Al at 3.3%, Al_GO50 at 4.7%,

Al_GO100 at 6.1%, Al_GO250 at 6.3%, and Al_GO500 at 7.0%. The Al_GO/P substrates

yielded higher loss in cell viability, with Al_GO100P at 88.1%, Al_GO250P at 97.1%, and

Al_GO500P at 98.2%, while Al_GO50P at 15.1% failed to show antimicrobial activity.

For *C. albicans* cells (Figure S7C, Supporting Information), 5 h exposure on control substrates

resulted in glass at 1.2% loss, bare Al at 1.8%, Al_GO50 at 1.8%, Al_GO100 at 3.5%,

Al_GO250 at 2.5%, and Al_GO500 at 15.4%. Al_GO/P substrates exhibited higher antifungal

activity, with Al_GO100P at 50.2%, Al_GO250P at 97.4%, and Al_GO500P at 98.5%, except

Al_GO50P at 3.3%. By 10 h, loss of cell viability in presence of glass was 1.9%, bare Al 3.1%,

Al_GO50 2.6%, Al_GO100 5.5%, Al_GO250 3.8%, and Al_GO500 44.8%; whereas the

Al_GO/P samples produced viability loss of 73.2% (Al_GO100P), 98.3% (Al_GO250P), and

99.4% (Al_GO500P), except Al_GO50P at 6%. Overall, substrates Al_GO250P and

Al_GO500P achieved near complete loss (~100%) of cell viability, closely followed by

Al_GO100P, showing superior broad-spectrum antimicrobial activity. However, Al_GO50P

remained the least effective. Additionally, cell viability assessments were further validated

using standard antimicrobials as positive controls: chloramphenicol (15 µg/ml) against *E. coli*

cells, vancomycin (15 µg/ml) against *S. aureus* cells, and fluconazole (15 µg/ml) against *C.*

albicans cells; exhibiting complete inhibition of microbial growth at both 5 h and 10 h

(Figure S8, Supporting Information) of exposure time.

3.2.2. Al_GO/P substrates demonstrate potent antibiofilm activity

Figure 6. Fluorescence microscopic images of mixed species (*C. albicans*, *S. aureus*, and *E. coli*) biofilm formation (10^7 CFU). Mixed candida-bacterial suspensions were exposed, (**A, B**) to control surfaces (glass and bare Al), and (**C–F**) to various Al_GO/P substrates. Post-exposure, mixed species biofilm were allowed to grow for 10 hours under biofilm stimulating conditions after which the samples were stained with calcofluor white (*blue*), acridine orange (*red*), and sodium fluorescein (*green*) to visualize *C. albicans*, *S. aureus*, and *E. coli*, respectively. Biofilms were imaged using an in-house fluorescence microscope at 40× magnification.

Biofilms are mixed community of microbial population adherent to various biotic and abiotic

surfaces[2]. These organized microbial structures play a crucial role in infection dissemination,

antibiotic resistance, and may pose a threat to the host's immune system[122]. As previously

reported, the antimicrobial efficacy of GO has been well documented across literature[53,123–125].

In this study, we have evaluated the activity of GO-PEDOT:PSS coated Al (Al_GO/P) surfaces

towards mixed species (*C. albicans*, *S. aureus*, and *E. coli*) biofilm formation by examining the

progress of biofilm maturation over a period of 10 hours under biofilm stimulating conditions.

Fluorescent stains were used to visualize Gram-positive *S. aureus* (acridine orange, red), Gram-

negative *E. coli* (sodium fluorescein, green), and fungus *C. albicans* (calcofluor white, blue).

Control surfaces, such as glass (Figure 6A) and bare Al (Figure 6B), demonstrated dense

biofilm formation consisting of bacterial cells within intricate fungal hyphae. This indicates

robust microbial colonization on these surfaces that provide a favorable environment for

biofilm maturation. On the contrary, significant biofilm inhibition was observed on Al_GO/P

substrates. A complete disruption of biofilm structure with only a few adherent microbial cells

were noted in presence of Al_GO500P (Figure 6F), closely followed by Al_GO250P (Figure

6E), Al_GO100P (Figure 6D). A moderately inhibited biofilm structure was visualized in

presence of Al_GO50P (Figure 6C).

Further to show the robust activity of Al_GO/P, antibiofilm potential was examined at a higher

microbial load of 10^8 CFU (Figure S9, Supporting Information). The extent of antibiofilm

activity of Al_GO/P substrates were comparable when tested with 10^7 CFU and 10^8 CFU of

mixed microbial population. These findings further support the broad-spectrum antimicrobial

nature of the Al_GO/P substrates as shown by growth inhibition assay, while substrates with

higher GO concentrations yield a more pronounced biofilm inhibitory effect. For a

quantitatively assessment, mean fluorescent intensity (MFI) was calculated from fluorescent

images of mixed biofilms both at 10^7 and 10^8 CFU using ImageJ software (Figure 6 and Figure

S9, Supporting Information). Compared to glass and bare Al controls, Al_GO/P test surfaces exhibited a significant decrease in the MFI for biofilm densities at both the inoculum concentration (10^7 and 10^8 CFU), indicating compromised microbial attachment (Figure S10, Supporting Information).

Next, crystal violet (CV) staining technique was performed to quantitate mixed species (10^7 CFU) biofilm formation over various test substrates. Glass was used as a positive growth control exhibiting 100% biofilm formation. It was observed that biofilm biomass was lowest when exposed to Al_GO500P, decreasing significantly to 14.3% ($p < 0.0001$), indicating the highest inhibitory activity among the tested Al_GO/P surfaces (Figure S11 and Table S4, Supporting Information). This was followed by Al_GO250P and Al_GO100P, with biofilm biomass reductions to 39.3% and 48.5%, respectively ($p < 0.0001$ for both). The biofilm biomass was reduced to 91.3% ($p > 0.05$) in presence of Al_GO50P, indicating the least inhibitory effect (Figure S11 and Table S4, Supporting Information). A similar result was obtained at higher microbial inoculum load at 10^8 CFU (Figure S12 and Table S4, Supporting Information).

Current results highlights a clear correlation between increasing GO concentration on Al surface and its inhibitory effect on biofilm formation. Al_GO50P appears to have a non-significant ($p > 0.05$) role in biofilm inhibition, whereas Al_GO/P substrates with higher concentration of GO (100, 250, and 500 μg/ml) could remarkably inhibit biofilm formation. Besides, a non-significant ($p > 0.05$) inhibition of biofilm formation over bare Al (Figure S11, Figure S12 and Table S4, Supporting information) suggested a superior antibiofilm activity of Al_GO/P surfaces. Additionally in a comparative study, we used pristine GO at corresponding concentrations, which resulted in non-significant ($p > 0.05$) inhibition of biofilm formation relative to control surface glass (Figure S13 and Table S4, Supporting Information). A pairwise analysis of antibiofilm efficacy between pristine GO and test surfaces indicated significant

inhibition (p < 0.0001) induced by Al_GO/P at corresponding concentration (Figure S14,

Supporting Information). The quantitative data of the antibiofilm assay for control and test

substrates are provided in Table S4, Supporting Information.

Summarizing the results from growth inhibition (Figure 5), cell viability (Figure S7,

Supporting Information) and antibiofilm assays; it was observed that Al_GO100P, Al_GO250P,

and Al_GO500P substrates exhibit superior antimicrobial activity compared to Al_GO50P and

control surfaces. This is possibly due to the suppression of microbial cell growth, colonization,

and biofilm maturation in the presence of Al_GO/P substrates[57]. Furthermore, the overall lower

porosity percentage of Al_GO/P substrates at increasing GO concentrations from 50-500 µg/ml

(Table 3) may have contributed to the enhanced antimicrobial activity by limiting microbial

adhesion[116]. Further analysis via SEM is required to visualize the membrane-damaging

(biocidal) activity of Al_GO/P, as demonstrated in the following section.

3.2.3. Al_GO/P substrates induced cell membrane damage in mixed species microbial cell population

Figure 7. SEM analysis to visualize mixed microbial (*C. albicans*, *S. aureus*, and *E. coli*) cells. Representative SEM micrographs show the morphology of mixed *C. albicans* (*arrowheads, yellow*), *S. aureus* (*arrowheads, pink*), and *E. coli* (*arrowheads, green*) cells after

10 hours of exposure to different control and test substrates: (**A**) Glass, (**B**) Bare Al, (**C**) Al_GO50P, (**D**) Al_GO100P, (**E**) Al_GO250P, and (**F**) Al_GO500P. Images captured at 5000× and 10,000× magnifications (*dashed circles, cyan*) revealed extensive membrane damage, and complete loss of cellular architecture in microbial cells exposed to Al_GO100P, Al_GO250P and Al_GO500P, compared to the intact morphology observed on control surfaces (Glass, Bare Al). Exposure to Al_GO50P resulted in minor morphological alterations, such as fused and wrinkled cell structures.

In a comprehensive study examining the effects of Al_GO/P surfaces on bacterial and fungal cells, SEM was employed to analyze alterations in cellular architecture and membrane integrity. SEM analysis revealed that cells exposed to the control surfaces (glass, bare Al) maintained their normal cellular morphology, appearing healthy and uniform (Figure 7A and 7B). Exposure to Al_GO50P, displayed less severe but notable morphological damage, including fused cells with wrinkled appearance (Figure 7C). In contrast, exposure to the Al_GO100P (Figure 7D), Al_GO250P (Figure 7E), and Al_GO500P (Figure 7F) induced significant damage to cell membrane with complete loss of cellular architecture for all (*C. albicans*, *S. aureus*, and *E. coli*) cell types. The study demonstrated consistent biocidal activity of the test substrates (Al_GO100P, Al_GO250P, Al_GO500P) towards a mixed microbial population consisting of Gram-positive and Gram-negative bacteria, as well as fungi.

The enhanced biocidal activity of Al_GO/P may be correlated to superior surface hydrophobicity at different GO concentrations relative to bare Al (Table 2 and Figure S3, Supporting Information). This may have facilitated sustained interactions between the microbial cell wall and the Al_GO/P surfaces, thereby compromising membrane integrity[126]. Besides, we cannot exclude the possibility of electron transfer events occurring in a conductive background of the Al_GO/P substrates, which may lead to the generation of reactive oxygen species (ROS), as shown in previous literature[57,63]. Next, we investigated ROS generation at the substrate interface and intracellularly to further validate the underlying biocidal mechanism of the Al_GO/P substrates.

3.2.4. Al_GO/P substrates induce intracellular and surface ROS production

Figure 8. Evaluation of (A, B) intracellular, and (C, D) surface ROS production on Al_GO/P substrates using H₂DCFDA and DHE dye. Following exposure to various test and control surfaces **(A)** Mixed microbial cell population (*C. albicans*, *S. aureus*, and *E. coli*) were stained with H₂DCFDA dye (green cells), and **(B)** mixed bacterial cells consisting of *S. aureus* and *E. coli* were stained with DHE dye (red cells), for detection of intracellular ROS production. No ROS production was observed on glass, and only minimal signal was detected on Al relative to the test substrates. Abundant fluorescent signals correlating to intracellular ROS generation were observed for the bacterial and fungal cells exposed to Al_GO500P, Al_GO250P, and Al_GO100P surfaces using H₂DCFDA (green) and DHE (red) fluorescent dyes. Al_GO50P induced relatively lesser number of fluorescent cells; Detection of ROS production on the surface of Al_GO/P substrates after a 10-hour of exposure to **(C)** mixed population of cells (*C. albicans*, *S. aureus*, and *E. coli*) using H₂DCFDA dye (green fluorescence), and **(D)** mixed bacterial cells (*S. aureus* and *E. coli*) with DHE dye (red fluorescence). ROS indicator dyes H₂DCFDA and DHE were applied on different test and control surfaces. No ROS production was noticed on the surface of Glass and Al relative to test substrates. Varied levels of abundant fluorescent signals correlating to ROS generation were observed on the surface of Al_GO500P, Al_GO250P, and Al_GO100P as revealed by H₂DCFDA (green) and DHE (red) stains. Relatively mild signal was detected on the surface of Al_GO50P. Cells were imaged using in-house fluorescence microscope at 40× magnification.

The catalytic generation of ROS at metal-environment interfaces is a well-characterized

process, mediated by physicochemical interactions that promote oxidative stress

conditions[127,128]. These interactions involve complex mechanisms, including redox reactions

and surface modifications, which could mediate the transfer of electrons and lead to the

formation of ROS[63]. The production of ROS can have significant implications for both the

metal surfaces and the biological systems they interact with, potentially affecting cellular

responses[127]. In this work, ROS production was evaluated using the indicator dye 2',7'-

dichlorodihydrofluorescein diacetate (H$_2$DCF-DA) after exposing mixed (bacterial and fungal)

microbial cells to various Al_GO/P substrates. This dye is effective in detecting a wide range

of ROS, including hydrogen peroxide (H$_2$O$_2$), hydroxyl radicals (•OH), and other reactive

species such as carbonate radicals and nitric oxide[129]. When ROS are present, the initially non-

fluorescent H$_2$DCF-DA is transformed into the highly fluorescent compound 2',7'-

dichlorofluorescein (DCF+), which emits a green signal observable through fluorescence

microscopy.

In addition, dihydroethidium (DHE) is also utilized for ROS detection. DHE displays blue

fluorescence in the cell cytoplasm; however, upon reacting with superoxide anions, it is

oxidized to form 2-hydroxyethidium, which intercalates into DNA and exhibits red

fluorescence (DHE+). This makes DHE particularly useful for detecting cytosolic superoxide

(O$_2$•$^-$)[129]. It can also undergo nonspecific oxidation by other radicals like peroxynitrite

(ONOO−) and hydroxyl radicals (•OH). In this work, H$_2$DCFDA dye was employed to assess

the overall oxidative stress levels in mixed *Candida*-bacterial cell suspensions because it

broadly detects multiple ROS species, including H$_2$O$_2$, •OH, and others, after deacetylation to

DCFH, yielding green-fluorescent DCF$^+$ suitable for overall oxidative stress assessment across

diverse cell types. Additionally, DHE was utilized specifically for mixed bacterial cell

suspensions (*S. aureus* and *E. coli*) due to its higher selectivity for superoxide ($O_2 \bullet^-$), the primary ROS generated in prokaryotic cells.

We observed that Al_GO/P substrates, especially Al_GO500P, Al_GO250P, Al_GO100P exhibited a significantly higher number of DCF+ signals indicative of elevated ROS relative to control surfaces both intracellularly (Figure 8A) and at the substrate surface (Figure 8C) in mixed pathogen populations consisting of *S. aureus*, *E. coli*, and *C. albicans*. This was closely followed by Al_GO50P displaying relatively lower number of DCF+ fluorescent cells. The control Al surface showed minimal DCF+ signal, while the glass surface displayed no detectable DCF+ (green) signal at all. The elevated ROS levels may directly correlate to an electron transfer event from the microbial cells to the GO functional groups over conductive substrates causing surface ROS production. Elevated intracellular ROS production is indicative of cell death and the activation of related cell signaling pathways[130].

We further examined the presence of cytosolic superoxide in a mixed bacterial population both intracellularly (Figure 8B) and at the substrate interface (Figure 8D). Similar to our observation in Figure 8A and 8C, control surfaces such as glass and bare aluminium, did not exhibit any DHE+ (red) cells, indicating a lack of ROS production overall. Conversely, varying numbers of fluorescent DHE+ cells were observed on different Al_GO/P substrates. Notably, Al_GO500P, Al_GO250P, and Al_GO100P induced a higher population of DHE+ cells than Al_GO50P. It is plausible that extending the exposure time on the substrate surface may lead to a greater number of ROS-positive cells. ROS production was quantified as average fluorescence intensity per cell using ImageJ analysis of H_2DCFDA and DHE stained images. For H_2DCFDA staining (Figure S15A, Supporting Information), bare Al exhibited baseline intracellular and surface ROS levels. Al_GO/P substrates showed concentration-dependent ROS elevation with increasing GO concentration, demonstrating significantly higher intracellular and surface ROS compared to bare Al. Similarly, DHE staining (Figure S15B,

Supporting Information) followed this trend, with moderate to high intracellular and surface ROS generation across Al_GO/P substrates. Notably, bare Al showed no detectable ROS-positive cells with DHE staining. Previous studies have highlighted the role of ROS in the broad-spectrum antimicrobial activity of graphene and its derivatives[57,131]. In fact, oxidative stress can lead to oxidation of proteins, lipids, and nucleic acids in microbial cells, resulting in irreversible membrane damage and cell death[132]. The pronounced microbiocidal activity observed for Al_GO100P, Al_GO250P, and Al_GO500P substrates may be attributed to the conductivity of these substrates (Table 2), possibly facilitating electron transfer from the microbial cell onto the GO surface, enhancing ROS generation. Besides higher surface hydrophobicity values for Al_GO/P substrates (Table 2), may have promoted a stable microbial interaction causing contact mediated membrane damage and ROS induced stress. Although Al_GO50P exhibited higher conductivity, its antimicrobial performance was less, likely due to its lower surface hydrophobicity, causing an attenuated microbial cell interaction with its surface.

3.3. Assessment of anticorrosion potential of Al_GO/P substrates

3.3.1. Al_GO/P substrates exhibit biocorrosion resistance

The corrosion rate of the fabricated Al_GO/P substrates was primarily assessed in two designated immersion systems (abiotic and biotic), for a comparative analysis[133]. The abiotic system consisting of growth media and antibiotics allowed to evaluate the chemical corrosion properties of Al_GO/P surfaces, free from biological contamination. Concurrent assessment of the biotic system in presence of microbial cells, monitored microbiologically influenced corrosion (MIC) potential of Al_GO/P substrates. This dual approach not only provides a comprehensive understanding of the corrosion behaviour of the fabricated Al_GO/P substrates but also highlights their potential effectiveness in real-world applications, where both chemical

(abiotic) and biological (biotic) factors influence corrosion rates[134]. Additional control materials such as cold-rolled steel (CR steel), which is recognized as a highly corrosive material [135], and bare Al were included for the study. Besides, the non-polymeric Al_GO substrates were included for a comparative analyses. Although both chemical corrosion and MIC involve material degradation, chemical corrosion generally proceeds faster and more aggressively due to its direct chemical interactions with the metal surface, especially in high-temperature or harsh environments[136]. Whereas MIC, also an electrochemical process, relies on the activity of microorganisms and their metabolites to promote corrosion, often under specific conditions[25]. While biofilms can occasionally form protective layers under specific conditions[137,138], they typically accelerate microbiologically influenced corrosion (MIC) through multiple mechanisms including differential aeration cells, production of corrosive metabolic byproducts, and extracellular polymeric substance (EPS) concentration effects, to name a few[25].

Figure 9. Corrosion rates and pH changes of various control and Al_GO/P substrates over 45 days of exposure to abiotic and biotic environments. (A) Corrosion rate(s) of different controls and test substrates after 45 days of exposure to abiotic and biotic immersion environments. Error bars represent ±1 standard deviation (SD) from mean of three independent biological replicates (n=3). **(B)** pH values of **(i)** abiotic and **(ii)** biotic immersion environments in presence of different controls, Al_GO, and Al_GO/P substrates over a period of 45 days.

Figure 9 illustrates the corrosion rates of various substrates after 45 days of immersion in the studied systems, highlighting the effects of both abiotic and biotic conditions. In the abiotic system, the corrosion rates were measured as follows: 1528.3 ± 0.1 µm/year for CR steel (Figure 9Ai), 94.3 ± 0.8 µm/year for aluminium (Figure 9Aii); 64.3 ± 1.8 µm/year for Al_GO50 and 38.8 ± 0.5 µm/year for Al_GO50P (Figures 9Aiii and 9Aiv); 53.0 ± 9.5 µm/year for Al_GO100 and 36.9 ± 0.5 µm/year for Al_GO100P (Figures 9Av and 9Avi); 52.7 ± 3.4 µm/year for Al_GO250 and 35.4 ± 1.0 µm/year for Al_GO250P (Figures 9Avii and 9Aviii); 51.1 ± 7.6 µm/year for Al_GO500 and 15.3 ± 4.1 µm/year for Al_GO500P (Figures 9Aix and 9Ax). In contrast, the corrosion rates in the biotic system were recorded as follows: 2674.2 ± 0.3 µm/year for CR steel (Figure 9Ai), 74.2 ± 0.8 µm/year for aluminium (Figure 9Aii); 75.3 ± 2.9 µm/year for Al_GO50 and 31.6 ± 0.5 µm/year for Al_GO50P (Figures 9Aiii and 9Aiv); 65.4 ± 3.7 µm/year for Al_GO100 and 17.6 ± 0.6 µm/year for Al_GO100P (Figures 9Av and 9Avi); 57.5 ± 0.8 µm/year for Al_GO250 and 1.0 ± 0.8 µm/year for Al_GO250P (Figures 9Avii and 9Aviii); 49.0 ± 3.0 µm/year for Al_GO500 and 0.6 ± 0.3 µm/year for Al_GO500P (Figures 9Aix and 9Ax). It was noted that, in general, the immersion systems lacking microbial presence (abiotic) tended to display higher corrosion rates than the corresponding biotic conditions in agreement with prior literature [136,139,140]. However, a known corrosive material CR steel did not exhibit this trend, but displayed highest overall corrosion rates. These observations align with the understanding that chemical corrosion often occurs at a faster and higher rate than MIC, which is primarily driven by electrochemical reactions in aggressive environments[136,139,140].

Corrosion rates for the Al_GO/P substrates immersed in the abiotic system corresponded to a

moderate corrosion intensity as defined by the NACE Standard RP-07-75[82].

The substrates in biotic immersion systems showed lower corrosion rates, reflecting the

variability of MIC, which can be influenced by factors such as the type of microorganisms

present and their metabolic by products [24,25]. Further, in the biotic system, Al_GO/P substrates,

particularly Al_GO500P and Al_GO250P, followed by Al_GO100P and Al_GO50P, exhibited

significantly lower corrosion rates compared to the control surfaces (bare Al and CR steel),

indicating enhanced resistance to MIC. This may be explained by a reduction in porosity

percentage with increase in GO concentration for the Al_GO/P test surfaces, which leads to

reduced microbial adhesion, enhanced barrier characteristics and improved corrosion

resistance [141–144]. Moreover, Al_GO/P displayed lower corrosion rate compared to the

corresponding non-polymeric Al_GO substrates (Figures 9Aiii-x) possibly due to higher

stability and reduced leaching as evaluated by ICP-MS later.

Additionally, FESEM analysis revealed distinct morphological alterations in control samples

(bare Al, CR steel, and Al_GO) compared to the synthesized test Al_GO/P substrates following

immersion under abiotic (Figure S16 and S17, Supporting Information) and biotic (Figure S18

and S19, Supporting Information) environments. These observations align with the corrosion

rate analyses (Figure 9A), underscoring the superior anticorrosion performance of the GO-

PEDOT:PSS functionalized Al system. In contrast, uncoated bare Al, CR steel and Al_GO

surfaces exhibited pronounced localized pitting and deep corrosion features, suggesting their

susceptibility towards chemical corrosion as well as MIC. For visual comparison, the optical

images of the control and test substrates captured before and after immersion in abiotic and

biotic environments are presented in Figure S20 (Supporting Information).

Additionally, the pH variation in both abiotic and biotic immersion systems was monitored

over a period of 45 days. The pH of each immersed sample was recorded daily, and the average

value was determined from two measurements to minimize experimental error. Under abiotic

conditions (Figure 9Bi), CR steel displayed a pH rise to alkaline values (~7.4 to ~8.5) over the

45 day immersion time, possibly due to release to Fe^{2+}. Bare Al demonstrated a pH rise from

~7.4 to 8.5 during the early phase (0-7 days), possibly driven by Al dissolution and $Al(OH)_3$

hydrolysis generating OH^- ions[145], followed by mid-late phase pH stabilization (7-45 days)

possibly due to accumulation of corrosion products and surface passivation[146]. Likewise,

Al_GO surfaces displayed pH rise to an alkaline value, may be due to compromised barrier

activity of GO coating in the absence of PEDOT:PSS[147]. Al_GO/P substrates maintained nearly

constant pH (7.4) under abiotic immersion condition, likely due to the superior barrier

properties of GO-PEDOT:PSS and improved adhesion on Al surface.

In biotic conditions (Figure 9Bii), CR steel demonstrated an sharp pH drop to an acidic range

(6–5.5) over the 45 day immersion period. Similarly, bare Al, Al_GO50, Al_GO100,

Al_GO250, and Al_GO500 gave rise to overall acidic pH likely due to microbial colonization

and release of microbial products during the immersion period[148,149]. In contrast, Al_GO/P

surfaces induced a neutral pH (7.0~7.5) condition in the immersion medium throughout,

possibly due to inhibition of microbial colonization and strong antibiofilm effect (Figure 6).

Previous studies have demonstrated that antimicrobials can serve as green corrosion inhibitors.

For instance, Obot and coworkers in 2008 reported fluconazole (antifungal) as an excellent

corrosion inhibitor for aluminium in acidic medium (0.1M HCl)[150]. Similarly, Ayoola *et al.*

reported the corrosion protection of chloramphenicol (antibiotic) on A315 mild steel in 0.1 M

HCl[151], while Alamry *et al.* showed the inhibitory capacity of ampicillin (antibiotic) on mild

steel in 5% HCl[152]. However, the anticorrosion performance noted for Al_GO/P substrates in

the abiotic immersion system cannot be attributed to such inhibitory roles of antimicrobials,

since pH analysis (Figure 9Bi) confirmed neutral conditions. Further the pH environment for

the control surfaces were alkaline over 45 day immersion period, ruling out corrosion inhibitory

potential for the antimicrobials used for the study. Therefore, in the current work, the

antimicrobials used in the abiotic system, did not influence the observed corrosion rates for the

test substrates.

Next, ICP–MS analysis was conducted to evaluate the long-term stability of the substrates after

45 days of immersion under abiotic and biotic conditions (Table S5, Supporting Information).

Under abiotic conditions, Fe^{2+} ions were detected at a concentration of 3 ppm for the known

corrosive control, CR steel. The release of Al^{3+} ions was measured as 0.82 ppm, 0.02 ppm, 0.26

ppm, 0.88 ppm, and 1.30 ppm for bare Al, Al_GO50, Al_GO100, Al_GO250, and Al_GO500,

respectively. In comparison, the Al_GO/P substrates demonstrated markedly lower Al^{3+} ion

release, with concentrations of 0.03 ppm (Al_GO50P), 0.09 ppm (Al_GO100P), 0.33 ppm

(Al_GO250P), and 0.43 ppm (Al_GO500P), indicating superior corrosion protection.

Under biotic conditions, Fe^{2+} ion concentration was comparatively lower (2 ppm) for CR steel,

indicating moderated corrosion dynamics under microbial environment. The corresponding

Al^{3+} ion release values were 0.75 ppm, 0.05 ppm, 0.12 ppm, 1.04 ppm, and 1.56 ppm for bare

Al, Al_GO50, Al_GO100, Al_GO250, and Al_GO500, respectively. Similar to abiotic

environment, the Al_GO/P substrates showed reduced ionic leaching, with Al^{3+} ion

concentrations of 0.01 ppm (Al_GO50P), 0.04 ppm (Al_GO100P), 0.45 ppm (Al_GO250P),

and 0.54 ppm (Al_GO500P).

Thus, the observed overall suppression of ion leaching in the Al_GO/P coatings under both

abiotic and biotic conditions may be attributed to improved surface integrity arising from

molecular-level interactions between GO and PEDOT:PSS[153]. The oxygenated functional

groups on GO (hydroxyl, epoxy, carbonyl, and carboxyl) provide negatively charged sites that

electrostatically associate with the positively charged PEDOT backbone, while simultaneously engaging in hydrogen bonding and dipolar interactions with the sulfonate-rich PSS domains. In parallel, the sulfonate oxygens of PSS establish additional electrostatic and hydrogen-bonding contacts with these GO functionalities, creating a dense interfacial network that possibly "locks" the GO sheets into the PEDOT:PSS matrix and suppresses GO leaching[154]. Taken together, these noncovalent interactions may stabilize the GO carbon lattice within the GO–PEDOT:PSS hybrid coating, such that PEDOT:PSS primarily serves as an adhesive interlayer that enhances GO adhesion at the molecular level rather than acting as an independent functional component.

Collectively, these results underscore the long-term stability of GO-PEDOT:PSS hybrid coated Al system in improving corrosion resistance under chemical and bio-corrosive environments. Improved GO adhesion due to PEDOT:PSS and higher surface hydrophobicity of Al_GO/P substrates may further enhance a stable interaction with GO, inducing contact-killing mechanisms (GO-edge effect, ROS production) more efficiently. These findings are further supported by results from the antibiofilm assays (Figure 6, Figure S11 and Table S4, Supporting Information), SEM analysis (Figure 7), ROS generation (Figure 8), and corrosion analysis (Figure 9 and Table S5, Supporting Information). The reduced surface leaching and superior corrosion resistance properties of Al_GO/P surfaces, led us to evaluate the biocompatibility of the test substrates.

3.4. Cytotoxicity assessment: Al_GO50P and Al_GO100P demonstrate superior biocompatibility

MTT assay is a widely utilized method for assessing cytotoxicity, while relying on the metabolic activity of living cells[86,155]. This method involves the reduction of the yellow tetrazolium salt, MTT (3-(4,5-dimethylthiazol-2-yl)-2,5-diphenyltetrazolium bromide), to an insoluble purple formazan product by mitochondrial enzymes present in metabolically active cells. The amount of formazan produced is directly proportional to the number of viable cells, allowing for quantification through absorbance measurements at 570 nm.

For biocompatibility assessment, Al_GO1000P, featuring a GO concentration of 1 mg/ml, was included for comparative analysis with the test Al_GO/P substrates[57]. We conducted MTT assay with material extracts as well as direct exposure to the substrates to gain a comprehensive understanding of their effects on HEK293T kidney cell lines[156,157]. Given that the release of nanomaterials from antimicrobial surfaces poses a significant concern, potentially leading to systemic toxicity affecting various organs and functional systems, it was crucial to investigate this further[27]. An extract test was performed on controls (glass, bare Al, and Al_GO) and test Al_GO/P substrates to determine leaching-related cytotoxicity of HEK293T cells [87]. The quantitative values used to plot the graphs are tabulated in Table S6A and S6B (Supporting Information) for indirect (extract) and direct contact assay, respectively.

The assessment of HEK293T cell viability after exposure to the Al_GO/P material extracts (indirect contact assay) (Al_GO50P, Al_GO100P, Al_GO250P, Al_GO500P, Al_GO1000P) revealed non-significant (p > 0.05) impact on cell growth or viability cell population when compared to the control HEK293T cells in growth media alone (Figure 10A and Table S6A, Supporting Information). No changes in HEK293T cell viability were observed upon indirect contact with the glass surface, as anticipated. In contrast, extracts from bare aluminum resulted

in a notable decrease in HEK293T cell viability, dropping to 71.9% ($p \leq 0.0001$) and 72.6% (p

≤ 0.0001) at 24 and 48 hours, respectively; compared to unexposed control cells, which

exhibited a viability of 100% at similar time points. As shown by previous literatures, systemic

toxicity concern arise from the ability of bare aluminum to release ions (Al^{3+}) or particles that

can disrupt cellular function, leading to reduced viability and potential long-term health

effects[158,159]. Current results suggested that fabricated Al_GO/P substrates possess a stable GO-

PEDOT:PSS coating, effectively minimizing the risk of harmful leaching and subsequent

toxicity.

Additionally, direct contact assay was conducted to validate uses of Al_GO/P substrates for

potential *in vivo* biomedical applications. HEK293T cell viability data (Figure 10B and Table

S6B, Supporting Information) indicate that exposure to Al_GO50P (89.5% at 24 h and 95.8%

at 48 h; $p > 0.05$) and Al_GO100P (90.9% at 24 h and 96.1% at 48 h; $p > 0.05$) resulted in no

significant change in HEK293T cell viability compared to the control. Al_GO250P (86.7% at

24 h, $p > 0.05$; 84.3% at 48 h, $p = 0.0116$) caused a non-significant inhibition of cell viability

percentage over 24 h, with a mild inhibition of viable cells at 48 h. In contrast, Al_GO500P

(82.5% at 24 h, $p = 0.0234$; 84.1% at 48 h, $p = 0.0108$) showed a moderate reduction in cell

viability over 24-48 hour. Notably, Al_GO1000P (64.9% at 24 h, $p < 0.0001$; 59.1% at 48 h, p

< 0.0001) caused a significant decrease in HEK293T cell viability. HEK293T cells exposed to

bare Al demonstrated similar loss in cell viability percentage, 77.5% at 24 hours ($p = 0.0038$)

and 53% at 48 hours ($p < 0.0001$). As expected there was no alteration in the viability of

HEK293T cells in direct contact with the glass surface. These results collectively highlight the

superior biocompatibility of Al_GO50P, Al_GO100P, and Al_GO250P underscoring their

potential for possible biomedical applications.

As a comparative study, we additionally synthesized Al_GO control substrates without

PEDOT:PSS and evaluated their cytotoxicity via extract (indirect) and direct contact assays.

Results revealed that Al_GO substrates exhibited significantly low cell viability percentages

relative to Al_GO/P substrates (Figure S21, Supporting Information), indicating that the

incorporation of PEDOT:PSS in Al_GO/P system displayed improved biocompatibility. We

further examined the cell viability of HEK293T cells exposed to pristine GO and PEDOT:PSS

at corresponding test concentrations. The cell viability percentage(s) decreased with increasing

concentrations of pristine GO (50 µg/ml, 100 µg/ml, 250 µg/ml, 500 µg/ml, and 1000 µg/ml)

and PEDOT:PSS (1 µg/ml, 50 µg/ml, 100 µg/ml, 250 µg/ml, 500 µg/ml, 1 mg/ml, and 2 mg/ml)

(Figures S22 and S23, Supporting Information) when exposed to HEK293T cells for a period

of 24 and 48 hours. Notably, PEDOT:PSS at a concentration used to prepare the hybrid coating

in this study (1 µg/ml) led to nonsignificant alteration to HEK293T cell viability.

1340

1341

1342

1343

1344

1345

1346

1347

1348

1349

1350

1351

1352

1353

Indirect contact (extract) assay

A

B

Direct contact assay

1354

1355

1356

1357

1358

1359

1360

1361

1362

1363

1364

1365

1366

1367

1368

Figure 10. Cytotoxicity evaluation of control and Al_GO/P substrates. Comparison of cell viability, assessed by MTT method in the DMEM culture medium, after exposure to (**A**) Al_GO/P sample extracts by indirect contact assay and (**B**) after direct contact with the Al_GO/P samples; at (**i**) 24-hour and (**ii**) 48-hour. Data are expressed as % values of result obtained in comparison to control cells (HEK293T) not exposed to materials or material

extracts. Results from indirect contact assay showed Al_GO/P substrates maintained optimal biocompatibility compared to bare Al over 48 hours. While direct contact assay indicated high cell viability for Al_GO50P and Al_GO100P, with Al_GO250P showing minor viability changes at 48 hours, while significant decreases were observed for Al_GO500P and Al_GO1000P over 48 hours. Error bars represent ±1 standard deviation (SD) from mean for three independent biological replicates (n=3). Statistical significance was assessed using one-way ANOVA; specific p-values of <0.05, <0.01, <0.001, and <0.0001 were indicated as *,**,***, and ****, respectively.

Current findings confirm that Al_GO/P surfaces do not exhibit elevated leaching, as evidenced by the extract (indirect) assay (Figure 10A), corrosion rate measurements (Figure 9A) and ICP-MS analysis (Table S5, Supporting Information). HEK293T cells exposed to extracts (indirect contact assay) from all Al_GO/P test surfaces maintained optimal viability comparable to the untreated controls, whereas extracts from bare aluminium caused a significant (p < 0.0001) reduction in cell viability. The corrosion resistance properties of the Al_GO/P substrates demonstrated in this study likely attenuated the cytotoxic effects associated with ion leaching, as reported in prior literature[160,161]. Additionally, direct contact assays displayed healthy, viable HEK293T cells in presence of Al_GO50P and Al_GO100P surfaces, with no statistically significant differences from the controls. In contrast, direct exposure to bare Al (p < 0.0001), Al_GO500P (p = 0.0108), and Al_GO1000P (p < 0.0001) surfaces resulted in significant inhibition of HEK293T cell viability over a period of 48 hours. Al_GO250P did not influence cell viability over 24 hour of exposure time, however induced minor alteration in viability (p < 0.05) after 48 hour of direct exposure. This indicates the possibly use of Al_GO250P for short-term biomedical applications. While Al_GO500P exhibited remarkable antibiofilm properties (Figure 6F), the significant loss of HEK293T cell viability suggest potential cytotoxicity concerns in direct-contact mediated biomedical applications. Therefore, Al_GO500P may be more suitable towards *in vitro* or exterior uses where robust antimicrobial activity is essential. Although, Al_GO50P demonstrated excellent biocompatibility, it lacked

significant antimicrobial, and antibiofilm efficacy, indicating a need for further optimization to enhance its performance. Overall, substrates Al_GO100P and Al_GO250P achieved a desirable balance, combining high biocompatibility and effective antibiofilm activity, and thus stand out as promising candidates for *in vivo* biomedical device applications where cellular compatibility and biofouling resistance are paramount.

In summary, the current results signify that GO-PEDOT:PSS hybrid coated Al demonstrates enhanced antibiofouling, biocorrosion resistance, and biocompatibility properties. Effective GO-PEDOT:PSS hybrid coating on Al surfaces might provide necessary surface integrity enhancing growth inhibition, loss of microbial cell viability, and biocidal activity, upon exposure to substrate surface. The broad-spectrum antimicrobial activity was supported by significant mitigation of mixed-species biofilm formation when exposed to Al_GO/P surfaces. Moreover, the surface hydrophobicity observed on the test Al_GO/P surface might play a distinct role by stabilizing microbial interaction increasing efficient exposure. Further, conductive Al_GO/P surfaces may facilitate electron transfer from microbial cells to the GO functional groups that leads to ROS production. Additional investigations highlight the superior corrosion resistance properties of Al_GO/P substrates through lower corrosion rates, maintenance of neutral pH, and reduced Al^{3+} ion leaching (ICP-MS). Biocompatibility tests highlighted the potential of Al_GO/P to be used as *in vivo* biomedical implant material. Notably, comparative studies with Al_GO substrates lacking PEDOT:PSS polymer exhibited markedly reduced antimicrobial activity, biocorrosion resistance, and biocompatibility compared to Al_GO/P surfaces. Although, PEDOT:PSS alone demonstrated no intrinsic antimicrobial activity in our experiments (Figure S6B, Supporting Information), ICP-MS analysis confirmed the critical contribution to reduced ionic leaching and long-term stability of the Al_GO/P substrates relative to Al_GO surfaces (Table S5, Supporting Information).

4. Conclusion

Biofilms are implicated in 60–70% of nosocomial infections and significantly increase the risk of medical device-associated complications, leading to higher infection rates, morbidity, and mortality in clinical settings[162]. The resilience of biofilms to conventional antibiotics underscores the urgency for innovative surface technologies that can effectively prevent microbial colonization and reduce HAIs. Considering these challenges, there is a critical need to design and systematically assess novel materials possessing broad-spectrum antifouling capabilities, while minimizing cytotoxicity and biocorrosion.

Addressing the phenomenon of MIC and understanding the basis of material degradation becomes essential for safe application in human environment. This represents an intersection where biotic and abiotic factors converge to accelerate material degradation through complex bio-electrochemical processes[24,136]. Apart from electrochemical corrosion process, microbial metabolites containing organic acids, carboxyl groups, lower the pH of the metallic environment, accelerating corrosion[149]. Prior research demonstrates that biofilm formation on metal surfaces can alter the microenvironment and cause an increased corrosion rate[163,164]. Extensive scientific literature demonstrates that metal corrosion results from synergistic interactions of multiple mechanisms rather than a single pathway, with biocorrosion operating in tandem with chemical corrosion processes to accelerate material degradation[25,163–165]. Moreover, aluminum alloys are particularly susceptible to MIC due to their inherent tendency to form passive oxide layers, which can be compromised by microbial metabolites leading to localized pitting and crevice corrosion[148]. Although PEDOT:PSS lacks intrinsic antimicrobial activity, it was incorporated to aid GO adhesion and barrier properties. PEDOT:PSS integration is known to enhance mechanical integrity and conductivity of Al-GO/P surfaces while potentially adding barrier protection against corrosive species[166].

Building upon this understanding, the antibiofouling, biocorrosion resistance and biocompatible nature of the synthesized Al_GO/P substrates were investigated. In order to evaluate the significance of PEDOT:PSS as an additive, Al_GO control surfaces were prepared without PEDOT:PSS. Broad-spectrum antimicrobial activity was assessed qualitatively and quantitatively via growth inhibition and cell viability assay, respectively. Results from antimicrobial assays demonstrated the superior antimicrobial properties of Al_GO100P, Al_GO250P, and Al_GO500P compared to Al_GO50P, Al_GO, and bare Al (Figure 5, Figures S5 and S7, Supporting Information).

Likewise, Al_GO/P substrates; Al_GO100P, Al_GO250P, and Al_GO500P displayed disrupted biofilm structures (Figures 6D, 6E, and 6F) and significantly lower biofilm biomass (Table S4, Supporting Information) relative to bare Al (Figure 6B and Table S4, Supporting Information). These findings were further substantiated through advanced microscopic (SEM) analysis confirming the biocidal nature of the Al_GO/P substrates except Al_GO50P (Figure 7C), which failed to show any contact-mediated membrane damage.

Next, the real-time performance of Al_GO/P were examined by evaluating biocorrosion resistance properties under abiotic and biotic immersion environments. Analyses from corrosion rates (Figure 9A), pH kinetics (Figure 9B), ICP-MS (Table S5, Supporting Information) and FESEM imaging (Figures S11 and S12, Supporting Information) revealed that Al_GO/P substrates exhibited superior biocorrosion resistance in the order; Al_GO500P, Al_GO250P, Al_GO100P, and Al_GO50P compared to controls (CR steel, bare Al, and Al_GO). Abiotic immersion environment in presence of the control substrates (CR steel, bare Al, and Al_GO) exhibited alkaline pH related to ionic leaching (Figure 9Bi), while Al_GO/P substrates maintained neutral pH (Figure 9Bi). Under biotic immersion conditions, Al_GO/P substrates also displayed neutral pH environment (Figure 9Bii), suggesting attenuated microbial colonization, and lack of production of microbial products, correlating to earlier

research[148]. The aforementioned observations were further supported by ICP-MS analysis,

which showed reduced Al^{3+} release during the 45 day immersion period for Al_GO/P

substrates, relative to controls (CR steel, bare Al, and Al_GO). Rhyming with these results

FESEM images also highlighted the superior corrosion resistance properties of fabricated

Al_GO/P surfaces (Figures S17 and S19, Supporting Information).

Therefore, in the current study, PEDOT:PSS incorporation likely enhanced surface stability

preventing ion leaching, significantly improving corrosion resistance of Al_GO/P surfaces. The

improved corrosion resistance of Al_GO/P can be further correlated with reduced porosity

percentages (Table 3), as shown by earlier literatures[57,116]. Current results suggest a reduction

in porosity percentage with increase in GO concentration from 50 µg/ml to 500 µg/ml for the

Al_GO/P test surfaces. Coatings with low porosity percentage has been shown to maximize

barrier performance by restricting ion transport pathways[69,119]. There are also reports

correlating porosity percentage to antimicrobial action; smooth surfaces with fewer porous

domains resist microbial attachment and biofilm formation[116]. Therefore, Al_GO/P surfaces

with lower porosity percentage should improve corrosion resistance, by decreasing microbial

contamination and lower MIC (Figure 8, Figures S17 and S19, Supporting Information).

Next, it was crucial to conduct biocompatibility testing to ensure the safety and suitability of

Al_GO/P as implant materials. Al_GO100P was identified as a promising candidate for *in vivo*

implant material, owing to its excellent biocompatibility (Figure 10) along with remarkable

antibiofilm (Figure 6) and anticorrosion properties (Figure 8, Figures S17 and S19, Supporting

Information). Al_GO250P demonstrated favorable biocompatibility profile at 24 hours and

minimal cytotoxicity at 48 hours, suggesting potential suitability for short-term biomedical

applications. In contrast, the reduced HEK293T cell viability observed with Al_GO500P and

Al_GO1000P suggests a potential for cytotoxicity, making them better suited for *ex vivo*

applications. Controls; bare Al and Al_GO surfaces displayed remarkable cytotoxic activity

(Figure 10, Figure S21, Supporting Information). The toxic effects of aluminum (Al^{3+}) result

from its ability to disrupt cellular homeostasis through multiple mechanisms, including

oxidative stress induction, enzymatic inhibition, and direct cellular membrane damage[158]. The

results from both indirect and direct contact assays indicated that GO-PEDOT:PSS hybrid

coating including GO at 100 µg/ml and 250 µg/ml concentration, may effectively reduce Al-

related cytotoxicity while preserving biocompatibility, essential for biomedical applications.

Earlier works have employed GO coatings at higher concentrations (0.5-10 mg/ml) to achieve

enhanced antimicrobial activity[49–53]. Further GO at a concentration of 1 mg/ml on AA1050 has

shown protection against corrosive agents (water, oxygen, ions), while displaying systemic

toxicity due to inflammatory responses. Current work has found that Al_GO/P substrates

including lower concentration of GO (100 and 250 µg/ml) have excellent antimicrobial efficacy

and biocompatibility for use as implant materials.

As reported earlier, the membrane-damaging activity of GO involves multiple mechanisms,

such as GO sharp-edge effects, membrane pore formation, phospholipid extraction, and

electron extraction by GO side groups, and ROS production which induce oxidative stress[44,63].

To elucidate the underlying mechanism of Al_GO/P substrates and correlate cell membrane

damage with potential electron extraction events, intracellular and surface ROS production

assays were performed using H_2DCFDA and DHE fluorescent probes (Figure 8). The presence

of intracellular ROS indicated microbial cell death, whereas the detection of ROS on the

Al_GO/P surface pointed towards an interface phenomenon that suggested electron transfer

directed ROS generation over the conductive Al_GO/P substrates.

Summarizing the experimental data, a mechanistic model underlying the robust antimicrobial

(Figure 5) and antibiofilm activity (Figure 6) of the fabricated Al_GO/P substrates

(Al_GO100P, Al_GO250P, and Al_GO500P) is discussed. First, surface hydrophobicity

(Table 2) of the Al_GO/P substrates promote stable interactions with microbial cells,

facilitating contact-mediated membrane damage on GO-rich surface. Moreover, the conductive

nature (Table 2) of the Al_GO/P substrates may have induced electron transfer events that

generate ROS (Figure 8), further contributing to microbial cell damage (Figure 7). Further, the

Al_GO/P surfaces were evaluated to possess low porosity percentages (Table 3), subsequently

limiting microbial colonization and superior antibiofilm activity[116]. Prior work showed low

porosity levels correlate with improve corrosion resistance, by decreasing microbial

contamination. Together, these physical and electrochemical interactions may have enhanced

the antibiofouling efficacy of fabricated Al_GO/P surfaces. The superior antibiofouling

activities observed for test substrates; Al_GO500P, Al_GO250P, Al_GO100P relative to

Al_GO50P can be linked to higher surface hydrophobicity, low porosity percentage, and higher

ROS production (Figure 8, Table 2, Table 3) relative to bare Al.

Beyond their antibiofouling, biocorrosion resistant, and biocompatible nature; the ecological

implications of the synthesized Al_GO/P substrates warrant careful consideration to ensure

safe deployment in biomedical or environmental settings. Although fabricated Al_GO/P

surfaces exhibited improved GO adhesion in presence of PEDOT:PSS, their long-term

environmental fate and potential release of micro-debris remain unaddressed. This underscores

the need for future lifecycle and ecotoxicity studies on GO and PEDOT:PSS leaching from

metal surfaces[167,168]. However, the coated Al surfaces can be further recycled following eco-

friendly removal and disposal of the GO-PEDOT:PSS coating.

In toto, the findings from this study may establish a strong foundation for practical

implementation of GO-PEDOT:PSS hybrid coated Al substrates. The synthesized substrates

may provide a promising approach for improving the durability and performance of Al;

particularly where corrosion resistance, antibiofouling nature, and biocompatibility are crucial,

such as in the health-care, water treatment, and varied industrial sectors, where MIC plays

detrimental roles. Further research and optimization of the Al_GO/P composite system could

facilitate the development of advanced Al-based materials, particularly in the design of next-
generation biomedical implants with improved material lifespan.

1553

Author Contributions

1555   **S.S.N.**, Conceptualization; Methodology; Validation; Formal analysis; Investigation; Resources; Data curation; Writing original draft; Writing review and editing; Visualization. **R.E.A.**, Validation; Formal analysis; Writing original draft; Writing review and editing. **A.K.R.**, Validation; Investigation; Writing review and editing; **T.N.N.**, Validation; Formal analysis; Resources; Writing original draft; Writing review and editing. **S.N.**, Conceptualization; Methodology; Validation; Formal analysis; Investigation; Resources; Writing original draft; Writing review and editing; Supervision; Project administration; Funding acquisition.

Acknowledgements

Aluminum substrates were provided by NALCO India, Ltd. The authors gratefully acknowledge the School of Basic Sciences at IIT Bhubaneswar for granting access to their facilities for substrate synthesis and porosity evaluation. Sincere thanks are extended to the central facilities at TIFR Hyderabad for their valuable support in the characterization of Al_GO/P substrates. The authors also appreciate the Central Research Facility at KIIT-DU, Bhubaneswar, for providing access to the scanning electron microscope (SEM). The infrastructure grant from the Department of Biotechnology, Government of India, under the Boost to University Interdisciplinary Life Science Departments for Education and Research (BUILDER) program at KIIT School of Biotechnology is also duly acknowledged. S.S.N. was supported by DD Innovation Incorporated, U.S.A. (Ref No: DD/KIIT/001/2023).

Conflict of Interest Statement

1577   The authors declare that they have no conflict of interest.

Data Availability Statement

All data sources are cited within this article and its Supporting Information.

References

(1) Bamford, N. C.; Macphee, C. E.; Stanley-Wall, N. R. Microbial Primer: An Introduction to Biofilms – What They Are, Why They Form and Their Impact on Built and Natural Environments. *Microbiology (United Kingdom)* **2023**, *169* (8), 001338. https://doi.org/10.1099/MIC.0.001338.

(2) Karygianni, L.; Ren, Z.; Koo, H.; Thurnheer, T. Biofilm Matrixome: Extracellular Components in Structured Microbial Communities. *Trends Microbiol* **2020**, *28* (8), 668–681. https://doi.org/10.1016/J.TIM.2020.03.016.

(3) *HAIs: Reports and Data | HAIs | CDC*. https://www.cdc.gov/healthcare-associated-infections/php/data/index.html (accessed 2025-05-05).

(4) Guarente, L.; Mosconi, C.; Cicala, M.; De Santo, C.; Ciccacci, F.; Carestia, M.; Emberti Gialloreti, L.; Palombi, L.; Quintavalle, G.; Di Giovanni, D.; Buonomo, E.; Moramarco, S.; Riccardi, F.; Orlando, S. Device Associated Healthcare Associated Infection (DA-HAI): A Detailed Analysis of Risk Factors and Outcomes in a University Hospital in Rome, Italy. *Infection Prevention in Practice* **2024**, *6* (4), 100391. https://doi.org/10.1016/J.INFPIP.2024.100391.

(5) Cassini, A.; Plachouras, D.; Eckmanns, T.; Abu Sin, M.; Blank, H. P.; Ducomble, T.; Haller, S.; Harder, T.; Klingeberg, A.; Sixtensson, M.; Velasco, E.; Weiß, B.; Kramarz, P.; Monnet, D. L.; Kretzschmar, M. E.; Suetens, C. Burden of Six Healthcare-Associated Infections on European Population Health: Estimating Incidence-Based Disability-Adjusted Life Years through a Population Prevalence-Based Modelling Study. *PLoS Med* **2016**, *13* (10), e1002150. https://doi.org/10.1371/JOURNAL.PMED.1002150.

(6) *Healthcare-associated infections in European hospitals (PPS survey) 2022-2023*. https://www.ecdc.europa.eu/en/publications-data/healthcare-associated-infections-european-hospitals-pps-survey-2022-2023 (accessed 2025-05-05).

(7) *Each year, 4.3 million patients in hospitals in the EU/EEA are affected by healthcare-associated infections*. https://www.ecdc.europa.eu/en/news-events/each-year-43-million-patients-hospitals-eueea-are-affected-healthcare-associated (accessed 2025-05-05).

(8) Klevens, R. M.; Edwards, J. R.; Richards, C. L.; Horan, T. C.; Gaynes, R. P.; Pollock, D. A.; Cardo, D. M. Estimating Health Care-Associated Infections and Deaths in U.S. Hospitals, 2002. *Public Health Reports* **2007**, *122* (2), 160–166. https://doi.org/10.1177/003335490712200205.

(9) World Health Organization (WHO); Infection Prevention and Control (IPC). *Global report on infection prevention and control 2024*. https://www.who.int/publications/i/item/9789240103986 (accessed 2025-05-05).

(10) U.S. Department of Health and Human Services. *HAI National Action Plan*. https://www.hhs.gov/oidp/topics/health-care-associated-infections/hai-action-plan/index.html (accessed 2025-05-05).

(11) Mathur, P.; Malpiedi, P.; Walia, K.; Srikantiah, P.; Gupta, S.; Lohiya, A.; Chakrabarti, A.; Ray, P.; Biswal, M.; Taneja, N.; Rupali, P.; Balaji, V.; Rodrigues, C.; Lakshmi Nag, V.; Tak, V.; Venkatesh, V.; Mukhopadhyay, C.; Deotale, V.; Padmaja, K.; Wattal, C.; Bhattacharya, S.; Karuna, T.; Behera, B.; Singh, S.; Nath, R.; Ray, R.; Baveja, S.; Fomda, B. A.; Sulochana Devi, K.; Das, P.; Khandelwal, N.; Verma, P.; Bhattacharyya, P.; Gaind, R.; Kapoor, L.; Gupta, N.; Sharma, A.; VanderEnde, D.; Siromany, V.; Laserson, K.; Guleria, R.; Malhotra, R.; Katoch, O.; Katyal, S.; Khurana, S.; Kumar, S.; Agrawal, R.; Dev Soni, K.; Sagar, S.; Wig, N.; Garg, P.; Kapil, A.; Lodha, R.; Sahu, M.; Misra, M. C.; Lamba, M.; Jain, S.; Paul, H.; Sarojini Michael, J.; Kumar Bhatia, P.; Singh, K.; Gupta, N.; Khera, D.; Himanshu, D.; Verma, S.; Gupta, P.; Kumar, M.; Pervez Khan, M.; Gupta, S.; Kalwaje Eshwara, V.; Varma, M.; Attal, R.; Sudhaharan, S.; Goel, N.; Saigal, S.; Khadanga, S.; Gupta, A.; Thirunarayan, M. A.; Sethuraman, N.; Roy, U.; Jyoti Raj, H.; D'Souza, D.; Chandy, M.; Mukherjee, S.; Kumar Roy, M.; Goel, G.; Tripathy, S.; Misra, S.; Dey, A.; Misra, T.; Ranjan Das, R.; Bashir, G.; Nazir, S.; Ranjana Devi, K.; Chaoba Singh, L.; Bhargava, A.; Gaikwad, U.; Vaghela, G.; Sukharamwala, T.; Ch. Phukan, A.; Lyngdoh, C.; Saksena, R.; Sharma, R.; Velayudhan, A. Health-Care-Associated Bloodstream and Urinary Tract Infections in a Network of Hospitals in India: A Multicentre, Hospital-Based, Prospective Surveillance Study. *Lancet Glob Health* **2022**, *10* (9), e1317–e1325. https://doi.org/10.1016/S2214-109X(22)00274-1.

(12) Murhekar, M. V.; Kumar, C. G. Health-Care-Associated Infection Surveillance in India. *Lancet Glob Health* **2022**, *10* (9), e1222–e1223. https://doi.org/10.1016/S2214-109X(22)00317-5.

(13) Mehta, A.; Rosenthal, V. D.; Mehta, Y.; Chakravarthy, M.; Todi, S. K.; Sen, N.; Sahu, S.; Gopinath, R.; Rodrigues, C.; Kapoor, P.; Jawali, V.; Chakraborty, P.; Raj, J. P.; Bindhani, D.; Ravindra, N.; Hegde, A.; Pawar, M.; Venkatachalam, N.; Chatterjee, S.; Trehan, N.; Singhal, T.; Damani, N. Device-Associated Nosocomial Infection Rates in Intensive Care Units of Seven Indian Cities. Findings of the International Nosocomial Infection Control Consortium (INICC). *Journal of Hospital Infection* **2007**, *67* (2), 168–174. https://doi.org/10.1016/j.jhin.2007.07.008.

(14) Lohiya, R.; Deotale, V. Surveillance of Health-Care Associated Infections in an Intensive Care Unit at a Tertiary Care Hospital in Central India. *GMS Hyg Infect Control* **2023**, *18*, Doc28. https://doi.org/10.3205/DGKH000454.

(15) Karuppiah, Y. Cumulative Analysis of Device-Associated Hospital-Acquired Infection Quality Indicators in a Teaching Hospital in Telangana. *Apollo Medicine* **2024**. https://doi.org/10.1177/09760016241262582.

(16) Rather, M. A.; Gupta, K.; Bardhan, P.; Borah, M.; Sarkar, A.; Eldiehy, K. S. H.; Bhuyan, S.; Mandal, M. Microbial Biofilm: A Matter of Grave Concern for Human Health and Food Industry. *J Basic Microbiol* **2021**, *61* (5), 380–395. https://doi.org/10.1002/JOBM.202000678.

(17) Bouhrour, N.; Nibbering, P. H.; Bendali, F. Medical Device-Associated Biofilm Infections and Multidrug-Resistant Pathogens. *Pathogens* **2024**, *13* (5), 393. https://doi.org/10.3390/PATHOGENS13050393.

(18)   Mishra, A.; Aggarwal, A.; Khan, F. Medical Device-Associated Infections Caused by Biofilm-Forming Microbial Pathogens and Controlling Strategies. *Antibiotics* **2024**, *13* (7), 623. https://doi.org/10.3390/ANTIBIOTICS13070623.

(19)   Pal, M. K.; Lavanya, M. Microbial Influenced Corrosion: Understanding Bioadhesion and Biofilm Formation. *J Bio Tribocorros* **2022**, *8* (3), 1–13. https://doi.org/10.1007/S40735-022-00677-X.

(20)   Zhang, E.; Zhao, X.; Hu, J.; Wang, R.; Fu, S.; Qin, G. Antibacterial Metals and Alloys for Potential Biomedical Implants. *Bioact Mater* **2021**, *6* (8), 2569–2612. https://doi.org/10.1016/J.BIOACTMAT.2021.01.030.

(21)   Kumar, S.; Roy, D. N.; Dey, V. A Comprehensive Review on Techniques to Create the Anti-Microbial Surface of Biomaterials to Intervene in Biofouling. *Colloid Interface Sci Commun* **2021**, *43*, 100464. https://doi.org/10.1016/J.COLCOM.2021.100464.

(22)   Tunney, M. M.; Gorman, S. P.; Patrick, S. Infections Associated with Medical Devices. *Drugs* **2012**, *65* (2), 179–214. https://doi.org/10.2165/00003495-200565020-00003.

(23)   S, A. D.; P, S. P. A.; Naveen, J.; Khan, T.; Khahro, S. H. Advancement in Biomedical Implant Materials—a Mini Review. *Front Bioeng Biotechnol* **2024**, *12*, 1400918. https://doi.org/10.3389/FBIOE.2024.1400918.

(24)   Liu, L.; Wu, X.; Wang, Q.; Yan, Z.; Wen, X.; Tang, J.; Li, X. An Overview of Microbiologically Influenced Corrosion: Mechanisms and Its Control by Microbes. *Corrosion Reviews* **2022**, *40* (2), 103–117. https://doi.org/10.1515/CORRREV-2021-0039.

(25)   Knisz, J.; Eckert, R.; Gieg, L. M.; Koerdt, A.; Lee, J. S.; Silva, E. R.; Skovhus, T. L.; An Stepec, B. A.; Wade, S. A. Microbiologically Influenced Corrosion—More than Just Microorganisms. *FEMS Microbiol Rev* **2023**, *47* (5), 1–33. https://doi.org/10.1093/FEMSRE/FUAD041.

(26)   Eliaz, N. Corrosion of Metallic Biomaterials: A Review. *Materials* **2019**, *12* (3), 407. https://doi.org/10.3390/MA12030407.

(27)   Pandit, S.; Gaska, K.; Kádár, R.; Mijakovic, I. Graphene-Based Antimicrobial Biomedical Surfaces. *ChemPhysChem* **2021**, *22* (3), 250–263. https://doi.org/10.1002/CPHC.202000769.

(28)   Mosas, K. K. A.; Chandrasekar, A. R.; Dasan, A.; Pakseresht, A.; Galusek, D. Recent Advancements in Materials and Coatings for Biomedical Implants. *Gels* **2022**, *8* (5), 323. https://doi.org/10.3390/GELS8050323.

(29)   *Aluminium Alloy - Commercial Alloy - 1050A H14 Sheet*. https://www.aalco.co.uk/datasheets/Aluminium-Alloy-1050A-H14-Sheet_57.ashx (accessed 2025-05-05).

(30)   Avcu, Y. Y.; Gönül, B.; Yetik, O.; Sönmez, F.; Cengiz, A.; Guney, M.; Avcu, E. Modification of Surface and Subsurface Properties of AA1050 Alloy by Shot Peening. *Materials* **2021**, *14* (21), 6575. https://doi.org/10.3390/MA14216575.

(31)   Witkowska, M.; Thompson, G. E.; Hashimoto, T.; Koroleva, E. Assessment of the Surface Reactivity of AA1050 Aluminium Alloy. *Surface and Interface Analysis* **2013**, *45* (10), 1585–1589. https://doi.org/10.1002/SIA.5271.

(32) Marti, A. Inert Bioceramics (Al2O3, ZrO2) for Medical Application. *Injury* **2000**, *31* (SUPPL. 4), D33–D36. https://doi.org/10.1016/S0020-1383(00)80021-2.

(33) Hardik, B. *Use of aluminium alloy for biomedical implants - Royal Dental Clinics Blog*. https://royalimplant.com/blogs/can-we-use-aluminum-alloy-for-biomedical-implants/ (accessed 2026-02-10).

(34) Roato, I.; Genova, T.; Duraccio, D.; Ruffinatti, F. A.; Zanin Venturini, D.; Di Maro, M.; Mosca Balma, A.; Pedraza, R.; Petrillo, S.; Chinigò, G.; Munaron, L.; Malucelli, G.; Faga, M. G.; Mussano, F. Mechanical and Biological Characterization of PMMA/Al2O3 Composites for Dental Implant Abutments. *Polymers (Basel)* **2023**, *15* (15). https://doi.org/10.3390/polym15153186.

(35) Bhutta, M. T.; Ali, S.; Umer, M. A.; Mubashar, A.; Din, E. U.; Munir, A.; Basit, A. Effect of Process Parameters and Material Composition of Al2O3-HAP Composite Using Powder Metallurgy. *Results in Materials* **2025**, *25* (3), 100669. https://doi.org/10.1016/j.rinma.2025.100669.

(36) Bahraminasab, M.; Arab, S.; Safari, M.; Talebi, A.; Kavakebian, F.; Doostmohammadi, N. In Vivo Performance of Al2O3-Ti Bone Implants in the Rat Femur. *J Orthop Surg Res* **2021**, *16* (1). https://doi.org/10.1186/s13018-021-02226-7.

(37) Kocjančič, B.; Avsec, K.; Šetina Batič, B.; Feizpour, D.; Godec, M.; Kralj-Iglič, V.; Podlipec, R.; Cör, A.; Debeljak, M.; Grant, J. T.; Jenko, M.; Dolinar, D. The Impact of Al2O3 Particles from Grit-Blasted Ti6Al7Nb (Alloy) Implant Surfaces on Biocompatibility, Aseptic Loosening, and Infection. *Materials* **2023**, *16* (21). https://doi.org/10.3390/ma16216867.

(38) Andersson, H.; Rosenqvist, J.; Karlsson, K. H. Dissolution, Leaching, and Al2O3 Enrichment at the Surface of Bioactive Glasses Studied by Solution Analysis. *J Biomed Mater Res* **1993**, *27* (7), 941–948. https://doi.org/10.1002/jbm.820270713.

(39) Sathiyaseelan, G.; Bhagyanathan, C.; Srinath, P.; Gottmyers Melwyn, J. Enhancing the Strength and Structure of Al–Si Alloys for Biomedical Applications through the Addition of Sr and Zr Grain Refiners on Secondary AlSi7Mg Aluminum Alloys. *Chemical Physics Impact* **2024**, *8* (4), 100557. https://doi.org/10.1016/j.chphi.2024.100557.

(40) Hashimoto, M.; Imazato, S. Cytotoxic and Genotoxic Characterization of Aluminum and Silicon Oxide Nanoparticles in Macrophages. *Dental Materials* **2015**, *31* (5), 556–564. https://doi.org/10.1016/j.dental.2015.02.009.

(41) Alumeco Group. *Aluminium: Corrosion*. https://www.alumeco.com/aluminium/corrosion-of-aluminium/?s=0 (accessed 2025-05-05).

(42) de Andrade, J. S.; Vieira, M. R. S.; Oliveira, S. H.; de Melo Santos, S. K.; Urtiga Filho, S. L. Study of Microbiologically Induced Corrosion of 5052 Aluminum Alloy by Sulfate-Reducing Bacteria in Seawater. *Mater Chem Phys* **2020**, *241*, 122296. https://doi.org/10.1016/J.MATCHEMPHYS.2019.122296.

(43) Sahoo, J.; Sarkhel, S.; Mukherjee, N.; Jaiswal, A. Nanomaterial-Based Antimicrobial Coating for Biomedical Implants: New Age Solution for Biofilm-Associated Infections. *ACS Omega* **2022**, *7* (50), 45962–45980. https://doi.org/10.1021/ACSOMEGA.2C06211.

(44)   Nasker, S. S.; Ajayan, P. M.; Nayak, S. Emerging Trends and Future Direction of Graphene
Family of Materials as Potential Antimicrobials: A Critical Review. *ACS Mater Lett* **2023**, *5* (3),
673–693. https://doi.org/10.1021/ACSMATERIALSLETT.2C01116.

(45)   Islam, M. A.; Hossain, A.; Hossain, N.; Ahmed, M. M. S.; Islam, S.; Henaish, A. M. A.; Soldatov,
A. V.; Chowdhury, M. A. Recent Achievement of Graphene in Biomedicine: Advancements by
Integrated Microfluidics System and Conventional Techniques. *Sensors International* **2024**, *5*,
100293. https://doi.org/10.1016/J.SINTL.2024.100293.

(46)   Podila, R.; Moore, T.; Alexis, F.; Rao, A. Graphene Coatings for Biomedical Implants. *J Vis Exp*
2013, No. 73, e50276. https://doi.org/10.3791/50276.

(47)   Staneva, A. D.; Dimitrov, D. K.; Gospodinova, D. N.; Vladkova, T. G. Antibiofouling Activity
of Graphene Materials and Graphene-Based Antimicrobial Coatings. *Microorganisms 2021, Vol.*
9, Page 1839 **2021**, *9* (9), 1839. https://doi.org/10.3390/MICROORGANISMS9091839.

(48)   Bhatt, S.; Pathak, R.; Punetha, V. D.; Punetha, M. Recent Advances and Mechanism of
Antimicrobial Efficacy of Graphene-Based Materials: A Review. *J Mater Sci* **2023**, *58* (19),
7839–7867. https://doi.org/10.1007/S10853-023-08534-Z.

(49)   Poniatowska, A.; Trzaskowska, P. A.; Trzaskowski, M.; Ciach, T. Physicochemical and
Biological Properties of Graphene-Oxide-Coated Metallic Materials. *Materials* **2021**, *14* (19).
https://doi.org/10.3390/ma14195752.

(50)   Li, B.; Yuan, Z.; Chang, F.; Zhang, W.; Zhang, Z.; Chen, S. Preparation and Characterization of
Cu-GO and Cu-GO-YSZ Nanocomposite Coating by Electrochemical Deposition for Improved
Mechanical and Anti-Corrosion Properties. *Surf Coat Technol* **2022**, *439*, 128441.
https://doi.org/10.1016/j.surfcoat.2022.128441.

(51)   Mohammed Ali Al-Sammarraie, A.; Raheema, M. H. Electrodeposited Reduced Graphene
Oxide Films on Stainless Steel, Copper, and Aluminum for Corrosion Protection Enhancement.
International Journal of Corrosion **2017**, *2017* (1), 6939354.
https://doi.org/10.1155/2017/6939354.

(52)   Choudhary, P.; Mathur, A. K.; Dhayal, V. Designing an Eco-Friendly Graphene Oxide-Based
Titanium Tetra-Acetoxime Modified Epoxy Coating for Anti-Corrosion Properties of
Aluminium. *Sci Rep* **2026**, *16* (1), 4117-. https://doi.org/10.1038/s41598-025-33849-z.

(53)   Zhou, Y.; Wang, H.; Zhang, C.; Zhou, Q.; Rodrigues, D. F. Graphene Oxide-Hybridized
Waterborne Epoxy Coating for Simultaneous Anticorrosive and Antibiofilm Functions. *Front*
Mater **2022**, *9*, 910152. https://doi.org/10.3389/fmats.2022.910152.

(54)   Polai, B.; Samal, A.; Ratha, S.; Das, D.; Kumar Nayak, S. Corrosion Inhibition Properties of
Graphene and Reduced Graphene Oxide on Aluminum Surface: A Comparative Analysis from
Experimental and Theoretical Studies. *Nano Express* **2025**, *6* (1), 015024.
https://doi.org/10.1088/2632-959X/ADC31E.

(55)   Huang, H.; Guo, H.; Qu, J.; -, al; Cho, Y.; Lee, H.; Jeong, Y.; Duan, Z. Application of Graphene
in Metal Corrosion Protection. In *IOP Conference Series: Materials Science and Engineering*;
IOP Publishing, 2019; Vol. 493, p 012020. https://doi.org/10.1088/1757-899X/493/1/012020.

(56)   Liu, J.; Wu, Y.; Yan, F.; Yan, Y.; Wang, F.; Zhang, G.; Zeng, L.; Ma, Y.; Guo, J.; Li, Y.; Zhang,
P. Graphene-Based Anticorrosion Coatings for Steel: Fundamental Mechanism, Recent Progress

and Future Perspectives. *Prog Org Coat* **2025**, *200*, 108966. https://doi.org/10.1016/J.PORGCOAT.2024.108966.

(57) Ojha, D. K.; Polai, B.; Nasker, S. S.; Mehra, A.; Das, S. R.; Nayak, S. K.; Ajayan, P. M.; Nayak, S. RGO-Aluminium Substrates as Broad-Spectrum Antimicrobial and Antibiofilm Functional Materials. *Adv Mater Interfaces* **2025**, *12* (5), 2400637. https://doi.org/10.1002/ADMI.202400637.

(58) Wu, X.; Lian, L.; Yang, S.; He, G. Highly Conductive PEDOT:PSS and Graphene Oxide Hybrid Film from a Dipping Treatment with Hydroiodic Acid for Organic Light Emitting Diodes. *J Mater Chem C Mater* **2016**, *4* (36), 8528–8534. https://doi.org/10.1039/C6TC02424F.

(59) Bittolo Bon, S.; Valentini, L.; Kenny, J. M. Preparation of Extended Alkylated Graphene Oxide Conducting Layers and Effect Study on the Electrical Properties of PEDOT:PSS Polymer Composites. *Chem Phys Lett* **2010**, *494* (4–6), 264–268. https://doi.org/10.1016/J.CPLETT.2010.06.024.

(60) Ko, S. H.; Kim, S. W.; Lee, S. H.; Lee, Y. J. Electrodeposited Reduced Graphene Oxide-PEDOT:PSS/Nafion Hybrid Interface for the Simultaneous Determination of Dopamine and Serotonin. *Sci Rep* **2023**, *13* (1), 1–11. https://doi.org/10.1038/s41598-023-47693-6.

(61) Lee, D. Y.; Na, S. I.; Kim, S. S. Graphene Oxide/PEDOT:PSS Composite Hole Transport Layer for Efficient and Stable Planar Heterojunction Perovskite Solar Cells. *Nanoscale* **2016**, *8* (3), 1513–1522. https://doi.org/10.1039/c5nr05271h.

(62) Singh, B. P.; Jena, B. K.; Bhattacharjee, S.; Besra, L. Development of Oxidation and Corrosion Resistance Hydrophobic Graphene Oxide-Polymer Composite Coating on Copper. *Surf Coat Technol* **2013**, *232*, 475–481. https://doi.org/10.1016/J.SURFCOAT.2013.06.004.

(63) Panda, S.; Rout, T. K.; Prusty, A. D.; Ajayan, P. M.; Nayak, S. Electron Transfer Directed Antibacterial Properties of Graphene Oxide on Metals. *Advanced Materials* **2018**, *30* (7), 1702149. https://doi.org/10.1002/ADMA.201702149.

(64) Kim, J.; Khoh, W. H.; Wee, B. H.; Hong, J. D. Fabrication of Flexible Reduced Graphene Oxide–TiO2 Freestanding Films for Supercapacitor Application. *RSC Adv* **2015**, *5* (13), 9904–9911. https://doi.org/10.1039/C4RA12980F.

(65) Horkstra, J.; Van Der Pauw, L. J.; Philips, N. V. Measurement of the Resistivity Constants of Anistotropic Conductors by Means of Plane-Parallel Discs of Arbitrary Shape. *Journal of Electronics and Control* **1959**, *7* (2), 169–171. https://doi.org/10.1080/00207215908937197.

(66) Konyashin, I. Y.; Chukalovskaya, T. V. A Technique for Measurement of Porosity in Protective Coatings. *Surf Coat Technol* **1997**, *88* (1–3), 5–11. https://doi.org/10.1016/S0257-8972(95)02758-0.

(67) Walsh, F. C.; Ponce de León, C.; Kerr, C.; Court, S.; Barker, B. D. Electrochemical Characterisation of the Porosity and Corrosion Resistance of Electrochemically Deposited Metal Coatings. *Surf Coat Technol* **2008**, *202* (21), 5092–5102. https://doi.org/10.1016/J.SURFCOAT.2008.05.008.

(68) Ahn, S. H.; Lee, J. H.; Kim, H. G.; Kim, J. G. A Study on the Quantitative Determination of Through-Coating Porosity in PVD-Grown Coatings. *Appl Surf Sci* **2004**, *233* (1–4), 105–114. https://doi.org/10.1016/J.APSUSC.2004.03.213.

(69) Creus, J.; Mazille, H.; Idrissi, H. Porosity Evaluation of Protective Coatings onto Steel, through
Electrochemical Techniques. *Surf Coat Technol* **2000**, *130* (2–3), 224–232.
https://doi.org/10.1016/S0257-8972(99)00659-3.

(70) Leonhard, M.; Zatorska, B.; Moser, D.; Schneider-Stickler, B. Growth Media for Mixed
Multispecies Oropharyngeal Biofilm Compositions on Silicone. *Biomed Res Int* **2019**, *2019* (1),
8051270. https://doi.org/10.1155/2019/8051270.

(71) Kumar, A.; Vemula, P. K.; Ajayan, P. M.; John, G. Silver-Nanoparticle-Embedded Antimicrobial
Paints Based on Vegetable Oil. *Nat Mater* **2008**, *7* (3), 236–241.
https://doi.org/10.1038/NMAT2099.

(72) Pringle, J. R. [52] Staining of Bud Scars and Other Cell Wall Chitin with Calcofluor. *Methods*
Enzymol **1991**, *194* (C), 732–735. https://doi.org/10.1016/0076-6879(91)94055-H.

(73) Wang, X.; Bing, J.; Zheng, Q.; Zhang, F.; Liu, J.; Yue, H.; Tao, L.; Du, H.; Wang, Y.; Wang, H.;
Huang, G. The First Isolate of Candida Auris in China: Clinical and Biological Aspects Article.
Emerg Microbes Infect **2018**, *7* (1). https://doi.org/10.1038/S41426-018-0095-0.

(74) Yue, H.; Bing, J.; Zheng, Q.; Zhang, Y.; Hu, T.; Du, H.; Wang, H.; Huang, G. Filamentation in
Candida Auris, an Emerging Fungal Pathogen of Humans: Passage through the Mammalian
Body Induces a Heritable Phenotypic Switch. *Emerg Microbes Infect* **2018**, *7* (1).
https://doi.org/10.1038/S41426-018-0187-X.

(75) Sharma, S.; Acharya, J.; Banjara, M. R.; Ghimire, P.; Singh, A. Comparison of Acridine Orange
Fluorescent Microscopy and Gram Stain Light Microscopy for the Rapid Detection of Bacteria
in Cerebrospinal Fluid. *BMC Res Notes* **2020**, *13* (1), 1–5. https://doi.org/10.1186/S13104-020-
4895-7.

(76) Fazii, P.; Ciancaglini, E.; Riario Sforza, G. Differential Fluorescent Staining Method for
Detection of Bacteria in Blood Cultures, Cerebrospinal Fluid and Other Clinical Specimens.
European Journal of Clinical Microbiology and Infectious Diseases **2002**, *21* (5), 373–378.
https://doi.org/10.1007/S10096-002-0731-3.

(77) Schneider, C. A.; Rasband, W. S.; Eliceiri, K. W. NIH Image to ImageJ: 25 Years of Image
Analysis. *Nat Methods* **2012**, *9* (7), 671–675. https://doi.org/10.1038/nmeth.2089.

(78) Haney, E. F.; Trimble, M. J.; Hancock, R. E. W. Microtiter Plate Assays to Assess Antibiofilm
Activity against Bacteria. *Nature Protocols 2021 16:5* **2021**, *16* (5), 2615–2632.
https://doi.org/10.1038/s41596-021-00515-3.

(79) Murphy, M. P.; Bayir, H.; Belousov, V.; Chang, C. J.; Davies, K. J. A.; Davies, M. J.; Dick, T.
P.; Finkel, T.; Forman, H. J.; Janssen-Heininger, Y.; Gems, D.; Kagan, V. E.; Kalyanaraman, B.;
Larsson, N. G.; Milne, G. L.; Nyström, T.; Poulsen, H. E.; Radi, R.; Van Remmen, H.;
Schumacker, P. T.; Thornalley, P. J.; Toyokuni, S.; Winterbourn, C. C.; Yin, H.; Halliwell, B.
Guidelines for Measuring Reactive Oxygen Species and Oxidative Damage in Cells and in Vivo.
Nat Metab **2022**, *4* (6), 651–662. https://doi.org/10.1038/S42255-022-00591-Z.

(80) Liao, P. C.; Yang, E. J.; Pon, L. A. Live-Cell Imaging of Mitochondrial Redox State
in Yeast Cells. *STAR Protoc* **2020**, *1* (3), 100160. https://doi.org/10.1016/J.XPRO.2020.100160.

(81) Advancing Standards Transforming Markets (ASTM) International. *ASTM G1-03, Standard Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens, ASTM International*. https://doi.org/10.1520/G0001-03R17E01.

(82) National Association of Corrosion Engineers (NACE), 'Laboratory Corrosion Testing of Metals for the Process Industries.' *NACE Standard RP0775-2005 - Preparation, Installation, Analysis, and Interpretation of Corrosion Coupons in Oilfield Operations*. https://webstore.ansi.org/standards/nace/nacestandardrp07752005?srsltid=AfmBOooEwMuik Xp0sU7qJ4f-5ow1Xs9P2pAvyH7yQjONhMQ4syB9C5-y (accessed 2025-05-05).

(83) Feldmann, J.; Hansen, H. R.; Karlsson, T. M.; Christensen, J. H. ICP-MS As a Contributing Tool to Nontarget Screening (NTS) Analysis for Environmental Monitoring. *Environ Sci Technol* **2024**, *58* (29), 12755–12762. https://doi.org/10.1021/acs.est.4c00504.

(84) Grossenbacher, J.; Gullo, M. R.; Dalcanale, F.; Blugan, G.; Kuebler, J.; Lecaudé, S.; Tevaearai Stahel, H.; Brugger, J. Cytotoxicity Evaluation of Polymer-Derived Ceramics for Pacemaker Electrode Applications. *J Biomed Mater Res A* **2015**, *103* (11), 3625–3632. https://doi.org/10.1002/JBM.A.35477.

(85) Lim, K.; Chua, R. R. Y.; Ho, B.; Tambyah, P. A.; Hadinoto, K.; Leong, S. S. J. Development of a Catheter Functionalized by a Polydopamine Peptide Coating with Antimicrobial and Antibiofilm Properties. *Acta Biomater* **2015**, *15*, 127–138. https://doi.org/10.1016/J.ACTBIO.2014.12.015.

(86) Necula, B. S.; Van Leeuwen, J. P. T. M.; Fratila-Apachitei, L. E.; Zaat, S. A. J.; Apachitei, I.; Duszczyk, J. In Vitro Cytotoxicity Evaluation of Porous TiO2–Ag Antibacterial Coatings for Human Fetal Osteoblasts. *Acta Biomater* **2012**, *8* (11), 4191–4197. https://doi.org/10.1016/J.ACTBIO.2012.07.005.

(87) Das, G. K.; Chan, P. P. Y.; Teo, A.; Loo, J. S. C.; Anderson, J. M.; Tan, T. T. Y. In Vitro Cytotoxicity Evaluation of Biomedical Nanoparticles and Their Extracts. *J Biomed Mater Res A* **2010**, *93* (1), 337–346. https://doi.org/10.1002/JBM.A.32533.

(88) Liu, X.; Shan, K.; Shao, X.; Shi, X.; He, Y.; Liu, Z.; Jacob, J. A.; Deng, L. Nanotoxic Effects of Silver Nanoparticles on Normal HEK-293 Cells in Comparison to Cancerous HeLa Cell Line. *Int J Nanomedicine* **2021**, *16*, 753–761. https://doi.org/10.2147/IJN.S289008.

(89) International Organization for Standardization (ISO). *ISO 10993-5:2009 - Biological evaluation of medical devices — Part 5: Tests for in vitro cytotoxicity*. https://www.iso.org/standard/36406.html (accessed 2025-05-05).

(90) Liu, L.; Mandler, D. Using Nanomaterials as Building Blocks for Electrochemical Deposition: A Mini Review. *Electrochem commun* **2020**, *120*, 106830. https://doi.org/10.1016/J.ELECOM.2020.106830.

(91) Kong, M.; Garriga, M.; Reparaz, J. S.; Alonso, M. I. Advanced Optical Characterization of PEDOT:PSS by Combining Spectroscopic Ellipsometry and Raman Scattering. *ACS Omega* **2022**, *7* (43), 39429–39436. https://doi.org/10.1021/ACSOMEGA.2C05945.

(92) Chang, S. H.; Chiang, C. H.; Kao, F. S.; Tien, C. L.; Wu, C. G. Unraveling the Enhanced Electrical Conductivity of PEDOT:PSS Thin Films for ITO-Free Organic Photovoltaics. *IEEE Photonics J* **2014**, *6* (4). https://doi.org/10.1109/JPHOT.2014.2331254.

1899   (93)   Wu, J. Bin; Lin, M. L.; Cong, X.; Liu, H. N.; Tan, P. H. Raman Spectroscopy of Graphene-Based
1900   Materials and Its Applications in Related Devices. *Chem Soc Rev* **2018**, *47* (5), 1822–1873.
1901   https://doi.org/10.1039/C6CS00915H.

1902   (94)   Kim, S.-G.; Park, O.-K.; Lee, J. H.; Ku, B.-C. Layer-by-Layer Assembled Graphene Oxide Films
1903   and Barrier Properties of Thermally Reduced Graphene Oxide Membranes. *Carbon letters* **2013**,
1904   *14* (4), 247–250. https://doi.org/10.5714/CL.2013.14.4.247.

1905   (95)   Rao, C. N. R.; Biswas, K.; Subrahmanyam, K. S.; Govindaraj, A. Graphene, the New
1906   Nanocarbon. *J Mater Chem* **2009**, *19* (17), 2457–2469. https://doi.org/10.1039/b815239j.

1907   (96)   Otmani, L.; Doufnoune, R.; Benguerba, Y.; Erto, A. Experimental and Theoretical Investigation
1908   of the Interaction of Sulfonated Graphene Oxide with Polyvinylalcohol/Poly (4-Styrenesulfonic)
1909   Complex. *J Mol Liq* **2019**, *284*, 599–606. https://doi.org/10.1016/j.molliq.2019.04.034.

1910   (97)   Suominen, M.; Damlin, P.; Kvarnström, C. Electrolyte Effects on Formation and Properties of
1911   PEDOT-Graphene   Oxide   Composites.   *Electrochim   Acta*   **2019**,   *307*,   214–223.
1912   https://doi.org/10.1016/j.electacta.2019.03.157.

1913   (98)   Hassanpour, A.; Ghorbanpour, K.; Tehrani, A. D. Covalent and Non-Covalent Modification of
1914   Graphene Oxide Through Polymer Grafting. *Advanced 2D Materials* **2016**, 287–351.
1915   https://doi.org/10.1002/9781119242635.ch8.

1916   (99)   Al-Gaashani, R.; Najjar, A.; Zakaria, Y.; Mansour, S.; Atieh, M. A. XPS and Structural Studies
1917   of High Quality Graphene Oxide and Reduced Graphene Oxide Prepared by Different Chemical
1918   Oxidation   Methods.   *Ceram   Int*   **2019**,   *45*   (11),   14439–14448.
1919   https://doi.org/10.1016/j.ceramint.2019.04.165.

1920   (100)   Titantah, J. T.; Lamoen, D. Carbon and Nitrogen 1s Energy Levels in Amorphous Carbon Nitride
1921   Systems: XPS Interpretation Using First-Principles. *Diam Relat Mater* **2007**, *16* (3), 581–588.
1922   https://doi.org/10.1016/j.diamond.2006.11.048.

1923   (101)   Spanninga, S. A.; Martin, D. C.; Chen, Z. X-Ray Photoelectron Spectroscopy Study of
1924   Counterion Incorporation in Poly(3,4-Ethylenedioxythiophene) (PEDOT) 2: Polyanion Effect,
1925   Toluenesulfonate, and Small Anions. *Journal of Physical Chemistry C* **2010**, *114* (35), 14992–
1926   14997. https://doi.org/10.1021/jp104591d.

1927   (102)   Alhummiany, H.; Rafique, S.; Sulaiman, K. XPS Analysis of the Improved Operational Stability
1928   of Organic Solar Cells Using a V2O5 and PEDOT:PSS Composite Layer: Effect of Varied
1929   Atmospheric Conditions. *Journal of Physical Chemistry C* **2017**, *121* (14), 7649–7658.
1930   https://doi.org/10.1021/acs.jpcc.6b13016.

1931   (103)   Raghupathy, Y.; Kamboj, A.; Rekha, M. Y.; Narasimha Rao, N. P.; Srivastava, C. Copper-
1932   Graphene Oxide Composite Coatings for Corrosion Protection of Mild Steel in 3.5% NaCl. *Thin
1933   Solid Films* **2017**, *636*, 107–115. https://doi.org/10.1016/J.TSF.2017.05.042.

1934   (104)   He, X.; Zhou, W. Hydrophobic Modification and Durability Protection of Cotton Garment
1935   Fabric Surfaces by Graphene Oxide/PGMA Composite Coatings. *Sci Rep* **2024**, *14* (1), 1–10.
1936   https://doi.org/10.1038/S41598-024-71736-1.

1937   (105)   Amiri, S. Enhancement of Hydrophobic and Anti-Corrosive Performance of Epoxy Coatings
1938   Based on Graphene Oxide and Nano-Silica/Graphene Oxide Hybrid. *Silicon* **2025**, 1–11.
1939   https://doi.org/10.1007/S12633-025-03298-4.

(106) Sánchez-López, L.; Chico, B.; Escudero, M. L.; Lozano, R. M.; García-Alonso, M. C. Barrier Graphene Oxide on a CoCr Alloy via Silane/GO Covalent Bonding and Its Electrochemical Behavior in a Simulated Synovial Fluid Electrolyte. *Metals (Basel)* **2023**, *13* (8). https://doi.org/10.3390/met13081331.

(107) Doyle, R. J. Contribution of the Hydrophobic Effect to Microbial Infection. *Microbes Infect* **2000**, *2* (4), 391–400. https://doi.org/10.1016/S1286-4579(00)00328-2.

(108) Oh, J. K.; Yegin, Y.; Yang, F.; Zhang, M.; Li, J.; Huang, S.; Verkhoturov, S. V.; Schweikert, E. A.; Perez-Lewis, K.; Scholar, E. A.; Taylor, T. M.; Castillo, A.; Cisneros-Zevallos, L.; Min, Y.; Akbulut, M. The Influence of Surface Chemistry on the Kinetics and Thermodynamics of Bacterial Adhesion. *Sci Rep* **2018**, *8* (1), 17247-. https://doi.org/10.1038/s41598-018-35343-1.

(109) Lipińska, M.; Bazarnik, P.; Lewandowska, M. The Influence of Severe Plastic Deformation Processes on Electrical Conductivity of Commercially Pure Aluminium and 5483 Aluminium Alloy. *Archives of Civil and Mechanical Engineering* **2016**, *16* (4), 717–723. https://doi.org/10.1016/j.acme.2016.04.013.

(110) Zhou, R.; Embury, J. D.; Wood, J. T.; Smith, J. L. High-Strength, High-Conductivity Copper-Steel Composite. *Mater Charact* **1996**, *37* (5), 239–243. https://doi.org/10.1016/S1044-5803(96)00179-9.

(111) Raygan, S.; Mofrad, H. E.; Pourabdoli, M.; Ahadi, F. K. Effect of Rolling and Annealing Processes on the Hardness and Electrical Conductivity Values of Cu–13.5%Mn–4%Ni Alloy. *J Mater Process Technol* **2011**, *211* (11), 1810–1816. https://doi.org/10.1016/J.JMATPROTEC.2011.06.002.

(112) Hani, D. B.; Athamneh, R. Al; Albataineh, Z.; Rawashdeh, M.; Makableh, I. Modeling the Effect of Magnesium Content on the Electrical Conductivity and Hardness of Technical Aluminum (1050) Alloy. *Crystals (Basel)* **2022**, *12* (4), 457. https://doi.org/10.3390/CRYST12040457.

(113) Xu, Z.; Bando, Y.; Liu, L.; Wang, W.; Bai, X.; Golberg, D. Electrical Conductivity, Chemistry, and Bonding Alternations under Graphene Oxide to Graphene Transition As Revealed by In Situ TEM. *ACS Nano* **2011**, *5* (6), 4401–4406. https://doi.org/10.1021/nn103200t.

(114) Lin, C. H.; Yeh, W. T.; Chan, C. H.; Lin, C. C. Influence of Graphene Oxide on Metal-Insulator-Semiconductor Tunneling Diodes. *Nanoscale Res Lett* **2012**, *7* (1), 1–6. https://doi.org/10.1186/1556-276X-7-343.

(115) An, S. J.; Zhu, Y.; Lee, S. H.; Stoller, M. D.; Emilsson, T.; Park, S.; Velamakanni, A.; An, J.; Ruoff, R. S. Thin Film Fabrication and Simultaneous Anodic Reduction of Deposited Graphene Oxide Platelets by Electrophoretic Deposition. *Journal of Physical Chemistry Letters* **2010**, *1* (8), 1259–1263. https://doi.org/10.1021/JZ100080C.

(116) Yadav, N.; Dubey, A.; Shukla, S.; Saini, C. P.; Gupta, G.; Priyadarshini, R.; Lochab, B. Graphene Oxide-Coated Surface: Inhibition of Bacterial Biofilm Formation Due to Specific Surface-Interface Interactions. *ACS Omega* **2017**, *2* (7), 3070–3082. https://doi.org/10.1021/ACSOMEGA.7B00371.

(117) Attia, M.; Mohamed, M. B. I.; Hegazy, M. A.; Ghobashy, M. M.; El-Wahab, H. A.; Abdelhai, F. Enhancing Corrosion Resistance with Chemically Modified Aluminum Oxide in UV-Curable

1980   Coatings Applied to Steel Surfaces. *Sci Rep* **2025**, *15* (1), 16720-.
1981   https://doi.org/10.1038/s41598-025-99898-6.

1982 (118) Seah, K. H. W.; Thampuran, R.; Teoh, S. H. The Influence of Pore Morphology on Corrosion.
1983     *Corros Sci* **1998**, *40* (4–5), 547–556. https://doi.org/10.1016/S0010-938X(97)00152-2.

1984 (119) Luiz, L. A.; de Andrade, J.; Pesqueira, C. M.; Siqueira, I. B. de A. F.; Sucharski, G. B.; de Sousa,
1985     M. J. Corrosion Behavior and Galvanic Corrosion Resistance of WC and Cr3C2 Cermet
1986     Coatings in Madeira River Water. *Journal of Thermal Spray Technology* **2021**, *30* (1), 205–221.
1987     https://doi.org/10.1007/s11666-021-01152-8.

1988 (120) Zou, X.; Zhang, L.; Wang, Z.; Luo, Y. Mechanisms of the Antimicrobial Activities of Graphene
1989     Materials. *J Am Chem Soc* **2016**, *138* (7), 2064–2077. https://doi.org/10.1021/JACS.5B11411.

1990 (121) Saeed, S. I.; Vivian, L.; Zalati, C. W. S. C. W.; Sani, N. I. M.; Aklilu, E.; Mohamad, M.; Noor,
1991     A. A. M.; Muthoosamy, K.; Kamaruzzaman, N. F. Antimicrobial Activities of Graphene Oxide
1992     against Biofilm and Intracellular Staphylococcus Aureus Isolated from Bovine Mastitis. *BMC*
1993     *Vet Res* **2023**, *19* (1), 1–11. https://doi.org/10.1186/S12917-022-03560-6.

1994 (122) Sharma, S.; Mohler, J.; Mahajan, S. D.; Schwartz, S. A.; Bruggemann, L.; Aalinkeel, R.
1995     Microbial Biofilm: A Review on Formation, Infection, Antibiotic Resistance, Control Measures,
1996     and Innovative Treatment. *Microorganisms* **2023**, *11* (6), 1614.
1997     https://doi.org/10.3390/MICROORGANISMS11061614.

1998 (123) Cao, G.; Yan, J.; Ning, X.; Zhang, Q.; Wu, Q.; Bi, L.; Zhang, Y.; Han, Y.; Guo, J. Antibacterial
1999     and Antibiofilm Properties of Graphene and Its Derivatives. *Colloids Surf B Biointerfaces* **2021**,
2000     *200*, 111588. https://doi.org/10.1016/J.COLSURFB.2021.111588.

2001 (124) Zhang, P.; Guo, Z.; Chen, C.; Lynch, I. Uncertainties in the Antibacterial Mechanisms of
2002     Graphene Family Materials. *Nano Today* **2022**, *43*, 101436.
2003     https://doi.org/10.1016/J.NANTOD.2022.101436.

2004 (125) Martini, C.; Longo, F.; Castagnola, R.; Marigo, L.; Grande, N. M.; Cordaro, M.; Cacaci, M.;
2005     Papi, M.; Palmieri, V.; Bugli, F.; Sanguinetti, M. Antimicrobial and Antibiofilm Properties of
2006     Graphene Oxide on Enterococcus Faecalis. *Antibiotics* **2020**, *9* (10), 692.
2007     https://doi.org/10.3390/ANTIBIOTICS9100692.

2008 (126) Krasowska, A.; Sigler, K. How Microorganisms Use Hydrophobicity and What Does This Mean
2009     for Human Needs? *Front Cell Infect Microbiol* **2014**, *4* (AUG), 102373.
2010     https://doi.org/10.3389/FCIMB.2014.00112.

2011 (127) Kessler, A.; Hedberg, J.; Blomberg, E.; Odnevall, I. Reactive Oxygen Species Formed by Metal
2012     and Metal Oxide Nanoparticles in Physiological Media—A Review of Reactions of Importance
2013     to Nanotoxicity and Proposal for Categorization. *Nanomaterials* **2022**, *12* (11), 1922.
2014     https://doi.org/10.3390/NANO12111922.

2015 (128) Morris, J. J.; Rose, A. L.; Lu, Z. Reactive Oxygen Species in the World Ocean and Their Impacts
2016     on Marine Ecosystems. *Redox Biol* **2022**, *52*, 102285.
2017     https://doi.org/10.1016/J.REDOX.2022.102285.

2018 (129) Wojtala, A.; Bonora, M.; Malinska, D.; Pinton, P.; Duszynski, J.; Wieckowski, M. R. Methods
2019     to Monitor ROS Production by Fluorescence Microscopy and Fluorometry. *Methods Enzymol*
2020     **2014**, *542*, 243–262. https://doi.org/10.1016/B978-0-12-416618-9.00013-3.

(130) Villalpando-Rodriguez, G. E.; Gibson, S. B. Reactive Oxygen Species (ROS) Regulates Different Types of Cell Death by Acting as a Rheostat. *Oxid Med Cell Longev* **2021**, *2021* (1), 9912436. https://doi.org/10.1155/2021/9912436.

(131) Yousefi, M.; Dadashpour, M.; Hejazi, M.; Hasanzadeh, M.; Behnam, B.; de la Guardia, M.; Shadjou, N.; Mokhtarzadeh, A. Anti-Bacterial Activity of Graphene Oxide as a New Weapon Nanomaterial to Combat Multidrug-Resistance Bacteria. *Materials Science and Engineering: C* **2017**, *74*, 568–581. https://doi.org/10.1016/J.MSEC.2016.12.125.

(132) Pizzino, G.; Irrera, N.; Cucinotta, M.; Pallio, G.; Mannino, F.; Arcoraci, V.; Squadrito, F.; Altavilla, D.; Bitto, A. Oxidative Stress: Harms and Benefits for Human Health. *Oxid Med Cell Longev* **2017**, *2017* (1), 8416763. https://doi.org/10.1155/2017/8416763.

(133) Huttunen-Saarivirta, E.; Rajala, P.; Carpén, L. Corrosion Behaviour of Copper under Biotic and Abiotic Conditions in Anoxic Ground Water: Electrochemical Study. *Electrochim Acta* **2016**, *203*, 350–365. https://doi.org/10.1016/j.electacta.2016.01.098.

(134) Pramanik, S. K.; Bhuiyan, M.; Robert, D.; Roychand, R.; Gao, L.; Cole, I.; Pramanik, B. K. Bio-Corrosion in Concrete Sewer Systems: Mechanisms and Mitigation Strategies. *Science of The Total Environment* **2024**, *921*, 171231. https://doi.org/10.1016/J.SCITOTENV.2024.171231.

(135) Park, S. A.; Kim, J. G.; He, Y. S.; Shin, K. S.; Yoon, J. B. Comparative Study on the Corrosion Behavior of the Cold Rolled and Hot Rolled Low-Alloy Steels Containing Copper and Antimony in Flue Gas Desulfurization Environment. *Physics of Metals and Metallography* **2014**, *115* (13), 1285–1294. https://doi.org/10.1134/S0031918X14130201.

(136) Li, Y.; Xu, D.; Chen, C.; Li, X.; Jia, R.; Zhang, D.; Sand, W.; Wang, F.; Gu, T. Anaerobic Microbiologically Influenced Corrosion Mechanisms Interpreted Using Bioenergetics and Bioelectrochemistry: A Review. *J Mater Sci Technol* **2018**, *34* (10), 1713–1718. https://doi.org/10.1016/J.JMST.2018.02.023.

(137) Guo, N.; Zhao, Q.; Hui, X.; Guo, Z.; Dong, Y.; Yin, Y.; Zeng, Z.; Liu, T. Enhanced Corrosion Protection Action of Biofilms Based on Endogenous and Exogenous Bacterial Cellulose. *Corros Sci* **2022**, *194*, 109931. https://doi.org/10.1016/j.corsci.2021.109931.

(138) Ma, Y.; Zhang, Y.; Zhang, R.; Guan, F.; Hou, B.; Duan, J. Microbiologically Influenced Corrosion of Marine Steels within the Interaction between Steel and Biofilms: A Brief View. *Appl Microbiol Biotechnol* **2019**, *104* (2), 515–525. https://doi.org/10.1007/s00253-019-10184-8.

(139) Ejileugha, C.; Ezealisiji, K. M.; Ezejiofor, A. N.; Orisakwe, O. E. Microbiologically Influenced Corrosion: Uncovering Mechanisms and Discovering Inhibitor—Metal and Metal Oxide Nanoparticles as Promising Biocorrosion Inhibitors. *J Bio Tribocorros* **2021**, *7* (3), 1–21. https://doi.org/10.1007/S40735-021-00545-0.

(140) Zuo, R. Biofilms: Strategies for Metal Corrosion Inhibition Employing Microorganisms. *Appl Microbiol Biotechnol* **2007**, *76* (6), 1245–1253. https://doi.org/10.1007/S00253-007-1130-6.

(141) Khosravi, I.; Shahryari, Z.; Jazaeri Moghadas, S. M.; Yeganeh, M.; Sarraf, H. T. The Application of Graphene Oxide as Corrosion Barrier. *Corrosion Protection at the Nanoscale* **2020**, 127–140. https://doi.org/10.1016/B978-0-12-819359-4.00008-8.

(142) Guo, Y.; Xu, Z.; Wang, Q.; Zu, S.; Liu, M.; Yu, Z.; Zhang, Z.; Ren, L. Corrosion Resistance and Biocompatibility of Graphene Oxide Coating on the Surface of the Additively Manufactured NiTi Alloy. *Prog Org Coat* **2022**, *164*, 106722. https://doi.org/10.1016/J.PORGCOAT.2022.106722.

(143) Necolau, M. I.; Pandele, A. M. Recent Advances in Graphene Oxide-Based Anticorrosive Coatings: An Overview. *Coatings* **2020**, *10* (12), 1149. https://doi.org/10.3390/COATINGS10121149.

(144) Richard Prabakar, S. J.; Hwang, Y. H.; Bae, E. G.; Lee, D. K.; Pyo, M. Graphene Oxide as a Corrosion Inhibitor for the Aluminum Current Collector in Lithium Ion Batteries. *Carbon N Y* **2013**, *52*, 128–136. https://doi.org/10.1016/J.CARBON.2012.09.013.

(145) Pyun, S. Il; Moon, S. M. Corrosion Mechanism of Pure Aluminium in Aqueous Alkaline Solution. *Journal of Solid State Electrochemistry* **2000**, *4* (5), 267–272. https://doi.org/10.1007/s100080050203.

(146) Liu, B.; Lv, T.; Zhou, A.; Zhu, X.; Lin, Z.; Lin, T.; Suo, L. Aluminum Corrosion–Passivation Regulation Prolongs Aqueous Batteries Life. *Nat Commun* **2024**, *15* (1), 2922-. https://doi.org/10.1038/s41467-024-47145-3.

(147) Obaid, A. N.; Al-Bermany, E. Performance of Functionalized Graphene Oxide to Improve Anti-Corrosion of Epoxy Coating on 2024-T3 Aluminium Alloy. *Mater Chem Phys* **2023**, *305*, 127849. https://doi.org/10.1016/j.matchemphys.2023.127849.

(148) Brinda; Divyashree, M. S.; Rao, S. A.; Rao, P.; Mulky, L. Microbiologically Influenced Corrosion in Aluminium Alloys and Premier Techniques for Comprehensive Identification and Characterization across Diverse Metal Types. *Journal of Chemical Technology & Biotechnology* **2025**, *100* (6), 1143–1158. https://doi.org/10.1002/JCTB.7848.

(149) Carpen, L.; Rajala, P.; Bomberg, M. Corrosion of Copper in Anoxic Ground Water in the Presence of SRB. *Corrosion Science and Technology* **2018**, *17* (4), 147–153. https://doi.org/10.14773/CST.2018.17.4.147.

(150) Obot, I. B.; Obi-Egbedi, N. O. Fluconazole as an Inhibitor for Aluminium Corrosion in 0.1 M HCl. *Colloids Surf A Physicochem Eng Asp* **2008**, *330* (2–3), 207–212. https://doi.org/10.1016/j.colsurfa.2008.07.058.

(151) Ayoola, A. A.; Fayomi, O. S. I.; Ogunkanmbi, S. O. Data on Inhibitive Performance of Chloraphenicol Drug on A315 Mild Steel in Acidic Medium. *Data Brief* **2018**, *19* (12), 804–809. https://doi.org/10.1016/j.dib.2018.05.108.

(152) Alamry, K. A.; Khan, A.; Aslam, J.; Hussein, M. A.; Aslam, R. Corrosion Inhibition of Mild Steel in Hydrochloric Acid Solution by the Expired Ampicillin Drug. *Sci Rep* **2023**, *13* (1), 6724-. https://doi.org/10.1038/s41598-023-33519-y.

(153) Yu, J. C.; Jang, J. I.; Lee, B. R.; Lee, G. W.; Han, J. T.; Song, M. H. Highly Efficient Polymer-Based Optoelectronic Devices Using PEDOT:PSS and a GO Composite Layer as a Hole Transport Layer. *ACS Appl Mater Interfaces* **2014**, *6* (3), 2067–2073. https://doi.org/10.1021/am4051487.

(154) Nabilah Azman, N. H.; Lim, H. N.; Sulaiman, Y. Effect of Electropolymerization Potential on
the Preparation of PEDOT/Graphene Oxide Hybrid Material for Supercapacitor Application.
Electrochim Acta **2016**, *188*, 785–792. https://doi.org/10.1016/j.electacta.2015.12.019.

(155) Mosmann, T. Rapid Colorimetric Assay for Cellular Growth and Survival: Application to
Proliferation and Cytotoxicity Assays. *J Immunol Methods* **1983**, *65* (1–2), 55–63.
https://doi.org/10.1016/0022-1759(83)90303-4.

(156) Koyuncu, I.; Gönel, A.; Akdağ, A.; Yilmaz, M. A. Identification of Phenolic Compounds,
Antioxidant Activity and Anti-Cancer Effects of the Extract Obtained from the Shoots of
Ornithogalum Narbonense L. *Cell Mol Biol* **2018**, *64* (1), 75–83.
https://doi.org/10.14715/CMB/2018.64.1.14.

(157) Gurunathan, S.; Iqbal, M. A.; Qasim, M.; Park, C. H.; Yoo, H.; Hwang, J. H.; Uhm, S. J.; Song,
H.; Park, C.; Do, J. T.; Choi, Y.; Kim, J. H.; Hong, K. Evaluation of Graphene Oxide Induced
Cellular Toxicity and Transcriptome Analysis in Human Embryonic Kidney Cells.
Nanomaterials **2019**, *9* (7), 969. https://doi.org/10.3390/NANO9070969.

(158) Rahimzadeh, M. R.; Rahimzadeh, M. R.; Kazemi, S.; Amiri, R. J.; Pirzadeh, M.; Moghadamnia,
A. A. Aluminum Poisoning with Emphasis on Its Mechanism and Treatment of Intoxication.
Emerg Med Int **2022**, *2022* (1), 1480553. https://doi.org/10.1155/2022/1480553.

(159) Exley, C. Human Exposure to Aluminium. *Environ Sci Process Impacts* **2013**, *15* (10), 1807–
1816. https://doi.org/10.1039/C3EM00374D.

(160) Catt, K.; Li, H.; Cui, X. T. Poly (3,4-Ethylenedioxythiophene) Graphene Oxide Composite
Coatings for Controlling Magnesium Implant Corrosion. *Acta Biomater* **2017**, *48*, 530–540.
https://doi.org/10.1016/J.ACTBIO.2016.11.039.

(161) Srimaneepong, V.; Rokaya, D.; Thunyakitpisal, P.; Qin, J.; Saengkiettiyut, K. Corrosion
Resistance of Graphene Oxide/Silver Coatings on Ni–Ti Alloy and Expression of IL-6 and IL-8
in Human Oral Fibroblasts. *Sci Rep* **2020**, *10* (1), 1–12. https://doi.org/10.1038/s41598-020-
60070-x.

(162) Cangui-Panchi, S. P.; Ñacato-Toapanta, A. L.; Enríquez-Martínez, L. J.; Reyes, J.; Garzon-
Chavez, D.; Machado, A. Biofilm-Forming Microorganisms Causing Hospital-Acquired
Infections from Intravenous Catheter: A Systematic Review. *Curr Res Microb Sci* **2022**, *3*,
100175. https://doi.org/10.1016/J.CRMICR.2022.100175.

(163) Salgar-Chaparro, S. J.; Lepkova, K.; Pojtanabuntoeng, T.; Darwin, A.; Machuca, L. L.
Microbiologically Influenced Corrosion as a Function of Environmental Conditions: A
Laboratory Study Using Oilfield Multispecies Biofilms. *Corros Sci* **2020**, *169*, 108595.
https://doi.org/10.1016/J.CORSCI.2020.108595.

(164) Xu, D.; Li, Y.; Gu, T. Mechanistic Modeling of Biocorrosion Caused by Biofilms of Sulfate
Reducing Bacteria and Acid Producing Bacteria. *Bioelectrochemistry* **2016**, *110*, 52–58.
https://doi.org/10.1016/J.BIOELECHEM.2016.03.003.

(165) Puentes-Cala, E.; Tapia-Perdomo, V.; Espinosa-Valbuena, D.; Reyes-Reyes, M.; Quintero-
Santander, D.; Vasquez-Dallos, S.; Salazar, H.; Santamaría-Galvis, P.; Silva-Rodríguez, R.;
Castillo-Villamizar, G. Microbiologically Influenced Corrosion: The Gap in the Field. *Front*
Environ Sci **2022**, *10*, 924842. https://doi.org/10.3389/FENVS.2022.924842.

(166) Monaci, S.; Minudri, D.; Aird, A. J. U.; Mantione, D.; Mecerreyes, D.; Somers, A.; Forsyth, M. Pedot Conducting Polymers as Corrosion Inhibitors Additives for Acrylic-Uv Coatings. *Prog Org Coat* **2025**, *200*, 109000. https://doi.org/10.1016/J.PORGCOAT.2024.109000.

(167) International Organization for Standardization. *ISO 14044:2006 - Environmental management — Life cycle assessment — Requirements and guidelines.* https://www.iso.org/standard/38498.html (accessed 2026-02-12).

(168) Fantke, P.; Aurisano, N.; Bare, J.; Backhaus, T.; Bulle, C.; Chapman, P. M.; De Zwart, D.; Dwyer, R.; Ernstoff, A.; Golsteijn, L.; Holmquist, H.; Jolliet, O.; McKone, T. E.; Owsianiak, M.; Peijnenburg, W.; Posthuma, L.; Roos, S.; Saouter, E.; Schowanek, D.; van Straalen, N. M.; Vijver, M. G.; Hauschild, M. Toward Harmonizing Ecotoxicity Characterization in Life Cycle Impact Assessment. *Environ Toxicol Chem* **2018**, *37* (12), 2955–2971. https://doi.org/10.1002/etc.4261.