**Morphogenesis of the diamond-type stereom microlattice and the origin of saddle-**

**shaped minimal surfaces in the echinoderm skeleton**

This is a revised version of the manuscript submitted to *Acta Biomaterialia*.

Kamil Humański[a], Giulio Facchini[b], Jenifer Croce[c], Dorota Kołbuk[d], Philippe Dubois[e],

Przemysław Gorzelak[a]**\***

[a]Institute of Paleobiology, Polish Academy of Sciences, Warszawa, Poland

[b]Laboratoire Matière et Systèmes Complexes, CNRS, Université Paris Cité, Paris, France

[c]Laboratoire de Biologie du Développement de Villefranche-sur-Mer (LBDV), Institut de la

Mer de Villefranche (IMEV), Sorbonne Université, CNRS, Villefranche-sur-Mer, France

[d]UCD Earth Institute and School of Biology and Environmental Science, University College

Dublin, Belfield, Dublin, Ireland

[e]Laboratoire de Biologie Marine, Faculté des Sciences, Université Libre de Bruxelles,

Bruxelles, Belgium

*Corresponding author: pgorzelak@twarda.pan.pl (P. Gorzelak)

**Abstract**

Echinoderm endoskeleton has a unique trabecular microstructure, called stereom, which can

exhibit highly ordered geometries. A striking example of these geometries is the recently

discovered "diamond-type" stereom, characterized by a diamond triply periodic minimal

surface (D-TPMS) and distinguished by exceptional mechanical and structural properties.

Despite its promise for engineering applications, the morphogenesis of this microarchitecture

remains poorly understood. Here, we applied a multimodal imaging and labeling approach to

investigate the developmental processes underlying the formation of the diamond-type

stereom in adults of a starfish *Protoreaster nodosus*. We showed that this stereom type

develops through two principal marginal growth patterns: trabecular trifurcation, which

typically occurs horizontally on flat external plate surfaces, oriented approximately along the

crystallographic {111} planes of the D-TPMS; and trabecular bifurcation, which generally

occurs along plate edges and between trifurcating zones, aligned with the crystallographic

{100} planes of the D-TPMS. Although these growth patterns may proceed at different rates,

they are tightly coordinated, producing the coherent D-TPMS microarchitecture. Furthermore,

we demonstrated that F-actin cytoskeletal deposition is consistently associated with active

biomineralization fronts in both diamond-type and less ordered, galleried stereom. Notably,

the formation of lateral bridges between adjacent stereom trabeculae is often preceded by

catenoid-like F-actin structures, suggesting a guiding and templating role for the cytoskeleton

in building trabecular connectivity and shaping its curvature. Given the recurrence of saddle-

like features across stereom types, we hypothesize that minimal-surface geometries may

emerge from tension-driven cytoskeletal dynamics acting as physical templates during

biomineralization. Our observations underscore the critical involvement of the cytoskeleton in

adult echinoderm biomineralization.

**Statement of Significance**

Triple periodic minimal surfaces (TPMS) are geometrically regular, three-dimensionally

repeating surfaces that minimize area by maintaining zero mean curvature. Among them, the

diamond-type (D-TPMS) is notable for exceptional mechanical stability, uniform porosity,

and low surface area-to-volume ratio. Although TPMS-like microarchitectures occur in

nature, D-TPMS structures, with large lattice parameters (>10 μm) are exceedingly rare; one

natural example is the stereom of certain echinoderms. Yet the mechanism governing the

formation of such ordered microstructures remains unresolved. We applied a multi-modal

approach to investigate principles of diamond-type stereom morphogenesis. Our results

provide key insight into the growth dynamics of this microarchitecture and highlight the

essential role of the cytoskeleton, particularly F-actin, in guiding trabecular connectivity and

the emergence of minimal-surface geometry, in both periodic and more irregular stereom

types.

Key words: D-TPMS, starfish, sea star, biomineralization, F-actin, cytoskeleton.

**1.  Introduction**

Stereom is a unique form of skeletal microstructure, regarded as a synapomorphy of all

echinoderms [1]. It is a three-dimensional meshwork of trabeculae that branch and intersect,

forming a porous and mechanically robust single-crystal magnesian calcite [2], which

develops with the involvement of organic molecules during biomineralization [3]. Variations

in stereom porosity, regularity, and structural directionality have led to the distinction of

several stereom types, including rectilinear (trabeculae arranged in a regular cubic or

orthorhombic lattice), galleried (parallel trabecular galleries oriented in a single direction),

and labyrinthic (irregular trabecular meshwork), among others [4]. Some of these stereom

types have been reported as carrying phylogenetic signals useful for resolving relationships

among echinoderm taxa [5]. Furthermore, within the same organism, various stereom types

may occur in different skeletal elements or within the same element of a single organism,

often reflecting functional specialization of those elements [4-7].

Despite their structural diversity, all stereom types share a common saddle-like profile [4] and

display a similar basic developmental pathway [8-12]: their formation begins with the growth

of conical protrusions (trabecular tips) that become interconnected through lateral bridging,

giving rise to trabecular meshwork. As such, these early structures give rise to a fine

meshwork of inner stereom, which may successively thicken and expand at a slow rate

through the incremental deposition of biomineral layers. At the cellular level, according to the

current model of stereom growth, the elongation of trabeculae is mediated by skeleton-

forming cells (referred to as sclerocytes or calcoblasts), which extend thin cytoplasmic

processes (skeletal sheaths) that envelop the growing trabecular tips [13, 14]. Between the

cytoplasmic processes and the surface of the already deposited biomineral, a confined space

occurs in which biomineralization takes place [14].

The conservation of the saddle-shape microstructure in the stereom of all echinoderms

suggests that such a special geometry is inherited from a common self-organizing

morphogenetic process driving structural complexity. Notably, interactions between soft

biological tissues and local curvature have been demonstrated in various organisms and across

multiple scales, including the cellular level [15], where they appear to be mediated by the

cytoskeleton. Accordingly, in echinoderm embryos and larvae, phalloidin-labeling

experiments have recently demonstrated that cytoskeleton plays an important role in

biomineralization by guiding morphogenesis. In particular, in echinoid embryos it has been

shown that F-actin accumulates around the growing larval spicules [16, 17], particularly at

their extending tips [18]. Furthermore, inhibition of F-actin has been shown to induce

abnormal, ectopic branching of larval spicules [19]. Recently, F-actin filaments have also

been observed connecting pairs of trabeculae in the stereom constituting the sclerites of sea

cucumber juveniles (young post-metamorphosis adults), apparently initiating directed growth

toward each other, ultimately leading to fusion of opposing trabecular tips [20]. Despite these

studies, the role of F-actin in the formation of more complex stereom architectures,

particularly within the plates of adult echinoderms, remains largely unexplored. Furthermore,

it remains unclear to what extent F-actin is merely a component of a complex skeletogenic

machinery, or rather a key determinant of the final curvature profile of the stereom.

In some starfish, sea urchin and sea lily species, the stereom of adults, can exhibit highly

organized, regular patterns, such as the recently described "diamond-type" stereom (a specific

variant of rectilinear stereom) [21-23]. This structure features a diamond triply periodic

minimal surface geometry (D-TPMS) - an exquisitely ordered and periodic surface forming

an interconnected diamond-like network, resulting in a highly efficient microarchitecture that

is rare in nature [24]. It demonstrates high mechanical strength, including remarkable specific

energy absorption capabilities [21]. However, the *in vivo* formation mechanisms of these

complex and highly periodic microstructures, especially given their large lattice parameters

(>10 μm), as well as the involvement of F-actin during these mechanisms, remain unknown.

Indeed, although at the nanoscale, the formation and stability of TPMS with lattice parameters

up to ~100 nm (observed in certain biological systems, including in butterfly wing scales

[25]) can be attributed to self-assembly of soft membranes governed by competing molecular

interactions among components like lipids or copolymers [26], the mechanism underlying the

emergence of such architectures at the microscopic scale remains puzzling. Understanding the

biomineralization processes underlying these microstructures would however be of great

value, not only to biological sciences, but also to the materials science community.

Here, we explored the growth dynamics and morphogenesis of the recently identified

diamond-type stereom in the adult starfish species *Protoreaster nodosus*. By integrating

complementary staining techniques with imaging approaches, we characterized the

development of this highly ordered microarchitecture. To assess the potential involvement of

the F-actin cytoskeleton in stereom formation, we further examine the spatial distribution of

F-actin filaments, aiming to elucidate their potential role in shaping the stereom microlattice

and regulating biomineralization processes. Altogether, these analyses led us to discover that

diamond-type stereom develops through two principal marginal growth patterns, and that the cytoskeleton might play an important role in guiding and templating trabecular connectivity, while also shaping its distinctive curvature profile.

## 2. Materials and methods

### 2.1. Starfish specimens

The study was conducted at the Laboratory of Marine Biology in Bruxelles (Université Libre de Bruxelles, Belgium) on a commercially available (De Jong Marinelife B.V.) and unprotected wild-type (i.e., not genetically altered) starfish species *Protoreaster nodosus*, in which a diamond-type stereom microstructure was recently discovered [21]. Prior to experiments, a total of 25 small starfish, ca. 2.5-6 cm in arm length, underwent a 2-week acclimatization: they were kept in three aerated, closed-circuit, ca. 100 L aquaria containing natural seawater (salinity ~33.3 psu, temperature ~27°C, pH ~7.95) (Fig. S1, Table S2).

### 2.2. Scanning Electron Microscopy imaging

Scanning Electron Microscopy (SEM) imaging was performed on two specimens which were not used in any labeling experiments. A few arm fragments from both specimens were rinsed in ultra-pure water, dried and dehydrated. These samples were then incubated in 5% sodium hypochlorite solution for one hour. A few other arm samples from both individuals were also incubated for 30 minutes in a two-fold diluted solution to preserve the connecting tissue between ossicles and maintain their original spatial arrangement. All of these samples were then rinsed three times in MilliQ water, dehydrated in graded ethanol series and dried. Next, they were coated in platinum and photographed (Fig. 2 and Fig. 3A, B) using a Philips XL-20 scanning electron microscope (SEM) at the Institute of Paleobiology of the Polish Academy of Sciences in Warsaw, Poland (accelerating voltage ca. = 25 kV, working distance ca. = 34 mm). Additionally, a thin section from one specimen illustrated in Fig. 1 was analyzed using a

Thermo Fisher Quattro S Environmental SEM (parameters: 20 kV, 0.58 nA, WD = 10mm on

carbon coated section) at the Institute of Paleobiology, Polish Academy of Sciences, Warsaw,

Poland.

**2.3. Manganese labeling**

Manganese (Mn)-labeling was conducted following the described procedure [12]. Ten

individuals (five controls and five experimental) were placed in independent, aerated 1.5 L

aquaria (Fig. S1). Each day, the parameters of the seawater (temperature, salinity and

electromagnetic force [emf]) were measured three times. Each day seawater was fully

replaced in each aquarium. Specimens were fed every second day with soft tissues of mussels.

The experiment spanned up to ten days and involved a total of ten specimens (five controls

and five experimental). Of these, six specimens (three experimental and three controls) were

subjected to the following sequence: one day in normal seawater, two days of incubation (Mn-

enriched seawater for experimental individuals, normal seawater for controls), and a final day

of recovery in normal seawater. Two additional individuals (one experimental and one

control) underwent an extended post-tagging recovery of three days instead of one. The last

two individuals (one experimental and one control) followed the same scheme, with only the

experimental individual exposed to a secondary Mn-labeling incubation on days 7 and 8,

while the control remained in normal seawater, followed by a 2-day recovery. During

labeling, seawater was enriched with manganese using $MnCl_2 \cdot 4H_2O$ (Sigma-Aldrich),

dissolved to result in a nominal $Mn^{2+}$ concentration of 3 mg/L.

After the experiments, all animals were fixed, rinsed in seawater and then in ultra-pure water

before being air dried for 48 hrs at 50°C. Afterwards, they were dehydrated in graded ethanol

series (70%, 90% and 100%, each step lasted 2 hrs), and dried again for 48 hrs at 50°C.

**2.3.1.   Statistical analyses**

Three times per day the parameters of the seawater (temperature, salinity and electromagnetic

force [emf]) were measured using a WTW Multi 340i multimeter and a Metrohm pH-meter

(826 pH mobile) equipped with a combined glass electrode (Metrohm Primatrode), and

calibrated everyday with CertiPUR® buffer solutions pH 4.00 and 7.00 (Merck, Darmstadt,

Germany). All emf measurements were subsequently converted to pH values following

DelValls and Dickson's method [27] with TRIS/AMP buffers. Differences between measured

water parameters in the different aquaria (Mn-treatment and control) were assessed using

repeated measures ANOVA. Significance was set at $P < 0.05$. Overall, sea water parameters

remained comparable between the Mn-exposed and control groups, with significant changes

detected only over time, but not attributable to treatment (Table S2).

**2.4. Cathodoluminescence imaging**

Thin sections were prepared from two arms randomly selected from each individual,

including both experimental and control specimens. Samples were embedded in epoxy resin,

and thin sections were prepared using a series of diamond suspensions and finally carbon-

coated. They were analyzed with the aid of Lumic HC5–LM cathodoluminescence (CL)

microscope equipped with a hot cathode at the Institute of Paleobiology, Polish Academy of

Sciences, Warsaw. Images were recorded using a Kappa video camera. An electron energy of

14 keV was applied and, depending on the sample, beam currents between 0.8 – 0.14 mA

were used. Exposure times varied between 1.5 and 10 seconds.

Variably oriented D-TPMS lattices within each plate, with stereom trabeculae cut both

parallel to their long axis and at oblique angles, were analyzed (Fig. 1). Given the co-

alignment of the calcite *c-axis* with the diamond-type stereom in this starfish species [21], the

major crystallographic plane family of analyzed sections were inferred by comparing the

observed stereom patterns with those illustrated in [21], cross-checked against model

diamond-TPMS sections, and further verified using 2D fast Fourier transform (FFT) analysis

and polarized-light microscopy (Fig. S3). Sections oriented approximately along

crystallographic {111}, {110} and {211} planes of the D-TPMS were found to be the most

informative and were therefore used to assess the growth patterns described below. Thin

sections are housed at the Institute of Paleobiology, Polish Academy of Sciences, Warsaw

(ZPAL As. 2/Protoreaster01-10).

### 2.5. Calcium, F-actin, nuclei and α-tubulin labeling

A group of six specimens, not previously used in any experiments, were used for labeling of

calcium, F-actin, nuclei and α-tubulin. We followed a slightly modified protocol recently

published by Vyas al. 2024 [20]. First, for calcium labeling, animals were incubated alive for

24 hours in aerated, independent 1.5 L aquaria, filled with seawater containing calcium-

binding fluorescent markers. Two different markers were tested, at a final concentration of

300 mg/L: Calcein Blue (Sigma Aldrich - M1255) and Xylenol orange (Sigma Aldrich -

1086770005), both of which bind to newly deposited calcium. This concentration is

comparable to that used in previous study [20], where 250 mg/L was applied. To mitigate the

impact of Calcein Blue on seawater pH, sodium bicarbonate solution was added to maintain

pH at ca. 8.0. Both markers proved effective in all specimens and provided similar results (see

Results section). Following incubation, for F-actin, nuclei and α-tubulin labeling, all animals

were rinsed for 30 minutes in aquaria containing fresh seawater. No mortality was observed.

For each specimen, two arm tips and two spines (knob-shaped arm tubercles of carinal plates)

were collected using a sharp blade. Samples were fixed in 4% paraformaldehyde (PFA)

solution for 30 minutes at room temperature (RT). The solution was prepared diluting in

MFSW a stock solution of PFA 8% prepared in MilliQ distilled water. Next, all samples were

rinsed five times for 5 minutes each at RT using the following proportion of Millipore filtered

seawater (MFSW) to Phosphate-Buffered Saline (PBS): 1:0, 3:1, 1:1, 1:3 and 0:1. Samples

were then rinsed four times for 5 minutes each at RT in 1x PBST (PBS 1x, 0.05% Tween20),

before being pre-blocked for 1 hour at RT in 1x Bovine Serum Albumin (BSA) solution in

PBS. For F-actin staining we used Phalloidin (1:100) coupled with four different dyes: iFluor

405, ALEXA Fluor 647, ALEXA Fluor 555plus and ALEXA Fluor 633 (Thermo Fisher

Scientific). For nuclei labeling, samples were incubated in 4',6-diamidino-2-phenylindole

(DAPI) (Thermo Fisher Scientific) (1:500). For α tubulin labeling, we used anti-α-tubulin

antibodies already coupled with FITC (1:100), as referenced by [20]. For those labeling, upon

blocking, samples were incubated overnight at 4°C. All stainings were carried out separately

or concomitantly depending on the need. Following labeling, samples were rinsed three times

5 minutes each at RT. Confocal micrographs were obtained using a ZEISS LSM 780 and

different magnification water objectives ranging from 20X to 63X, at the Matière et Systèmes

Complexes Laboratory UMR 7057 in Paris. Fluorescent labeling was excited using 405, 488,

543 or 633 nm lasers usually acting on two or three different and independent scanning

sequences. Z-stack was acquired with an interval of 0.57 μm and was later examined using

ImageJ Software [28].

**Fig.1. Example of a cathodoluminescence image (A) of a thin section cut along the longitudinal axis of the distal arm portion, with SEM enlargements of selected microregions (B-F).** Mn-induced luminescent skeleton appears as a bright orange signal; black and dark grey regions indicate skeleton grown in normal (without $Mn^{2+}$) seawater and resin with soft tissues, respectively. Arrows indicate the following features: green – partially visible carinal plate composed of diamond-type stereom, red – ambulacral plates composed of labyrinthic (unordered) stereom exhibiting regional differences in porosity density, yellow – labyrinthic stereom in the internal portion of the distal adambulacral plates, blue – diamond-type stereom of the adambulacral plates. In the adambulacral plates, the yellow dashed lines indicate the approximate boundaries between the labyrinthic and the diamond-type stereom. B-D show the diamond-type stereom with varying patterns caused by different sectioning planes, while E-F show the labyrinthic stereom [1.5 column image]

## 3. Results

### 3.1. Microstructural observations by Scanning Electron Microscopy (SEM)

The skeletal organization of *Protoreaster nodosus* comprises several distinct types of plates (Fig. S4). As previously reported [21], we observed that the carinal, inferomarginal, superomarginal, dorsolateral, and adambulacral plates exhibit the same diamond-type (D-TPMS) stereom, whereas the ambulacral plates display labyrinthic stereom (Fig. 1, Fig. S4). All of these plates are further covered by small covering spinelet plates bearing less organized galleried stereom (Fig. S4).

Following [21], the porous lattice of plates with D-TPMS geometry can be described as a network of nodes (points where a variable number of trabeculae converge) and branches (trabeculae connecting two nodes), for which both width and length can be quantified. In the D-TPMS lattice analyzed here, the predominant node type is N4 - a node connected to four

branches (Figs. 2-4 and Fig. S4C, D). These nodes are arranged in tetrahedral coordination

along the {111} crystallographic direction: the basal vertices of the tetrahedron and the apical

vertices extending along {111} (as seen on Fig. 3A, B and Fig. 4).

SEM imaging allowed us to study the spatial distribution of skeletal structures and stereom

microarchitectures preserved at different developmental stages (Figs. 2-5). Through high-

resolution SEM imaging of plate surfaces, we observed repetitive stereom structures

associated with distinct patterns of stereom growth, consistently appearing on all D-TPMS-

bearing plates. However, elucidating the formation mechanisms of these structures required

integrating data from both SEM and cathodoluminescence studies (see subchapter 3.3).

On every plate exhibiting D-TPMS stereom lattice, three main patterns of diamond-type

stereom growth were observed (see Fig. 2): (1) here termed trifurcation, which is a stereom

growth resulting in the formation of successive layers roughly diamond to elliptical in shape

and occurring on flat external surfaces of plates oriented approximately along the {111}

planes of the D-TPMS (Fig. 2 and Fig. 3A). (2) here termed bifurcation, which is a growth

pattern that appears to be supplementary to trifurcation, typically occurring around the edges

of external surfaces of plates or between trifurcating regions on surfaces of varying shape,

roughly aligned with the {100} planes of the D-TPMS lattice (Fig. 2 and Fig. 3E); (3) an

intermediate growth pattern, which is present at the borders between tri- and bifurcating

regions, and exhibits a combination of characteristics from both growth types (Fig. 2A, B). It

is worth noting that if the D-TPMS microarchitecture ultimately results from marginal

(surface-driven) growth, the range of viable geometric configurations becomes inherently

limited, which is consistent with the emergence of bifurcating and trifurcating growth patterns

along defined orientations.

Layers in trifurcating regions consist of nodes extending laterally and apically. Each node in

lateral vertices (hereafter referred to as crown node) connects to three nodes in apical vertices

(hereafter referred to as budding nodes) of the same layer and one budding node in the layer

below, while each budding node connects to three crown nodes in the same layer and one

crown node in the layer above (Fig. 4). During growth, crown nodes form on top of the

branch extending from a budding node, and branches extending from the crown node connect

with each other, forming new budding nodes while maintaining the tetrahedral connectivity.

This process will be explained in detail in chapter 3.3.

All aforementioned plate types exhibiting D-TPMS were found to further contain small

volumes of irregular, unordered labyrinthic stereom (Fig. S5). These regions are typically

located within the interior and exhibit ellipsoidal shapes. They are clearly distinct in both size

and trabecular thickness from the D-TPMS stereom (which usually displays some minor

dislocations [21]). In adambulacral plates, the labyrinthic stereom is located in the internal

portion of the plate. The morphogenesis of the labyrinthic stereom has not been explored here.

**Fig. 2. SEM images of superomarginal plates, orientated nearly along the {110} (A) and {100} (B) planes of D-TPMS, and with enlargement of different growth regions on the outer surface of trabeculae (C)**. Dashed lines highlight distinct growth regions: yellow – approximate extent of trifurcating region; red – approximate extent of bifurcating regions, cyan – a rare occurrence of irregular stereom visible on the surface. The area between red,

312   yellow and cyan boundaries exhibits intermediate growth patterns. White arrows in (C)

313   indicate exemplary bifurcating rows, some of which were denoted (a-c); in each of those a

314   steady progression of growth is observed from a node in the lower left (indicated by arrow) to

315   the node in the upper right. Green arrows mark newly formed trabecular arches (see

316   Discussion). [single column figure]

**Fig. 3. Trifurcating (A-D) and bifurcating (E) regions of the D-TPMS**. (A, B) Same

region of superomarginal plates viewed along their {111} plane. In (A), yellow dashed lines

demarcate the approximate boundaries of successive layers and, in (B), arrows point to the

group of nodes forming a new uppermost layer (magenta), to proto-nodes (red), "dormant

nodes" (yellow) and crown nodes (cyan) growing at the edges of expanding layers (for

definitions see subchapter 3.3). (C) Simplified scheme of trifurcating growth dynamics, based

on compilation of data from CL studies. Stereom lattice is depicted as viewed in a thin section

perpendicular to the {111} plane of D-TPMS. Growing trabeculae and thickening growth

have been omitted. Black branches represent all trabeculae formed prior to the

biomineralization of the red-colored trabeculae. The red branches correspond to trabeculae

that formed within a short time interval (2-3 days). The thin dashed black line outlines the

margin of the growing plate. (D) Surface of an inferomarginal plate, exhibiting an active

trifurcating region: thin sections cut roughly perpendicularly to the {111} plane of D-TPMS.

Arrows labeled with numbers mark the oldest (e.g., A1, B1) and youngest (e.g., A2, B7)

trabeculae located at the respective edges of each highlighted layer. (E) Surface of a different

inferomarginal plate, within an active bifurcating region. White lines separate angular

unconformities on the thin section. [double column figure]

**3.2. Cathodoluminescence analysis of stereom growth patterns**

Manganese (Mn) labeling followed by cathodoluminescence (CL) imaging has previously

been shown to be an efficient method for tracking stereom growth dynamics at the

microstructural scale in echinoderms [12]. In adult starfish, Mn-stained stereom was

consistently well-differentiated under CL, in all thin sections taken from the arm fragments of

specimens in the main experimental group (Fig. 1), with staining being detected in every

marked specimen. In contrast, the stereom of the control group showed no Mn-induced

luminescence (Fig. S6).

The skeleton labeled with Mn exhibits distinct, bright orange luminescent increments at the

plate periphery, indicating that skeletal growth and Mn incorporation occurred during the two-

day incubation treatments. In contrast skeletal growth during the one-day recovery period, in

the main experimental group, was rarely observed in the examined plates, indicating a delay

in biomineralization upon $Mn^{2+}$ exposure, likely caused by the equilibration of manganese

pools between ambient seawater and internal tissues of starfish. Note that a single individual

incubated for an extended (3-day) recovery period exhibited somewhat more pronounced and

clearly detectable non-luminescent skeletal growth following the tagging event (Fig. S7). In

contrast, another specimen subjected to two separate Mn-labeling events yielded inconclusive

results regarding non-luminescent skeletal growth, as no clearly distinguishable two growth

increments were consistently observable.

Precise quantification of growth rates was hindered by orientation-dependent variability of the

sectioned surfaces, which introduced measurement bias. Nevertheless, the rate of progression

of both tri- and bifurcating growth fronts appeared to vary with plate type and anatomical

position within the arm, ranging from several to tens of micrometers per day, and were highly

dependent on factors such as the individual specimen, plate size (or inferred age), and specific

location on the plate. Only on some surfaces a continuous, evenly thick stereom

(approximately twenty micrometers thick) was formed during labeling (Fig.1) while on other

plates the Mn-induced luminescent growth fronts contained gaps (Fig. 3D). Thickening of

previously formed stereom trabeculae (including both longitudinal trabeculae and lateral

bridges) was also well visible, and could extend up to several tens of micrometers below the

areas where trabecular tips were forming. In general, the peripheral growth was most

pronounced in the distal plates.

Despite these uncertainties, we were able to identify a general growth pattern and formulate

hypotheses concerning its dynamics. For instance, if we define the growth rate as the change

in the trifurcating layer radius over the measured time interval, one observes that the average

growth rate generally decreases towards the lower layers (Fig. 3C, D), relative to the ring

thickness, in order to maintain the surface curvature. Considering the minimal size differences

between layers, the minimal observed growth rate was ca. ~15 µm/2 days (corresponding to

the incorporation of a single new crown node within that time frame). The maximal observed

growth rate of a pre-existing (second youngest) layer in one direction was approximately 40

µm/2 days, equivalent to 3 newly incorporated crown nodes (Table. S8). Conversely, defining

the growth rate globally, as the number of new nodes (red in Fig. 3C, D) along a line

perpendicular to the dashed envelope, showed that it remains approximately constant (one

node per period) within the resolution of our measurements, explaining the preservation of the

overall dome shape.

**3.3. Stereom growth patterns**

As mentioned before, the information obtained through SEM was complementary to CL

imaging, with SEM providing high-resolution details of stereom architecture, while CL

allowed the determination of the sequence of stereom formation (see also Fig. S9). The

following subsections present these observations in detail, integrating data from both

techniques - collected from five individuals subjected to Mn labeling and two individuals

examined using SEM.

**3.3.1. Trifurcating stereom growth**

Trifurcating growth was only observed on external surfaces of plates oriented along the D-

TPMS planes belonging to the crystallographic {111} family. Most prominently, it occurred

when the surface of the plate was oriented at an angle between 0° and 30° to the {111} plane,

around which it became less distinguishable and was progressively replaced by bifurcating

growth mode, which became most pronounced at the plate surface inclined at an angle 30° to

45° relative to the {111} plane. When viewed from the top (Fig 3A), along the {111} plane of

the D-TPMS, the stereom formed by this mode of growth appeared as a bundle of layers

stacked upon one another (Fig. S9B). The outermost layer in this view, corresponding to the

trifurcating region, represented the youngest stage of growth.

As pointed out above, each fully developed crown node is connected to three budding nodes

within the same layer and one budding node from the layer below. Conversely, each fully

developed budding node is connected to three crown nodes within the same layer and one

crown node from the layer above (Fig. 4 Stage 1). When such a layer reached a certain width,

few budding nodes located near its center (presumably the oldest from the previous

generation) - simultaneously formed small protrusions (buds) that elongated vertically along

the crystallographic {111} direction, which corresponds to the *c-axis* of the constituent calcite

at the atomic scale (Fig. S3), giving rise to vertical branches directed upwards (Fig. 3B, Fig.

S9 and Fig. 4 Stage 2). At the tip of each branch, a new crown node formed (Fig. 4 Stage 3).

These new crown nodes then trifurcated (Fig. 4 Stage 4), creating three small lateral

protrusions. From each new crown node, one of these protrusions was growing visibly faster

(Fig. 4 Stage 5) and eventually formed at their tip a node-like structure, hereafter referred to

as a proto-node. New proto-nodes in a given trifurcating region consistently emerged along

the same direction (Fig. 3B and Fig. S9). Depending on their location, proto-nodes can thus

grow toward (e.g. Fig. 3: lowermost red arrow and Fig. S9, blue nodes in the middle),

outward (Fig. 3: uppermost red arrow) or along the layer margin (Fig. 3: two other red

arrows), with the latter case being most common on all plates due to the D-TPMS stereom

geometry. Subsequently, if another branch or branches from a nearby crown nodes are

available for coupling, they connected to the proto-node that ultimately became a new

budding node (Fig. 4 Stage 6).

After forming its core, each layer expanded peripherally by incorporating additional crown

nodes that budded from the underlying layer in a circular pattern around the growing layer

(Fig. 3B). Thus, zones of active trifurcating growth formed concentric rings around the

periphery of each layer, spreading outward horizontally like ripples, as the layer increased in

size. The horizontal growth of each layer remained approximately isotropic until it

approached the plate edge where a non-trifurcating region begins (see Fig. 2A). Budding

nodes located between active growth zones remained "dormant", exhibiting only thickening

growth of trabeculae until they reached their maximum width. In general, each successive pair

of layers exhibited a decreasing size difference, leading to progressively thinner "rings" of

exposed nodes in each subsequent layer (Fig. 3A, C). The minimal ring width (~30 μm) was

observed when it consisted of a single line of exposed budding nodes. This is consistent with

marginal growth, occurring mainly at the edges of the 3D structure of the ossicle, i.e.,

normally to the dashed envelope sketched in Fig. 3C.

The active, thickening, and dormant zones can be observed on CL images (Fig. 3D, E). In

these images, the manganese signal was most prominent on the edges of each layer, where

nodes and branches were composed entirely of manganese-induced luminescent calcite

(active zones) (e.g. Fig 3D, nodes B6-B7 and C5-C6). Few preceding nodes in each layer

might also exhibit distinct luminescence, but only on their outer surfaces, which indicates that

these nodes underwent only thickening growth during the staining period (thickening zones)

(e.g. Fig. 3D, nodes C3-C4). The remaining exposed budding nodes of each layer showed dull

or no luminescence, suggesting that no growth occurred during that time (dormant zones)

(e.g. Fig. 3D, nodes B1-B4 and C1-C2). The number of those nodes in a layer and the time

they spent in "dormant" phase varied depending on the shape of the plate and the size of the

layer, however, this duration, based on CL images, can be approximated to range from a day

to a week.

Fig. 4. Simplified 3D diagram illustrating successive stages of trifurcating growth localized at the edge of a pre-existing layer, in a plate exhibiting D-TPMS. Nodes are represented with small spheres and branches with cylindrical rods, thus their thickness and length do not represent their actual proportions. Color code: light blue – crown nodes; light green – budding nodes (color distinction shown only in the first panel); yellow – pre-existing branches, that are no longer elongating; white – pre-existing, fully formed nodes; red – nodes and branches undergoing elongation/thickening; orange – nodes and branches that were formed within the depicted time frame, but are no longer elongating. In the figure, we depicted budding nodes from the lower layer (A, B, C, D, E) and crown nodes that grew out of them, belonging to the upper layer (A', B', C', D', E'), as well as all branches and nodes connected to those ten nodes at the given stage. In the first picture, nodes A, B, C are illustrated at stage 1, nodes D and E are fully developed and nodes D' and E' are at stage 6. Other, undefined nodes are fully developed. The symbols BN, CN, and PN were used to denote representative budding node, crown node, and proto-node, respectively. Stage 1. Each budding node (A, B, C) connects only to three crown nodes within the same layer. Stage 2. A budding protrusion emerges upwards along the *c-axis* of calcite from the top of the budding node. Stage 3. A crown node is formed at the tip of the budding protrusion, being noticeably thicker than the budding branch. The original budding node, now connected to four nodes, will no longer develop except for thickening. All further stages refer to the set of newly

formed crown nodes (A', B', C'). Stage 4. Three protrusions can be distinguished at the top of

the crown nodes (around this time, the next set of budding nodes, which are not shown in the

diagram, would begin advancing from stage 1 to stage 2). Stage 5. The trifurcating branches

elongate and one becomes distinctly longer and thicker at its tip, forming a proto-node (proto-

nodes in this diagram are orientated along the layer edge). Stage 6. Branches extending from

the crown nodes connect with other adjacent branches, and the developing crown nodes are

incorporated into the upper layer. After these connections, nodes D' and E' finish their

development and only thickening is observed on existing branches. Similarly, nodes A', B'

and C' finish their development only after the next set of crown nodes reaches stage 6. Stages

1-3 describe three lower-layer nodes (A, B, C), while stages 3-6 correspond to crown nodes

(A', B', C'). Proto-nodes, which have connected to two adjacent branches emerging from the

nearby crown nodes, form new budding nodes in the upper layer. The minimal estimated

(based on CL images) time for progression from a budding node at the beginning of stage 2 to

a crown node at the end of stage 6 is approximately 12 hours. [two column figure]

**3.3.2. Bifurcating stereom growth**

As previously mentioned, bifurcating growth is considered supplementary growth, occurring

on surfaces orientated at ca. 30-45° angle to any of the {111} planes, where uniform

trifurcation is not supported. In contrast to trifurcating regions, which possess a fixed central

point, concentric growth zones surrounding it and distinct layers, bifurcating regions exhibited

a seemingly irregular growth that only locally exhibited repeating structures (Fig. 2C). As

such, bifurcating growth regions could have only been seen as a patchwork of linear rows of

different length, which grew by extending one or both of their ends.

The bifurcating growth pattern was most clearly observed in two adjacent, parallel rows as

sketched in Fig. 5. Growth initiated from the oldest budding nodes in each row (Fig. 5 Stage

1), giving rise to small protrusions (Fig. 5 Stage 2), which subsequently extended into

branches (Fig. 5 Stage 3). As the two branches elongated, they further gradually inclined

toward each other (Fig. 5 Stage 3) and as a result connected to each other (Fig. 5 Stage 4).

Upon connecting, an initial arch-like structure lacking a distinct central node was formed (Fig.

2C (green arrows), Fig. S9D and Fig. 5 Stage 4). Ultimately, a new node formed upward from

the apex of this arch (Fig. 5 Stage 5).

**Fig. 5. Simplified 3D diagram showing sequential stages of bifurcating growth across**

**three node generations in a plate exhibiting D-TPMS**. Node and branch thicknesses and

lengths are not representative, as explained in Fig. 4; colors follow those of Fig. 4. Stage 1.

The upper nodes in two parallel rows (A-C, A'-C') are connected to two bottom nodes in the

same row. Here, six rows are illustrated: four lower (marked by arrows), and two higher,

perpendicular to them (containing nodes A–C and A'–C'). Stage 2. Two side branches emerge

from two oldest upper nodes (A, A'), forming a straight top ridge perpendicular to the row.

Stage 3. Branches extend and, while growing, incline slightly toward adjacent nodes, while at

the same time the subsequent upper nodes start stage 1. Stage 4. At least one branch connects

with that of a neighboring node, forming an arch-shaped skeletal bridge. Stage 5. A new node

develops from the top of the arch. The new node enters stage 1, starting the next cycle. Nodes

B, B', C, C' and subsequent pairs (not shown on the diagram) continue to grow until, one

after another, they reach stage 5. In this way, growth waves propagate along each row,

generating surfaces of parallel node series. Growth typically proceeds at a steady pace during

stages 1–2, then accelerates within stage 2. Longer bifurcating series show most nodes at

stages 1 or 2 (Fig. 2C - therein rows a-c contain 2-3 such nodes each, then row c includes a

stage 4 node; rows a and b reach stage 5) [Two-column figure]

**3.4. Confocal observations - overall characterization**

To gain insights into the potential involvement of the cytoskeleton in stereom growth,

regardless of stereom type, and in particular at the level of individual trabeculae and their

fusion processes, we next performed a series of staining targeting F-actin filaments and

microtubules. Along these staining, we further labeled nuclei and newly biomineral deposition

of calcium, to concomitantly visualize trabecular growth. We found, as previously reported

[10, 20], the accumulation of calcium located at the growing tips of trabeculae (Figs. 6, 7).

Furthermore, we observed that cell nuclei were commonly localized near the base of the

growing trabeculae (Fig. 6), rather than at the growing tips, and showed a loosely dispersed

pattern therein with no evident spatial regularity. Microtubules, in turn, appeared arranged in

bundles, predominantly oriented longitudinally along the trabeculae (Fig. 6A). However,

although the α-tubulin signal was typically strong at the onset of image acquisition, it

exhibited thereafter rapid deterioration upon increased laser power and depth imaging,

impairing further analyses. By contrast, cytoskeletal labeling carried out for F-actin, revealed

a similar spatial distribution and three-dimensional organization of F-actin filaments on the

growing surfaces of both the diamond-type stereom-bearing plates (carinal, inferomarginal,

superomarginal, dorsolateral and adambulacral) and the less-ordered galleried stereom-

bearing covering spinelet plates (Figs. 6, 7). A consistent pattern emerged across all observed

plates and stereom types in all six marked specimens: F-actin densification was localized at

the tips of actively growing trabeculae (identified by strong calcium-related fluorescence

signal) regardless of plate morphology or underlying stereom microarchitecture.

In the galleried stereom of spinelet plates, the intensified F-actin signal appeared as minute

caps positioned a few micrometers above the tips of growing trabeculae, or as catenoid-

shaped structures forming between adjacent elongating branches (Fig. 6). In diamond-type

stereom, F-actin signals were also detected at the tips and in between trabeculae, where they

form several recurring structural morphotypes (ranging from thin, disordered bundles to

catenoid-like tubular structures, and sheath-like coatings), which seem to be related to specific

developmental stages of the associated trabecular tips (Fig. 7).

**Fig. 6. Confocal images of galleried stereom in spinelet plates of an adult starfish showing F-actin densification in growing trabecular tips and between trabeculae.** (A, B) Zoom-ins of F-actin caps located at the tip of growing trabeculae. (C-H) Zoom-ins of F-actin catenoid-shaped filaments connecting adjacent growing trabeculae or wrapping adjacent trabecular bridges. Yellow – freshly biomineralized skeleton, blue – nuclei, magenta – F-actin, green – α-tubulin, white plain arrows – F-actin caps, black arrows – trabecular tips, dotted white arrows – F-actin catenoid bridges, * – sheath-like coating of trabeculae, dotted white double arrows – complex F-actin catenoid bridges, green arrow – thin F-actin filament. [1.5 column figure]

**Fig. 7. Confocal images of F-actin densification in growing trabecular tips in active growth zones of diamond-type stereom in adambulacral plates of an adult starfish.** (A, B) Trifurcating zones. (C, D) Bifurcating zones. Arrows highlight a variety of F-actin structures possibly at different stages of development. Yellow – freshly biomineralized skeleton, magenta – F-actin, white plain arrows – F-actin caps, dotted white arrows – F-actin catenoid bridges, white plain short arrow – fully developed trabecular calcite bridge without F-actin coating, dotted white double arrows – complex F-actin catenoid bridges, green arrow – thin F-actin filament. [2 columns figure]

## 4. Discussion

As noted recently [21], the formation mechanisms of diamond-type stereom have not been systematically explored, and understanding these processes would be of great value not only to the materials science community, but also to a broader audience across multiple scientific

domains. Here, we provide the first detailed characterization of these morphogenetic

processes, demonstrating that ossicle formation bearing diamond-type stereom can be

described in terms of two fundamental growth modes: trifurcation and bifurcation. While

progressing on different distinct planes, these growth modes are synchronized, ultimately

generating a coherent D-TPMS lattice. Trifurcating growth can be divided into six identifiable

stages, as visualized in Fig. 4; it should be noted that the sequence is qualitative and does not

imply a constant growth rate or a uniformly distributed timeline. Similarly, bifurcating growth

can be described in terms of five observable stages, depicted in Fig. 5, with the same caveat

regarding the qualitative nature of the sequence.

Building upon the delineated growth patterns of ossicles, we further explored the cytoskeletal

dynamics that is linked to trabecular formation. We found that intensified F-actin signals at

the tips of growing trabeculae were consistently observed at active growth fronts in both

diamond-type and less-ordered galleried stereom of *Protoreaster nodosus* (Figs. 6, 7). These

findings corroborate some earlier reports documenting F-actin accumulation at

biomineralization sites in echinoid embryos and holothuroid juveniles [17-20], while

representing the first visualization of F-actin distribution in asteroid skeletal elements. The

possibility that F-actin participates in initiating or guiding trabecular growth and connections

within echinoderm stereom has only recently been proposed [20] and still requires more

thorough documentation. Thus, the observations presented here not only support the

hypothesis of a key role for the cytoskeleton in echinoderm biomineralization [18-20], but

also suggest actin-mediated structural templating/guiding in the form of caps and catenoid-

like bridges during stereom morphogenesis.

In general, F-actin structures associated with elongating trabeculae can be classified into two

categories: (i) caps, which are situated immediately above or closely associated with growing

trabecular tips, and (ii) bridges, which connect two opposing growing trabeculae. Both

categories exhibit some variability in shape and size, likely reflecting differences in

developmental stage and growth dynamics.

F-actin accumulation was consistently observed across all skeletal plates, irrespective of

whether they contained galleried stereom (e.g., spinelet covering plates) or diamond-type

stereom, the morphogenesis of which was explored in detail herein. In both stereom types, F-

actin caps appear as loosely hemispherical or open conical concentrations, typically thinner

than the underlying trabecular protrusions and positioned up to about a few micrometers

above the trabecular tips (Figs. 6, 7). Notably, thread-like projections composed of membrane

and F-actin forming between the tips of growing trabeculae have recently been documented in

juvenile holothurians [20]. Those projections were notably occurring only between

approaching trabeculae, suggested to enable their curved growth and eventual fusion [20]. In

our study, we demonstrate that within these projections, which were also distinguished only

between approaching trabeculae, F-actin forms however structurally distinct cytoskeleton

bridges, which likely guide and template the ongoing biomineralization of the stereom lattice.

We observed F-actin in various forms, thus potentially in different organizational stages,

ranging from thin, disordered bundles (Fig. 6G) to catenoid-like tubular structures (Fig. 6C, H

and Fig. 7C), and, hypothetically, even to a sheath-like coating (Fig. 6D, E) filled with newly

deposited mineral. Furthermore, we observed complex catenoid-like bridges between multiple

neighboring trabeculae (e.g., Fig. 6H). In trifurcating regions of D-TPMS, specifically

between proto-nodes extending from the crown node (outward to the layer margin) and two

nearby budding nodes, these bridges exhibit a "pants-like" morphology (Fig. 7A, B).

Together, these observations provide new insights into the dynamic processes underlying the

formation of these structures. However, a detailed understanding of the developmental

progression of these structures will require further investigations. In the Supplementary

Materials (Figs. S10, S11), we present hypothetical, simplified representations of the F-actin

structures observed during trifurcating and bifurcating growth, organized according to their

putative developmental stages. These models, however, require additional experimental

validation in future studies, for instance, through experimental manipulation of F-actin (e.g.,

disruption via pharmacological treatments), which could help clarify the temporal relationship

between actin organization and stereom formation in adult echinoderms.

Interestingly, the most commonly observed structure was the F-actin catenoid-like bridge

(e.g., Fig. 6C-H and Fig. 7C), herein referred to as a "catenoid bridge". In *Protoreaster*

*nodosus*, catenoid bridges were observed in both galleried and diamond-type stereom,

consistently forming between pairs of trabecular protrusions emerging from neighboring

nodes prior to trabecular branch fusion at that site. Notably, the catenoid is a classic example

of a minimal surface. We hypothesize that the tension exerted by F-actin filaments may

impose a characteristic catenoid geometry, which in turn could coherently drive the formation

of the stereotypical saddle-shaped morphology of trabecular surfaces. Given that saddle-

shaped surfaces are a common feature across all stereom types, we further speculate that this

geometric motif may be a consequence of actin-based templating governed by tension-

dominated cytoskeletal dynamics. Notably, it has recently been suggested [29], although

without experimental verification, that the tension of the soft tissue in sea urchins (stroma)

could play a critical role in stereom morphogenesis and its saddle-shaped surfaces.

Interestingly, similar actin-mediated processes have been observed in mammalian skeletal

development and in vascular morphogenesis. For example, recent work [30] has shown that

the organization of F-actin in osteoblast-like cells regulates differentiation and mineralization

of the extracellular matrix, highlighting the central role of the cytoskeleton in bone formation.

Furthermore, it has been demonstrated [31] that VEGF (Vascular Endothelial Growth Factor)

signaling involved in tubulogenesis may represent a conserved mechanism shared between

spicule formation in sea urchin larvae and blood vessel development in mammals, hinting at a

deep evolutionary link between biomineralization and vascular morphogenesis.

Taken together, we hypothesize that the curvature signature exhibited by the stereom of

*Protoreaster nodosus* and echinoderms in general emerges from a robust growth pattern

driven by the self-assembly of cytoskeletal structures. While different protein filaments may

contribute to this process, F-actin appears to play a fundamental, evolutionarily conserved

role, as suggested by its recurrent involvement in biomineralization across diverse lineages,

including silicifying diatoms [32, 33], calcifying algae [34, 35], foraminifers [36], and

echinoderms [20, this study].

## 659 5. Conclusions

Altogether, our findings reveal that, in the adult starfish *Protoreaster nodosus*, the formation

of plates (or ossicles) bearing diamond-type stereom proceeds via two primary growth

patterns, which we named trifurcation and bifurcation. These two patterns develop on distinct

planes across the plate surface, although they are yet coordinated to form a coherent D-TPMS

lattice. Overall, plate growth is highly dynamic, exhibiting localized variation in growth rate,

which points to a high degree of cellular control over biomineralization. We demonstrate that

such control is highly localized at the growing front and is likely mediated by the

cytoskeleton. Indeed, irrespective of plate or stereom type, F-actin densification consistently

localizes at sites of active biomineralization, particularly at elongating trabecular tips, thereby

strongly supporting previous findings that underscore a critical role of the cytoskeleton in

stereom morphogenesis. Furthermore, in certain regions, the formation of F-actin catenoid-

like bridges precedes the development of lateral connections between adjacent stereom

trabeculae, suggesting a potential role in triggering and templating trabecular fusion. We

hypothesize that the cytoskeleton exerts a significant modulatory function in stereom growth,

influencing also its characteristic saddle-shaped minimal surface geometry.

**Declaration of Competing Interest**

The authors declare that they have no known competing financial interests or personal

relationships that could have appeared to influence the work reported in this paper.

**Acknowledgements**

The project was funded by NCN grant 2023/51/B/ST10/01640. Ph.D. is a Research Director

of the National Fund for Scientific Research (Belgium). We thank members of the laboratory

of Marine Biology at ULB for help in performing experiments. We thank the Editor and the

three anonymous reviewers for their constructive and valuable comments. We also thank

Paweł Bącal (Institute of Paleobiology, PAS) for his help in the acquisition of some SEM

photographs.

**CRediT authorship contribution statement**

Kamil Humański: Conceptualization; Formal analysis; Investigation; Methodology;

Visualization; Writing - original draft; and Writing - review & editing. Giulio Facchini:

Conceptualization; Formal analysis; Investigation; Methodology; Visualization; Writing -

review & editing. Jenifer Croce: Conceptualization; Methodology; Writing - review &

editing. Dorota Kołbuk: Formal analysis; Investigation; Methodology; Supervision; Writing -

review & editing. Philippe Dubois: Methodology; Supervision; Writing - review & editing.

Przemysław Gorzelak: Conceptualization; Formal analysis; Funding acquisition;

Investigation; Methodology; Project administration; Supervision; Visualization; Writing -

review & editing.

**References**

1.   D. J. Bottjer, E. H. Davidson, K. J. Peterson, R. A. Cameron, Paleogenomics of echinoderms, *Science* 314 (2006) 956–960, https://doi.org/10.1126/science.1132310.

2.   H. U. Nissen, Crystal orientation and plate structure in echinoid skeletal units, *Science* 166 (1969) 1150–1152, https://doi.org/10.1126/science.166.3909.1150.

3.   L. Ameye, G. De Becker, C. Killian, F. Wilt, R. Kemps, S. Kuypers, P. Dubois, Proteins and saccharides of the sea urchin organic matrix of mineralization: characterization and localization in the spine skeleton. *Journal of Structural Biology*, 134(1) (2001) 56–66, https://doi.org/10.1006/jsbi.2001.4361.

4.   A. B. Smith, Stereom microstructure of the echinoid test, *Spec. Pap. Palaeontol.* 25 (1980) 1–81.

5.   M.J. Simms, Stereom microstructure of columnal latera: a character for assessing phylogenetic relationships in articulate crinoids, *Swiss J. Palaeontol.* 130 (2011) 143–154, https://doi.org/10.1007/s13358-010-0013-0.

6.   D. B. Macurda, D. L. Meyer, The microstructure of the crinoid endoskeleton, *Univ. Kans. Paleontol. Contrib.* 74 (1975) 1–22.

7.   T. Yang, Z. Jia, Z. Wu, H. Chen, Z. Deng, L. Chen, Y. Zhu, L. Li, High strength and damage-tolerance in echinoderm stereom as a natural bicontinuous ceramic cellular solid. *Nat. Commun.* 13 (2022) 6083, https://doi.org/10.1038/s41467-022-33712-z.

8.   Ph. Dubois, M. Jangoux, Stereom morphogenesis and differentiation during regeneration of fractured adambulacral spines of *Asterias rubens* (Echinodermata, Asteroidea), *Zoomorphology* 109 (1990) 263–272, https://doi.org/10.1007/BF00312193.

9.   P. Gorzelak, J. Stolarski, A. Dery, Ph. Dubois, S. Escrig, A. Meibom, Ultrascale and microscale growth dynamics of the cidaroid spine of *Phyllacanthus imperialis* revealed

by $^{26}$Mg labeling and NanoSIMS isotopic imaging, *J. Morphol.* 275(7) (2014) 788–796, https://doi.org/10.1002/jmor.20260.

10. P. Gorzelak, J. Stolarski, P. Dubois, Ch. Kopp, A. Meibom, 26Mg labeling of the sea urchin regenerating spine: Insights into echinoderm biomineralization process, *J. Struct. Biol.* 176 (2011) 119–126, https://doi.org/10.1016/j.jsb.2011.07.008.

11. B.M. Heatfield, D.F. Travis, Ultrastructural studies of regenerating spines of the sea urchin *Strongylocentrotus purpuratus* I. Cell types without spherules, *J. Morphol.* 145(1) (1975) 13–49, https://doi.org/10.1002/jmor.1051450103.

12. P. Gorzelak, A. Dery, P. Dubois, J. Stolarski, Sea urchin growth dynamics at microstructural length scale revealed by Mn-labeling and cathodoluminescence imaging, *Front. Zool.* 14 (2017) 1–17, https://doi.org/10.1186/s12983-017-0227-8.

13. S. Weiner, L. Addadi, Crystallization pathways in biomineralization, *Annu. Rev. Mater. Res.* 41 (2011) 21–40, https://doi.org/10.1146/annurev-matsci-062910-095803.

14. P. Dubois, L. Ameye, Regeneration of spines and pedicellariae in echinoderms: a review, *Microsc. Res. Tech.* 55(6) (2001) 427–437, https://doi.org/10.1002/jemt.1188.

15. B. Schamberger, R. Ziege, K. Anselme, M. B. Amar, M. Bykowski, A. P. G. Castro, A. Cipitria, R. A. Coles, R. Dimova, M. Eder, S. Ehrig, L. M. Escudero, M. E. Evans, P. R. Fernandes, P. Fratzl, L. Geris, N. Gierlinger, E. Hannezo, A. Iglič, J. J. K. Kirkensgaard, P. Kollmannsberger, Ł. Kowalewska, N. A. Kurniawan, I. Papantoniou, L. Pieuchot, T. H. V. Pires, L. D. Renner, A. O. Sageman-Furnas, G. E. Schröder-Turk, A. Sengupta, V. R. Sharma, A. Tagua, C. Tomba, X. Trepat, S. L. Waters, E. F. Yeo, A. Roschger, C. M. Bidan, J. W. C. Dunlop, Curvature in biological systems: Its quantification, emergence and implications across the scales, *Adv. Mater.* 35 (2023) 2206110, https://doi.org/10.1002/adma.202206110.

16.   B. Moreno, A. DiCorato, A. Park, K. Mobilia, R. Knapp, R. Bleher, C. Wilke, K.

Alvares, D. Joester, Culture of and experiments with sea urchin embryo primary

mesenchyme cells, *Methods Cell Biol.* 150 (2019) 293–330,

https://doi.org/10.1016/bs.mcb.2019.01.002.

17.   M.R. Winter, M. Morgulis, T. Gildor, A.R. Cohen, S. Ben-Tabou de-Leon, Calcium-

vesicles perform active diffusion in the sea urchin embryo during larval

biomineralization, *PLoS Comput. Biol.* 17(2) (2021) e1008780,

https://doi.org/10.1371/journal.pcbi.1008780.

18.   N.A. Stepicheva, M. Dumas, P. Kobi, J.G. Donaldson, J.L. Song, The small GTPase

Arf6 regulates sea urchin morphogenesis, *Differentiation* 95 (2017) 31–43,

https://doi.org/10.1016/j.diff.2017.01.003.

19.   E. Hijaze, T. Gildor, R. Seidel, M. Layous, M. Winter, L. Bertinetti, Y. Politi, S. Ben-

Tabou, S.B.T. de-Leon, ROCK and the actomyosin network control biomineral growth

and morphology during sea urchin skeletogenesis, *Elife* 12 (2024) RP89080,

https://doi.org/10.7554/eLife.89080.4.

20.   P. Vyas, C. Brannon, L. Formery, C.J. Lowe, M. Prakash, Algorithmic construction of

topologically complex biomineral lattices via cellular syncytia, *bioRxiv* (2024)

2024.02.06.579287, https://doi.org/10.1101/2024.02.20.580924.

21.   T. Yang, H. Chen, Z. Jia, Z. Deng, L. Chen, E.M. Peterman, J.C. Weaver, L. Li, A

damage-tolerant, dual-scale, single-crystalline microlattice in the knobby starfish,

*Protoreaster nodosus*, *Science* 375(6581) (2022) 647–652,

https://doi.org/10.1126/science.abj9472.

22.   P. Gorzelak, D. Kołbuk, J. Stolarski, P. Bącal, B. Januszewicz, P. Duda, D. Środek, T.

Brachaniec, M.A. Salamon, A Devonian crinoid with a diamond microlattice, *Proc. R.*

*Soc. B* 290(1995) (2023) 20230092, https://doi.org/10.1098/rspb.2023.0092.

23. A.L. Jessop, A.J. Millsteed, J.J. Kirkensgaard, J. Shaw, P.L. Clode, G.E. Schröder-Turk,

Composite material in the sea urchin *Cidaris rugosa*: ordered and disordered

micrometre-scale bicontinuous geometries, *J. R. Soc. Interface* 21(212) (2024)

20230597, https://doi.org/10.1098/rsif.2023.0597.

24. J. Feng, J. Fu, X. Yao, Y. He, Triply periodic minimal surface (TPMS) porous

structures: from multi-scale design, precise additive manufacturing to multidisciplinary

applications, *Int. J. Extrem. Manuf.* 4 (2022) 022001, https://doi.org/10.1088/2631-

7990/ac5be6.

25. Z. Gan, M.D. Turner, M. Gu, Biomimetic gyroid nanostructures exceeding their natural

origins. *Sci. Adv.* 2 (2016) e1600084, https://doi.org/10.1126/sciadv.1600084.

26. S. Hyde, Z. Blum, T. Landh, S. Lidin, B. W. Ninham, S. Andersson, K. Larsson, The

language of shape: the role of curvature in condensed matter: physics, chemistry and

biology. Elsevier. (1996)27.    T.A. Del Valls, A.G. Dickson, The pH of buffers based

on 2-amino-2-hydroxymethyl 1,3-propanediol ('tris') in synthetic sea water, *Deep-Sea*

*Res. Part I* 45 (1998) 1541–1554, https://doi.org/10.1016/S0967-0637(98)00019-3.

28. C.A. Schneider, W.S. Rasband, K.W. Eliceiri KW. NIH Image to ImageJ: 25 years of

image analysis, *Nature Methods* 9 (2012) 671–675, https://doi.org/10.1038/nmeth.2089.

29. R. Seidel, K. Handrich, M. Albéric, J. Perrin, D. Joester, Y. Politi, L. Bertinetti,

Comparative structural analysis of stereom polymorphs in the sea urchin test, *Faraday*

*Discussions* 261 (2025) 340–358, https://doi.org/10.1039/D5FD00033E.

30. H. Suzuki, K. Tatei, N. Ohshima, S. Sato, T. Izumi,Regulation of MC3T3-E1

differentiation by actin cytoskeleton through lipid mediators reflecting the cell

differentiation stage. *Biochem. Biophys. Res. Commun.* 514(2) (2019) 393–400,

https://doi.org/10.1016/j.bbrc.2019.04.093.

31.   M. Morgulis, T. Gildor, M. Roopin, N. Sher, A. Malik, M. Lalzar, M. Dines, S. Ben-

Tabou de-Leon, L. Khalaily, S. Ben-Tabou de-Leon, Possible cooption of a VEGF-

driven tubulogenesis program for biomineralization in echinoderms, *Proc. Natl. Acad.*

*Sci. U.S.A.* 116(25) (2019) 12353–12362, https://doi.org/10.1073/pnas.1902126116.

32.   B. Tesson, M. Hildebrand, Extensive and Intimate Association of the Cytoskeleton with

Forming Silica in Diatoms: Control over Patterning on the Meso- and Micro-Scale.

*PLoS ONE* 5(12) (2010) e14300. https://doi.org/10.1371/journal.pone.0014300

33.   B. Tesson, M. Hildebrand, Dynamics of silica cell wall morphogenesis in the diatom

*Cyclotella cryptica*: Substructure formation and the role of microfilaments, *J. Struct.*

*Biol.* 169 (2010) 62–74, https://doi.org/10.1016/j.jsb.2009.08.013.

34.   G. Langer, L.J. De Nooijer, K. Oetjen, On the role of the cytoskeleton in coccolith

morphogenesis: The effect of cytoskeleton inhibitors, *J. Phycol.* 46 (2010) 1252–1256,

https://doi.org/10.1111/j.1529-8817.2010.00916.x.

35.   G.M. Durak, C. Brownlee, G.L. Wheeler, The role of the cytoskeleton in

biomineralisation in haptophyte algae, *Sci. Rep.* 7 (2017) 15409,

https://doi.org/10.1038/s41598-017-15562-8.

36.   J. Tyszka, U. Bickmeyer, M. Raitzsch, J. Bijma, K. Kaczmarek, A. Mewes, M. Janse,

Form and function of F-actin during biomineralization revealed from live experiments

on foraminifera, *Proc. Natl. Acad. Sci. U.S.A.* 116(10) (2019) 4111–4116,

https://doi.org/10.1073/pnas.1810394116.