AI-Guided Stability Tuning of a Heterodimeric Linker for Programmable Protein Tube

Architectures

Masahiro Noji[1], Takuro Fujiwara[2,3], Yukihiko Sugita[2,4], and Yuta Suzuki[1,5]*

[1]Institute for Integrated Cell-Material Sciences, Kyoto University, Kyoto, Japan; [2]Institute for Life and

Medical Sciences, Kyoto University, Kyoto, Japan; [3]Graduate School of Medicine, Kyoto University,

Kyoto, Japan; [4]Graduate School of Biostudies, Kyoto University, Kyoto, Japan; [5]PRESTO, JST, Saitama,

Japan; *e-mail: suzuki.yuta.2m@kyoto-u.ac.jp

Abstract

The ability to rationally modulate the morphology of artificial higher-order protein assemblies

remains limited, particularly for geometrically constrained architectures such as tubes. Here, we

show that simple tuning of the interaction stability within a heterodimeric coiled-coil linker, guided

by deep-learning-based predictions from ThermoMPNN, provides an effective strategy for

programming the assembly behaviour of two-component protein tubes. By engineering a systematic

stability gradient within the M3L2/p66α heterodimeric linker, we generated single-amino-acid

variants that exhibit predictable shifts in the temperature window for tube formation and produce

tubes with distinct diameters. Notably, the least stable variant uniquely accesses multilayered tube-

in-tube architectures. Time-course electron microscopy reveals that these hierarchical structures

arise through a sequential process involving the initial formation of thin tubes, subsequent wall

thickening, and eventual development of nested tubes, highlighting the role of transient linker

rearrangements near the thermal transition. Together, these findings establish coiled-coil stability as

a minimal and tunable design parameter that governs higher-order morphology and offer a minimal

and programmable framework for constructing rationally designed protein tube architectures.

Higher-order protein assemblies underpin a wide range of essential biological processes. Nature employs

an extraordinary repertoire of architectures—from cytoskeletal filaments whose length and flexibility are

precisely regulated[1-4], to clathrin cages and viral capsids whose size, curvature, and symmetry are carefully

controlled[5-8]—to support functions that depend on both structural accuracy and dynamic adaptability. In

these systems, morphology is not merely a consequence of assembly but a parameter that is actively tuned

to enable transport[2,9], compartmentalisation[10,11], force generation[2,4,12], and responsive behaviour[2,13,14]. Such

naturally evolved mechanisms illustrate a level of morphological control that remains unmatched in
artificial protein assemblies.

Transferring these principles into artificial protein design could, in principle, enable the construction of
assemblies that are not only geometrically defined but also capable of dynamic, stimulus-responsive
behaviour reminiscent of natural systems. Such capabilities would advance both our fundamental
understanding of how morphology governs biological function and our ability to engineer artificial
structures with the precision and adaptability required for next-generation biotechnological applications[15-
20]. Such tunability of morphology may ultimately support applications in which size-defined or
compartmentalised architectures are advantageous, including delivery-oriented or catalytic systems.
Achieving this goal requires strategies that allow the architecture and physical properties of designed
assemblies to be modulated in a predictable and programmable manner.

Recent breakthroughs in computational design have enabled de novo construction of multi-component
assemblies[21-24]. Although these computational methods can accurately specify interaction geometries, they
provide only limited capacity to adjust the resulting assemblies—such as tuning their size or modulating
their overall architecture. Despite emerging platforms that allow modular control over size and shape[25-27],
broadly applicable methods for predictably tuning the architecture and mechanical properties of protein
assemblies remain relatively scarce. This is particularly true for closed, finite assemblies such as cages and
tubes, where geometric constraints impose strict requirements on interaction design.

In our previous work, two-component protein tubes assembled via MBD3L2 (M3L2)/p66α heterodimeric
coiled-coil exhibited a broad range of diameters and symmetries, revealing that this system inherently
supports rich morphological diversity[28]. This observation suggested that such diversity would be amenable
to deliberate tuning through rational design. Building on our previous design philosophy—which integrates
naturally inspired heterolinkers with symmetry-defined scaffold proteins to govern assembly pathways—
we reasoned that the properties of the coiled-coil linker itself could be exploited as a tunable element to
reshape tube morphology. Because the M3L2/p66α coiled-coil serves as the central connecting element of
the tube, we hypothesised that subtle modulation of its stability could offer a direct and predictable route to
controlling higher-order architecture.

To test this concept, we employed ThermoMPNN, a deep-learning model capable of predicting the stability
effects of point mutations with residue-level resolution[29]. This approach allowed us to systematically design
point mutations predicted to subtly modulate the stability of the coiled-coil linker without disrupting

heterodimer formation. Moreover, when incorporated into the tube-forming system, these engineered

linkers retained assembly competence yet produced distinct morphological outcomes, including increased

tube diameters and the emergence of tube-in-tube architectures. Together, these results demonstrate that

tuning coiled-coil stability offers a powerful and generalizable strategy for modulating the architecture and

dynamics of multi-component protein tubes, thereby expanding the design toolkit for programmable and

responsive higher-order assemblies.

Engineering the coiled-coil linker for controlled modulation of tube morphology

Given our observation that the M3L2/p66α coiled-coil linker plays a central role in defining tube

morphology, we first sought to test whether intentional modulation of its stability could serve as a design

parameter to reshape the architecture of the two-component tubular assemblies (**Fig. 1**).

In our previous study, dynamic rearrangement of the M3L2/p66α interaction near its melting temperature

(T_m) facilitated the formation of tubes with diverse diameters and symmetries[28]. This observation suggested

that coiled-coil interaction may directly influence assembly pathways and morphological outcomes, making

it an attractive target for rational engineering. Because p66α is intrinsically helical and structurally rigid,

whereas M3L2 is more flexible and partially disordered[30,31], we focused our engineering efforts on M3L2

while leaving p66α unmodified to avoid disrupting heterodimer formation. Our previous study indicated

that morphological diversity of these tubes arises from dynamic rearrangement of the M3L2/p66α

interaction near its T_m, where the effective binding strength becomes transiently weakened rather than

inherently destabilized. Based on this observation, we introduced a deliberately controlled gradient of

stability perturbations into the M3L2 helix to directly test how shifting the coiled-coil's thermal

responsiveness governs assembly morphology.

To introduce well-controlled stability perturbations, we systematically designed single-point mutations

using ThermoMPNN, a deep-learning model that predicts mutation-induced stability changes ($\Delta\Delta G_\mathrm{Pred}$)

with residue-level resolution[29]. Because ThermoMPNN is not applicable to multimer prediction, we first

generated an M3L2-Gly$_{50}$-p66α heterodimer structure using AlphaFold 2 (AF2)[32], and the most reliable

model was used for stability inference (**Fig. 1**). We then confined mutation scanning to previously reported

coiled-coil key residues in M3L2[31] and selected 13 point mutations predicted to yield a broad and

intentionally destabilised range of $\Delta\Delta G_\mathrm{Pred}$ values (**Fig. 2a, Table 1, and Supplementary Table 1**). This

design strategy ensured that the resulting variant set would span a predictable and tunable spectrum of

reduced coiled-coil stabilities.

Having established a set of variants spanning a wide and well-controlled range of predicted coiled-coil
stabilities, we next sought to investigate how these mutations affected heterodimer formation with p66α
and the thermal behaviour of the resulting coiled-coil complexes. To this end, we first constructed N-
terminal His-tagged versions of M3L2 (WT and all mutants) and p66α to characterise their biophysical
properties in isolation and in complex.

Expression in *E. coli* yielded both M3L2 and p66α constructs in soluble form, but purification behaviours
differed markedly. Whereas 6×His-TEVcs-p66α was readily purified using nickel-affinity chromatography,
the corresponding 6×His-TEVcs-M3L2(WT) construct predominantly appeared in the flowthrough,
preventing efficient recovery. We therefore extended the His-tag to 8×His-TEVcs, which enabled robust
purification of M3L2(WT). All 13 designed variants (Mvs) were subsequently constructed and purified in
the same 8×His-TEVcs-tagged format, ensuring consistency across the dataset.

To assess coiled-coil formation between M3L2 and p66α, we performed circular dichroism (CD)
spectroscopy using the purified His-tagged peptides (**Fig. 2b and Supplementary Fig. 1**). As expected,
M3L2(WT) exhibited a largely disordered conformation, whereas p66α adopted a more helical structure
when examined individually. Upon mixing the two peptides, however, a temperature-dependent increase in
α-helical signal characteristic of coiled-coil formation was observed, confirming that the isolated peptides
can reconstitute the heterodimeric interaction. Although our peptide constructs contain minor sequence
differences outside the core coiled-coil region compared with the previously reported peptides, the thermal
denaturation profile yielded an averaged T_m ($T_{m, Ave}$) of 31.7 °C (**Fig. 2c, Supplementary Fig. 2, Table 1,**
and Supplementary Table 1), which is close to the reported value of 34.8 °C for the M3L2/p66α coiled-
coil[31]. This agreement indicates that the essential interaction properties of the heterodimer are preserved in
our construct and that the purified peptide system reliably recapitulates its expected behaviour.

We next applied the same analyses to the 13 engineered Mvs to determine how the designed stability
perturbations influenced coiled-coil formation with p66α. CD spectroscopy revealed that several variants
showed reduced or less well-defined coiled-coil signatures, consistent with their strongly destabilising
$\Delta\Delta G_{Pred}$. Among the full panel of mutants, five variants—Mv3, Mv4, Mv5, Mv8, and Mv11—formed
sufficiently stable coiled-coil complexes with p66α to permit reliable thermal denaturation analysis (**Fig.**
2b and Supplementary Fig. 1).

Thermal unfolding experiments on these five variants yielded well-defined T_m, which collectively spanned
a broad and intentionally destabilised range that reflected the designed gradient of reduced coiled-coil

stabilities (**Fig. 2c, Supplementary Fig. 2, Table 1, and Supplementary Table 1**). Importantly, the

experimentally obtained $T_{m,Ave}$ values exhibited a strong negative correlation with the ThermoMPNN-

predicted $\Delta\Delta G_{Pred}$ values (r = −0.71 ± 0.35), supporting the validity of our deep-learning-based design

strategy (**Fig. 2d**). This agreement indicates that ThermoMPNN successfully generated mutations whose

experimentally observed effects followed the expected systematic decrease in coiled-coil stability across

the engineered spectrum. For the remaining variants, thermal denaturation curves were poorly defined, in

line with their weak CD signatures (**Supplementary Figs. 1 and 2**), preventing reliable T_m determination.

These observations are consistent with the strongly destabilising $\Delta\Delta G_{Pred}$ values for these mutants and

confirm that our engineered M3L2 panel spans a deliberately extended and well-controlled range of coiled-

coil stabilities. This set of linkers therefore provides a robust foundation for evaluating how stability tuning

influences the morphology and assembly behaviour of the two-component protein tubes.

Structural analysis of engineered coiled-coil variants

To understand how the designed mutations influenced coiled-coil formation with the deliberately

constructed stability gradient, we next analysed the structural consequences of each substitution using

AlphaFold 3 (AF3)[33]. AF3, which employs a diffusion-based generative approach, has recently been

reported to provide improved accuracy for predicting protein–protein interactions and the effects of point

mutations relative to AF2[33-35]. We therefore generated AF3 structural models for all M3L2/p66α

heterodimer pairs (**Fig. 2e–i and Supplementary Fig. 3**).

Among the variants, Mv1 (Q3Y) had the lowest destabilising $\Delta\Delta G_{Pred}$ (**Supplementary Table 1**), yet the

AF3 model suggested that this mutation disrupts an interchain hydrogen bond near the disordered N-

terminal region of M3L2 (**Supplementary Fig. 3a**). Although this mutation shows only a small predicted

destabilising effect in terms of $\Delta\Delta G$, the reduced reliability of structure prediction within intrinsically

disordered regions may obscure additional intra- or interchain contacts, and such unmodelled interactions

could inhibit coiled-coil formation.

For Mv2–Mv4, AF3 models indicated that the mutated residues do not directly participate in interchain

interactions (**Fig. 2e, f and Supplementary Fig. 3b**). This is consistent with their relatively modest $\Delta\Delta G_{Pred}$

values (**Table 1, Supplementary Table 1**). Nonetheless, Mv2 (P7G) exhibited surprisingly weak coiled-

coil propensity in experiments. Because P7 is located at the helix "N-cap," where proline contributes

favourably to helix stability[36,37], replacing it with glycine may reduce local structural stability more than

predicted, explaining the experimentally observed destabilisation.

The remaining variants (Mv5–Mv13) generally weakened or disrupted interchain packing interactions, in
agreement with their higher $\Delta\Delta G_{Pred}$ values (**Fig. 2g–i, Supplementary Fig. 3c–h, Table 1, and**
Supplementary Table 1). These models support the interpretation that mutations predicted to be highly
destabilising by ThermoMPNN indeed perturb key interchain interactions within the coiled-coil interface.
Together, these AF3-based structural analyses rationalise the experimentally observed stability gradient
across the M3L2 variant panel and reinforce the suitability of computationally guided stability tuning as a
foundation for subsequent morphology control in the two-component tube system.

Effect of coiled-coil stability tuning on two-component tube formation
Having established that the engineered M3L2 variants span a wide range of coiled-coil stabilities, we next
examined how these stability differences influence the morphology of the two-component tubular
assemblies (**Fig. 3a**). Because the majority of variants either formed weak or poorly defined coiled-coils
with p66α or lacked reliable thermal unfolding behaviour, they were unlikely to yield interpretable
outcomes when incorporated into the PuuE system. Among the variants that did form sufficiently well-
defined coiled-coils, Mv3 and Mv4 represented the most informative pair: they exhibited the highest and
lowest $T_{m,Ave}$ values, respectively, within the reliably characterised subset, and their $T_{m,Ave}$ values decreased
in an approximately uniform manner across the panel (**Table 1**). These features provided an intentionally
broad and predictable contrast in linker stability, allowing us to probe how defined shifts in thermal
responsiveness affect assembly morphology. Based on this rationale, we selected Mv3 and Mv4 as
representative variants for incorporation into the PuuE system.

As reported previously[28], PuuE-M(WT) and PuuE-p form two-component tubes via the C-terminal
M3L2/p66α coiled-coil linkers, with tube formation being strongly promoted at 35 °C, likely due to thermal
fluctuations near the T_m of the coiled-coil linker (**Fig. 3b**). This temperature dependence further motivated
the use of stability-shifted linkers to modulate assembly outcomes in a controlled manner. To evaluate this
possibility, we introduced the Mv3 and Mv4 mutations individually into PuuE-M(WT) and purified the
resulting proteins (PuuE-Mvs) to assess their effects on tube assembly (**Fig. 3a**). Both PuuE-Mv3 and PuuE-
Mv4 were purified successfully and, when examined in isolation, did not form higher-order structures
according to negative-stain transmission electron microscopy (nsTEM) imaging (**Supplementary Fig. 4**).
Upon mixing with PuuE-p at 35 °C, PuuE-Mv3 and PuuE-Mv4 formed tubes in a manner broadly similar
to the wild-type system (**Fig. 3b, Supplementary Fig. 5**), confirming that both variants retain the minimal
requirements for heterodimerisation with p66α and for productive tube assembly. With tube formation
established across PuuE-M(WT), PuuE-Mv3, and PuuE-Mv4, we next turned to how differences in coiled-

coil stability influence more detailed aspects of assembly behaviour, including temperature dependence and

tube architecture.

To dissect the temperature sensitivity of each linker variant, we examined how the stability differences

between Mv3, Mv4, and the WT linker affect the temperature dependence of tube formation. As reported

previously[28], the PuuE-M(WT)/PuuE-p system exhibits a strong temperature dependence, with efficient

tube formation occurring between 30 and 40 °C and only limited assembly at lower temperatures. This

behaviour is attributed to dynamic rearrangements of the M3L2/p66α coiled-coil interaction near its T_{m}.

Consistent with this temperature dependence, mixtures of PuuE-M(WT) and PuuE-p formed micron-scale

tubes most efficiently at 35 °C, whereas markedly fewer tubes were observed at 15 °C (**Fig. 3b,**

Supplementary Fig. 5). In contrast, the three linkers exhibited a clear stability-dependent continuum:

PuuE-M(WT) showed almost no tube formation at 15 °C, PuuE-Mv3 displayed partial but limited assembly,

and PuuE-Mv4 retained robust tube-forming capability even under these low-temperature conditions.

Notably, PuuE-Mv4—the least stable coiled-coil among the reliably characterised variants—retained

substantial tube-forming capability even at 15 °C, producing discernible micron-scale tubes under

conditions where both WT and Mv3 showed only sparse assembly. In contrast, PuuE-Mv3, whose coiled-

coil stability is intermediate between WT and Mv4, exhibited an intermediate phenotype: reduced tube

formation at 15 °C but more robust assembly than WT. These findings establish that decreasing coiled-coil

stability systematically shifts the tube-forming temperature range toward lower temperatures.

Having established the stability-dependent temperature behaviour, we next tested whether these stability

differences also manifest in the physical architecture of the resulting tubes. Given that our previous work[28]

showed that PuuE tubes inherently exhibit a broad distribution of diameters, we sought to determine

whether rational tuning of linker stability could shift this distribution in a predictable manner. To address

this question, we quantified tube architectures across WT, Mv3, and Mv4. At 35 °C, the three variants again

formed a clear stability-dependent series: PuuE-M(WT) produced the thinnest tubes, PuuE-Mv3 yielded

intermediate diameters, and PuuE-Mv4 generated the thickest structures (**Fig. 3b, Supplementary Fig. 5**).

Quantitative analysis clearly demonstrated that lower coiled-coil stability correlates with larger tube

diameters, with Mv4 forming the thickest tubes and WT forming the thinnest (**Fig. 3c**). This systematic and

reproducible diameter shift indicates that the naturally occurring morphological diversity of PuuE tubes can

be deliberately biased through rational tuning of linker stability. Together, these observations support the

idea that coiled-coil stability serves as a tunable structural parameter governing tube architecture.

Formation process and structural features of multi-tube architectures

Strikingly, tubes formed by PuuE-Mv4 at 35 °C were not only larger in diameter (**Fig. 4a**) but also displayed

multilayered architectures, including clearly identifiable tube-in-tube structures (**Fig. 4b, Supplementary**

Fig. 6a). Cryo-electron tomography (Cryo-ET) revealed tube-in-tube assemblies concentrically arranged in

up to four layers (**Supplementary Fig. 7a–d**), across multiple fields of view, indicating that nested

organisation is a recurrent structural feature rather than a rare event. In regions of thin ice, we frequently

observed distorted and incomplete multilayered states, including tubes that appeared markedly flattened,

consistent with deformation imposed by local ice-thickness constraints. We also observed tube-in-tube

assemblies in which the outer layer partially covered the inner tube or was locally discontinuous, leaving

segments of the inner tube exposed (**Supplementary Fig. 7e**). Together, these thin-ice-associated

deformations and outer-layer discontinuities support the interpretation that the higher-order assemblies are

flexible yet mechanically labile.

Such nested morphologies were not observed for PuuE-M(WT) or PuuE-Mv3 under the same conditions.

Importantly, multilayered architectures were observed exclusively for PuuE-Mv4; neither PuuE-M(WT)

nor the intermediate-stability variant PuuE-Mv3 displayed any evidence of tube-in-tube formation. To

examine how these higher-order architectures arise, we performed time-resolved nsTEM imaging of PuuE-

Mv4/PuuE-p mixtures incubated at 35 °C and analysed the evolution of tube morphologies over the course

of assembly (**Fig. 4 and Supplementary Fig. 6a**).

At early time points (0–30 min), only thin, single-walled tubes were detected, typically spanning several

hundred nanometres in length. After 1–2 h, thicker tubes became increasingly dominant, showing that tube

elongation and thickening continue well after initial nucleation. Importantly, multilayered or tube-in-tube

structures were not apparent during these stages, consistent with wall thickening occurring prior to the

emergence of higher-order organisation. By approximately 4 h, however, distinct tube-in-tube architectures

began to appear, in which a secondary tubular layer was observed either partially or fully nested within a

pre-existing primary tube. These multilayered structures remained stable from 4 h to 24 h, indicating that

once formed, the tube-in-tube architecture represents a stable and mature structural state rather than a

transient intermediate.

In addition to these multilayered states, nsTEM also revealed regions where adjacent tubes meet at

incomplete or misaligned junctions, as well as displaced wall segments (**Supplementary Fig. 6b**). These

structural irregularities were particularly apparent in PuuE-Mv4 and were occasionally observed during

early stages of tube growth. Although their functional significance cannot be determined from these

observations alone, the presence of such local instabilities indicates that the assembling tubes can
temporarily adopt imperfect configurations during the growth.

This sequential progression—from thin tubes to thickened tubes, and ultimately to multilayered
architectures—shows that only Mv4 accesses hierarchical tube morphologies under these conditions,
whereas WT and Mv3 remain confined to single-walled architectures. Together, these observations indicate
that tuning coiled-coil stability not only shifts the temperature window and diameter of tube formation, but
also governs access to higher-order, hierarchical tubular states, including the emergence and stabilisation
of multi-walled tube architectures.

Discussion

In this study, we demonstrated that deliberate tuning of coiled-coil stability—guided by deep-learning–
based predictions from ThermoMPNN—provides a powerful means of controlling the assembly behaviour
and final morphology of two-component protein tubes (**Fig. 1**). Although ThermoMPNN was developed to
predict mutation-induced changes in protein thermal stability—most commonly to guide the identification
of stabilising mutations[29,38-41]—our study employs it in an inverse manner. By systematically selecting
destabilising mutations, we repurposed the model to modulate the energetics of the heterodimeric linker
interaction, highlighting both the versatility of the tool and the modular advantage of our assembly design.
Furthermore, although ThermoMPNN does not inherently support complex inference, we achieved pseudo-
complex prediction by focusing solely on the coiled-coiled linker. This exemplifies the modularity built
into our system, in which the scaffold and linker functions are fully separable.

By engineering a systematic, AI-assisted stability gradient within the M3L2/p66α heterodimeric linker, we
showed that single-amino-acid substitutions can systematically shift the temperature window for tube
formation and modulate tube diameter in a predictable manner (**Fig. 3b, c**). Critically, further destabilization
enables access to hierarchical assembly states that are not observed for more stable variants under the same
conditions, including multilayered tube-in-tube architectures (**Fig. 4b; Supplementary Fig. 7**). Time-
resolved imaging further revealed that these hierarchical states emerge through a stepwise morphological
transition—from thin tubes to wall-thickened intermediates, and ultimately to nested architectures—
reflecting the increased dynamic rearrangements near the temperature range where the linker undergoes
partial destabilization. Together, these findings demonstrate that local interaction energetics at a single
heterodimeric interface can directly govern the macroscopic morphology of multi-component protein
assemblies.

The results presented in this study reveal a clear and systematic relationship between the stability of the
M3L2/p66α heterodimeric linker and the morphology of the resulting two-component protein tubes (**Fig.
3, 4, and Table 1**). Across the engineered stability gradient—ranging from the most stable PuuE-M(WT),
through the intermediate variant Mv3, to the least stable Mv4—tube formation behaviour, temperature
sensitivity, tube diameter, and access to higher-order architectures all varied in a coherent and predictable
manner. This continuum of behaviours underscores the central role of local interaction energy in shaping
global assembly outcomes.
310
For PuuE-M(WT), the high stability of the coiled-coil interaction limits dynamic rearrangements even near
its T_m, resulting in a relatively narrow temperature window for tube formation and the production of thin,
single-walled tubes. In Mv3, moderate destabilisation weakens the interaction sufficiently to permit partial
tube formation at lower temperatures and to yield tubes of intermediate diameter, yet not enough to trigger
higher-order architectural transitions. In contrast, Mv4, the least stable linker, experiences substantial
transient weakening of the coiled-coil near its T_m, greatly increasing the frequency of dynamic linker
rearrangements. This enhanced dynamism enables growth processes not accessible in the more stable
variants—including progressive wall thickening and, ultimately, the formation of multilayered tube-in-tube
structures.
320
These differences in assembly behaviour are consistent with the intrinsic structural properties of the
engineered M3L2 variants. AF3 modelling indicated that, although both Mv3 and Mv4 introduce glycine
substitutions, their structural contexts differ in ways that directly impact coiled-coil stability (**Fig. 2e, f**).
Glycine is known to have one of the lowest intrinsic helix propensities among the canonical amino acids,
whereas alanine and arginine are comparatively helix-favouring, particularly in alanine-based model
helices[42]. In Mv3, the A14G substitution is positioned in a semi-exposed region where replacing alanine
with glycine is expected to modestly weaken local helical stability but not substantially disrupt the packing
interface, consistent with its intermediate phenotype. In contrast, the R16G mutation in Mv4 lies close to
interfacial packing and ionic contacts that stabilise the antiparallel heterodimer; replacing a bulky, helix-
compatible arginine side chain with glycine both creates a packing void and introduces a strong helix-
breaking residue at a structurally sensitive position. Positional studies in alanine-based helices have shown
that substitutions closer to the C-terminal region can exert disproportionately large effects on helicity
compared with substitutions nearer the N-terminus, consistent with enhanced sensitivity of C-terminal sites
to local perturbation[43]. These considerations provide a mechanistic rationale for why Mv3 remains confined
to single-walled tubes, whereas Mv4 accesses thickened and multilayered tube architectures through
enhanced dynamic rearrangements enabled by reduced coiled-coil stability. Our results establish that the

energetics of a single heterodimeric interaction can directly govern the macroscopic morphology of a multi-
component protein assembly.

The structural intermediates accompanying this transition provide further mechanistic insight. nsTEM
imaging revealed that PuuE-Mv4 frequently exhibits incomplete or misaligned junctions, as well as
displaced wall segments (**Supplementary Fig. 6b**). Although similar structural irregularities may also arise
in PuuE-M(WT) and Mv3, their consequences differ markedly among the variants. In Mv4, reduced coiled-
coil stability creates a dynamic regime in which transient structural fluctuations arise more readily and,
crucially, can be amplified into productive growth events. This heightened architectural potential enables
Mv4 to convert local instabilities into initiation sites for secondary nucleation or lateral association,
processes that are not observed for the more stable WT or intermediate-stability Mv3 linkers. These locally
unstable configurations are therefore consistent with a model in which transient partial dissociation of the
linker below its stability threshold enables the emergence of nested architectures by permitting
reorganization and re-engagement of the assembling interfaces. Moreover, the experimentally observed
temporal sequence—from thin tubes, through wall-thickened intermediates, and ultimately to mature tube-
in-tube assemblies—aligns with this stability-dependent dynamic-rearrangement model. Importantly, this
sequential progression indicates a path-dependent assembly process in which access to hierarchical tube
architectures is kinetically gated, rather than arising from simultaneous multilayer formation. Together,
these findings demonstrate that the capacity to access hierarchical morphologies is not determined solely
by the presence of structural defects but by the linker's ability to exploit such transient irregularities. Local
tuning of coiled-coil stability thus emerges as a minimal yet powerful lever for reshaping higher-order
architecture, influencing assembly efficiency, temperature responsiveness, and access to complex
hierarchical states.

The multilayered tube-in-tube architectures observed in PuuE-Mv4 resonate with the broader principle that
many natural protein assemblies—such as clathrin cages[5,6], actin networks[2], and microtubules with variable
protofilament numbers[13,44,45]—can access multiple geometric states through flexible and dynamic
interaction modules. Although these biological systems operate within far more complex regulatory
environments, our artificial scaffold captures an important aspect of this behaviour in a minimal and fully
defined form. The appearance of local junctional irregularities and their subsequent amplification into
higher-order architectures mirrors the way natural assemblies use transient structural fluctuations to
diversify morphology. Thus, by tuning the stability of a single heterodimeric linker, we reveal a
generalisable route for introducing natural-like architectural plasticity into designed protein assemblies,

providing a simple framework for exploring how dynamic interactions can give rise to hierarchical

structural diversity.

Although demonstrated here using the M3L2/p66α heterodimer and the tetrameric PuuE scaffold, these

results suggest that tuning the stability of a single interaction interface provides a general strategy for

controlling access to hierarchical assembly states in designed protein systems. Many naturally occurring

and engineered coiled-coils share modular architectures with well-defined positional roles of residues,

allowing their interaction energetics to be systematically tuned by minimal sequence modifications.

Likewise, the concept is not restricted to tubular assemblies: sheets, cages, or lattices that rely on linker-

mediated connectivity may also exhibit tunable morphology when the stability of the connecting element

is rationally modulated. Beyond expanding the design space for protein-based materials, stability-tuned

linkers may support the construction of assemblies that respond to external or physicochemical stimuli such

as temperature or ionic strength, suggesting applications in responsive biomaterials, encapsulation systems,

or programmable nanoscale scaffolds. Taken together, these observations indicate that stability modulation

of heterodimeric linkers can serve as a general handle for steering assembly outcomes, providing a

foundation for designing increasingly complex and functional protein architectures.

Having shown that linker stability can systematically influence tube morphology, we see several

opportunities for extending and refining this design framework. In this context, extending stability tuning

to orthogonal linkers and alternative protein backbones will be important for establishing the generality of

the approach. In addition, quantitative kinetic analyses may help reveal how the frequency and lifetime of

dynamic linker rearrangements depend on interaction energetics. More broadly, integrating stability tuning

with orthogonal design strategies—such as pH-responsive, ligand-gated, or redox-responsive linkers—may

enable the construction of fully programmable, multi-responsive assemblies with increasingly sophisticated

morphological and functional behaviours. Ultimately, this framework provides a starting point for creating

protein-based materials whose architectures and dynamics can be rationally guided through fine control of

local interaction stability.

Methods

Computational engineering of the M3L2/p66α coiled-coil interaction

The structure of M3L2-Gly$_{50}$-p66α was predicted using AlphaFold 2.3 (DeepMind)[32]. The most reliable

model (ranked_0 model) was used as the input for ThermoMPNN[29] to infer $\Delta\Delta G_{\text{Pred}}$ values for all possible

single-mutations. The resulting $\Delta\Delta G_{\text{Pred}}$ scores were examined, and for the previously reported coiled-coil

key residues in M3L2, the most destabilising mutation ($\Delta\Delta G_{\text{Pred}} > 0$) was selected. The overall

computational workflow is summarized in **Fig. 1**, and the selected mutations are listed in **Table 1** and
Supplementary Table 1. Amino acid sequences for all constructs used in this study are provided in
Supplementary Table 2.

Plasmids and cloning

The plasmids encoding N-terminal 6×His-TEVcs-tagged PuuE-M(WT) and PuuE-p were previously
constructed. The plasmids encoding N-terminal 6×His-TEVcs-tagged M3L2(WT) and p66α were generated
from the PuuE-M(WT) and PuuE-p plasmids, respectively, by removal of the PuuE coding region. The
plasmid encoding N-terminal 8×His-TEVcs-tagged M3L2(WT) was generated from the 6×His-TEVcs-
M3L2(WT) plasmid by introducing two additional His codons. The plasmids encoding N-terminal 8×His-
TEVcs-tagged Mv series (Mvs) and 6×His-TEVcs-tagged PuuE-Mv series (PuuE-Mvs) were generated
from the 8×His-TEVcs-M3L2(WT) and PuuE-M(WT) plasmids, respectively, by site-directed substitution
of the corresponding codons. All primers used in this study were purchased from Eurofins Genomics, and
all primer sequences are shown in **Supplementary Data 1**. Mutagenesis was performed using the KOD -
Plus- Mutagenesis Kit (TOYOBO) according to the manufacturer's instructions. The 6×His-TEVcs-
M3L2(WT), 8×His-TEVcs-M3L2(WT), Mvs, and p66α plasmids were amplified in *E. coli* strain BL21
(DE3) derived ECOS SONIC competent cells (NIPPON GENE) and extracted using the NucleoSpin
Plasmid EasyPure (MACHEREY-NAGEL) according to the manufacturer's protocol. The PuuE-Mvs
plasmids were amplified in *E. coli* strain DH5α (NIPPON GENE) and purified using the same procedure.
All construct sequences were verified by Eurofins Genomics. Amino acid sequences for all constructs used
in this study are provided in **Supplementary Table 2**.

Protein expression and purification

The recombinant proteins of N-terminal 6× or 8×His-TEVcs-tagged M3L2(WT), Mvs, and p66α were
expressed using *E. coli* strain BL21 (DE3) derived ECOS SONIC competent cells as follows. Glycerol
stocks of transformed cells were used to inoculate 5 mL of liquid LB broth supplemented with 100 μg/mL
ampicillin (Amp) and grown overnight at 37 °C and 200 rpm. Overnight cultures were diluted into 1 L of
LB-Amp broth and grown at 37 °C and 200 rpm until reaching an optical density at 600 nm of 0.4–0.6.
Protein expression was induced by adding 0.1 mM isopropyl-β-D-thiogalactopyranoside, and the cultures
were grown at 16 °C for 18–20 h. Cells were harvested by centrifugation at 15,317 × *g* for 5 min at 4 °C
and stored at –80 °C.

The recombinant proteins of PuuE-M(WT), PuuE-Mvs, and PuuE-p were expressed using *E. coli* strain
BL21 (DE3) (NIPPON GENE) co-transformed with a pGro7 chaperone plasmid (Takara Bio). After

transformation, colonies grown overnight on LB agar plates supplemented with Amp and 20 μg/mL

chloramphenicol (Crm) at 37 °C were used to inoculate 5 mL of liquid LB-Amp-Crm broth and cultured

overnight at 37 °C and 200 rpm. Overnight cultures were diluted into 1 L of liquid LB-Amp-Crm broth

supplemented with 0.5 mg/mL L-arabinose and grown at 37 °C and 200 rpm until reaching an optical

density at 600 nm of 0.4–0.6. Protein induction and cells harvest was performed as described above.

All recombinant proteins were purified as follows. Cell pellets were thawed at 37 °C, resuspended in 60

mL of ice-cold purification buffer (20 mM Tris-HCl, pH 8.0, containing 300 mM NaCl), and lysed by

sonication (9 min, 1:2 on/off cycles, 70% amplitude; SFX250, Branson) on ice. Cell debris was removed

by centrifugation at 15,317 × g for 30 min at 4 °C. The supernatants were passed through a 0.45-μm pore

size membrane filter (Merck), loaded onto a HisTrap FF crude column (Cytiva) pre-equilibrated with the

purification buffer, and washed with 5 column volumes of 2% elution buffer (20 mM Tris-HCl, pH 8.0,

containing 300 mM NaCl and 1 M imidazole; 2% means 20 mM imidazole). Target proteins were eluted

with 10 column volumes of elution buffer with a linear gradient of 2–40% (i.e., 20–400 mM imidazole).

Fractions containing the target proteins as verified by UV absorbance and SDS-PAGE were dialysed twice

against a 50-fold volume of experimental buffer (50 mM Tris-HCl, pH 8.0, containing 100 mM NaCl and

0.5 mM EDTA) at 4 °C. Purified proteins were concentrated by Amicon Ultra centrifugal filter unit (Merck)

with an appropriate molecular weight cutoff, followed by filtration through a 0.45 μm pore size membrane

filter (Merck). Protein concentrations were determined by measuring absorbance at 280 nm using a

NanoDrop OneC spectrophotometer (Thermo Scientific). The molar extinction coefficients at 280 nm for

the proteins were calculated based on amino acid composition[46]. The concentrated proteins were flash-

frozen in liquid nitrogen and stored at –80 °C until use.

Circular dichroism (CD) spectrum measurements

All proteins were thawed immediately before CD measurements and kept on ice. Each sample was prepared

in a 1.5-mL microtube using experimental buffer to adjust the final protein concentration to 5.0 μM for

single-component samples or 2.5 + 2.5 μM for binary complexes, in a total volume of 200 μL at 25 ± 1 °C.

Far-UV CD spectra were recorded at a wavelength of 195 to 250 nm using a J-1100 spectropolarimeter

(JASCO) equipped with a 1-mm-path-length quartz cuvette, at the temperatures indicated in the manuscript.

Thermal denaturation measurements were performed over a temperatures range of 0 to 60 °C, with a heating

rate of 1 °C/min, while monitoring ellipticity at 222 nm. All spectra data were collected using Spectra

Manager version 2.5 (JASCO) and expressed as mean residue ellipticity. The T_m value of each sample was

determined from the thermal denaturation curve by sigmoid fitting using Igor Pro 9 version 9.0.5.1
(WaveMetrics).
473
Tube formation
All proteins were thawed immediately before tube formation experiments and kept on ice. Each sample was
prepared in a 1.5-mL microtube using experimental buffer to adjust the concentration as indicated in the
figure legends, with a final volume of 100 μL at 25 ± 1 °C. Sample incubation was performed using a
ThermoMixer C (Eppendorf) or a MATRIX Orbital Delta Plus (IKA) with shaking at 300 rpm, at the
temperatures described in the manuscript.
480
Negative-stain transmission electron microscopy (nsTEM)
A naked G600TT copper grid (Nisshin EM) was carbon-coated using a VE-2030 (VACUUM DEVICE).
The grid was glow-discharged using a PIB-10 (VACUUM DEVICE). Then, a 5-μL aliquot of the sample
solution was placed on the grid for 1 min, and the remaining solution was removed with filter paper (No. 2,
ADVANTEC) followed by rinsing thrice with a 5-μL aliquot of Milli-Q water. After blotting off the water
with filter paper, the sample was stained briefly with a 3-μL aliquot of 2% (w/v) uranyl acetate solution
three times. The remaining solution was removed with filter paper and the grid was dried on the benchtop.
TEM observation was performed using a transmission electron microscope HT-7700 (Hitachi) with an
acceleration voltage of 80 kV. The images were recorded using HT-7700 control software version 02.22
(Hitachi).
491
Cryo-electron tomography (Cryo-ET)
A 2.7-μl aliquot of specimen solution was applied onto glow-discharged Quantifoil R1.2/1.3 Gold 200
mesh grids (Quantifoil Micro Tools GmbH). After blotting excess solution from the grids with filter paper,
specimens were rapidly frozen in liquid ethane on a Vitrobot Mark IV (Thermo Fisher Scientific). Cryo-
ET datasets were collected using a Glacios cryo-TEM (Thermo Fisher Scientific) operated at an
acceleration voltage of 200 kV, equipped with a Falcon4 direct electron detector at the Institute for Life
and Medical Sciences, Kyoto University. Tilt-series were collected with a dose-symmetric tilt scheme[47]
using TEM Tomography 5 software (Thermo Fisher Scientific). The tilt span of ±60° was used in 3°
increments, starting at 0°. All tilt-series were collected in nanoprobe mode with a defocus of -4.0 μm and
TIFF compression enabled. Data were acquired at a dose rate of 10.6 e⁻/pixel/s, a pixel size of 1.55 Å, and
a total exposure of 144 e⁻/Å² per tilt series. Eucentric height estimation was performed once for each tilt
angle using stage-tilt method in TEM Tomography 5 software. Regions of interest were added manually,
and positions were saved. Tracking and focusing were performed before and after each tilt step. All data

were processed using RELION-5 tomography pipeline[48]. TIFF movie frames were motion corrected using

RELION's own implementation and gain normalisation using a gain reference image generated by the

"relion_estimate_gain" command in RELION-5. Tilt-series alignment was performed using AreTomo2[49],

which simultaneously estimates the contrast transfer function (CTF) for each tilt image during alignment.

The aligned tilt series were subsequently used to reconstruct tomograms. All tomographic reconstructions

were binned to yield a final pixel size of 12.4 Å, and were visualized using IMOD software package[50].

Tube diameter analysis

For each sample incubated at 35 °C, more than 200 clearly discernible tubes were picked up manually on

10k-magnification nsTEM images. Tube segments in which tubes overlapped were excluded from analysis.

Tube diameters were measured using ImageJ (Fiji) version 1.53[51]. For quantitative comparison, a

representative subset of 150 tubes was selected from the measurable population using the same inclusion

criteria across all samples, focusing on the larger-diameter species that predominated under the tube-

forming conditions. Diameter distributions and plots were generated using Igor Pro 9.

Molecular modelling

The structure of M3L2-Gly$_{50}$-p66α, PuuE-M(WT), and PuuE-p was predicted by AlphaFold 2.3

(DeepMind)[32,52]. All other predicted protein structures were generated using AlphaFold 3 (DeepMind)[33].

Cartoon representations of protein models were drawn using PyMOL version 2.5 (Schrödinger)[53] and UCSF

ChimeraX version 1.9 (UCSF RBVI and NIH)[54].

Statistics and Reproducibility

For the analysis of tube diameter, a two-sided Welch's *t* test was performed to test the null hypothesis, and

the exact *p* values are provided in the figure legend. Each of the tube formation experiment was repeated

using at least two biological replicates, and consistent results were confirmed by nsTEM.

References

1   Korn, E. D., Carlier, M. F. & Pantaloni, D. Actin polymerization and ATP hydrolysis. *Science* **238**,
638-644 (1987).
2   Pollard, T. D. & Cooper, J. A. Actin, a central player in cell shape and movement. *Science* **326**,
1208-1212 (2009).
3   Block, J., Schroeder, V., Pawelzyk, P., Willenbacher, N. & Koster, S. Physical properties of
cytoplasmic intermediate filaments. *Biochim Biophys Acta* **1853**, 3053-3064 (2015).
4   Gudimchuk, N. B. & McIntosh, J. R. Regulation of microtubule dynamics, mechanics and function
through the growing tip. *Nat Rev Mol Cell Biol* **22**, 777-795 (2021).
5   Fotin, A. et al. Molecular model for a complete clathrin lattice from electron cryomicroscopy.
Nature **432**, 573-579 (2004).

6   Morris, K. L. et al. Cryo-EM of multiple cage architectures reveals a universal mode of clathrin
self-assembly. *Nat Struct Mol Biol* **26**, 890-898 (2019).
7   Perlmutter, J. D. & Hagan, M. F. Mechanisms of virus assembly. *Annu Rev Phys Chem* **66**, 217-
239 (2015).
8   Sevvana, M., Klose, T. & Rossmann, M. G. Principles of Virus Structure. *Encyclopedia of Virology*,
257-277 (2021).
9   Kaksonen, M. & Roux, A. Mechanisms of clathrin-mediated endocytosis. *Nat Rev Mol Cell Biol*
19, 313-326 (2018).
10   Sugita, Y., Matsunami, H., Kawaoka, Y., Noda, T. & Wolf, M. Cryo-EM structure of the Ebola virus
nucleoprotein-RNA complex at 3.6 A resolution. *Nature* **563**, 137-140 (2018).
11   Zhou, R. Q. et al. Structure and assembly of the alpha-carboxysome in the marine cyanobacterium
Prochlorococcus. *Nat Plants* **10**, 661-672 (2024).
12   Hvorecny, K. L., Sladewski, T. E., De La Cruz, E. M., Kollman, J. M. & Heaslip, A. T. Toxoplasma
gondii actin filaments are tuned for rapid disassembly and turnover. *Nat Commun* **15**, 1840 (2024).
13   Chalfie, M. & Thomson, J. N. Structural and functional diversity in the neuronal microtubules of
Caenorhabditis elegans. *J Cell Biol* **93**, 15-23 (1982).
14   Fukushige, T. et al. MEC-12, an alpha-tubulin required for touch sensitivity in C. elegans. *J Cell
Sci* **112 (Pt 3)**, 395-403 (1999).
15   Bai, Y., Luo, Q. & Liu, J. Protein self-assembly via supramolecular strategies. *Chem Soc Rev* **45**,
2756-2767 (2016).
16   Huang, P. S., Boyken, S. E. & Baker, D. The coming of age of de novo protein design. *Nature* **537**,
320-327 (2016).
17   Gainza-Cirauqui, P. & Correia, B. E. Computational protein design-the next generation tool to
expand synthetic biology applications. *Curr Opin Biotechnol* **52**, 145-152 (2018).
18   Kuhlman, B. & Bradley, P. Advances in protein structure prediction and design. *Nat Rev Mol Cell
Biol* **20**, 681-697 (2019).
19   Zhu, J. et al. Protein Assembly by Design. *Chem Rev* **121**, 13701-13796 (2021).
20   Kortemme, T. De novo protein design-From new structures to programmable functions. *Cell* **187**,
526-544 (2024).
21   King, N. P. et al. Accurate design of co-assembling multi-component protein nanomaterials. *Nature*
510, 103-108 (2014).
22   Bale, J. B. et al. Accurate design of megadalton-scale two-component icosahedral protein
complexes. *Science* **353**, 389-394 (2016).
23   Ben-Sasson, A. J. et al. Design of biologically active binary protein 2D materials. *Nature* **589**, 468-
473 (2021).
24   Wang, S. et al. Bond-centric modular design of protein assemblies. *Nat Mater* **24**, 1644-1652 (2025).
25   Brodin, J. D. et al. Metal-directed, chemically tunable assembly of one-, two- and three-
dimensional crystalline protein arrays. *Nat Chem* **4**, 375-382 (2012).
26   Huddy, T. F. et al. Blueprinting extendable nanomaterials with standardized protein blocks. *Nature*
627, 898-904 (2024).
27   Koziej, L. et al. Dynamic Assembly of Pentamer-Based Protein Nanotubes. *ACS Nano* **19**, 8786-
8798 (2025).
28   Noji, M., Sugita, Y., Yamazaki, Y., Miyazaki, M. & Suzuki, Y. Protein design of two-component
tubular assemblies similar to cytoskeletons. *Nat Commun* **16**, 6738 (2025).
29   Dieckhaus, H., Brocidiacono, M., Randolph, N. Z. & Kuhlman, B. Transfer learning to leverage
larger datasets for improved prediction of protein stability changes. *Proc Natl Acad Sci U S A* **121**,
e2314853121 (2024).
30   Gnanapragasam, M. N. et al. p66Alpha-MBD2 coiled-coil interaction and recruitment of Mi-2 are
critical for globin gene silencing by the MBD2-NuRD complex. *Proc Natl Acad Sci U S A* **108**,
7487-7492 (2011).

Walavalkar, N. M., Gordon, N. & Williams, D. C., Jr. Unique features of the anti-parallel, heterodimeric coiled-coil interaction between methyl-cytosine binding domain 2 (MBD2) homologues and GATA zinc finger domain containing 2A (GATAD2A/p66alpha). *J Biol Chem* **288**, 3419-3427 (2013).

Jumper, J. et al. Highly accurate protein structure prediction with AlphaFold. *Nature* **596**, 583-589 (2021).

Abramson, J. et al. Accurate structure prediction of biomolecular interactions with AlphaFold 3. *Nature* **630**, 493-500 (2024).

Wee, J. & Wei, G. W. Evaluation of AlphaFold 3's Protein-Protein Complexes for Predicting Binding Free Energy Changes upon Mutation. *J Chem Inf Model* **64**, 6676-6683 (2024).

Lu, W., Zhang, J., Rao, J., Zhang, Z. & Zheng, S. AlphaFold3, a secret sauce for predicting mutational effects on protein-protein interactions. *bioRxiv* (2024).

Watanabe, K., Masuda, T., Ohashi, H., Mihara, H. & Suzuki, Y. Multiple proline substitutions cumulatively thermostabilize Bacillus cereus ATCC7064 oligo-1,6-glucosidase. Irrefragable proof supporting the proline rule. *Eur J Biochem* **226**, 277-283 (1994).

Watanabe, K. & Suzuki, Y. Protein thermostabilization by proline substitutions. *J Mol Catal B-Enzym* **4**, 167-180 (1998).

Peccati, F., Segovia, C. M., Núñez-Franco, R. & Jimenez-Oses, G. Computation of Protein Thermostability and Epistasis. *Wires Comput Mol Sci* **15** (2025).

Cui, X. C., Zheng, Y., Liu, Y., Yuchi, Z. & Yuan, Y. J. AI-driven de novo enzyme design: Strategies, applications, and future prospects. *Biotechnol Adv* **82**, 108603 (2025).

Sun, C. et al. Iterative recombinase technologies for efficient and precise genome engineering across kilobase to megabase scales. *Cell* **188**, 4693-4710 e4615 (2025).

Ou, W., Dan, J., Guo, X., Liu, Q. & Tan, L. An Integrative Strategy Enhancing Nanobody Thermostability via CDR Grafting, In Silico Mutagenesis Screening, and Multiplex Evaluation. *ACS Synth Biol* **14**, 2690-2702 (2025).

Chakrabartty, A., Kortemme, T. & Baldwin, R. L. Helix propensities of the amino acids measured in alanine-based peptides without helix-stabilizing side-chain interactions. *Protein Sci* **3**, 843-852 (1994).

Cheng, R. P. et al. Positional effects on helical Ala-based peptides. *Biochemistry* **49**, 9372-9384 (2010).

Chaaban, S. & Brouhard, G. J. A microtubule bestiary: structural diversity in tubulin polymers. *Mol Biol Cell* **28**, 2924-2931 (2017).

Ferreira, J. L. et al. Variable microtubule architecture in the malaria parasite. *Nat Commun* **14**, 1216 (2023).

Pace, C. N., Vajdos, F., Fee, L., Grimsley, G. & Gray, T. How to measure and predict the molar absorption coefficient of a protein. *Protein Sci* **4**, 2411-2423 (1995).

Hagen, W. J. H., Wan, W. & Briggs, J. A. G. Implementation of a cryo-electron tomography tilt-scheme optimized for high resolution subtomogram averaging. *J Struct Biol* **197**, 191-198 (2017).

Burt, A. et al. An image processing pipeline for electron cryo-tomography in RELION-5. *FEBS Open Bio* **14**, 1788-1804 (2024).

Zheng, S. et al. AreTomo: An integrated software package for automated marker-free, motion-corrected cryo-electron tomographic alignment and reconstruction. *J Struct Biol X* **6**, 100068 (2022).

Kremer, J. R., Mastronarde, D. N. & McIntosh, J. R. Computer visualization of three-dimensional image data using IMOD. *J Struct Biol* **116**, 71-76 (1996).

Schindelin, J. et al. Fiji: an open-source platform for biological-image analysis. *Nat Methods* **9**, 676-682 (2012).

Evans, R. et al. Protein complex prediction with AlphaFold-Multimer. *bioRxiv*, 2021.2010.2004.463034 (2022).

Schrodinger, LLC. *The PyMOL Molecular Graphics System, Version 2.5*.

643   54   Meng, E. C. et al. UCSF ChimeraX: Tools for structure building and analysis. *Protein Sci* **32**, e4792
644   (2023).

Fig. 1. AI-guided stability tuning of a heterodimeric coiled-coil linker enables programmable protein tube architectures. | Design workflow for generating stability-tunable M3L2/p66α coiled-coil variants using AF2 structural modelling, ThermoMPNN $\Delta\Delta G$ predictions, and selection of mutants spanning an engineered stability gradient (top). Assembly schematic and representative TEM images illustrating architecture-specific tube morphologies obtained with each variant (bottom). Stability-tuned M3L2 variants yield distinct tube architectures—thin (WT), intermediate (Mv3), and thick (Mv4)—upon assembly with PuuE-p. Scale bar, 100 nm.

Fig. 2. Deep-learning-guided engineering generates a predictable and experimentally validated coiled-coil stability gradient. | a, Schematic representations of the M3L2/p66α heterodimeric coiled-coil predicted by AF3 (left) and the targeted mutation sites (right). **b,** CD spectra of WT and selected M3L2 mutants complexed with p66α indicating preserved coiled-coil secondary structure. **c,** Thermal denaturation profiles of WT and selected M3L2 mutants. **d,** Correlation between ThermoMPNN-predicted $\Delta\Delta G_{\text{Pred}}$ values and the experimentally determined $T_{\text{m,Ave}}$. **e–i,** AF3 structural models illustrating mutation-dependent local perturbations within the M3L2/p66α interface. Mutated residues are shown in space-filling (ball) representation to highlight steric volume and hydrophobic packing effects, whereas neighbouring residues involved in hydrogen-bonding or other directional interactions are shown in stick representation to visualise how each substitution alters the local interaction environment.

Fig. 3. M3L2/p66α coiled-coil stability dictates the temperature-dependent formation and morphology of two-component protein tubes. | a, Schematic representation of the two-component tube-forming system, showing PuuE-M(WT) or its stability-tuned variants (PuuE-Mv3, PuuE-Mv4) paired with PuuE-p via the C-terminal M3L2/p66α heterodimeric linker. b, Representative nsTEM images of tubes formed by PuuE-M(WT), PuuE-Mv3, and PuuE-Mv4 in complex with PuuE-p at 15, 25, and 35 °C. Additional representative TEM images across temperatures are provided in Supplementary Fig. 5. c, Quantified tube diameter distributions for PuuE-M(WT), PuuE-Mv3, and PuuE-Mv4 after 24 h of incubation at 35 °C. Mean values are shown with diamond-shaped markers. ***$p < 0.001$ (p-values; WT–Mv3 = 4.21×10^{-12}, Mv3–Mv4 = 8.87×10^{-88}, and WT–Mv4 = 2.11×10^{-97}, two-sided Welch's t test). Scale bar, 100 nm.

Fig. 4. Reduced coiled-coil stability enables a hierarchical tube-in-tube assembly pathway through

transient structural intermediates. | a, Time-resolved nsTEM images of PuuE-Mv4 assembled with

PuuE-p at 35 °C, illustrating the progressive elongation of tubes over time (0.5, 1, 2, 4, and 24 h). Insets

show magnified views of representative tube segments at each time point. **b,** Representative nsTEM images

comparing tubes lacking tube-in-tube features (2 h) with those in which tube-in-tube architectures begin to

appear (4 h) and fully develop (24 h). Additional time points and further representative images are provided

in **Supplementary Fig. 6**. Scale bars: white, 1 μm; black, 100 nm.

Name	Mutation	$\Delta\Delta G_{\text{Pred}}$ (kcal/mol)	$T_{\text{m,Ave}}$ (°C)
WT	None	None (= 0)	31.7
Mv3	A14G	0.888	25.5
Mv4	R16G	1.136	17.2
Mv5	L28G	1.443	22.6
Mv8	R21D	1.637	17.7
Mv11	V5N	2.439	20.9

Table 1. M3L2 wild-type and selected mutants. | Predicted stability changes for point mutations ($\Delta\Delta G_{\text{Pred}}$) derived from ThermoMPNN inference are shown for M3L2 wild-type (WT) and its selected mutants (Mvs). Averaged melting temperatures ($T_{\text{m,Ave}}$) determined from CD measurements are provided for coiled-coil complexes formed between p66α and each variant. Source data are provided as a Source Data file.

Acknowledgements

This work was supported by JSPS KAKENHI (grant nos. 19H02832, 19K22253, and 21H05116 to Yuta Suzuki (Y. Suzuki); 21H05117 to Y. Suzuki and Yukihiko Sugita (Y. Sugita); and 20K22628, 21J00530, and 22KJ1644 to M.N.), JST PRESTO (grant no. JPMJPR22A7 to Y. Suzuki.), Takeda Science Foundation to Y. Suzuki, Chubei Itoh Foundation to Y. Suzuki, and The Hakubi Center for Advanced Research to Y. Sugita, and Y. Suzuki.

Author contributions Statement

Y. Suzuki directed the project and led the conceptual framework. M.N. and Y. Suzuki conceived and designed the study. M.N. performed all experiments except cryo-EM and analysed the data with Y.Suzuki. providing interpretative guidance. T.F., Y. Sugita and M.N. performed cryo-EM data collection, and T.F. and Y. Sugita analysed the cryo-EM data. Y.Suzuki and M.N. wrote the manuscript with contributions from T.F. and Y. Sugita.

Supplementary Figures

Supplementary Fig. 1. Coiled-coil formation of M3L2(WT) and Mvs. | CD spectra for isolated M3L2 variants (solid black lines) and p66α (dashed black lines) measured at 25 °C, as well as spectra for mixtures of each variant with p66α measured at 5 °C and 25 °C (blue and red lines, respectively). All spectra are labelled with the corresponding construct names. Source data are provided as a Source Data file.

Supplementary Fig. 2. Thermal stability of M3L2(WT) and Mvs. | Thermal denaturation curves of mixtures of M3L2 variants with p66α recorded from 0 to 60 °C. For each variant, three independent experiments were performed; individual $\theta_{222\ nm}$ values are plotted with different markers. Fitted curves (solid lines) and the extracted T_m values (dashed lines) are shown in matching colours for each dataset. Numerical T_m and the calculated $T_{m,Ave}$ values are summarised in **Supplementary Table 1**. Source data are provided as a Source Data file.

Supplementary Fig. 3. AF3 structural prediction of Mvs/p66α coiled-coil complexes. | a–h, the most reliable AF3-predicted models of WT (left) and each Mv variant (right) in complex with p66α, excluding the models shown in Fig. 2. For each model, the region surrounding the mutated residue is enlarged. Mutated residues and interacting partners are shown in ball (space-filling) or stick representations, with interchain hydrogen bonds indicated by dashed lines.

Supplementary Fig. 4. nsTEM images of PuuE-Mvs in the absence of PuuE-p. | a, b, Representative nsTEM images of PuuE-Mv3 (**a**) and PuuE-Mv4 (**b**). 12.5 μM PuuE-Mvs in experimental buffer was incubated at 25 °C for 24 h and imaged via nsTEM. Scale bars, 1 μm (white), 100 nm (black).

Supplementary Fig. 5. Additional nsTEM images corresponding to Fig. 3b. | Representative nsTEM images of tube formed from PuuE-M(WT) (top), PuuE-Mv3 (middle), and PuuE-Mv4 (bottom) mixed individually with PuuE-p and incubated for 24 h under the temperature conditions indicated at the top (15, 25, and 35 °C).

Supplementary Fig. 6. nsTEM analysis of PuuE-Mv4 tube formation at 35 °C. | a, Representative nsTEM images of tubes formed from PuuE-Mv4 mixed with PuuE-p and incubated at 35 °C from 0 to 24 h. These images provide time-course data complementary to Fig. 4, but show fields of view not included in the main figure. Time points are indicated at the top of each image. **b,** Representative nsTEM images

showing junctions between tubes of different diameters and displaced tube-wall segments, captured in the same dataset as panel **a**. Scale bars: 1 μm (white); 100 nm (black).

Supplementary Fig. 7. Cryo-ET analysis of PuuE-Mv4 tube formation at 35 °C. | a–d, Representative tomographic slices showing longitudinal views (left panel; single slice) and cross-sectional views (right panels; sum of 25 consecutive slices) of PuuE-Mv4 tubes in thicker ice (~120–280 nm) from cryo-ET reconstructions. Single- (a), double- (b), triple- (c), and four-layered (d) tubes are shown. **e**, PuuE-Mv4 tubes in ~80 nm of thin ice, showing pronounced tube flattening and an incomplete outer layer. White and blue dashed lines indicate the positions of cross-sections, labelled with numbers, and the ice surface, respectively. Scale bar: 50 nm.

Supplementary Tables

Name	Mutation	$\Delta\Delta G_{Pred}$ (kcal/mol)	T_m (°C)	$T_{m,Ave}$ (°C)
WT	None	None (= 0)	29.3 ± 1.7	31.7
			31.6 ± 1.0	
			34.1 ± 1.6	
Mv1	Q3Y	0.145	21.6 ± 5.8	-
			20.7 ± 13.3	
			−5.8 ± 48.9	
Mv2	P7G	0.489	40.1 ± 106.0	-
			−4.5 ± 134.0	
			25.8 ± 2.4	
Mv3	A14G	0.888	24.5 ± 1.1	25.5
			26.7 ± 1.4	
			25.3 ± 0.9	
Mv4	R16G	1.136	16.7 ± 2.8	17.2
			17.5 ± 4.2	
			17.5 ± 3.1	
Mv5	L28G	1.443	22.2 ± 1.6	22.6
			22.5 ± 1.0	
			23.1 ± 2.2	
Mv6	A20D	1.476	19.5 ± 1.8	-
			22.3 ± 4.7	
			19.5 ± 9.9	
Mv7	Q13D	1.546	17.6 ± 1.4	-
			−21.6 ± 93.1	
			14.9 ± 4.1	
Mv8	R21D	1.637	15.0 ± 3.2	17.7
			19.8 ± 2.2	
			18.2 ± 1.6	
Mv9	A27D	1.759	15.2 ± 6.4	-
			14.6 ± 3.3	
			9.7 ± 7.5	
Mv10	I10G	2.393	−5.6 ± 44.0	-
			−1.7 ± 34.8	
			16.7 ± 2.4	
Mv11	V5N	2.439	19.1 ± 3.2	20.9
			23.9 ± 1.4	
			19.8 ± 3.4	
Mv12	V17D	2.452	15.6 ± 4.2	-
			−11.3 ± 45.1	
			−4.6 ± 34.5	
Mv13	L24G	2.802	20.0 ± 4.4	-

			12.2 ± 7.5	
			26.5 ± 3.0	

Supplementary Table 1. M3L2(WT) and its mutants. | Predicted stability changes for point mutations ($\Delta\Delta G_{Pred}$) derived from ThermoMPNN inference are shown for M3L2(WT) and its mutants (Mvs). T_m and $T_{m,Ave}$ determined CD measurements are provided for coiled-coil complexes formed between p66α and each variant. T_m values are shown with standard deviation. Source data are provided as a Source Data file.

M3L2-Gly₅₀-p66α; M3L2-Gly₅₀-p66α

SGQLVTPADIRRQARRVKKARERLAKALQADRLAGGGGGGGGGGGGGGGGGGGGGGGGGGGGG
GGGGGGGGGGGGGGGGGGGGGGGGPEERERMIKQLKEELRLEEAKLVLLKKLRQSQIQ

6xHis-TEVcs-M3L2(WT); 6xHis-TEVcs-M3L2

MHHHHHHENLYFQGSGQLVTPADIRRQARRVKKARERLAKALQADRLA

p66α; 6xHis-TEVcs-p66α

MHHHHHHENLYFQGPEERERMIKQLKEELRLEEAKLVLLKKLRQSQIQ

8xHis-TEVcs-M3L2(WT); 8xHis-TEVcs-M3L2

MHHHHHHHHENLYFQGSGQLVTPADIRRQARRVKKARERLAKALQADRLA

Mv1; 8xHis-TEVcs-M3L2(Q3Y)

MHHHHHHHHENLYFQGSGYLVTPADIRRQARRVKKARERLAKALQADRLA

Mv2; 8xHis-TEVcs-M3L2(P7G)

MHHHHHHHHENLYFQGSGQLVTGADIRRQARRVKKARERLAKALQADRLA

Mv3; 8xHis-TEVcs-M3L2(A14G)

MHHHHHHHHENLYFQGSGQLVTPADIRRQGRRVKKARERLAKALQADRLA

Mv4; 8xHis-TEVcs-M3L2(R16G)

MHHHHHHHHENLYFQGSGQLVTPADIRRQARGVKKARERLAKALQADRLA

Mv5; 8xHis-TEVcs-M3L2(L28G)

MHHHHHHHHENLYFQGSGQLVTPADIRRQARRVKKARERLAKAGQADRLA

Mv6; 8xHis-TEVcs-M3L2(A20D)

MHHHHHHHHENLYFQGSGQLVTPADIRRQARRVKKDRERLAKALQADRLA

Mv7; 8xHis-TEVcs-M3L2(Q13D)

MHHHHHHHHENLYFQGSGQLVTPADIRRDARRVKKARERLAKALQADRLA

Mv8; 8xHis-TEVcs-M3L2(R21D)

MHHHHHHHHENLYFQGSGQLVTPADIRRQARRVKKADERLAKALQADRLA

Mv9; 8xHis-TEVcs-M3L2(A27D)

MHHHHHHHHENLYFQGSGQLVTPADIRRQARRVKKARERLAKDLQADRLA

Mv10; 8xHis-TEVcs-M3L2(I10G)

MHHHHHHHHENLYFQGSGQLVTPADGRRQARRVKKARERLAKALQADRLA

Mv11; 8xHis-TEVcs-M3L2(V5N)

MHHHHHHHHENLYFQGSGQLNTPADIRRQARRVKKARERLAKALQADRLA

Mv12; 8xHis-TEVcs-M3L2(V17D)

MHHHHHHHHENLYFQGSGQLVTPADIRRQARRDKKARERLAKALQADRLA

Mv13; 8xHis-TEVcs-M3L2(L24G)

MHHHHHHHHENLYFQGSGQLVTPADIRRQARRVKKARERGAKALQADRLA

PuuE-M(WT); 6xHis-TEVcs-PuuE-M3L2

MHHHHHHENLYFQGVDYPRDLIGYGSNPPHPHWPGKARIALSFVLNYEEGGERNILHGDKESEA
FLSEMVSAQPLQGERNMSMESLYEYGSRAGVWRILKLFKAFDIPLTIFAVAMAAQRHPDVIRAMV
AAGHEICSHGYRWIDYQYMDEAQEREHMLEAIRILTELTGERPLGWYTGRTGPNTRRLVMEEGG
FLYDCDTYDDDLPYWEPNNPTGKPHLVIPYTLDTNDMRFTQVQGFNKGDDFFEYLKDAFDVLYA
EGAEAPKMLSIGLHCRLIGRPARLAALQRFIEYAKSHEQVWFTRRVDIARHWHATHPYTSGQLVT
PADIRRQARRVKKARERLAKALQADRLA

PuuE-p; 6xHis-TEVcs-PuuE-p66α

MHHHHHHENLYFQGVDYPRDLIGYGSNPPHPHWPGKARIALSFVLNYEEGGERNILHGDKESEA
FLSEMVSAQPLQGERNMSMESLYEYGSRAGVWRILKLFKAFDIPLTIFAVAMAAQRHPDVIRAMV
AAGHEICSHGYRWIDYQYMDEAQEREHMLEAIRILTELTGERPLGWYTGRTGPNTRRLVMEEGG
FLYDCDTYDDDLPYWEPNNPTGKPHLVIPYTLDTNDMRFTQVQGFNKGDDFFEYLKDAFDVLYA
EGAEAPKMLSIGLHCRLIGRPARLAALQRFIEYAKSHEQVWFTRRVDIARHWHATHPYTPEERER
MIKQLKEELRLEEAKLVLLKKLRQSQIQ

PuuE-Mv3; 6xHis-TEVcs-PuuE-M3L2(A14G)

MHHHHHHENLYFQGVDYPRDLIGYGSNPPHPHWPGKARIALSFVLNYEEGGERNILHGDKESEA
FLSEMVSAQPLQGERNMSMESLYEYGSRAGVWRILKLFKAFDIPLTIFAVAMAAQRHPDVIRAMV
AAGHEICSHGYRWIDYQYMDEAQEREHMLEAIRILTELTGERPLGWYTGRTGPNTRRLVMEEGG
FLYDCDTYDDDLPYWEPNNPTGKPHLVIPYTLDTNDMRFTQVQGFNKGDDFFEYLKDAFDVLYA
EGAEAPKMLSIGLHCRLIGRPARLAALQRFIEYAKSHEQVWFTRRVDIARHWHATHPYTSGQLVT
PADIRRQGRRVKKARERLAKALQADRLA

PuuE-Mv4; 6xHis-TEVcs-PuuE-M3L2(R16G)

MHHHHHHENLYFQGVDYPRDLIGYGSNPPHPHWPGKARIALSFVLNYEEGGERNILHGDKESEA
FLSEMVSAQPLQGERNMSMESLYEYGSRAGVWRILKLFKAFDIPLTIFAVAMAAQRHPDVIRAMV
AAGHEICSHGYRWIDYQYMDEAQEREHMLEAIRILTELTGERPLGWYTGRTGPNTRRLVMEEGG
FLYDCDTYDDDLPYWEPNNPTGKPHLVIPYTLDTNDMRFTQVQGFNKGDDFFEYLKDAFDVLYA
EGAEAPKMLSIGLHCRLIGRPARLAALQRFIEYAKSHEQVWFTRRVDIARHWHATHPYTSGQLVT
PADIRRQARGVKKARERLAKALQADRLA

Supplementary Table 2. Amino acid sequences of the protein constructs used in this study.