Production of prolyl-hydroxylated human type III collagen in Physcomitrella photobioreactors

Lennard L. Bohlender[1], Juliana Parsons[1], Antonia Mitgau[1], Sebastian N. W. Hoernstein[2], Giovanna Grigolon[3], Bernhard Henes[3], Eva L. Decker[1], Ralf Reski[1,4,5,*]

[1]Plant Biotechnology, Faculty of Biology, University of Freiburg, Schaenzlestr. 1, 79104 Freiburg, Germany

[2]Biochemistry and Functional Proteomics, Faculty of Biology, University of Freiburg, Schaenzlestr. 1, 79104 Freiburg, Germany

[3]Mibelle Group Biochemistry, Mibelle AG, Bolimattstr. 1, 5033 Buchs, Switzerland

[4]CIBSS – Centre for Integrative Biological Signalling Studies, University of Freiburg, Schaenzlestr. 18, 79104 Freiburg, Germany

[5]Cluster of Excellence *liv*MatS at FIT – Freiburg Center for Interactive Materials and Bioinspired Technologies, University of Freiburg, Georges-Köhler-Allee 105, 79110 Freiburg, Germany

Corresponding author: ralf.reski@biologie.uni-freiburg.de

ORCID IDs

Lennard L. Bohlender	0000-0002-4599-7807
Juliana Parsons	0000-0001-6261-2342
Antonia Mitgau	0009-0002-5146-0587
Sebastian N. W. Hoernstein	0000-0002-2095-689X
Giovanna Grigolon	0000-0002-0838-8826
Bernhard Henes	0009-0005-3177-1822
Eva L. Decker	0000-0002-9151-1361
Ralf Reski	0000-0002-5496-6711

Acknowledgements

We thank Christine Glockner and Britta Rothgänger for technical assistance and Anne Katrin Prowse for proof reading.

Abstract

Collagens are important structural proteins of the extracellular matrix that are essential for skin elasticity and integrity and are widely used in dietary supplements and cosmetics. Conventional collagens of animal origin raise concerns regarding ethics, safety, and sustainability. As a vegan alternative, we report on the production of a 30 kDa prolyl-hydroxylated human collagen polypeptide from Physcomitrella moss plants. For secretion-based production and formulation compatibility, a hydrophilic region encompassing 334 amino acids from human type III collagen was selected, which includes four protein domains involved in cell adhesion, collagen binding, integrin recognition and wound healing. Transgenic moss lines were generated via PEG-mediated protoplast transformation. Immunodetection identified collagen polypeptide-producing lines, and mass spectrometric analysis validated the product and confirmed its prolyl-hydroxylation. The presence of this important post-translational modification underscores the high biomimetic quality of the product derived from moss. To enable industrial-scale production, the transformants were quantitatively analysed at the genomic, transcript, and protein levels. The most productive lines were forwarded to process development, where culture conditions including CO_2 supplementation, pH, and light intensity were optimized. Upscaling to 5 L photobioreactors established a robust, light- and biomass-dependent production regime that yielded nearly 1 mg/L of secreted collagen polypeptide after 11 days of cultivation. Taken together, this study presents the first scalable moss-based production of a post-translationally modified human collagen and offers a sustainable and vegan alternative to conventional collagens. This highlights the versatility of Physcomitrella as a production host for high-quality proteins with industrial applicability that also meet consumer requirements.

Key words

Bioactive, COL3A1, Green Biomanufacturing, Moss Bioreactor, prolyl-hydroxylated collagen, vegan collagen

Key message

Moss bioreactors enable the production of high-quality recombinant prolyl-hydroxylated human collagen, offering a sustainable and vegan alternative to conventional collagens derived from animals.

Introduction

Human collagen is the dominant structural protein of the extracellular matrix (ECM) and the main component of connective tissue, where it contributes to its resilience and elasticity. Type III collagen provides tensile strength to hollow organs such as blood vessels, functions in cell adhesion, is involved in the blood-clotting cascade, and is important for wound healing (Ihlberg et al. 1993; Kim et al. 2005; Malfait 2018; Kuivaniemi and Tromp 2019).

Collagen is mainly obtained from animals such as cattle, pigs, rats, and fish, and it is widely used in biomedical materials, as an ingredient in dietary supplements and in cosmetics (Sionkowska et al. 2020). Due to growing market demands, safety concerns, including potential immunogenic reactions and the transmission of zoonoses, as well as consumer reservations about animal sources (Grigolon et al. 2023; Chen et al. 2024; Ariyanta et al. 2025), collagens are increasingly being biotechnologically produced in various non-animal derived expression systems (Rodríguez et al. 2018; Zhao et al. 2023; Chen et al. 2024). While the global collagen market was valued at approximately USD 9.9 billion in 2024, it is projected to reach USD 18.7 billion by 2030 (Grand View Research 2024). In contrast, the market value of recombinant humanized collagen was approximately USD 1.5 billion in 2023 and is expected to reach USD 3.6 billion by 2032 (DataIntelo 2024).

In selecting a suitable production host, it is essential that post-translational protein modifications (PTM), in particular prolyl 4-hydroxylation by prolyl 4-hydroxylases (P4H), are carried out efficiently. The primary structure of collagen is defined by its highly repetitive Gly-Xaa-Yaa motif, with glycine occupying every third position and proline residues frequently occurring at both the Xaa and Yaa positions. Prolines at the Yaa position are frequently hydroxylated (Brodsky and Ramshaw 1997; Engel and Bächinger 2005). This site-specific prolyl-hydroxylation is an important PTM in collagen that is essential for its structural integrity, thermal stability, and biological function (Myllyharju 2008; Taga et al. 2021).

Green systems used for the recombinant production of human collagen include the vascular plants barley, corn and tobacco (Shoseyov et al. 2014; Wang et al. 2017; Zhao et al. 2023). When produced in barley cell culture (Ritala et al. 2008) and barley seeds (Eskelin et al. 2009), corn grains (Zhang et al. 2009a; Zhang et al. 2009b) or tobacco (Ruggiero et al. 2000), the products showed little or no prolyl-hydroxylation

and no additional detectable PTMs. Therefore, co-expression with different non-plant P4Hs was achieved in tobacco plants (Merle et al. 2002; Stein et al. 2009) and corn grains (Xu et al. 2011) with higher PTM yields.

The moss Physcomitrella (new botanical name: *Physcomitrium patens*) is a model plant for basic biology and biotechnology (Decker and Reski 2020; Lueth and Reski 2023) with a proven track record as a production host for biopharmaceuticals (Reski et al. 2015; Reski et al. 2018), including difficult-to-express proteins such as human factor H and its derivatives (Michelfelder et al. 2017; Top et al. 2019; Ruiz-Molina et al. 2022a), human erythropoietin (Weise et al. 2007; Parsons et al. 2012), spider silk (Ramezaniaghdam et al. 2025), and virus-like nanoparticles (Niederau et al. 2025). Unlike vascular plants, Physcomitrella can be grown in bioreactors (Hohe et al. 2002; Hiss et al. 2014) that can be operated in accordance with the principles of good manufacturing practice (GMP; Decker and Reski 2007). Moreover, its ability to secrete recombinant products directly into the simple mineral culture medium allows simplified downstream processing (Baur et al. 2005; Schaaf et al. 2005; Gitzinger et al. 2009), eliminating the need for tissue extraction and laborious purification steps. Furthermore, Physcomitrella is ideal for precise genome engineering due to efficient homologous recombination in mitotic cells (Strepp et al. 1998; Wiedemann et al. 2018), and its P4H enzymes are well characterised (Parsons et al. 2013; Rempfer et al. 2024). Non-transgenic mosses are rich in secondary metabolites (Erxleben et al. 2012; Horn et al. 2021; Munoz et al. 2024) and, when grown in photobioreactors, serve as a source of bioactive substances for the cosmetics industry, with the first products already on the market (Wandrey et al. 2018).

Here, we identified a fragment of 334 amino acids (aa) from the human collagen α1(III) chain (P02461, COL3A1) that comprises four important protein domains and is hydrophilic. We optimized the construct for expression in Physcomitrella without altering the aa sequence of human collagen. The transgenic moss lines were examined quantitatively at the genomic, transcript and protein levels. The product was secreted into a simple mineral medium, harvested and characterized. Analysis by mass spectrometry provided evidence for an intact product with prolyl-hydroxylation. A bioreactor process was established and optimized, resulting in up to 1 mg/L of secreted prolyl-hydroxylated human collagen polypeptide after 11 days of cultivation.

Results

Polypeptide selection and codon optimization

In this study, we aimed to establish the recombinant production of a vegan collagen alternative to animal-derived collagens for use in cosmetic formulations, employing the moss Physcomitrella as a production platform. Given its crucial role in wound healing (Krafts 2010; Stewart et al. 2025), skin integrity, and tissue regeneration (Volk et al. 2011; D'hondt et al. 2018), human collagen type III was selected as the basis for the recombinant polypeptide. With regard to compatibility with a secretion-based production system and broad applicability in cosmetic formulations, particular attention was paid to selecting a predominantly polar protein sequence.

Therefore, the full-length sequence of human pre-procollagen α1(III) (1466 aa, including the signal peptide; UniProt ID: P02461), from which the collagen triple helix-forming collagen α1(III) chain is formed after cleavage of the N- and C-terminal propeptides, was examined *in silico* for its hydropathicity. This analysis identified an extended hydrophilic region of 334 aa within the collagen α1(III) chain extending from glycine 456 to glycine 789 (**Figure 1**). In addition, this polypeptide sequence contains four protein domains that are positively associated with skin integrity: I) The domain Gly489–Gly510, which is involved in collagen binding (Hua et al. 2019), II+III) Two integrin-binding motifs (GAOGER, GMOGER; O: hydroxyproline; Siljander et al. 2004; Kim et al. 2005), and IV) A substantial portion of the Gly426–Ser560 region, which can increase type I collagen production and promote wound healing *in vitro* (Kim et al. 2024) (**Figure 1**). The resulting polypeptide has a calculated molecular weight of 30 kDa and an isoelectric point (pI) of 6.65 (ExPASy Compute pI/Mw; https://web.expasy.org/compute_pi/).

Fig. 1 Full-length amino acid sequence of the human pre-procollagen α1(III) and corresponding hydropathicity plots

A Full-length amino acid sequence of the human pre-procollagen α1(III) (P02461), consisting of the signal peptide (yellow; aa 1–23), the N-terminal propeptide (light grey; aa 24–153), the collagen α1(III) chain (italics; aa 154–1221), and the C-terminal propeptide (dark grey; aa 1222–1466). The sequence region selected for recombinant production is highlighted in green (aa 456–789), integrin recognition motifs are marked in orange, the segment Gly426-Ser560 involved in collagen-related signalling and interactions is underlined, and the collagen binding Gly489-Gly510 sequence stretch within this region is emphasized in blue. **B** *In silico* hydropathicity plot of the human pre-procollagen α1(III) aa sequence. **C** *In silico* hydropathicity plot of the selected 334-aa region. Hydropathicity plots were generated using the ExPASy ProtScale tool (https://web.expasy.org/protscale/) with the Kyte and Doolittle (1982) scale. Positive values indicate hydrophobic amino acids, and negative values indicate hydrophilic amino acids. Abbreviations: SP: signal peptide; N-PP: N-terminal propeptide; C-PP: C-terminal propeptide; aa: amino acid.

The coding sequence (CDS) of the selected Col3A1 polypeptide underwent three rounds of *in-silico* optimization. First, the codons were adapted towards the Physcomitrella codon usage. Subsequently, nucleotides within 11 heterosplicing recognition motifs (AGGT, Top et al. 2021) were altered. In a final step, eight codons that are underrepresented in Physcomitrella (Nakamura et al. 2000; Hiss et al. 2017), were replaced with the corresponding overrepresented alternatives (**Supplementary**

Table S1) using the online tool physCO (Top et al. 2021). This resulted in 192 base

changes at the nucleic acid sequence level (**Supplementary Figure S1**) but did not

alter the resulting aa sequence of the human collagen polypeptide. After *in-silico* fusion

of the CDS to the PpAP1 (Pp6c5_10120V6.1) signal-peptide (Schaaf et al. 2004) to

enable product secretion and the addition an 8x His-tag, the synthesized CDS

(GeneArt, Thermo Fisher Scientific) was cloned into an Actin5 promoter-driven (Weise

et al. 2006; Niederau et al. 2024) expression vector, which additionally contained an

hpt cassette (Decker et al. 2015) for selection purposes (**Supplementary Figure S2**).

Immunodetection and mass spectrometric sequence analysis

Following PEG-mediated transformation of Physcomitrella wild type (WT) protoplasts,

their regeneration and selection, 50 hygromycin-resistant moss lines were cultivated

in agitated flasks and examined for collagen production using Western blot analysis.

For this purpose, total soluble proteins were extracted from protonema, the young

filamentous tissue of the moss, which was cultivated under standard conditions. The

collagen polypeptide was enriched using ion affinity chromatography (His SpinTrap)

and analysed by Western blot using anti-His antibodies. Collagen polypeptide-

producing lines showed a strong signal at approximately 45 kDa. In addition, an

unspecific band at around 37 kDa was consistently detected in all analysed lines,

including WT. The eight lines with the strongest signals (C6.1, C5, C11, C13, C15,

C34, C44, and C46) are shown alongside a WT control in **Figure 2A**. To verify that the

45 kDa signal originated from the recombinantly produced collagen polypeptide, the

purified extract from line C6.1, which together with C5 showed the strongest anti-His

antibody signals, was further analysed using an anti-collagen antibody-based

immunodetection. The resulting signals were consistent with those obtained using the

anti-His antibody (**Figure 2B**), confirming that the bands detected at approximately 45

kDa correspond to the recombinant collagen polypeptide. To analyse the quality of the

recombinant product, the protein band corresponding to the 45 kDa signal was excised

from an SDS-PAGE gel prepared and run in parallel (**Figure 2B**) and analysed by

mass spectrometry. This analysis confirmed the successful production of the intact full-

length collagen polypeptide and confirmed the proper cleavage of the signal peptide

(**Figure 2C**). Of the eight lines compared, five lines (C5, C6.1, C15, C34, and C44)

were selected for further analysis.

Fig. 2 Analysis of the Physcomitrella-produced recombinant collagen polypeptide
A Western blot using anti-His antibodies of 10 µg His SpinTrap-enriched proteins from protonema tissue of transgenic Physcomitrella lines producing recombinant collagen polypeptide, compared with a WT control. **B** Co-localization of signals confirmed by anti-His and anti-collagen immunodetections on His SpinTrap-enriched proteins from line C6.1. **C** Mass spectrometric analysis of the intracellularly accumulated recombinant collagen polypeptide revealed 81% sequence coverage (identified aa are shown in green, non-identified in grey) of the mature polypeptide and confirmed cleavage of the signal peptide (highlighted in yellow). Uncropped immunodetection and SDS-PAGE images are provided in **Supplementary Figure S3**.

Quantitative analysis at genomic, transcript and protein level

To compare the production yields of the five selected lines C5, C6.1, C15, C34 and C44, the produced collagen polypeptide was quantified using ELISA. Protonema suspension cultures of the selected lines, along with a WT control, were adjusted to a density of 60 mg dry weight (DW) per litre, cultivated under standard conditions and harvested after seven days of cultivation. Extracted total proteins were analysed using an anti-His antibody-based ELISA. Signals were blank-corrected, WT-subtracted, and calibrated against a His-tagged elastin peptide standard curve. Lines C5 and C6.1

produced the highest amounts of collagen polypeptide, with approximately 30 µg and 32 µg per gram of protonema fresh weight (FW), respectively. Line C15 yielded an intermediate amount of around 19 µg/g FW, while the lowest levels were observed in lines C34 and C44, with approximately 8 µg/g FW and 9 µg/g FW (**Figure 3A**).

For molecular characterization at the genomic level, the number of construct copies that had been integrated into the moss genome was determined by quantitative PCR (qPCR). This analysis was performed on the three best-producing lines using primer pairs targeting the Actin5 promoter, the collagen CDS, and the hpt cassette, respectively. In addition, all five selected lines were compared using only the Actin5 promoter- and collagen-specific primers. Alongside the collagen-producing lines, the WT and line Bag4.2, a known single-integration line for the hpt CDS (Bohlender et al. 2022), were included as references for relative quantification of Actin5- and hpt-derived signals. To normalize for genomic DNA input, integration signal intensities were obtained for each line using two primer pairs targeting the CLF gene, a confirmed single-copy gene in Physcomitrella (Pereman et al. 2016). The qPCR analysis revealed that line C15 carried the highest construct copy number, with approximately 200 integrations. Lines C5 and C6.1 followed, each harbouring around 140 integrations (**Figure 3B**). In contrast, lines C34 and C44 contained lower copy numbers, with about 20 and 30 integrations, respectively (**Supplementary Figure S4**).

To compare the two best-producing lines C5 and C6.1 at the transcript level, collagen CDS expression levels were quantified by qRT-PCR. Total RNA was extracted from protonema material of suspension cultures initiated with 60 mg DW/L and harvested seven days after inoculation, then reversely transcribed into cDNA. Expression levels were normalized to the two strongly expressed housekeeping genes LWD (Pp6c22_10850V6.1; Yin et al. 2021) and L21 (Pp6c13_1120V6.1; Beike et al. 2015). This analysis showed that line C5 exhibited an approximately 250-fold, and line C6.1 a 266-fold higher expression of the collagen CDS relative to the two housekeeping genes (**Figure 3C**). Based on these quantitative analyses, the two best performing collagen-producing lines C5 and C6.1 were chosen for the establishment of a secretion-based production process.

Fig. 3 Quantitative analysis of intracellular yields, construct copy numbers, and expression levels in collagen-producing moss lines
A Intracellular accumulation of recombinant collagen polypeptide in producing lines, quantified by ELISA. Bars represent blank-corrected and WT-signal subtracted values (mean ± SD, n = 3). **B** qPCR analysis of construct copy numbers in the three best-producing lines using primer pairs targeting the Actin5 promoter (Act5), the collagen CDS (Collagen), and the hygromycin resistance cassette (hpt). Normalization was performed against signals from two primer pairs targeting the endogenous single-copy CLF gene. WT and the confirmed hpt single-integration line Bag4.2 served as references for normalization of Act5 and hpt-derived signals, respectively. Bars represent normalized mean values ± SD (n = 3). **C** qRT-PCR analysis of collagen expression levels in the two best-producing lines compared to WT. Expression was measured with a primer pair targeting collagen cDNA and normalized to the housekeeping genes LWD and L21. Relative expression is shown as $2^{-\Delta CT}$, where ΔCT = CT(transgene) - CT(housekeeping). Bars represent mean ± SD (n = 3).

Optimization of production parameters

To establish a secretion-based production process suitable for the downstream industrial formulation of the recombinant collagen polypeptide, cultivation parameters influencing the secretion and accumulation of recombinant human collagen in the culture medium were investigated and optimized. For this purpose, 500 mL agitated Erlenmeyer flasks were inoculated with 200 mL of protonema suspension culture from either line C5 or the WT, adjusted to a density of 300 mg DW/L. Cultures were grown for 16 days under standard conditions (Decker et al. 2015) or with supplementation of 2% CO_2 in the incubator atmosphere (20,000 ppm CO_2). Supernatant samples were collected on days 3, 6, 9, 14, and 16 and analysed by ELISA. In both conditions, the highest collagen polypeptide accumulation occurred on day 6, followed by a decline in supernatant concentrations toward the end of cultivation. Under 2% CO_2 supplementation, approximately 50 µg/L collagen polypeptide was achieved, more

than twice the amount compared to the ~22 µg/L achieved under standard atmospheric

conditions (**Figure 4A**).

Next, the effect of medium pH on collagen polypeptide accumulation was examined

under CO_2 supplementation. The medium was adjusted to pH 4.5, 5.5, or 6.5, and

product levels were monitored over 8 days. The highest accumulation was observed

in medium adjusted to pH 4.5, which reached about 80 µg/L on day 7. At pH 5.5,

accumulation peaked at about 55 µg/L on the same day, while at pH 6.5 about 37 µg/L

at its maximum on day 6 were achieved (**Figure 4B**).

Collectively, these optimization experiments identified an increased CO_2 availability of

2% and medium pH adjusted to 4.5 as the most favourable conditions for collagen

polypeptide accumulation in the culture supernatant. These optimized conditions were

subsequently applied in 5 L photobioreactor runs for scale-up and industrial

formulation.

Fig. 4 Effects of cultivation conditions on recombinant collagen polypeptide
accumulation in the culture supernatant
Secreted collagen polypeptide levels from cultures inoculated with protonema tissue (300 mg
DW/L) of line C5 and WT controls were quantified by ELISA. **A** Cultivation for 16 days under
standard conditions (Air) or with 2% CO_2 supplementation (Air + 2% CO_2). **B** Cultivation for 8
days at pH 4.5, 5.5, or 6.5 with 2% CO_2 supplementation. Data points represent blank-
corrected, WT-subtracted mean values ± SD (n = 3). DPI: day(s) post inoculation.

Upscaling to 5 L photobioreactors

To provide the recombinant collagen polypeptide in amounts suitable for industrial

formulation, the secretion-based production process was scaled up to 5 L

photobioreactors. Therefore, based on the information gained from our previous results, a 5 L photobioreactor was set up with a pH controlled at 4.8 and aerated with air enriched with 2% CO_2. The bioreactor was inoculated with line C5 at an initial biomass density of 400 mg DW/L and maintained for 22 days. Light intensity was set to 90 µmol m^{-2} s^{-1} until day 9, then set to 190 µmol m^{-2} s^{-1} until day 14, followed by 380 µmol m^{-2} s^{-1} until day 17, and finally set to 760 µmol m^{-2} s^{-1} until the end of the bioreactor run. Biomass growth was monitored, and supernatant as well as biomass samples were collected for further analysis.

Over the course of the bioreactor run, secreted collagen polypeptide concentrations increased first slowly from 3 µg/L on day 3 to 250 µg/L on day 17 and then strongly reaching a maximum of 986 µg/L on day 21, before slightly declining on day 22 (**Figure 5A**). Intracellular collagen levels remained low throughout, peaking at 7 µg/g fresh weight on day 7 (**Figure 5A**). The biomass initially increased almost linearly from 400 mg DW/L to 1800 mg DW/L by day 7, then gradually reached approximately 2700 mg DW/L by day 17, followed by a stronger increase to 4200 mg DW/L until day 22 (**Figure 5A**). This initial process yielded nearly 1 mg of collagen polypeptide per litre of culture supernatant within a production period of 22 days.

To develop a more time- and cost-efficient production process, conclusions were drawn from several bioreactor runs conducted under different parameter regimes. Evaluation of these data led to the establishment of a biomass-dependent, light-intensity-regulated production process. A light intensity of 100 µmol m^{-2} s^{-1} was applied up to a biomass of 2 g DW/L, followed by a light intensity of 350 µmol m^{-2} s^{-1} until a biomass density of 2.8 g DW/L, which was then increased to 680 µmol m^{-2} s^{-1} until the harvest of the supernatant, which was performed at a biomass density of about 4 g DW/L. It appeared that biomass accumulation higher than 4 g DW/L resulted in a decrease of the amount of collagen polypeptide in the culture supernatant. With the optimized production conditions, product concentrations exceeding 900 µg/L were achieved after approximately 11 days of cultivation (**Figure 5A**). This effectively halved the original production time while maintaining comparably high product yields.

To render the collagen polypeptide-containing supernatant directly suitable for downstream industrial formulation, a clarification protocol was established. First, the bioreactor material was harvested under sterile conditions, and the biomass was removed from the culture supernatant through two sequential filtration steps using

100 μm and 11 μm mesh polypropylene sieves. To ensure a product free of residual
cells and debris, the suitability of the following filter materials was assessed for a
subsequent filtration step: cellulose acetate (0.45 μm), glass microfiber (1.6 μm), nylon
(0.45 μm), polyethersulfone (PES; 0.22, 1, and 5 μm), polyamide (0.45 μm),
polyvinylidene difluoride (PVDF; 0.45 and 5 μm), and water-wettable
polytetrafluoroethylene (wwPTFE; 0.45 μm). Collagen polypeptide concentrations in
these filtrates and in the 11 μm mesh-filtered control were quantified by ELISA, and
recoveries were calculated as percentages of the initial product concentration present
prior to the additional filtration step. When cellulose acetate, glass microfiber, nylon,
polyamide and wwPTFE filters were used, less than 25% of the initial product was
recovered. In contrast, filtration with PVDF and PES filters preserved nearly 100% of
the initial product. This was particularly evident with filters of 5 μm pore size, where
almost no collagen loss was detected. At smaller pore sizes, 87% of the initial collagen
concentration was recovered with 0.45 μm PVDF filters, whereas 1 μm and 0.22 μm
PES filters resulted in a recovery of 50-60% (**Figure 5B**).

Taking all results into consideration, PVDF filter material with a pore size of 0.45 μm
provided the best relationship between collagen recovery and filtration effect, and thus
represents a promising option for integration into the production process.

Fig. 5 Bioreactor culture parameters and clarification of recombinant collagen
polypeptide containing supernatant
A Collagen polypeptide accumulation profiles (solid lines), moss biomass accumulation
(dashed lines), and applied light intensity settings (dotted lines) during 5 L photobioreactor runs
of line C5 under initial and optimized conditions. Collagen concentrations were quantified by
ELISA (mean ± SD, technical triplicates) and the biomass was analysed via dry weight
measurements (mean ± SD, technical duplicates). **B** Recovery efficiency of the collagen
polypeptide (in %) after an additional filtration step using different filter materials, relative to the
11 μm mesh-filtered supernatant. Abbreviations: opti.: optimized; SN: supernatant, FW: fresh
weight, DW: dry weight, DPI: day(s) post inoculation, Glass microf.: Glass microfiber, Cell.
acetate: Cellulose acetate.

Evaluation of product quality

Following the establishment of the secretion-based production process, the quality of the product in the culture supernatant was evaluated using Western blot-based immunodetection and mass spectrometry.

The immunodetection of precipitated supernatants from C6.1 and WT bioreactor runs revealed a band at approximately 37 kDa in the supernatant of line C6.1, along with a very intense high molecular weight signal ranging from 45 to over 130 kDa, while no signals were detected in the sample of the WT supernatant (**Figure 6A**). To check if the detected signals originated from the collagen polypeptide, the corresponding regions were excised from an SDS-PAGE gel run in parallel and analysed by mass spectrometry. These analyses confirmed the presence of the collagen polypeptide in all signal-associated gel regions, verified the correct cleavage of the AP1 signal peptide, and yielded a combined sequence coverage of 58% of the mature collagen polypeptide (**Figure 6B**). In addition, these measurements confirmed the presence of hydroxyproline residues (**Figures 6B, C**) as a consequence of enzymatic prolyl-hydroxylation (Rempfer et al. 2024). In the secreted collagen fraction, a total of 41 proline residues were identified. Of these, 28 were located at the Yaa position and 13 at the Xaa position within the characteristic collagen Gly-Xaa-Yaa amino acid motif. Among all identified proline sites, 23 (~54%) were hydroxylated, with site-specific occupancy ranging on average from 10% to 80% (**Figure 6C**). Seventeen (~74%) of these hydroxylated prolines were found at Yaa positions, including the hydroxylated GAOGER integrin-binding motif (**Figure 6B**) and the remaining six occurred at Xaa positions.

Finally, Western blot analysis of the non-precipitated supernatant revealed that under the applied conditions the majority of the product accumulated in a molecular weight range between 70 and 100 kDa (**Supplementary Figure S5**).

Fig. 6 Evaluation of the secreted recombinant collagen polypeptide in bioreactor supernatants

409
410

A Anti-His immunodetection of acetone-precipitated bioreactor supernatants (1.5 mL) from a bioreactor run of line C6.1 compared with an equally treated WT control. Mass spectrometry confirmed the presence of the recombinant collagen polypeptide in all detected signal areas (**Supplementary Figure S5**). **B** Combined sequence coverage of the secreted collagen polypeptide obtained from seven mass spectrometric measurements of the bioreactor supernatant. Identified sequence regions are highlighted in green, hydroxylated proline residues in red, and non-identified regions in grey. The length of the secretion-mediating AP1 signal peptide is indicated above and the two sequence regions of the two integrin binding motifs GAOGER and GMOGER (O: hydroxyproline) are highlighted in blue. **C** Site occupancy of hydroxylation of prolines at the 23 modified positions identified over seven measurements of secreted collagen polypeptide containing bioreactor supernatant samples. Sites within the G-X-Y motif are shown in order of their occurrence along the amino acid sequence. Only prolines with a PTMProphet site localization probability > 0.75 were used. As quantitative values, label-free quantitation intensities were used, log2 transformed and normalized to the median intensity of each measurement. Subsequently, all values were centred to the median across all measurements. Data points represent percentages related to the single experiments whereas bars represent percentages across all measurements. A list of all measured hydroxyproline sites and their intensities is available in **Supplementary Table S3**.

At the current stage, the established 5 L photobioreactor process, combined with sequential filtration through 100 μm and 11 μm mesh polypropylene sieves, yields a final product containing nearly 1 mg/L recombinant collagen polypeptide. Following

sterile harvesting, the product will be subsequently subjected to further filtration, *in-vitro* activity testing, and formulation.

Discussion

Collagens have gained increasing popularity as cosmetic ingredients in recent years. However, the vast majority of available products still rely on animal-derived sources (Sionkowska et al. 2020). Animal collagens pose potential risks, including contamination with human pathogens and may trigger immune reactions (Mullins et al. 1996; Mitura et al. 2020; Ariyanta et al. 2025). Recombinant collagen production offers clear advantages, including high purity, low immunogenicity, and alignment with the growing consumer demand for vegan, sustainable, and ethically sourced ingredients (Chen et al. 2024). To address these demands, this study describes the production of a prolyl-hydroxylated recombinant human type III collagen polypeptide in transgenic Physcomitrella moss plants, alongside the development of a secretion-based production process in 5 L photobioreactors.

Among the 28 known collagen types (Gordon and Hahn 2010; Ricard-Blum 2011), human type III collagen was selected for recombinant production due to its critical roles in wound healing (Krafts 2010; Stewart et al. 2025), tissue formation, fibrillogenesis (Liu et al. 1997; Kuivaniemi and Tromp 2019), and the maintenance of skin integrity and regeneration (Volk et al. 2011; D'hondt et al. 2018).

Within the human collagen type III sequence, a 334 aa long segment (Gly456 - Gly789) was computationally identified as a promising candidate for recombinant production. This region, representing 31% of the triple-helix-forming human collagen α1(III) chain, shows low hydrophobicity, favourable aqueous solubility, and contains four domains implicated in the modulation of the extracellular matrix (ECM). These features make it particularly well-suited for secretion and formulation purposes, defining it as a compelling candidate for recombinant production as a bioactive cosmetic ingredient.

Codon-optimized collagen-encoding expression constructs were introduced in Physcomitrella protoplasts by PEG-mediated transformation. Immunodetection of purified total protein extracts of producing lines revealed specific bands at approximately 45 kDa, exceeding the predicted molecular weight of the collagen polypeptide of 30 kDa. This shift is consistent with the extended conformation of

collagens in SDS-PAGE, a known phenomenon for both recombinant collagen products and commercial collagen standard proteins (Aly et al. 2022).

To enable the production of the recombinant collagen polypeptide at an industrially relevant scale, successful Physcomitrella lines were identified by quantifying construct copy numbers *via* qPCR and intracellular collagen accumulation *via* ELISA. In four of the five tested lines, accumulation levels positively correlated with construct copy numbers, consistent with previous observations in transgenic Physcomitrella lines (Ruiz-Molina et al. 2022b; Saliba et al. 2025). The highest intracellular collagen polypeptide levels, with 30 µg/g FW and 32 µg/g FW, respectively, were obtained from lines C5 and C6.1, both carrying approximately 140 integrated construct copies. In contrast, line C34, with about 20 integrations, produced 8 µg/g FW, representing the lowest yield among the tested lines. Interestingly, line C15, despite harbouring ~200 copies, accumulated only 19 µg/g FW, possibly due to construct insertions disrupting endogenous genes. Because lines C5 and C6.1 showed nearly identical copy numbers, yields, and expression levels, both were considered suitable for establishing a scalable production pipeline.

Secretion of the collagen polypeptide into the culture medium, enabled by a signal sequence (Schaaf et al. 2005) and by its deliberate hydrophilicity, was confirmed and optimized in small-scale flask experiments. The highest extracellular collagen accumulation was achieved under 2% CO_2 supplementation. A medium pH of 4.5 outperformed the accumulation yields achieved at pH levels of 5.5 and 6.5, respectively. This is consistent with the calculated isoelectric point of the collagen polypeptide (pI = 6.65). Near the pI, peptides exhibit minimal net charge and tend to aggregate (Vate et al. 2023), while at pH < pI they carry a net positive charge, enhancing their water solubility (Wu et al. 2024). Thus, the increased yields at acidic pH reflect a greater solubility and stability under these conditions.

The optimized parameters were successfully scaled up to 5 L photobioreactors, and a robust light- and biomass-oriented production process was developed. Over 11 days of cultivation, this process yielded nearly 1 mg collagen polypeptide per litre of culture supernatant, providing a suitable product for further industrial formulation.

While Western blot and mass spectrometry analyses of the intracellularly accumulated collagen polypeptide already confirmed the synthesis of the full-length product with a nearly complete sequence coverage accumulating in a single band at a molecular

weight of about 45 kDa, the quality of the secreted product from photobioreactors was also examined. Immunodetection of precipitated bioreactor supernatants revealed a band at ~37 kDa corresponding to the collagen polypeptide monomer alongside intense higher molecular weight signals ranging from 45 to over 130 kDa. Mass spectrometric analyses confirmed the presence of the collagen polypeptide in all signal-related areas and confirmed the correct cleavage of the AP1 secretion signal peptide (Schaaf et al. 2004). The slight size difference between the monomeric intra- and extracellular product likely reflects differences in the sample matrices, as buffer components and co-purified proteins can influence peptide migration in the SDS-PAGE (See et al. 1985; Rath et al. 2009).

The signals observed with higher molecular weight present in the secreted fraction may be due to the cross-linking of collagen polypeptides, a known property of collagens that contributes to tissue stability (Tanzer 1973). While this process is mainly catalysed by lysyl oxidase, non-enzymatic spontaneous crosslinking has also been reported (Gaar et al. 2020). Such spontaneous *in vitro* dimerization and multimerization may explain some of the higher molecular weight signals detected by immunoblotting. In addition, collagens are capable of forming both covalent and non-covalent crosslinks with polyphenols. Non-covalent interactions are promoted at acidic pH values (4-5), where hydrogen bonding and electrostatic interactions between protonated collagen amino groups and polyphenol hydroxyl groups are favoured (Wu et al. 2019). Such polyphenol crosslinks can enhance collagen biostability and protect against proteolytic degradation (Madhan et al. 2005; Shavandi et al. 2018; Wu et al. 2019; Hass et al. 2021). Since the presence of polyphenols in Physcomitrella cultures is well documented (Richter et al. 2012; Renault et al. 2017; Kriegshauser et al. 2021), such interactions could be responsible for three observed phenomena: I) the increased product accumulation at pH 4.5 compared to higher pH values (5.5 and 6.5), II) the occurrence of additional high molecular weight signals in precipitated supernatant samples, and III) the lower sequence coverage achieved for the secreted collagen polypeptide compared to the intracellular collagen polypeptide. In the latter case, cross-linking could mask peptides, making it difficult to identify them using mass spectrometry.

Additionally, immunodetection of the non-precipitated bioreactor culture supernatant showed that under our conditions, the majority of the product accumulates between 70

and 100 kDa. The absence of additional signals detected in the precipitated supernatant samples, each corresponding to 1.5 mL of culture supernatant, is likely due to the lower protein amount in the analysed 40 µL of untreated supernatant, which fell below the detection limit.

In biomedical applications, collagen-polyphenol cross-linked hydrogels can improve cell viability, mechanical properties, hydrophilicity, and enzyme resistance while supporting wound healing (Shavandi et al. 2018; Manjari et al. 2020; Han et al. 2024). These results suggest that potential collagen-polyphenol interactions in recombinant collagen polypeptide from moss bioreactors could offer additional benefits for cosmetic applications. Further studies are needed to confirm whether such cross-links are formed under our production conditions.

Mass spectrometric analysis of the secreted recombinant collagen polypeptide additionally confirmed its prolyl-hydroxylation, a hallmark of collagen biomimicry. The performance of this PTM on recombinant collagens by Physcomitrella is unique compared to other established non-mammalian biotechnological production hosts such as *E. coli* (Kersteen et al. 2004; Pinkas et al. 2011; Shi et al. 2017), yeast (Myllyharju et al. 2000; Myllyharju 2009; Chan et al. 2012), insect cells (Lamberg et al. 1996; Pihlajamaa et al. 1999), and vascular plant systems (Ruggiero et al. 2000; Perret et al. 2001; Ritala et al. 2008; Eskelin et al. 2009; Zhang et al. 2009b). In contrast to these production hosts, which either do not perform prolyl-hydroxylation naturally or achieve only low yields, Physcomitrella, with its six endogenous prolyl-4-hydroxylase (P4H) enzymes (Parsons et al. 2013; Rempfer et al. 2024), was able to facilitate prolyl-hydroxylation of the recombinantly produced collagen polypeptide without requiring additional metabolic engineering.

In the secreted collagen polypeptide fraction, a total of 41 proline residues were detected within the 58% sequence coverage obtained from seven mass spectrometric measurements. Of these identified proline sites, 23 (~56%) were found to be hydroxylated across the seven datasets, with site-specific hydroxylation prevalences ranging from 10% to 80%. The detected ratio of hydroxylated to non-hydroxylated proline residues in the recombinant polypeptide is consistent with levels found in native human collagens (Guo et al. 2025). Of these 23 hydroxylated prolines, 17 were located at the Yaa position of the Gly-Xaa-Yaa motif, which is typical for native human collagens. The prolyl-hydroxylation at this position is essential for collagen's structural

integrity, thermal stability, and biological function and also displays the most frequent site of prolyl-hydroxylation in human type III collagen (Shoulders and Raines 2009; Xu et al. 2019; Taga et al. 2021). Among these sites, the integrin-binding motif GAOGER was detected in its hydroxylated form with a prevalence of ~80%, whereas the second motif, GMOGER, showed no evidence of hydroxyproline modification in the analysed samples. The remaining six hydroxyprolines were located at the Xaa position of the Gly-Xaa-Yaa motif, a position less frequently hydroxylated in native human collagens (Van Huizen et al. 2019). When hydroxylation at this position occurs, its prevalence typically ranges between 10% and 80%, depending on the specific site, collagen type, and tissue of origin (Kirchner et al. 2021).

Hydroxyprolines in collagens contribute to receptor binding (Chin et al. 2013; Rappu et al. 2019) and, particularly in short peptides derived from collagen, can activate signalling cascades that promote collagen synthesis (Taga et al. 2018), cell proliferation (Ide et al. 2021), hyaluronic acid production (Ohara et al. 2010) and tissue regeneration (Sato et al. 2019). Thus, their presence confirms the biomimetic nature of the collagen polypeptide derived from Physcomitrella and adds potential benefits in terms of bioactivity that are relevant to cosmetic applications.

In photobioreactor cultures, titres of approximately 1 mg/L of secreted collagen polypeptide were achieved, corresponding to about 40-50 g FW (≈ 4-5 g DW) of Physcomitrella protonema. These yields must therefore be interpreted in the context of secretion into the culture medium which differs fundamentally from intracellular accumulation in plant tissues (Doran 2006). First of all, the Physcomitrella culture supernatant contains only minimal amounts of other host proteins (Hoernstein et al. 2018). Furthermore, product secretion in Physcomitrella provides practical advantages over intracellular strategies, as it facilitates scalability and circumvents the laborious extraction and purification steps otherwise required to recover intracellularly stored proteins (Wilken and Nikolov 2012). Beyond these benefits, secretion also ensures passage through the ER and Golgi apparatus, the intracellular sites of key PTMs, such as prolyl-hydroxylation (Parsons et al. 2013; Rempfer et al. 2024).

Direct comparisons of yields across production systems are notoriously difficult. However, based on biomass-specific productivity, our optimized process achieved approximately 32 mg/kg biomass in agitated flask cultures. Compared to other plant-based production systems for recombinant collagens, Physcomitrella clearly

outperforms barley cell cultures, where 2-9 µg/kg of product were obtained (Ritala et al. 2008), and even surpasses production in tobacco leaves (0.5-1 mg/kg; Merle et al. 2002) and maize seeds (3-4 mg/kg; Zhang et al. 2009b; Xu et al. 2011). Other plant-based systems, such as maize (Zhang et al. 2009a), barley (Eskelin et al. 2009), and tobacco (Ruggiero et al. 2000), reported intracellular accumulation levels between 13 and 45 mg/kg tissue, which is in the range of our system, while higher yields, up to 200 mg/kg in tobacco leaf tissue, were described by Stein et al. (2009). However, production in these systems requires down-stream processing of the product with potential product losses during purification, besides the cost aspects.

Prior to further formulation, a three-stage filtration process was developed to effectively separate the collagen polypeptide-containing culture supernatant effectively from plant material and debris. A first filtration through 100 µm sieves allowed the recovery and recycling of Physcomitrella biomass for further processes. A second filtration through 11 µm sieves prevented clogging of subsequently used filters of smaller pore sizes. Among several materials tested for this final clarification, PVDF and PES filters with 5 µm pores achieved nearly 100% recovery, compared to the control filtered through 100 µm and 11 µm mesh sieves. PVDF filters with a pore size of 0.45 µm still recovered 87% of the initial product, whereas PES filters with smaller pore sizes resulted in poor recoveries of 50-60%. In contrast, the other tested filter materials, wwPTFE (0.45 µm), glass microfiber (1.6 µm), cellulose acetate (0.45 µm), nylon (0.45 µm), and polyamide (0.45 µm), resulted in recovery rates below 25%. These results are consistent with the low protein binding properties of PVDF and PES membranes compared to the other materials (Dunleavy 2024). Based on these results, PVDF filters with a pore size of 0.45 µm proved to be the most promising option for integration into the production process, as they achieved the highest product recovery while maintaining a strict filtration limit.

The collagen-rich Physcomitrella culture supernatant is currently being evaluated for efficacy, focusing on the modulation of collagen-related gene expression, ECM remodelling, skin regeneration, and hyaluronic acid release in cell-based assays. Following formulation, market introduction is anticipated in 2026, enabling the use of Physcomitrella-derived recombinant human type III collagen polypeptide as a novel and high-quality bioactive ingredient in diverse cosmetic formulations.

Conclusion

This study demonstrates the potential of Physcomitrella as a sustainable production platform for the growing demand for vegan collagen. The recombinant human type III collagen polypeptide produced in Physcomitrella fulfils an important quality criterion through prolyl-hydroxylation, while the established secretion-based, GMP-compliant process in photobioreactors enables the generation of collagen polypeptide-rich supernatants. These supernatants are currently being evaluated for their *in-vitro* activity in relation to skin appearance and optimized for formulation. Commercial development is already underway, with market launch planned for 2026. Overall, these achievements underscore Physcomitrella as a high-performance production host that combines excellent product quality with ethical and sustainability benefits.

Materials and methods

Plant material and cell culture

Physcomitrella plants (new species name: *Physcomitrium patens* (Hedw.) Mitt.; IMSC accession number 41269) were cultivated in modified Knop medium (Reski and Abel 1985) according to Decker et al. (2015) and Hoernstein et al. (2018).

Hydropathicity analysis

To select a soluble human type III collagen polypeptide region suitable for production, the hydropathicity of the amino acid sequence of the human collagen α1(III) chain (P02461) was analysed *in silico* using ExPASy ProtScale (https://web.expasy.org/protscale/). For the analysis the hydropathy scale provided by Kyte and Doolittle (1982) was employed.

Codon optimization and splice site avoidance

The sequence encoding for the human type III collagen (COL3A1; NM_000090.4) was obtained from NCBI (https://www.ncbi.nlm.nih.gov/) The codons in the selected collagen polypeptide-encoding sequence were adapted *in silico* towards the Physcomitrella codon usage (Hiss et al. 2017; Top et al. 2021). This codon optimization was performed by Thermo Fisher Scientific. Further, nucleotides in the 11 identified heterosplicing recognition motifs AGGT (Top et al. 2021) were replaced without a

change in the respective collagen amino acid sequence (**Supplementary Figure S1**). To possibly enhance production even further, the eight underrepresented codons for Cys, Glu, The, His, Lys, Asn, Gln, and Tyr were replaced with the overrepresented alternative codons (**Supplementary Table S1**) using the online tool physCO (Top et al. 2021; available at www.plant-biotech.uni-freiburg.de). A subsequent search for potential microRNA target sites (Khraiwesh et al. 2010) which was performed with the online tool psRNATarget (https://www.zhaolab.org/psRNATarget/analysis?function=2) yielded no hits. In total, this adaption led to the exchange of 192 of the total 1002 bases (**Supplementary Figure S1**) without changing the amino acid sequence.

Design of the expression vector

To obtain a secreted product, the desired recombinant collagen polypeptide should be provided with an N-terminal secretory pathway targeting signal peptide and additionally feature a C-terminal His-tag for detection and purification. The codon-optimized and splice site-abolished collagen polypeptide encoding DNA sequence (CDS) was therefore fused *in silico* to the PpAP1 (Pp6c5_10120V6.1) signal-peptide CDS (Schaaf et al. 2004) and the CDS of an 8x His-tag. For cloning purposes, the restriction sites of *Xho*I or *Bgl*II were included at the beginning and the end, respectively, and the sequence obtained was synthesized by GeneArt (Thermo Fisher Scientific, Waltham, USA). The synthesized sequence was subsequently blunt-end ligated in pJet 1.2 (Thermo Fisher Scientific) and the correctness of the sequence was confirmed by sequencing (Eurofins Genomics, Ebersberg, Germany). By using the respective restriction enzymes (Thermo Fisher Scientific), the synthesized sequence as well as a previously used expression vector (Niederau al. 2025) were digested and purified on an agarose gel. The corresponding bands of the expression vector backbone and of the collagen polypeptide-encoding sequence were extracted and subsequently ligated using a T4 ligase (Thermo Fisher Scientific). This resulted in the expression vector containing the strong and endogenous Physcomitrella promoter of the PpActin5 gene (Weise et al. 2006; Niederau et al. 2024), the synthesized target sequence followed by a nos terminator and a hpt cassette for hygromycin selection (Decker et al. 2015) of transformed plants (**Supplementary Figure S2**). For protoplast transfection the expression vector was amplified in *E. coli* DH5a cells, purified using the Plasmid Mega Kit (QIAGEN®, Hilden, Germany) according to the manufacturer´s instructions and sterilized via ethanol precipitation according to Sambrook and Russell (2006).

Generation of transgenic moss lines

Collagen polypeptide-producing moss lines were obtained by stable, polyethylene glycol-mediated transfection of Physcomitrella WT protoplasts (Hohe and Reski 2002; Hohe et al. 2004). Transfection was performed with 50 µg of *Hind*III linearized collagen polypeptide expression vector per reaction according to Decker et al. (2015). Subsequent protoplast regeneration (Schween et al. 2003) followed by the selection of stable transformants on Knop agarose plates containing 50 mg/L hygromycin were performed according to Decker et al. (2015).

Identification by Western blot

Moss colonies which survived the selection procedure were used to inoculate 500 mL Erlenmeyer flasks containing 180 mL Knop medium with microelements (Knop ME; Egener et al. 2002). They were cultivated for at least 12 weeks prior to screening for collagen production under weekly disruption according to Decker et al. (2015).

To analyse the lines for collagen polypeptide production, protonema suspension cultures were inoculated with 100 mg DW/L and after seven days of cultivation under standard conditions harvested by vacuum filtration. Subsequently, total soluble protein was extracted and purified by His trap spin-down columns (Cytiva, Marlborough, USA) and finally analysed by immunodetections. For this, 100 mg protonema fresh weight (FW) was transferred to 2 mL tubes with one tungsten carbide (Ø 3 mm, QIAGEN®, Hilden, Germany) and one glass bead (Ø 3 mm, Roth, Karlsruhe, Germany), frozen in liquid nitrogen and subsequently disrupted by using a tissue lyser (MM 400, Retsch, Haan, Germany) at 30 Hz for 90 seconds. For extraction, 600 µL of extraction buffer (75 mM $Na_2HPO_4x2H_2O$, 0.5 M NaCl, 20 mM imidazole, 0.05% Tween 20, 10% glycerol, pH 7) were added, the samples were vortexed for 5 min, and subsequently incubated in a cold ultrasound bath for 15 min (Sonorex RK52, Bandelin, Berlin, Germany), followed by 10 min of centrifugation at 14,000 rpm and 4°C. Afterwards, the supernatant was loaded to the His trap spin-down column (Cytiva) which was handled according to the manufacturer's instructions. Elution of the columns was performed with 200 µL of elution buffer (100 mM $Na_2HPO_4x2H_2O$, 0.5 M NaCl, 500 mM imidazole, 10% glycerol, pH 7.4). For Western blot analysis, a final concentration (f.c.) of 50 mM dithiothreitol (DTT, Thermo Fisher Scientific) and a f.c. of 1x Laemmli buffer (Bio-Rad, Feldkirchen, Germany) were added and the samples were incubated at 90 °C for 20 min. Subsequently, 10% SDS polyacrylamide gel electrophoresis (SDS-PAGE Ready

Gel® Tris-HCl Precast Gels, BioRad) was run at 120 V for 1.5 h and blotted to polyvinylidene fluoride (PVDF) membrane (Amersham^{TM} Hybond P 0.45 µm pore size PVDF blotting membrane, Cytiva) in a Trans-Blot® SD Semi-Dry Transfer Cell (BioRad) for 1h 15 min with 1.5 mA/cm^2 membrane. The membrane was blocked for 1 h at room temperature in TBS and 0.1% Tween 20 (TBST) containing 4% Amersham^{TM} ECL Prime Blocking Reagent (Cytiva). Subsequently, the membrane was incubated over night with the 1:2,000 in TBST diluted monoclonal anti-6x-His Tag antibody (HIS.H8, MA1-21315, Invitrogen, Thermo Fisher Scientific) at 4 °C. Afterwards, the membrane was washed three times with TBST and incubated with horseradish peroxidase-linked anti-mouse IgG (NA931V, Cytiva) at a dilution of 1:10,000 for 1 h at RT. The blot was washed again and proteins were detected using the Amersham^{TM} ECL Prime Western Blotting Detection Reagent (Cytiva) according to the manufacturer's instructions.

ELISA-mediated collagen quantification

The intracellular accumulation as well as the concentration of collagen polypeptide in the suspension culture supernatant were quantified by ELISA, with identically treated WT analysed in parallel. For intracellular collagen polypeptide analysis, 30 mg of vacuum-filtered protonema material from suspension cultures were homogenized as described for Western blot analysis and extracted in 120 µL of extraction buffer (408 mM NaCl, 60 mM Na$_2$HPO$_4$, 10.56 mM KH$_2$PO$_4$, pH 7.4, and 1% protease inhibitor (P9599, Sigma-Aldrich, Merck, Darmstadt, Germany) by vortexing for 5 min, followed by sonication for 15 min in an ultrasonic bath (Bandelin). After centrifugation for 10 min at 14,000 rpm and 4 °C, the supernatants were diluted (1:1,000-1:5,000) in coating buffer (50 mM carbonate/bicarbonate buffer, pH 9.6). A 6xHis-elastin standard protein (ABIN7081465; 28 kDa; antibodies online, Aachen, Germany) was serially diluted in coating buffer (64, 32, 16, 8, 4, 2, 1, and 0 ng/mL). For ELISA, 100 µL of either samples or standards were applied per well of a microtiter plate (NUNC Maxisorb, Wiesbaden, Germany) and incubated overnight at 4 °C. Blocking, incubation, washing, and detection were performed as described previously (Büttner-Mainik et al. 2011), using an anti-6xHis tag monoclonal antibody (HIS.H8, MA1-21315, Invitrogen, Thermo Fisher Scientific; 1:2,000) as primary and an anti-mouse HRP conjugate (NA931V; Cytiva; 1:2,000) as secondary antibody. Under these conditions, the ELISA displayed a linear detection range from 0 to 64 ng/mL. For quantification of collagen polypeptide in the suspension culture supernatant, the ELISA was performed as described above,

except that culture supernatants were directly diluted (1:10-1:50) in coating buffer before overnight coating at 4 °C. In both cases, collagen polypeptide concentrations were determined based on the standard curve generated with the serially diluted His-tagged reference protein, with values corrected for background signal and normalized by subtracting the corresponding WT control.

Secretion optimization

To investigate the accumulation of recombinant collagen polypeptide in the culture supernatant under different cultivation conditions, 200 mL suspension cultures were inoculated with protonema material of line C5 at a density of 300 mg DW/L in aerated 500 mL Erlenmeyer flasks and cultivated under standard conditions, unless otherwise specified. For each condition, WT controls were treated identically and analysed in parallel. Sampling was performed by harvesting 2 mL of suspension culture at the indicated time points. Cell-free supernatants were distributed into 100 μL aliquots, frozen in liquid nitrogen, and stored at -80 °C until ELISA-based analysis.

To test elevated CO_2 conditions while otherwise maintaining standard cultivation parameters, the corresponding cultures were incubated in a temperature-controlled, illuminated CO_2 shaker (ISF1-X Climo-Shaker, Kuhner, Basel, Switzerland) set to an atmosphere of 20,000 ppm CO_2 (2% CO_2) To investigate the effect of pH, the medium was buffered either with 2.5 mM ammonium tartrate (pH 4.5) or with 1 g/L MES (pH 5.5 and 6.5). Media were adjusted to the respective pH values using 1 M KOH or 1 M HCl and sterile-filtered prior to cultivation. Collagen polypeptide accumulation was quantified by ELISA as previously described. All values were blank-corrected and normalized by subtracting the corresponding WT signals.

Precipitation of collagen polypeptide

To analyse the quality of the secreted collagen polypeptide, culture supernatant samples were precipitated using acetone. For this, 1-6 mL of culture supernatant were transferred into 50 mL Oak Ridge-style Teflon tubes (Thermo Fisher Scientific) and mixed with five-fold of ice-cold acetone containing 0.2% DTT (Thermo Fisher Scientific). After incubating overnight at -20 °C, the samples were centrifuged at 12,000 x g for 45 min at 0 °C. The supernatant was then discarded, and the pellet was washed with 20 mL of ice-cold acetone, followed by centrifugation under the same conditions. After discarding the supernatant, the pellets were resuspended in 2 mL of acetone,

792 transferred to 2 mL reaction tubes, and centrifuged again under the same conditions.
793 Finally, the supernatant was discarded, and the remaining pellets were air-dried for
794 about 20 minutes. The pellets were stored at -20 °C until further use.

Mass spectrometric analysis

To investigate the sequence and post-translational modifications of the produced
collagen polypeptide, both intracellularly accumulated and secreted fractions were
analysed by mass spectrometry. Intracellular collagen polypeptide was prepared as
described for the Western blot analysis, whereas secreted collagen polypeptide was
obtained by acetone precipitation of the culture supernatant as outlined above. The
resulting pellets were dissolved in buffer containing 4% SDS, 125 mM Tris-HCl (pH
6.8), and 50 mM DTT by incubation at 95 °C for 20 min under shaking conditions,
followed by centrifugation at 12,000 × g for 5 min at room temperature. For both
intracellular and secreted fractions, the protein samples were loaded in duplicate onto
two identical 10% SDS-PAGE gels. After electrophoresis, one gel was stained with
PageBlue® (Thermo Fisher Scientific), while proteins from the second gel were
transferred to a PVDF membrane (Cytiva) and subjected to immunodetection as
described above. Bands in the PageBlue®-stained gel corresponding to the
immunodetected signals were excised and destained as previously outlined in
Bohlender et al. (2020). Overnight digestion was carried out with 0.2 µg of trypsin
(Trypsin Gold, Promega, Wisconsin, USA) at 37 °C. The resulting peptides were
recovered and desalted using C18 StageTips (Thermo Fisher Scientific), followed by
analysis on Orbitrap Elite and Orbitrap XL mass spectrometers (Thermo Fisher
Scientific), as previously described (Njenga et al. 2024).

The raw data of the measurement of intracellular collagen were processed using
Mascot Distiller V2.7.10, and a database search was conducted with the Mascot server
V2.7 (Matrix Science, London, United Kingdom). Processed spectra were searched
against a database containing all Physcomitrella protein models (V3.372; Lang et al.
2018), the sequence of the collagen polypeptide, and a database of known
contaminants (269 entries; Mueller et al. 2014), using a precursor mass tolerance of 8
ppm and a fragment mass tolerance of 0.6 Da. Variable modifications included
Gln→pyroGlu (N-term. Q) -17.026549 Da, dehydration Glu→pyroGlu (N-term. E) -
18.010565 Da, oxidation +15.994915 Da (P and M), and deamidation +0.984016 Da
(N).

For label-free quantitation of identified Hyp sites, the seven measurements from secreted samples were run again in *FragPipe* v23.1 configured for data dependent acquisition (DDA). Peptides were identified using *MSFragger* (Kong et al. 2017) and a Physcomitrella protein database (48,582 entries; Lang et al. 2018) including target and decoy sequences for FDR estimation as well as the sequence of the collagen polypeptide. A precursor mass tolerance of -20 to +20 ppm was used, enzyme specificity was set to semi trypsin and a peptide mass range of 500 to 5,000 Da with a minimum peptide length of 7 and a maximum of 40 amino acids was set. Carbamidomethylation of cysteines (+57.02146 Da) was set as fixed modification. Variable modifications, oxidation (+15.9949 Da) of methionine (M) and proline (P), cyclisation of N-terminal asparagine and carbamidomethylated cysteine (-17.0265 Da) as well as deamidation of glutamine (Q, -18.010565 Da) and acetylation at the protein N-terminus (+42.010567 Da). Validation of peptide-spectrum matches, and prolyl-hydroxylation site was done with *MSBooster* (Yang et al. 2023), Percolator (Käll et al. 2007; The et al. 2017), and PTMProphet (Shteynberg et al. 2019). Quantification was conducted using *IonQuant* applying a protein-level false discovery rate (FDR) threshold of 0.01.

Dry weight measurement

To determine the dry weight (DW) of suspension cultures from flasks, three samples of 10 mL each were collected under shaking conditions, filtered through pre-dried and pre-weighed Miracloth tissues (Merck, Darmstadt, Germany), and subsequently dried for 2 h at 105 °C. The DW was then determined using an analytical balance (CPA 3245; Sartorius, Göttingen, Germany). For bioreactor cultures, 100 mL of suspension were transferred into a beaker equipped with a magnetic stirrer. While stirring, triplicate samples of 10–20 mL were collected and processed as described above to determine the culture dry weight. (DW).

Bioreactor operation

For large-scale recombinant collagen polypeptide production, 5 L stirred-tank photobioreactors (Applikon Biotechnology, Schiedam, The Netherlands) were inoculated with 400 mg DW of moss protonema material per litre medium. Aeration was maintained at 1.5 vvm using CO_2-enriched air (2% CO_2, 0.3 vvm), and agitation was provided by a three-blade pitched impeller operating at 375 rpm. The pH was controlled at 4.8, and the temperature was kept constant at 22 °C. Continuous

illumination was supplied by twelve neutral white (4000 K) LED strips (MaxLine70, Lumitronix, Hechingen, Germany), evenly distributed across the bioreactor surface. Light intensity (μmol m^{-2} s^{-1}) was measured and calibrated with a light meter (LI-250A, LI-COR, Bad Homburg, Germany) at the inner bioreactor wall prior to sterilization. The applied light regime was as follows: light intensity was initially set to 100 μmol m^{-2} s^{-1} and increased to 350 μmol m^{-2} s^{-1} once a biomass concentration of 2 g DW/L was reached. When biomass reached 2.8 g DW/L, the intensity was further increased to 680 μmol m^{-2} s^{-1} and maintained at this level until harvest, which was performed at an accumulated biomass of 4 g DW/L.

Bioreactor sampling

During the bioreactor runs, samples were collected to monitor biomass accumulation and to determine both intracellular and secreted collagen polypeptide concentrations. For sampling, 100 mL of suspension culture was harvested from the bioreactor and replaced with fresh medium. The collected suspension was stirred in a beaker and first 3x 10 mL samples for dry weight determination were collected. For ELISA measurements, 100 μL aliquots were collected after allowing the suspension to sediment for 10 min, in order to minimize the carryover of moss tissue. Aliquots were frozen immediately in liquid nitrogen and stored at -80 °C until analysis. For protonema sampling, the remaining suspension culture was vacuum filtered, and 30 mg as well as 100 mg fresh weight (FW) of protonema was transferred into 2 mL reaction tubes, frozen in liquid nitrogen, and stored at −80 °C until further use.

Filtration of collagen-containing supernatants

To remove residual cells and debris from collagen polypeptide-containing culture supernatants, which had already been separated from moss tissue using 100 μm and 11 μm protoplast sieves, the suitability of various filter materials was evaluated. The tested filters included cellulose acetate (0.45 μm; Ø 50 mm; OE67; Whatman^{TM}; Cytiva), glass microfiber (1.6 μm; Ø 50 mm; GF/A; Whatman^{TM}; Cytiva), nylon (0.45 μm; Ø 47 mm; Nylaflo^{TM}; Cytiva), polyethersulfone (PES; 0.22 μm; Ø 33 mm; Rotilabo$^®$, Roth; Karlsruhe, Germany and 1 μm; Ø 25mm; Whatman^{TM} Puradisc; Cytiva and 5 μm; Ø 25mm; Chromafil$^®$Xtra; Macherey-Nagel, Düren, Germany), polyamide (0.45 μm; Ø 50 mm; NL17; Whatman^{TM}; Cytiva), polyvinylidene difluoride (PVDF; 0.45 μm; Ø 33 mm, Rotilabo$^®$, Roth; and 5 μm; Ø 47 mm; Durapore$^®$; Merck), and water-wettable polytetrafluoroethylene (wwPTFE; 0.45 μm; Ø 47 mm; Cytiva). These filters

were used either as disc filters, mounted in an individual filter holder (16201, Sartorius) and operated with a vacuum flask, or, in the case of PES (0.22 µm, 1 µm, and 5 µm) and PVDF (0.45 µm), as syringe filters. For each condition, 100 mL of harvested bioreactor supernatant were processed. Collagen polypeptide concentrations in the filtrates and in the unfiltered control were quantified by ELISA, and recoveries were calculated as percentages of the initial collagen polypeptide concentration present prior to filtration.

Nucleic acids extraction and quantitative PCR

Both genomic DNA (for qPCR) and RNA (for qRT-PCR) were extracted from 100 mg of protonema material frozen in liquid nitrogen (Schlink and Reski 2002). Protonema material for qRT-PCR analyses was harvested from equally inoculated flasks after seven days of cultivation. For the qPCR all subsequent steps were performed as described in Ruiz-Molina et al. (2022b), while the qRT-PCR analyses were conducted as carried out in Bohlender et al. (2020). Primers were designed using the online tool Primer3Plus (https://www.primer3plus.com/) with the qPCR server settings and checked for specificity against the Physcomitrella genome in the Phytozome v13 database (https://phytozome-next.jgi.doe.gov) (Goodstein et al. 2012). Primer specificity and efficiency were validated for each primer pair using DNA serial dilutions. For construct copy number determination, primer pairs targeting the collagen polypeptide CDS, the Actin5 promoter, and the hpt selection cassette were used. Reference signals for single integrations for normalization were obtained with two primer pairs (CLF5 and CLF7) targeting the single-copy gene PpCLF (Pp6c22_9280V6.1, Pereman et al. 2016). Transgene copy numbers were determined using two control calibrators: the Bag4.2 moss line, which carries a single integration of the hpt selection cassette, and the WT, which served as a single-copy reference for the Actin5 promoter. For qRT-PCR, a primer pair targeting the collagen polypeptide CDS was used, and normalization was performed with two primer pairs amplifying regions of the strongly expressed housekeeping genes LWD (Pp6c22_10850V6.1, Yin et al. 2021) encoding the WD repeat-containing protein 68 and L21 (Pp6c13_1120V6.1; Beike et al. 2015) encoding the large subunit ribosomal protein L21. All primers were synthesized by Eurofins Genomics and are listed in **Supplementary Table S2**.

Author contributions

L.L.B., A.M. and J.P. performed research. L.L.B., J.P., S.N.W.H., G.G., B.H., E.L.D. and R.R. analysed data. E.L.D. and R.R. supervised research. B.H., E.L.D. and R.R. acquired funding. L.L.B. and R.R. wrote the manuscript. All authors read and approved the final version of the manuscript.

Funding

This work was supported by Deutsche Forschungsgemeinschaft under Germany's Excellence Strategy (CIBSS – EXC-2189 – Project ID 390939984).

Data availability

The Physcomitrella WT used in this study, as well as the collagen-producing transgenic strains are available from the International Moss Stock Center IMSC (https://www.moss-stock-center.org) under the accession numbers 41269 (WT D14), 40996 (C5), and 40997 (C6.1). The mass spectrometry proteomics data have been deposited at the ProteomeXchange Consortium via the PRIDE partner repository (Deutsch et al. 2023; Perez-Riverol et al. 2025) with the dataset identifier PXDXYZ.

Conflict of Interest

G.G. and B.H. are employees of Mibelle Biochemistry, which will bring moss-made human collagen to the market. All other authors declare no conflict of interest.

Short legends for Supporting Information

Supplementary Figure S1 Alignment of the selected coding region (nucleotides 1266–2367) of the human COL3A1 CDS (COL3A1, NM_000090.4) and the codon- and splice site-optimized COL3A1 sequence (COL3A1_opt.) used for generation of collagen-producing Physcomitrella lines

Supplementary Figure S2 Schematic representation of the pJET1.2-based vector containing the expression construct used to generate recombinant collagen-polypeptide producing Physcomitrella lines

Supplementary Figure S3 Uncropped immunodetection images and Coomassie stained SDS-PAGE gel image corresponding to Figure 2

Supplementary Figure S4 Quantitative analysis of construct copy numbers in selected moss lines

Supplementary Figure S5 Immunodetection from bioreactor culture supernatants, corresponding SDS-PAGE gels, mass spectrometrically determined sequence coverages of the recombinant collagen polypeptide, and uncropped images

Supplementary Table S1 Underrepresented codons that were exchanged by overrepresented ones in the optimized CDS used for collagen production

Supplementary Table S2 Primers used for quantitative PCR

Supplementary Table S3 Quantitation summary of identified hydroxylated prolines in secreted collagen samples

References

Aly N, Benoit E, Chaubard JL, Chintalapudi K, Choung S, de Leeuw M, Diaz M, Dueppen D, Ferraro B, Fischetti V, Gassaway E, Hansenne-Cervantes I, Heeres A, Karas C, Khan M, Kral JM, Lam S, Lartey R, Leonhard M, Lue SW, McDaniel J, Ramirez K, Rauw B, Raymond KA, Roggero-Lovisi C, Rubin S, Ruebling-Jass K, Vincent KE, Wang J, Williamson D, Yu Z, Dai L (2022) Cosmetic potential of a recombinant 50 kDa protein. Cosmet 9:8. doi: 10.3390/cosmetics9010008

Ariyanta HA, Sholeha NA, Fatriasari W (2025) Current and future outlook of research on renewable cosmetics derived from biomass. Chem Biodiv 22:e202402249. doi: 10.1002/cbdv.202402249

Baur A, Reski R, Gorr G (2005) Enhanced recovery of a secreted recombinant human growth factor using stabilizing additives and by co-expression of human serum albumin in the moss *Physcomitrella patens*. Plant Biotech J 3:331–340. doi: 10.1111/j.1467-7652.2005.00127.x

Beike AK, Lang D, Zimmer AD, Wüst F, Trautmann D, Wiedemann G, Beyer P, Decker EL, Reski R (2015) Insights from the cold transcriptome of *Physcomitrella patens*: global specialization pattern of conserved transcriptional regulators and identification of orphan genes involved in cold acclimation. New Phytol 205:869–881. doi: 10.1111/nph.13004

Bohlender LL, Parsons J, Hoernstein SNW, Rempfer C, Ruiz-Molina N, Lorenz T, Jahnke FR, Figl R, Fode B, Altmann F, Reski R, Decker EL (2020) Stable protein sialylation in Physcomitrella. Front Plant Sci 11:610032. doi: 10.3389/fpls.2020.610032

Bohlender LL, Parsons J, Hoernstein SNW, Bangert N, Rodriguez-Jahnke F, Reski R, Decker EL (2022) Unexpected arabinosylation after humanization of plant protein N-glycosylation. Front Bioeng Biotech 10:838365. doi: 10.3389/fbioe.2022.838365

Brodsky B, Ramshaw JAM (1997) The collagen triple-helix structure. Matrix Bio 15:545–554. doi: 10.1016/S0945-053X(97)90030-5

Büttner-Mainik A, Parsons J, Jerome H, Hartmann A, Lamer S, Schaaf A, Schlosser A, Zipfel PF, Reski R, Decker EL (2011) Production of biologically active recombinant human factor H in Physcomitrella. Plant Biotech J 9:373–383. doi: 10.1111/j.1467-7652.2010.00552.x

Chan SWP, Greaves J, Da Silva NA, Wang SW (2012) Assaying proline hydroxylation in recombinant collagen variants by liquid chromatography-mass spectrometry. BMC Biotech 12:51. doi: 10.1186/1472-6750-12-51

Chen CX, Zhang YY, Yang J, Yan MH, Jia Y, Jiang S (2024) An overview of progress in the application of recombinant collagen in cosmetics. J Derm Sci Cosmet Tech 1:100059. doi: 10.1016/j.jdsct.2024.100059

Chin YKY, Heady SJ, Mohanty B, Patil R, McEwan PA, Swarbrick JD, Mulhern TD, Emsley J, Simpson JS, Scanlon MJ (2013) The structure of integrin α1I domain in complex with a collagen-mimetic peptide. J Biol Chem 288:36796–36809. doi: 10.1074/jbc.M113.480251

DataIntelo (2024) Recombinant Humanized Collagen Market Report | Global Forecast From 2025 To 2033. Available at: https://dataintelo.com/report/recombinant-humanized-collagen-market (Accessed November 12, 2025).

Decker EL, Reski R (2007) Moss bioreactors producing improved biopharmaceuticals. Curr Op Biotech 18:393–398. doi: 10.1016/j.copbio.2007.07.012

Decker EL, Reski R (2020) Mosses in biotechnology. Curr Op Biotech 61:21–27. doi: 10.1016/j.copbio.2019.09.021

Decker EL, Wiedemann G, Reski R (2015) Gene targeting for precision glyco-engineering: Production of biopharmaceuticals devoid of plant-typical glycosylation in moss bioreactors. Meth Mol Biol 1321:213-224. doi: 10.1007/978-1-4939-2760-9_15

Deutsch EW, Bandeira N, Perez-Riverol Y, Sharma V, Carver JJ, Mendoza L, Kundu DJ, Wang S, Bandla C, Kamatchinathan S, Hewapathirana S, Pullman BS, Wertz J, Sun Z, Kawano S, Okuda S, Watanabe Y, MacLean B, MacCoss MJ, Zhu Y, Ishihama Y, Vizcaíno JA (2023) The ProteomeXchange consortium at 10 years: 2023 update. Nucl Acids Res 51:D1539-D1548. doi: 10.1093/nar/gkac1040

D'hondt S, Guillemyn B, Syx D, Symoes S, De Rycke R, Vanhoutte L, Toussaint W, Lambrecht BN, De Paepe A, Keene DR, Ishikawa Y, Bächinger HP, Janssens S, Bertrand MJM, Malfait F (2018) Type III collagen affects dermal and vascular collagen fibrillogenesis and tissue integrity in a mutant *Col3a1* transgenic mouse model. Matrix Biol 70:72–83. doi: 10.1016/j.matbio.2018.03.008

Doran PM (2006) Foreign protein degradation and instability in plants and plant tissue cultures. Trends Biotech 24:426–432. doi: 10.1016/j.tibtech.2006.06.012

Dunleavy M (2024) Polyethersulfone membranes facilitate sterile filtration of biological materials. Biosci Techn. Available at: https://biosciencetechnology.com/articles/2003/01/polyethersulfone-membranes-facilitate-sterile-filtration-biological-materials (Accessed November 12, 2025).

Egener T, Granado J, Guitton MC, Hohe A, Holtorf H, Lucht JM, Rensing SA, Schlink K, Schulte J, Schween G, Zimmermann S, Duwenig E, Rak B, Reski R (2002) High frequency of phenotypic deviations in *Physcomitrella patens* plants transformed with a gene-disruption library. BMC Plant Bio 2:6. doi: 10.1186/1471-2229-2-6

Engel J, Bächinger HP (2005) Structure, stability and folding of the collagen triple helix. Collagen 247:7-33. doi: 10.1007/b103818

Erxleben A, Gessler A, Vervliet-Scheebaum M, Reski R (2012) Metabolite profiling of the moss *Physcomitrella patens* reveals evolutionary conservation of osmoprotective substances. Plant Cell Rep 31:427–436. doi: 10.1007/s00299-011-1177-9

Eskelin K, Ritala A, Suntio T, Blumer S, Holkeri H, Wahlström EH, Baez J, Mäkinen K, Maria NA (2009) Production of a recombinant full-length collagen type I α-1 and of a 45-kDa collagen type I α-1 fragment in barley seeds. Plant Biotech J 7:657–672. doi: 10.1111/j.1467-7652.2009.00432.x

Frank W, Decker EL, Reski R (2005) Molecular tools to study *Physcomitrella patens*. Plant Bio 7:220–227. doi: 10.1055/s-2005-865645

Frantz C, Stewart KM, Weaver VM (2010) The extracellular matrix at a glance. J Cell Sci 123:4195–4200. doi: 10.1242/jcs.023820

Gaar J, Naffa R, Brimble M (2020) Enzymatic and non-enzymatic crosslinks found in collagen and elastin and their chemical synthesis. Org Chem Front 7:2789–2814. doi: 10.1039/d0qo00624f

Gitzinger M, Parsons J, Reski R, Fussenegger M (2009) Functional cross-kingdom conservation of mammalian and moss (*Physcomitrella patens*) transcription, translation and secretion machineries. Plant Biotech J 7:73-86. doi: 10.1111/j.1467-7652.2008.00376.x

Goodstein DM, Shu SQ, Howson R, Neupane R, Hayes RD, Fazo J, Mitros T, Dirks W, Hellsten U, Putnam N, Rokhsar DS (2012) Phytozome: a comparative platform for green plant genomics. Nucl Acids Res 40:D1178-D1186. doi: 10.1093/nar/gkr944

Gordon MK, Hahn RA (2010) Collagens. Cell Tissue Res 339:247–257. doi: 10.1007/s00441-009-0844-4

Grand View Research (2024) *Collagen Market Size, Share & Growth | Industry Report 2030.* Available at: https://www.grandviewresearch.com/industry-analysis/collagen-market (Accessed November 12, 2025).

Grigolon G, Nowak K, Poigny S, Hubert J, Kotland A, Waldschütz L, Wandrey F (2023) From coffee waste to active ingredient for cosmetic applications. Int J Mol Sci 24:8516. doi: 10.3390/ijms24108516

Guo L, Xiang W, Pan Z, Gu H, Jiang X (2025) Post-translational modifications of collagen and its related diseases in metabolic pathways. Acta Pharm Sin B 15:1773-1795. doi: 10.1016/j.apsb.2025.02.007

Han Y, Jiang J, Li J, Zhao L, Xi Z (2024) Influences of polyphenols on the properties of crosslinked acellular fish swim bladders: Experiments and molecular dynamic simulations. Polym 16:1111. doi: 10.3390/polym16081111

Hass V, Liu H, Cook W, Walker MP, Wang Y (2021) Distinct effects of polyphenols and solvents on dentin collagen crosslinking interactions and biostability. Dent Mater 37:1794-1805. doi: 10.1016/j.dental.2021.09.009

Hiss M, Laule O, Meskauskiene RM, Arif MA, Decker EL, Erxleben A, Frank W, Hanke ST, Lang D, Martin A, Neu C, Reski R, Richardt S, Schallenberg-Rüdinger M, Szövenyi P, Tiko T, Wiedemann G, Wolf L, Zimmermann P, Rensing SA (2014) Large-scale

gene expression profiling data for the model moss *Physcomitrella patens* aid understanding of developmental progression, culture and stress conditions. Plant J 79:530–539. doi: 10.1111/tpj.12572

Hiss M, Schneider L, Grosche C, Barth MA, Neu C, Symeonidi A, Ullrich KK, Perroud PF, Schallenberg-Rüdinger M, Rensing SA (2017) Combination of the endogenous *lhcsr1* promoter and codon usage optimization boosts protein expression in the moss *Physcomitrella patens*. Front Plant Sci 8:1842. doi: 10.3389/fpls.2017.01842

Hohe A, Reski R (2002) Optimisation of a bioreactor culture of the moss *Physcomitrella patens* for mass production of protoplasts. Plant Sci 163:69-74. doi: 10.1016/S0168-9452(02)00059-6

Hohe A, Decker E, Gorr G, Schween G, Reski R (2002) Tight control of growth and cell differentiation in photoautotrophically growing moss (*Physcomitrella patens*) bioreactor cultures. Plant Cell Rep 20:1135-1140. doi: 10.1007/s00299-002-0463-y

Hohe A, Egener T, Lucht JM, Holtorf H, Reinhard C, Schween G, Reski R (2004) An improved and highly standardised transformation procedure allows efficient production of single and multiple targeted gene-knockouts in a moss, *Physcomitrella patens*. Curr Genet 44:339-347. doi: 10.1007/s00294-003-0458-4

Hoernstein SNW, Fode B, Wiedemann G, Lang D, Niederkrüger H, Berg B, Schaaf A, Frischmuth T, Schlosser A, Decker EL, Reski R (2018) Host cell proteome of *Physcomitrella patens* harbors proteases and protease inhibitors under bioproduction conditions. J Proteom Res 17:3749-3760. doi: 10.1021/acs.jproteome.8b00423

Horn A, Pascal A, Loncarevic I, Marques RV, Lu Y, Miguel S, Bourgaud F, Thorsteinsdottir M, Cronberg N, Becker JD, Reski R, Simonsen HT (2021) Natural products from bryophytes: From basic biology to biotechnological applications. Crit Rev Plant Sci 40:191-217. doi: 10.1080/07352689.2021.1911034

Hua C, Zhu Y, Xu W, Ye S, Zhang RG, Lu L, Jiang SB (2019) Characterization by high-resolution crystal structure analysis of a triple-helix region of human collagen type III with potent cell adhesion activity. Biochem Biophys Res Comm 508:1018–1023. doi: 10.1016/j.bbrc.2018.12.018

Ide K, Takahashi S, Sakai K, Taga Y, Ueno T, Dickens D, Jenkins R, Falciani F, Sasaki T, Ooi K, Kawashiri S, Mizuno K, Hattori S, Sakai T (2021) The dipeptide prolyl-hydroxyproline promotes cellular homeostasis and lamellipodia-driven motility via active β1-integrin in adult tendon cells. J Biol Chem 297:100819. doi: 10.1016/j.jbc.2021.100819

Ihlberg L, Haukipuro K, Risteli L, Oikarinen A, Kairaluoma MI, Risteli J (1993) Collagen synthesis in intact skin is suppressed during wound healing. Ann Surg 217:397-403. doi: 10.1097/00000658-199304000-00012

Käll L, Canterbury JD, Weston J, Noble WS, MacCoss MJ (2007) Semi-supervised
learning for peptide identification from shotgun proteomics datasets. Nat Methods
4:923-925. doi: 10.1038/nmeth1113

Kersteen EA, Higgin JJ, Raines RT (2004) Production of human prolyl 4-hydroxylase
in *Escherichia coli*. Protein Expr Purif 38:279-291. doi: 10.1016/j.pep.2004.09.008

Khraiwesh B, Arif MA, Seumel GI, Ossowski S, Weigel D, Reski R, Frank W (2010)
Transcriptional control of gene expression by microRNAs. Cell 140:111-122. doi:
10.1016/j.cell.2009.12.023

Kim JK, Xu Y, Xu X, Keene DR, Gurusiddappa S, Liang XW, Wary KK, Höök M (2005)
A novel binding site in collagen type III for integrins α1β1 and α2β1. J Biol Chem
280:32512-32520. doi: 10.1074/jbc.M502431200

Kim YU, Gi H, Jeong EK, Han S, Seo WY, Kim YJ, Lee SB, Kim K (2024) Development
of a highly effective recombinant protein from human collagen type III Alpha 1
(COL3A1) to enhance human skin cell functionality. BMB Rep 57:424-429. doi:
10.5483/BMBRep.2024-0107

Kirchner M, Deng H, Xu Y (2021) Heterogeneity in proline hydroxylation of fibrillar
collagens observed by mass spectrometry. PLOS ONE 16:e0250544. doi:
10.1371/journal.pone.0250544

Kong AT, Leprevost FV, Avtonomov DM, Mellacheruvu D, Nesvizhskii AI (2017)
MSFragger: ultrafast and comprehensive peptide identification in mass spectrometry-
based proteomics. Nat Methods 14:513-520. doi: 10.1038/NMETH.4256

Krafts KP (2010) Tissue repair: The hidden drama. Organogen 6:225-233. doi:
10.4161/org.6.4.12555

Kriegshauser L, Knosp S, Grienenberger E, Tatsumi K, Gütle DD, Sorensen I, Herrgott
L, Zumsteg J, Rose JKC, Reski R, Werck-Reichhart D, Renault H (2021) Function of
the HYDROXYCINNAMOYL-CoA:SHIKIMATE HYDROXYCINNAMOYL
TRANSFERASE is evolutionary conserved in embryophytes. Plant Cell 33:1472-1491.
doi: 10.1093/plcell/koab044

Kuivaniemi H, Tromp G (2019) Type III collagen (COL3A1) gene and protein structure,
tissue distribution, and associated diseases. Gene 707:151–171. doi:
10.1016/j.gene.2019.05.003

Kyte J, Doolittle RF (1982) A simple method for displaying the hydropathic character
of a protein. J Mol Bio 157:105-132. doi: 10.1016/0022-2836(82)90515-0

Lamberg A, Helaakoski T, Myllyharju J, Peltonen S, Notbohm H, Pihlajaniemi T,
Kivirikko KI (1996) Characterization of human type III collagen expressed in a
baculovirus system. Production of a protein with a stable triple helix requires
coexpression with the two types of recombinant prolyl 4-hydroxylase subunit. J Biol
Chem 271:11988-11995. doi: 10.1074/jbc.271.20.11988

Lang D, Ullrich KK, Murat F, Fuchs J, Jenkins J, Haas FB, Piednoel M, Gundlach H, Van Bel M, Meyberg R, Vives C, Morata J, Symeonidi A, Hiss M, Muchero W, Kamisugi Y, Saleh O, Blanc G, Decker EL, van Gessel N, Grimwood J, Hayes RD, Graham SW, Gunter LE, McDaniel S, Hoernstein SNW, Larsson A, Li FW, Perroud PF, Phillips J, Ranjan P, Rokshar DS, Rothfels CJ, Schneider L, Shu SQ, Stevenson DW, Thümmler F, Tillich M, Aguilar JCV, Widiez T, Wong GKS, Wymore A, Zhang Y, Zimmer AD, Quatrano RS, Mayer KFX, Goodstein D, Casacuberta JM, Vandepoele K, Reski R, Cuming AC, Tuskan GA, Maumus F, Salse J, Schmutz J, Rensing SA (2018) The *Physcomitrella patens* chromosome-scale assembly reveals moss genome structure and evolution. Plant J 93:515-533. doi: 10.1111/tpj.13801

Liu X, Wu H, Byrne M, Krane S, Jaenisch R (1997) Type III collagen is crucial for collagen I fibrillogenesis and for normal cardiovascular development. Proc Natl Acad Sci USA 94:1852-1856. doi: 10.1073/pnas.94.5.1852

Lueth VM, Reski R (2023) Mosses. Curr Bio 33:R1175-R1181. doi: 10.1016/j.cub.2023.09.042

Madhan B, Subramanian V, Rao JR, Nair BU, Ramasami T (2005) Stabilization of collagen using plant polyphenol: role of catechin. Int J Biol Macromol 37:47–53. doi: 10.1016/j.ijbiomac.2005.08.005

Malfait F (2018) Vascular aspects of the Ehlers-Danlos syndromes. Matrix Bio 71-72:380–395. doi: 10.1016/j.matbio.2018.04.013

Manjari MS, Aaron KP, Muralidharan C, Rose C (2020) Highly biocompatible novel polyphenol cross-linked collagen scaffold for potential tissue engineering applications. React Funct Polym 153:104630. doi: 10.1016/j.reactfunctpolym.2020.104630

Merle C, Perret S, Lacour T, Jonval V, Hudaverdian S, Garrone R, Ruggiero F, Theisen M (2002) Hydroxylated human homotrimeric collagen I in *Agrobacterium tumefaciens*-mediated transient expression and in transgenic tobacco plant. FEBS Lett 515:114–118. doi: 10.1016/S0014-5793(02)02452-3

Michelfelder S, Parsons J, Bohlender LL, Hoernstein SNW, Niederkrüger H, Busch A, Krieghoff N, Koch J, Fode B, Schaaf A, Frischmuth T, Pohl M, Zipfel PF, Reski R, Decker EL, Häffner K (2017) Moss-produced, glycosylation-optimized human factor H for therapeutic application in complement disorders. J Am Soc Nephrol 28:1462-1474. doi: 10.1681/ASN.2015070745

Mitura S, Sionkowska A, Jaiswal A (2020) Biopolymers for hydrogels in cosmetics: review. J Mater Sci Mater Med 31:50. doi: 10.1007/s10856-020-06390-w

Mueller SJ, Lang D, Hoernstein SNW, Lang EGE, Schuessele C, Schmidt A, Fluck M, Leisibach D, Niegl C, Zimmer AD, Schlosser A, Reski R (2014) Quantitative analysis of the mitochondrial and plastid proteomes of the moss *Physcomitrella patens* reveals protein macrocompartmentation and microcompartmentation. Plant Phys 164:2081-2095. doi: 10.1104/pp.114.235754

Mullins RJ, Richards C, Walker T (1996) Allergic reactions to oral, surgical and topical
bovine collagen: Anaphylactic risk for surgeons. Austr New Zeal J Ophthal 24:257–
260. doi: 10.1111/j.1442-9071.1996.tb01589.x

Munoz C, Schröder K, Henes B, Hubert J, Leblond S, Poigny S, Reski R, Wandrey F
(2024) Phytochemical exploration of ceruchinol in moss: A multidisciplinary study on
biotechnological cultivation of *Physcomitrium patens* (Hedw.) Mitt. Appl Sci 14:1274.
doi: 10.3390/app14031274

Myllyharju J (2008) Prolyl 4-hydroxylases, key enzymes in the synthesis of collagens
and regulation of the response to hypoxia, and their roles as treatment targets. Ann
Med 40:402–417. doi: 10.1080/07853890801986594

Myllyharju J (2009) Recombinant collagen trimers from insect cells and yeast. Meth
Mol Biol 522:51–62. doi: 10.1007/978-1-59745-413-1_3

Myllyharju J, Nokelainen M, Vuorela A, Kivirikko KI (2000) Expression of recombinant
human type I-III collagens in the yeast *Pichia pastoris*. Biochem Soc Trans 28:353–
357. doi: 10.1042/bst0280353

Nakamura Y, Gojobori T, Ikemura T (2000) Codon usage tabulated from international
DNA sequence databases: status for the year 2000. Nucl Acids Res 28:292. doi:
10.1093/nar/28.1.292

Niederau PA, Eglé P, Willig S, Parsons J, Hoernstein SNW, Decker EL, Reski R (2024)
Multifactorial analysis of terminator performance on heterologous gene expression in
Physcomitrella. Plant Cell Rep 43:43. doi: 10.1007/s00299-023-03088-5

Niederau PA, Weilguny MC, Chamas S, Turney CE, Parsons J, Rodríguez-Franco M,
Hoernstein SNW, Decker EL, Simonsen HT, Reski R (2025) Production of human
papillomavirus type 16 virus-like particles in Physcomitrella photobioreactors. Plant
Cell Rep 44:216. doi: 10.1007/s00299-025-03602-x

Niu G, Chen X (2011) Why integrin as a primary target for imaging and therapy.
Theranostics 1:30–47. doi: 10.7150/thno/v01p0030

Njenga RK, Boele J, Drepper F, Sinha K, Marouda E, Huesgen PF, Blaby-Haas C,
Koch HG (2024) Ribosome-inactivation by a class of widely distributed C-tail anchored
membrane proteins. Struct 32:2259-2275. doi: 10.1016/j.str.2024.09.019

Ohara H, Ichikawa S, Matsumoto H, Akiyama M, Fujimoto N, Kobayashi T, Tajima S
(2010) Collagen-derived dipeptide, proline-hydroxyproline, stimulates cell proliferation
and hyaluronic acid synthesis in cultured human dermal fibroblasts. J Derma 37:330–
338. doi: 10.1111/j.1346-8138.2010.00827.x

Parsons J, Altmann F, Arrenberg CK, Koprivova A, Beike AK, Stemmer C, Gorr G,
Reski R, Decker EL (2012) Moss-based production of asialo-erythropoietin devoid of
Lewis A and other plant-typical carbohydrate determinants. Plant Biotech J 10:851–
861. doi: 10.1111/j.1467-7652.2012.00704.x

Parsons J, Altmann F, Graf M, Stadlmann J, Reski R, Decker EL (2013) A gene responsible for prolyl-hydroxylation of moss-produced recombinant human erythropoietin. Sci Rep 3:3019. doi: 10.1038/srep03019

Pereman I, Mosquna A, Katz A, Wiedemann G, Lang D, Decker EL, Tamada Y, Ishikawa T, Nishiyama T, Hasebe M, Reski R, Ohad N (2016) The Polycomb group protein CLF emerges as a specific tri-methylase of H3K27 regulating gene expression and development in *Physcomitrella patens*. Biochim Biophys Acta 1859:860–870. doi: 10.1016/j.bbagrm.2016.05.004

Perez-Riverol Y, Bandla C, Kundu DJ, Kamatchinathan S, Bai J, Hewapathirana S, John NS, Prakash A, Walzer M, Wang S, Vizcaíno, JA (2025) The PRIDE database at 20 years: 2025 update. Nucl Acids Res 53:D543-D553. doi: 10.1093/nar/gkae1011

Perret S, Merle C, Bernocco S, Berland P, Garrone R, Hulmes DJS, Theisen M, Ruggiero F (2001) Unhydroxylated triple helical collagen I produced in transgenic plants provides new clues on the role of hydroxyproline in collagen folding and fibril formation. J Biol Chem 276:43693–43698. doi: 10.1074/jbc.M105507200

Pihlajamaa T, Perälä M, Vuoristo MM, Nokelainen M, Bodo M, Schulthess T, Vuorio E, Timpl R, Engel J, Ala-Kokko L (1999) Characterization of recombinant human type IX collagen: Association of α chains into homotrimeric and heterotrimeric molecules. J Biol Chem 274:22464–22468. doi: 10.1074/jbc.274.32.22464

Pinkas DM, Ding S, Raines RT, Barron AE (2011) Tunable, post-translational hydroxylation of collagen domains in *Escherichia coli*. ACS Chem Bio 6:320–324. doi: 10.1021/cb100298r

Post A, Wang E, Cosgriff-Hernandez E (2019) A review of integrin-mediated endothelial cell phenotype in the design of cardiovascular devices. Ann Biomed Engin 47:366–380. doi: 10.1007/s10439-018-02171-3

Ramezaniaghdam M, Bohlender LL, Parsons J, Hoernstein SNW, Decker EL, Reski R (2025) Recombinant production of spider silk protein in Physcomitrella photobioreactors. Plant Cell Rep 44:103. doi: 10.1007/s00299-025-03485-y

Rappu P, Salo AM, Myllyharju J, Heino J (2019) Role of prolyl hydroxylation in the molecular interactions of collagens. Extracell Matrix 63:325–335. doi: 10.1042/EBC20180053

Rath A, Glibowicka M, Nadeau VG, Chen G, Deber CM (2009) Detergent binding explains anomalous SDS-PAGE migration of membrane proteins. Proc Natl Acad Sci USA 106:1760–1765. doi: 10.1073/pnas.0813167106

Renault H, Alber A, Horst NA, Lopes AB, Fich EA, Kriegshauser L, Wiedemann G, Ullmann P, Herrgott L, Erhardt M, Pineau E, Ehlting J, Schmitt M, Rose JKC, Reski R, Werck-Reichhart D (2017) A phenol-enriched cuticule is ancestral to lignin evolution in land plants. Nat Comm 8:14713. doi: 10.1038/ncomms14713

Rempfer C, Hoernstein SNW, van Gessel N, Graf AW, Spiegelhalder RP, Bertolini A, Bohlender LL, Parsons J Decker EL, Reski R (2024) Differential prolyl hydroxylation by six Physcomitrella prolyl-4 hydroxylases. Comp Struct Biotech J 23:2580–2594. doi: 10.1016/j.csbj.2024.06.014

Reski R, Abel WO (1985) Induction of budding on chloronemata and caulonemata of the moss, *Physcomitrella patens*, using isopentenyladenine. Planta 165, 354–358. doi: 10.1007/BF00392232

Reski R, Parsons J, Decker EL (2015) Moss-made pharmaceuticals: from bench to bedside. Plant Biotech J 13:1191-1198. doi: 10.1111/pbi.12401

Reski R, Bae H, Simonsen HT (2018) *Physcomitrella patens*, a versatile synthetic biology chassis. Plant Cell Rep 37:1409–1417. doi: 10.1007/s00299-018-2293-6

Ricard-Blum S (2011) The collagen family. Cold Spring Harb Perspect Bio 3:a004978. doi: 10.1101/cshperspect.a004978

Richter H, Lieberei R, Strnad M, Novák O, Gruz J, Rensing SA, von Schwartzenberg K (2012) Polyphenol oxidases in *Physcomitrella*: functional PPO1 knockout modulates cytokinin-dependent development in the moss *Physcomitrella patens*. J Exp Bot 63:5121–5135. doi: 10.1093/jxb/ers169

Ritala A, Wahlström EH, Holkeri H, Hafren, A., Mäkeläinen K, Baez J, Mäkinen K, Nuutila AM (2008) Production of a recombinant industrial protein using barley cell cultures. Protein Expr Purif 59:274–281. doi: 10.1016/j.pep.2008.02.013

Rodríguez MIA, Rodríguez Barroso LG, Sánchez ML (2018) Collagen: A review on its sources and potential cosmetic applications. J Cosmet Dermat 17:20–26. doi: 10.1111/jocd.12450

Ruggiero F, Exposito JY, Bournat P, Gruber V, Perret S, Comte J, Olagnier B, Garrone R, Theisen M (2000) Triple helix assembly and processing of human collagen produced in transgenic tobacco plants. FEBS Lett 469:132–136. doi: 10.1016/S0014-5793(00)01259-X

Ruiz-Molina N, Parsons J, Müller M, Hoernstein SNW, Bohlender LL, Pumple S, Zipfel PF, Häffner K, Reski R, Decker EL (2022a) A synthetic protein as efficient multitarget regulator against complement over-activation. Comm Bio 5:152. doi: 10.1038/s42003-022-03094-5

Ruiz-Molina N, Parsons J, Schroeder S, Posten C, Reski R, Decker EL (2022b) Process engineering of biopharmaceutical production in moss bioreactors via model-based description and evaluation of phytohormone impact. Front Bioeng Biotech 10:837965. doi: 10.3389/fbioe.2022.837965

Saliba E, Hoernstein SNW, van Gessel N, Sentimenti A, Höß KMV, Parsons J, Decker EL, Huesgen PF, Simonsen HT, Reski R (2025) Functional characterization of Target of Rapamycin (TOR) signalling in Physcomitrella. bioRxiv. doi: 10.1101/2025.11.04.686496.

Sambrook J, Russell DW (2006) Standard ethanol precipitation of DNA in microcentrifuge tubes. Cold Spring Harb Protoc 2006. doi: 10.1101/pdb.prot4456

Sato K, Jimi S, Kusubata M (2019) Generation of bioactive prolyl-hydroxyproline (Pro-Hyp) by oral administration of collagen hydrolysate and degradation of endogenous collagen. Int J Food Sci Tech 54:1976–1980. doi: 10.1111/ijfs.14145

Schaaf A, Reski R, Decker EL (2004) A novel aspartic proteinase is targeted to the secretory pathway and to the vacuole in the moss *Physcomitrella patens*. Eur J Cell Bio 83:145–152. doi: 10.1078/0171-9335-00371

Schaaf A, Tintelnot S, Baur A, Reski R, Gorr G, Decker EL (2005) Use of endogenous signal sequences for transient production and efficient secretion by moss (*Physcomitrella patens*) cells. BMC Biotech 5:30. doi: 10.1186/1472-6750-5-30

Schlink K, Reski R (2002) Preparing high-quality DNA from moss (*Physcomitrella patens*). Plant Mol Bio Rep 20:423. doi: 10.1007/BF02772133

Schween G, Hohe A, Koprivova A, Reski R (2003) Effects of nutrients, cell density and culture techniques on protoplast regeneration and early protonema development in a moss, *Physcomitrella patens*. J Plant Phys 160:209-212. doi: 10.1078/0176-1617-00855

See YP, Olley PM, Jackowski G (1985) The effects of high salt concentrations in the samples on molecular weight determination in sodium dodecyl sulfate polyacrylamide gel electrophoresis. Electrophor 6:382–387. doi: 10.1002/elps.1150060806

Shavandi A, Bekhit AEDA, Saeedi P, Izadifar Z, Bekhit AA, Khademhosseini A (2018) Polyphenol uses in biomaterials engineering. Biomat 167:91–106. doi: 10.1016/j.biomaterials.2018.03.018

Shi J, Ma X, Gao Y, Fan D, Zhu C, Mi Y, Xue WJ (2017) Hydroxylation of human type III collagen alpha chain by recombinant coexpression with a viral prolyl 4-hydroxylase in *Escherichia coli*. Protein J 36:322-331. doi: 10.1007/s10930-017-9723-0

Shoseyov O, Posen Y, Grynspan F (2014) Human collagen produced in plants: More than just another molecule. Bioeng 5:49-52. doi: 10.4161/bioe.26002

Shoulders MD, Raines RT (2009) Collagen structure and stability. Ann Rev Biochem 78:929–958. doi: 10.1146/annurev.biochem.77.032207.120833

Shteynberg DD, Deutsch EW, Campbell DS, Hoopmann MR, Kusebauch U, Lee D, Mendoza L, Midha MK, Sun Z, Whetton AD, Moritz RL (2019) PTMProphet: Fast and accurate mass modification localization for the trans-proteomic pipeline. J Proteome Res 18:4262–4272. doi: 10.1021/acs.jproteome.9b00205

Siljander PRM, Hamaia S, Peachey AR, Slatter DA, Smethurst PA, Ouwehand WH, Knight CG, Farndale RW (2004) Integrin activation state determines selectivity for novel recognition sites in fibrillar collagens. J Biol Chem 279:47763–47772. doi: 10.1074/jbc.M404685200

Sionkowska A, Adamiak K, Musial K, Gadomska M (2020) Collagen based materials in cosmetic applications: A review. Materials 13:4217. doi: 10.3390/ma13194217

Stein H, Wilensky M, Tsafrir Y, Rosenthal M, Amir R, Avraham T, Ofir K, Dgany O, Yayon A, Shoseyov O (2009) Production of bioactive, post-translationally modified, heterotrimeric, human recombinant type-I collagen in transgenic tobacco. Biomacromol 10:2640–2645. doi: 10.1021/bm900571b

Stewart DC, Brisson BK, Yen WK, Liu Y, Wang C, Ruthel G, Gullberg D, Mauck RL, Maden M, Han L, Volk SW (2025) Type III collagen regulates matrix architecture and mechanosensing during wound healing. J Invest Derm 145:919-938.e14. doi: 10.1016/j.jid.2024.08.013

Strepp R, Scholz S, Kruse S, Speth V, Reski R (1998) Plant nuclear gene knockout reveals a role in plastid division for the homolog of the bacterial cell division protein FtsZ, an ancestral tubulin. Proc Natl Acad Sci USA 95:4368–4373. doi: 10.1073/pnas.95.8.4368

Taga Y, Kusubata M, Ogawa-Goto K, Hattori S, Funato N (2018) Collagen-derived X-Hyp-Gly-type tripeptides promote differentiation of MC3T3-E1 pre-osteoblasts. J Funct Foods 46:456–462. doi: 10.1016/j.jff.2018.05.017

Taga Y, Tanaka K, Hattori S, Mizuno K (2021) In-depth correlation analysis demonstrates that 4-hydroxyproline at the Yaa position of Gly-Xaa-Yaa repeats dominantly stabilizes collagen triple helix. Matrix Bio Plus 10:100067. doi: 10.1016/j.mbplus.2021.100067

Tanzer ML (1973) Cross-linking of collagen. Science 180:561–566. doi: 10.1126/science.180.4086.561

The M, MacCoss MJ, Noble WS, Käll L (2016) Fast and accurate protein false discovery rates on large-scale proteomics data sets with Percolator 3.0. J Am Soc Mass Spec 27:1719-1727. doi: 10.1007/s13361-016-1460-7

Top O, Parsons J, Bohlender LL, Michelfelder S, Kopp P, Busch-Steenberg C, Hoernstein SNW, Zipfel PF, Häffner K, Reski R, Decker EL (2019) Recombinant production of MFHR1, a novel synthetic multitarget complement inhibitor, in moss bioreactors. Front Plant Sci 10:260. doi: 10.3389/fpls.2019.00260

Top O, Milferstaedt SWL, van Gessel N, Hoernstein SNW, Özdemir B, Decker EL, Reski R (2021) Expression of a human cDNA in moss results in spliced mRNAs and fragmentary protein isoforms. Comm Bio 4:964. doi: 10.1038/s42003-021-02486-3

Van Huizen NA, Burgers PC, Saintmont F, Brocorens P, Gerbaux P, Stingl C, Dekker LJM, Jzermans JNMI, Luider TM (2019) Identification of 4-hydroxyproline at the Xaa position in collagen by mass spectrometry. J Proteome Res 18:2045-2051. doi: 10.1021/acs.jproteome.8b00930

Vate NK, Strachowski P, Undeland I, Abdollahi M (2023) Structural and functional properties of collagen isolated from lumpfish and starfish using isoelectric precipitation vs salting out. Food Chem 18:100646. doi: 10.1016/j.fochx.2023.100646

Volk SW, Wang Y, Mauldin EA, Liechty KW, Adams SL (2011) Diminished type III collagen promotes myofibroblast differentiation and increases Scar deposition in cutaneous wound healing. Cells Tiss Org 194:25–37. doi: 10.1159/000322399

Wandrey F, Henes B, Zülli F, Reski R (2018) Biotechnologically produced moss active improves skin resilience. SOFW J 144:34-37.

Wang T, Lew J, Premkumar J, Poh CL, Naing MW (2017) Production of recombinant collagen: state of the art and challenges. Engin Bio 1:18-23. doi: 10.1049/enb.2017.0003

Weise A, Rodriguez-Franco M, Timm B, Hermann M, Link S, Jost W, Gorr G (2006) Use of *Physcomitrella patens* actin 5′ regions for high transgene expression: importance of 5′ introns. Appl Microbio Biotech 70:337-345. doi: 10.1007/s00253-005-0087-6

Weise A, Altmann F, Rodriguez-Franco M, Sjoberg ER, Bäumer W, Launhardt H, Kietzmann M, Gorr G (2007) High-level expression of secreted complex glycosylated recombinant human erythropoietin in the Physcomitrella Delta-fuc-t Delta-xyl-t mutant. Plant Biotech J 5:389–401. doi: 10.1111/j.1467-7652.2007.00248.x

Wiedemann G, van Gessel N, Köchl F, Hunn L, Schulze K, Maloukh L, Nogue F, Decker EL, Hartung F, Reski R (2018) RecQ helicases function in development, DNA repair, and gene targeting in *Physcomitrella patens*. Plant Cell 30:717–736. doi: 10.1105/tpc.17.00632

Wilken LR, Nikolov ZL (2012) Recovery and purification of plant-made recombinant proteins. Biotech Adv 30:419–433. doi: 10.1016/j.biotechadv.2011.07.020

Wu L, Shao H, Fang Z, Zhao Y, Cao CY, Li Q (2019) Mechanism and effects of polyphenol derivatives for modifying collagen. ACS Biomat Sci Engin 5:4272–4284. doi: 10.1021/acsbiomaterials.9b00593

Wu K, Li Y, Chen J (2024) Effect of pH on the structure, functional properties and rheological properties of collagen from greenfin horse-faced filefish (*Thamnaconus septentrionalis*) skin. Marine Drugs 22:45. doi: 10.3390/md22010045

Xu X, Gan Q, Clough RC, Pappu KM, Howard JA, Baez JA, Wang K (2011) Hydroxylation of recombinant human collagen type I alpha 1 in transgenic maize co-expressed with a recombinant human prolyl 4-hydroxylase. BMC Biotech 11:69. doi: 10.1186/1472-6750-11-69

Xu S, Gu M, Wu K, Li G (2019) Unraveling the role of hydroxyproline in maintaining the thermal stability of the collagen triple helix structure using simulation. J Phys Chem B 123:7754-7763. doi: 10.1021/acs.jpcb.9b05006

Yang KL, Yu F, Teo GC, Li K, Demichev V, Ralser M, Nesvizhskii AI (2023) MSBooster:
improving peptide identification rates using deep learning-based features. Nat Comm
14:4539. doi: 10.1038/s41467-023-40129-9

Yin J, Hou L, Jiang X, Yang J, He Y, Zhou XK, Zhu XM, Gong AD, Zhu YX, Chen ZY
(2021) Identification and validation of reference genes for quantitative real-time PCR
studies in alligatorweed (*Alternanthera philoxeroides*). Weed Sci 69:404-411. doi:
10.1017/wsc.2021.32

Yu F, Haynes SE, Teo GC, Avtonomov DM, Polasky DA, Nesvizhskii AI (2020) Fast
quantitative analysis of timsTOF PASEF data with MSFragger and IonQuant. Mol Cell
Proteom 19:1575-1585. doi: 10.1074/mcp.TIR120.002048

Yu F, Haynes SE, Nesvizhskii AI (2021) IonQuant enables accurate and sensitive
label-free quantification with FDR-controlled match-between-runs. Mol Cell Proteom
20:100077. doi: 10.1016/j.mcpro.2021.100077

Zhang C, Baez J, Glatz CE (2009a) Purification and characterization of a 44-kDa
recombinant collagen I α 1 fragment from corn grain. J Agric Food Chem 57:880-887.
doi: 10.1021/jf8026205

Zhang C, Baez J, Pappu KM, Glatz CE (2009b) Purification and characterization of a
transgenic corn grain-derived recombinant collagen type I alpha 1. Biotech Prog
25:1660-1668. doi: 10.1002/btpr.257

Zhao Z, Deng J, Fan D (2023) Green biomanufacturing in recombinant collagen
biosynthesis: trends and selection in various expression systems. Biomat Sci 11:5439-
5461. doi: 10.1039/D3BM00724C

Supplementary Information

Supplementary Figure S1 Alignment of the selected coding region (nucleotides 1266–2367) of the human COL3A1 CDS (COL3A1, NM_000090.4) and the codon- and splice site-optimized COL3A1 sequence (COL3A1_opt.) used for generation of collagen-producing Physcomitrella lines

The CDS of the human collagen α1(III) chain (COL3A1) was obtained from NCBI (NM_000090.4). The region coding for the selected recombinant collagen polypeptide is depicted, aligned with the corresponding sequence after *in silico* codon and potential heterosplice sites optimization. Codon optimization according to Physcomitrella codon usage was carried out by Thermo Fisher Scientific. In addition, underrepresented codons (as listed in **Supplementary Table S1**) were substituted with corresponding, overrepresented alternatives using the physCO online tool (available at www.plant-biotech.uni-freiburg.de). To prevent potential heterosplicing, nucleotides within the heterosplicing recognition motif AGGT (HS motif, Top et al. 2021) were silently mutated *in silico*. The resulting optimized sequence (COL3A1_opt.) encodes the original amino acid sequence and was modified exclusively at the nucleotide level.

1473

1474

1475

Supplementary Figure S2 Schematic representation of the pJET1.2-based vector containing the expression construct used to generate recombinant collagen-polypeptide producing Physcomitrella lines

The codon- and spice site optimized collagen polypeptide CDS including the CDS for the aspartic protease signal peptide PpAP1 (Pp6c5_10120V6.1; Schaaf et al. 2004) and an 8xHis-tag were cloned into an pJET1.2-based expression vector containing the Physcomitrella Actin5 (PpActin5) promoter (Weise et al. 2006; Niederau et al. 2024) and the nos terminator (nos_T). For selection purposes this vector additionally contained a hygromycin selection cassette coding for a hygromycin B phosphotransferase (hpt; Decker et al. 2015) under the control of a nos promoter (nos_P) and a nos terminator. Targeted genome integration via homologous recombination was facilitated by a 327 bp long 3´ homologous region of the 3´ UTR of the endogenous actin 5 encoding gene, while the Actin5 promoter sequence serves as 5´ homologous flank. Prior transformation the plasmid was linearized using *Hin*dIII.

1489

1490

1491

Supplementary Figure S3 Uncropped immunodetection images and Coomassie stained SDS-PAGE gel image corresponding to Figure 2

A Corresponds to **Figure 2A** and **B** corresponds to **Figure 2B**.

1495

1496

1497

Supplementary Figure S4 Quantitative analysis of construct copy numbers in selected moss lines

The five selected collagen polypeptide-producing lines and an equally treated WT control were investigated for the numbers of integrated expression constructs by qPCR. Copy numbers were analysed using the primer pairs targeting the Actin5 promotor (Act5) and the collagen CDS (Collagen). Internal normalization to single integration signals was performed with signals obtained by two primer pairs targeting the endogenous single copy CLF gene and single integration signals for the Actin5 promoter were gained from the wild type (WT). Bars represent normalized mean values ± SD from n = 3.

1507

1510

Supplementary Figure S5 Immunodetection from bioreactor culture supernatants, corresponding SDS-PAGE gels, mass spectrometrically determined sequence coverages of the recombinant collagen polypeptide, and uncropped images

A Anti-His antibody-based immunodetection of SDS-PAGE–separated and PVDF-transferred, non-precipitated bioreactor culture supernatants (40 µL per lane) from line C6.1 and the wild type (WT). **B** Coomassie-stained SDS-PAGE gels and corresponding anti-His immunodetection of 1.5 mL acetone-precipitated bioreactor culture supernatants from line C6.1 after 16 days of cultivation, compared to an equally treated WT control. Gel regions corresponding to immunodetection signals (marked as 1-4) were excised and analysed by mass spectrometry. The identified sequence coverages of the recombinant collagen polypeptide are marked in red. **C** Uncropped immunodetection image corresponding to **Supplementary Figure S5 A**. **D** Uncropped SDS-PAGE gel image corresponding to **Supplementary Figure S5 B**. **E** Uncropped immunodetection image corresponding to **Figure 5B** and **Supplementary Figure S5 B**.

1525

1526 **Supplementary Table S1 Underrepresented codons that were exchanged by**
1527 **overrepresented ones in the optimized CDS used for collagen production**
1528 These selections are based the codon usage tables described by Hiss et al. (2017) and
1529 Nakamura et al. (2000).
1530

Amino acid	Underrepresented codon	Overrepresented codon
Cys	TGT	TGC
Glu	GAA	GAG
Phe	TTT	TTC
His	CAT	CAC
Lys	AAA	AAG
Asn	AAT	AAC
Gln	CAA	CAG
Tyr	TAT	TAC

1531

1532

1533 **Supplementary Table S2 Primers used for quantitative PCR**

1534

Primer	Sequence	Target	Experiment
Collagen_qP_F	AGAGAAGGGACCTGCTGGAG	Collagen CDS	qPCR, qRT-PCR
Collagen_qP_R	GGAGATCCAGGCATTCCTCTC	Collagen CDS	qPCR, qRT-PCR
qPCR LWD fwd	CACTGCAGGAGCTGAAATCAATC	LWD CDS	qRT-PCR
qPCR LWD rev	CGTAGTATCTGGAGCTTGGTGGA	LWD CDS	qRT-PCR
c45-tg2F	ACGCACCGGCATCGT	L21 CDS	qRT-PCR
c45-tg2R	TGCTTGTTCATCACGACACCA	L21 CDS	qRT-PCR
pPCLF_5915_qf	AGCAATGTCCGTGCCTACTT	CLF CDS	qPCR
pPCLF_5981_qr	TTGTAAGAATCACTCACCCACAG	CLF CDS	qPCR
pPCLF_7739_qf	GTATTGGCGATCCCACTCTT	CLF CDS	qPCR
pPCLF_7804_qr	GCATAAAATAGGTCACAGATTGAGG	CLF CDS	qPCR
qhpt_f	ATACGAGGTCGCCAACATCT	hpt CDS	qPCR
qhpt_r	TGCCTCCGCTCGAAGTAG	hpt CDS	qPCR
Act5P_qPCR_fwd	GCTTGGTCCGAGGCTATTATT	Actin5 promoter	qPCR
Act5p_qPCR_rev	TAGGTGCAACCCGCTGTT	Actin5 promoter	qPCR

1535

Supplementary Table S3 Quantitation summary of identified hydroxylated prolines in secreted collagen samples

Shown are the proline residues identified across the seven analysed measurements (raw files), including their respective G-X-Y motif and their corresponding amino acid positions in the recombinant collagen polypeptide (Position_Motif). Log_2-transformed peptide intensities were used as quantitative values. These were first normalized to the median intensity within each measurement and subsequently centred to the global median intensity across all measurements. For each identified hydroxyproline or its unmodified counterpart the quantitative values from each corresponding peptide isoform were summed within each measurement (Raw File). The relative proportion of modified versus unmodified prolines per peptide is given as a percentage.

Raw File	Position Motif	Type	Summed Intensity	Total Intensity	Percent
ELITE-RSLC037807	40_GSP	Mod.	20.8633	84.8853	24.58
ELITE-RSLC037807	40_GSP	Unmod.	64.0221	84.8853	75.42
ELITE-RSLC037807	43_GEP	Unmod.	84.8853	84.8853	100.00
ELITE-RSLC037807	49_GLP	Unmod.	84.8853	84.8853	100.00
ELITE-RSLC037807	63_GPA	Mod.	16.1702	16.1702	100.00
ELITE-RSLC037807	66_GPN	Mod.	16.1702	16.1702	100.00
ELITE-RSLC037807	70_GIP	Unmod.	34.5415	34.5415	100.00
ELITE-RSLC037807	75_GPA	Unmod.	35.5944	35.5944	100.00
ELITE-RSLC037807	94_GEP	Unmod.	18.7694	18.7694	100.00
ELITE-RSLC037807	100_GVP	Mod.	18.7694	53.3520	35.18
ELITE-RSLC037807	100_GVP	Unmod.	34.5826	53.3520	64.82
ELITE-RSLC037807	103_GGP	Mod.	18.7694	36.9129	50.85
ELITE-RSLC037807	103_GGP	Unmod.	18.1435	36.9129	49.15
ELITE-RSLC037807	145_GQP	Unmod.	23.2473	23.2473	100.00
ELITE-RSLC037807	153_GPK	Unmod.	23.2473	23.2473	100.00
ELITE-RSLC037807	250_GAP	Mod.	17.6325	17.6325	100.00
ELITE-RSLC037807	255_GPP	Unmod.	20.5607	20.5607	100.00
ELITE-RSLC037807	256_GPP	Unmod.	61.5526	61.5526	100.00
ELITE-RSLC037807	262_GAP	Mod.	38.1931	38.1931	100.00
ELITE-RSLC037807	316_GEP	Unmod.	33.5776	33.5776	100.00
ELITE-RSLC037807	319_GGP	Unmod.	33.5776	33.5776	100.00
ELITE-RSLC037807	325_GVP	Unmod.	33.5776	33.5776	100.00
ELITE-RSLC037809	28_GVP	Mod.	66.4161	139.2935	47.68
ELITE-RSLC037809	28_GVP	Unmod.	72.8774	139.2935	52.32
ELITE-RSLC037809	40_GSP	Mod.	133.3001	529.5811	25.17
ELITE-RSLC037809	40_GSP	Unmod.	396.2810	529.5811	74.83
ELITE-RSLC037809	43_GEP	Unmod.	599.2329	599.2329	100.00
ELITE-RSLC037809	49_GLP	Mod.	58.1106	599.2329	9.70
ELITE-RSLC037809	49_GLP	Unmod.	541.1223	599.2329	90.30
ELITE-RSLC037809	58_GAP	Unmod.	20.2887	20.2887	100.00
ELITE-RSLC037809	63_GPA	Mod.	39.3541	58.2412	67.57
ELITE-RSLC037809	63_GPA	Unmod.	18.8871	58.2412	32.43

ELITE-RSLC037809	66_GPN	Mod.	39.3541	98.2693	40.05
ELITE-RSLC037809	66_GPN	Unmod.	58.9152	98.2693	59.95
ELITE-RSLC037809	70_GIP	Unmod.	176.4821	176.4821	100.00
ELITE-RSLC037809	75_GPA	Unmod.	176.2793	176.2793	100.00
ELITE-RSLC037809	94_GEP	Mod.	23.9800	66.7997	35.90
ELITE-RSLC037809	94_GEP	Unmod.	42.8198	66.7997	64.10
ELITE-RSLC037809	100_GVP	Mod.	23.9800	61.5583	38.95
ELITE-RSLC037809	100_GVP	Unmod.	37.5784	61.5583	61.05
ELITE-RSLC037809	103_GGP	Mod.	23.9800	77.9768	30.75
ELITE-RSLC037809	103_GGP	Unmod.	53.9969	77.9768	69.25
ELITE-RSLC037809	145_GQP	Mod.	44.9735	93.5253	48.09
ELITE-RSLC037809	145_GQP	Unmod.	48.5518	93.5253	51.91
ELITE-RSLC037809	151_GFP	Mod.	21.0235	88.6469	23.72
ELITE-RSLC037809	151_GFP	Unmod.	67.6234	88.6469	76.28
ELITE-RSLC037809	153_GPK	Mod.	21.0235	161.6960	13.00
ELITE-RSLC037809	153_GPK	Unmod.	140.6725	161.6960	87.00
ELITE-RSLC037809	169_GPG	Unmod.	17.9621	17.9621	100.00
ELITE-RSLC037809	172_GPG	Unmod.	17.9621	17.9621	100.00
ELITE-RSLC037809	174_GPQ	Unmod.	17.9621	17.9621	100.00
ELITE-RSLC037809	177_GPP	Unmod.	17.9621	17.9621	100.00
ELITE-RSLC037809	178_GPP	Unmod.	17.9621	17.9621	100.00
ELITE-RSLC037809	241_GAP	Unmod.	16.0661	16.0661	100.00
ELITE-RSLC037809	250_GAP	Mod.	68.8330	84.9600	81.02
ELITE-RSLC037809	250_GAP	Unmod.	16.1270	84.9600	18.98
ELITE-RSLC037809	255_GPP	Unmod.	90.1647	90.1647	100.00
ELITE-RSLC037809	256_GPP	Mod.	26.2192	160.7007	16.32
ELITE-RSLC037809	256_GPP	Unmod.	134.4815	160.7007	83.68
ELITE-RSLC037809	262_GAP	Mod.	93.2291	113.0045	82.50
ELITE-RSLC037809	262_GAP	Unmod.	19.7754	113.0045	17.50
ELITE-RSLC037809	283_GPP	Unmod.	20.1412	20.1412	100.00
ELITE-RSLC037809	285_GPP	Unmod.	20.1412	20.1412	100.00
ELITE-RSLC037809	286_GPP	Unmod.	20.1412	20.1412	100.00
ELITE-RSLC037809	292_GTP	Unmod.	20.1412	20.1412	100.00
ELITE-RSLC037809	298_GMP	Unmod.	20.1412	20.1412	100.00
ELITE-RSLC037809	307_GSP	Unmod.	19.6213	19.6213	100.00
ELITE-RSLC037809	309_GPK	Unmod.	19.6213	19.6213	100.00
ELITE-RSLC037809	316_GEP	Unmod.	289.2604	289.2604	100.00
ELITE-RSLC037809	319_GGP	Mod.	21.3337	290.5687	7.34
ELITE-RSLC037809	319_GGP	Unmod.	269.2350	290.5687	92.66
ELITE-RSLC037809	325_GVP	Mod.	57.9244	309.5610	18.71
ELITE-RSLC037809	325_GVP	Unmod.	251.6366	309.5610	81.29
ELITE-RSLC037809	330_GPR	Unmod.	193.2421	193.2421	100.00
ELITE-RSLC037842	28_GVP	Mod.	16.5849	101.8921	16.28
ELITE-RSLC037842	28_GVP	Unmod.	85.3072	101.8921	83.72
ELITE-RSLC037842	40_GSP	Mod.	39.8071	204.3013	19.48

ELITE-RSLC037842	40_GSP	Unmod.	164.4942	204.3013	80.52
ELITE-RSLC037842	43_GEP	Mod.	19.7206	266.1995	7.41
ELITE-RSLC037842	43_GEP	Unmod.	246.4790	266.1995	92.59
ELITE-RSLC037842	49_GLP	Unmod.	284.1138	284.1138	100.00
ELITE-RSLC037842	63_GPA	Mod.	35.2337	35.2337	100.00
ELITE-RSLC037842	66_GPN	Mod.	35.2337	52.2873	67.38
ELITE-RSLC037842	66_GPN	Unmod.	17.0536	52.2873	32.62
ELITE-RSLC037842	70_GIP	Unmod.	103.9241	103.9241	100.00
ELITE-RSLC037842	75_GPA	Mod.	17.7395	87.3611	20.31
ELITE-RSLC037842	75_GPA	Unmod.	69.6216	87.3611	79.69
ELITE-RSLC037842	103_GGP	Unmod.	19.7747	19.7747	100.00
ELITE-RSLC037842	145_GQP	Unmod.	17.4944	17.4944	100.00
ELITE-RSLC037842	151_GFP	Mod.	17.4944	81.1963	21.55
ELITE-RSLC037842	151_GFP	Unmod.	63.7019	81.1963	78.45
ELITE-RSLC037842	153_GPK	Mod.	17.4944	100.1879	17.46
ELITE-RSLC037842	153_GPK	Unmod.	82.6935	100.1879	82.54
ELITE-RSLC037842	169_GPG	Unmod.	31.8294	31.8294	100.00
ELITE-RSLC037842	172_GPG	Unmod.	31.8294	31.8294	100.00
ELITE-RSLC037842	174_GPQ	Unmod.	31.8294	31.8294	100.00
ELITE-RSLC037842	177_GPP	Unmod.	31.8294	31.8294	100.00
ELITE-RSLC037842	178_GPP	Unmod.	31.8294	31.8294	100.00
ELITE-RSLC037842	250_GAP	Mod.	21.4815	21.4815	100.00
ELITE-RSLC037842	255_GPP	Unmod.	66.0051	66.0051	100.00
ELITE-RSLC037842	256_GPP	Mod.	24.9956	87.4866	28.57
ELITE-RSLC037842	256_GPP	Unmod.	62.4910	87.4866	71.43
ELITE-RSLC037842	262_GAP	Mod.	68.8090	87.4866	78.65
ELITE-RSLC037842	262_GAP	Unmod.	18.6776	87.4866	21.35
ELITE-RSLC037842	282_GPP	Unmod.	17.7921	17.7921	100.00
ELITE-RSLC037842	283_GPP	Unmod.	17.7921	17.7921	100.00
ELITE-RSLC037842	285_GPP	Unmod.	17.7921	17.7921	100.00
ELITE-RSLC037842	286_GPP	Unmod.	17.7921	17.7921	100.00
ELITE-RSLC037842	292_GTP	Unmod.	17.7921	17.7921	100.00
ELITE-RSLC037842	298_GMP	Unmod.	17.7921	17.7921	100.00
ELITE-RSLC037842	316_GEP	Unmod.	81.4029	81.4029	100.00
ELITE-RSLC037842	319_GGP	Unmod.	81.4029	81.4029	100.00
ELITE-RSLC037842	325_GVP	Unmod.	66.5101	66.5101	100.00
ELITE-RSLC037842	330_GPR	Unmod.	31.9191	31.9191	100.00
ELITE-RSLC037844	40_GSP	Unmod.	105.4740	105.4740	100.00
ELITE-RSLC037844	43_GEP	Unmod.	105.4740	105.4740	100.00
ELITE-RSLC037844	49_GLP	Unmod.	85.9872	85.9872	100.00
ELITE-RSLC037844	63_GPA	Mod.	18.1163	18.1163	100.00
ELITE-RSLC037844	66_GPN	Unmod.	34.2999	34.2999	100.00
ELITE-RSLC037844	70_GIP	Mod.	18.1163	51.7510	35.01
ELITE-RSLC037844	70_GIP	Unmod.	33.6348	51.7510	64.99
ELITE-RSLC037844	75_GPA	Unmod.	35.1084	35.1084	100.00

ELITE-RSLC037844	94_GEP	Unmod.	37.5798	37.5798	100.00
ELITE-RSLC037844	100_GVP	Mod.	19.5219	19.5219	100.00
ELITE-RSLC037844	103_GGP	Mod.	19.5219	19.5219	100.00
ELITE-RSLC037844	145_GQP	Mod.	19.4177	44.3263	43.81
ELITE-RSLC037844	145_GQP	Unmod.	24.9086	44.3263	56.19
ELITE-RSLC037844	151_GFP	Unmod.	40.6166	40.6166	100.00
ELITE-RSLC037844	153_GPK	Mod.	19.4177	62.7464	30.95
ELITE-RSLC037844	153_GPK	Unmod.	43.3287	62.7464	69.05
ELITE-RSLC037844	169_GPG	Unmod.	16.1934	16.1934	100.00
ELITE-RSLC037844	172_GPG	Unmod.	16.1934	16.1934	100.00
ELITE-RSLC037844	174_GPQ	Unmod.	16.1934	16.1934	100.00
ELITE-RSLC037844	177_GPP	Unmod.	16.1934	16.1934	100.00
ELITE-RSLC037844	178_GPP	Unmod.	16.1934	16.1934	100.00
ELITE-RSLC037844	250_GAP	Mod.	43.4220	43.4220	100.00
ELITE-RSLC037844	255_GPP	Unmod.	40.4483	40.4483	100.00
ELITE-RSLC037844	256_GPP	Unmod.	86.8307	86.8307	100.00
ELITE-RSLC037844	262_GAP	Mod.	43.1026	83.8703	51.39
ELITE-RSLC037844	262_GAP	Unmod.	40.7677	83.8703	48.61
ELITE-RSLC037844	316_GEP	Unmod.	33.4864	33.4864	100.00
ELITE-RSLC037844	319_GGP	Unmod.	33.4864	33.4864	100.00
ELITE-RSLC037844	325_GVP	Unmod.	33.4864	33.4864	100.00
ELITE-RSLC037846	40_GSP	Mod.	19.0729	126.0361	15.13
ELITE-RSLC037846	40_GSP	Unmod.	106.9632	126.0361	84.87
ELITE-RSLC037846	43_GEP	Mod.	40.7095	177.4290	22.94
ELITE-RSLC037846	43_GEP	Unmod.	136.7195	177.4290	77.06
ELITE-RSLC037846	49_GLP	Unmod.	177.4290	177.4290	100.00
ELITE-RSLC037846	63_GPA	Mod.	57.5090	130.3027	44.13
ELITE-RSLC037846	63_GPA	Unmod.	72.7938	130.3027	55.87
ELITE-RSLC037846	66_GPN	Mod.	54.8535	164.7228	33.30
ELITE-RSLC037846	66_GPN	Unmod.	109.8693	164.7228	66.70
ELITE-RSLC037846	70_GIP	Mod.	41.4313	115.0897	36.00
ELITE-RSLC037846	70_GIP	Unmod.	73.6584	115.0897	64.00
ELITE-RSLC037846	75_GPA	Mod.	41.4313	110.7541	37.41
ELITE-RSLC037846	75_GPA	Unmod.	69.3228	110.7541	62.59
ELITE-RSLC037846	94_GEP	Unmod.	18.3197	18.3197	100.00
ELITE-RSLC037846	103_GGP	Unmod.	18.3197	18.3197	100.00
ELITE-RSLC037846	145_GQP	Mod.	43.6728	94.3200	46.30
ELITE-RSLC037846	145_GQP	Unmod.	50.6472	94.3200	53.70
ELITE-RSLC037846	151_GFP	Mod.	20.9698	20.9698	100.00
ELITE-RSLC037846	153_GPK	Mod.	20.9698	115.2898	18.19
ELITE-RSLC037846	153_GPK	Unmod.	94.3200	115.2898	81.81
ELITE-RSLC037846	169_GPG	Unmod.	17.8969	17.8969	100.00
ELITE-RSLC037846	172_GPG	Unmod.	17.8969	17.8969	100.00
ELITE-RSLC037846	174_GPQ	Unmod.	17.8969	17.8969	100.00
ELITE-RSLC037846	177_GPP	Unmod.	17.8969	17.8969	100.00

ELITE-RSLC037846	178_GPP	Unmod.	17.8969	17.8969	100.00
ELITE-RSLC037846	238_GAP	Unmod.	15.7655	15.7655	100.00
ELITE-RSLC037846	241_GAP	Mod.	15.7655	31.5955	49.90
ELITE-RSLC037846	241_GAP	Unmod.	15.8301	31.5955	50.10
ELITE-RSLC037846	250_GAP	Mod.	15.7655	38.0657	41.42
ELITE-RSLC037846	250_GAP	Unmod.	22.3003	38.0657	58.58
ELITE-RSLC037846	255_GPP	Mod.	22.3003	45.4473	49.07
ELITE-RSLC037846	255_GPP	Unmod.	23.1470	45.4473	50.93
ELITE-RSLC037846	256_GPP	Mod.	22.3003	87.7776	25.41
ELITE-RSLC037846	256_GPP	Unmod.	65.4773	87.7776	74.59
ELITE-RSLC037846	262_GAP	Mod.	45.4473	45.4473	100.00
ELITE-RSLC037846	282_GPP	Unmod.	18.6874	18.6874	100.00
ELITE-RSLC037846	283_GPP	Unmod.	18.6874	18.6874	100.00
ELITE-RSLC037846	285_GPP	Unmod.	18.6874	18.6874	100.00
ELITE-RSLC037846	286_GPP	Unmod.	18.6874	18.6874	100.00
ELITE-RSLC037846	298_GMP	Unmod.	18.6874	18.6874	100.00
ELITE-RSLC037846	316_GEP	Unmod.	124.4596	124.4596	100.00
ELITE-RSLC037846	319_GGP	Unmod.	124.4596	124.4596	100.00
ELITE-RSLC037846	325_GVP	Mod.	32.7884	124.4596	26.34
ELITE-RSLC037846	325_GVP	Unmod.	91.6712	124.4596	73.66
ELITE-RSLC037848	28_GVP	Unmod.	41.7938	41.7938	100.00
ELITE-RSLC037848	40_GSP	Unmod.	228.8501	228.8501	100.00
ELITE-RSLC037848	43_GEP	Mod.	18.8140	250.1121	7.52
ELITE-RSLC037848	43_GEP	Unmod.	231.2981	250.1121	92.48
ELITE-RSLC037848	49_GLP	Unmod.	268.6751	268.6751	100.00
ELITE-RSLC037848	58_GAP	Unmod.	17.1999	17.1999	100.00
ELITE-RSLC037848	63_GPA	Mod.	18.1023	37.4342	48.36
ELITE-RSLC037848	63_GPA	Unmod.	19.3319	37.4342	51.64
ELITE-RSLC037848	66_GPN	Mod.	37.4342	91.2268	41.03
ELITE-RSLC037848	66_GPN	Unmod.	53.7926	91.2268	58.97
ELITE-RSLC037848	70_GIP	Mod.	19.3319	126.5739	15.27
ELITE-RSLC037848	70_GIP	Unmod.	107.2420	126.5739	84.73
ELITE-RSLC037848	75_GPA	Mod.	19.3319	129.3813	14.94
ELITE-RSLC037848	75_GPA	Unmod.	110.0494	129.3813	85.06
ELITE-RSLC037848	103_GGP	Unmod.	21.3252	21.3252	100.00
ELITE-RSLC037848	145_GQP	Mod.	40.3388	108.1789	37.29
ELITE-RSLC037848	145_GQP	Unmod.	67.8401	108.1789	62.71
ELITE-RSLC037848	151_GFP	Unmod.	57.5944	57.5944	100.00
ELITE-RSLC037848	153_GPK	Unmod.	119.7812	119.7812	100.00
ELITE-RSLC037848	169_GPG	Unmod.	31.5013	31.5013	100.00
ELITE-RSLC037848	172_GPG	Unmod.	31.5013	31.5013	100.00
ELITE-RSLC037848	174_GPQ	Unmod.	31.5013	31.5013	100.00
ELITE-RSLC037848	177_GPP	Unmod.	31.5013	31.5013	100.00
ELITE-RSLC037848	178_GPP	Unmod.	31.5013	31.5013	100.00
ELITE-RSLC037848	250_GAP	Mod.	20.6807	20.6807	100.00

ELITE-RSLC037848	255_GPP	Unmod.	64.5775	64.5775	100.00
ELITE-RSLC037848	256_GPP	Mod.	20.6807	115.6182	17.89
ELITE-RSLC037848	256_GPP	Unmod.	94.9376	115.6182	82.11
ELITE-RSLC037848	262_GAP	Mod.	68.8397	68.8397	100.00
ELITE-RSLC037848	282_GPP	Unmod.	20.0323	20.0323	100.00
ELITE-RSLC037848	283_GPP	Unmod.	20.0323	20.0323	100.00
ELITE-RSLC037848	285_GPP	Unmod.	20.0323	20.0323	100.00
ELITE-RSLC037848	286_GPP	Unmod.	20.0323	20.0323	100.00
ELITE-RSLC037848	292_GTP	Unmod.	20.0323	20.0323	100.00
ELITE-RSLC037848	298_GMP	Unmod.	20.0323	20.0323	100.00
ELITE-RSLC037848	307_GSP	Mod.	35.7435	35.7435	100.00
ELITE-RSLC037848	309_GPK	Mod.	35.7435	35.7435	100.00
ELITE-RSLC037848	316_GEP	Unmod.	106.9230	106.9230	100.00
ELITE-RSLC037848	319_GGP	Mod.	17.9221	177.4607	10.10
ELITE-RSLC037848	319_GGP	Unmod.	159.5386	177.4607	89.90
ELITE-RSLC037848	325_GVP	Unmod.	177.4607	177.4607	100.00
ELITE-RSLC037848	330_GPR	Unmod.	56.7676	56.7676	100.00
ORBI-RSLC037282	40_GSP	Unmod.	50.9065	50.9065	100.00
ORBI-RSLC037282	43_GEP	Unmod.	50.9065	50.9065	100.00
ORBI-RSLC037282	49_GLP	Unmod.	50.9065	50.9065	100.00
ORBI-RSLC037282	151_GFP	Unmod.	21.3525	21.3525	100.00
ORBI-RSLC037282	153_GPK	Unmod.	21.3525	21.3525	100.00
ORBI-RSLC037282	169_GPG	Unmod.	16.0640	16.0640	100.00
ORBI-RSLC037282	172_GPG	Unmod.	16.0640	16.0640	100.00
ORBI-RSLC037282	174_GPQ	Unmod.	16.0640	16.0640	100.00
ORBI-RSLC037282	177_GPP	Unmod.	16.0640	16.0640	100.00
ORBI-RSLC037282	178_GPP	Unmod.	16.0640	16.0640	100.00
ORBI-RSLC037282	255_GPP	Unmod.	22.7614	22.7614	100.00
ORBI-RSLC037282	256_GPP	Unmod.	22.7614	22.7614	100.00
ORBI-RSLC037282	262_GAP	Unmod.	22.7614	22.7614	100.00
ORBI-RSLC037282	270_GPP	Unmod.	14.6829	14.6829	100.00
ORBI-RSLC037282	271_GPP	Unmod.	14.6829	14.6829	100.00
ORBI-RSLC037282	273_GPE	Unmod.	14.6829	14.6829	100.00
ORBI-RSLC037282	282_GPP	Unmod.	41.6391	41.6391	100.00
ORBI-RSLC037282	283_GPP	Unmod.	41.6391	41.6391	100.00
ORBI-RSLC037282	285_GPP	Unmod.	60.3819	60.3819	100.00
ORBI-RSLC037282	286_GPP	Unmod.	60.3819	60.3819	100.00
ORBI-RSLC037282	292_GTP	Unmod.	41.6391	41.6391	100.00
ORBI-RSLC037282	298_GMP	Unmod.	60.3819	60.3819	100.00

1548