New formula and conversion factor to compute tree species basic wood density from a global wood technology database

Ghislain Vieilledent[⋆,1,2,3]   Fabian Jörg Fischer[4]

Jérôme Chave[4]   Daniel Guibal[5,6]

Patrick Langbour[5,6]   and   Jean Gérard[5,6]

[⋆] Corresponding author: ghislain.vieilledent@Cirad.fr
[1] Cirad, UPR Forêt et Sociétés, F-34398 Montpellier, France
[2] Forêt et Sociétés, Univ Montpellier, Cirad, Montpellier, France
[3] Joint Research Centre of the European Commission, Bio-economy unit, I-21027 Ispra, Italy
[4] UMR 5174 Laboratoire Evolution et Diversité Biologique, Université Paul Sabatier, CNRS, IRD, Toulouse, France
[5] Cirad, UPR BioWooEB, F-34398 Montpellier, France
[6] BioWooEB, Univ Montpellier, Cirad, Montpellier, France

Abstract

Basic wood density is an important ecological trait for woody plants. It is used to characterize species performance and fitness in community ecology, and to compute tree and forest biomass in carbon cycle studies. While wood density has been historically measured at 12% moisture for construction purpose, it is convenient to convert this measure to basic wood density, i.e. the ratio of dry mass over green volume. Basic wood density can then be used to compute tree dry biomass from living tree volume.

Here, we show that previous conversion factors used to convert densities at 12% moisture into basic wood densities are inconsistent. We derive a new, exact formula to compute the basic wood density D_b from the density at moisture content w denoted D_w, the fibre saturation point S, and the volumetric shrinkage coefficient R. We estimated a new conversion factor using a global wood technology database where values to use this formula are available for 4022 trees collected in 63 countries (mostly tropical) and representing 872 species.

Based on theory and data, we found that basic wood density could be inferred from the density at 12% moisture using the following formula: $D_b = 0.828 D_{12}$. This value of 0.828 provides basic wood density estimates 4-5% smaller than values inferred from previous methods.

This new conversion factor should be used to derive basic wood densities in global wood density databases. This would prevent overestimating global forest carbon stocks and allow predicting better tree species community dynamics from wood density.

Keywords: basic wood density, biomass, carbon stock, fibre saturation point, forest dynamics, functional trait, tree species, tropical forest, wood specific gravity

1 Introduction

Wood density of woody plant is a key functional trait (Chave *et al.*, 2009; Violle *et al.*, 2007). It helps understand the functionning of forest ecosystems both in terms of carbon sequestration (Chave *et al.*, 2005; Vieilledent *et al.*, 2012) and community dynamics (Díaz *et al.*, 2016; Kunstler *et al.*, 2016; Westoby & Wright, 2006). In carbon cycle research, tree wood-density is used to compute forest carbon stock and assess the role of forest in mitigating climate-change (Pan *et al.*, 2011; Vieilledent *et al.*, 2016) or evaluate the impact of deforestation on climate (Achard *et al.*, 2014). In community ecology, wood density reflects a trade-off between growth potential and mortality risk from biomechanical or hydraulic failure (Díaz *et al.*, 2016). Fast-growing, short-lived species tend to have a lower wood density while slow-growing, long-lived species tend to have a higher wood density (Chave *et al.*, 2009). In wood technology, most physical and mechanical properties of wood (strength, stiffness, porosity, heat transmission, yield of pulp per unit volume, etc.) are closely related to wood density (Sallenave, 1955; Shmulsky & Jones, 2011; Thibaut *et al.*, 2001). This explains why wood density has been one of the first wood characteristic to be measured by scientists in forestry institutes.

Wood density has been originally measured at ambient air moisture after air drying. Thereafter, wood density has been measured at fixed moisture content, such as 15% or 12%, this last value now being an international standard (Sallenave, 1955). In temperate countries, construction wood is at equilibrium with ambient air at an average moisture close to 12%. Wood density at 12% moisture is the ratio between the mass and volume of a wood sample at 12% moisture, and is expressed in g/cm^3. In the past, this measure was also commonly reported in the British literature in pounds per cubic foot ($1 \ g/cm^3 = 62.427 \ lb/ft^3$) (Reyes *et al.*, 1992; Sallenave, 1971). In carbon cycle research and ecology, the most useful metric is the basic wood density, the ratio between oven-dry mass (at

0% moisture) and green volume (water-saturated wood volume) in g/cm³. This trait is

sometimes referred to as wood specific gravity (abbreviated WSG). Both terms describe

the same quantity but wood specific gravity is usually the ratio between the mass of a

given volume of wood and the mass of the same volume of water, and is therefore unitless

(Williamson & Wiemann, 2010). Here we use the term "basic wood density". Basic wood

density can be directly used to compute tree dry biomass and carbon stock from a standing

tree volume estimated using an allometric equation (Brown, 1997; Chave *et al.*, 2005, 2014;

Vieilledent *et al.*, 2012). For example, Chave *et al.* (2014) have estimated the following

pantropical tree biomass allometric equation: $AGB = 0.0673 \times (\rho D^2 H)^{0.976}$ with AGB the

tree dry aboveground biomass in kg, D the tree diameter at 1.30 m in cm, H the tree height

in m and ρ the basic wood density in g/cm³. Tree dry biomass can then be converted to

carbon stock using the IPCC default carbon fraction of 0.47 (McGroddy *et al.*, 2004).

Different methods have been used to convert measures of wood density at 12% moisture

(D_{12}), which are often available in forestry institute databases, into basic wood density

(D_b). Based on basic wood density data and air-dry wood density data (supposedly close

to 12% moisture) for 379 tropical species or genera (Chudnoff, 1984), Reyes *et al.* (1992)

have proposed a linear regression between D_b and D_{12} (Eq. 1).

(1) $$D_b = 0.0134 + 0.800 D_{12}$$

71 This relationship has been used to estimate the basic wood densities of 223 species in

72 Reyes *et al.* (1992), successively reported in Brown (1997), IPCC (2006) and Zanne *et al.*

73 (2009). Sallenave (1971) has proposed another formula to compute basic wood density from

74 the wood density at 12% moisture (Eq. 2). In this formula, d is a density conversion factor

75 per 1% change in moisture content denominated "hygroscopicity" by Sallenave (1971), S is

the fibre saturation point (moisture content S in % at which wood volume starts decreasing in the drying process), and ν is the variation in volume on a dry basis per 1% change in moisture content (in %/%). The values of d, ν, and S vary between species and individual trees. Sallenave (1955; 1964; 1971) published values of D_{12}, d, ν, and S for 1893 trees sampled worldwide in tropical forests.

$$(2) \qquad D_b = \frac{D_{12} - 12d}{1 + (\nu/100)(S - 12)}$$

Using Sallenave's data and formula, it is possible to compute $D_{b,i}$ for each wood sample i and estimate the conversion factor α_{12} between wood density at 12% moisture and basic wood density from the following statistical model: $D_{b,i} = \alpha_{12} D_{12,i} + \varepsilon_i$, assuming a normal error term $\varepsilon_i \sim \mathcal{N}ormal(0, \sigma^2)$. Using the wood samples of the Sallenave data-set, Chave *et al.* (2006) obtained a value of 0.872 for the conversion factor α_{12} between D_{12} and D_b. Several studies have since used Sallenave's method to derive conversion factors for particular sets of species (Muller-Landau, 2004) or to convert wood density at a particular moisture content w into basic wood density (Bastin *et al.*, 2015; Chave *et al.*, 2009; Swenson & Enquist, 2007) by extending Sallenave's original formula assuming that $D_b = (D_w - wd)/(1 + (\nu/100)(S - w))$. The resulting conversion factor was close to 0.872. Notably, Chave *et al.* (2009) used a value of 0.861 (see supplementary material of the cited reference) to convert any wood density between 10-18% moisture content into basic wood density. The estimated basic wood densities were included in the Global Wood Density Database, a large global compilation of wood density data (Chave *et al.*, 2009; Zanne *et al.*, 2009). This database combines measured (40% of the data) and inferred (60% of the data) basic wood densities. It has been extensively used to compute forest biomass and carbon stock with the aim of studying the role of forest in the global carbon cycle (Avitabile *et al.*, 2016;

Baccini *et al.*, 2012, 2017; Saatchi *et al.*, 2011; Vieilledent *et al.*, 2016) or address questions

in functional ecology (Baraloto *et al.*, 2010; Chave *et al.*, 2009; Kunstler *et al.*, 2016).

Simpson (1993) proposed a simplified formula to compute wood density at any moisture

content from basic wood density. With this formula, the relationship only depends on the

moisture content w: $D_w = D_b(1 + w/100)/(1 - 0.265aD_b)$, with $a = 1 - w/30$. Simpson's

formula can be inverted to compute D_b from D_w (Eq. 3).

$$(3) \qquad\qquad D_b = 1/(0.265a + (100 + w)/(100D_w))$$

Two assumptions were made to derive this formula, (i) the fibre saturation point S can

be approximated to 30% for all tree species, and (ii) the total volumetric shrinkage R_T (in

%) from S to 0% moisture content is proportional to the basic wood density D_b, and can

be approximated by the following relationship (Stamm, 1964): $R_T/100 = 0.265D_b$.

Because relationships proposed by Reyes *et al.* (1992), Sallenave (1971) and Simpson

(1993) give significantly different estimates of the basic wood density for a same value of

wood density at 12% moisture, it is important to further test their underlying theories. In

this study, we present a new and exact formula to convert wood density at any moisture

content into basic wood density. The formula is derived from the definitions of the fibre

saturation point and the volumetric shrinkage coefficient. We compare this new formula

with formulas provided by Reyes, Sallenave and Simpson, and explain why they differ.

We combine our theoretical formula with the latest version of a wood technology database

compiled by Cirad (the French agricultural research and international cooperation orga-

nization) to estimate a new conversion factor between density at 12% moisture and basic

wood density. We finally discuss the consequences of this new conversion factor in carbon

cycle research and ecology.

2   Materials and Methods

2.1   The Cirad wood technology database

2.1.1   A global database including 872 tree species

The Cirad wood technology database includes data from 4022 trees. Tree species names (latin binomial) were first spell-checked with the Global Names Resolver available in the `taxize` R package (Chamberlain & Szocs, 2013) using The Encyclopedia of Life, The International Plant Names Index, and the Tropicos databases as references. Then, we searched for synonyms in the list of species names and corrected the species names when necessary using The Plant List version 1.1 (http://www.theplantlist.org) as reference. We used the `Taxonstand` R package (Cayuela *et al.*, 2017) to do so. Taxonomic families were retrieved from updated species names using The Plant List. Trees belong to 1010 taxa from 484 genera and 94 taxonomic families. Most of the taxa (872) were identified up to the species level, with varieties and subspecies combined. Out of the 872 species names, 832 were "accepted" species names and 40 were "unresolved", according to The Plant List. The rest of the taxa (138) were identified up to the genus level. The dataset includes trees from 63 countries but the major part of the trees come from 13 tropical countries (countries with more than 20 tree species) mostly in South America, Africa and in Oceanic islands (Tab. 1 and Fig. 1). Sallenave was working for a tropical forestry institute now part of Cirad, the database is thus the direct continuation and extension of Sallenave's work.

2.1.2   Measuring wood mass, moisture content, and volume

The volume V_w and mass m_w of a wood sample depend on its water content w. The moisture content of wood is a function of both relative humidity and temperature of ambient air (Hailwood & Horrobin, 1946). In the Cirad database, wood volume and mass measurements were done in the same laboratory following the French standard AFNOR NF B51-005

(09/1985). Wood samples are cubes of about 20 mm side ($\pm$ 0.5 mm). To measure V_w and m_w, wood samples were put under controled and fixed atmospheric conditions to reach a water content w. Wood samples were supposed to be stabilized when their variation in mass (in g) after four hours was less than 0.5%.

Wood mass m_w (in g) was measured with a 0.01 g precision balance. The exact moisture content w (in %) of a wood sample is defined as a percentage of the dry mass, $w = 100(m_w - m_0)/m_0$, with m_0 being the mass of the wood sample at the anhydrous state and m_w being the mass of the wood at moisture content w.

Wood volume V_w (in cm^3) was measured with three different methods. For wood samples of irregular dimensions, we used a mercury volumenometer, or the water displacement method based on Archimede's principle (Williamson & Wiemann, 2010). The mercury volumenometer for volume measurement was progressively abandoned from the end of years 90s due to mercury toxicity. For perfectly rectangular parallelepiped or cubic wood samples, a stereometric method was used measuring the wood cube size in the three dimensions using a digital caliper having a 0.02 mm precision. Using one of these three methods, wood volume was measured with a precision <0.003 cm^3.

2.1.3 Measuring fibre saturation point, volumetric shrinkage coefficient, and wood density at 12% moisture

The fibre saturation point S (in %) is the water content above which the wood volume does not increase (Skaar, 1988). This is also the point in the wood drying process at which the only remaining water is that bound to the cell walls, no free water remaining in the cell cavities. Further drying of the wood results in the strengthening of the wood fibres, and is usually accompanied by shrinkage (Skaar, 1988).

To estimate the fibre saturation point S, we first measured wood volume at the saturated state V_S using the water displacement method. To reach a state saturated in water,

whith $w > S$, wood samples were autoclaved, subjected to one hour of vacuum (to accelerate water impregnation) and then soaked in water during 15 hours at 5 bar pressure. Then, wood samples were stabilized at four decreasing moisture contents w until reaching the anhydrous state. First, wood samples were put in a stove at 30°C temperature and 85% humidity to reach a moisture content close to 18%. Second, wood samples were put in an air-conditioned room at 20°C temperature and 65% humidity to reach a moisture content close to 12%. Third, they were put in a stove at 20°C temperature and 50% humidity to reach a moisture content close to 9%. Fourth, they were put in a stove at 103°C to reach the anhydrous state. Wood mass m_w and wood volume V_w were measured at each of the four stabilized stages. The exact water content w at the three stabilized states previous to the anhydrous state was computed from the mass m_w and the anhydrous mass m_0. Three volumetric shrinkage values $\Delta V/V = 100(V_S - V_w)/V_S$ were computed between the saturated state and the three other stabilized states. The fibre saturation point S was defined as the intercept of the linear model $w = S + b \times \Delta V/V$ (Stamm, 1964). To minimise the errors in estimating S, only the relationships with a coefficient of determination $r^2 > 98\%$ were considered.

The volumetric shrinkage coefficient R (in %/%) is the variation in volume per 1% change in water content. The total volumetric shrinkage R_T of the wood samples from the saturated state to the anhydrous state (in %) was computed from V_S and V_0: $R_T = 100(V_S - V_0)/V_S$. Then, the volumetric shrinkage coefficient R (in %/%) was estimated from R_T and the fibre saturation point S: $R = R_T/S$. This definition of the volumetric shrinkage coefficient differs from the one used in Sallenave's work. Sallenave used the anhydrous volume V_0 as the reference volume and ν was defined as $\nu = B/S$ with $B = 100(V_S - V_0)/V_0$. Because this definition corresponded to wood swelling and not to wood shrinkage, it has been changed when compiling the new Cirad wood technology database. Sallenave's B values were converted to R_T values with the following formula derived from the definitions

$_{195}$ of B and R_T: $R_T = 100(1 - 1/(B/100 + 1))$.

$_{196}$ Wood density at 12% moisture (D_{12} in g/cm³) was obtained computing the ratio m_w/V_w

$_{197}$ with w close to 12% moisture (when wood samples were stabilized at 20°C temperature

$_{198}$ and 65% humidity). Because the moisture content w was not exactly 12%, densities were

$_{199}$ initially corrected using the "hygroscopicity" term d defined by Sallenave and the following

$_{200}$ formula $D_{12} = D_w - (w - 12)d$ (Sallenave, 1971). This correction affected only the third

$_{201}$ decimal of the wood density value, so it was progressively abandonned.

$_{202}$ Mean values for S, R and D_{12} for each tree were estimated using >10 wood sam-

$_{203}$ ples taken at various positions in the trunk. Definitions and units of wood physical and

$_{204}$ mechanical properties used in the present study are all summarized in Supp. Info. S1.

$_{205}$ 2.2 Model relating D_w and D_b

$_{206}$ Using D_w (the wood density at moisture content w), R (the newly defined volumetric

$_{207}$ shrinkage coefficient), and S (the fibre saturation point), we derived a new relationship

$_{208}$ linking the basic wood density D_b with D_w. We first considered the relationship bewteen

$_{209}$ V_S and V_w. The volumetric shrinkage coefficient R (variation in volume per 1% change in

$_{210}$ water content) is defined as $R = (100\Delta V)/(V\Delta w)$. Let's consider a wood sample saturated

$_{211}$ in water ($w = S$) that would be dried until reaching a water content w. The volume of the

$_{212}$ wood sample would decrease (wood shrinkage) and R can be written as:

$$(4) \qquad R = (100(V_S - V_w))/(V_S(S - w))$$

$_{213}$ Using Eq. 4, we can express V_S as a function of V_w, R, S and w:

$$(5) \qquad\qquad V_S = V_w/(1 - (R/100)(S - w))$$

We then considered the relationship between m_0 and m_w. Water content w is defined as $w = 100(m_w - m_0)/m_0$. Using this definition, we expressed m_0 as a function of m_w and w:

$$(6) \qquad\qquad m_0 = m_w/(1 + w/100)$$

Following the definition of the basic wood density D_b ($D_b = m_0/V_S$, D_b), and replacing V_S and m_0 by their expressions in Eq. 5 and Eq. 6 respectively, we obtained $D_b = (m_w/(1 + w/100))((1 - (R/100)(S - w))/V_w)$. Given that $D_w = m_w/V_w$, we found the following relationship between D_b and D_w:

$$(7) \qquad\qquad D_b = \frac{1 - (R/100)(S - w)}{1 + w/100} D_w$$

For each individual tree i, we used this new formula to compute the basic wood density $D_{b,i}$ from the values of $D_{12,i}$ (wood density at 12% moisture), R_i, and S_i reported for 3832 trees in the Cirad wood technology database (190 trees had no values for R or S). We then estimated the parameters of a statistical linear regression model linking $D_{b,i}$ to $D_{12,i}$, where parameter α_{12} corresponds to the conversion factor between D_{12} and D_b (Eq. 8).

$$(8) \qquad\qquad D_{b,i} = \alpha_{12} D_{12,i} + \varepsilon_i, \varepsilon_i \sim N(0, \sigma^2)$$

We extended this approach to compute an additional conversion factor α_{15} between D_{15}, the wood density at 15% moisture (which was the French standard before international conventions fixed the moisture content at 12%, see Sallenave (1955)) and D_b. We inverted Eq. 7 to compute $D_{15,i}$ from previously computed $D_{b,i}$ values and estimated the slope of a linear regression model linking $D_{b,i}$ to $D_{15,i}$.

2.3   Comparison with the Global Wood Density Database

The Global Wood Density Database (GWDD, http://hdl.handle.net/10255/dryad. 235) provides wood densities for 8412 species from around the world (Chave *et al.*, 2009; Zanne *et al.*, 2009). The GWDD and Cirad wood density databases share common wood samples and measurements from Sallenave (1955, 1964, 1971). We quantified the amount of novel information in the Cirad wood density database. We identified and computed (i) the number of species studied by Sallenave and present in the two databases, (ii) the number of species common to the two databases but not studied by Sallenave (for which wood density values were independent), and (iii) the number of species in the Cirad database not present in the GWDD. For the species shared between databases, and with independent measurements, we compared the mean basic wood density values in the two databases. To quantify the differences between the two databases, we computed the Pearson correlation coefficient between the two values, a measure of the linear correlation (dependence), and the coefficient of variation (in %) between the two databases. The coefficient of variation is the ratio of the standard deviation of the differences between density values in the two databases divided by the mean basic wood density in the Cirad database. It is a measure of the average difference between the wood density values in the two databases. Finally, we quantified the bias (in %) in the GWDD compared to the Cirad database. This bias was defined as the mean difference between density values in the two databases divided by the mean basic wood density in the Cirad database.

3 Results

3.1 Relationship between D_b and D_w

The linear regression model linking D_b and D_{12} had a coefficient of determination $r^2 = 0.999$ and a residual standard error of 0.015 g/cm3 (Fig. 2). We estimated a new conversion factor $\alpha_{12} = 0.828$ based on the slope estimate of the linear regression. Thus, the basic wood density can be estimated from wood density at 12 % moisture from Eq. 9.

$$(9) \qquad\qquad [D_b]_{\text{est}} = 0.828 D_{12}$$

With this new conversion factor, we were able to compute the basic wood density D_b from D_{12} for the 190 trees without values for R or S. At the species level, when accounting for all the trees in the data-base, D_b ranged from 0.191 to 1.105 g/cm^3 (Tab. 2).

We also observed that R, S and D_{12} were not independant (Fig. 3). Thus, it is not possible to directly estimate the conversion factor from the means of R and S on the basis of the formula we derived to link basic wood density to wood density at moisture content w (Eq. 7). Instead, the conversion factor estimated with the linear regression model must be used.

The linear regression model linking D_b and D_{15} had a coefficient of determination $r^2 = 0.999$ and a residual standard error of 0.014 g/cm3. We estimated a conversion factor $\alpha_{15} = 0.819$ between D_{15} and D_b.

3.2 Comparison with the Global Wood Density Database

Out of the 872 species in the Cirad wood density database, we identified 260 species that have been measured by Sallenave (1955, 1964, 1971) and for which one or more samples were

₂₇₁ already included in the GWDD. For these species, the Cirad database provides additional

₂₇₂ information compared to the GWDD, with values for R, S, and D_{12}. We also identified 411

₂₇₃ species common to the two databases but for which measurements of D_b were completely

₂₇₄ independant. For these species, the Cirad wood density database also provides R, S, and

₂₇₅ D_{12} values. Finally, we identified 201 original species in the Cirad database which were

₂₇₆ not present in the GWDD. Both R and S were highly variable among species (Tab. 2). In

₂₇₇ particular, S ranged from 17 to 41% with a mean of 27.93% and a standard deviation of

₂₇₈ 4.06%.

₂₇₉ Using the independent measurements for the 411 common species in the two databases,

₂₈₀ we estimated a Pearson correlation coefficient of 86% and a coefficient of variation of 13.69%

₂₈₁ (Fig.4). We also observed that, on average, D_b values in the GWDD were 3.05% higher

₂₈₂ compared to D_b values in the Cirad database.

4 Discussion

4.1 Relationship between D_b and D_{12}

We found a new value of 0.828 for the conversion factor between the wood density at 12% moisture and the basic wood density. This value is 5% lower compared to the value of 0.872 used by Chave *et al.* (2006) and based on Sallenave's data and formula. To compare this value with the results obtained by Reyes *et al.* (1992), we derived the expectation $\mathbb{E}(D_b/D_{12})$ from Reyes' formula $D_b = 0.0134 + 0.800D_{12}$. We obtained $\mathbb{E}(D_b/D_{12}) = 0.0134 \times \mathbb{E}(1/D_{12}) + 0.800$. This led to an estimate of 0.821 for the conversion factor. This value is much closer to our value of 0.828 than the value of 0.872 (Chave *et al.*, 2006).

Why was the conversion factor overestimated in Chave *et al.* (2006)? As calculations were based on the formula from Sallenave (1971), we decided to re-examine its derivation. When looking more closely at Sallenave's own example page 11 in Sallenave (1971), a discrepancy became apparent. For the African tree species *Khaya ivorensis* (with $D_{12} = 0.57$ g/cm³, $d = 0.0030$, $S = 24\%$, $\nu = 0.46$ and measured $D_b = 0.483$ g/cm³), Sallenave's formula (Eq. 2) led to an estimate of 0.506 g/cm³ for the basic wood density. Our formula, on the other hand, gave an estimate of 0.484 g/cm³ which is much closer to the measured basic wood density value of 0.483 g/cm³. Given these findings, we suspected an error or approximation in Sallenave's formula.

Based on the definition of the basic wood density $D_b = m_0/V_S$ and the definition of the parameters used by Sallenave (1971), we demonstrate that Sallenave's formula is true only if $V_0 = V_{12}$ (Eq. 10 and demonstration in Supp. Info. S2). This, however, is a too strong assumption if we want to estimate an accurate conversion factor.

$$(10) \qquad D_b = \frac{V_0[D_{12} - 12d]}{V_{12}[1 + (\nu/100)(S - 12)]}$$

We thus recommend the use of the new formula we derived in this study (Eq. 7) to

compute individual basic wood density D_b from D_{12}, the wood density at 12% moisture,

when R and S are available. This formula is more appropriate than Sallenave's one. It

does not only avoid making the strong assumption that $V_0 = V_{12}$, but also needs only two

parameters to compute D_b compared to Sallenave's formula which also includes a third

parameter, the "hygroscopicity" d. Moreover, the new formula, unlike Sallenave's one,

implies $D_0 = 0$ when $D_{12} = 0$, which is physically consistent. Finally, the new formula we

derived in this study is more generic than Reyes' and Sallenave's original formula. It can

be used, together with the data-set on wood properties we provide as supplementary data,

to derive conversion factors between D_b and density D_w at any water content w under the

fibre saturation point S.

We also demonstrate that our formula is more appropriate than Simpson's one. As-

sumptions used to derive Simpson's formula are not supported by our data. In the Cirad

database, the fibre saturation point S is highly variable between species and cannot be

assumed constant at 30%. We also estimated a coefficient of 0.201 for the relationship be-

tween $R_T/100$ and D_b, a value different from the coefficient of 0.265 suggested by Stamm

(1964). We estimated a mean error (coefficient of variation of the root-mean-square-error)

of 26% for $R_T/100$ predictions, suggesting that $R_T/100$ cannot be precisely estimated from

D_b using a simple correlation coefficient (see also Fig. 3). As a consequence, Simpson's

formula leads to a large under-estimation of basic wood densities for $D_{12} > 0.7$ g/cm^3

(Fig. 2).

If only D_{12} and no other measurement is available, we recommend the use of the value

0.828 for the conversion factor to compute the basic wood density D_b. We also recommend

this value of 0.828 over the value of 0.821 obtained with Reyes' relationship. The conversion

factor of 0.828 is based on a larger and more consistent database than the one used by

Reyes *et al.* (1992). Database used by Reyes combined density data at the species and

genera level and included air-dry densities not stabilized at 12% (Chudnoff, 1984).

4.2   Additional value of the Cirad wood density database

Using the new formula we obtained in this study (Eq. 7), the new estimated conversion factor 0.828, and the Cirad database, we estimated the basic wood density of 4022 trees belonging to 872 species (1010 taxa), 484 genus and 94 families. Compared with the Global Wood Density Database (Zanne *et al.*, 2009), we provide basic wood density for 201 new tree species. Most of the 872 species come from 13 oceanic tropical islands or countries in tropical America, Africa and Asia. We underline that the Cirad database is of high quality with regard to the measurements taken by experienced staff and following a consistent standard (NF-B51). Thus, the uncertainty regarding basic wood-densities computed at the individual tree level is low, at about 0.01 g/cm^3.

In the Cirad wood density database, in addition to wood densities, the fibre saturation point S and the volumetric shrinkage coefficient R are provided for each tree. The fibre saturation point S is an essential wood characteristic that can be used, in combination with the fresh volume, the fresh mass and the dry mass, to estimate the volume of water for each of the three bulk phases ("solid" or bound water, liquid and gas) in a tree (Berry & Roderick, 2005). The volume of "solid" water is an essential plant functional trait as it determines wood strength and constraints on plant architecture (Niklas, 1993), as is the volume of liquid water which is the ultimate source of the biochemical activity in living plants (Berry & Roderick, 2005).

Tree wood characteristic values in the Cirad database are the average of >10 wood samples taken at various position in the trunk. Thus, wood characteristic values at the tree level integrate intra-individual variability (for example the difference in wood density values for the same tree which depends on the position in the trunk (Bastin *et al.*, 2015)). But because the Cirad database provides wood characteristics for individual trees, it can

be used to compute both intra-specific and inter-specific trait variability. Intra-specific trait variability, due to genetic variability and phenotypic plasticity, participates in determining species fitness and community assemblages (Albert *et al.*, 2011; Courbaud *et al.*, 2012; Roughgarden, 1979). The Cirad database could also help quantify phylogenetic conservatism and divergences of wood densities in tree species (Flores & Coomes, 2011).

4.3 Consequences of the new conversion factor value for ecological studies

This new value of 0.828 for the conversion factor has significant implications for the study of the role of forest in the global carbon cycle. The error on the conversion factor between wood density at 12% moisture and basic wood density propagates to forest carbon stock. Combined with biomass allometric equations available in the litterature (Chave *et al.*, 2005, 2014; Vieilledent *et al.*, 2012), these wood density values have been used to compute forest carbon maps globally (Avitabile *et al.*, 2016; Baccini *et al.*, 2012, 2017; Saatchi *et al.*, 2011). About 60% of the basic wood densities in the Global Wood Density Database have been estimated with an overestimated conversion factor. On the basis of 411 tree species, we showed that the GWDD overestimates wood densities by +3.05% on average. It is hard to quantify precisely the consequences of this bias on forest carbon stock estimates as it depends on relative species abundance in the forest and relative tree size distribution between species. However, if dominant species (in terms of size and abundance) have an overestimated wood density, due to the use of an inaccurate conversion factor (0.872 or 0.861 in (Chave *et al.*, 2009, 2006) against 0.828 in our study), it can potentially lead to an overestimation of 4-5% of the forest biomass and carbon stock. We are currently in the process of updating the GWDD and the present study provides a firm basis for this revision.

This study will also provide a firmer basis for future ecological research on wood density as a functional trait. Indeed, wood density is often considered as a key tree functional trait determining species performance and fitness (Baraloto *et al.*, 2010; Chave *et al.*, 2009; Díaz *et al.*, 2016; Kunstler *et al.*, 2016). For example, Kunstler *et al.* (2016) have demonstrated that values of wood density explained the competition outcome between pairs of tree species at the global scale. Using a wood density database with unbiased values of basic wood densities would allow to properly estimate species difference with regards to this trait and predict better the dynamics of tree species community.

5   Acknowledgements

Authors warmely thank all the researchers, technicians and students who have intensively and accurately measured wood properties of thousands of trees and hundreds of species from the tropical forests at the *"Centre Technique Forestier Tropical"* and Cirad since the 1950s. They thank in particular Pierre Sallenave who made a considerable contribution to research in describing protocols and compiling data on wood properties in his three volumes (Sallenave, 1955, 1964, 1971). GV was funded by Cirad and through the European Commission ReCaREDD project at the Joint Research Center. This work has benefitted from *"Investissement d'Avenir"* grants managed by Agence Nationale de la Recherche (CEBA: ANR-10-LABX-25-01; TULIP: ANR-10-LABX-0041).

6   Authors' contribution

GV, FF, JC, and JG conceived the ideas and designed methodology; DG, PL, and JG collected the data; GV and FF analysed the data; GV led the writing of the manuscript. All authors contributed critically to the drafts and gave final approval for publication.

7   Data accessibility

Data (including the Cirad wood density database) and R script associated to the present study have been archived on the Cirad Dataverse research data repository (`http://dx.doi.org/10.18167/DVN1/KRVF0E`) (Vieilledent *et al.*, 2018).

References

Achard, F., Beuchle, R., Mayaux, P., Stibig, H.J., Bodart, C., Brink, A., Carboni, S., Desclée, B., Donnay, F., Eva, H.D., Lupi, A., Raši, R., Seliger, R. & Simonetti, D. (2014) Determination of tropical deforestation rates and related carbon losses from 1990 to 2010. *Global Change Biology*, **20**, 2540–2554.

Albert, C.H., Grassein, F., Schurr, F.M., Vieilledent, G. & Violle, C. (2011) When and how should intraspecific variability be considered in trait-based plant ecology? *Perspectives in Plant Ecology, Evolution and Systematics*, **13**, 217–225.

Avitabile, V., Herold, M., Heuvelink, G., Lewis, S.L., Phillips, O.L., Asner, G.P., Armston, J., Ashton, P.S., Banin, L., Bayol, N. *et al.* (2016) An integrated pan-tropical biomass map using multiple reference datasets. *Global change biology*.

Baccini, A., Goetz, S.J., Walker, W.S., Laporte, N.T., Sun, M., Sulla-Menashe, D., Hackler, J., Beck, P.S.A., Dubayah, R., Friedl, M.A., Samanta, S. & Houghton, R.A. (2012) Estimated carbon dioxide emissions from tropical deforestation improved by carbon-density maps. *Nature Climate Change*, **2**, 182–185.

Baccini, A., Walker, W., Carvalho, L., Farina, M., Sulla-Menashe, D. & Houghton, R.A. (2017) Tropical forests are a net carbon source based on aboveground measurements of gain and loss. *Science*.

Baraloto, C., Timothy Paine, C.E., Poorter, L., Beauchene, J., Bonal, D., Domenach, A.M., Hérault, B., Patiño, S., Roggy, J.C. & Chave, J. (2010) Decoupled leaf and stem economics in rain forest trees. *Ecology Letters*, **13**, 1338–1347.

Bastin, J.F., Fayolle, A., Tarelkin, Y., Van den Bulcke, J., de Haulleville, T., Mortier, F., Beeckman, H., Van Acker, J., Serckx, A., Bogaert, J. & De Cannière, C. (2015) Wood specific gravity variations and biomass of central african tree species: The simple choice of the outer wood. *PLOS ONE*, **10**, 1–16.

Berry, S.L. & Roderick, M.L. (2005) Plant-water relations and the fibre saturation point. *New Phytologist*, **168**, 25–37.

Brown, S. (1997) Estimating biomass and biomass change of tropical forests: a primer. Technical report, FAO Forestry Paper 134, Rome, Italy.

Cayuela, L., Stein, A. & Oksanen, J. (2017) *Taxonstand: Taxonomic Standardization of Plant Species Names*. R package version 2.1.

Chamberlain, S. & Szocs, E. (2013) taxize - taxonomic search and retrieval in R. *F1000Research*.

Chave, J., Andalo, C., Brown, S., Cairns, M.A., Chambers, J.Q., Eamus, D., Folster, H., Fromard, F., Higuchi, N., Kira, T., Lescure, J.P., Nelson, B.W., Ogawa, H., Puig, H., Riera, B. & Yamakura, T. (2005) Tree allometry and improved estimation of carbon stocks and balance in tropical forests. *Oecologia*, **145**, 87–99.

Chave, J., Coomes, D., Jansen, S., Lewis, S.L., Swenson, N.G. & Zanne, A.E. (2009) Towards a worldwide wood economics spectrum. *Ecology Letters*, **12**, 351–366.

Chave, J., Muller-Landau, H.C., Baker, T.R., Easdale, T.A., Steege, H.t. & Webb, C.O. (2006) Regional and phylogenetic variation of wood density across 2456 neotropical tree species. *Ecological applications*, **16**, 2356–2367.

Chave, J., Réjou-Méchain, M., Búrquez, A., Chidumayo, E., Colgan, M.S., Delitti, W.B., Duque, A., Eid, T., Fearnside, P.M., Goodman, R.C., Henry, M., Martínez-Yrízar, A., Mugasha, W.A., Muller-Landau, H.C., Mencuccini, M., Nelson, B.W., Ngomanda, A., Nogueira, E.M., Ortiz-Malavassi, E., Pélissier, R., Ploton, P., Ryan, C.M., Saldarriaga, J.G. & Vieilledent, G. (2014) Improved allometric models to estimate the aboveground biomass of tropical trees. *Global Change Biology*, **20**, 3177–3190.

Chudnoff, M. (1984) *Tropical Timbers of the World*. Agriculture handbook. U.S. Department of Agriculture, Forest Service.

Courbaud, B., Vieilledent, G. & Kunstler, G. (2012) Intra-specific variability and the competition-colonisation trade-off: coexistence, abundance and stability patterns. *Theoretical Ecology*, **5**, 61–71.

Díaz, S., Kattge, J., Cornelissen, J.H.C., Wright, I.J., Lavorel, S., Dray, S., Reu, B., Kleyer, M., Wirth, C., Prentice, I.C., Garnier, E., Bönisch, G., Westoby, M., Poorter, H., Reich, P.B., Moles, A.T., Dickie, J., Gillison, A.N., Zanne, A.E., Chave, J., Wright, S.J., Sheremet'ev, S.N., Jactel, H., Baraloto, C., Cerabolini, B., Pierce, S., Shipley, B., Kirkup, D., Casanoves, F., Joswig, J.S., Günther, A., Falczuk, V., Rüger, N., Mahecha, M.D. & Gorné, L.D. (2016) The global spectrum of plant form and function. *Nature*, **529**, 167–171.

Flores, O. & Coomes, D.A. (2011) Estimating the wood density of species for carbon stock assessments. *Methods in Ecology and Evolution*, **2**, 214–220.

Hailwood, A. & Horrobin, S. (1946) Absorption of water by polymers: analysis in terms of a simple model. *Transactions of the Faraday Society*, **42**, B084–B092.

IPCC (2006) Guidelines for national greenhouse gas inventories, prepared by the national greenhouse gas inventories programme. Technical report, The Intergovernmental Panel on Climate Change, IPCC/IGES, Japan.

Kunstler, G., Falster, D., Coomes, D.A., Hui, F., Kooyman, R.M., Laughlin, D.C., Poorter, L., Vanderwel, M., Vieilledent, G., Wright, S.J., Aiba, M., Baraloto, C., Caspersen,

J., Cornelissen, J.H.C., Gourlet-Fleury, S., Hanewinkel, M., Herault, B., Kattge, J., Kurokawa, H., Onoda, Y., Peñuelas, J., Poorter, H., Uriarte, M., Richardson, S., Ruiz-Benito, P., Sun, I.F., Ståhl, G., Swenson, N.G., Thompson, J., Westerlund, B., Wirth, C., Zavala, M.A., Zeng, H., Zimmerman, J.K., Zimmermann, N.E. & Westoby, M. (2016) Plant functional traits have globally consistent effects on competition. *Nature*, **529**, 204–207.

McGroddy, M.E., Daufresne, T. & Hedin, L.O. (2004) Scaling of C:N:P stoichiometry in forests worldwide: implications of terrestrial redfield-type ratios. *Ecology*, **85**, 2390–2401.

Muller-Landau, H.C. (2004) Interspecific and inter-site variation in wood specific gravity of tropical trees. *Biotropica*, **36**, 20–32.

Niklas, K.J. (1993) Influence of tissue density-specific mechanical properties on the scaling of plant height. *Annals of Botany*, **72**, 173–179.

Pan, Y., Birdsey, R.A., Fang, J., Houghton, R., Kauppi, P.E., Kurz, W.A., Phillips, O.L., Shvidenko, A., Lewis, S.L., Canadell, J.G., Ciais, P., Jackson, R.B., Pacala, S.W., McGuire, A.D., Piao, S., Rautiainen, A., Sitch, S. & Hayes, D. (2011) A large and persistent carbon sink in the world's forests. *Science*, **333**, 988–993.

Reyes, G., Brown, S., Chapman, J. & Lugo, A.E. (1992) Wood densities of tropical tree species. *General Technical Report - Southern Forest Experiment Station, USDA Forest Service*, pp. i + 15 pp.

Roughgarden, J. (1979) *Theory of population genetics and evolutionary ecology: an introduction.* Macmillan New York NY United States 1979.

Saatchi, S.S., Harris, N.L., Brown, S., Lefsky, M., Mitchard, E.T.A., Salas, W., Zutta, B.R., Buermann, W., Lewis, S.L., Hagen, S., Petrova, S., White, L., Silman, M. & Morel, A. (2011) Benchmark map of forest carbon stocks in tropical regions across three continents. *Proceedings of the National Academy of Sciences*, **108**, 9899–9904.

Sallenave, P. (1955) Propriétés physiques et mécaniques des bois tropicaux de l'Union française. https://doi.org/10.18167/agritrop/00359. Technical report, Nogent-sur-Marne, France.

Sallenave, P. (1964) Propriétés physiques et mécaniques des bois tropicaux. Premier supplément. https://doi.org/10.18167/agritrop/00357. Technical report, Nogent-sur-Marne, France.

Sallenave, P. (1971) Propriétés physiques et mécaniques des bois tropicaux. Deuxième supplément. https://doi.org/10.18167/agritrop/00358. Technical report, Nogent-sur-Marne, France.

Shmulsky, R. & Jones, P. (2011) *Forest Products and Wood Science.* Wiley.

Simpson, W.T. (1993) Specific gravity, moisture content, and density relationship for wood. Technical report.

Skaar, C. (1988) *Wood-water relations.* Springer-Verlag.

Stamm, A. (1964) *Wood and cellulose science.* Ronald Press Co.

Swenson, N.G. & Enquist, B.J. (2007) Ecological and evolutionary determinants of a key plant functional trait: wood density and its community-wide variation across latitude and elevation. *American Journal of Botany*, **94**, 451–459.

Thibaut, B., Gril, J. & Fournier, M. (2001) Mechanics of wood and trees: some new highlights for an old story. *Comptes Rendus de l'Académie des Sciences - Series IIB - Mechanics*, **329**, 701 – 716.

Vieilledent, G., Vaudry, R., Andriamanohisoa, S.F.D., Rakotonarivo, O.S., Randrianasolo, H.Z., Razafindrabe, H.N., Rakotoarivony, C.B., Ebeling, J. & Rasamoelina, M. (2012) A universal approach to estimate biomass and carbon stock in tropical forests using generic allometric models. *Ecological Applications*, **22**, 572–583.

Vieilledent, G., Fischer, F.J., Chave, J., Guibal, D., Langbour, P. & Gérard, J. (2018) Code and data for: New formula and conversion factor to compute tree species basic wood density from a global wood technology database. *CIRAD Dataverse*, http://dx.doi.org/10.18167/DVN1/KRVF0E.

Vieilledent, G., Gardi, O., Grinand, C., Burren, C., Andriamanjato, M., Camara, C., Gardner, C.J., Glass, L., Rasolohery, A., Rakoto Ratsimba, H., Gond, V. & Rakotoarijaona, J.R. (2016) Bioclimatic envelope models predict a decrease in tropical forest carbon stocks with climate change in madagascar. *Journal of Ecology*, **104**, 703–715.

Violle, C., Navas, M.L., Vile, D., Kazakou, E., Fortunel, C., Hummel, I. & Garnier, E. (2007) Let the concept of trait be functional! *Oikos*, **116**, 882–892.

Westoby, M. & Wright, I.J. (2006) Land-plant ecology on the basis of functional traits. *Trends in Ecology & Evolution*, **21**, 261 – 268.

Williamson, G.B. & Wiemann, M.C. (2010) Measuring wood specific gravity ... correctly. *American Journal of Botany*, **97**, 519–524.

Zanne, A., Lopez-Gonzalez, G., Coomes, D., Ilic, J., Jansen, S., Lewis, S., Miller, R., Swenson, N., Wiemann, M. & Chave, J. (2009) Data from: Towards a worldwide wood economics spectrum. *Dryad*, https://doi.org/10.5061/dryad.234. *Ecology Letters*.

 # 8 Tables

Table 1: **Countries with the highest number of tree species (>20) in the Cirad wood density database.** The dataset includes values from 63 countries but the major part of the measurements of wood physical and mechanical properties has been done in tropical countries in South America, Africa and tropical Oceanic islands.

Country	n species
South America	
Brazil	108
French Guiana	168
Africa	
Burundi	29
Cameroon	83
Central African Republic	27
Côte d'Ivoire	117
Democratic Republic of the Congo	60
Gabon	105
Guinea	20
Asia	
Viet Nam	20
Oceanic islands	
Guadeloupe	43
Madagascar	94
New Caledonia	87

Table 2: **Descriptive statistics at the species level (872 species) for the wood physical and mechanical properties in the Cirad database.**

Variable	min	max	mean	median	sd	95% quantiles
R (%/%)	0.190	0.810	0.461	0.456	0.098	0.292–0.660
S (%)	17	41	27.93	28.00	4.06	20.18–36.00
D_{12} (g/cm^3)	0.228	1.290	0.736	0.720	0.194	0.396–1.107
D_b (g/cm^3)	0.191	1.105	0.608	0.600	0.157	0.331–0.916

 # 9 Figures

Figure 1: **Number of tree species by country in the Cirad wood density database**.

Figure 2: **Relationship between basic wood density (D_b oven dry mass/green volume, in g/cm^3) and wood density at 12% moisture (D_{12}).** Grey dots represent the 3832 trees from the Cirad database for which D_{12}, R and S have been measured and D_b computed with our new formula. The grey dashed line represents the identity line. Based on D_{12} and D_b values, we estimated the following relationship (plain large black line): $D_b = 0.828 D_{12}$ ($n = 3832$, $r^2 = 0.999$). Using Sallenave's data and formula, Chave *et al.* (2006) estimated a significantly different conversion factor of 0.872 (plain thin black line). We also plotted Simpson's (dashed black curve) and Reyes' relationships (dotted black line).

Figure 3: **Correlation between variables describing wood properties.** This figure shows the correlation between the volumetric shrinkage coefficient R, the fibre saturation point S, and the wood density at 12% moisture D_{12}. In the lower-left panels, numbers indicate the absolute value of the Pearson's correlation coefficient for each pair of variables. In the upper-right panels, figures show the scatter-plot for each pair of variables with a non-parametric smoother in red.

Figure 4: **Relationship between basic wood density (D_b oven dry mass/green volume, in g/cm³) from Cirad and GWDD databases for 411 species.** The black line represents the identity line. Grey dots represent species mean basic wood densities from Cirad and GWDD databases. These 411 species are common to the two databases but wood samples and measurement protocols differ in each database. Comparing the two databases, we obtained a Pearson correlation coefficient of 86% and a coefficient of variation of 13.69%. We also observed that, on average, D_b values in the GWDD were higher by 3.05% compared with D_b values in the Cirad database.

 # 10 Supporting Information

Supporting Information S1: **Definition and unit of wood physical and mechanical properties.**

Notation	Definition	Unit
w	water content or moisture $w = 100(m_w - m_0)/m_0$	% of the dry mass
m_w	mass at moisture $= w$	g
m_0	anhydrous mass or "oven dry mass"	g
S	fibre saturation point (water content above which the wood volume does not increase)	%
V_w	volume at moisture $= w$	cm^3
V_S	volume at $w = S$ or "green volume"	cm^3
D_b	basic wood density (m_0/V_S) or "wood specific gravity"	g/cm^3
D_{12}	wood density at 12% moisture (m_{12}/V_{12})	g/cm^3
D_{15}	wood density at 15% moisture (m_{15}/V_{15})	g/cm^3
D_0	anhydrous wood density (m_0/V_0)	g/cm^3
R	volumetric shrinkage coefficient (variation in volume per 1% change in water content) $R = 100(V_S - V_0)/(V_S S)$	%/%

Supporting Information S2: **Correcting Sallenave formula.**

Step 1: Computing the anhydrous mass m_0

Using d the density conversion factor per 1% change in moisture content defined by Sallenave (1955), we compute D_0, the anhydrous density: $D_0 = D_{12} - 12d$. Because $D_0 = m_0/V_0$, we obtain $m_0 = V_0(D_{12} - 12d)$ (Eq. A5).

Step 2: Computing the saturated volume V_S

Sallenave (1955) defined ν as the volumetric shrinkage coefficient (in %/%) using V_0 as the reference volume: $\nu = 100(V_S - V_{12})/(V_0(S - 12))$. We use this definition to derive $V_S = V_{12}(1 + (\nu/100)(S - 12))$ (Eq. A6)

Step 3: Computing the basic wood density D_b

Basic wood density D_b is defined as $D_b = m_0/V_S$. Using Eq. A5 and Eq. A6, D_b can be written $D_b = (V_0/V_{12})(D_{12} - 12d)/(1 + (\nu/100)(S - 12))$. This demonstrates that Sallenave's formula is true only if $V_0 = V_{12}$.