Predicting gene expression using morphological cell responses to nanotopography

Marie F.A. Cutiongco[1], Bjørn S. Jensen[2], Paul M. Reynolds[1], Nikolaj Gadegaard[1,*]

[1]Divison of Biomedical Engineering, School of Engineering, University of Glasgow, Glasgow, United Kingdom
[2]School of Computing Science, University of Glasgow, Glasgow, United Kingdom
* corresponding author

Corresponding author:

Nikolaj Gadegaard, PhD

Division of Biomedical Engineering

Oakfield Avenue, Rankine Building

Glasgow, United Kingdom G12 8LT

Email: Nikolaj.Gadegaard@glasgow.ac.uk

Tel no: 01413305243

Keywords: machine learning, high content imaging, quantitative structure and function, rational design, image-based profiling, biomaterial

Abstract

Cells respond in complex ways to topographies, making it challenging to identify a

direct relationship between surface topography and cell response. A key problem is

the lack of informative representations of topographical parameters that translate

directly into biological properties. Here, we present a platform to relate the effects of

nanotopography on morphology to function. This platform utilizes the 'morphome', a

multivariate dataset containing single cell measures of focal adhesions, the

cytoskeleton, and chromatin. We demonstrate that nanotopography-induced

changes in cell phenotype (both morphological and functional) are uniquely encoded

by the morphome. The morphome was used to create a Bayesian linear regression

model that robustly predicted changes in bone, cartilage, muscle and fibrous gene

expression induced by nanotopography. Furthermore, the morphome effectively

predicted nanotopography-induced gene expression within a complex co-culture

microenvironment. The spatial, morphological and functional resolution of the

morphome uncovered previously unknown effects of nanotopography on selectively

altering cell-cell interaction and osteogenesis at the single cell level. Thus, the

morphome confers the ability to quantify phenotype arising from cell-material

interactions. Our new platform shows promise for rapidly assessing novel surface-

patterned biomaterials for tissue regeneration and enables cell function-oriented

exploration of new topographies.

1 **Introduction**
2

Biomedical implants continue to be developed to improve patient outcomes. One

way to enhance implant efficacy and tissue regeneration is to vary substrate texture

with nanotopographies. Topographies at the cell-material interface are widely shown

to direct cell behaviour: nanopillars change cell morphology[1]; nanogratings

drastically alter lipid metabolism[2], and pluripotent[3-5] and multipotent cell

differentiation[6]; nanogradients improve stem cell cardiomyogenic differentiation; and

subtle changes to nanopit geometric arrangement switches human mesenchymal

stem cells from multipotent to osteogenic fate[7-10]. Morphological responses to

nanotopography are manifested through varying focal adhesion size[17-19],

orientation[19-21], and composition[22,23] and changes in actin contractility and nuclear

deformation[24].

A quantitative relationship exists between a material's physicochemical structure and

its biological activity. Rational drug design has long relied on molecule solubility,

ionisation and lipophilicity to predict activity[11]. Protein engineering has similarly

modelled protein-peptide interactions from protein structure[12]. Cell metabolic activity

correlates with synthetic polymer composition, glass transition temperature, and

water contact angle[13]. Meanwhile, bacterial attachment can be predicted from

descriptors of secondary ionic hydrocarbon chains[14]. In contrast to active

biomolecules, the mechanotransductive effects of topography on cell response do

not intuitively relate to topography length scale, isotropy, geometry, and polarity. This

limits the discovery of functional topography to the screening of libraries for hits

using a single, representative cell type[15-18]. Among its limitations (which include cost,

inefficiency and the sampling of a small topography space), this screening approach

disregards the cell specificity of response to nanotopogrpahy. Thus, it is vitally

important to develop a systematic method to capture cell phenotypes (both at

morphological and functional levels) induced by topography.

Here, we demonstrate an image profiling-based platform that encompasses cell

function and morphological response induced by nanotopography. Measurements of

focal adhesions, actin cytoskeleton and chromatin, referred to here as the

'morphome', were obtained from single cells on nanotopographies. The morphome signature clearly reflected cell type, nanotopography and levels of gene expression at the single cell level. We used a Bayesian linear regression model to directly relate the morphological and phenotypic changes induced by nanotopography. Using the morphome as predictors and without prior knowledge about the nanotopography, the model robustly predicted gene expression induced by nanotopography. Precluding topography measurements (e.g. diameter, pitch of topography) in the model and the mechanosensitive response in all cell types highlights the broad applicability of this platform to many biomaterial and cell systems. In fact, a new morphome from a co-culture of osteoblastic and fibroblastic cells verified this by positively predicting level of osteogenesis induced by nanotopography. This is the first study to quantify morphological, functional and topographical relationships induced by cell-material interaction at a single cell level.

Results

Measuring morphological cell responses to topography: the morphome

We used nanopit topographies consisting of 120 nm diameter, 100 nm depth and with a 300 nm centre-to-centre distance in a square array (SQ)[7], hexagonal array (HEX)[25-27], and arranged with centre-to-centre distance offset from 300 nm by 50 nm in both x and y directions (NSQ array)[7,8]. An unpatterned ('FLAT') surface was used as a control (Figure 1A).

We employed cells of the musculoskeletal system due to the diverse responses of muscle, bone, cartilage and fibrous cell types to nanotopographies[27-29]. Mouse myoblasts, osteoblasts, chondrocytes, fibroblasts, and pre-osteoblast[30] and pre-myoblast[31] progenitors, were grown on nanotopographies. Responses from combinations of each cell type on all nanotopographies were measured, providing 24 unique combinations of cell type and nanotopography (Figure S1). Effects of nanotopography on conventional morphological characteristics such as cell and nuclear area, actin intensity, focal adhesion area and intensity, and mechanosensor nuclear translocation were evident (Figure S1-S4).

Quantitative polymerase chain reaction (qPCR) was then used to assess changes in lineage marker expression induced by nanotopography by day 7 (Figure 1B). At day 2, we performed image-based profiling (Figure 1C). From images of the chromatin and actin, the nucleus and the cell body, respectively, was robustly segmented using CellProfiler. Within these cellular features, we measured morphology (shape and geometry of different compartments), texture (spatial patterns of fluorescence), intensity (total fluorescence value), and radial distribution of intensity (measuring radial arrangement of fluorescence) of chromatin, actin, focal adhesion kinase (FAK) and phosphorylated FAK (pFAK) signals. The morphome consisted of 624 single cell measurements ("features"), with 75 chromatin and nuclear features, 211 actin and whole-cell features, 168 FAK features, and 170 pFAK features (Supplementary data). Machine learning was then applied on the morphome: (i) hierarchical clustering was used to uncover unique patterns of morphological features that distinguish cell type-specific responses on nanotopographies, and nanotopography-specific morphological changes induced within the cell; (ii) Bayesian linear regression was used to predict myogenic, osteogenic, chondrogenic and fibrogenic gene expression induced by nanotopography using the morphome as predictors (Figure 1D).

(A) Musculoskeletal cell types on nanotopographies

Supportive fibrous tissue (fibroblast)

Skeletal muscle (Pre-myoblast, Myoblast)

Cartilage (Chondrocyte)

Bone (Pre-osteoblast, Osteoblast)

FLAT — 500nm
NSQ — 1μm
SQ — 1μm
HEX — 1μm

(B) qPCR-based population phenotyping at day 7

Lineage marker gene expression

Fold change — FLAT SQ NSQ HEX

(C) Image-based single cell morphome at day 2

(i)
Chromatin | Actin
FAK | pFAK
50 μm

(ii)

	Chromatin features (D)	Actin features (A)	Focal adhesion features (FA)	
Cell stain	DNA	Actin	Focal adhesion kinase	Y397 phosphorylated FAK
Subcellular nuclear measurements	**Morphometry:** Shape, Zernike			
	Global and local intensity: Whole object intensity, Granularity, Radial distribution **Textures:** Angular second moment, Gabor, Contrast, Correlation			
Whole cell measurements		**Morphometry:** Shape, Zernike		
	Global and local intensity: Whole object intensity, Granularity, Radial distribution **Textures:** Angular second moment, Gabor, Contrast, Correlation			
Total features extracted	273	289	244	244
Features used	75	211	168	170

(D) Machine learning

(i) Hierarchical unsupervised clustering

Identify nanotopography-induced and cell type-specific morphome signatures

(ii) Linear modeling

Predicted qPCR value — Actual qPCR value

Predict gene expression using the morphome as covariates in Bayesian linear regression model

Figure 1. An overview of the morphome platform for relating cell function and morphology changed by nanotopography. (A) Osteoblastic, myoblastic, chondroblastic and fibroblastic cell lines were cultured on nanotopographies to obtain 24 combinations of cell type and topography. Image of musculoskeletal system obtained from Servier Medical Art under creative commons licence 3.0. (B) At day 7, lineage-specific gene expression induced by nanotopography was measured using population-based qPCR. (C) At day 2, various measures of chromatin (blue), actin (red), focal adhesion kinase (FAK, yellow) and phosphorylated FAK (pFAK, green) were obtained from images of single cells to create the 'morphome'. (i) Representative images of cells stained against different cellular aspects. Black lines show the cell and nucleus outlines, from which morphology measurements were extracted. Cell and nucleus outlines were obtained from the actin and chromatin images, respectively, using CellProfiler. (ii) Cell morphology features extracted from 4 stains across single cells. (D) Machine learning for data-driven exploration and model building using the morphome. (i) Hierarchical clustering uncovered unique patterns that delineate cell type and nanotopography within the morphome. (ii) Bayesian linear regression created a predictive model that related the morphome to gene expression.

The morphome depicts unique cell signatures induced by nanotopographies

Patterns of nanotopography-induced morphological changes were visible from the morphome (Figure 2A). Immediately apparent were large blocks of actin, FAK and pFAK measurements with similar values within a cell type on a specific nanotopography. These features correspond to increasingly complex measures of texture, granularity and radial intensity distribution for chromatin, actin, FAK and pFAK (Table S1). Frequency of pixel gray levels measure texture and homogeneity of pixels, with high values indicating coarseness. Granularity measures an object's coarseness, with higher values indicating heterogeneity of pixel intensities and coarser texture. The Zernike coefficient measures the spatial arrangement of intensity as it resembles the increasingly complex Zernike polynomials (Figure 2A). The Zernike coefficient was used to measure both cell shape and radial distribution of fluorescence intensity of chromatin, actin, pFAK and FAK. Interestingly, higher order Zernike polynomials resemble the punctate shape and spatial distribution of focal adhesions[32]. This provides an integrative analysis of focal adhesions at the single cell level compared to traditional measures that define individual adhesion characteristics.

Nanotopography induces cell type-specific gene expression changes

Gene expression was used to determine the effect of nanotopographies on cell function (Figure S5). We discuss here the changes induced by nanotopography on lineage-specific gene expression relevant to the cell type. Pre-myoblasts showed significantly higher expression of the early lineage marker *MYOD1*, and of the late markers *MYOG* and *MYH7* when cultured on SQ surfaces relative to FLAT surfaces (Figure 2B-2D). Both pre-osteoblasts and osteoblasts showed increased expression of early (*RUNX2*, *SP7*) and late (*BGLAP*, *SPP1*) osteogenic markers when cultured on NSQ relative to FLAT (Figure 2E-2H), in line with previous studies[7,8,10,33]. Chondrocytes cultured on HEX showed increased expression of *COL2A1* (early marker) and *ACAN* (late marker) compared to those cultured on FLAT (Figure 2I-2K). Meanwhile, fibroblasts showed increased expression of pathogenic fibrosis markers, *TGFB1I1*, *COL3A1* and *ELN*[34,] on all nanotopographies compared with FLAT (Figure 2M-2O). In general, a cell type-specific response to nanotopography was observed. Each lineage was notably enhanced in a specific cell type and

1 nanotopography combination: SQ stimulated the myoblast phenotype, NSQ

2 enhanced the osteoblast phenotype, HEX stimulated the chondrocyte phenotype,

3 while all surfaces except FLAT stimulated the fibrotic phenotype.

(caption for figure in next page) Figure 2. Unique responses of cells to nanotopography at

single-cell and population levels. (A) Heat map of the morphome across cell types and

nanotopographies. The morphome consisted of 624 features that quantitatively measure the

cell and nucleus geometries, as well as chromatin, actin, FAK, pFAK characteristics within

single cells. The colour and intensity of each tile represents the average value of the feature

for a particular cell type and nanotopography combination. Each feature has an average of 0

and a standard deviation of 1 after normalization across all cell types. Schematic diagrams

of representative morphome features are included in (i) to (v). (B-O) QPCR of

musculoskeletal genes in response to nanotopographies. Measurement of (B-D) myogenic

markers from pre-myoblasts and myoblasts, (E-H) osteogenic markers from pre-osteoblasts

and osteoblasts, (I-L) chondrogenic markers from chondrocytes, (M-O) fibrotic markers from

fibroblasts on nanotopographies. Gene expression is listed left to right in order of increasing

maturity for the given cell lineage. QPCR measurements shown here were normalized to the

reference gene and cell type on FLAT. QPCR measurements across all 24 combinations of

cell type and topography are shown in Figure S5. All qPCR measurements are given as

mean ± standard deviation from 2 independent experiments (n=6). Significance levels

obtained from one-way ANOVA with Tukey's post-hoc test for pairwise comparison.

Significance levels were denoted by * ($p<0.05$), ** ($p<0.01$), *** ($p<0.001$), and ****

($p<0.0001$).

Distinct nanotopographical responses of single cells are reflected in the

morphome

A subset of the morphome, consisting of 185 features, varied significantly across cell

types (Figure 3, Supplementary Data). For ease of visualization of a multivariate

dataset, hierarchical clustering was employed to group morphome features of high

similarity together and thus reveal morphological profiles across different

nanotopographies. Before clustering, each morphome feature was mean centered

and normalized, transforming each morphome feature to a relative scale with

negative values denoting decrease and positive values denoting increase from the

mean = 0. When taken entirely, hierarchical clustering of the morphome revealed

distinct morphological profiles of all combinations of cell type and nanotopography

(Figure S6). Our results were further distilled to hierarchical clustering of the

morphome separated by cell type (Figure 3). Here, we highlight the morphome for

cell type and nanotopography combinations that induced highest lineage-specific

gene expression. When compared to FLAT, pre-myoblasts on SQ showed high

average values of: focal adhesion textures (Figure 3A, cluster 2); pFAK radial

distribution (cluster 4); nuclear morphometry; and chromatin textures (cluster 4). The

morphome of pre-myoblasts cultured on SQ reflects the need for FAK

phosphorylation and for its preferential localization at stress fiber edges, which is

necessary for myotube differentiation[36,37]. In contrast, myoblasts on SQ showed a

particularly high average value for chromatin granularity and nuclear morphometry

(cluster 4), and near-zero values for radial distribution of actin and of focal adhesions

(cluster 1). High chromatin granularity observed for both pre-myoblasts and

myoblasts on SQ denotes chromatin heterogeneity and condensation and

transcriptional activity, which is reportedly higher prior to myotube formation[38,39].

Pre-osteoblasts on SQ and NSQ had high average values for pFAK radial

distribution, intensity, granularity and texture, and high average values for granularity

of chromatin and actin (clusters 1-5). However, pre-osteoblasts on SQ had higher

order pFAK and FAK radial distribution than on NSQ, which induced the highest

expression of osteogenic markers. The morphome of pre-osteoblasts grown on NSQ

featured radially variable actin that resemble bone cells, which have high contractility and actin stress fibers[40].

For osteoblasts, the differences between the SQ and NSQ morphome were more prominent: NSQ induced lower average values of focal adhesion granularity, chromatin texture and nuclear morphometry (cluster 1), and higher average values for focal adhesion radial distribution (clusters 4-7) compared to SQ (Figure 3D). The osteoblast morphome on NSQ indicates that focal adhesions localize at regular intervals along the periphery, which is associated with osteogenesis[41]. Furthermore, changes in nuclear morphometry attributed to spreading after growth on stiff surfaces is also associated with osteogenic differentiation[42].

Chondrocytes on HEX, which significantly increased chondrogenic marker gene expression relative to FLAT, showed high average values of radial distribution, texture and granularity of actin and FAK, high average nuclear morphometry, and low average values of pFAK and chromatin measurements (Figure 3E, clusters 1-3). These characteristics reflect the morphological changes (including reduced contractility and stress fiber formation, increased cell circularity, and decreased cell spreading[40], low FAK phosphorylation[43] and poor focal adhesion formation[44]) of stem cells undergoing chondrogenesis.

The morphome of fibroblasts cultured on FLAT had high average values of both actin and focal adhesion measurements (Figure 3F, clusters 3 and 5). The highly uniform radial arrangement of focal adhesions and actin of cells on FLAT indicate reduced polarization and contractile morphology of fibroblasts activated to a fibrotic state[45]. Inflammation pathways are reportedly increased in fibroblasts on HEX[46], inducing low adhesion that is reflected in low actin and focal adhesion radial distribution (clusters 3-9). Fibroblasts grown on NSQ and HEX showed low average values of focal adhesion and actin radial distribution but high values when grown on SQ (cluster 2-5).

Overall, the morphome reflected cell-type specific responses to nanotopography. This was highlighted by the dissimilarity of cell types with similar lineage or origin

(e.g. pre-osteoblasts vs osteoblasts, Table 1). A multi-class logistic regression

classifier was able to accurately distinguish 6 different cell types using the

morphome (Figure S7). The radial arrangement of actin and focal adhesions were a

critical distinction of the musculoskeletal cell types induced by nanotopography,

while the arrangement of actin fibers into stress fibers or into cortical, circular

bundles provided information on various cell states.

We also clustered the morphome based on nanotopography (Figure S8,

Supplementary data). Patterns emerge in the morphome in direct response to

nanotopography: NSQ induced high average values of pFAK radial distribution,

texture and granularity; and HEX induced high average values of actin radial

distribution. Correlation between the dendrograms confirm that the morphome

clusters of different nanotopographies were dissimilar to each other (Table S2). The

morphome enabled discrimination between 4 nanotopographies with 68% overall

accuracy (87% classification rate for HEX) using multi-class logistic regression

(Figure S9).

(A) Pre-myoblast

Chromatin · Actin · FAK · pFAK

-1 -0.5 0 0.5 1

FLAT
SQ
NSQ
HEX

1 2 3 4

1. Texture of chromatin
2. Texture of FAK, pFAK
Granularity of chromatin, actin,
FAK, pFAK
Radial distribution of pFAK
3. Radial distribution of FAK,
Granularity of actin, FAK, pFAK
Texture of chromatin

4. Texture of chromatin, pFAK
Radial distribution of actin, pFAK
Edge intensity of actin
Intensity and edge intensity of pFAK
Nuclear morphometry
Granularity of chromatin

(B) Myoblast

FLAT
SQ
NSQ
HEX

1 2 3 4

1. Radial distribution of actin,
FAK, pFAK
Edge intensity of actin
Granularity of chromatin, actin,
FAK, pFAK
Texture of chromatin
Nuclear morphometry

2. Granularity of chromatin
Texture of chromatin, pFAK
3. Texture of chromatin, FAK, pFAK
Edge intensity of pFAK
4. Intensity and edge intensity of pFAK
Texture of chromatin

(C) Pre-osteoblast

FLAT
SQ
NSQ
HEX

1 2 3 4 5 6 7

1. Radial distribution of FAK
Granularity of chromatin and actin
2. Radial distribution of pFAK
3. Granularity of FAK, pFAK
Intensity and edge intensity
of pFAK/Actin
4. Texture of pFAK
Granularity of actin

5. Radial distribution of actin, pFAK
Texture of chromatin, pFAK
6. Radial distribution of actin, FAK, pFAK
Texture of chromatin, FAK, pFAK
Nuclear morphometry
Edge intensity of actin
7. Granularity of chromatin, FAK, pFAK
Radial distribution of FAK
Texture of chromatin

(D) Osteoblast

FLAT
SQ
NSQ
HEX

1 2 3 4 5 6 7

1. Granularity of FAK, pFAK
Texture of chromatin, FAK
Nuclear morphometry
2. Edge intensity of pFAK/FAK
3. Radial distribution of pFAK
4. Granularity of chromatin, actin
FAK, pFAK
Texture of chromatin, FAK, pFAK
Radial distribution of Actin, FAK, pFAK
Edge intensity of actin

5. Radial distribution of pFAK
Texture of pFAK
6. Granularity of chromatin
7. Texture of chromatin, pFAK
Radial distribution of pFAK
Intensity of pFAK

(E) Chondrocyte

FLAT
SQ
NSQ
HEX

1 2 3

1. Radial distribution of actin, FAK
Texture of chromatin, pFAK
Granularity of chromatin, actin,
FAK, pFAK
Nuclear morphometry
Edge intensity of actin

2. Granularity of actin, pFAK
Texture of chromatin, FAK, pFAK
Radial distribution of pFAK
3. Intensity and edge intensity of pFAK
Radial distribution of pFAK
Granularity of chromatin

(F) Fibroblast

FLAT
SQ
NSQ
HEX

1 2 3 4 5 6 7 8 9

1. Radial distribution of pFAK
2. Texture and granularity
of chromatin
Radial distribution of FAK, pFAK
3. Radial distribution of actin, FAK
Texture of chromatin, pFAK
Granularity of chromatin, actin
Nuclear morphometry
4. Nuclear morphometry
Granularity of pFAK
Radial distribution of FAK

5. Texture of FAK, pFAK
Radial distribution of actin, pFAK
6. Intensity of pFAK
Edge intensity of actin
7. Granularity of chromatin, FAK
Texture of chromatin, FAK, pFAK
8. Granularity of chromatin, actin, pFAK
9. Edge intensity of pFAK
Texture of pFAK
Radial distribution of FAK

Figure 3. Morphome features hierarchically clustered by cell type revealed nanotopography-specific changes to cell morphology. (A-F) Hierarchical clustering of the morphome within each cell type. The data morphome from each cell type were clustered separately. Within the cell type-specific morphome, each morphome feature was normalized to have a mean= 0 and standard deviation = 1. The colour and intensity of each tile represents the average value of the feature. The morphome features analysed were comprised of 21 chromatin, 42 actin, 23 FAK and 60 pFAK features. Features included were changed significantly across topographies ($p < 0.05$ using one-way ANOVA). The total number of cells analyzed from two independent experiments were: (A) n=877 pre-myoblasts; (B) n=931 myoblasts; (C) n=644 pre-osteoblasts; (D) n=728 osteoblasts; (E) n=619 chondrocytes; and (F) n=1140 fibroblasts.

Table 1. Correlation coefficient of morphome features hierarchically clustered by cell type.

	All cell types	Pre-myoblast	Myoblast	Pre-osteoblast	Osteoblast	Chondrocyte	Fibroblast
All cell types	1						
Pre-myoblast	0.392	1					
Myoblast	0.274	0.280	1				
Pre-osteoblast	0.429	0.236	0.218	1			
Osteoblast	0.410	0.201	0.280	0.354	1		
Chondrocyte	0.540	0.164	0.374	0.393	0.397	1	
Fibroblast	0.473	0.313	0.408	0.350	0.381	0.485	1

The morphome predicts nanotopography induced gene expression changes

The Spearman rank correlation revealed that varying degrees of correlation exist

between morphome features and gene expression (Figure S10). We hypothesized

that the features of the morphomes would sufficiently encompass cell phenotypes

induced by nanotopography. We utilized Bayesian linear regression to predict gene

expression using the morphome features as predictors (for the explicit model

definition, see Materials and Methods). A Bayesian linear regression model reflects

uncertainty in the estimation of regression weights compared to point value

estimates using maximum likelihood regression. Gene expression was modelled

independently of each other, thereby creating 14 different equations with variable

weighting of the morphome features. Importantly, the model was trained without any

prior knowledge of topography type or parameters (e.g. nanodot diameter or center-

to-center distance), instead relying on the morphome to encode this information.

The morphome clearly captured gene expression changes induced by

nanotopography (Figure 4A). The heterogeneity inherent in single cells, usually

uncaptured by population measurements of gene expression, are apparent in the

variance of the predictions using the morphome and the model. The mean absolute

error (MAE) for prediction of all genes was between 10% (for prediction of *MYOD1*,

MYOG and *MYH7*) and 21% (for prediction of *COL3A1*, Table S3).

The magnitude of the regression weight of each morphome feature reflects the

contribution of the morphome feature in predicting gene expression. Across all 14

genes, pFAK activation, as indicated by pFAK/FAK integrated intensity ratio,

consistently contributed to the prediction of all 14 genes. FAK texture and radial

distribution, actin texture, and chromatin granularity features considerably

contributed to prediction of gene expression (Figure S11, Supplementary data).

pFAK was particularly important to the model due to its relevance in contractility

induced by nanotopography[19], fibrosis and scar tissue formation[48], *in vitro*

osteogenesis[49,50], and chondrogenic maintenance[43]. Through the variability in the

model, we obtain realistic expectations of single cell predictions from population level

measurements

The sensitivity and predictive power of the morphome was verified by iteratively

training a model without one combination of cell type and topography (Figure 4B).

Drastic increases in MAE were observed when lineage-specific genes were

predicted using models that excluded the particular cell type lineage being tested,

regardless of nanotopography. The results are logically explained by the fact that the

particular cell type contributes the most information to prediction by virtue of its

lineage. Removal of the morphome of the particular cell type in question thus

drastically reduces the amount of information in the model that uniquely determines

that particular cell type. Model prediction after removal of particular

nanotopographies showed higher consistency indicating that the generalizability of

the morphome model towards predicting gene expression in response to

nanotopographies outside of FLAT, SQ, NSQ and HEX.

(Caption for figure in previous page) Figure 4. The morphome reliably predicts

nanotopography-induced gene expression from specific cell type and topography

combinations. (A) The morphome was used to train a Bayesian linear regression model that

predicted myogenic, osteogenic, chondrogenic, and fibrotic gene expression. The

expression of each gene (response) was trained against linear combinations of morphome

features (predictors) and without any prior knowledge on topography parameters. The linear

regression model was trained using 60% of the dataset and tested using 40% of the data.

Scatterplots show actual and predicted gene expression values by using the test set as input

to the model. Mean absolute error (MAE) was obtained by averaging the differences

between actual and predicted qPCR values. (B) Testing the predictive power of the

morphome by leave-one-out validation. To test the predictive power and bias of the

morphome, the linear regression model was retrained after exclusion of one combination of

cell type and topography. The excluded cell type and topography dataset was used for

prediction, from which MAE was calculated. The tile position denotes the cell type and

nanotopography combination that was excluded in the model and used for testing, while the

color of each tile denotes the MAE.

The morphome encompasses cell response to topography within a complex

environment

We demonstrate the application of the linear regression model by predicting the

outcome of pre-osteoblasts and fibroblasts co-cultured on nanotopographies. A new

morphome was obtained from all cells on the entire nanotopography (Figure S12).

This co-culture morphome was then used as input in the Bayesian linear regression

model to predict gene expression (Figure S13).

For visualization, the sum of predicted osteogenic (*RUNX2, SP7, BGLAP* and *SPP1*)

and fibrotic (*TGFB1I1, COL3* and *ELN*) genes was plotted against the spatial

coordinates of the pre-osteoblasts and fibroblasts. Osteogenic gene expression was

highest on NSQ, which also induced concentrated areas of highly expressing cells

(Figure 5A). These areas might represent hotspots or nuclei of osteogenic paracrine

signaling induced by the NSQ nanotopography[9]. In contrast, osteogenic gene

expression was low and homogenous on the FLAT, SQ and HEX topographies. The

uniformity of cell distribution across each nanotopography (Figure S12) eliminates

the possibility of inadvertent cell clustering as the origin of gene expression changes.

Fibrotic gene expression showed more spatial variability across nanotopographies

but was also maximized on the NSQ nanotopography, and largely overlaps with the

spatial pattern of osteogenic gene expression (Figure 5B). This is attributable to the

synergistic interaction of osteoblasts and fibroblasts on osteogenic differentiation and

mineralization[51]. The predicted effect of high osteogenic gene expression induced by

NSQ was verified in the increased mineralization compared to FLAT at 28 days

(Figure S14). Given that the morphome-based platform was created using single cell

populations, the co-culture results indicate the capability to encode not just cell-

material interaction but a concerted response arising from the cellular milieu.

For the first time, we gleaned new insights in single cell responses induced by

nanotopography using the morphome. Due to the spatial, morphological and

functional information at the single cell level, the morphome permits analysis of

single cells similar to flow cytometry. As an example, we focused on correlating

morphome features with high contribution to the predictive model and gene

expression. Nanotopographies induced indistinct effects on either nuclear perimeter

or pFAK activation, yet there was a clear gradient in predicted osteogenic gene

expression (Figure 5C). As the nucleus became smaller and pFAK activation

increased, both osteogenic and fibrotic gene expression increased. In contrast,

nanotopographies exhibited clearly separable effects on actin and pFAK radial

distribution, with cells on SQ showing the lowest values (Figure 5D). These particular

changes in cell morphology correlated more with osteogenic gene expression than

fibrotic gene expression, which lacked clear separation by nanotopography. From

the morphome, we found strong evidence to implicate changes in nucleus shape and

pFAK activation induced by nanotopography as drivers of osteogenesis.

The morphome additionally uncovered effects of nanotopography on cell-cell

interaction at the morphological and functional levels (Figure 5E, 5F). On average,

the effect of FLAT on cell-cell interaction and the resulting cell morphology extended

up to 1 mm (Figure 5E), yet gene expression changed maximally at a separation

distance of only 250-375 µm between neighboring cells (Figure 5F). In contrast, the

average effect of SQ and HEX on cell-cell interaction and morphology were minute

and apparent only at short cell-cell separation distances of 250 µm and 500 µm,

respectively. A predominantly negative effect on pFAK activation was observed between neighboring cells grown on either SQ or HEX. This suppresive effect of nanotopography on cell-cell interaction correlate strongly with the homogeneity in gene expression induced by SQ and HEX (Figure 5F). On the contrary, long-range effects between cells on NSQ were distinct (Figure 5E). In contrast to FLAT, neighboring cells on NSQ separated by 1 mm or less selectively exhibited drastic changes only in nucleus perimeter and pFAK activation. The long-range effects of cell-cell interaction observed in NSQ were clearly manifested in gene expression (Figure 5F). In fact, NSQ showed a critical distance of 500 - 625 μm between neighboring cells where fibrotic and osteogenic gene expression were maximally changed. In summary, we observed a clear augmentation in cell-cell interaction induced by NSQ compared to FLAT, SQ and HEX. This long-range interaction between neighboring cells on NSQ separated by 1 mm or less drove changes in pFAK activation and osteogenesis.

(Caption for figure in next page) Figure 5. The morphome enables simulataneous analysis of morphological and functional changes induced by nanotopography at the single cell. (A-B) Predicted functional response of a pre-osteoblast and fibroblast co-culture to nanotopography. Contour plots show the sum of predicted (A) osteogenic (RUNX2, SP7, BGLAP, SPP1) and (B) fibrotic (TGFB1I1, COL3, ELN) gene expression for individual cells on FLAT, SQ, NSQ and HEX topographies. Pre-osteoblast and fibroblast cells were co-cultured on FLAT, SQ, NSQ and HEX nanotopographies for 2 days, and their morphome obtained from the entire grid. This new morphome was then used as input in the linear regression model (shown in Figure 4) to predict gene expression. X and Y axes of each contour plot shows are spatial coordinates on the nanotopogrpahy substrate. (C-D) Morphological and functional information at the single-cell level is provided by the morphome. Each dot in the plot denotes a single cell. (E-F) Cell-cell interaction altered by nanotopography. The average changes in (E) cell morphology and (F) gene expression between two cells separated by a given distance was measured and normalized to the maximum observed change. Data are presented as mean ± standard deviation and reported as a function of distance between two cells binned eveyr 125 μm. N ≥ 5000 cells per topography.

Discussion

In this study, we present a system that robustly encodes nanotopography parameters into functional cell specific output. The morphome, which in this study is the collective morphological measurements of chromatin, actin and focal adhesions within single cells, were found to manifest nanotopography-induced changes in cell morphology and gene expression. The information encoded in the morphome underpinned the performance of a Bayesian linear regression model for predicting gene expression. Using the morphome, we gleaned new biological insights resulting from nanotopographical perturbation of the cell microenvironment.

Focal adhesion complexes are the primary mechanosensing machinery of the cell that respond to the biophysical microenvironment. Focal adhesion assembly or confinement induced by nanotopography allows spontaneous actin cytoskeleton assembly, nucleus deformation, and cell fate determination[24,52,53]. Cells also change and control their microenvironment, thereby dictating focal adhesion and cellular characteristics to varying degrees[54,55]. Focal adhesion growth is particularly significant in sensing nanoscale changes in ligand arrangement, as this supports force redistribution throughout the cell [56]. This reciprocity between the nanotopographical microenvironment, focal adhesions, cytoskeleton and chromatin, and gene expression underline the platform presented in this study.

Our results demonstrate that cell morphological and functional response to nanotopography emerge from the morphome. The morphome-based platform reported here offers two unique advantages. First, the design parameters of the nanotopographies were explicitly excluded in predicting gene expression. To use structural information from topography (e.g. depth, diameter, pitch, geometry, isotropy, roughness) considerably limits the dataset to only a handful of descriptors. As opposed to polymer-based biomaterials that contain easily interpretable physicochemical properties derived from chemical structure, the effects of topography parameters on hydrophobicity, serum adsorption and cell attachment are less well understood and quantified. Instead, the information contained in the morphome encompass both topography and gene expression. Furthermore, by creating a general model that is independent of topographical parameters, this

approach can be easily applied to predict cell phenotype induced by new

nanotopographies, given a set of images of cells grown on them. Second, in this

approach, gene expression-based measures of cell phenotype determined the

specialized function of cells. In contrast to our system, many quantitative structure

and function relationship studies of polymeric biomaterials have focused only on

adhesion and metabolic activity[13,14]. Since gene expression is highly scalable, the

linear regression model can be adapted to predict other cell behaviours. This also

ensures that the morphome supports a function-focused exploration of the

topography space and the rational design of topographies, as opposed to the

currently used trial-and-error screening approach.

Our data reveals that the morphome can also manifest nuanced information within

the cellular lineage commitment timeline. The morphome easily captured higher

levels of gene expression in cells farther along lineage commitment compared to

precursor cells. Additionally, our co-culture experiments robustly predicted the

osteogenic properties induced by NSQ. The elevated level of predicted osteogenic

gene expression was supported by high mineralization on NSQ after 28 days of

culture. Our results suggest that the morphome can manifest cellular changes

induced by nanotopography, as well as changes driven by chemical or paracrine

cues. This property of the morphome can be exploited to predict cell behavior in

complex microenvironmental settings.

The co-culture experiment also demonstrated that the morphome dataset

encompasses, at high resolution, structural, functional and spatial information.

Indeed, we took advantage of this informationally rich dataset to uncover

enhancement of cell-cell interaction (from micron to millimeter range) resulting from a

subtle change in nanotopography order. SQ and HEX, both of which present an

ordered interface to the cell, suppressed cell-cell interaction at 250 – 500 µm.

Meanwhile, cell-cell interaction was apparent at long distances of 1 mm on FLAT and

NSQ, which preferentially varied pFAK activation between neighboring cells. This

result presents a new mechanism for nanotopography induced-cell behavior.

Clearly, morphome capture is crucial to the ability of the linear regression model to predict nanotopography induced gene expression. While population-level measures of gene expression strongly indicate cell function, they introduce a measure of uncertainty and biological variability into the linear regression model. Thus, a one-to-one relationship between the morphome and cell function is essential to develop. Non-destructive microscopic and molecular tools[57] that combine spatial and structural information from the morphome with single-cell functional assays are vitally important for establishing quantitative topography structure- and cell-function relationships using the morphome. However, the use of routine methods, such as high-content imaging and qPCR, permits any lab to measure the morphome and to model it against the gene expression in question.

By generating a multivariate morphome dataset and combining it with machine learning, we have created a powerful platform for relating topography structure to gene expression. The predictive power of the Bayesian linear regression model we have developed easily lends to sequential experimental design by exploiting uncertainty and variability within the model[58,59]. Combined with bench-top lithographic techniques[60] and *in silico* simulation of morphological response to nanotopography[61], we envision a completely closed-loop system that enables functionally-oriented exploration of new topographies.

Materials and methods

Polycarbonate surfaces with nanotopography

Surfaces patterned with 120 nm diameter and 100 nm depth nanopits were fabricated on polycarbonate using injection molding[62]. The following nanotopographies were used: surfaces without nanopits (FLAT); nanopits in a square array with 300 nm center-to-center spacing (SQ); nanopits in a square array with approximately 300 nm center-to-center spacing distorted by 50 nm in both x and y directions (NSQ); nanopits in a hexagonal array with 300 nm center-to-center spacing (HEX). Samples were cleaned in 70% ethanol and dried before treating with O_2 plasma at 120 W for 1.5 mins. Samples were sterilized using UV light in biological safety cabinet for at least 20 mins before cell seeding.

Cell culture

Mouse fibroblast cell line NIH3T3 (ATCC) was cultured in reduced sodium

bicarbonate content (1.5 g/L) Dulbecco's modified eagle's medium with (DMEM)

supplemented with L-glutamate (2mM), 10% bovine calf serum, and 1% penicillin-

streptomycin. Mouse C2C12 myoblasts (ATCC) were cultured in DMEM with 20%

FBS and 1% penicillin-streptomycin, and differentiated into skeletal muscle using

DMEM supplemented with 2% horse serum and 1% penicillin streptomycin. Mouse

chondrocytes were cultured in minimum essential medium alpha (MEMα) with

nucleosides, ascorbic acid, glutamate, sodium pyruvate supplemented with 10%

FBS and 1% penicillin-streptomycin. Mouse MC3T3 cells (ATCC) were cultured in

MEMα with nucleosides and L-glutamine without ascorbic acid and supplemented

with 10% FBS and 1% penicillin-streptomycin. To differentiate MC3T3 into

osteoblasts, MC3T3 media was supplemented with 10 nM dexamethasone, 50 µg/ml

ascorbic acid and 10 mM β-glycerophosphate[63]. Lineage committed progenitor cells,

referred to here as pre-osteoblasts and pre-myoblasts, were also included in the

study to mimic the osteogenic and myogenic regeneration in the adult tissue[30,31].

Cell seeding

Cells were harvested from flasks using trypsin in versene buffer and spun down at

400 x g for 5 minutes. NIH3T3 and MC3T3 cells were resuspended in complete

media and seeded at 4000 cells/cm^2. Chondrocytes and C2C12 were seeded at

2500 cells/cm^2. Cells were seeded at different densities to ensure single cells at

approximately 30% confluency on each surface after 2 days culture. To ensure

homogeneity of seeding, cells were seeded using a cell seeder that controlled fluid

flow. For co-culture studies, MC3T3 and NIH3T3 cells were simultaneously seeded

at 2000 cells/cm^2 per cell type in MC3T3 growth media. All cells were grown for 2

days on nanotopographies before fixation for immunofluorescence staining.

Quantitative polymerase chain reaction (qPCR)

After 6 days, total RNA was obtained from lysed cells according to manufacturer's

instructions (Promega ReliaPrep Cell Miniprep kit). Gene expression was measured

directly from 5 ng RNA using a one-step RT PCR kit with SYBR dye (PrimerDesign).

qPCR was run on the BioRad CFX96 platform. Relative gene expression was normalized to the 18S ribosomal RNA reference gene. A list of the forward and reverse primers used to study different mouse genes is given in Table S4. Bar charts for qPCR data were obtained using GraphPad Prism (v7.0). One-way ANOVA with Tukey's post hoc test for multiple comparisons was performed to determine the effect of nanotopography on gene expression compared with FLAT. Statistical significance was considered at $p < 0.05$.

Immunofluorescence staining

After 2 days, cells on surfaces were fixed with 4% paraformaldehyde solution in phosphate buffered saline (PBS) at 4°C for 15 minutes. Fixed cells were then permeabilized and blocked with 10% goat serum and 2% bovine serum albumin in PBS for 1 hour at room temperature. Surfaces were stained with the following primary antibodies overnight at 4°C: pFAK Y397 (Abcam 39967, 1:400) and FAK (ThermoScientific 396500, 1:400). Afterwards, Alexa Fluor-conjugated secondary antibodies (ThermoScientific, 1:500) against the host species of the primary antibody were used. Alexa Fluor 549 conjugated phalloidin (ThermoScientific, 1:200) were used to structuralize the actin cytoskeleton. Cells were also stained with DAPI (ThermoScientific) to visualize chromatin inside the nuclei. DAPI was previously reported contribute textural information as a means of alternatively representing chromatin[64]. All surfaces were mounted on 0.17 µm thick Glass coverslips with ProLong mounting medium (ThermoScientific) and dried overnight at 4°C before imaging.

Image acquisition and feature extraction

For single-cell population studies, monochrome images of each fluorophore were obtained at 40X magnification (numeric aperture 1.3) using the EVOS FL1 System (ThermoScientific). For co-culture studies, the entire nanotopography field was imaged and stitched through an automated microscope (EVOS FL2 Auto) with a 40X magnification. All images from one cell type were obtained using the same camera and light settings. Afterwards, image processing and feature extraction were perfomed using CellProfiler[65] (v2.4.0, The Broad Institute). Image processing, including illumination correction and channel alignment, was performed across each

independent experiment and each cell type[66]. Nucleus and cell body were

segmented from each cell in each image, allowing single cell analysis of shape or

morphometric measurements, total and local intensities and textures from chromatin,

actin, pFAK and FAK.

Multivariate analysis

The morphome initially consisted of a total of 1050 measurements obtained from

single cells. Morphome measurements from single-cell populations were combined

and were scaled by subtracting the mean and normalizing by the standard deviation

of the entire data set. Morphome data from co-culture studies were similarly scaled

and normalized using the mean and standard deviation from the initial dataset

consisting of homogeneous cell populations. Prior to machine learning, features with

zero variance within each batch (e.g. Zernike Phase measurements) were removed

from the data set. A Pearson correlation method at significance level 90% was used

to remove features with correlation higher than 0.9 without significantly reducing total

data variance (Figure S15) using the *KMDA* (v1.0) package for R[67]. After pre-

processing, 624 morphome features were used in the study.

Hierarchical clustering

To determine the features that were significantly varied across nanotopography, a

one-way ANOVA with Tukey's post hoc test for multiple comparisons was performed

(KNIME v3.3.0). Prior to clustering, each morphome feature was mean centered and

normalized to the standard deviation. An agglomerative hierarchical clustering

algorithm was performed using a Euclidean distance metric and an average linkage

method for cluster linkage using *gplots* (v3.0.1) package[68]. Membership of each

morphome in a cluster was obtained from silhouette analysis using the *cluster*

(v2.0.7-1) package[69]. Hierarchical clustering was visually represented with a

dendrogram, and a heatmap with color intensity corresponding to the average values

of the morphome features. Dendrogram correlation was performed using the

corrplot package[70].

Bayesian linear log-Normal regression

Only morphome features with an absolute Spearman correlation coefficient ≥ 0.7

against all examined expression markers were used in the linear regression model

(Supplementary data). The linear regression model used 243 morphome features,

containing 22 nuclear morphometry and chromatin, 71 actin, 75 FAK and 75 pFAK

measurements, as predictors of the model. Each replicate of the qPCR data was

propagated across each replicate of the single-cell morphome data. For each gene

analysed, data were rescaled from 0 to 1 by normalizing to the maximum gene

expression.

Linear regression was performed as a simple approximation of the relationship

between the morphome and myogenic, osteogenic, chondrogenic and fibrotic gene

expression. Established Bayesian inference methods were used to determine the

probabilities of observing gene expression with a given morphome set. We consider

a linear model where expression of one gene (response y) was predicted through a

linear combination of the morphome features (predictors X) transformed by the

inverse identity link function. We assume that y follows a log Normal distribution

parametrized by the mean μ and variance σ_i^2:

$$y_i \sim Lognormal(\mu_i, \sigma_i^2)$$

And that μ is a linear function of X parametrized by β:

$$\mu_i = \ \alpha + \ \beta_0 + \ \beta_1 X_1 + \ \beta_2 X_2 + \cdots + \ \beta_n X_n$$

All model parameters β were assumed *a priori* to come from a normal distribution,

parametrized by mean and standard deviation:

$$\beta \sim Normal(0, 2)$$

Each gene was trained independently resulting in 14 different linear regression

equations. A 60%-40% training and test split for Bayesian linear regression was

performed randomly and with stratification using the *caret* (v6.0-81) package for R[71].
The Bayesian linear model was created using the *brms* (v2.5.0) package for R[72],
which utilizes the Hamiltonian Markov Chain Monte Carlo sampler for estimation of
the posterior distribution of β. Bayesian linear modelling was carried out using with
1000 warm-up iterations and 1000 sampling iterations within each chain for 3
independent chains. All models were confirmed to converge to the equilibrium
distribution by confirming potential scale reduction statistic split-$\hat{R} \geq 1$, effective
sample size was smaller than total sample size and low autocorrelation. Predicted
gene expression was performed by using the test set or the morphome obtained
from the co-culture study as input to the linear model. Predicted values were
averaged across 50 draws from the posterior distribution. The magnitude of the
average values of parameters β indicated feature importance as it effectively
weighted the contribution of each morphome feature in predicting gene expression.

To determine the predictive power of the morphome, a specific combination of cell
type, topography and replicate were iteratively omitted and the remaining dataset
was used to refit new models. Thus, 576 additional models were created to test 24
different cell type combinations across 12 genes and 2 replicates. The predictive
quality of the models was assessed by predicting the expression of all 14 genes from
the omitted cell type, topography and replicate dataset. We report the mean absolute
error (MAE) of qPCR prediction for each cell type and topography combination
averaged across 2 replicates. MAE was calculated as the average across all
absolute differences between predicted and actual gene expression.

Analysis of cell-cell interaction
The co-culture morphome was used to predict gene expression at the single cell
level. The dataset was then used to determine changes in gene expression and
morphome between neighboring cells of a given distance. Changes in cell
morphology and gene expression was performed for each cell against all other cells.
Distances between cells were binned to calculate average value of changes in cell
morphology and gene expression at 125 µm intervals. The changes in cell behavior
between two cells was normalized to the maximum value of change observed.

Statistics, visualization and software

Statistical analysis and machine learning were performed using statistical software R (v3.4.3) and its graphical interface RStudio (v1.0)[73]. Scatterplots, boxplots and histograms were generated using *ggplot2* (v3.1.0) in R[74]. Interpolation of x and y coordinates and sum of predicted osteogenic or fibrotic gene expression was performed using bivariate interpolation of a regularly gridded dataset using *akima* (v0.6-2) package[75]. Afterwards, the contour plots were created using the *fitted.contour* function in the base package of R, with the nuclear centroid position used as spatial coordinates of the cell. Barcharts and one-way ANOVA analysis of qPCR values were obtained using GraphPad Prism (v7.0a).

Data availability

The data that support the findings of the study are available from the corresponding author upon reasonable request.

Code availability

The statistical models proposed and evaluated in this paper is realised using standard packages in R. The code is available from the corresponding author upon reasonable request.

Acknowledgements

We acknowledge ERC funding through FAKIR 648892 Consolidator Award. MFAC is financially supported by the University of Glasgow MG Dunlop Bequest, College of Science and Engineering Scholarship, and FAKIR consolidator award. We acknowledge the James Watt Nanofabrication Centre for fabrication work, and Steen Lillelund for initiating the machine learning work. We thank Julie Russell for her contribution to the qPCR, Carmen Huesa for providing the primary cartilage cells and Rachel Love for the injection moulding of nanopatterned polycarbonate surfaces.

Author contributions

MFAC, PMR and NG designed the biological experiments. MFAC and BSJ designed the machine learning analysis. MFAC carried out imaging, image analysis, qPCR,

machine learning. PMR fabricated and characterized the nanotopographical surfaces. MFAC, BSJ, PMR and NG wrote the manuscript. All authors have read and approved the manuscript before submission.

Disclosure of competing financial interests

The authors have no competing financial interests to disclose.

References

1. Reynolds, P. M., Pedersen, R. H., Riehle, M. O. & Gadegaard, N. A Dual Gradient Assay for the Parametric Analysis of Cell-Surface Interactions. *Small* **8,** 2541–2547 (2012).
2. Di Rienzo, C. *et al.* Unveiling LOX-1 receptor interplay with nanotopography: mechanotransduction and atherosclerosis onset. *Sci. Rep.* **3,** 1–8 (2013).
3. Chan, L. Y., Birch, W. R., Yim, E. K. F. & Choo, A. B. H. Temporal application of topography to increase the rate of neural differentiation from human pluripotent stem cells. *Biomaterials* **34,** 382–392 (2013).
4. Tan, K. K. B. *et al.* Enhanced differentiation of neural progenitor cells into neurons of the mesencephalic dopaminergic subtype on topographical patterns. *Biomaterials* **43,** 32–43 (2015).
5. Rasmussen, C. H. *et al.* Enhanced Differentiation of Human Embryonic Stem Cells Toward Definitive Endoderm on Ultrahigh Aspect Ratio Nanopillars. *Adv. Funct. Mater.* **26,** 815–823
6. Yim, E. K. F., Pang, S. W. & Leong, K. W. Synthetic nanostructures inducing differentiation of human mesenchymal stem cells into neuronal lineage. *Exp. Cell Res.* **313,** 1820–1829 (2007).
7. McMurray, R. J. *et al.* Nanoscale surfaces for the long-term maintenance of mesenchymal stem cell phenotype and multipotency. *Nature Materials* **10,** 637–644 (2011).
8. Dalby, M. J. *et al.* The control of human mesenchymal cell differentiation using nanoscale symmetry and disorder. *Nature Materials* **6,** 997–1003 (2007).
9. Tsimbouri, P. M. *et al.* Using Nanotopography and Metabolomics to Identify Biochemical Effectors of Multipotency. *ACS Nano* **6,** 10239–10249 (2012).
10. Yang, J. *et al.* Nanotopographical Induction of Osteogenesis through Adhesion, Bone Morphogenic Protein Cosignaling, and Regulation of MicroRNAs. *ACS Nano* **8,** 9941–9953 (2014).
11. Luan, F. & (null), M. C. in *Recent Trends on QSAR in the pharmaeutical perceptions* (ed. Khan, M.) 194–241 (books.google.com, 2012). doi:10.2174/97816080537971120101 0194

12. Jenson, J. M. *et al.* Peptide design by optimization on a data-parameterized protein interaction landscape. *Proc. Natl. Acad. Sci. U.S.A.* **592,** 201812939 (2018).

13. Kholodovych, V. *et al.* Accurate predictions of cellular response using QSPR: a feasibility test of rational design of polymeric biomaterials. *Polymer* **45,** 7367–7379 (2004).

14. Hook, A. L. *et al.* Combinatorial discovery of polymers resistant to bacterial attachment. *Nat Biotechnol* **30,** 868–875 (2012).

15. Moe, A. A. K. *et al.* Microarray with Micro- and Nano-topographies Enables Identification of the Optimal Topography for Directing the Differentiation of Primary Murine Neural Progenitor Cells. *Small* **8,** 3050–3061 (2012).

16. Kukumberg, M., Yao, J. Y., Neo, D. J. H. & Yim, E. K. F. Microlens topography combined with vascular endothelial growth factor induces endothelial differentiation of human mesenchymal stem cells into vasculogenic progenitors. *Biomaterials* **131,** 68–85 (2017).

17. Unadkat, H. V. *et al.* An algorithm-based topographical biomaterials library to instruct cell fate. *Proc. Natl. Acad. Sci. U.S.A.* **108,** 16565–16570 (2011).

18. Ankam, S. *et al.* Substrate topography and size determine the fate of human embryonic stem cells to neuronal or glial lineage. *Acta Biomaterialia* **9,** 4535–4545 (2013).

19. Teo, B. K. K. *et al.* Nanotopography Modulates Mechanotransduction of Stem Cells and Induces Differentiation through Focal Adhesion Kinase. *ACS Nano* **7,** 4785–4798 (2013).

20. Zhou, Q. *et al.* Directional nanotopographic gradients: a high-throughput screening platform for cell contact guidance. *Sci. Rep.* **5,** 16240 (2015).

21. Balaban, N. Q. *et al.* Force and focal adhesion assembly: a close relationship studied using elastic micropatterned substrates. *Nature Cell Biology* **3,** 466–472 (2001).

22. Kulangara, K., Yang, Y., Yang, J. & Leong, K. W. Nanotopography as modulator of human mesenchymal stem cell function. *Biomaterials* **33,** 4998–5003 (2012).

23. Cavalcanti-Adam, E. A. *et al.* Cell Spreading and Focal Adhesion Dynamics Are Regulated by Spacing of Integrin Ligands. *Biophysical Journal* **92,** 2964–2974 (2007).

24. Natale, C. F., Ventre, M. & Netti, P. A. Tuning the material-cytoskeleton crosstalk via nanoconfinement of focal adhesions. *Biomaterials* **35,** 2743–2751 (2014).

25. Dalby, M. J. *et al.* Nanomechanotransduction and interphase nuclear organization influence on genomic control. *J. Cell. Biochem.* **102,** 1234–1244 (2007).

26. Dalby, M. J., Gadegaard, N. & Wilkinson, C. D. W. The response of fibroblasts to hexagonal nanotopography fabricated by electron beam lithography. *J Biomed Mater Res A* **84,** 973–979 (2008).

27. Dalby, M. J. *et al.* Group analysis of regulation of fibroblast genome on low-adhesion nanostructures. *Biomaterials* **28,** 1761–1769 (2007).

28. Dalby, M. J., Riehle, M. O., Yarwood, S. J., Wilkinson, C. D. W. & Curtis, A. S. G. Nucleus alignment and cell signaling in fibroblasts: response to a micro-grooved topography. *Exp. Cell Res.* **284,** 272–280 (2003).

29. Allan, C. *et al.* Osteoblast response to disordered nanotopography. *J Tissue Eng* **9,** 204173141878409–7 (2018).

30. Quarles, L. D., Yohay, D. A., Lever, L. W., Caton, R. & Wenstrup, R. J. Distinct proliferative and differentiated stages of murine MC3T3-E1 cells in culture: an in vitro model of osteoblast development. *Journal of Bone and Mineral Research* **7,** 683–692 (1992).

31. Wagers, A. J. & Conboy, I. M. Cellular and molecular signatures of muscle regeneration: current concepts and controversies in adult myogenesis. *Cell* **122,** 659–667 (2005).

32. Kumar, R. M. & Sreekumar, K. A survey on image feature descriptors. *Int J Comput Sci Inf Technol* (2014).

33. Tsimbouri, P. *et al.* Nanotopographical effects on mesenchymal stem cell morphology and phenotype. *J. Cell. Biochem.* **115,** 380–390 (2014).

34. Van De Water, L., Varney, S. & Tomasek, J. J. Mechanoregulation of the Myofibroblast in Wound Contraction, Scarring, and Fibrosis: Opportunities for New Therapeutic Intervention. *Advances in Wound Care* **2,** 122–141 (2013).

35. Bollong, M. J. *et al.* Small molecule-mediated inhibition of myofibroblast transdifferentiation for the treatment of fibrosis. *Proceedings of the National Academy of Sciences* **114,** 4679–4684 (2017).

36. Quach, N. L., Biressi, S., Reichardt, L. F., Keller, C. & Rando, T. A. Focal Adhesion Kinase Signaling Regulates the Expression of Caveolin 3 and β1 Integrin, Genes Essential for Normal Myoblast Fusion. *Molecular Biology of the Cell* **20,** 3422–3435 (2009).

37. Clemente, C. F. M. Z., Corat, M. A. F., Saad, S. T. O. & Franchini, K. G. Differentiation of C 2C 12myoblasts is critically regulated by FAK signaling. *American Journal of Physiology-Regulatory, Integrative and Comparative Physiology* **289,** R862–R870 (2005).

38. Bachmann, P. & Hinrichsen, K. Semiautomated evaluation of morphometric data of myoblasts and myotubes and the calculation of the relative DNA content with the television texture analysis system (TAS). *Histochemistry* **69,** 233–242 (1980).

39. Lassalle, B., Gautron, J., Martelly, I. & Le Moigne, A. Image analysis of rat satellite cell proliferation in vitro. *Cytotechnology* **2,** 213–224 (1989).

40. Treiser, M. D. *et al.* Cytoskeleton-based forecasting of stem cell lineage fates. *Proc. Natl. Acad. Sci. U.S.A.* **107,** 610–615 (2010).

41. Kilian, K. A., Bugarija, B., Lahn, B. T. & Mrksich, M. Geometric cues for directing the differentiation of mesenchymal stem cells. *Proc. Natl. Acad. Sci. U.S.A.* **107,** 4872–4877 (2010).

42. Swift, J. *et al.* Nuclear lamin-A scales with tissue stiffness and enhances matrix-directed differentiation. *Science* **341,** 1240104 (2013).

43. Shin, H. *et al.* Focal Adhesion Assembly Induces Phenotypic Changes and Dedifferentiation in Chondrocytes. *J. Cell. Physiol.* **231,** 1822–1831 (2016).

44. Connelly, J. T., García, A. J. & Levenston, M. E. Interactions between integrin ligand density and cytoskeletal integrity regulate BMSC chondrogenesis. *J. Cell. Physiol.* **217,** 145–154 (2008).

45. Vasilopoulos, Y., Gkretsi, V., Armaka, M., Aidinis, V. & Kollias, G. Actin cytoskeleton dynamics linked to synovial fibroblast activation as a novel pathogenic principle in TNF-driven arthritis. *Annals of the Rheumatic Diseases* **66 Suppl 3,** iii23–8 (2007).

46. Dalby, M. J. Cellular response to low adhesion nanotopographies. *Int J Nanomedicine* **2,** 373–381 (2007).

47. Newman, P. *et al.* Relationship between nanotopographical alignment and stem cell fate with live imaging and shape analysis. *Sci. Rep.* **6,** 37909 (2016).

48. Wong, V. W. *et al.* Focal adhesion kinase links mechanical force to skin fibrosis via inflammatory signaling. *Nat Med* **18,** 148–152 (2011).

49. Castillo, A. B. *et al.* Focal Adhesion Kinase Plays a Role in Osteoblast Mechanotransduction In Vitro but Does Not Affect Load-Induced Bone Formation In Vivo. *PLoS ONE* **7,** e43291–11 (2012).

50. Salasznyk, R. M., Klees, R. F., Williams, W. A., Boskey, A. & Plopper, G. E. Focal adhesion kinase signaling pathways regulate the osteogenic differentiation of human mesenchymal stem cells. *Exp. Cell Res.* **313,** 22–37 (2007).

51. Wang, I.-N. E. *et al.* Role of osteoblast-fibroblast interactions in the formation of the ligament-to-bone interface. *J. Orthop. Res.* **25,** 1609–1620 (2007).

52. Gautrot, J. E. *et al.* The Nanoscale Geometrical Maturation of Focal Adhesions Controls Stem Cell Differentiation and Mechanotransduction. *Nano Lett.* **14,** 3945–3952 (2014).

53. Changede, R., Cai, H., Wind, S. & Sheetz, M. P. Ligand Geometry Controls Adhesion formation via Integrin Clustering. *bioRxiv* (2018). doi:10.1101/435826

54. Li, B., Moshfegh, C., Lin, Z., Albuschies, J. & Vogel, V. Mesenchymal stem cells exploit extracellular matrix as mechanotransducer. *Sci. Rep.* **3,** 2425 (2013).

55. Trappmann, B. *et al.* Extracellular-matrix tethering regulates stem-cell fate. *Nature Materials* **11,** 642–649 (2012).

56. Oria, R. *et al.* Force loading explains spatial sensing of ligands by cells. *Nature* 1–20 (2017). doi:10.1038/nature24662

57. Guillaume-Gentil, O. *et al.* Tunable Single-Cell Extraction for Molecular Analyses. *Cell* **166,** 506–516 (2016).

58. Lindley, D. V. On a Measure of the Information Provided by an Experiment. *The Annals of Mathematical Statistics* **27,** 986–1005 (1956).

59. Chaloner, K. & Verdinelli, I. Bayesian Experimental Design: A Review. *Statistical Science* **10,** 273–304 (1995).

60. Heydari, T. *et al.* Development of a Virtual Cell Model to Predict Cell Response to Substrate Topography. *ACS Nano* **11,** 9084–9092 (2017).

61. Huntington, M. D. & Odom, T. W. Lithography: A Portable, Benchtop Photolithography System Based on a Solid-State Light Source (Small 22/2011). *Small* **7,** 3105–3105 (2011).

62. Stormonth-Darling, J. M., Saeed, A., Reynolds, P. M. & Gadegaard, N. Injection Molding Micro- and Nanostructures in Thermoplastic Elastomers. *Macromol. Mater. Eng.* **301,** 964–971 (2016).

63. Yan, X.-Z. *et al.* Effects of continuous passaging on mineralization of MC3T3-E1 cells with improved osteogenic culture protocol. *Tissue Engineering Part C: Methods* **20,** 198–204 (2014).

64. Gray, M. *et al.* NuMA promotes homologous recombination repair by regulating the accumulation of the ISWI ATPase SNF2h at DNA breaks. *Nucleic Acids Research* **42,** 6365–6379 (2014).

65. Kamentsky, L. *et al.* Improved structure, function and compatibility for CellProfiler: modular high-throughput image analysis software. *Bioinformatics* **27,** 1179–1180 (2011).

66. Caicedo, J. C. *et al.* Data-analysis strategies for image-based cell profiling. *Nat Meth* **14,** 849–863 (2017).

67. Zhan, X., Patterson, A. D. & Ghosh, D. Kernel approaches for differential expression analysis of mass spectrometry-based metabolomics data. *BMC Bioinformatics* **16,** 77 (2015).

68. Warnes, G. R. *et al.* gplots: Various R programming tools for plotting data. *R package version* **2,** 1 (2009).

69. Maechler, M., Rousseeuw, P., Struyf, A., Hubert, M. & Hornik, K. cluster: Cluster Analysis Basics and Extensions. (2017).

70. Wei, T. *et al.* corrplot: Visualization of a Correlation Matrix. (2017).

71. Kuhn, M. Building Predictive Models in R Using the caret Package. *Journal of Statistical Software* **28,** 1–26 (2008).

72. Bürkner, P.-C. brms: An RPackage for Bayesian Multilevel Models Using Stan. *Journal of Statistical Software* **80,** 1–28 (2017).

73. Team, R. R: A language and environment for statistical computing. (2017).

74. Wickham, H. *ggplot2: Elegant Graphics for Data Analysis*. (Springer-Verlag New York, 2009).

75. Akima, H. & Gebhardt, A. akima: Interpolation of Irregularly and Regularly Spaced Data.