Opportunistic interactions on Fe^0 between methanogens and acetogens from a climate lake

Paola Andrea Palacios [1] and Amelia-Elena Rotaru[1*]

[1]Nordcee, Department of Biology, University of Southern Denmark, Odense, Denmark

* Correspondence:
Amelia-Elena Rotaru
arotaru@biology.sdu.dk

Keywords: microbial influenced corrosion, acetogens, methanogens, interspecies interactions, iron corrosion, Clostridium, Methanosarcinales, Methanothermobacter.

Abstract

Microbial-induced corrosion has been extensively studied in pure cultures. However, Fe^0 corrosion by complex environmental communities, and especially the interplay between microbial physiological groups, is still poorly understood. In this study, we combined experimental physiology and metagenomics to explore Fe^0-dependent microbial interactions between physiological groups enriched from anoxic climate lake sediments. Then, we investigated how each physiological group interacts with Fe^0. We offer evidence for a new interspecies interaction during Fe^0 corrosion. We showed that acetogens enhanced methanogenesis but were negatively impacted by methanogens (opportunistic microbial interaction). Methanogens were positively impacted by acetogens. In the metagenome of the corrosive community, the acetogens were mostly represented by *Clostridium* and *Eubacterium,* the methanogens by *Methanosarcinales*, *Methanothermobacter* and *Methanobrevibacter.* Within the corrosive community, acetogens and methanogens produced acetate and methane concurrently, however at rates that cannot be explained by abiotic H_2-buildup at the Fe^0 surface. Thus, microbial-induced corrosion might have occurred via a direct or enzymatically mediated electron uptake from Fe^0. The shotgun metagenome of *Clostridium* within the corrosive community contained several H_2-releasing enzymes including [FeFe]-hydrogenases, which could boost Fe^0-dependent H_2-formation as previously shown for pure culture acetogens. Outside the cell, acetogenic hydrogenases could become a common good for any H_2/CO_2-consuming member in the microbial community including methanogens that rely on Fe^0 as a sole energy source. However, the exact electron uptake mechanism from Fe^0 remains to be unraveled.

1   Introduction

Steel infrastructure extends for billions of kilometers below ground enabling transport and storage of clean water, chemicals, fuels, sewage, but also protection for telecommunication and electricity cables. Climate change has led to extreme weather conditions like severe storms and rainfall. Urban storm and rainfall management in many countries especially northers countries like Denmark involves so called climate lakes (also known as storm water ponds or retention ponds) harvesting rainfall at large scale thus alleviating stormwater runoff in the cities (Mishra et al., 2020). If stormwater runoff is improperly detained, undergrown steel infrastructure could suffer tremendous damage. Damages induced by microbial induced corrosion (MIC) in the underground are often discovered too late, leading to environmental and economic devastation. Thus, it is important to be able to predict the lifespan of the material if exposed to microbial communities native to the site where steel structures are located. This would lead to effective replacement strategies and

recuperation of the metal prior to accidental spills that may be detrimental to the surrounding
environment (Arriba-Rodriguez et al., 2018; Skovhus et al., 2017; Usher et al., 2014a).
Corrosion occurring in climate lakes is poorly understood. In this study, we investigate corrosion by
microorganisms from the anoxic sediments of a danish climate lake. In such anoxic environments
where non-sulfidic conditions prevail, steel was expected to persist unharmed for centuries (Arriba-
Rodriguez et al., 2018; Skovhus et al., 2017; Usher et al., 2014a). And yet, researchers showed that
certain groups of anaerobes (methanogens and acetogens) strip electrons off the Fe^0 surface leading
to MIC (Kato et al., 2015; Mand et al., 2014, 2016; Mori et al., 2010; Zhang et al., 2003). Previous
studies showed that MIC in non-sulfidic environments is often linked to the presence of acetogens
like *Clostridium* and methanogens like *Methanosarcinales* on the surface of the corroded steel
structure (Kato et al., 2015; Mand et al., 2014, 2016; Mori et al., 2010; Zhang et al., 2003; Zhu et al.,
2003). It was therefore suggested that *Methanosarcinales* were indirectly involved in corrosion,
growing in a mutualistic relationship with the acetogens, and allegedly both groups were gaining
from the interaction (Mand et al., 2016; Zhang et al., 2003). This assumption was based on acetogens
producing acetate, which would be then consumed by acetotrophic *Methanosarcinales* methanogens,
acetogens were expected to be favored by the removal of their metabolic product - acetate. Such a
mutualistic association on Fe^0 between acetogenic *Clostridium* and methanogenic *Methanosarcinales*
has not been yet demonstrated. In contrast, we recently showed that instead of acting cooperatively
on Fe^0, acetogens and methanogens competed for Fe^0-electrons (Palacios et al., 2019a). Since,
interspecies interactions on Fe^0 are scantily examined, here we investigated the interplay between
climate lake acetogens (reaction 1) and methanogens (reaction 2) when provided solely with Fe^0 as
their electron donor.
$4Fe^0 + 2CO_2 + 4HCO_3^- + 4H^+ \rightarrow 4FeCO_3 + CH_3COOH + 2H_2O$ ($\Delta G0$' = -388 kJ/mol; Reaction 1)
$4Fe^0 + CO_2 + 4HCO_3^- + 4H^+ \rightarrow 4FeCO_3 + CH_4 + 2H_2O$ ($\Delta G0$' = -446 kJ/mol; Reaction 2)
Theoretically, under standard thermodynamic conditions, methanogens should have an advantage
over acetogens when provided with Fe^0 as sole electron donor (Reactions 1 & 2). Especially, since
methanogens, unlike acetogens, are more effective at retrieving abiotic H$_2$ (formed on Fe^0) due to
their low H$_2$-uptake thresholds (Drake et al., 2002; Kotsyurbenko et al., 2001). Several groups of
methanogens could corrode Fe^0 independent of acetogenic bacteria, including species of
Methanosarcina (Belay and Daniels, 1990; Boopathy and Daniels, 1991; Daniels et al., 1987),
Methanobacterium (Belay and Daniels, 1990; Dinh et al., 2004; Lorowitz et al., 1992) and
Methanococcus (Lienemann et al., 2018c; Mori et al., 2010; Tsurumaru et al., 2018; Uchiyama et al.,
2010). The mechanism by which methanogens corrode Fe^0, has been debated and includes reports
which suggest they retrieve abiotic-H$_2$ off the Fe^0 surface (Daniels et al., 1987), retrieve electrons
directly using an unknown electron-uptake mechanism (Beese-Vasbender et al., 2015; Dinh et al.,
2004) or use extracellular enzymes, which stimulate enzymatic H$_2$-evolution or formate generation
on the Fe^0-surface (Deutzmann et al., 2015a; Lienemann et al., 2018c; Tsurumaru et al., 2018). The
later mechanisms were especially relevant for *Methanococcus* species which harbored an unstable
genomic island encoding [NiFe]-hydrogenases along with the heterodisulfide reductase super
complex involved in formate generation (Lienemann et al., 2018c; Tsurumaru et al., 2018).
And yet, oftentimes acetogens dominate corrosive communities, outcompeting methanogens when
concentrations of H$_2$ are high and temperatures are low, presumably due to the higher kinetics (V$_{max}$)
of their hydrogenases (Kotsyurbenko et al., 2001). Moreover, unlike methanogens, acetogens
contain [FeFe]-hydrogenases (Peters et al., 2015), which could retrieve electrons directly from Fe^0
for proton reduction to H$_2$ (Mehanna et al., 2008, 2016; Rouvre and Basseguy, 2016).
In this study, we were interested to understand the interspecies dynamics on Fe^0 of acetogens and
methanogens from a climate lake. We used a combination of physiological experiments, inhibition
strategies and whole metagenomic analyses to study the interactions of acetogens and methanogens
during Fe^0 corrosion. In contrast to our previous report on a corrosive coastal community (Palacios et

al., 2019a), in this climate lake we observed a different type of microbial interaction, where
acetogens (*Clostridium*) were negatively impacted by the presence of methanogens whereas
methanogens were benefiting from their presence in a parasitic (-/+) type of interaction while
inducing Fe^0 corrosion.

2   Materials and methods

2.1   Sample collection and enrichment culture conditions

Sediment cores were sampled during the month of July 2016 from a small climate lake located near a
construction site on the campus of the University of Southern Denmark (SDU), Odense. The salinity
of the lake was 0.6 psu, and gas bubbles (including methane) were continuously released to the water
surface while sampling. Sediment cores were sliced in the laboratory, and the depth horizon 15- 20
cm was used for downstream enrichments in a DSM modified 120 media (modifications: 0.6g/L
NaCl, without casitone, without sodium acetate, without methanol, and without $Na_2S \times 9H_2O$). The
enrichment cultures were prepared in 50 mL blue butyl-rubber-stoppered glass vials with an anoxic
headspace of a CO_2: N_2 gas mix (20:80, v/v). Iron granules (99.98% Thermo Fisher, Germany) or
iron coupons (3cm × 1cm × 1mm) were the only source of electrons over the course of five
successive transfers. All incubations were performed in triplicate.
All enrichments were transferred when methane production reached stationary phase. DNA
extractions, SEM analyses, and further experiments were performed at the fourth transfer, after 2
years of enrichment on Fe^0. In addition, methanogen-specific coenzyme F_{420} auto-fluorescence was
monitored via routine microscopy to confirm the presence or absence of methanogens. To evaluate
the solitary corrosive potential of methanogens, we blocked all bacteria with an antibiotic cocktail
200 µg/mL of kanamycin and 100 µg/mL of ampicillin as done before (Palacios et al., 2019a). To
evaluate the solitary corrosive potential of the acetogens, we inhibited all methanogens with 2 mM 2-
bromoethanesulfonate (BES) (Zhou et al., 2011).

2.2   Chemical analyses

Methane and hydrogen concentrations were analyzed on a Thermo Scientific Trace 1300 gas
chromatograph system coupled to a thermal conductivity detector (TCD). The injector was operated
at 150°C and the detector at 200°C with 1.0 mL/min argon as reference gas. The oven temperature
was constant at 70°C. Separation was done on a TG-BOND Msieve 5A column (Thermo Scientific;
30-m length, 0.53-mm i.d., and 20-µm film thickness) with argon as carrier gas at a flow of 25
mL/min. The GC was controlled and automated by a Chromeleon software (Dionex, Version 7). On
our set-up the limit of detection for H_2 and CH_4 was 5 µM.
Acetate production was measured using the Dionex ICS-1500 Ion Chromatography System (ICS-
1500) equipped with the AS50 autosampler, and an IonPac AS22 column coupled to a conductivity
detector (31 mA). For separation of volatile fatty acids, we used 4.5 mM Na_2CO_3 with 1.4 mM
$NaHCO_3$ as eluent. The run was isothermic at 30°C with a flow rate of 1.2mL/min. The limit of
detection for acetate was 0.1 mM.

2.3   DNA purification and metagenomic analyses

DNA was isolated as previously described (Palacios et al., 2019a), using a combination of two
commercially available kits: MasterPure™ Complete DNA and RNA Purification Kit (Epicenter,
Madison, Wi, USA), and the Fast Prep spin MP_{tm} kit for soil (Mobio/Qiagen, Hildesheim, Germany).
DNA quality was verified on an agarose gel, and DNA was quantified on a mySPEC
spectrophotometer (VWR®/ Germany). Whole metagenome sequencing was performed on a

NovaSeq 6000 system, using an Illumina TrueSeq PCR-free approach via a commercially available
service (Macrogen/ Europe). Unassembled DNA sequences were merged, quality checked, and
annotated using the Metagenomics Rapid Annotation (MG-RAST) server (v4.03) with default
parameters (Meyer et al., 2008). Illumina True Seq sequencing resulted in 1,982,966 high-quality
reads of a total of 2,137,679 with an average length of 102 bp. For taxonomic analyses, the
metagenomic data was compared with the RefSeq (Tatusova et al., 2015) database available on the
MG-RAST platform. The rarefaction curve indicated that most of the prokaryotic diversity was
covered in our sample. To investigate functional genes in the metagenome, sequencing reads were
annotated against the KEGG Orthology (KO) reference database. Both taxonomic and functional
analyses were performed with the following cutoff parameters: e-value of 1e–5, a minimum identity
of 80%, and a maximum alignment length of 15 bp. The metagenome data is available at MG-RAST
with this ID:xxxxxx.

2.4   Removal of corrosion crust and corrosion rates

The corrosion crust from the iron coupons was removed with inactivated acid (10% hexamine in 2M
HCl) (Enning and Garrelfs, 2014). Then, the iron coupons were dried with N_2 gas stream, and
weighted.

2.5   Scanning electron microscopy

Fixation of cells on iron coupons was performed anaerobically by adding 2.5% glutaraldehyde in
0.1M phosphate buffer (pH 7.3) and incubating at 4°C for 12 h. The corroded coupons were then
washed three times with 0.1 M phosphate buffer at 4°C for 10 min each. Dehydration was
accomplished by a series of anoxic pure ethanol steps (each step 10 min; 35%, 50%, 70%, 80%, 90%,
95% and 100% v/v) (Araujo et al., 2003). The coupons were chemical dried with
hexamethyldisilazane under a gentle N_2 gas stream. Specimens were stored under N_2 atmosphere and
analyzed within 18-24 h at the UMASS electron microcopy facility using the FEI Magellan 400
XHR-SEM with a resolution of 5kV.
160
3   Results and discussion
Here we report on an opportunistic (+/-) interaction on Fe^0, between methanogens and acetogens
from the sediments of a climate lake. In the absence of any other terminal electron acceptor but CO_2,
microorganisms are expected to corrode Fe^0 via either CO_2-reductive methanogenesis ($CO_2 + 8e^- +$
$8H^+ \rightarrow CH_4 + 2H_2O$ / CO_2-reductive methanogenesis) or via acetogenesis coupled with acetoclastic
methanogenesis ($2CO_2 + 8e^- + 8H^+ \rightarrow CH_3COOH + 2H_2O$ / acetogenesis; $CH_3COOH \rightarrow CH_4 + CO_2$
/ acetoclastic methanogenesis).
For the later, acetoclastic methanogens were commonly assumed to be indirectly involved in the
corrosion of Fe^0 since they were expected to establish a mutualistic association (+/+) with acetogens
(Mand et al., 2016; Zhang et al., 2003). However, this is not always the case. We recently showed
that coastal marine methanogens competed (-/-) with acetogens for Fe^0-electrons (Palacios et al.,
2019b). But now, we bring evidence for an opportunistic association between methanogens and
acetogens from the sediments of a climate-lake. The methanogens from these sediments were favored
by the acetogens however could not be explained by acetate-consumption alone. Acetogenic [FeFe]
hydrogenases were heavily represented in the acetogens' metagenome and may induce significant
electron uptake from Fe^0 coupled with H_2-production. When released, hydrogenases may
indiscriminately stimulate the growth of opportunistic hydrogenotrophic methanogens.

3.1   Pitted Fe^0 corrosion

We monitored corrosion by a climate lake community maintained for 2 years on Fe^0 in the absence of
any typical electron acceptors. A time course of corrosion was taken during the fourth transfer on
Fe^0. The microbial community corroded Fe^0 significantly in contrast to cell-free controls according to
microscopy observations (Fig. 1), gravimetric measurements (Fig. 2) and metabolic product build-up
(Fig. 3).
After incubation for several months in the presence of cells the iron sheets were coated with a black
crust, which after removal revealed small pitted corrosion underneath (Fig. 1). Scanning electron
microscopy prior to crust removal shows cells entrapped on Fe^0 in between minerals likely formed
due to biocorrosion (Fig. 1d).
Gravimetric measurements showed that when this climate lake community was provided with Fe^0 it
induced 41% more weight loss and consumed 2.8 ± 0.6 mg more Fe^0 (n=3; p=0.008) than cell-free
controls (Fig. 2).
Metabolic product build-up showed that the microbial-community generated methane and acetate
simultaneously once provided with Fe^0 (Fig. 3), confirming that Fe^0 delivers electrons for two types
of microbial metabolisms, acetogenesis and methanogenesis. As expected, the abiotic controls with
Fe^0 showed no traces of microbial metabolic products (methane and acetate) (Fig. 3a).
During 3-months long incubations with Fe^0, the corrosive community generated acetate transiently
(first month), and ultimately accumulated only methane (Fig. 3b). At the start of the incubation (first
month), acetogenesis rates (68 ± 1 µM acetate/day) surpassed methanogenesis rates (27 ± 6 µM
methane/day) (Fig. 3, Fig. 4a). Whereas during the last two months of incubation, acetogenesis
ceased. At the same time, methanogenesis sped up achieving rates twofold (62.5 ± 5.1 µM
methane/day) above those predicted (28 ± 7.3 µM methane/day) by acetoclastic methanogenesis (Fig.
3, Fig. 4a). These results show that methanogens did not rely on the acetate generated by acetogens
for methanogenesis. Altogether, the microbial community produced 3.3-fold more methane (3.5 ± 0.1
mM) than expected (1.1 ± 0.2 mM) from the H$_2$ evolved abiotically ($2e^- + 2H^+ \rightarrow H_2$) at the Fe^0
surface (Fig. 5). These results show that the microbial community employs effective alternative
mechanisms (other than abiotic H$_2$) to access electrons from the Fe^0-surface. Unraveling these
mechanisms is difficult without pure cultures. Nevertheless, we attempted to determine how the
microorganisms influence each other's metabolism and Fe^0-corrosion by separating each physiologic
group with group-specific inhibitors.

3.2   Unravelling interspecies interactions on Fe^0

In all our enrichments, methane is the final product of the microbial community provided with Fe^0 as
electron donor and CO$_2$ as electron acceptor. Thus, methanogens must interact with acetogens for
example by consuming their metabolic product. There are three possible interspecies interactions that
would give off only methane:
(a) mutualism (+/+) when methanogens feed on the product of the acetogen both partners being
influenced favorably one (acetogen) by the removal of metabolic product the other (methanogen) by
the availability of a food substrate;
(b) commensalism (0/+) when acetogens are unaffected by the presence of the methanogen, whereas
methanogens are influenced favorably e.g., by feeding on acetate, the product of acetogenic
metabolism.
(c) parasitism/scavenging opportunism (-/+) when acetogens are negatively influenced by the
presence of the methanogen, while methanogens are influenced favorably by the presence of the
acetogen.
To test these scenarios, we carried out inhibition experiments to specifically block each metabolic
group. Archaea methanogens were inhibited with 2-bromoethane sulfonate (BES), a coenzyme A
analogue, resulting in favorable conditions solely for acetogens. Bacteria (including acetogens) were

inhibited by a cocktail of antibiotics (kanamycin and ampicillin), thus favoring only methanogens.
Then we compared corrosion by each group alone by documenting corrosion of via gravimetric
measurements and metabolite production (Fig. 2, Fig. 3).
Gravimetric measurements showed that even when separated, methanogens and acetogens remained
significantly more corrosive compared to cell free controls (Fig. 3c, 3d). However, methanogens
were only slightly less corrosive than the mixed community (ca. 5% less, n=3, p=0.18). Whereas,
acetogens were significantly more corrosive alone than they were in the mixed community (ca. 16%
more; n=3, p=0.03). These results indicate that electron uptake from Fe^0 by acetogens was negatively
affected by the presence of the methanogens. The observation that acetogens are negatively impacted
by methanogens was also supported by examining acetate metabolism. The rate of acetate build-up
was lowered by the presence of the methanogens. Thus, the bacterial community alone accumulated
acetate faster (Fig. 3c, 23% rate increase, n=3, p=0.0003) than when acetogens were members of the
mixed community, substantiating the gravimetric results above, which revealed that acetogens were
more corrosive alone (Fig. 2). Together, these results reflect that acetogens are negatively impacted (-
) by the presence of the methanogens.
Methanogens on the other hand, produced 3-fold less methane alone than within the mixed
community (Fig. 3d, n=3, p=0.0002). During the first month of incubation, rates of methanogenesis
were 2-fold faster when acetogens were metabolically active (Fig. 3b) than they were when
methanogens were incubated alone (Fig. 3d). In the mixed community, rates of methanogenesis
increased significantly when acetogens reached stationary, now becoming 4-fold faster than when
methanogens were incubated alone on Fe^0. The rates of methanogenesis could not be linked to
acetate-utilization, since acetate consumption (28±7 µM/day) did not match methane production
(62.5±5µM/day). Thus, methanogens appear to be significantly favored (+) by the presence of the
acetogens but only minutely by the acetate released by acetogens. It appears that methanogens may
be favored by the presence of biogenic-chemicals and enzymes released by acetogens during the
exponential-growth phase and especially during the stationary phase.
Altogether, our results show that during Fe^0-corrosion, acetogens were negatively (-) impacted by the
presence of methanogens whereas methanogens were positively (+) impacted, demonstrating a
parasitic/opportunistic (-/+) type of interaction between these two physiologic groups.
255
A possible negative effect on the acetogens could be due to the alkalinization of the media by protons
being dislocated from solution during CO_2 conversion to methane. During CO_2 conversion by
methanogens the pH often becomes alkaline (Xu et al., 2014). Consequently, we verified the pH
change over time. Typically, our cultivation media has a pH of 7.06±0.02. However, after six months
of incubation, four cultures incubated solely with Fe^0 exhibited an alkaline pH of 8.47±0.06. To
verify whether alkalinization was dependent on cellular activity we monitored pH changes in abiotic
Fe^0-media, versus Fe^0-media with cells (transfer 10) over the course of 30 days. We noticed a
significantly higher alkalinization in media with cells compared to media without cells starting with
day 15 (Fig. 6). Typically, CO_2 reducing acetogenesis is negatively affected by alkaline conditions
(Mohanakrishna et al., 2015), which explains the sudden decrease in acetogenic activity after day 15.
On the other hand, alkaline conditions inhibit acetotrophic methanogenesis, while favoring CO_2
reducing methanogenesis (Phelps and Zeikus, 1984).
268
To further investigate the possible interplay between acetogens and methanogens we investigated the
metabolic potential of the community by shotgun metagenomics.

3.3   Corrosive acetogens and methanogens

At transfer four, after 1 month of incubation, we studied the microbial community by shotgun
metagenomics. Additional details about the results of shotgun metagenomics are available in the
supplementary material. Pertinent to energy metabolism, the shotgun metagenome reinforced
physiological observations confirming that the enriched corrosive community employs two major
respiratory metabolisms: acetogenesis and methanogenesis.
277
3.3.1 Acetogens
By shotgun metagenomics of the corrosive community, we discovered several genera of acetogens
(Table 1). Of these genera, *Clostridium* had the best relative sequence abundance of all Bacteria
(62.1%; Fig. 7a) and the best coverage of the Wood-Ljungdahl pathway for autotrophic acetogenesis
(Fig.7, Table 1). *Clostridium* includes several species of autotrophs that use H_2 as electron donor
(Bengelsdorf et al., 2018) but also electrodes (Nevin et al., 2011) and Fe^0 (Monroy et al., 2011).
Besides, *Clostridium* was previously enriched on Fe^0 from environments such as scraped bicycles
thrown in a Dutch channel (Philips et al., 2019), rice paddies (Kato and Yumoto, 2015) or oilfield
production waters (Ma et al., 2019). These studies along with ours suggests *Clostridium* is a likely
corrosive acetogen when Fe^0 becomes available in their environment.
Another autotrophic acetogen reasonably well represented in the shotgun metagenome was
Eubacterium (1.9% of all Bacteria; Fig. 7a), which displayed the second-best gene recovery of the
Wood Ljungdahl pathway (Table 1). *Eubacterium* includes two known species of autotrophic
acetogens that use H_2 as electron donor (Mechichi et al., 1998; Schwartz and Friedrich, 2006).
Besides *Eubacterium* has been found in communities from thermogenic gas wells (Struchtemeyer et
al., 2011) and stimulated Fe^0 corrosion when co-existing with sulfate reducers, but have not been
shown to be involved in Fe^0 corrosion when alone (Dowling et al., 1992).
Other known autotrophic acetogens like *Moorella, Carboxydothermus*, *Treponema*,
Desulfotomaculum and *Thermoanaerobacter* were scarce in this corrosive metagenome (<0.5% of all
Bacteria) with a poor representation of the WL-pathway (Fig. 7a, Table 1). Of these, members of the
genus *Desulfotomaculum* have been often shown to corrode Fe^0 under sulfate reducing conditions
(Anandkumar et al., 2009; Cetin and Aksu, 2009; Liu et al., 2019), but it remains to be investigated
whether they can corrode Fe^0 under acetogenic conditions.
Moreover, the metagenomes contained genera that include H_2-utilizing species like *Bacillus* (1.6%),
Ruminococcus (1.1%), *Desulfitobacterium* (1.1%) (Schwartz and Friedrich, 2006) and *Alkaliphilus*
(1.3%) (Roh et al., 2007). These organisms use H_2 when electron acceptors are available. But it is
unknown whether any of these species can act as autotrophic acetogens, which is the only possibility
in this enrichment. Of these, some *Bacillus* induced corrosion under nitrate reducing conditions (Wan
et al., 2018; Xu et al., 2013), but in other instances *Bacillus* species inhibited corrosion by forming a
passivating film of extracellular polymeric substances and/or calcite (Guo et al., 2019; Li et al.,
2019). Corrosion was also inhibited by a *Desulfitobacterium* that oxidized Fe(III)-minerals to
vivanite, forming a protective passivating layer on the metal surface (Comensoli et al., 2017).
Desulfitobacterium's protective effect against corrosion was even confirmed on archaeological iron
artefacts (Comensoli et al., 2017).
Other well represented bacterial groups were *Bacteroidetes* (5.4% of all Bacteria) and
Parabacteroidetes (4.2%), which are typically chemoorganotrophs (Sakamoto and Benno, 2006;
Wexler, 2007) and may be involved in fermentation of decaying organic matter.
These results suggest that *Clostridium* is the central lithotrophic acetogen corroding Fe^0 in these
enrichments.

3.3.2 Methanogens

The archaeal community was diverse with the highest relative sequence abundance matching members of the classes *Methanomicrobia* (45% of Archaea), *Methanobacteria* (24% of Archaea) and *Methanococci* (10% of Archaea).

The metagenome contained both acetate-utilizing methanogens and H_2/CO_2 utilizing methanogens. Acetate-utilizing methanogens belonging to the order *Methanosarcinales* were the best represented order making up for 32% of Archaea sequences, with *Methanosarcina* (19% of Archaea) showing the highest relative sequence abundance followed by *Methanosaeta* (9% of Archaea). Both genera showed good coverage of the methanogenesis pathway, however we could only find the 16S rRNA gene of *Methanosaeta*.

Generally, the role of acetotrophic *Methanosarcinales* in corrosion is assumed to be syntrophic and not directly corrosive (Mand et al., 2014; Zhang et al., 2003). However, previous studies reported that *Methanosarcina* species are corrosive (Daniels et al., 1987), and get enriched on Fe^0 from the marine environment (Palacios et al., 2019a) or oilfield production waters (Ma et al., 2019). Often, *Methanosarcina* are members of corrosive biofilms on steel pipelines from oil production facilities (Lahme et al., 2021; Vigneron et al., 2016), gas industry pipelines (Zhu et al., 2003) and sewer system pipelines (Cayford et al., 2017). Unlike *Methanosarcina*, *Methanosaeta* have never been reported as independently corrosive, although they easily colonize Fe^0-coupons in enrichments from oil production facilities (Mand et al., 2014) and have been often found as members of biofilms on corroded pipelines from such facilities (Conlette et al., 2016; Lahme et al., 2021).

Best represented H_2/CO_2-utilizing methanogens in relative gene abundance were members of *Methanothermobacter* (10% of Archaea) and *Methanobrevibacter* (9 % of Archaea) (Fig. 7b). These were also the genera with the highest number of gene hits for the CO_2 reduction pathway (Table 2). *Methanothermobacter* species have been previously shown capable of Fe^0-corrosion in pure culture (e.g., *M. thermoautotrophicum* (Daniels et al., 1987; Karr, 2013) or *M. thermoflexus* (Mayhew et al., 2016)). On the other hand, a *Methanothermobacter* strain isolated from a corroded oil pipeline could not corrode Fe^0 alone, and required partnering with other microorganisms (Davidova et al., 2012). Often, *Methanothermobacter* are enriched or live within biofilms built on corroded oil pipelines (Liang et al., 2014; Okoro et al., 2017), corroded sea-submerged railway lines (Usher et al., 2014b), or oil facility infrastructure (Duncan et al., 2009; Lenchi et al., 2013; Suarez et al., 2019). Recently it was proposed that members of *Methanobacteriales* (order that includes *Methanothermobacter*) lead to the buildup of a carbonate-rich passivating layer with protective / anticorrosive properties (in 't Zandt et al., 2019). A possible protective role of *Methanothermobacter* in steel corrosion remains, however, to be demonstrated experimentally.

Methanobrevibacter species on the other hand, are less often associated with corrosion with only a few studies reporting the presence of *Methanobrevibacter* in corrosive biofilms (Gomez-Alvarez et al., 2012; Schlegel et al., 2018; Usher et al., 2014b), while their role in corrosion remains unclear.

3.4   Possible mechanism of electron uptake during Fe^0 corrosion

Since abiotic H_2 does not explain the enhanced corrosion we observed, other mechanisms likely to enhance Fe^0-corrosion by methanogens and acetogens in our enrichments such as: (1) the maintenance of low H_2-partial pressure (Philips, 2020); (2) enzymatically mediated electron uptake (e.g., hydrogenases) (Deutzmann et al., 2015a; Lienemann et al., 2018b; Rouvre and Basseguy, 2016) or (3) direct electron uptake (e.g., via outermembrane cytochromes) (Tang et al., 2019).

In methanogens and acetogens it is unlikely that Fe^0 oxidation proceeds via self-produced shuttles. This is because, although several other microorganisms produce their own shuttles to access

363   extracellular electrons donors (Sund et al., 2007) acetogens and methanogens have never been
364   documented to produce shuttles.
365
366   It is also unlikely that the community relies on a direct mechanism of electron uptake from Fe^0,
367   because it includes several groups of effective H_2-utilizing microorganisms which could stimulate
368   corrosion either by maintaining a low H_2-partial pressure (Philips, 2020) or by enhancing electron
369   uptake from Fe^0 with the help of enzymes (Deutzmann et al., 2015b).
370
The first mechanism involves the maintenance of low H_2 partial pressure at the Fe^0 surface due to the
low H_2 thresholds of the microorganisms (concentration at which H_2-uptake is not observed). It has
been hypothesized that microorganisms with low H_2-thresholds increase the H_2 evolution reaction at
the Fe^0 surface (Philips, 2020). If microorganisms with low H_2 thresholds were better Fe^0 corroders
in this corrosive community, strict hydrogenotrophic methanogens should be favored since it is the
group with the lowest H_2-threshold. They were not favored. Instead acetogens known to have high
H_2-thresholds were favored (Fig. 2, p=0.003). Generally, strict CO_2-reducing methanogens exhibit
very low H_2-uptake thresholds (0.1-4 Pa, except for *M. wolfei* with 15 Pa) (Neubeck et al., 2016)
followed by *Methanosarcinales* methanogens which exhibit higher H_2-thresholds (13-46 Pa) during
CO_2 reductive methanogenesis. Even during organotrophy (acetate-grown), *Methanosarcinales*
maintain a leveled H_2-threshold concentration (20 Pa for *M. acetivorans* and 50 Pa for *M.*
thermophila). On the other hand, CO_2 reducing acetogens exhibit high H_2-uptake thresholds (5-600
Pa, rarely below 10 Pa) (Philips, 2020). Thus, it is unlikely the maintenance of low H_2 partial
pressure plays aa major role in enhancing Fe^0 corrosion in this community.
385
On the other hand, it is possible that H_2-evolving enzymes boost microbial uptake of electrons from
Fe^0. Several H_2-evolving enzymes were found in the metagenome of the corrosive community
including: [FeFe] hydrogenases of acetogens, [NiFe] hydrogenases of strict hydrogenotrophic
methanogens the formate/H_2-evolving enzyme supercomplex of strict hydrogenotrophic methanogens
(Mvh/Hdr: methyl viologen reducing hydrogenase / heterodisulfide reductase), but also enzymes that
evolve H_2 as a side reaction, like nitrogenases (Table 3).
392
The [FeFe]-hydrogenases of acetogens have characteristic high H_2-production rates (Adams, 1990)
and can take up electrons directly from Fe^0 to carry out proton reduction to H_2 (Mehanna et al., 2008;
Rouvre and Basseguy, 2016). The formate/H_2-evolving enzyme supercomplex, Mvh/Hdr was shown
to take up electrons directly from Fe^0 to oxidize during formate synthesis (Lienemann et al., 2018a).
In this case, formate-utilizing microorganisms would benefit. The [NiFe] hydrogenases of
methanogens, especially those located on the MIC-island, appear to be crucial in inducing severe
corrosion by hydrogenotrophic methanogens like *Methanobacterium* and *Methanococcus* (Lahme et
al., 2021; Tsurumaru et al., 2018). However, the MIC island has not been identified in any other
genera of methanogens.Thus, we could not detect the MIC-island in any of the genomes available for
Methanothermobacter, Methanobrevibacter or *Methanosarcina* and *Methanosaeta* when using *in*
silico PCR with specific MIC-island primers (Lahme et al., 2021).. On the other hand, using the
same *in silico* approach we could for example detect the MIC-island in a *Methanobacterium* species
(*M. congolense*) or in *Methanococcus* species (*M. maripaludis* OS7 and KA1) which have been
documented to induce severe corrosion (Tsurumaru et al., 2018; Uchiyama et al., 2010).
407
Without the MIC-island these climate lake methanogens may be using an alternative approach to
access Fe^0-electrons effectively. Since acetate alone cannot explain the high methanogenesis rates,
we hypothesize that acetogenic enzymes promote electron uptake from Fe^0 to form H_2 benefiting the
methanogens. Thus, when acetogenesis becomes inhibited by the pH increase (prompted by

methanogens delocalizing protons from solution into the gas phase), acetogen cell lysis cold release
[FeFe]-hydrogenases and nitrogenases, and thereby produce H$_2$ at the Fe^0 surface. Enzymatically
released H$_2$ would benefit hydrogenotrophic methanogens like *Methanothermobacter* and
Methanobrevibacter and could explain the acceleration of methanogenesis when acetogenesis ceased
(Fig.3, Fig. 4). Regarding *Methanosarcinales,* their role in Fe^0 corrosion could be simply that of
commensals feeding on the acetate generated by acetogens, or they could be involved in direct
electron uptake from extracellular electron donors (Rotaru et al., 2014b, 2014a; Yee et al., 2019; Yee
and Rotaru, 2020) including Fe^0 (Palacios et al., 2019a). However, direct electron uptake in
Methanosarcinales is poorly understood and remains to be further investigated.

4   Conclusion

Interspecies interactions at the Fe^0-surface have been poorly investigated. Here we bring evidence for
an opportunistic interaction (+/-) on Fe^0 between methanogens (*Methanothermobacter*,
Methanobrevibacter and *Methanosarcinales*) and acetogens (esp. *Clostridium*) enriched from the
sediments of a climate lake. We observed that the acetogens were more effective Fe^0-corroders (and
acetate producers) when decoupled from methanogens with the help of a specific inhibitor – 2-
bromoethane sulfonate. Methanogens, on the other hand, became less effective Fe^0-dependent
methane producers when decoupled from acetogens with the help of antibiotics. Since abiotic H$_2$
could not explain the corrosion rates, we screened a shotgun metagenome for hints of enzymatic-
mediated H$_2$-evolution. The metagenome of acetogens (esp. *Clostridium*) contained [FeFe]
hydrogenases, effective in direct electron uptake from Fe^0 in order to reduce protons to H$_2$. On the
other hand, the MIC-island, a typical indicator for enzymatic mediated electron uptake in
methanogens was not detected in *Methanothermobacter*, *Methanobrevibacter* or *Methanosarcinales*.
As acetogenesis ceased methanogenesis rates picked up, the later could not be explained by acetate
turnover. Therefore, we propose that the methanogenic community benefits from H$_2$-evolving
enzymes released by acetogens during stationary phase. With these results we expand the diversity of
microbial interactions on Fe^0 between acetogens and methanogens (from competition (Palacios et al.,
2019b) to opportunism (this study)). Some studied suggested that methanogens like
Methanothermobacter may have a protective role during corrosion (in 't Zandt et al., 2019), however
here we show how such methanogens are positively affected by acetogenic partners. In consequence
we recommend that the corrosive effects of methanogens should be investigated not only in pure
culture but also in consortia with bacterial partners before suggesting they have a protective
anticorrosive role.

5   Conflict of Interest

445 The authors declare that the research was conducted in the absence of any commercial or financial
446 relationships that could be construed as a potential conflict of interest.

6   Author Contributions

448 AER and PAP developed the idea. PAP carried out all experimental work and some of the analyses.
449 AER carried out some of the data analyses. PAP drafted the paper. AER wrote the final manuscript.

7   Funding

451 This is a contribution to a Sapere Aude Danish Research Council grant awarded to AER (grant
452 number 4181-00203).

8   Acknowledgments

We would like to thank Oona Snoeyenbos-West, Carolin Löscher, Satoshi Kawaichi and Christian
Furbo Reeder for help with sampling and valuable discussions. We would like to thank Joy Ward for
help with preparing samples for scanning electron microscopy and we'd like to recognize the
University of Massachusetts electron microscopy facility which provided access and training of PAP
on the FEI Magellan XHR-SEM.

9   References

Adams, M. W. W. (1990). The structure and mechanism of iron-hydrogenases. *Biochim. Biophys.*
Acta (BBA)-Bioenergetics 1020, 115–145.

Anandkumar, B., Rajasekar, A., Venkatachari, G., and Maruthamuthu, S. (2009). Effect of
thermophilic sulphate-reducing bacteria (Desulfotomaculum geothermicum) isolated from
Indian petroleum refinery on the corrosion of mild steel. *Curr. Sci.*, 342–348.

Araujo, J. C., Téran, F. C., Oliveira, R. A., Nour, E. A. A., Montenegro, M. A. P., Campos, J. R., et
al. (2003). Comparison of hexamethyldisilazane and critical point drying treatments for SEM
analysis of anaerobic biofilms and granular sludge. *J. Electron Microsc. (Tokyo).* 52, 429–33.

Arriba-Rodriguez, L., Villanueva-Balsera, J., Ortega-Fernandez, F., and Rodriguez-Perez, F. (2018).
Methods to Evaluate Corrosion in Buried Steel Structures: A Review. *Metals (Basel).* 8, 334.
doi:10.3390/met8050334.

Beese-Vasbender, P. F., Grote, J.-P., Garrelfs, J., Stratmann, M., and Mayrhofer, K. J. J. (2015).
Selective microbial electrosynthesis of methane by a pure culture of a marine lithoautotrophic
archaeon. *Bioelectrochemistry* 102, 50–55. doi:10.1016/j.bioelechem.2014.11.004.

Belay, N., and Daniels, L. (1990). Elemental metals as electron sources for biological methane
formation from COz. *Antonie Van Leeuwenhoek* 57, 1–7.

Bengelsdorf, F. R., Beck, M. H., Erz, C., Hoffmeister, S., Karl, M. M., Riegler, P., et al. (2018).
"Bacterial anaerobic synthesis gas (syngas) and CO2+ H2 fermentation," in *Advances in applied*
microbiology (Elsevier), 143–221.

Boopathy, R., and Daniels, L. (1991). Effect of pH on anaerobic mild steel corrosion by
methanogenic bacteria. *Appl. Environ. Microbiol.* 57, 2104–2108. Available at:
http://aem.asm.org/cgi/content/long/57/7/2104.

Cayford, B. I., Jiang, G., Keller, J., Tyson, G., and Bond, P. L. (2017). Comparison of microbial
communities across sections of a corroding sewer pipe and the effects of wastewater flooding.
Biofouling 33, 780–792. doi:10.1080/08927014.2017.1369050.

Cetin, D., and Aksu, M. L. (2009). Corrosion behavior of low-alloy steel in the presence of
Desulfotomaculum sp. *Corros. Sci.* 51, 1584–1588.

Comensoli, L., Maillard, J., Albini, M., Sandoz, F., Junier, P., and Joseph, E. (2017). Use of Bacteria
To Stabilize Archaeological Iron. *Appl. Environ. Microbiol.* 83, 1–14. doi:10.1128/AEM.03478-
16.

Conlette, O. C., Emmanuel, N. E., and Chijoke, O. G. (2016). Methanogen Population of an Oil

Production Skimmer Pit and the Effects of Environmental Factors and Substrate Availability on
Methanogenesis and Corrosion Rates. *Microb. Ecol.* 72, 175–184. doi:10.1007/s00248-016-
0764-2.

Daniels, L., Belay, N., Rajagopal, B., and Weimer, P. (1987). Bacterial Methanogenesis and Growth
from CO2 with Elemental Iron as the Sole Source of Electrons. *Science (80-.).* 237, 509–511.

Davidova, I. A., Duncan, K. E., Perez-Ibarra, B. M., and Suflita, J. M. (2012). Involvement of
thermophilic archaea in the biocorrosion of oil pipelines. *Environ. Microbiol.* 14, 1762–1771.
doi:10.1111/j.1462-2920.2012.02721.x.

Deutzmann, J. S., Sahin, M., and Spormann, A. M. (2015a). Extracellular Enzymes Facilitate
Electron Uptake in Biocorrosion and Bioelectrosynthesis. *MBio* 6, 1–8.
doi:10.1128/mBio.00496-15.Editor.

Deutzmann, J. S., Sahin, M., and Spormann, A. M. (2015b). Extracellular Enzymes Facilitate
Electron Uptake in Biocorrosion and Bioelectrosynthesis. *MBio* 6, 293.
doi:10.1128/mBio.00496-15.

Dinh, H. T., Kuever, J., Mußmann, M., Hassel, A. W., Mussman, M., Hassel, A. W., et al. (2004).
Iron corrosion by novel anaerobic microorganisms. *Nature* 427, 829–832.
doi:10.1038/nature02349.1.2.3.4.5.6.7.8.9.10.Wilson.

Dowling, N. J. E., Brooks, S. A., Phelps, T. J., and White, D. C. (1992). Effects of selection and fate
of substrates supplied to anaerobic bacteria involved in the corrosion of pipe-line steel. *J. Ind.
Microbiol.* 10, 207–215.

Drake, H. L., Küsel, K., and Matthies, C. (2002). Ecological consequences of the phylogenetic and
physiological diversities of acetogens. *Antonie Van Leeuwenhoek* 81, 203–213.
doi:10.1023/A:1020514617738.

Duncan, K. E., Tanner, R. S., Tringe, S. G., and Bristow, J. I. M. (2009). Biocorrosive Thermophilic
Microbial Communities in Alaskan North Slope Oil Facilities. *Environ. Sci. Technol.* 43, 7977–
7984.

Enning, D., and Garrelfs, J. (2014). Corrosion of iron by sulfate-reducing bacteria: new views of an
old problem. *Appl. Environ. Microbiol.* 80, 1226–36. doi:10.1128/AEM.02848-13.

Gomez-Alvarez, V., Revetta, R. P., and Domingo, J. W. S. (2012). Metagenome analyses of corroded
concrete wastewater pipe biofilms reveal a complex microbial system. *BMC Microbiol.* 12.
doi:10.1186/1471-2180-12-122.

Guo, Z., Pan, S., Liu, T., Zhao, Q., Wang, Y., Guo, N., et al. (2019). Bacillus subtilis inhibits Vibrio
natriegens-induced corrosion via biomineralization in seawater. *Front. Microbiol.* 10, 1111.

in 't Zandt, M. H., Kip, N., Frank, J., Jansen, S., van Veen, J. A., Jetten, M. S. M., et al. (2019).
High-Level Abundances of Methanobacteriales and Syntrophobacterales May Help To Prevent
Corrosion of Metal Sheet Piles. *Appl. Environ. Microbiol.* 85, 1–15. doi:10.1128/AEM.01369-
19.

Karr, E. A. (2013). Examination of metal corrosion by Desulfomicrobium thermophilum,
Archaeoglobus fulgidus, and Methanothermobacter thermautotrophicus. *Bios* 84, 59–64.

Kato, S., and Yumoto, I. (2015). Isolation of acetogenic bacteria that induce biocorrosion by utilizing
metallic iron as the sole electron donor. *Appl. Environ. Microbiol.* 81, 67–73.
doi:10.1128/AEM.02767-14.

Kato, S., Yumoto, I., and Kamagata, Y. (2015). Isolation of acetogenic bacteria that induce
biocorrosion by utilizing metallic iron as the sole electron donor. *Appl. Environ. Microbiol.* 81,
67–73. doi:10.1128/AEM.02767-14.

Kotsyurbenko, O. R., Glagolev, M. V., Nozhevnikova, A. N., and Conrad, R. (2001). Competition
between homoacetogenic bacteria and methanogenic archaea for hydrogen at low temperature.
FEMS Microbiol. Ecol. 38, 153–159. doi:10.1111/j.1574-6941.2001.tb00893.x.

Lahme, S., Mand, J., Longwell, J., Smith, R., and Enning, D. (2021). Severe corrosion of carbon steel
in oil field produced water can be linked to methanogenic archaea containing a special type of
[NiFe] hydrogenase. *Appl. Environ. Microbiol.* 1, 2–7. doi:10.1128/AEM.01819-20.

Lenchi, N., Inceoğlu, Ö., Kebbouche-Gana, S., Gana, M. L., Llirós, M., Servais, P., et al. (2013).
Diversity of Microbial Communities in Production and Injection Waters of Algerian Oilfields
Revealed by 16S rRNA Gene Amplicon 454 Pyrosequencing. *PLoS One* 8.
doi:10.1371/journal.pone.0066588.

Li, S., Li, L., Qu, Q., Kang, Y., Zhu, B., Yu, D., et al. (2019). Extracellular electron transfer of
Bacillus cereus biofilm and its effect on the corrosion behaviour of 316L stainless steel.
Colloids Surfaces B Biointerfaces 173, 139–147.

Liang, R., Grizzle, R. S., Duncan, K. E., McInerney, M. J., and Suflita, J. M. (2014). Roles of
thermophilic thiosulfate-reducing bacteria and methanogenic archaea in the biocorrosion of oil
pipelines. *Front. Microbiol.* 5, 1–12. doi:10.3389/fmicb.2014.00089.

Lienemann, M., Deutzmann, J. S., Milton, R. D., Sahin, M., and Spormann, A. M. (2018a).
Mediator-free enzymatic electrosynthesis of formate by the *Methanococcus maripaludis*
heterodisulfide reductase supercomplex. *Bioresour. Technol.* 254, 278–283.
doi:10.1016/j.biortech.2018.01.036.

Lienemann, M., Deutzmann, J. S., Milton, R. D., Sahin, M., and Spormann, A. M. (2018b).
Mediator-free enzymatic electrosynthesis of formate by the *Methanococcus maripaludis*
heterodisulfide reductase supercomplex. *Bioresour. Technol.* 254, 278–283.
doi:10.1016/j.biortech.2018.01.036.

Lienemann, M., Deutzmann, J. S., Milton, R., Sahin, M., and Spormann, A. M. (2018c). Mediator-
free enzymatic electrosynthesis of formate by the Methanococcus maripaludis heterodisulfide
reductase supercomplex. *Bioresour. Technol.* Accepted. doi:10.1016/j.biortech.2018.01.036.

Liu, H., Meng, G., Li, W., Gu, T., and Liu, H. (2019). Microbiologically influenced corrosion of
carbon steel beneath a deposit in CO2-saturated formation water containing Desulfotomaculum
nigrificans. *Front. Microbiol.* 10, 1–13. doi:10.3389/fmicb.2019.01298.

Lorowitz, W. H., Nagle, D. P., and Tanner, R. S. (1992). Anaerobic oxidation of elemental metals
coupled to methanogenesis by Methanobacterium thermoautotrophicum. *Environ. Sci. Technol.*
26, 1606–1610. doi:10.1021/es00032a018.

Ma, L., Zhou, L., Ruan, M.-Y., Gu, J.-D., and Mu, B.-Z. (2019). Simultaneous methanogenesis and
acetogenesis from the greenhouse carbon dioxide by an enrichment culture supplemented with
zero-valent iron. *Renew. Energy* 132, 861–870.

Mand, J., Park, H. S., Jack, T. R., and Voordouw, G. (2014). The role of acetogens in microbially
influenced corrosion of steel. *Front. Microbiol.* 5, 1–14. doi:10.3389/fmicb.2014.00268.

Mand, J., Park, H. S., Okoro, C., Lomans, B. P., Smith, S., Chiejina, L., et al. (2016). Microbial
Methane Production Associated with Carbon Steel Corrosion in a Nigerian Oil Field. *Front.*
Microbiol. 6, 1–12. doi:10.3389/fmicb.2015.01538.

Mayhew, L. E., Lau, G. E., and Templeton, A. S. (2016). Distinct geochemistries of water-basalt-Fe0
reactions in the presence versus absence of CO2-driven microbial methanogenesis. *Chem. Geol.*
428, 92–105. doi:10.1016/j.chemgeo.2016.02.028.

Mechichi, T., Labat, M., Woo, T. H. S., Thomas, P., Garcia, J.-L., and Patel, B. K. C. (1998).
Eubacterium aggregansssp. nov., a New Homoacetogenic Bacterium from Olive Mill Wastewater
Treatment Digestor. *Anaerobe* 4, 283–291.

Mehanna, M., Basseguy, R., Delia, M. L., Girbal, L., Demuez, M., and Bergel, A. (2008). New
hypotheses for hydrogenase implication in the corrosion of mild steel. *Electrochim. Acta* 54,
140–147. doi:10.1016/j.electacta.2008.02.101.

Mehanna, M., Rouvre, I., Delia, M.-L., Feron, D., Bergel, A., and Basseguy, R. (2016). Discerning
different and opposite effects of hydrogenase on the corrosion of mild steel in the presence of
phosphate species. *Bioelectrochemistry* 111, 31–40. doi:10.1016/j.bioelechem.2016.04.005.

Meyer, F., Paarmann, D., D'Souza, M., Olson, R., Glass, E., Kubal, M., et al. (2008). The
metagenomics RAST server – a public resource for the automatic phylogenetic and functional
analysis of metagenomes. *BMC Bioinformatics* 9, 386. doi:10.1186/1471-2105-9-386.

Mishra, B. K., Chakraborty, S., Kumar, P., and Saraswat, C. (2020). "Urban Stormwater
Management: Practices and Governance BT - Sustainable Solutions for Urban Water Security :
Innovative Studies," in, eds. B. K. Mishra, S. Chakraborty, P. Kumar, and C. Saraswat (Cham:
Springer International Publishing), 115–146. doi:10.1007/978-3-030-53110-2_6.

Mohanakrishna, G., Seelam, J. S., Vanbroekhoven, K., and Pant, D. (2015). An enriched
electroactive homoacetogenic biocathode for the microbial electrosynthesis of acetate through
carbon dioxide reduction. *Faraday Discuss.* 183, 445–462. doi:10.1039/c5fd00041f.

Monroy, O. A. R., Gayosso, M. J. H., Ordaz, N. R., Olivares, G. Z., and Ramírez, C. J. (2011).
Corrosion of API XL 52 steel in presence of Clostridium celerecrescens. *Mater. Corros.* 62,
878–883. doi:10.1002/maco.200905582.

Mori, K., Tsurumaru, H., and Harayama, S. (2010). Iron corrosion activity of anaerobic hydrogen-
consuming microorganisms isolated from oil facilities. *J. Biosci. Bioeng.* 110, 426–430.

doi:10.1016/j.jbiosc.2010.04.012.

Neubeck, A., Sjöberg, S., Price, A., Callac, N., and Schnürer, A. (2016). Effect of nickel levels on
hydrogen partial pressure and methane production in methanogens. *PLoS One* 11, 1–19.
doi:10.1371/journal.pone.0168357.

Nevin, K. P., Hensley, S. A., Franks, A. E., Summers, Z. M., Ou, J., Woodard, T. L., et al. (2011).
Electrosynthesis of organic compounds from carbon dioxide is catalyzed by a diversity of
acetogenic microorganisms. *Appl. Environ. Microbiol.* 77, 2882–2886.
doi:10.1128/AEM.02642-10.

Okoro, C. C., Samuel, O., and Lin, J. (2017). Substrate Availability , pH , and Temperature Influence
Methanogenesis and Mild Steel Corrosion. *Geomicrobiol. J.* 0451.
doi:10.1080/01490451.2016.1257662.

Palacios, P. A., Snoeyenbos-West, O., Löscher, C. R., Thamdrup, B., and Rotaru, A.-E. (2019a).
Baltic Sea methanogens compete with acetogens for electrons from metallic iron. *ISME J.*
doi:10.1038/s41396-019-0490-0.

Palacios, P. A., Snoeyenbos-West, O., Löscher, C. R., Thamdrup, B., and Rotaru, A. E. (2019b).
Baltic Sea methanogens compete with acetogens for electrons from metallic iron. *ISME J.* 13,
3011–3023. doi:10.1038/s41396-019-0490-0.

Peters, J. W., Schut, G. J., Boyd, E. S., Mulder, D. W., Shepard, E. M., Broderick, J. B., et al. (2015).
[FeFe]- and [NiFe]-hydrogenase diversity, mechanism, and maturation. *Biochim. Biophys. Acta*
- Mol. Cell Res. 1853, 1350–1369. doi:10.1016/j.bbamcr.2014.11.021.

Phelps, T. J., and Zeikus, J. G. (1984). Influence of pH on Terminal Carbon Metabolism in Anoxic
Sediments from a Mildly Acidic Lake. *Appl. Environ. Microbiol.* 48, 1088–1095.
doi:10.1128/aem.48.6.1088-1095.1984.

Philips, J. (2020). Extracellular Electron Uptake by Acetogenic Bacteria: Does H2 Consumption
Favor the H2 Evolution Reaction on a Cathode or Metallic Iron? *Front. Microbiol.* 10, 1–13.
doi:10.3389/fmicb.2019.02997.

Philips, J., Monballyu, E., Georg, S., De Paepe, K., Prévoteau, A., Rabaey, K., et al. (2019). An
Acetobacterium strain isolated with metallic iron as electron donor enhances iron corrosion by a
similar mechanism as *Sporomusa sphaeroides*. *FEMS Microbiol. Ecol.* 95, 1–13.
doi:10.1093/femsec/fiy222.

Roh, Y., Chon, C. M., and Moon, J. W. (2007). Metal reduction and biomineralization by an
alkaliphilic metal-reducing bacterium, Alkaliphilus metalliredigens (QYMF). *Geosci. J.* 11,
415–423. doi:10.1007/BF02857056.

Rotaru, A.-E., Shrestha, P. M., Liu, F., Markovaite, B., Chen, S., Nevin, K. P., et al. (2014a). Direct
interspecies electron transfer between Geobacter metallireducens and Methanosarcina barkeri.
Appl. Environ. Microbiol. 80, 4599–4605. doi:10.1128/AEM.00895-14.

Rotaru, A.-E., Shrestha, P. M., Liu, F., Shrestha, M., Shrestha, D., Embree, M., et al. (2014b). A new
model for electron flow during anaerobic digestion: Direct interspecies electron transfer to

Methanosaeta for the reduction of carbon dioxide to methane. *Energy Environ. Sci.* 7.
doi:10.1039/c3ee42189a.

Rouvre, I., and Basseguy, R. (2016). Exacerbation of the mild steel corrosion process by direct
electron transfer between [Fe-Fe]-hydrogenase and material surface. *Corros. Sci.* 111, 199–211.
doi:10.1016/j.corsci.2016.05.005.

Sakamoto, M., and Benno, Y. (2006). Reclassification of Bacteroides distasonis, Bacteroides
goldsteinii and Bacteroides merdae as Parabacteroides distasonis gen. nov., comb. nov.,
Parabacteroides goldsteinii comb. nov. and Parabacteroides merdae comb. nov. *Int. J. Syst. Evol.*
Microbiol. 56, 1599–1605.

Schlegel, M. L., Necib, S., Daumas, S., Labat, M., Blanc, C., Foy, E., et al. (2018). Corrosion at the
carbon steel-clay borehole water interface under anoxic alkaline and fluctuating temperature
conditions. *Corros. Sci.* 136, 70–90.

Schwartz, E., and Friedrich, B. (2006). The H2-metabolizing prokaryotes. *The prokaryotes* 7, 496–
563.

Skovhus, L. T., Enning, D., and Lee, J. S. (2017). *Microbiologically Influenced Corrosion in the*
Upstream Oil and Gas Industry. Boca Raton, FL: CRC Press.

Struchtemeyer, C. G., Davis, J. P., and Elshahed, M. S. (2011). Influence of the drilling mud
formulation process on the bacterial communities in thermogenic natural gas wells of the
Barnett Shale. *Appl. Environ. Microbiol.* 77, 4744–4753. doi:10.1128/AEM.00233-11.

Suarez, E. M., Lepkova, K., Kinsella, B., and Machuca, L. L. (2019). Aggressive corrosion of steel
by a thermophilic microbial consortium in the presence and absence of sand. *Int. Biodeterior.*
Biodegrad. 137, 137–146. doi:10.1016/j.ibiod.2018.12.003.

Sund, C. J., McMasters, S., Crittenden, S. R., Harrell, L. E., and Sumner, J. J. (2007). Effect of
electron mediators on current generation and fermentation in a microbial fuel cell. *Appl.*
Microbiol. Biotechnol. 76, 561–568. doi:10.1007/s00253-007-1038-1.

Tang, H. Y., Holmes, D. E., Ueki, T., Palacios, P. A., and Lovley, D. R. (2019). Iron corrosion via
direct metal-microbe electron transfer. *MBio* 10, 1–10. doi:10.1128/mBio.00303-19.

Tatusova, T., Ciufo, S., Federhen, S., Fedorov, B., McVeigh, R., O'Neill, K., et al. (2015). Update on
RefSeq microbial genomes resources. *Nucleic Acids Res.* 43, D599–D605.
doi:10.1093/nar/gku1062.

Tsurumaru, H., Ito, N., Mori, K., Wakai, S., Uchiyama, T., Iino, T., et al. (2018). An extracellular
[NiFe] hydrogenase mediating iron corrosion is encoded in a genetically unstable genomic
island in *Methanococcus maripaludis*. *Sci. Rep.* 8, 15149. doi:10.1038/s41598-018-33541-5.

Uchiyama, T., Ito, K., Mori, K., Tsurumaru, H., and Harayama, S. (2010). Iron-corroding
methanogen isolated from a crude-oil storage tank. *Appl. Environ. Microbiol.* 76, 1783–8.
doi:10.1128/AEM.00668-09.

Usher, K. M., Kaksonen, A. H., Cole, I., and Marney, D. (2014a). Critical review: Microbially

influenced corrosion of buried carbon steel pipes. *Int. Biodeterior. Biodegrad.* 93, 84–106.
doi:10.1016/j.ibiod.2014.05.007.

Usher, K. M., Kaksonen, A. H., and MacLeod, I. D. (2014b). Marine rust tubercles harbour iron
corroding archaea and sulphate reducing bacteria. *Corros. Sci.* 83, 189–197.
doi:10.1016/j.corsci.2014.02.014.

Vigneron, A., Alsop, E. B., Chambers, B., Lomans, B. P., Head, I. M., and Tsesmetzis, N. (2016).
Complementary microorganisms in highly corrosive biofilms from an offshore oil production
facility. *Appl. Environ. Microbiol.* 82, AEM.03842-15. doi:10.1128/AEM.03842-15.Editor.

Wan, H., Song, D., Zhang, D., Du, C., Xu, D., Liu, Z., et al. (2018). Corrosion effect of Bacillus
cereus on X80 pipeline steel in a Beijing soil environment. *Bioelectrochemistry* 121, 18–26.

Wexler, H. M. (2007). Bacteroides: The good, the bad, and the nitty-gritty. *Clin. Microbiol. Rev.* 20,
593–621. doi:10.1128/CMR.00008-07.

Xu, D., Li, Y., Song, F., and Gu, T. (2013). Laboratory investigation of microbiologically influenced
corrosion of C1018 carbon steel by nitrate reducing bacterium Bacillus licheniformis. *Corros.*
Sci. 77, 385–390.

Xu, H., Wang, K., and Holmes, D. E. (2014). Bioelectrochemical removal of carbon dioxide (CO2):
an innovative method for biogas upgrading. *Bioresour. Technol.* 173, 392–8.
doi:10.1016/j.biortech.2014.09.127.

Yee, M. O., and Rotaru, A.-E. (2020). Extracellular electron uptake in Methanosarcinales is
independent of multiheme c-type cytochromes. *Sci. Rep.* 10, 372. doi:10.1038/s41598-019-
57206-z.

Yee, M. O., Snoeyenbos-West, O. L., Thamdrup, B., Ottosen, L. D. M., and Rotaru, A.-E. (2019).
Extracellular electron uptake by two *Methanosarcina* species. *Front. Energy Res.* 7, 458091.
doi:10.3389/fenrg.2019.00029.

Zhang, T., Fang, H. H. P., and Ko, B. C. B. (2003). Methanogen population in a marine biofilm
corrosive to mild steel. *Appl. Microbiol. Biotechnol.* 63, 101–106. doi:10.1007/s00253-003-
1396-2.

Zhou, Z., Meng, Q., and Yu, Z. (2011). Effects of methanogenic inhibitors on methane production
and abundances of methanogens and cellulolytic bacteria in in vitro ruminal cultures. *Appl.*
Environ. Microbiol. 77, 2634–2639. doi:10.1128/aem.02779-10.

Zhu, X. Y., Lubeck, J., and Ii, J. J. K. (2003). Characterization of Microbial Communities in Gas
Industry Pipelines. *Appl. Environ. Microbiol.* 69, 5354–5363. doi:10.1128/AEM.69.9.5354.

713   **Tables**

714   **Table 1.** Gene coverage of the Wood Ljungdahl pathway in a shotgun metagenome from a climate
715   lake. Here we only show genera of lithoautotrophic acetogens.

Genus	Gene coverage of the Wood Ljungdahl pathway*	Described lithoautotrophic acetogens of the genus
*Clostridium***	9 genes (*fhs, folD, metF, acsB, acsCD, cooS, pta, ack*)	12 species (*C. aceticum, C. autoethanogenum, C. carboxidivorans, C. coskatii, C. difficile, C. drakei, C. formicoaceticum, C. ljungdahlii, C. magnum, C. methoxybenzovorans, C. ragsdalei, C. scatologenes*)
*Eubacterium***	7 genes (*fhs, folD, acsB, acsD, cooS, pta, ack*)	2 species (*E. aggregans, E. limosum*)
Carboxydothermus	2 genes (*fhs, folD*)	3 species (*C. ferrireducens, C. hydrogenoformans, C. pertinax)*
Moorella	2 genes (*fhs, ack*)	4 species (*M. glycerini, M. mulderi, M. thermoacetica, M. thermoautotrophica*)
Treponema	2 genes (*fhs, ack*)	1 species (*T. primitia*)
*Desulfotomaculum***	2 genes (*metF, ack*)	1 species (*D. thermobenzoicum*)
Thermoanaerobacter	1 gene (*ack*)	1 species (*T. kivui*)

*The Wood Ljungdahl pathway includes enzymes encoded by 13 genes which catalyze 10 reactions (see Fig. 7c): *fdhAB* (formate dehydrogenase), *fhs* (formate—tetrahydrofolate ligase), *folD* (methenyltetrahydrofolate cyclohydrolase), *metF* (methylenetetrahydrofolate reductase), *acsE* (5-methyltetrahydrofolate:corrinoid/iron-sulfur protein Co-methyltransferase), *acsAB* (CO-methylating acetyl-CoA synthase), *acsCD* (5-methyltetrahydrosarcinapterin:corrinoid/iron-sulfur protein CO-methyltransferase), *acsA/cooS* (Ni CO dehydrogenase), pta (phosphate acetyltransferase), ack (acetate kinase).

** The 16S rRNA gene was detected in *Clostridium*, *Eubacterium* and *Desulfotomaculum*

718 **Table 2.** Gene hits of the CO_2-reductive methanogenesis and acetotrophic methanogenesis pathway
719 in a shotgun metagenome from a climate lake. Here we show genera that were relatively well
720 represented.

Genus	Gene hits of the CO_2 reductive methanogenesis pathway*	Gene hits of acetotrophic methanogenesis
Methanothermobacter	48 gene hits (*fwdABCDFE, ftr, mch, mtd, mer, mtrACDEFG, mcrAA$_2$BGCD, hdrA$_1$B$_1$C$_1$, mvhAGD, ehaCDFGHJNOPQ, ehbEFLKNOQ, frhABG*)	6 gene hits (*acs, cdhCED, cdhAB*)
Methanobrevibacter	25 genes (*fwdHF, ftr, mch, mer, mtrACDGC, mcrAA$_2$GC, hdrA1B1, mhvGD, ehaCFGOQ, ehbNQ, frhA*)	None
*Methanosaeta***	24 genes (*fwdFG, ftr, mch, mtd, mer, mtrABCDFGH, mcrAA$_2$BGCD, hdrA$_1$, hdrDE, ehbQ, frhB*)	5 gene hits (*cdhCED, cdhA, cooS, acs*)
Methanosarcina	19 genes (*fwdBCDFE, ftr, mtd, mtrAH, mcrAA$_2$BG, hdrA$_1$, hdrD, vhoG, frhDG, echA*)	7 gene hits (*cdhCED, cdhA, cooS, acs, ackA*)

*The CO_2-reductive methanogenesis pathway includes 7 C-transforming reactions catalyzed by enzymes /enzyme complexes encoded by ca. 58 genes, while the acetoclastic methanogenesis includes 3 or 4 C-transforming reactions catalyzed by enzymes encoded by 9 genes (see Fig. 7d).

Genes for CO_2-reductive methanogenesis: *fmd/fwdABCDHFEG* (formylmethanofuran dehydrogenase), *ftr* (formate—tetrahydrofolate ligase), *mch* (N^5,N^{10}-methenyltetrahydromethanopterin cyclohydrolase), *mtd* (F$_{420}$-dependent N^5, N^{10}-methylene-H4MPT dehydrogenase), *mer* (N^5,N^{10}-methylene-H$_4$MPT reductase), *mtrABCDEFGH* (coenzyme M methyltransferase), *mcrAA$_2$BGCD* (methyl:coenzyme M reductase), *hdrA$_1$B$_1$C$_1$* (ferredoxin:CoB—CoM heterosulfide reductase), *mvhAGD (-[NiFe]-hydrogenase*, *ehaBCDFGHJNOPQ* (energy-converting hydrogenase A), *ehbEFLKNOQ* (energy-converting hydrogenase B), *frhABG* (F$_{420}$-reducing hydrogenase).

Genes for acetotrophic methanogenesis: *cdhED* (acetyl-CoA decarbonylase), *cdhC* (CO-methylating acetyl-CoA synthase), *acs* (acetyl-CoA synthetase), *ackA* (acetate kinase), *pta* (phosphotransacetylase).

The 16S rRNA gene was detected only for *Methanosaeta*.

723 **Table 3.** Gene hits for H_2-evolving enzymes in a shotgun metagenome of a corrosive enrichment
724 from a climate lake.

[Enzyme class] gene cluster Type and characteristics	Incidence in acetogens* and methanogens* from our corrosive enrichment
[EC 1.12.7.2] *hydAB* gene cluster [FeFe] ferredoxin hydrogenase found in fermenters & syntrophs Does not occur in methanogens	*Clostridium* (*hydA*), *Eubacterium* (*hydA*), *Carboxydothermus* (*hydA*), and other bacteria (*hydAB*)
[EC 1.12.7.2] *echA-F* gene cluster Energy converting hydrogenase [FeFe] ferredoxin hydrogenase found in bacteria [NiFe] ferredoxin hydrogenase found in acetoclastic methanogens	*Clostridium* (*echABCDE*), *Methanosarcina* (*echAB*), other bacteria (*echABCEF*), and archaea (*echAB*)
[EC 1.12.7.2] *ehaA-R* gene cluster Energy converting hydrogenase [NiFe] ferredoxin hydrogenase found in strict hydrogenotrophic methanogens	*Methanothermobacter* (*ehaCDFGHJNOP*), *Methanobrevibacter* (*ehaCFGO*) and other archaea (*ehaBFGHJNO*)
[EC 1.12.7.2] *ehbA*-Q gene cluster Energy converting hydrogenase [NiFe] ferredoxin hydrogenase found in strict hydrogenotrophic methanogens	*Methanothermobacter* (*ehbEFIKNOQ*), *Methanobrevibacter* (*ehbNOQ*), *Methanosaeta* (*ehbQ*) and other archaea (*ehbFOQ*)
[EC 1.12.99.-] *mvh/vhu*-gene cluster [NiFe] hydrogenases MvhAGD forms a complex with HdrABC. Found in strict hydrogenotrophic methanogens.	*Methanothermobacter* (*mvhAGD/hdrABC*), *Methanobrevibacter* (mvhGD/hdrAB), other archaea (one/two rarely all)
[EC 1.18.6.1] *nifHDK* gene cluster [Mo] nitrogenase H_2-evolving	*Clostridium* (*nifHDK*), *Desulfotomaculum* (*nifHDK*), other bacteria (*nifHDK*, one/two rarely all) *Methanothermobacter* (*nifHD*), *Methanobrevibacter* (*nifH*), *Methanosarcina* (*nifHDK*), *Methanosaeta* (*nifH*), other archaea (one/two rarely all)

*Only the most relevant groups (see Table 1 and 2) are listed. All others are under other bacteria or archaea.

726 **Figures**

727 **Figure 1. Pitted corrosion by microorganisms**. Metallic iron sheets prior to exposure to cells (a),

728 prior to removal of the crust (b) and after crust removal. (d) A scanning electron micrograph showing

729 cells entrenched on the metal surface.

730
731

Figure 2. Gravimetric determination of Fe^0 corrosion in abiotic controls (gray), by a microbial

community from SDU sediments (black), by bacteria alone, after specific inhibition of the

methanogens with 2-bromoethanesulfonate (blue), and methanogens alone after inhibition of all

bacteria using a mix of antibiotics (red). n=3, p<0.05.

Figure 3. **Product formation** (methane – red; acetate – blue) by (a) abiotic controls (none), (b) a

mixed acetogenic-methanogenic community; (c) unaccompanied acetogens, obtained by the specific

inhibition of methanogens with 2-bromoethanesulfonate; (d) unaccompanied methanogens, obtained

by specific inhibition of all bacteria with an antibiotic mix of kanamycin and ampicillin. All

incubations were run in parallel and in triplicate (n=3).

Figure 4. Electron recovery. Changes in electron recovery rates over the course of three months (a)

and total electron recovery into products as mM electron equivalents (eeq) produced from Fe^0 under

four different conditions (abiotic, with the mixed community, with acetogens alone, with

methanogens alone). To calculate electron recoveries we consider: 2 mM electron equivalents / eeq

per mol H_2 (according to: $2e^- + 2H^+ \rightarrow H_2$) and 8 mM eeq for each mol of methane or acetate

(according to: $CO_2 + 8e^- + 8H^+ \rightarrow CH_4 + 2H_2O$; and $2CO_2 + 8e^- + 8H^+ \rightarrow C_2H_4O_2 + 2H_2O$). All

experiments are run in triplicates (n=3).

Figure 5. Hydrogen evolution in Fe⁰-media. Hydrogen production in abiotic controls (mineral

media controls) with Fe⁰, versus incubations of cells (community, acetogens and methanogens alone)

with Fe⁰. All experiments are run in triplicates (n=3) in parallel with experiments in Figure 3.

Figure 6. Proton activity (pH) changes during Fe0-incubations. pH changes in abiotic (white bars,

mineral media controls) and cells (black bars, mixed corrosive community) when exposed to Fe⁰ for

1 month.

Figure 7. Microbes and pathways involved in Fe^0 corrosion from a climate lake enrichment.

Relative abundance of Bacteria (a) and Archaea (b) genera in a shotgun metagenome (outer circles)

obtained from an SDU-pond community grown on Fe^0 for 4 successive transfers. Inner circles are the

relative distribution of genera according to genes of the Wood-Ljundgahl pathway for acetogenesis

(a-inner circle) and genes for the methanogenesis pathway (b-inner circle). **Genes encoding for**

enzymes involved in C-modification during (c) acetogenesis and (d) methanogenesis. The Wood

Ljungdahl pathway involves: *fdh*-operon (formate dehydrogenase), *fhs* (formate—tetrahydrofolate

ligase), *folD* (methenyltetrahydrofolate cyclohydrolase), *metF* (methylenetetrahydrofolate reductase),

acsE (5-methyltetrahydrofolate:corrinoid/iron-sulfur protein Co-methyltransferase), *acs* (CO-

methylating acetyl-CoA synthase), *acsCD* (5-methyltetrahydrosarcinapterin:corrinoid/iron-sulfur

protein CO-methyltransferase), *acsA/cooS* (Ni CO dehydrogenase), pta (phosphate acetyltransferase),

ack (acetate kinase). Methanogenesis involves: *fmd/fwd*-operon (formylmethanofuran

dehydrogenase), *ftr* (formate—tetrahydrofolate ligase), *mch* (N^5,N^{10}-

methenyltetrahydromethanopterin cyclohydrolase), *mtd* (F$_{420}$-dependent N^5, N^{10}-methylene-H4MPT

dehydrogenase), *mer* (N^5,N^{10}-methylene-H4MPT reductase), *mtr*-operon (coenzyme M

methyltransferase), *mcr*-operon (methyl:coenzyme M reductase), *hdrA$_1$B$_1$C$_1$* (ferredoxin:CoB—CoM

heterosulfide reductase), *mvhAGD (-[NiFe]-hydrogenase*, *eha*-operon (energy-converting

hydrogenase A), *ehb*-operon (energy-converting hydrogenase B), *frhABG* (F$_{420}$-reducing

hydrogenase) for CO$_2$-reductive methanogenesis. Plus, *cdhED* (acetyl-CoA decarbonylase), *cdhC*

(CO-methylating acetyl-CoA synthase), *acs* (acetyl-CoA synthetase), *ackA* (acetate kinase), *pta*

(phosphotransacetylase) for accetotrophic methanogenesis.