1 *In-vitro* and *in-vivo* **Characterization of a Multi-Stage Enzyme-Responsive**

2 **Nanoparticle-in-Microgel Pulmonary Drug Delivery System**

5 Joscelyn C. Mejías, Krishnendu Roy*, PhD.

7 The Wallace H. Coulter Department of Biomedical Engineering at Georgia Institute of Technology and

8 Emory University, Atlanta, GA, 30332

*Corresponding author

Krishnendu Roy, PhD

Director, Center for ImmunoEngineering

Director, NSF Engineering Research Center for Cell Manufacturing Technologies (CMaT)

Director, Marcus Center for Therapeutic Cell Characterization and Manufacturing

EBB 3018, 950 Atlantic Dr.

Atlanta, GA, 30332 USA.

krish.roy@gatech.edu

Graphical Abstract:

Abstract:

Although the lung is an obvious target for site-specific delivery of many therapeutics for respiratory airway diseases such as asthma, COPD, and cystic fibrosis, novel strategies are needed to avoid key physiologic barriers for efficient delivery and controlled release of therapeutics to the lungs. Specifically, deposition into the deep lung requires particles with a 1-5 μm aerodynamic diameter; however, particles with a geometric diameter less than 6 μm are rapidly cleared by alveolar macrophages. Additionally, epithelial, endothelial, and fibroblast cells prefer smaller (< 300 nm) nanoparticles for efficient endocytosis. Here we address these contradictory design requirements by using a nanoparticle-inside-microgel system (Nano-in-Microgel). Using an improved maleimide-thiol based Michael Addition during (water-in-oil) Emulsion (MADE) method, we fabricated both trypsin-responsive and neutrophil elastase-responsive polymeric Nano-in-Microgel to show the versatility of the system in easily exchanging enzyme-responsive crosslinkers for disease-specific proteases. By varying the initial macromer concentration, from 20-50 % w/v, the size distribution means ranged from 4-8 μm, enzymatic degradation of the microgels is within 30 minutes, and *in vitro* macrophage phagocytosis is lower for the higher % w/v. We further demonstrated that *in vivo* lung delivery of the multi-stage carriers through the pulmonary route yields particle retention up to several hours and followed by clearance within in naïve mice. Our results provide a further understanding of how enzymatically-degradable multi-stage polymeric carriers can be used for pulmonary drug delivery.

Keywords: Pulmonary delivery, nanoparticle, microparticle, phagocytosis, controlled release, multi-stage carriers, nano-in-microgel, microgel

Introduction:

Asthma, chronic obstructive pulmonary disorder (COPD), and cystic fibrosis (CF) are chronic inflammatory diseases characterized by an influx of innate immune cells to the lungs, including macrophages[1-3], neutrophils[4, 5], and eosinophils[2]. These cells impose a heavy enzymatic burden through proteases such as matrix metalloproteinases and elastases that promote significant tissue damage. Pulmonary delivery is a potentially non-invasive administration route for treating these chronic inflammatory disorders; however, the anatomy and physiology of the lung present significant design challenges for achieving efficient and effective drug delivery. Nanoparticles can inherently provide protection for encapsulated biologic therapeutics (proteins, RNAs) from high levels of exogenous proteases present in lung diseases, but they must be smaller than 300 nm to provide efficient cellular endocytosis[6-8] and transport across the mucosal barrier to target epithelial cells[9-12]. However, nanoparticles alone cannot efficiently aerosolize and deposit within the lung via inhalation; particles with aerodynamic diameters less than 1 µm are predominantly exhaled, while those between 1-5 µm are deposited more efficiently into the deep lung, and those greater than 5 µm are impacted in the mouth or throat[13]. At the same time, alveolar macrophages rapidly phagocytose particles with geometric diameters within the 1-5 µm range[14, 15], making efficient delivery difficult.

Current strategies for addressing this conflicting design issues include the use of porous polymers and swellable microparticles. By lowering the density of the microparticles, large porous particles provide an aerodynamic diameter between 1-5 µm and a geometric diameter greater than 6 µm[16-18] thus increasing residence time after deposition in the lungs. Swellable microparticles in their relaxed, dry state provide the correct aerodynamic size for lung delivery, and swell in the humid lung environments to a size capable of avoiding rapid macrophage clearance[19-22]. However, once these microscale carriers reach the deep lung, transport across mucosal surfaces and intracellular delivery to target cells, remain significant challenges.

The goal of this research was to synthesize and characterize a multi-stage, nano-in-microgel pulmonary

delivery system that addresses the complex design challenges for treating chronic inflammatory lung

diseases. Nano-in-Micro particles have been previously reported for intestinal[23, 24] and lung

delivery[19-22]. Our group have previously reported a proof-of-concept Nano-in-Microgel formulation

using a trypsin-responsive crosslinker with 60% w/v 4-arm-PEG acrylate[19]. Poly(ethylene glycol)

based hydrogels with protease responsive backbones have been used to respond and degrade to the

cellular microenvironment[25-27].

We hypothesize that including enzyme-responsive peptides relevant to chonic inflammatory

pulmonoray disorders in our Nano-in-Microgel system would allow them to degrade rapidly in diseased

airways of the lung with high enzymatic burden, and subsequently release encapsulated therapeutic

nanoparticles. In contrast, in airways with low enzymatic burden, the Nano-in-Microgels would not

degrade rapidly; instead clear through mucosal turover without releasing the nanoparticles – thus

lowering side effects. We studied the impact of reducing the starting polymer concentrations for the

Nano-in-Microgel formulation on avoiding rapid macrophage clearance using two different peptide

crosslinkers, trypsin-responsive CGRGGC, and neutrophil elastase-responsive CGAAPVRGGGGC

(adapted from [28]). The neutrophil elastase responsive peptide was chosen as this protease is well

known to be involved in various acute and chronic pulmonary inflammatory diseases[4, 29-31]. We

developed an improved Michael Addition During (water-in-oil) Emulsion (MADE) method which provides

faster reaction kinetics during fabrication while avoiding degradative conditions such as UV light, high

temperatures, and organic solvents that could denature biologic drugs or sensitive therapeutics. We

also report *in vivo* performance of these Nano-in-Microgels following pulmonary delivery in naïve mice,

including addressing their pulmonary biodistribution, cellular uptake, and clearance kinetics. Our results

show that multi-stage Nano-in-Microgels are a promising delivery system for efficient intracellular

delivery to the lung

Materials and Methods

Microparticle Formulation: Microgels were fabricated using Michael Addition During Water-in-Oil Emulsion (MADE). Briefly, equimolar amounts of a di-sulfhydryl peptide (CGRGGC, CGAAPVRGGGGC; CHI Scientific, Maynard, USA) and a 4-arm PEG Maleimide (Mal, 10kDa, Laysan Bio, Arab, USA) were dissolved separately in PBS to the desired combined concentration (e.g., 20 % w/v is 20 mg of molar ratio thiol:Mal in 100µL of PBS, Supplemental Table 1). To physically entrap the nanoparticles within the PEG network during crosslinking, the nanoparticles were resuspended in the PEG macromere solution. The PEG-nanoparticle-peptide mixture was added to 15 mL of mineral oil (Sigma Aldrich, St. Louis, USA) with 1% v/v surfactant (Span 80/Tween 80, HLB = 5, Sigma Aldrich) and homogenized on a PRO Scientific D Series homogenizer (Oxford, USA) for three minutes at 4000 rpm in a 35-40ºC water bath. The emulsion was then left rotating for a minimum of two hours at 37ºC. Microgels were removed from the surfactant and residual unreacted material by multiple centrifuge washes in water. To make non-enzyme responsive microgels, a 1 kDa HS-PEG-SH (Creative PEGWorks, Chapel Hill, USA) was used in place of the peptide, and the solution pH lowered to increase the crosslinking time. Microgels were filtered through a 40 µm cell filter before use to prevent clogging of the flow cytometers and the Penn-Century Inc. MicroSprayer (Wyndmoor, USA). Nanoparticles encapsulated include: 0.1 ± 0.012 µm Blue FluoSpheres (ThermoFisher Scientific, Waltham, USA) or 60 nm Carboxylated Dragon Green polystyrene beads (Bang's Laboratories, Fishers, USA). Microgels were labeled for microscopy or flow cytometry with 0.01 mg of DyLight 650-4xPEG-mal, DyLight 650-mal or DyLight 488-mal (ThermoFisher, dissolved at 10 mg/mL in DMSO). Encapsulation efficiency of Blue FluoSpheres was measured by fluorescence of nanoparticles against a standard curve with a BioTek (Winooski, USA) plate reader.

Microscopy and Analysis: Fluorescent images were collected either on a Zeiss (Oberkochen, Germany) 710 Laser Scanning Confocal Microscope with a 63X NA-1.4 oil Plan Apochromat objective or on a PerkinElmer (Waltham, USA) UltraVIEW VoX spinning disk confocal microscope with a Hamamatsu C9100-23b back-thinned EM-CCD and Nikon 100x NA-1.45 oil objective. Sizing of swollen

particles was performed with the Matlab function "imfindcircles". Other image processing, linear

contrasts, particle-size in oil, calculations, stitching, and three-dimensional reconstruction were

performed in Volocity (PerkinElmer).

Rheometry: Hydrogel storage and loss moduli were measured by dynamic oscillatory strain, and

frequency sweeps using an MCR 302 Rheometer (Anton Paar, Graz, Austria) with a 9 mm diameter 2°

cone and plate set at 25°C. Bulk hydrogels were made in 4.5 mm diameter silicone isolators,

crosslinked, then removed from the isolators and allowed to swell in PBS overnight. One gel per

formulation was used to determine the linear viscoelastic range of the hydrogel using a strain amplitude

sweep with an angular frequency of 10 rad/s; strain from the linear portion was then used for the

oscillatory frequency sweeps. Frequency sweeps were run with the constant strain from ω = 0.1-100

rad/s or until at least six points were linear.

In-vitro Degradation: Microgels were studied in both the absence and presence of enzyme using time-

lapse imaging of a loaded cell trap provided by the Lu lab [32]. The use of a cell trap allows for the

imaging of Nano-in-Microgel degradation over time with a high n (n > 100) per run. Once traps were

loaded DyLight 650 labeled microgels, enzyme solutions were flown into the trap, and the trap was

fluorescently imaged every minute for 30 minutes on a BioTek Lionheart using a 4x objective. Images

were stitched and analyzed in Gen 5.02 (BioTek). De-identified CF pooled patient sputum was collected

by the Emory Biospecimens Repository under protocols approved by the Institutional Review Boards at

Emory University and Georgia Institute of Technology.

Macrophage Uptake Study: RAW 264.7 Macrophage cells (ATCC, Manassas, USA) were cultured in

DMEM medium supplemented with 10% Fetal Bovine Serum (FBS) 100 U/mL/100 µg/mL Penicillin-

Streptomycin (HyClone, Logan, USA) in a 37°C incubator with 5% CO_2. RAW cells were detached by

scraping and stained with CellTrace Yellow (ThermoFisher) following manufacturer instructions, then

incubated with 20-50% w/v Nano-in-Microgel at a 1:1 ratio in a 96 well V-bottom plate. At 0.5, 1, 2, 6,

and 12 hours the plates were moved to 4°C, and the cells stained with Zombie Green (BioLegend, San

Diego, USA) and fixed with Cytofix (BD Biosciences, San Jose, USA). Fluorescence was evaluated

using a BD LSRFortessa with a high-throughput system.

Pulmonary Administration and whole organ imaging: All studies were performed according to

protocols approved by the IACUC at the Georgia Institute of Technology and all methods were

performed in accordance with the relevant guidelines and regulations. C57BL/6 and 8-12 weeks old

female Balb/c mice (Jackson Laboratories, Bar Harbor, USA) were maintained in pathogen-free

facilities, given sterile water, and food (low alfalfa if used for imaging) ad libitum. Using a 1A-1C

MicroSprayer Aerosolizer and FMJ-250 high pressure syringe assembly (Penn-Century, Inc) for

aerosolized delivery, mice were anesthetized with a Ketamine/Xylazine 80-100 mg/kg/ 10-20 mg/kg

cocktail, positioned on an intubation table, endotracheally intubated with a 1.22 mm ET Tube (Hallowell

EMC, Pittsfield, USA), and swollen Nano-in-Microgel formulations (1e6 microgels in 50 µL) were

injected. If there was injection failure, the mouse was marked for follow up and removed from data sets;

all samples removed are marked within the relevant supplemental figures. For oropharyngeal

aspirations, mice were anesthetized with isoflurane, placed on an intubation table, then the tongue was

pulled and held with atraumatic forceps as the formulation was administered into the mouth, and the

nose gently covered until the liquid was inhaled. Within experiments, the concentration of microgels

was equal between formulations. After sacrificing the mice with sodium pentobarbital, perfusing the

lungs with PBS through the right ventricle then excising the lungs, the fluorescence intensity of the

excised lungs was measured by imaging via IVIS Spectrum µCT (Perkin Elmer).

Flow Cytometry to study *in vivo* cellular targeting and clearance: Single cell suspensions were

prepared using a gentleMACS tissue dissociator (Miltenyi Biotec, Bergisch Gladbach, Germany) with 1

mg/mL of Collagenase D (Roche, Basel, Switzerland) and 0.1 mg/mL DNase I (Roche) in Opti-MEM

(ThermoFisher), then straining through a 40 µm cell strainer. Red blood cells (RBC) were lysed using

1x RBC Lysis Buffer (eBioscience, San Diego, USA). The single cell suspension was then washed and

stained with Zombie Aqua (BioLegend, San Diego, USA), incubated with Fc Block (BioLegend) then

with fluorochrome-conjugated antibodies (BioLegend unless noted; clone used), and fixed with Cytofix

(BD Bioscience). Antibodies used were: Ly-6G-BV711 (1A8), CD45-BV605 (30-F11), SiglecF-PE (BD

Bioscience; E50-2440), CD11c-APC/Fire750 (N418), F4/80-PE/Dazzle™ 594 (BM8), CD11b-PE/Cy7

(M1/70). Cells were collected on an untreated littermate to set the gates with noise below 1% by FMOs

(fluorescence minus one). The gating scheme is illustrated in Supplemental Figure 1. Data were

acquired on a BD LSRFortessa flow cytometer; compensation and data analyses were performed using

FlowJo (TreeStar, Ashland USA).

Statistical Analysis: Data was analyzed using GraphPad Prism (San Diego, CA) with a Shapiro-Wilk

test for normality (α=0.05). A one-way Anova (α=0.01) with post-hoc Tukey's test with an adjusted P

value for multiple comparisons, a two-way Anova (α = 0.01) with Sidak post hoc analysis was used with

data that passed Shapiro-Wilk. Where applicable, a Mann-Whitney (α = 0.01) or Kruskal-Wallis (α =

0.01) with Dunn's test was used for data that failed Shapiro-Wilk.

Results and Discussion

Design and Synthesis of Nano-in-Microgel Particles for aerodynamic and geometric size:

Microgel formulations were made at 20, 30, 40, 50% w/v starting polymer concentration to assess the

effect on microgel size, degradation, and macrophage phagocytosis. 4-arm PEG Maleimide was

crosslinked with a trypsin-responsive (CGRGGC) or neutrophil elastase-responsive

(CGAAPVRGGGGC) peptide backbone via crosslinking of the thiols on the cysteine residues. A

maleimide-thiol reaction was chosen for the Michael Addition During water-in-oil Emulsion because of

the faster kinetics relative to an acrylate-thiol[33]. By using both trypsin- and elastase-degradable

crosslinker, we show the versatility of the multi-stage system, whereby the crosslinker can be

exchanged for different disease-related protease responsive sequences. These peptides allow for the

controlled degradation of the microgels by proteases to release their nanoparticle cargo, schematic

representation in Figure 1A. To fluorescently label the microgel for imaging and flow cytometry, a

DyLight 650-4x-PEG-Maleimide was added to the 4x-PEG-Maleimide precursor solution.

Representative images of a DyLight-650 labeled microgel with 60 nm carboxylated polystyrene beads

can be seen in Figure 1B. Carboxylated beads (60 nm) can be seen in more than 89% of the microgels

by flow cytometry, Supplemental Figure 2. Encapsulation efficiency of the 100 nm Blue FluoSpheres for

each formulation was between 30-40% with total nanoparticles encapsulated (~1e11) in the microgels

within the same order of magnitude as theoretical maximum (3.6e11), Supplemental Table 2.

Figure 1: Synthesis of the Nanoparticle-in-Microgel (N-in-M) System. *(A) Schematic of the*

synthesis and degradation process for the Nano-in-Microgel formulation. To fabricate the Nano-in-

Microgels, a Michael Addition reaction During water-in-oil Emulsion (MADE) was used. 4-arm PEG

Maleimide and DyLight 650 4-arm PEG Mal is crosslinked by a protease-responsive di-thiol peptide in

emulsion. During microgel fabrication, nanoparticles are physically entrapped into the microgels.

Following delivery, protease dependent degradation at tissue or disease sites leads to nanoparticle

release (B) Representative image of a 20% trypsin-responsive DyLight 650 labeled microgel

encapsulating 60 nm Dragon Green polystyrene beads. Scale bars = 5 µm. Contrast linearly adjusted

for clarity.

The mean geometric diameter of the microgels for each starting polymer concentration were between

4.5-8.5 µm, Figure 2A. Mean size generally showed an increasing trend with the increase of starting

polymer concentrations; however, they were not statistically different. The lowest size is limited by the

imaging technique used for the measurement. 60% w/v microgels were not included in the studies as

their yield was low and the viscosity of the solution was difficult to transfer to the homogenizer

efficiently.

Aerodynamic diameter (D_a) is dependent on the geometric diameter (D_g), shape factor (1 for spheres)

and density of the particle through the following relationship: $D_a = D_g * \rho^{0.5}$ [14]. Using the density of PEG

as 1.13 g/mL, aerodynamic diameters of various microgel formulations were calculated and shown in

Table 1 (Figure 2B). Aerodynamic diameters of 0.5 to 5 µm are most suitable for deep lung deposition

[13, 14]; which corresponds to a theoretical geometric size range of 0.94 and 4.7 µm for PEG based

particles. This range is represented by dashed red lines on Figure 2B. The actual aerodynamic

diameter measured by a next generation impactor, after developing a dry powder formulation, would be

necessary to account for microgel aggregation, density, and shape factor in the future.

A

Relaxed (oil) | Swollen (water)

Trypsin-Responsive CGRGGC:
- Relaxed: 1.5 ± 1.0 μm, 2.0 ± 1.3 μm, 2.2 ± 1.7 μm, 2.4 ± 1.6 μm
- Swollen: 6.6 ± 2.6 μm, 5.9 ± 2.5 μm, 6.8 ± 2.9 μm, 8.5 ± 3.4 μm

Elastase-Responsive CGAAPVRGGGGC:
- Relaxed: 2.1 ± 1.4 μm, 1.7 ± 1.1 μm, 1.7 ± 1.1 μm, 2.0 ± 1.7 μm
- Swollen: 4.5 ± 1.8 μm, 4.7 ± 2.0 μm, 6.8 ± 2.8 μm, 6.0 ± 3.1 μm

B

Table 1: Aerodynamic Diameters			
Trypsin-Responsive			
% w/v	Mean (μm)	Std Dev.	75th Percentile
20	1.6	1.0	1.9
30	2.1	1.4	2.8
40	2.3	1.8	2.7
50	2.6	1.7	3.4
Elastase-Responsive			
20	2.3	1.5	3.2
30	1.8	1.1	2.4
40	1.8	1.1	2.2
50	2.1	1.8	2.8

Figure 2: Size distribution of the trypsin- and elastase-responsive Nano-in-Microgel

formulations in relaxed vs swollen states. *(A) Microgels fabricated with a trypsin responsive*

(CGRGGC) peptide sequence or a neutrophil-elastase responsive (CGAAPVRGGGGC) peptide with

varying starting polymer concentrations 20% (green), 30% (blue), 40% (cyan), 50% (purple) were sized

via microscopy in their relaxed polymer state (in oil) and swollen state (in water). The dashed red lines

on the relaxed state graphs represent the theoretical range of geometric diameters that correspond to

0.5-5 μm aerodynamic range, which is thought to be appropriate for deep lung delivery [13, 14]. These

were calculated by the relationship: $D_a = D_g * \rho^{0.5}$ for Da = 0.5 and 5. Each violin plot is from max to min

with median (black line) and quartiles labeled, n > 200 for each measurement. (B) The table shows the

mean, standard deviation (Std Dev.) and 75th percentile aerodynamic diameters for the trypsin- and

elastase-responsive microgels from 20-50% w/v starting polymer concentrations, calculated from the

geometric diameters using $D_a = D_g{*}\rho^{0.5}$.

More than 95% of Microgels degrade within 30 minutes in vitro: In order to confirm enzymatic

degradation of the microgels by the incorporated peptide backbone, Nano-in-Microgels were loaded

into microfluidic, PDMS single cell traps [32] then exposed to the relevant proteases and imaged over

time (Figure 3A). Trypsin-responsive microgels were exposed to 0.01 mg/mL of trypsin (≥ 90 u/mL).

For all formulations, 95% of the microgels degraded within 20 minutes. These studies were repeated

with the elastase-responsive microgels, which were exposed to pooled sputum from cystic fibrosis

patients (courtesy of the Emory Cystic Fibrosis Center, Atlanta, GA). For all elastase-responsive

microgel formulations, 95% of the microgels degraded within 25 minutes of exposure to the sputum. It

is possible that the protease-responsive crosslinkers in these microgels could non-specifically degraded

by other proteases present in the disease state; e.g., matriptase for the trypsin-responsive peptide or

cathepsin S for the elastase-responsive peptide (identified using PACMANs[34]), and this *in vivo*

degradation rate in disease states could be faster – an aspect we plan to evaluate in future studies.

Non-enzyme degradable 20% w/v microgels were fabricated by crosslinking with a dithiol PEG and

exposed to 0.01 mg/mL of trypsin (≥ 900 u/mL) as a control to show the peptide crosslinker is

necessary for enzyme-responsive degradation. The fluorescence change of the non-enzymatically

degradable PEG microgels followed similar trend as several sets of trypsin and elastase crosslinked

microgels that were imaged without exposure to the enzyme to confirm limited bleaching of the

microgels; the mean at 25 minutes is 91%, Figure 3B – indicating minimal background degradation.

Interestingly, we did not observe a difference in degradation when varying polymer concentrations. This

could be due to either the limits of the measurement method (1-minute intervals) or the polydispersity of

the microgels and overlap in size of the different groups. It is also possible that the enzyme

concentration is high and the kinetics of degradation is much faster than the increase in number of

additional crosslinks. It should be noted that the release of the 100 nm nanoparticles should follow the

degradation curve, since the theoretical pore size calculated[35] is smaller than the size of the

nanoparticles (10-20 nm) i.e., the nanoparticles can only be released as the microgels degrade,

Supplemental Table 3.

Figure 3: Degradation of trypsin- and elastase-responsive microgels by their respective

proteases *(A) Representative phase contrast, Cy5 overlaid images of cell traps at 0, 5, 10, 15, and 20*

minutes holding microgels crosslinked with PEG (non-protease responsive), trypsin-, or elastase-

responsive microgels. Whole cell traps were imaged before protease addition and once every minute

for 30 minutes after addition. PEG was imaged with and without exposure to 0.01 mg/mL of trypsin to

measure photobleaching and show the necessity of the protease-responsive peptide for the microgel

degradation. Trypsin-responsive microgels were exposed to 0.01 mg/mL trypsin and elastase-

responsive were exposed to pooled CF patient-derived airway supernatant; scale bar = 10 µm. (B)

Mean ± SEM plots of the percent of non-degraded microgels remaining in the trap over 30 minutes for

PEG microgels (N = 5), trypsin- (N = 5) and elastase- (N = 3) responsive microgels. Trypsin- and

elastase- responsive microgels were tested for each 20-50% w/v starting polymer concentration with

95% of trypsin-responsive microgels degrading in 20 minutes and 95% of elastase-responsive

degrading in 25 minutes.

Bulk hydrogels from 20-50% are relatively soft: Since macrophage phagocytosis has been shown to

be interdependent on size and mechanical properties of the particles [36, 37], we next measured

storage (G') and loss (G'') moduli of the bulk hydrogels (Figure 4). For the trypsin-responsive

crosslinker, the 20% w/v microgels had significantly lower loss modulus than the 40 and 50% w/v ones.

Furthermore, both the trypsin and elastase-responsive 20% w/v formulation had lower storage modulus

than the 40 and 50% w/v bulk gels. However, across all formulations, the hydrogels are relatively soft

(10kPa).

Figure 4: Storage (G') and loss (G'') moduli for trypsin- and elastase-responsive crosslinked

bulk hydrogels*. Trypsin- and elastase- responsive bulk hydrogels with varying starting polymer*

concentrations from 20-50% w/v (n = 8). Bars within formulation are group mean ± SD. Horizontal bars

represent statistical significance, Kruskal-Wallis with Dunn's multiple comparison test (α < 0.01)

Higher polymer concentration results in lower phagocytosis of microgels by macrophages in

vitro: To study macrophage phagocytosis *in vitro*, DyLight 650-4xPEG mal labeled Nano-in-Microgel

formulation (20-50% w/v) loaded with 100 nm Blue FluoSpheres were mixed and incubated with RAW

264.7 cells at a 1:1 cell:particle ratio. At 0.5, 1, 2, 6, and 12 hours of incubation, the cells were fixed and

analyzed using flow cytometry for Nano-in-Microgels positive macrophages (double positive DyLight

650 and Blue FluoSpheres) or nanoparticle only macrophages (Blue FluoSpheres), Supplemental

Figure 3A. After fixing, a small sample of cells from each treatment group was placed on a slide and

imaged on a spinning disc confocal. A representative image (Figure 5A) showed that macrophages

appear to phagocytose multiple particles. Over time, the percentage of macrophages that were positive

for the Nano-in-Microgels increased for all formulations; however, Nano-in-Microgels with a higher

polymer concentrations exhibited lower uptake by macrophages. This trend was observed for both the

trypsin- and elastase-responsive microgels, Figure 5B. The size and rheological properties of the

microgels may have a combined effect resulting in differential phagocytosis. The RAW 264.7

macrophages were not activated with any immune-stimulatory signals, nor were additional proteases

added into the media to degrade the microgels. Thus, nanoparticle release should primarily happen

inside the macrophages following microgel degradation by intracellular enzymes. Therefore, as

expected, macrophages positive for nanoparticles only (in flow cytometry plots), appear at later time

points, presumably after the macrophages have phagocytosed the Nano-in-Microgels and the DyLight

650 fluorescence has either degraded inside the cells or is not stable in the endosomal pH – thus

shifting the flow population to the Blue Fluosphere only (i.e. nanoparticle only) flow quadrant (see

Supplemental Figure 3).

Figure 5: *Trypsin- and elastase-responsive microgel-uptake by RAW 264.7 macrophages. Microgels were delivered at a 1:1 ratio to RAW 264.7 macrophages and run on flow cytometry to measure microgel positive macrophages at 30 minutes, 1, 2, 6, and 12 hours. (A) Representative images of a CellTrace Yellow labeled macrophage with 100 nm Blue FluoSpheres, and DyLight 650 labeled microgels; scale bar = 15 μm, images linearly contrasted for clarity. (B) Trypsin- and elastase-responsive microgel uptake over time measured by the percentage of DyLight 650 positive RAW 264.7 macrophages; trypsin- (n=6) and elastase- responsive (n=12), Kruskal-Wallis with Dunn's multiple comparison test, bars represent statistical significance, α < 0.01.*

Microgels are detectable up to 24h following intratracheal delivery: We used the trypsin-responsive 20% w/v formulation in vivo to evaluate the fastest clearance kinetics of microgels in naïve animals following pulmonary delivery. The choice of the 20% w/v microgel is based on our in vitro results which showed that these gels have the highest phagocytosis by macrophages. We chose to evaluate this in naïve animals to understand the baseline clearance rate in the absence of disease-specific proteases. Balb/c mice were treated with saline or 20% w/v trypsin-responsive DyLight 650-

mal Microgels by a Penn-Century MicroSprayer aerosolizer. Lungs were harvested within 30 minutes

after microgel instillation, and processed for crysectioning. Histologically, we observed that microgels

were present in all 5 lobes of the lungs. Few sections were also stained for Siglec F, an aleveloar

macrophage and eosinophil marker. Our results show that some microgels are associated with

SiglecF+ cells immediately after delivery (Supplemental Figure 4).

For longitudinal evaluation of microgel retention, Nano-in-Microgel formulations (100 nm Blue

FluoSpheres, DyLight 650-4xPEG mal microgels) were instilled naïve Balb/c lungs which were excised

at 0.5, 6, and 24 hours, and the radiant efficiency of the whole lung was measured using IVIS.

Fluorescence intensity decreased with time but was still visible at 6 and 24 hours after injection (Figure

6 and Supplemental Figure 5A). We expect that the levels of proteases present in these naïve lungs

were relatively low, and thus the measured decrease in fluorescence should not be due to enzymatic

degradation of the peptide backbone on the microgels, which was confirmed by the similar rates of

clearance for both the protease- and non-protease degradable Nano-in-Microgel formulations.

Furthermore, in the absence of significant proteolytic degradation (in naïve animals we do not expect

disease-related proteolytic enzymes to be present in the lung), few nanoparticles should be released

from the microgels. This was confirmed by flow cytometry showing that alveolar macrophages,

neutrophils, and epithelial cells (Supplemental Figure 5B) were not positive for free nanoparticles (i.e.

nanoparticles released out of microgels, Supplemental Figure 5C). Nano-in-Microgel uptake in alveolar

macrophages (Supplemental Figure 5D) were minimal suggesting avoidance of rapid macrophage

phagocytosis within the early timepoints – which is a primary design critera for pulmonary delivery.   .

Without degradation the entrapped nanoparticles or partially degraded microgels are not expected to be

found in other organs, except potentially in lung draining lymph nodes (carried by lung phagocytic

cells). However, IVIS images showed no detectable radiant efficiency in the lymph nodes

(Supplemental Figure 5B), indicating minimal or no transport of the microgels outside of the lung. This

suggests that without relevant proteases to degrade the microgels, and with minimal macrophage-

phagocytosis as discussed above, they are most likely cleared by normal mucociliary clearance of the

lung.

Figure 6: Trypsin- and non-protease(PEG)-degradable microgel residence time in naïve mice.

Saline, DyLight 650 trypsin-responsive microgels, or DyLight 650 PEG (non-protease responsive)

microgels were instilled in naïve mice airways using a MicroSprayer then lungs were excised and

radiant efficiency measured by IVIS at 0.5, 6, and 24 hours post delivery. (A) Representative IVIS

images for lung background control (saline), and DyLight 650 emission from trypsin-responsive and

PEG-crosslinked microgels at 0.5, 6, and 24 hours after instillation. (B) IVIS measured radiant efficiency

decreased for both formulations over time with similar rates (n = 3 - 4). Kruskal-Wallis with Dunn's

multiple comparison test within each time point is not statistically significant, α < 0.01.

The radiant efficiency observed in 20 and 30% w/v formulations were similar (Supplemental Figure 6A-

B), clearance also remained similar between the formulations, and additional flow cytometry showed no

alveolar macrophages or neutrophils positive for either the Nano-in-Microgel formulations or the

nanoparticles alone (Supplemental Figure 6C). Fluorescence of the Nano-in-Microgel formulation was

maintained at 6 hours, showing that microgels avoid rapid clearance by phagocytosis and when

designed to be used in diseased states should degrade within this time frame (< 6 h) leading to

effective release of the nanoparticles.

Limited phagocytosis *in vivo* within the first hour of administration: To determine whether the

microgels with different peptide crosslinkers are phagocytosed differently, a 1:1 ratio of trypsin-

responsive microgels and elastase-responsive microgels (labeled with DyLight 650-4xPEG mal and

DyLight 488-mal, respectively) were loaded with Blue FluoSpheres were delivered to the airways of

naïve mice. Microgels were administered with the aerosolizer (PC) or by oropharyngeal aspiration

between Balb/c littermates. Additionally, microgels were delivered by oropharyngeal aspiration to

C57BL/6 mice from two age group (5-6 and 16-17 week old) since this strain is often used in LPS

models of neutrophilic infiltration. One hour after delivery (Figure 7) the mice were sacrificed, the lungs

collected, and digested into single cell suspensions. Stained samples were then run to determine the

phagocytic cells positive for the different microgel formulations. Cell populations were defined as

follows: 1) polymorphonuclear neutrophils (PMN): CD45+Ly6G+, 2) alveolar macrophages (AM):

CD45+Ly6G-SiglecF+CD11c+CD11b-, 3) eosinophils (Eo): CD45+Ly6G-SiglecF+CD11c-CD11b+, and

4) non-alveolar F4/80+ macrophages (Mφ): CD45+Ly6G-SiglecF-F4/80+. The MicroSprayer appears to

deliver microgels in the vicinity of eosinophils and alveolar macrophages, Supplemental Figure 4;

however, the extent and dose with which these particles reach the lower airways could be low, and with

oropharyngeal aspirations may be even lower since the velocity added by the MicroSprayer is absent.

Additionally, the F4/80+ macrophage populations can include both non-alveolar macrophages as well

as interstitial macrophages [38] that may or may not come in contact with the microgel formulations,

skewing the percentages of populations positive for microgels low. Statistical analysis comparisons

were kept within species for each cell type.

The neutrophil populations for the two Balb/c delivery methods were significantly different and the

alveolar macrophage population between the two C57BL/6 Groups were significantly different using a

two-way Anova (α = 0.01) with Sidak post hoc test, Figure 7A. While the microgel+ populations within

each of the cell populations have median values below 5% for each type, (Figure 7B-C), the elastase-

responsive group has a few between 5-10%; the grey dashed line marks the 1% threshold used to set

the gates on FMOs. Due to the low number of cells within each of the sub-populations the nanoparticles

(Figure 7D) were gated directly off their parent cell population rather than from the microgel positive

populations with only the Balb/c F4/80+ macrophage populations showing cells positive for

nanoparticles.

Figure 7: 20% w/v trypsin- and elastase- responsive microgel uptake in naïve Balb/c or C57BL6

phagocytic populations one hour post-delivery. *20% w/v DyLight 650 trypsin-responsive microgels*

encapsulating 100 nm Blue FluoSpheres and 20% w/v DyLight 488 elastase-responsive microgels

encapsulating 100 nm Blue FluoSpheres were instilled at a 1:1 ratio in mice airways by either Penn-

Century MicroSprayer (PC) or oropharyngeal aspirations in naïve Balb/c littermates (PC-green, purple)

or by oropharyngeal aspirations to 5-6 week-old (light blue) or 16-17 week-old (dark blue) C57BL/6

naïve mice. Single cell suspensions were stained and run on flow cytometry (A) Percentage of

neutrophils (PMN; CD45+Ly6G+), eosinophils (EO; CD45+Ly6G-SiglecF+CD11c-CD11b+), alveolar

macrophage (AM; CD45+Ly6G-SiglecF+CD11c+CD11b-), and F4/80+ macrophage (Mφ; CD45+Ly6G-

SiglecF-F4/80+) of the CD45 populations; two-way Anova (α = 0.01) with Sidak post hoc. Percentage of

neutrophils, eosinophils, alveolar macrophages, and F4/80 macrophages positive for (B) trypsin-

responsive microgels and (C) elastase-responsive microgels or (D) Blue FluoSpheres; Mann-Whitney

(α = 0.01). Grey dashed line marks the 1% threshold used to set the gates on FMOs.

While particle size is an important factor for phagocytosis and endocytosis, recent work looking at the

relationship between particle elasticity and cellular uptake has shown that softer particles are often

more difficult for cells to consume. This is because particle deformation leads to a greater extent of

spreading between the elastic particle and the cell; specifically, phagocytosis by immune cells for

particles in the softer (kPa) range having slower uptake than stiffer (MPa) particles[37, 39]. We

observed that with the 20% w/v trypsin- and elastase-responsive microgels, there was minimal rapid

clearance by phagocytosis in the first hour by neutrophils, eosinophils, alveolar macrophages, and

F4/80+ macrophages for both Balb/c and C57BL/6 mice regardless of delivery method (aerosolizer vs.

oropharyngeal aspiration); we believe the larger size of the microgels in the swelled state and their low

mechanical stiffness leads to lower phagocytic clearance.

Furthermore, that *in vitro* elastase-responsive microgels degraded in CF patient sputum within 30

minutes, which suggested that the elastase-responsive microgels should degrade and release

nanoparticles before most of the microgels are cleared from diseased lungs. This microgel

phagocytosis and clearance from Figures 6-7 was observed in naïve animals, however, under severe

disease burdens (such as asthma, COPD, and CF) there is reduced phagocytic ability of these innate

cells [40-43] which may create a longer window for the microgels to degrade—releasing their cargo.

Conclusions

The Nano-in-Microgel system was designed for (a) needed aerodynamic properties (b) avoiding rapid

clearance by alveolar macrophages, and (c) protease-triggered rapid degradation in diseased

microenvironments for the release of nanoparticles. The purpose of these studies was to understand

two issues: 1) how the starting polymer concentration of our Nano-in-Microgel multistage particles

influenced the size and degradation *in vitro* and 2) the cellular-biodistribution, phagocytosis, and

clearance of the Nano-in-Microgel system in naïve *in vivo* settings following pulmonary delivery. The

trypsin peptide crosslinker was used to understand how the Nano-in-Microgel system without specific

enzymatic degradation cleared *in vivo*, while the neutrophil-elastase responsive microgels

demonstrated that we could incorporate a pulmonary disease-relevant crosslinker into the system and

study nanoparticle release. We have further improved the MADE method by changing the chemistry

from an acrylate-thiol to maleimide-thiol for faster reaction kinetics and lowering the necessary % w/v

for the microgel formulations while maintaining the size ranges needed for deposition and avoiding

rapid clearance by phagocytosis within the first 24 hours. While the work used representative

fluorescent nanoparticles, these nanoparticles can be easily exchanged for target-specific nanoparticles

as they are physically entrapped in the microgel network during fabrication.

Future studies with the elastase-responsive peptide in disease models with therapeutic nanoparticles

should be completed to determine this optimal clearance vs. degradation kinetics and to understand the

efficacy of the Nano-in-Microgel system for drug delivery under various disease conditions.

The results of these studies show that the MADE method for fabricating multi-stage particles produces

enzyme-responsive microgels without exposure to degradative conditions for biologics that allow for

quick release of nanoparticles for targeting pulmonary disease. Future work in optimizing a dry powder

formulation for existing pulmonary delivery devices (e.g., DPIs, nebulizers) is needed to translate the

system into clinical usage.

Acknowledgements: This work was supported by funding from the Marcus Center for Therapeutic Cell

Characterization and Manufacturing (MC3M) at Georgia Tech, Georgia Tech Foundation (KR), Georgia

Tech Research Alliance (KR), Center for Cystic Fibrosis Airways Disease Research and Children's

Healthcare of Atlanta, NIH/NIGMS-sponsored Cell and Tissue Engineering (CTEng) Biotechnology

Training Program T32GM008433 (JCM) and NSF Graduate Research Fellowship DGE-1148903

(JCM). The authors would like to thank the Prof. Hang Lu and her lab for the use of their cell traps,

Prof. Andrés García's lab for the use of their Rheometer, Dr. Randall Toy for help during animal

experiments, and Prof. Rabin Tirouvanziam for help with Emory's Cystic Fibrosis Biospecimen Registry.

We also thank the Parker H. Petit Institute for Bioengineering and Bioscience at the Georgia Institute of

Technology for the use of their core facilities.

Conflict of interest: The authors declare that no conflict of interest exists.

Supplemental Data: Supplementary data related to this article can be found online

References:

[1] J. Balhara, A.S. Gounni, The alveolar macrophages in asthma: a double-edged sword, Mucosal Immunol, 5 (2012) 605-609.

[2] B.N. Lambrecht, H. Hammad, The immunology of asthma, Nature Immunology, 16 (2015) 45-56.

[3] P.J. Barnes, Inflammatory mechanisms in patients with chronic obstructive pulmonary disease, Journal of Allergy and Clinical Immunology, 138 (2016) 16-27.

[4] C. Castellani, B.M. Assael, Cystic fibrosis: a clinical view, Cellular and Molecular Life Sciences, 74 (2016) 1-12.

[5] F. Ratjen, S.C. Bell, S.M. Rowe, C.H. Goss, A.L. Quittner, A. Bush, Cystic fibrosis, Nature Reviews Disease Primers, 1 (2015) 15010-15010.

[6] T.W. Shen, C.A. Fromen, M.P. Kai, J.C. Luft, T.B. Rahhal, G.R. Robbins, J.M. DeSimone, Distribution and Cellular Uptake of PEGylated Polymeric Particles in the Lung Towards Cell-Specific Targeted Delivery, Pharmaceutical Research, 32 (2015) 3248-3260.

[7] A. Popov, L. Schopf, J. Bourassa, H. Chen, Enhanced pulmonary delivery of fluticasone propionate in rodents by mucus-penetrating nanoparticles, International Journal of Pharmaceutics, 502 (2016) 188-197.

[8] N. Nafee, A. Husari, C.K. Maurer, C. Lu, C. De Rossi, A. Steinbach, R.W. Hartmann, C.M. Lehr, M. Schneider, Antibiotic-free nanotherapeutics: Ultra-small, mucus-penetrating solid lipid nanoparticles enhance the pulmonary delivery and anti-virulence efficacy of novel quorum sensing inhibitors, Journal of Controlled Release, 192 (2014) 131-140.

[9] C.S. Schneider, Q. Xu, N.J. Boylan, J. Chisholm, B.C. Tang, B.S. Schuster, A. Henning, L.M. Ensign, E. Lee, P. Adstamongkonkul, B.W. Simons, S.-Y.S. Wang, X. Gong, T. Yu, M.P. Boyle, J.S. Suk, J. Hanes, Nanoparticles that do not adhere to mucus provide uniform and long-lasting drug delivery to airways following inhalation, Science Advances, 3 (2017).

[10] X. Murgia, P. Pawelzyk, U.F. Schaefer, C. Wagner, N. Willenbacher, C.-M. Lehr, Size-Limited Penetration of Nanoparticles into Porcine Respiratory Mucus after Aerosol Deposition, Biomacromolecules, 17 (2016) 1536-1542.

[11] A. Kolte, S. Patil, P. Lesimple, J.W. Hanrahan, A. Misra, PEGylated composite nanoparticles of PLGA and polyethylenimine for safe and efficient delivery of pDNA to lungs, International Journal of Pharmaceutics, 524 (2017) 382-396.

[12] O. Gartziandia, S.P. Egusquiaguirre, J. Bianco, J.L. Pedraz, M. Igartua, R.M. Hernandez, V. Préat, A. Beloqui, Nanoparticle transport across in vitro olfactory cell monolayers, International Journal of Pharmaceutics, 499 (2016) 81-89.

[13] J. Heyder, J. Gebhart, G. Rudolf, C.F. Schiller, W. Stahlhofen, Deposition of particles in the human respiratory tract in the size range 0.005-15 μm, Journal of Aerosol Science, 17 (1986) 811-825.

[14] D.A. Edwards, C. Dunbar, Bioengineering of Therapeutic Aerosols, Annual Review of Biomedical Engineering, 4 (2002) 93-107.

[15] B. Patel, N. Gupta, F. Ahsan, Particle engineering to enhance or lessen particle uptake by alveolar macrophages and to influence the therapeutic outcome, European Journal of Pharmaceutics and Biopharmaceutics, 89 (2015) 163-174.

[16] D.A. Edwards, J. Hanes, G. Caponetti, J. Hrkach, A. BenJebria, M.L. Eskew, J. Mintzes, D. Deaver, N. Lotan, R. Langer, A. Ben-jebria, M.L. Eskew, J. Mintzes, D. Deaver, N. Lotan, R. Langer, Large Porous Particles for Pulmonary Drug Delivery, Science, 276 (1997) 1868-1871.

[17] I. D'Angelo, B. Perfetto, G. Costabile, V. Ambrosini, P. Caputo, A. Miro, R. D'Emmanuele Di Villa Bianca, R. Sorrentino, G. Donnarumma, F. Quaglia, F. Ungaro, Large Porous Particles for Sustained Release of a Decoy Oligonucleotide and Poly(ethylenimine): Potential for Combined Therapy of Chronic Pseudomonas aeruginosa Lung Infections, Biomacromolecules, 17 (2016) 1561-1571.

[18] S. Nishimura, T. Takami, Y. Murakami, Porous PLGA microparticles formed by "one-step" emulsification for pulmonary drug delivery: The surface morphology and the aerodynamic properties, Colloids and Surfaces B: Biointerfaces, 159 (2017) 318-326.

[19] P. Wanakule, G.W. Liu, A.T. Fleury, K. Roy, Nano-inside-micro: Disease-responsive microgels with encapsulated nanoparticles for intracellular drug delivery to the deep lung, Journal of Controlled Release, 162 (2012) 429-437.

[20] R. Ni, J. Zhao, Q. Liu, Z. Liang, U. Muenster, S. Mao, Nanocrystals embedded in chitosan-based
respirable swellable microparticles as dry powder for sustained pulmonary drug delivery, European
Journal of Pharmaceutical Sciences, 99 (2017) 137-146.
[21] I.M. El-Sherbiny, H.D.C. Smyth, Biodegradable nano-micro carrier systems for sustained
pulmonary drug delivery: (I) Self-assembled nanoparticles encapsulated in respirable/swellable semi-
IPN microspheres, International Journal of Pharmaceutics, 395 (2010) 132-141.
[22] E. Secret, S.J. Kelly, K.E. Crannell, J.S. Andrew, Enzyme-Responsive Hydrogel Microparticles for
Pulmonary Drug Delivery, ACS Applied Materials & Interfaces, 6 (2014) 10313-10321.
[23] M.D. Bhavsar, M.M. Amiji, Gastrointestinal distribution and in vivo gene transfection studies with
nanoparticles-in-microsphere oral system (NiMOS), 119 (2007) 339-348.
[24] J.C. Imperiale, P. Nejamkin, J. Maria, C.E. Lanusse, A. Sosnik, Biomaterials Novel protease
inhibitor-loaded Nanoparticle-in-Microparticle Delivery System leads to a dramatic improvement of the
oral pharmacokinetics in dogs, 37 (2015) 383-394.
[25] M.P. Lutolf, J.L. Lauer-Fields, H.G. Schmoekel, A.T. Metters, F.E. Weber, G.B. Fields, J.A.
Hubbell, Synthetic matrix metalloproteinase-sensitive hydrogels for the conduction of tissue
regeneration: Engineering cell-invasion characteristics, Proceedings of the National Academy of
Sciences, 100 (2003) 5413.
[26] J. Patterson, J.A. Hubbell, Enhanced proteolytic degradation of molecularly engineered PEG
hydrogels in response to MMP-1 and MMP-2, Biomaterials, 31 (2010) 7836-7845.
[27] G.A. Foster, D.M. Headen, C. González-García, M. Salmerón-Sánchez, H. Shirwan, A.J. García,
Protease-degradable microgels for protein delivery for vascularization, Biomaterials, 113 (2017) 170-
175.
[28] A.A. Aimetti, M.W. Tibbitt, K.S. Anseth, A.A. Aimetti, M.W. Tibbitt, K.S. Anseth, Human Neutrophil
Elastase Responsive Delivery from Poly (ethylene glycol) Hydrogels, Biomacromolecules, 10 (2009)
1484-1489.
[29] S. Kolahian, I.E. Fernandez, O. Eickelberg, D. Hartl, Immune mechanisms in pulmonary fibrosis,
American Journal of Respiratory Cell and Molecular Biology, 55 (2016) 309-322.
[30] K. Hoenderdos, A. Condliffe, The neutrophil in chronic obstructive pulmonary disease, Am J Respir
Cell Mol Biol, 48 (2013) 531-539.
[31] C.J. Wagner, C. Schultz, M.A. Mall, Neutrophil elastase and matrix metalloproteinase 12 in cystic
fibrosis lung disease, Molecular and cellular pediatrics, 3 (2016) 25-25.
[32] K. Chung, C.A. Rivet, M.L. Kemp, H. Lu, Imaging Single-Cell Signaling Dynamics with a
Deterministic High-Density Single-Cell Trap Array, Analytical Chemistry, 83 (2011) 7044-7052.
[33] E.A. Phelps, N.O. Enemchukwu, V.F. Fiore, J.C. Sy, N. Murthy, T.A. Sulchek, T.H. Barker, A.J.
García, Maleimide cross-linked bioactive PEG hydrogel exhibits improved reaction kinetics and cross-
linking for cell encapsulation and in situ delivery, Advanced Materials, 24 (2012) 64-70.
[34] M.C. Ferrall-Fairbanks, Z.T. Barry, M. Affer, M.A. Shuler, E.W. Moomaw, M.O. Platt, PACMANS: A
bioinformatically informed algorithm to predict, design, and disrupt protease-on-protease hydrolysis,
Protein Science, 26 (2017) 880-890.
[35] T. Canal, N.A. Peppas, Correlation between mesh size and equilibrium degree of swelling of
polymeric networks, Journal of Biomedical Materials Research, 23 1183-1193.
[36] J.A. Champion, A. Walker, S. Mitragotri, Role of Particle Size in Phagocytosis of Polymeric
Microspheres, Pharmaceutical Research, 25 (2008) 1815-1821.
[37] A.C. Anselmo, S. Mitragotri, Impact of particle elasticity on particle-based drug delivery systems,
Adv Drug Deliv Rev, 108 (2017) 51-67.
[38] A.V. Misharin, L. Morales-Nebreda, G.M. Mutlu, G.R.S. Budinger, H. Perlman, Flow cytometric
analysis of macrophages and dendritic cell subsets in the mouse lung, American Journal of Respiratory
Cell and Molecular Biology, 49 (2013) 503-510.
[39] N. Doshi, A.S. Zahr, S. Bhaskar, J. Lahann, S. Mitragotri, Red blood cell-mimicking synthetic
biomaterial particles, Proceedings of the National Academy of Sciences, 106 (2009) 21495-21499.
[40] A.M. Fitzpatrick, F. Holguin, W.G. Teague, L.A. Brown, Alveolar macrophage phagocytosis is
impaired in children with poorly controlled asthma, J Allergy Clin Immunol, 121 (2008) 1372-1378, 1378
e1371-1373.

[41] N.E. Alexis, M.S. Muhlebach, D.B. Peden, T.L. Noah, Attenuation of host defense function of lung
phagocytes in young cystic fibrosis patients, Journal of Cystic Fibrosis, 5 (2006) 17-25.
[42] M. Leveque, S. Le Trionnaire, P. Del Porto, C. Martin-Chouly, The impact of impaired macrophage
functions in cystic fibrosis disease progression, J Cyst Fibros, 16 (2017) 443-453.
[43] Z. Liang, Q. Zhang, C.M. Thomas, K.K. Chana, D. Gibeon, P.J. Barnes, K.F. Chung, P.K. Bhavsar,
L.E. Donnelly, Impaired macrophage phagocytosis of bacteria in severe asthma, Respiratory Research,
15 (2014) 72.
624