1

Degradation of recalcitrant polyurethane and xenobiotic additives by a selected landfill microbial community and its biodegradative potential revealed by proximity ligation-based metagenomic analysis

Itzel Gaytán[1†], Ayixon Sánchez-Reyes[1†], Manuel Burelo[2], Martín Vargas-Suárez[1], Ivan Liachko[3], Maximilian Press[3], Shawn Sullivan[3], M. Javier Cruz-Gómez[4] and Herminia Loza-Tavera[1]*

[1]Departamento de Bioquímica, [2]Departamento de Química Analítica, [4]Departamento de Ingeniería Química, Facultad de Química, Universidad Nacional Autónoma de México, Ave. Universidad 3000, Col. UNAM, Ciudad de México, 04510, MÉXICO. [3]Phase Genomics Inc, 1617 8[th] Ave N, Seattle, WA 98109, USA.

†These authors contributed equally: Itzel Gaytán, Ayixon Sánchez-Reyes

*To whom correspondence should be addressed

Tel. +52 (55) 5622-5280

e-mail: hlozat@unam.mx

ABSTRACT

Polyurethanes (PU) are the sixth more produced plastics with around 19-million tons/year, but since they are not recyclable they are burned or landfilled, generating ecological damage. To elucidate the mechanisms that landfill microbial communities perform to attack recalcitrant PU plastic, we studied the BP8 community selected by its capability to grow in a water PU dispersion (WPUD) that contains a polyether-polyurethane-acrylate (PE-PU-A) copolymer and xenobiotic additives (N-methyl 2-pyrrolidone, isopropanol and glycol ethers), and performed a proximity ligation-based metagenomic analysis for revealing the community structure and potential biodegradative capacity. Additives were consumed early whereas the copolymer was cleaved throughout the 25-days incubation. BP8 metagenomic deconvolution reconstructed five genomes, three of them from novel species. Genes encoding enzymes for additives biodegradation were predicted. The chemical and physical analysis of the biodegradation process, and the identified biodegradation products show that BP8 cleaves esters, aromatic urethanes, C-C and ether groups by hydrolytic and oxidative mechanisms. The metagenomic analysis allowed to predicting comprehensive metabolic pathways and enzymes that explain the observed PU biodegradation. This is the first study revealing the metabolic potential of a landfill microbial community that thrives within a WPUD system and shows potential for bioremediation of polyurethane- and xenobiotic additives-contaminated sites.

INTRODUCTION

Plastic pollution represents a pervasive anthropogenic threat for the survival of natural ecosystems. Worldwide, plastics have become so abundant that they have been proposed as geological markers for the Anthropocene era [1]. In 2017, 348 million tons of plastics were manufactured [2] and their production keeps increasing. Polyurethanes (PU) are versatile plastics produced as thermoplastics, thermosets, coatings, adhesives, sealants and elastomers that are incorporated into our daily life in building insulation, refrigerators and freezers, furniture and bedding, footwear, automotive, coatings, adhesives, and others. PU has been ranked as the sixth most used polymer worldwide with a production of 18 million tons in 2016 [3,4]. The extensive utilization of PU generates wastes that are mainly disposed in municipal landfills where, because of its structural complexity will remain as polymeric structures for decades, or are burned generating toxic substances that negatively impact human health and ecosystems [3]. Furthermore, some PU such as polyether (PE)-PU are more recalcitrant than others, and additionally, some polyurethane-based liquid formulations contain additives that include secondary alcohols and glycol ethers that function as solvents or coalescing agents. Glycol ethers enter the environment in substantial quantities, are toxic for many microbial species [5-7] and represent a potential hazard for human health [8].

Over the last three decades, several research groups have isolated microorganisms with capacity to attack PU [9-15] and degrade xenobiotic additives [7, 9, 16, 17], and the abilities from several fungal and bacterial communities have been assessed in compost, soil, or liquid cultures [18-21] and in different activated sludges [22-25]. However, PU biodegradation is still a challenge for environmental and biological disciplines and little is known about structure or potential degradative enzymatic

pathways of microbial communities capable of PU biodegradation. Metagenomics

provides access to the structure and genetic potential of microbial communities, helping

to understand the ecophysiological relationships governing the dynamics of their

populations in the environment. Recently, a new approach has been developed that

allows the reconstruction of individual genomes of microbial species using physical

interactions between sequences within cells [26]. This approach involves Hi-C proximity

ligation and yields direct evidence of sequences co-occurrence within a genome, which is

used for *de novo* assembly, identification of complete and novel genomes [27] and for

testing functional and phylogenetic hypotheses, surpassing other methods for clustering

contigs by taxonomic origins [28-30].

To characterize the biodegradation process of the recalcitrant plastic PE-PU by

microbial communities, we adopted the commercial water PU dispersion PolyLack®

(Sayer Lack, México) that contains a proprietary aromatic polyether-polyurethane-

acrylate (PE-PU-A) copolymer and the xenobiotic additives N-methyl 2-pyrrolidone

(NMP), isopropanol (IP) 2-butoxyethanol (2-BE), dipropyleneglycol butyl ether (DPGB),

and dipropyleneglycol methyl ether (DPGM). In this work, we provide comprehensive

chemical and physical evidences for the capacity of a selected landfill microbial

community to degrade an aromatic PE-PU-A copolymer and the aforementioned

xenobiotic additives, and analyze its structure and phenotypic potential by applying the

Hi-C proximity ligation technology. Based on these analyses, we identified a novel

microbial landscape that can deal with PE-PU-A and xenobiotics additives degradation

and proposed the putative metabolic pathways and genes that can account for these

capabilities. This is one of the few studies that combine physical and chemical analyses

with metagenomics to elucidate possible metabolic pathways involved in xenobiotics

biodegradation, and the first metagenomic analysis of a polyurethane-degrading enriched

landfill community. Understanding these pathways will help to design environmental

biotechnological strategies that contribute to mitigate plastics and xenobiotics pollution

and to achieve a better environmental quality.

MATERIALS AND METHODS

Microbiological techniques

The BP8 community, studied in this work, was selected by inoculating deteriorated pieces

of PU foam collected at El Bordo Poniente municipal landfill, as previously described [21],

into a minimal medium (MM) [10] containing PolyLack® (0.3% v/v), as the sole carbon

source (MM-PolyLack). PolyLack® (Sayer Lack, Prod. Num. UB-0810, México) contains a

proprietary aromatic PE-PU-A copolymer (≤30% w/v), and the additives NMP (≤6% v/v),

2-BE (≤5% v/v), IP (≤3% v/v), DPGB (≤2% v/v), DPGM (≤1% v/v), and silica (≤3% w/v)

[31]. BP8 growth was quantified by dry weight. For that, flasks with MM-PolyLack (25 ml)

were inoculated with fresh cells (3 mg/ml) harvested from pre-cultures grown in MM-

PolyLack for 48 h at 37ºC, 220 rpm. At different incubation times, cells of one flask were

harvested, washed three times with phosphate buffer (50 mM, pH 7) and dried to

constant weight. Emulsification index (EI_{24}) and cell surface hydrophobicity (CSH) were

determined as described [32]. To observe cell-copolymer interactions, cells were fixed

with 3% (v/v) glutaraldehyde in phosphate buffer (100 mM, pH 7.4), at 4°C overnight,

washed three times, dehydrated with serial dilutions of ethanol, coated with gold and

analyzed in a JEOL JSM-5900-LV electron microscope.

Analytical techniques

Nuclear magnetic resonance spectra from dried PolyLack® dissolved in C_5D_5N (30 mg/ml)

were recorded at 298 K in a Bruker Avance 400 NMR (Billerica, MA, USA) at 400 MHz

(^{1}H). For most of the analytical techniques, cell-free supernatants (CFS) were obtained by

centrifugation at 17 211 x g for 10 min, filtered through Whatman grade 41 paper, and

dried at 37ºC for 5 days. Carbon content was determined in a Perkin Elmer Elemental

Analyzer (2400 CHN/O, Series II, Shelton, CT., USA). For gas chromatography coupled

to mass spectrometry (GC-MS) analysis, 25 ml CFS were extracted in 6 ml LC-18

cartridges (Supelco) at a flow rate of 2 ml/min, eluted with 2 ml chloroform:methanol (1:1,

v/v) and concentrated to 0.5 ml. Samples were injected in an Agilent GC system (7890B,

Santa Clara, CA, USA) using two 5%-phenyl-methylpolysiloxane columns (15 m x 250

μm x 0.25 μm). Oven was heated from 50ºC to 300ºC at 20ºC/min, Helium was used as

carrier gas at a flow rate of 1 ml/min. The injector temperature was 300ºC. For the

quantification of additives, pure compounds (Sigma-Aldrich Chemicals ≥98% purity) were

used for standard curves. Identification of biodegradation products was performed in an

Agilent Quadrupole Mass Analyzer (5977A MSD, Santa Clara, CA, USA) with electronic

ionization energy of 1459 EMV and the mass range scanned at 30-550 amu. Scan rate

was 2.8 spec/s. Data acquisition was performed with the Enhanced MassHunter software

system. Compounds were identified based on mass spectra compared to the NIST

database (2002 Library). Fourier transform infrared spectroscopy (FTIR) analyses were

performed in a Perkin Elmer spectrometer (Spectrum 400, Waltham, MA, USA) in

attenuated total reflection mode; 64 scans with a resolution of 4 cm^{-1} were averaged in

the range of 500-4000 cm^{-1}, processed and analyzed (Spectrum v6.3.5.0176 software).

Derivative thermogravimetric analyses (DTG) were performed in a Perkin Elmer

Thermogravimetric Analyzer (TGA 4000, Waltham, MA, USA) on 2.5 mg of dried CFS

samples heated 30-500ºC at a rate of 20ºC/min, under a N_2 atmosphere. Differential

Scanning Calorimetry (DSC) was performed analyzing 10 mg of dry CFS in a Q2000 (TA

Instrument, New Castle, DE, USA) at a rate of 10°C/min, under a nitrogen flow of 50

ml/min, at a 20-600ºC range. Gel Permeation Chromatography was performed in a

Waters 2695 Alliance Separation Module GPC (Milford, MA, USA) at 30°C in

tetrahydrofuran, using a universal column and a flow rate of 0.3 ml/min in CFS. All the

analyses were performed at least in three replicates. Controls were non-inoculated MM-

PolyLack supernatants similarly processed.

HI-C proximity ligation based metagenomic analysis

BP8 community cells cultured for 5 days in 50 ml of MM-PolyLack were harvested and

washed three times with phosphate buffer. Cells were resuspended in 20 ml TBS buffer

with 1% (v/v) formaldehyde (J.T. Baker) (crosslinker) and incubated 30 min with periodic

mixing. The crosslinker was quenched with glycine (0.2 g) (Bio-Rad) for 20 min,

thereafter cells were centrifuged, lyophilized and frozen at -20°C. For DNA extraction, cell

pellets (100 µl) were resuspended in 500 µl of TBS buffer containing 1% (v/v) Triton-X

100 and protease inhibitors [27]. DNA was digested with *Sau*3AI and *Mlu*CI and

biotinylated with DNA Polymerase I Klenow fragment (New England Biolabs) followed by

ligation reactions incubated for 4 h and then overnight at 70°C to reverse crosslinking.

The Hi-C DNA library was constructed by using the HyperPrep Kit (KAPA Biosystems,

Wilmington, MA, USA). A shotgun library was also prepared from DNA extracted from

non-crosslinked cells using Nextera DNA Sample Preparation Kit (Illumina). The two

libraries were paired-end sequenced using NextSeq 500 Illumina platform (Illumina, San

Diego, CA, USA). *De novo* metagenome draft assemblies from the raw reads were made

using the metaSPAdes assembler [33]. Hi-C reads were then aligned to the contigs

obtained from the shotgun library using the Burrows-Wheeler Alignment tool [34]

requiring exact read matching. The ProxiMeta algorithm was used to cluster the contigs

of the draft metagenome assembly into individual genomes [27]. Additionally, we

performed a community taxonomic profiling from shotgun reads using MetaPhlAn tool

[35]. Genome completeness, contamination, and other genomic characteristics were

evaluated using CheckM pipeline [36]. Phylogenetic analysis was performed using the

single copy molecular markers, DNA gyrase subunit A and ribosomal proteins L3 and S5,

selected from each deconvoluted genome and compared to homologous sequences from

GenBank. Alignments were cured with Gblocks tool

(http://phylogeny.lirmm.fr/phylo_cgi/one_task.cgi?task_type=gblocks) and WAG plus G

evolutionary models were selected using Smart Model Selection tool [37]. Finally,

phylogeny was inferred with the graphical interface of SeaView [38] using the Maximum

Likelihood method. To compare genetic relatedness, Average Nucleotide Identity (ANI)

between the genomes and the closest phylogenetic neighbors was calculated [39]. Open

reading frames were identified using MetaGeneMark [40]. KO assignments (KEGG

Orthology) and KEGG pathways reconstruction were performed with GhostKOALA server

and KEGG Mapper tool, respectively [41]. All the xenobiotic degradation pathways were

manually curated to only report those pathways in which most of the enzymes were

encoded in the BP8 metagenome.

Data availability

Genomes described in this manuscript were deposited to GenBank under Bioproject

Accession number: PRJNA488119.

RESULTS

Growth and interactions of BP8 cells with PolyLack®

The BP8 community cultivated in MM-PolyLack for 25 days exhibited a biphasic growth

with a first phase, from 0-13 days, presenting a growth rate (2-4 days) of 0.008 h^{-1} and a

second phase, from 13-25 days, with a growth rate (13-20 days) of 0.005 h^{-1}. Biomass

increased from 0.32 to 2.9 mg/ml and consumed 50.3% of the carbon from the medium at

25 days (Figure 1a). EI$_{24}$ initial value was 70%, it decreased to 24% at 20 days and

increased again to 70%. CSH started at 62% and decreased to 25% at the first growth

phase, thereafter it increased to 42% and remained constant until 20 days to increase to

67% at the end of the second phase (Figure 1b). SEM analysis at 10 days of cultivation

revealed multiple-sized (0.5-1.5 μm) rod-shaped cells aggregated and attached to

copolymer particles (Figure 1c). The changes in CSH and EI$_{24}$, reflect the complex cell-

substrate interactions involved in promoting substrate bioaccessibility and mineralization,

as has been observed in bacteria degrading other xenobiotics [42, 43].

Chemical and physical changes in PolyLack® components generated by the BP8

community

To characterize the biodegradative activity of the BP8 community on the PolyLack®

components, we performed different analytical techniques. GC-MS analysis of the CFS

revealed that BP8 metabolized the xenobiotic additives, NMP and IP at the first day of

cultivation, 2-BE at the fourth day and DPGM and DPGB were metabolized 85 and 73%

respectively at the first day, and remained constant until the end of the experiment

(Figure 2). Since the PE-PU-A copolymer structure is unknown, we proposed a

hypothetical structure (Figure S1), based on ^{1}H-NMR, the manufacturer's technical sheet

and in the most frequently used chemicals for the synthesis of this copolymer [44-46].

Since the first day of cultivation, complex and diverse chemical compounds such as

aromatics, nitrogen-containing, ethers, esters, aliphatics, alcohols and organic acids,

derived from the copolymer breakdown were observed. During the first 3 days (log

phase) the degradation products were low abundant, at 10 days (intermediate lag phase)

accumulation occurred, and during the second log phase their abundance decreased. Notably, isocyanates (2,4-toluene diisocyanate (TDI) and methylene diphenyl diisocyanate (MDI)) derivatives were aromatic amines observed maximal at the beginning and diminished throughout the cultivation period (Figure 2, S2), suggesting that metabolization of the urethane groups is being achieved. FTIR of CFS revealed changes in PE-PU-A functional groups. The signal intensity of the C=O stretch from urethane and acrylate carbonyl groups (1 730 cm^{-1}) increased at 5 days and lately decreased, suggesting hydrolysis and subsequent catabolism of urethanes and acrylates. The signal for aromatic groups C=C stretch (1 600 cm^{-1}) considerably decreased at 20 days, while the signal for aromatic C-C stretch (1 380 cm^{-1}) showed variable intensities at different days, and a new C-C signal for aromatics (1 415 cm^{-1}) appeared at 20 days, indicating the cleavage of the aromatic rings. The urethane N-H bending plus C-N stretch signal (1 530 cm^{-1}) slightly decreased at 15 days and increased at the end of the cultivation time, whereas urethane C-N stretching band (1 231 cm^{-1}) significantly increased, indicating urethane attack. Signals associated with urethane C-O-C stretch (1 086 cm^{-1}, 1 049 cm^{-1}) and C-O-C symmetric stretch (977 cm^{-1}) decreased during the cultivation period, indicating microbial activity on the ether groups. The signal for the acrylate's vinyl group C=C-H out of plane (850 cm^{-1}) decreased at 20 days, indicating the cleavage of the acrylate component. Also, the aliphatic chain signals (704 and 520 cm^{-1}) decreased during the cultivation period (Figure 3a). DTG thermograms exhibited four stages of thermal decomposition corresponding to the functional groups of the copolymer. Stages II and IV, for urethane and ether groups respectively, reduced their masses at early cultivation times, while stage III, for esters, steadily kept reducing its mass during the whole experimental period. Interestingly, stage I, which accounts for low molecular weight

compounds, in this case biodegradation products, showed a fluctuating behavior that

increased at 10 days, and decreased afterwards (Figure 3b). DSC analysis of the

copolymer showed multiple thermal transitions revealing complex microstructures: the

glass transition temperature (Tg: 50.2ºC) reflects the proportion of soft and hard

segments; the three melting temperatures (Tm-I: 70ºC, Tm-II: 210.6ºC, Tm-III: 398.1ºC)

are associated with the hard segments of the polymer and the crystallization temperature

(Tc: 459.6ºC) is attributed to heat-directed crystallization of copolymer chains [47, 48]

(Figure 3c). BP8 biodegradative activity caused Tg decrease (46.2ºC), changes in Tms,

and strong decrease in Tc area, indicating that BP8 disrupts both, the soft and the hard

segments (associated with urethane groups) (Figure 3, Table S1). GPC analysis showed

that the number-average molecular weight of the copolymer decreased 35.6% and the

PDI increased to values higher than 2, at 25 days of cultivation with BP8 (Table S2). All

these results indicate that the degradative activity of the BP8 community generates

changes in the soft and hard segments of the copolymer microstructure resulting from the

attack to the different functional groups, including the more recalcitrant ether and

urethane groups.

Community structure and metagenomic deconvolution of the BP8 community

Analysis of the BP8 community taxonomic profile with MetaPhlAn, by using 17 282 414

reads, detected five bacterial orders (abundance), *Rhodobacterales* (83%), *Rhizobiales*

(8.9%), *Burkholderiales* (6.8%), *Actinomycetales* (0.83%), *Sphingobacteriales* (0.08%),

and one viral order *Caudovirales* (0.33%). Bacteria included 16 genera, being the most

abundant *Paracoccus* (83.9%) and *Ochrobactrum* (8.7%) (Figure S3). *De novo* assembly

of the shotgun metagenome sequences generated 3 072 contigs with a total length of 17

618 521 bp. Alignment of Hi-C reads to this assembly allowed the deconvolution of five

genome clusters, three near complete drafts (>95%), and two substantially complete

drafts (89 and 71%) [36] (Table S3). The phylogenetic analysis showed well-supported

clades within *Paracoccus*, *Chryseobacterium*, *Parapedobacter*, a member of the

Microbacteriaceae family, and *Ochrobactrum intermedium* (Figure S4). The deconvoluted

genomes of *Paracoccus* sp. BP8 and *O. intermedium* BP8.5 showed low novelty scores

and high ANI values compared to their closest phylogenetic relatives, while

Chryseobacterium sp. BP8.2, *Parapedobacter* sp. BP8.3 and the *Microbacteriaceae*

bacterium BP8.4 showed high novelty scores and low ANI values (<95%) indicating they

are new species. GC content and genomes' sizes were similar to the closest relatives

except for the *O. intermedium* BP8.5 genome size, probably because of the low genome

completeness (Table S3, S4).

Analysis of the xenobiotic metabolism encoded in the BP8 metagenome

In all the genomes, except in *O. intermedium* BP8.5, the genes and proteins assigned

were in the range reported for the phylogenetically related members (Table S3, S4).

Reconstruction of the metabolic pathways encoded in the BP8 metagenome was

performed with 18 386 ORFs from which 8 637 were annotated into KEGG Orthology

groups and the rest was not assigned to any orthologous functional category. Analysis of

the BP8 xenobiotic metabolism identified 215 sequences encoding 59 unique proteins

participating in pathways for benzoate (ko00362), fluorobenzoate (ko00364),

aminobenzoate (ko00627), chlorocyclohexane and chlorobenzene (ko00361), and n-

alkanes (ko00071) degradation. The most relevant enzymes are listed in Table 1. The

genes for benzoate metabolism include all the enzymes for benzoate and 4-

methoxybenzoate activation as well as 4-methoxybenzoate monooxygenase, a O-

demethylating enzyme that transforms methoxybenzoate to hydroxybenzoate, and for

their subsequent transformation to β-ketoadipate (first 18 EC numbers in Table 1). Two

genes encoding carboxymethylene butanolidase that cleavages the ring of cyclic ester

dienelactone to produce maleylacetate, acting on the fluorobenzoate and

chlorocyclohexane and chlorobenzene metabolisms, were identified. Genes encoding

enzymes for the aminobenzoate pathway, such as 4-hydroxybenzoate decarboxylase

that participates in the transformation of phenol into hydroxybenzoate, amidase that

transforms benzamide into benzoate, and benzoyl phosphate phospohydrolase that

converts benzoyl phosphate into benzoate, were identified. All the genes encoding

enzymes needed for chlorocyclohexane and chlorobenzene degradation, the specific 2,4-

dichlorophenol 6-monooxygenase, the enzymes that transform 4-chlorophenol to cis-

acetylacrylate (EC1.13.11.1, EC5.5.1.1 and EC3.1.1.45), and the 2-haloacid

dehalogenase, which eliminates halogens from alkanes, were found. Likewise, genes

encoding enzymes for n-alkanes degradation (Table 1 Alkanes metabolism), as well as

all the enzymes for beta-oxidation were also detected.

BP8 community phenotypic potential to biodegrade the xenobiotic additives

present in PolyLack®

NMP degradation. Genes encoding putative proteins for NMP degradation, with

significant similarity (>40%) to the enzymes of *Alicycliphilus denitrificans* BQ1 [52] were

identified in several BP8 genomes (Table 1). However, only in *Paracoccus* sp. BP8 a

gene cluster (RQP05666.1-RQP05671.1) comparable to the BQ1 *nmp* cluster was

identified. *Isopropanol degradation.* Genes encoding proteins with significant similarity

to NAD+-dependent secondary ADH with capability to oxidize IP to acetone were

identified in the BP8 metagenome [49], but not the genes encoding the enzymes for the

oxidative transformation of acetone. However, the three genes encoding acetone

carboxylase, that transforms acetone into acetoacetate, were identified, as well as the enzymes that convert acetoacetate into acetoacetyl-CoA and this to acetyl-CoA are also encoded in the BP8 metagenome (Figure 4a, Table 1). *Glycol ethers degradation.* In the BP8 metagenome, homologous genes to PEG-degrading ADHs and ALDHs [50, 51], and diverse enzymes that could attack the ether bonds, such as glycolate oxidase (RQP04511.1, RQP04512.1, RQP04513.1, RQP11464.1, RQP19624.1, RQP19625.1, RQP16322.1, RQP16256.1), dye decoloring peroxidase (RQP04907.1, RQP09154.1) and superoxide dismutase (RQP04715.1, RQP13424.1, RQP09887.1, RQP11889.1, RQP18047.1, RQP18034.1, RQP09190.1, RQP20377.1), as well as genes encoding enzymes involved in glutathione metabolism, which have been proposed to participate in PEG metabolism [53] were identified (Figure 4b, Table 1).

BP8 community phenotypic potential to degrade polyurethane

Genes encoding PU-esterases verified for PU degradation [54-56] and confirmed carbamate-hydrolyzing enzymes *i.e.* arylamidase A [57], amidase [58], urethanase [59], and carbaryl hydrolase [60], were searched by standalone BLASTP analyses. Six and five sequences with similarity to PU-esterases and carbamate hydrolases were retrieved from the BP8 metagenome, respectively (Table 2). We also identified genes encoding ureases (EC3.5.1.5), suggested to act on PU degradation [61], in *Parapedobacter* sp. BP8 (RQP19536.1, RQP19537.1 RQP19538.1) and *O. intermedium* BP8.5 (RQP17756.1, RQP17448.1, RQP17449.1, RQP17450.1) genomes.

DISCUSSION

To elucidate the mechanisms that landfill microbial communities perform to degrade the recalcitrant PE-PU plastic, here we studied the degradative activity of the BP8 microbial community that was selected because of its capability to grow in PolyLack®, a WPUD that

contains a proprietary PE-PU-A copolymer and several xenobiotic additives (NMP, IP, 2-

BE, DPGB and DPGM). Chemical and physical analyses demonstrated that BP8

consumes the additives and breaks the copolymer whereas Hi-C based metagenomic

analysis allowed us to unveil the phenotypic potential to degrade PU and xenobiotics of

five deconvoluted genomes from the community. The diauxic growth of BP8 observed

during 25 days of cultivation in MM-PolyLack suggested that two different metabolic

processes were involved in degrading the components of the WPUD. We hypothesized

that the additives were consumed during the first phase whereas the copolymer was

broken during the second one. However, the biomass increment and the carbon

decrease observed in the first growth phase (Figure 1a) resulted not only from additive

consumption, but also from the copolymer breakdown (Figures 2, 3, S2, Tables S1, S2).

These observations indicate that the diauxic growth is the result of simultaneous

degradation of additives and copolymer and that microbial enrichment could have

selected a more effective PU-degrading community that accounts for the second

exponential growth phase. Further studies to demonstrate this possibility are being

undertaken.

Exploring the BP8 metagenome, genes encoding enzymes presumably involved in

the degradation of the PolyLack® additives were identified in several of the deconvoluted

genomes. Genes for NMP degradation, similar to the ones reported for *A. denitrificans*

BQ1 [52] were identified in the *Paracoccus* sp. BP8 genome. *Paracoccus* strains able to

utilize NMP as carbon source have been reported [62], but the genes sustaining this

capability have not been described. IP biodegradation occurs by oxidative pathways in *P.*

denitrificans GH3 and *Gordonia* sp. TY-5. In these strains, IP is transformed by NAD^+-

dependent secondary ADH into acetone that is oxidized by a specific monooxygenase to

produce methyl acetate, which is transformed to acetic acid and methanol [49, 63]. However, the enzymes for metabolizing acetone by these reactions are not encoded in the BP8 metagenome. Instead, genes encoding enzymes for acetone carboxylation, to produce acetoacetate (acetone carboxylase), and for its subsequent transformation to acetoacetyl-CoA by 3-oxoacid-CoA transferase and thereafter to acetyl-CoA by acetyl-CoA C-acetyltransferase [64] were identified (Figure 4a, Table 1). The possibility that IP degradation occurs by transformation to acetyl-CoA, via acetone in BP8 is supported by the observation that in the *Paracoccus* sp. BP8 genome, a gene encoding an ADH (RQP05888.1), homologous to the *Gordonia* sp. TY-5 *adh*2, and genes encoding the acetone carboxylase subunits (RQP05866.1, RQP05867.1, RQP05889.1) are contiguously located. Adjacent to these genes, a sequence encoding a sigma-54-dependent transcriptional regulator (RQP05868.1) was observed, suggesting an operon-like organization. This presumptive IP degradative operon has not been described in any other bacteria. Degradation of 2-BE, DPGM and DPGB, the glycol ethers present in PolyLack®, has not been reported in bacteria. Degradation pathways for PEG and PPG reported in *Sphingomonads* species and *Microbacterium* (formerly *Corynebacterium*) sp. No. 7 [5, 65, 66-68] show similar reactions where the glycols' hydroxyl terminal groups are sequentially oxidized by specific ADHs and ALDHs to produce aldehydes, and thereafter carboxylic acids [50, 51], suggesting a widespread strategy for glycol ethers metabolism in prokaryotes. Nevertheless, few enzymes involved in scission of ether bonds, present in these compounds, have been identified in bacteria. A glycolic acid oxidase [69] and a glycolic acid dehydrogenase [70] have been reported acting on PEG, although several other enzymes such as superoxide dismutase, monooxygenase, ether hydrolase, carbon-oxygen lyase, peroxidase and laccase have been suggested [5].

Homolog genes for specific ADHs and ALDHs were identified in the *Paracoccus* sp. BP8

genome (Table 1). Therefore, we hypothesize that 2-BE can be oxidized to 2-

butoxyacetic acid, DPGM to 2-methoxypropionic acid, which has been reported as a

metabolite in the degradation of DPGM by rats [71], and DPGB to 2-butoxypropionic acid

(Figure 4b). In *Paracoccus* sp. BP8, and in other genomes of the BP8 community, genes

encoding   glycolate   oxidase,   dye   decoloring   peroxidase,   4-methoxybenzoate

monooxygenase and unspecific monooxygenase, which could account for the ether

scission of the aforementioned carboxylic acids, were identified (Table 1). The cleavage

of the carboxylates produced by ALDHs would generate the metabolizable intermediaries

glyoxylate, butyraldehyde, propylene glycol and formaldehyde (Figure 4b). Glyoxylate can

be funneled to the glyoxylate metabolism, butyraldehyde to the butanoate metabolism,

propylene   glycol   to   the   pyruvate   metabolism,   by   lactaldehyde   and   lactate

dehydrogenases as suggested in *P. yeei* TT13 [72], and formaldehyde can be channeled

to the formate metabolism where glutathione-dependent enzymes could oxidize it to

formate and thereafter to CO_2 (Figure 4b, Table 1). All the enzymes for the aforesaid

metabolic pathways are encoded in the BP8 metagenome. Additionally, in PEG

metabolism, long chains of PEG-carboxylate can be processed by acyl-CoA synthetase

and glutathione-S transferase forming glutathione-conjugates [53]. Although these

reactions would not be needed for glycol ethers catabolism, they could be required for the

degradation of long polypropylene glycol moieties that are part of the PE-PU-A copolymer

(Figure S1).

By using different analytical techniques, we demonstrate that the BP8 community

attacks   the   main   functional   groups   of   the   PE-PU-A   copolymer;   from   the   more

enzymatically susceptible ester bonds, present in acrylate and carbamate, to the more

recalcitrant C-C from aliphatics and aromatics, C-N from urethane, and C-O-C from ether

bonds of polypropylene glycol (Figures S1, 2, 3). The changes in the chemical and

physical properties of the polymer when incubated with BP8, and the generation of

diverse degradation products, some of them potential metabolic intermediates in the

degradation process, are evidences of the BP8's degradative capability, which is

sustained by the diverse xenobiotic degrading enzymes encoded in its metagenome

(Table 1). Some of the biodegradation products (Figure 2) seem to be the result of

oxidative reactions on C-C bonds flanking TDI, MDI or the acrylates' styrene ring (Figure

3, S1), generating aromatic compounds containing hydroxyl, aldehydes or organic acids.

Additionally,   the   copolymer   aromatic   compounds   could   be   destabilized   by

monooxygenases, which introduces hydroxyl groups to the aromatic rings, and by

dioxygenases that catalyzes reductive dihydroxylation, generating central intermediates

that can be cleaved by dearomatizing dioxygenases producing carboxylic acids [73, 74].

The enzymes for the complete benzoate metabolism are encoded in the BP8

metagenome and could account for PE-PU-A aromatic rings catabolism (Table 1).

Aliphatic chains from acrylates and polypropylene glycols can be metabolized by alkane

1-monooxygenases, that activate aliphatic chains by terminal or subterminal oxidations

and by the activities of ADH and ALDH, generating compounds that can be channeled by

beta-oxidation into the fatty acids metabolism (Table 1). If terminal oxidations are

introduced, primary alcohols are generated and transformed into aldehydes, carboxylic

acids and acyl-CoA. If subterminal oxidations of aliphatic chains occur, secondary

alcohols are formed, which upon breakdown, will produce ketones and thereafter esters,

which are hydrolyzed to alcohol and organic acids [75, 76]. Many different esters

compounds   were   identified   in   the   BP8's   degradation   products,   suggesting   that

subterminal oxidation of alkanes could be an important route in PU metabolism (Figures

2, 3, S1). The cleavage of ester bonds by PU-esterases would produce alcohols and

organic acids, and the cleavage of urethane groups by carbamate-hydrolases would

produce nitrogen-containing compounds and aromatic isocyanate derivatives. As we

detected these degradation products by GC-MS analysis (Table 1, 2, Figure 2),

hydrolysis of ester and urethane bonds are accomplished during PE-PU-A degradation by

BP8. The identification of several PU-esterases and carbamate hydrolases encoded in

most of the BP8 genomes support this conclusion (Table 2).

The metabolic reactions proposed for the degradation of the additives and the PE-

PU-A copolymer present in PolyLack® by the BP8 community are based on the

phenotypic potential encoded in its metagenome. The use of proximity ligation Hi-C

technology allowed to define, with high confidence, what genes belong to each of the

different species of BP8 (Table 1). In this community, xenobiotic degradation is a niche

dominated by *Paracoccus* sp. BP8 and *Ochrobactrum intermedium* BP8.5, in whose

genomes, key enzymes for different steps of biodegradation are widely represented

(Table 1), which must be the reason for their preponderance in the BP8 community. In

addition, Microbacteriaceae bacterium BP8.4 genome encodes enzymes for the

metabolism of aromatic compounds suggesting that metacleavage ring excision and

muconate lactone formation might be functional. On the other hand, *Chryseobacterium*

sp. BP8.2 and *Parapedobacter* sp. BP8.3 genomes, harbor genes encoding

complementary metabolic activities for alkanes oxidation, such as hydrolysis and

oxidation of linear intermediates. The finding of such a diverse genetic repertoire in the

BP8 metagenome suggests a remarkable metabolic versatility, with strong hydrolytic and

oxidative capabilities that can play significant roles in the degradation of diverse

environmental contaminants. The abundance and distribution of these catabolic enzymes

among the different members of the BP8 community, suggest syntrophic mechanisms

driving community behavior. However, incomplete genome reconstruction in the

deconvolution analysis, resulting in potential pathway gaps in certain genomes, cannot be

ruled out, nor can the collapsing of multiple strains into a single cluster. On the other

hand, although *Paracoccus* and *Ochrobactrum* are predominant in the BP8 community by

far, we cannot discard that specific enzymatic activities encoded in genomes of little

abundant species can be crucial for the successful performance of BP8.

The present work provides deep understanding of the microbial ecology of a

selected landfill microbial community capable of PU and xenobiotics degradation by

revealing its composition and its outstanding phenotypic potential observed in the

catalytic capabilities that its members could display to cleave different recalcitrant

functional groups. Altogether, these features place BP8 community as a quite promising

source for developing environmental biotechnology strategies contributing to mitigate

anthropogenic plastics and xenobiotics pollution for achieving better environmental

quality. Moreover, further exploration of individual species of the community will allow the

manipulation of novel catabolic capabilities in order to improve biodegradative

technological processes.

ACKNOWLEDGEMENTS

IG and MB acknowledge Consejo Nacional de Ciencia y Tecnología for their Ph.D.

scholarships. ASR acknowledges Dirección General de Asuntos del Personal

Académico, UNAM, for his scholarship for a posdoctoral position at Facultad de Química,

UNAM. We thank USAII-FQ analytical support provided by Ch. Marisela Gutiérrez

Franco, Ch. Rafael Iván Puente Lee, Ch. Víctor Hugo Lemus and Ch. Elvira del Socorro

Reynosa in the FTIR, SEM, carbon quantification, and thermogravimetry analyses,

respectively. The technical support of MSc. Fernando de Jesús Rosas Ramírez in the

use of the GC-MS equipment is appreciated. Also, we are grateful to Gerardo Cedillo,

Salvador López and Karla E. Reyes from Institute of Materials Research (IIM-UNAM) for

their assistance in NMR, GPC and DSC analyses, respectively, and to Taylor Reiter and

C. Titus Brown for help with metagenomic analysis.

FUNDING INFORMATION

This work was funded by Programa de Apoyo a Proyectos de Investigación e Innovación

Tecnológica, Dirección General de Asuntos del Personal Académico, Universidad

Nacional Autónoma de México grants IN217114 and IN223317, and Programa de Apoyo

a la Investigación y el Posgrado, Facultad de Química, Universidad Nacional Autónoma

de México, grant 5000-9117. IL, MP, and SS were supported in part by NIAID grant

2R44AI122654-02A1.

CONFLICT OF INTEREST STATEMENT

IL, MP, and SS are employees and shareholders of Phase Genomics, a company

commercializing proximity ligation technology.

REFERENCES

1. Zalasiewicz J, Waters CN, Ivar do Sul JA, Corcoran PL, Barnosky AD, Cearreta A,

Edgeworth M, Gałuszka A, Jeandel C, Leinfelder R, McNeill JR, Steffen W,

Summerhayes C, Wagreich M, Williams M, Wolfe AP, Yonan Y. The geological cycle of

plastics and their use as a stratigraphic indicator of the Anthropocene. Anthropocene,

2016; 13: 4-17.

2. Plastics Europe. Plastics – the Facts 2018. An analysis of European plastics production,

demand and waste data. Association of Plastics Manufacturers.

http://www.plasticseurope.org 2018.

3. Cornille A, Auvergne R, Figovsky O, Boutevin B, Caillol S. A perspective approach to

sustainable routes for non-isocyanate polyurethanes. Eur. Polym. J. 2017; 87:535–52.

4. Furtwenglera P, Perrin R, Redl A, Avérous L. Synthesis and characterization of

polyurethane foams derived of fully renewable polyester polyols from sorbitol. Eur. Polym.

J. 2017; 97:319–27.

5. Kawai F. The biochemistry and molecular biology of xenobiotic polymer degradation by

microorganisms. Biosci Biotechnol Biochem. 2010; 74:1743-59.

6. Malla MA, Dubey A, Yadav S, Kumar A, Hashem A, Abd Allah EF. Understanding and

designing the strategies for the microbe-mediated remediation of environmental

contaminants using omics approaches. Front Microbiol. 2018; 9:1132.

7. Varsha YM, Naga Deepthi CH, Chenna S. An emphasis on xenobiotic degradation in

environmental clean up. J Bioremed Biodegradad. 2011; S11:001.

8. Organization for Economic Co-operation and Development. SIDS Initial Assessment

Report For SIAM 17. Propylene glycol ethers. UNEP Publications. 2003.

9. Cregut M, Bedas M, Durand MJ, Thouand G. New insights into polyurethane

biodegradation and realistic prospects for the development of a sustainable waste

recycling process. Biotechnol Adv. 2013; 31:1634-47.

10. Nakajima-Kambe T, Onuma F, Kimpara N, Nakahara T. Isolation and characterization of

a bacterium which utilizes polyester polyurethane as a sole carbon and nitrogen source.

FEMS Microbiol Lett. 1995; 129:39-42.

11. Osman M, Satti SM, Luqman A, Hasan F, Shah Z, Shah A. Degradation of polyester

polyurethane by *Aspergillus* sp. strain S45 isolated from soil. J Polym Environ. 2018;

26:301-10.

12. Oceguera-Cervantes A, Carrillo-García A, López N, Bolaños-Nuñez S, Cruz-Gómez MJ,

Wacher C, Loza-Tavera H. Characterization of the polyurethanolytic activity of two

Alicycliphilus sp. strains able to degrade polyurethane and Nmethylpyrrolidone. Appl

Environ Microbiol. 2007; 73:6214–23.

13. Gamerith C, Herrero AE, Pellis A, Ortner A, Vielnascher R, Luschnig D, Zartl B, Haernvall

K, Zitzenbacher S, Strohmeier G, Hoff O, Steinkellner G, Gruber K, Ribitsch D, Guebitz

GM . Improving enzymatic polyurethane hydrolysis by tuning enzyme sorption. Polym

Degrad Stabi. 2016; 132: 69-77.

14. Magnin A, Pollet E, Perrin R, Ullmann Ch, Persillon C, Phalip V, Avérous L. Enzymatic

recycling of thermoplastic polyurethanes: Synergistic effect of an esterase and an

amidase and recovery of building blocks. Waste Management. 2019; 85:141-50.

15. Tang YW, Labow RS, Santerre JP. Isolation of methylene dianiline and aqueous-soluble

biodegradation products from polycarbonate-polyurethanes. Biomaterials. 2003; 24:2805-

19.

16. Howard GT. Biodegradation of polyurethane: a review. Int Biodeterior Biodegrad. 2002;

49:245-52.

17. Ojo OA. Molecular strategies of microbial adaptation to xenobiotics in natural

environment. Biotechnol Mol Biol Rev. 2007; 2:1-3.

18. Cosgrove L, McGeechan PL, Robson GD, Handley PS. Fungal communities associated

with degradation of polyester polyurethane in soil. Appl Environ Microb. 2007; 73:5817-

24.

19. Zafar U, Nzerem P, Langarica-Fuentes A, Houlden A, Heyworth A, Saiani A, Robson GD.

Biodegradation of polyester polyurethane during commercial composting and analysis of

associated fungal communities. Bioresource Technol. 2014; 158:374-7.

20. Shah Z, Gulzar M, Hasan F, Shah AA. Degradation of polyester polyurethane by an

indigenously developed consortium of *Pseudomonas* and *Bacillus* species isolated from

soil. Polym Degrad Stabil. 2016; 134:349-56.

21. Vargas-Suárez M, Fernández-Cruz V, Loza-Tavera H. Biodegradation of polyacrylic and

polyester polyurethane coatings by enriched microbial communities. Appl Microbiol

Biotechnol. 2019; 103:3225-36.

22. Bustard MT, Meeyoo V, Wright P. Biodegradation of isopropanol in a three phase fixed

bed bioreactor: start up and acclimation using a previously-enriched microbial culture.

Environ Technol. 2001; 22:1193-201.

23. Loh CH, Wu B, Ge L, Pan Cha, Wang R. High-strength N -methyl-2-pyrrolidone-

containing process wastewater treatment using sequencing batch reactor and membrane

bioreactor: A feasibility study. Chemosphere. 2017; 194:534-42.

24. Liu T, Ahn H, Sun W, McGuinness LR, Kerkhof LJ, Häggblom, MM. Identification of a

Ruminococcaceae Species as the Methyl tert-Butyl Ether (MTBE) Degrading Bacterium

in a Methanogenic Consortium. Environ Sci Technol. 2016; 50:1455-64.

25. Ferrero P, San-Valero P, Gabaldón C, Martínez-Soria V, Penya-Roja JM. Anaerobic

degradation of glycol ether-ethanol mixtures using EGSB and hybrid reactors:

Performance comparison and ether cleavage pathway. J Environ Manag. 2018; 213:159-

67.

26. Burton JN, Liachko I, Dunham MJ, Shendure J. Species-level deconvolution of

metagenome assemblies with Hi-C-based contact probability maps. G3-Genes Genom

Genet. 2014; 4:1339-46.

27. Press MO, Wiser AH, Kronenberg ZN, Langford KW, Shakya M, Lo C-C, Mueller KA,

Sullivan ST, Chain PSG, Liachko I. Hi-C deconvolution of a human gut microbiome yields

high-quality draft genomes and reveals plasmid-genome interactions. bioRxiv 2017;

198713.

28. Wu Y-W, Tang Y-H, Tringe SG, Simmons BA, Singer SW. MaxBin: an automated binning

method to recover individual genomes from metagenomes using an expectation-

maximization algorithm. Microbiome. 2014; 2:26.

29. Breitwieser FP, Pertea M, Zimin AV, Salzberg SL. Human contamination in bacterial

genomes has created thousands of spurious proteins. Genome Res. 2019; 29:954-60.

30. Shaiber A, Eren AM. Composite metagenome-assembled genomes reduce the quality of

public genome repositories. mBio. 2019; 10:e00725-19.

31. SayerLack. Poly Lack Aqua Mate UB-0810. Manual Técnico. 2013.

http://www.gruposayer.com//web/uploads/file/TDS_UB-0810-file160515563.pdf

32. Gaytán I, Mejía MA, Hernández-Gama R, Torres LG, Escalante CA, Muñoz-Colunga A.

Effects of indigenous microbial consortia for enhanced oil recovery in a fragmented

calcite rocks system. J Petrol Sci Eng. 2015; 128:65-72.

33. Nurk S, Meleshko D, Korobeynikov A, Pevzner PA. metaSPAdes: a new versatile

metagenomic assembler. Genome Res. 2017; 27:824-34.

34. Li H, Durbin R. Fast and accurate long-read alignment with Burrows–Wheeler transform.

Bioinformatics. 2010; 26:589-95.

35. Segata N, Waldron L, Ballarini A, Narasimhan V, Jousson O, Huttenhower, C.

Metagenomic microbial community profiling using unique clade-specific marker genes.

Nature Methods. 2012; 9:811-4.

36. Parks DH, Imelfort M, Skennerton CT, Hugenholtz P, Tyson GW. CheckM: Assessing the

quality of microbial genomes recovered from isolates, single cells, and metagenomes.

Genome Res. 2015; 25:1043-55.

37. Lefort V, Longueville JE, Gascuel O. SMS: Smart Model Selection in PhyML. Mol Biol

Evol. 2017; 34:2422-4.

38. Gouy M, Guindon S, Gascuel O. SeaView version 4: A multiplatform graphical user

interface for sequence alignment and phylogenetic tree building. Mol Biol Evol. 2010;

27:221-4.

39. Yoon S-H, Ha S, Lim J, Kwon S, Chun J. A large-scale evaluation of algorithms to

calculate average nucleotide identity. Antonie Van Leeuwenhoek. 2017; 110:1281-6.

40. Zhu W, Lomsadze A, Borodovsky M. Ab initio gene identification in metagenomic

sequences. Nucleic Acids Res. 2010; 38:e132.

41. Kanehisa M, Sato Y, Morishima K. BlastKOALA and GhostKOALA: KEGG Tools for

functional characterization of genome and metagenome sequences. J Mol Biol. 2016;

428:726-31.

42. Stelmack PL, Gray MR, Pickard MA. Bacterial adhesion to soil contaminants in the

presence of surfactants. Appl Environ Microbiol. 1999; 65:163-8.

43. Wick L, Ruiz de Munain A, Springael D, Harms H. Responses of *Mycobacterium* sp.

LB501T to the low bioavailability of solid anthracene. Appl Microbiol Biotechnol. 2002;

8:378-85.

44. Gite VV, Mahulikar PP, Hundiwale DG. Preparation and properties of polyurethane

coatings based on acrylic polyols and trimer of isophorone diisocyanate. Prog Org Coat.

2010; 68:307-12.

45. Maurya SD, Kurmvanshi SK, Mohanty S, Nayak SK. A review on acrylate-terminated

urethane oligomers and polymers: synthesis and applications. Polym Plast Technol Eng.

2018; 57:625-56.

46. Pardini OR, Amalvy JI. FTIR, 1H-NMR spectra, and thermal characterization of water-

based polyurethane/acrylic hybrids. J Appl Polym Sci. 2008; 107:1207-14.

47. Cipriani E, Bracco P, Kurtz SM, Costa L, Zanetti M. In-vivo degradation of

poly(carbonate-urethane) based spine implants. Polym Degrad Stabil. 2013; 98:1225-35.

48. Sultan M, Islam A, Gull N, Bhatti H, Safa Y. Structural variation in soft segment of

waterborne polyurethane acrylate nanoemulsions. J Appl Polym Sci. 2014; 132:41706.

49. Kotani T, Yamamoto T, Yurimoto H, Sakai Y, Kato, N. Propane monooxygenase and

NAD$^+$-dependent secondary alcohol dehydrogenase in propane metabolism by *Gordonia*

sp. strain TY-5. J Bacteriol. 2003; 185:7120-8.

50. Ohta T, Kawabata T, Nishikawa K, Tani A, Kimbara K, Kawai F. Analysis of amino acid

residues involved in catalysis of polyethylene glycol dehydrogenase from *Sphingopyxis*

terrae, using three-dimensional molecular modeling-based kinetic characterization of

mutants. Appl Environ Microbiol. 2006; 72:4388-96.

51. Tani A, Charoenpanich J, Mori T, Takeichi M, Kimbara K, Kawai F. Structure and

conservation of a polyethylene glycol-degradative operon in sphingomonads.

Microbiology. 2007; 153:338-46.

52. Solís-González CJ, Domínguez-Malfavón L, Vargas-Suárez M, Gaytán I, Cevallos MA,

Lozano L, Cruz-Gómez MJ, Loza-Tavera H. Novel metabolic pathway for *N*-

methylpyrrolidone degradation in *Alicycliphilus* sp. BQ1. Appl Environ Microbiol. 2018;

84:pii: e02136-17.

53. Somyoonsap P, Tani A, Charoenpanich J, Minami T, Kimbara K, Kawai F. Involvement of

PEG-carboxylate dehydrogenase and glutathione S-transferase in PEG metabolism by

Sphingopyxis macrogoltabida strain 103. Appl Microbiol Biotechnol. 2008; 81:473-84.

54. Nomura N, Shigeno-Akutsu Y, Nakajima-Kambe T, Nakahara T. Cloning and sequence

analysis of a polyurethane esterase of *Comamonas acidovorans* TB-35. J Ferment

Bioeng. 1998; 86:339-45.

55. Stern RV, Howard GT. The polyester polyurethanase gene (*pueA*) from *Pseudomonas*

chlororaphis encodes a lipase. FEMS Microbiol Lett. 2000; 185:163-8.

56. Ufarté L, Laville E, Duquesne S, Morgavi D, Robe P, Klopp C, Rizzo A, Pizzut-Serin S,

Potocki-Veronese G. Discovery of carbamate degrading enzymes by functional

metagenomics. PLoS One. 2017; 12:1-21.

57. Zhang J, Yin J-G, Hang B-J, Cai S, He J, Zhou S-G, Li S-P. Cloning of a novel

arylamidase gene from *Paracoccus* sp. strain FLN-7 that hydrolyzes amide pesticides.

Appl Environ Microbiol. 2012; 78:4848-55.

58. Yun H, Liang B, Qiu J, Zhang L, Zhao Y, Jiang J, Wang A. Functional characterization of

a novel amidase involved in biotransformation of triclocarban and its dehalogenated

congeners in *Ochrobactrum* sp. TCC-2. Environ Sci Technol. 2016; 51:291-300.

59. Liu X, Fang F, Xia X, Du G, Chen J. Stability enhancement of urethanase from

Lysinibacillus fusiformis by site-directed mutagenesis. Sheng Wu Gong Cheng Xue Bao.

2016; 32:1233-42.

60. Hashimoto M, Mizutani A, Tago K, Ohnishi-Kameyama M, Shimojo T, Hayatsu M.

Cloning and nucleotide sequence of carbaryl hydrolase gene (*cahA*) from *Arthrobacter*

sp. RC100. J Biosci Bioeng. 2006; 101:410-14.

61. Yang Y, Kang Z, Zhou J, Chen J, Du G. High-level expression and characterization of

recombinant acid urease for enzymatic degradation of urea in rice wine. Appl Microbiol

Biotechnol. 2015; 99:301-08.

62. Cai S, Cai T, Liu S, Yang Q, He J, Chen L, Hu J. Biodegradation of N-methylpyrrolidone

666 by *Paracoccus* sp. NMD-4 and its degradation pathway. Int Biodeterior Biodegradation

667 2014; 93:70–7.

668 63. Geng Y, Deng Y, Chen F, Jin H, Tao K, Hou T. Biodegradation of isopropanol by a

669 solvent-tolerant *Paracoccus denitrificans* strain. Prep Biochem Biotechnol. 2015;

670 45:4919.

671 64. Schühle K, Heider J. Acetone and butanone metabolism of the denitrifying bacterium

672 *Aromatoleum aromaticum* demonstrates novel biochemical properties of an ATP-

673 dependent aliphatic ketone carboxylase. J Bact. 2012; 194:131-41.

674 65. Tachibana S, Kawai F, Yasuda M. Heterogeneity of dehydrogenases of

675 *Stenotrophomonas maltophilia* showing dye-linked activity with polypropylene glycols.

676 Biosci Biotechnol Biochem. 2002; 66:737-42.

677 66. Kawai, F. Microbial degradation of polyethers. Appl Microbiol Biotechnol. 2002; 58:30-8.

678 67. Hu X, Liu X, Tani A, Kimbara K, Kawai F. Proposed oxidative metabolic pathway for

679 polypropylene glycol in *Sphingobium* sp. Strain PW-1. Biosci Biotechnol Biochem. 2008;

680 72:1115-18.

681 68. Ohtsubo Y, Nagata Y, Numata M, Tsuchikane K, Hosoyama A, Yamazoe A, Tsuda M,

682 Fujita N, Kawai F. Complete genome sequence of a polypropylene glycol-degrading

683 strain, *Microbacterium* sp. No. 7. Genome Announc. 2015; 3:e01400-15,

684 69. Yamanaka H, Kawai F. 1991. Purification and characterization of a glycolic acid (GA)

685 oxidase active toward diglycolic acid (DGA) produced by DGA-utilizing *Rhodococcus* sp.

686 No. 432. J Ferment Bioeng. 1991; 7:83-8.

687 70. Enokibara S, Kawai F. 1997. Purification and characterization of an ether bond-cleaving

688 enzyme involved in the metabolism of polyethylene glycol. J Ferment Bioeng. 1997;

689 83:549-54.

71. Miller RR, Langvardt PW, Calhoun LL, Yahrmarkt MA. Metabolism and disposition of

propylene glycol monomethyl ether (PGME) beta isomer in male rats. Toxicol Appl

Pharmacol. 1986; 83:170–7.

72. Lim JY, Hwang I, Ganzorig M, Pokhriyal S, Singh R., Lee K. Complete genome sequence

of Paracoccus yeei TT13, isolated from human skin. Genome Announc. 2018; 6:e01514-

17.

73. Seo JS, Keum Y-S, Li QX. Bacterial degradation of aromatic compounds. Int J Environ

Res Public Health. 2009; 6:278-309.

74. Ladino-Orzuela G, Gomes E, da Silva R, Salt C, Parsons JR. Metabolic pathways for

degradation of aromatic hydrocarbons by bacteria. Rev Environ Contamination Toxicol.

2016; 237,doi10.1007/978-3-319-23573-8_5

75. Rojo F. Degradation of alkanes by bacteria. Environment Microbiol. 2009; 11:2477-90.

76. Wentzel A, Ellingsen TE, Kotlar HK, Zotchev SB, Throne-Holst M. Bacterial metabolism

of long-chain *n*-alkanes. Appl Microbiol Biotechnol. 2007; 76:1209-21.

Table 1. Distribution of genes encoding relevant proteins involved in xenobiotics degradation in the BP8 metagenome.

Activity	K Number	EC	Name	*Paracoccus* sp. BP8	*Chryseobacterium* sp. BP8.2	*Parapedobacter* sp. BP8.3	Microbacteriaceae bacterium BP8.4	*O. intermedium* BP8.5
Benzoate and related compounds metabolism								
Benzoate/toluate 1,2-dioxygenase	K05549 K05550 K05784	1.14.12.10 1.18.1.-	*benA-xylX* *benB-xylY* *benC-xylZ*	1 1 1	-	-	-	-
Dihydroxyclohexadiene carboxylate dehydrogenase	K05783	1.3.1.25	*benD-xylL*	1	-	-	-	-
p-Hydroxybenzoate 3-monooxygenase	K00481	1.14.13.2	*pobA*	1	-	-	-	1
Catechol 1,2-dioxygenase	K03381	1.13.11.1	*catA*	1	-	-	-	-
Catechol 2,3-dioxygenase	K07104	1.13.11.2	*catE*	1	-	-	1	1
Protocatechuate 3,4-dioxygenase	K00448 K00449	1.13.11.3	*pcaG-pcaH*	1 1	- -	- -	- -	1 1
Muconate cycloisomerase	K01856	5.5.1.1	*catB*	1	-	-	1	-
3-Carboxy-cis,cis-muconate cycloisomerase	K01857	5.5.1.2	*pcaB*	1	-	-	-	1
Muconolactone isomerase	K01856	5.3.3.4	*catC*	1	-	-	-	-
4-Carboxymuconolactone decarboxylase	K01607	4.1.1.44	*pcaC*	2	-	-	-	1
Enol-lactone hydrolase	K01055	3.1.1.24	*pcaD*	3	-	-	-	1
β-ketoadipate:succyinyl-CoA transferase,	K01031 K01032	2.8.3.6	*pcaI-pcaJ*	1 1	- -	- -	- -	2 1
β-ketoadipyl-CoA thiolase	K00632	2.3.1.16	*pcaF*	-	1	1	1	1
2-Oxopent-4-enoate hydratase (benzoate)	K02554	4.2.1.80	*mhpD*	-	-	-	1	-
4-Hydroxy 2-oxovalerate aldolase	K01666	4.1.3.39	*mhpE*	-	-	-	2	-
Acetaldehyde dehydrogenase	K04073	1.2.1.10	*mhpF*	-	-	-	2	-
4-Methoxybenzoate monooxygenase (O-	K22553	1.14.99.15	CYP199A2	1	-	-	-	-

demethylating)

Carboxymethylene butanolidase	K01061	3.1.1.45	*clcD*	-	-	-	1	1
4-Hydroxybenzoate decarboxylase	K03186	4.1.1.61	*ubiX*	2	-	1	-	1
Amidase	K01426	3.5.1.4	*amiE*	1	-	-	1	1
Benzoyl phosphate phosphohydrolase	K01512	3.6.1.7	*acyP*	-	-	1	1	-
2,4-Dichlorophenol 6-monooxygenase	K10676	1.14.13.20	*tfdB*	1	-	-	-	-
2-Haloacid dehalogenase	K01560	3.8.1.2		2	-	-	-	1
Alkanes metabolism								
Alkane 1-monooxygenase	K00496	1.14.15.3	*alkB1_B2 alkM*	2	-	-	-	-
Ferredoxin NAD reductase component	K00529	1.18.1.3	*hcaD*	2	-	-	-	1
Unspecific monooxygenase	K00493	1.14.14.1		2	-	-	-	1
Long-chain-alkane monooxygenase	K20938	1.14.14.28	*LadA*	-	-	-	1	-
Alcohol dehydrogenase propanol preferring	K13953	1.1.1.1	*adhP*	2	-	1	-	1
Aldehyde dehydrogenase (NAD$^+$ dependent)	K00128	1.2.1.3	ALDH	6	2	-	-	3
Aldehyde dehydrogenase (NADP dependent)	K14519	1.2.1.4	*aldH*	-	1	-	-	-
Lipocalin family protein	K03098	-	*Blc*	-	1	1	-	1
Long chain fatty acid transport protein	K06076	-	*fadL*	1	-	-	-	-
N-methyl 2-pyrrolidone metabolism								
N-methylhydantoin amidohydrolase	K01473 K01474	3.5.2.14	*nmpA nmpB*	5 5	- -	- -	- 1	1 -
Aminoacid oxidase	-	-	*nmpC*	3	-	-	2	1
Succinate-semialdehyde dehydrogenase	K00135	1.2.1.16	*nmpF*	7	-	1	2	1
Isopropanol metabolism								
[a]Alcohol dehydrogenase propanol preferring	K13953	1.1.1.-	*adh1*	1	-	-	-	-

Enzyme	KO	EC	Gene					
Alcohol dehydrogenase	K18369	1.1.1.-	*adh2*	2	-	-	-	-
[b]Aldehyde dehydrogenase	K00138	1.2.1.-	*adh3*	1	-	-	1	-
Acetone carboxylase	K10854		*acxB*	1				
	K10855	6.4.1.6	*acxA*	1	-	-	-	1
	K10856		*acxC*	1				
3-Oxoacid-CoA transferase	K01028	2.8.3.5		1	1	1	1	-
	K01029			1	1	1	1	-
Acetoacetate-CoA ligase	K01907	6.2.1.16	*acsA*	-	-	-	-	1
Acetyl-CoA C-acetyltransferase	K00626	2.3.1.9	*atoB*	10	1	1	3	5

Glycol ethers and polypropylene glycols metabolism

Enzyme	KO	EC	Gene					
[c]Alcohol dehydrogenase,	.	1.1.1.-	*pegdh*	3	-	-	-	3
[d]Aldehyde dehydrogenase	-	1.2.1.3	*pegC*	3	-	-	1	-
Glycolate oxidase	K00104		*glcD*	1	-	-	-	2
	K11472	1.1.3.15	*glcE*	1	-	-	-	1
	K11473		*glcF*	1	-	-	1	1
Superoxide dismutase	K04564	1.15.1.1	SOD2	-	1	3	1	1
	K04565		SOD1	1	1	-	-	-
Dye decoloring peroxidase	K15733	1.11.1.19	*DyP*	1	-	-	1	-
Glutathione S-transferase	K00799	2.5.1.18	*gst*	11	-	-	-	8
Acyl Co-A synthetase	K01897	6.2.1.3	*ACSL*	2	3	2	2	1
S-(hydroxymethyl) glutathione dehydrogenase	K00121	1.1.1.284	*frmA*	3	-	-	-	2
S-formylglutathione hydrolase	K01070	3.1.2.12	*fghA*	1	-	-	-	1

[a] *Adh1* was identified by BLAST analysis using the *adh1* sequence (Acc. num. BAD03962.1) reported for *Gordonia* sp. TY-5 [49] as query (Query cover ≥ 99%; E-value ≤ 4E-42; Identity 34%). The gene accession number in the BP8 metagenome is RQP06405.1.

[b] *Adh3* genes were identified by BLAST analysis using the *adh3* sequence (Acc. num. BAD03965.1) reported for *Gordonia* sp. TY-5 [49] as query (Query cover ≥ 97%; E-value ≤ 1E-97; Identity ≥ 38.8%). The gene accession numbers in the BP8 metagenome are RQP06404.1 and RQP13157.1. These genes were classified as aldehyde dehydrogenases by KEGG, similarly as described in [49].

[c] *Pegdh* genes were identified by BLAST analysis using the polyethylene glycol dehydrogenase sequence (*pegdh*) from *Sphingophyxis terrae* (Acc. num. BAB61732) [50] as query (Query cover ≥ 97%; E-value ≤ 2.0E-122; Identity ≥ 38.5%). The gene accession numbers in the BP8 metagenome are RQP05609.1, RQP06903.1, RQP07092.1, RQP19606.1, RQP18819.1, RQP20974.1.

[d] *Pegc* genes were identified by BLAST using polyethylene glycol aldehyde dehydrogenase sequence from *Sphingophyxis macrogoltabida* (Acc. num. BAF98449.1) [50] as query (Query cover ≥ 98%; E-value ≤ 1.0E-80; Identity ≥ 38%; Similarity ≥ 56%). The gene accession numbers in the BP8 metagenome are RQP06197.1, RQP04172.1, RQP06015.1, RQP13157.1. Only RQP06197.1 was identified as K00128 by KEGG.

Table 2. Esterases and carbamate hydrolyzing enzymes encoded in the BP8 metagenome.

Enzyme Query Organism (Accession number)	E.C. num.	Amino acids in the query	Hit in the BP8 metagenome	E value/ [a]Identity/ Similarity	Amino acids in the hit	Reference
Polyurethane esterase *Delftia acidovorans* (BAA76305)	3.1.1.6	548	*Parapedobacter* sp. BP8.3 (RQP17780.1)	1.0E-07/ 32%/ 48%	640	[54]
Polyurethanase esterase A *Pseudomonas chlororaphis* (AAD22743)	3.1.1.-	617	*Paracoccus* sp. BP8 (RQP07762.1)	4.0E-16/ 34%/ 50%	783	[55]
			Paracoccus sp. BP8 (RQP06646.1)	2.0E-14/ 33%/ 46%	980	
			Paracoccus sp. BP8 (RQP04598.1)	7.0E-12/ 30%/ 43%	854	
			Paracoccus sp. BP8 (RQP06839.1)	5.0E-12/ 32%/ 43%	612	
Esterase CE_Ubrb uncultured bacterium (SIP63154)	3.1.1.-	295	*Microbacteriaceae* bacterium BP8.4 (RQP12977.1)	8.0E-05/ 35%/ 48%	309	[56]
Arylamidase A *Paracoccus huijuniae* (AEX92978)	3.4.11.2	465	*Paracoccus* sp. BP8 (RQP04489.1)	6.0E-25/ 41%/ 52%	471	[57]
Amidase *Ochrobactrum* sp. TCC-2 (ANB41810)	3.5.1.4	474	*Microbacteriaceae* bacterium BP8.4 (RQP11486.1)	2.0E-47/ 35%/49%	475	[58]
			O. intermedium BP8.5 (RQP19215.1)	6.0E-24/ 39%/50%	326	
Urethanase *Lysinibacillus fusiformis* (KU353448)	3.5.1.4	472	*Microbacteriaceae* bacterium BP8.4 (RQP12064.1)	1.0E-60/ 32%/ 48%	499	[59]
Carbaryl hydrolase *cahA Arthrobacter* sp. RC100 (BAC15598)	3.6.3.5	506	*Paracoccus* sp. BP8 (RQP06118.1)	1.0E-15/ 35%/ 48%	326	[60]

[a]Only genes with identity ≥ 30% are presented.

Figure 1. Characteristics of the BP8 community growing in MM-PolyLack. a) Growth and carbon consumption, **b)** emulsification index (EI$_{24}$) and cell surface hydrophobicity (CSH) at different cultivation times; **c)** SEM micrograph of BP8 cells attached to the PE-PU-A copolymer at 10 days of cultivation. Bars represent standard deviation. n=3.

Figure 2. Xenobiotic additives consumed (a) and PE-PU-A biodegradation products generated (b) by the BP8 community. Cell-free supernatants were extracted at differents culture times with chloroform:methanol and analyzed by GC-MS. **a)** Additives were quantified using standard curves for each compound and **b)** biodegradation products by analyzing their relative areas in independent chromatograms. n=3. Compounds with mass spectra similarity values over 700 were considered the same compounds of the Library hits. The numbers in the compounds correspond to signals in the chromatograms of Figure S2.

Figure 3. Physical and chemical analyses of the aromatic PE-PU-A copolymer after incubation with the BP8 community. a) FTIR spectra. **b)** DTG analysis. Thermal degradation stages correspond to the following functional groups: I. Low molecular weight compounds, II. Urethane, III. Ester, IV. Ether; **c)** DSC analysis. Glass transition temperature (Tg) represents the relative amount of soft and hard segments; melting temperatures, Tm-I, Tm-II and Tm-III are associated with hard domains, and crystallization temperature (Tc) represents heat-directed crystallization of copolymer chains**.**

Figure 4

Figure 4. Potential degradation pathways for isopropanol (a) and glycol ethers (b) encoded in the BP8 metagenome. a) *Paracoccus* sp. BP8 genome encodes ADH enzymes that can oxidize IP to acetone, but no genes encoding enzymes for acetone metabolism were found. Instead, the genes encoding the three subunits of acetone carboxylase that reductively transforms acetone to acetoacetate were found. Acetoacetate can be transformed to acetoacetyl-CoA by 3-oxoacid-CoA transferase activity, present in *Paracoccus* sp. BP8 or by acetoacetate-CoA ligase, present in O. intermedium BP8.5. Acetoacetyl CoA is transformed by acetyl-CoA C-acetyltransferase to acetyl CoA, that enters the TCA pathway encoded in the BP8 metagenome (See Table 1). **b)** Degradation of 2-BE could be carried out by subsequent oxidations of the hydroxy terminal group by PEG-DH and PEG-ALDH, followed by scission of the ether bond by glycolate oxidase or other ether scission enzymes to produce glyoxylate and butyraldehyde [5, 65]. Glyoxylate would be funneled to the glyoxylate metabolism (white rectangle) and butyraldehyde to the butanoate metabolism (light gray rectangle). DPGB and DPGM can also be degraded by initial oxidation of the hydroxy terminal groups and further be ether-cleaved by ether scission enzymes. The products of these processes would be butyraldehyde an propylene glycol from DPGB and propylene glycol and formaldehyde from DPGM. Propylene glycol can be funneled to the pyruvate metabolism (medium gray rectangle) and formaldehyde can be transformed by the methane metabolism (dark gray rectangle), Genes encoding homologs for PEG-DH and PEG-ALDH (pegdh and pegc) from *Sphyngophyxis terrae* and S. macrogoltabida, the three subunits of glycolate oxidase (glcD, glcE, glcF) and other possible ether scission enzymes were identified in *Paracoccus* sp. BP8 (See Table 1). Pathways for glyoxylate, butanoate, pyruvate and methane metabolisms as well as the TCA pathway were fully reconstructed from the BP8 metagenome based on KEGG annotated genes, using KEGG Mapper.

Degradation of recalcitrant polyurethane and xenobiotic additives by a selected landfill microbial community and its biodegradative potential revealed by proximity ligation-based metagenomic analysis

Itzel Gaytán[1†], Ayixon Sánchez-Reyes[1†], Manuel Burelo[2], Martín Vargas-Suárez[1], Ivan Liachko[3], Maximilian Press[3], Shawn Sullivan[3], M. Javier Cruz-Gómez[4] and Herminia Loza-Tavera[1]*

Pages 9

Tables 4

Figures 4

Table S1. Effects of BP8 biodegradative activity on the PE-PU-A copolymer analyzed by Differential Scanning Calorimetry.

Culture time (days)	Tg (°C)	Tm-I (°C)	Tm-II (°C)	Tm-III (°C)	Tc (°C)
Non-inoculated	50.2	70.0	210.6	398.1	459.6
5	39.5	68.8	211.0	408.7	478.2
10	46.0	68.0	210.1	407.9	480.2
15	38.1	70.5	211.1	393.2	479.9
20	46.2	78.8	213.9	392.5	476.2

Tg = glass transition temperature; Tm = melting temperature; Tc = crystallization temperature.

Table S2. Molecular weight and polydispersity index of the PE-PU-A copolymer during cultivation with the BP8 community.

Culture time (days)	Mn (g/mol)	PDI
Non-inoculated	101 896 ± 8098	2.0 ± 0.3
5	96 798 ± 712	2.2 ± 0.1
10	89 258 ± 5825	2.5 ± 0.3
15	82 577 ± 1168	3.1 ± 0.6
20	79 859 ± 9225	2.4 ± 0.3
25	65 609 ± 990	2.6 ± 0.2

Number-average molecular weight (Mn) and polydispersity index (PDI) were calculated by Gel Permeation Chromatography with monodisperse polystyrene calibration standards and using THF as eluent. n=3

Table S3. General features of the deconvoluted genomes from the BP8 metagenome.

Cluster ID	Genome Size (bp)	Num Contigs	Contig N50	[a]Comple-teness (%)	[b]Relative Abun-dance (%)	Novelty Score (%)	GC (%)	Identification	Genes assigned	Proteins assigned
1	4 275 656	282	51 004	89.4	57.7	1.6	67.8	*Paracoccus* sp. BP8	4 225	4 073
2	2 157 639	388	7 081	95.6	3.7	98.7	47.3	sp. BP8.2	2 253	185
3	5 478 545	1098	6 493	95.5	12.5	99.2	48.1	*Parapedobacter* sp. BP8.3	5 310	5 173
4	2 790 120	158	39 967	97.7	3.6	94.0	71.3	bacterium BP8.4	2 850	705
5	2 916 513	1146	2 823	71.0	22.5	2.5	58.4	*Ochrobactrum intermedium* BP8.5	3 472	3 162

[a]Completeness was calculated based on 40 single copy gene markers [36]. All the genomes' drafts have at least 18 tRNAs and, except for cluster 5, at least 1 rDNA gene copy.
[b]Relative abundance was normalized according to the reads distribution along the deconvoluted taxon.
[c]For Microbacteriaceae bacterium BP8.4 no further classification was possible even that nine single-copy markers were analyzed.

Table S4. [a]Phylogenetic relatedness of the bacterial species from the BP8 community identified by Hi-C metagenome deconvolution

Clusters/ Clasification/ GeneBank Acc. Num.	Organism	Assembly	Genome size (Mb)	GC content (%)	[a]ANI value (%)	Proteins encoded in the genomes
Cluster 1/ *Paracoccus* sp. BP8 GCA_003852815.1	*Paracoccus* sp. J39	GCA_000518925.1	4.42837	68.08	98.73	
	Paracoccus denitrificans	GCA_000203895.1	5.23619	66.78	90.24	
	Paracoccus aminovorans	GCA_001546115.1	4.58940	67.50	85.59	4131-4993
	Paracoccus halophilus	GCA_900111785.1	4.00871	65.20	82.17	
	Paracoccus yeei	GCA_002073635.2	4.82967	67.08	81.95	
Cluster 2/ *Chryseobacterium* sp. BP8.2 GCA_003852805.1	*Chryseobacterium koreense*	GCA_001045435.1	3.15420	40.10	69.38	
	Chryseobacterium camelliae	GCA_002770595.1	4.37635	41.80	68.86	
	Chryseobacterium luteum	GCA_000737785.1	4.71855	37.30	68.70	3000-4810
	Chryseobacterium sp. 52	GCA_002754245.1	5.29882	37.00	68.49	
	Chryseobacterium antarcticum	GCA_000729985.1	3.12366	36.10	68.10	
Cluster 3/ *Parapedobacter* sp. BP8.3 GCA_003852785.1	*Parapedobacter indicus*	GCA_900113765.1	6.15523	48.00	80.23	
	Parapedobacter koreensis	GCA_900109365.1	5.54776	48.20	74.24	3796-4949
	Parapedobacter luteus	GCA_900168055.1	4.82992	49.30	73.66	
	Parapedobacter composti	GCA_900112315.1	4.62202	50.00	73.32	
Cluster 4/ Microbacteriaceae bacterium BP8.4 GCA_003852775.1	*Micrococcales bacterium* 72-143	GCA_001898835.1	3.33048	71.60	85.07	
	[b]*Leifsonia* sp. Leaf336	GCA_001423695.1	4.15779	69.60	74.40	
	[b]*Microcella alkaliphila*	GCA_002355395.1	2.70284	68.40	74.10	
	[b]*Plantibacter* sp. H53	GCA_001650455.1	4.01278	69.40	73.98	2535-3047
	[b]*Herbiconiux* sp. YR403	GCA_000799285.1	3.60404	62.00	71.66	
	[c]*Arthrobacter cupressi*	GCA_900099975.1	4.0588	67.00	70.82	
Cluster 5/ *Ochrobactrum intermedium* BP8.5 GCA_003852825.1	*Ochrobactrum intermedium* LMG 3301	GCA_000182645.1	4.72539	57.70	98.48	
	Ochrobactrum anthropi	GCA_000017405.1	5.20578	56.15	87.48	
	Ochrobactrum oryzae OA447	GCA_002943495.1	4.46700	56.20	87.19	3645-4502
	Brucella ceti	GCA_000590795.1	3.27803	57.27	82.03	
	Ochrobactrum sp. P6BS-III	GCA_002016635.1	5.25313	56.00	81.19	

[a] Phylogenetic relatedness was calculated based on ANI value with OrthoANIu algorithm. ANI values higher than 95% indicate that the compared genomes are the same species [39].
[b] Members of Microbacteriaceae family, order Micrococcales.
[c] Member of Micrococcaceae family, order Micrococcales.

Figure S1. Proposed chemical structure for the PE-PU-A copolymer present in PolyLack®. This structure was proposed based on the ¹H-NMR analysis of dried PolyLack®, the information included in the manufacturer technical manual [SayerLack. Poly Lack Aqua Mate UB-0810. Manual Técnico. 2013. http://www.gruposayer.com//web/uploads/file/TDS_UB-0810-file160515563.pdf], the GC-MS analysis (Figure 2), and the most frequent acrylates used in the synthesis of these types of copolymers [Maurya SD, Kurmvanshi SK, Mohanty S, Nayak SK. A review on acrylate-terminated urethane oligomers and polymers: synthesis and applications. Polym Plast Technol Eng. 2018; 57:625-56; Pardini OR, Amalvy JI. FTIR, 1H-NMR spectra, and thermal characterization of water-based polyurethane/acrylic hybrids. J Appl Polym Sci. 2008; 107:1207-14]. Synthesis of PE-PU-A copolymers starts by the polycondensation of polyols (polypropylene glycol) (y moiety) and diisocyanates (TDI and MDI) (x and z moieties) followed by end capping with acrylates' mixture (m moiety). From the most frequently used acrylates we selected methyl methacrylate, butyl acrylate, hydroxy acrylate and styrene as representatives in this structure. In the ¹H-NMR spectrum, chemical shifts are provided in parts per million from SiMe₄ as internal reference. Signal 1 is assigned to carbamate groups (NH-COO); signals a, b, c, 2, 3, 9-11 are assigned to the aromatic protons; signals 4 and 8 correspond to the protons of methylene (CH₂) and methyl (CH₃) groups in MDI and TDI, respectively; signals 5-7 correspond to PPG; signals l correspond to the hydroxyl proton (CH₂-O) and methylene groups (CH₂) in the chain of hydroxy-acrylate; signals f, j, o and p correspond to the acrylic groups (CH-COO, CH₂-COO or CH₃-COO), signals d (CH), e, g, i, k, q, r (CH₂), h and s (CH₃) are assigned to methylene and methyl groups in the acrylate mixtures.

Figure S2. Chromatograms of cell-free supernatants from BP8 cultures grown in MM-PolyLack. Numbered signals designate compounds identified by mass spectrometry listed in Figure 2. Chromatogram of non-inoculated sample is at original scale, whereas the other chromatograms are at larger scale.

A:s Yualikevirus unclassified
B:s Sphingobacterium unclassified
C:s Leifsonia unclassified
D:s Leucobacter unclassified
E:s Propionibacterium acnes
F:s Paracoccus unclassified
G:s Paracoccus denitrificans
H:s Brevundimonas diminuta
I:s Ochrobactrum intermedium
J:s Ochrobactrum unclassified
K:s Afipia unclassified
L:s Afipia broomeae
M:s Rhizobium lupini
N:s Agrobacterium unclassified
O:s Alicycliphilus unclassified
P:s Thiomonas unclassified
Q:s Achromobacter unclassified
R:s Achromobacter piechaudii
S:s Pusillimonas unclassified
T:s Bordetella unclassified
U:s Ralstonia unclassified

- F ALCALIGENACEAE
- F BRADYRHIZOBIACEAE
- F BRUCELLACEAE
- F BURKHOLDERIACEAE
- F BURKHOLDERIALES NONAME
- F CAULOBACTERACEAE
- F COMAMONADACEAE
- F MICROBACTERIACEAE
- F PROPIONIBACTERIACEAE
- F RHIZOBIACEAE
- F RHODOBACTERACEAE
- F SIPHOVIRIDAE
- F SPHINGOBACTERIACEAE

Figure S3. Taxonomic cladogram of BP8 community microbial diversity profiled with MetaPhlAn. Circles size is proportional to the taxon relative abundance. The most abundant taxa were *Paracoccus* genus (83.3%) and *Ochrobactrum* genus (8.7%). Families are color-labeled and predicted species diversity is indicated by capital letters [Asnicar F, Weingart G, Tickle TL, Huttenhower C, Segata N. Compact graphical representation of phylogenetic data and metadata with GraPhlAn. PeerJ. 2015;3:e1029].

Figure S4. Maximum likelihood phylogeny for taxonomic delimitation of the deconvoluted genomes from the BP8 metagenome. This analysis was performed with three phylogenetic markers, ribosomal protein L3, ribosomal protein L5 and DNA gyrase A subunit, which generated similar results. Here we present the analysis for ribosomal protein L3. Branch support values are indicated in the corresponding nodes. Bar indicates the number of expected substitutions per site under the WAG + G model. A sequence of *Ruminococcus albus* (Firmicutes) was used as outgroup. Key genome clusters are highlighted in bold and different Phyla are indicated at the left. Sequences for L3 ribosomal proteins of the deconvoluted genomes are accessible in the NCBI GenBank under accession numbers RQP07704.1, RQP15098.1, RQP16503.1, RQP08603.1 and RQP16393.1 for clusters 1 to 5, respectively.