Foreign body reaction is triggered *in vivo* by cellular mechanosensing of implants

stiffer than host tissue

Alejandro Carnicer-Lombarte[1,2,†], Damiano G. Barone[1,3,†], Ivan B. Dimov[2], Russell S.

Hamilton[4], Malwina Prater[4], Xiaohui Zhao[4], Alexandra L. Rutz[5], George G. Malliaras[5],

Stephanie P. Lacour[6], Clare E. Bryant[3], James W. Fawcett[1,7,*], Kristian Franze[2,8,9,*].

[1]John van Geest Centre for Brain Repair, Department of Clinical Neurosciences, University

of Cambridge, Cambridge CB2 0PY, UK.

[2]Department of Physiology Development and Neuroscience, University of Cambridge,

Cambridge CB2 3DY, UK.

[3]Department of Veterinary Medicine, University of Cambridge, Madingley Road, Cambridge

CB3 0ES, UK.

[4]Centre for Trophoblast Research, University of Cambridge, Cambridge, CB2 3EG, UK.

[5]Electrical Engineering Division, Department of Engineering, University of Cambridge,

Cambridge CB3 0FA, UK.

[6]Bertarelli Foundation Chair in Neuroprosthetic Technology, Laboratory for Soft

Bioelectronics Interface, Institute of Microengineering, Institute of Bioengineering, Centre for

Neuroprosthetics, Ecole Polytechnique Fédérale de Lausanne (EPFL), 1202 Geneva,

Switzerland.

[7] Centre for Reconstructive Neuroscience, Institute for Experimental Medicine CAS, Prague,

Czech Republic

[8] Institute of Medical Physics, Friedrich-Alexander University Erlangen-Nuremberg, 91052

Erlangen, Germany

[9] Max-Planck-Zentrum für Physik und Medizin, 91054 Erlangen, Germany

[†] These authors contributed equally to this work.

* To whom correspondence should be addressed: jf108@cam.ac.uk, kf284@cam.ac.uk

Abstract

Medical implants offer a unique and powerful therapeutic approach in many areas of

medicine. However, their lifetime is often limited as they may cause a foreign body

reaction (FBR) leading to their encapsulation by scar tissue[1-4]. Despite the importance

of this process, how cells recognise implanted materials is still poorly understood[5,6].

Here, we show how the mechanical mismatch between implants and host tissue leads

to FBR. Fibroblasts and macrophages, which are both crucially involved in mediating

FBR, became activated when cultured on materials just above the stiffness of healthy

tissue. Coating stiff implants with a thin layer of hydrogel or silicone with a tissue-like

elastic modulus (~20 kPa in subcutaneous and ~2 kPa in peripheral nerve implants) or

softer significantly reduced inflammation and fibrosis three months after

implantation. Materials stiffer than the host tissue led to nuclear localisation of the

mechanosensitive transcriptional regulator YAP in neighbouring cells *in vivo*,

confirming mechanotransduction. The alleviation of FBR by soft coatings not

exceeding the stiffness of the host tissue provides a strategy to achieve long-term

implant stability without extensive modification of current implant manufacturing

techniques, facilitating clinical translation.

Introduction

Medical implants have become an indispensable tool for a wide range of applications,

including bladder control[7], treatment of neurological disorders[8], drug delivery[9], and tissue

repair[10]. Recent advances in fabrication techniques have allowed for the development of

increasingly complex implants, capable of better integrating into the host tissue and much

improved functionality. This is particularly visible in the field of neural interfaces, where

implants are capable of establishing electrical connections with individual axons and neurons

without disrupting their connectivity[11,12]. Functionality of such implants actively interacting

with their environment requires the establishment and maintenance of intimate interfaces

between implant and tissue.

However, this interface and thus long-term functionality of medical implants is often limited

by foreign body reaction (FBR) – a process by which the body recognises implanted

materials as foreign and attempts to degrade them. FBR is characterised by chronic

inflammation and fibrosis, and with time results in the formation of a scar – a fibrotic capsule

– separating the implant from the host tissue[5]. How the body recognises implanted materials

as foreign and what triggers the associated inflammatory response is still not fully

understood[5,6].

The breakdown of the tissue-implant interface is one of the leading causes of implant

failure[1–3], which has led to large efforts to develop a treatment to prevent and manage FBR

to implanted materials[13,14]. Impregnation of implants with anti-inflammatory drugs such as

dexamethasone is currently widely used in clinical practice to alleviate inflammatory

reactions and suppress FBR in nerve interfaces[15]. However, such chemical treatments can

have significant side effects[15].

Recent studies indicated that softer materials may also alleviate FBR[16–19]. However, to date

we do not know how soft materials need to be in order to avoid foreign body reactions. In

fact, elastic moduli (a measure of stiffness) of implant materials classified as 'soft' in

literature range from kPa to GPa – spanning 6 orders of magnitude[20]. Here we show that

implant materials need to be at least as soft as the host tissue to suppress FBR. We show

that FBR is triggered by cellular mechanotransduction at the surface of stiff implants *in vivo*

rather than by tissue damage due to rigid implants as often thought[20–22]. Furthermore, we

developed a scalable technique to manufacture implants with a thin layer of a very soft

material – down to the softness of the host tissue itself – which accommodates cellular

mechanosensitivity and greatly reduces FBR.

Results

We first investigated how primary macrophages and fibroblasts, cell types crucial for FBR in

many tissue types, respond to substrates with different mechanical properties, covering a

physiologically relevant stiffness range. Macrophages are a central component of innate

immunity and are responsible for driving the inflammatory response to implanted materials[5,6].

Fibroblasts, on the other hand, are the primary mediators of the fibrotic response,

responsible for the formation of the fibrotic capsule around the implant.

Most macrophages involved in FBR are derived from blood-circulating monocytes, while

fibroblasts proliferate from tissue-resident populations[5,6]. We cultured primary bone marrow-

derived macrophages and fibroblast populations derived from peripheral nerve tissue on

polyacrylamide substrates of a range of elastic (shear) moduli. We chose nerve fibroblasts

because of the high impact of FBR on peripheral nerve interfaces. While implants with shear

moduli of few hundreds of kPa are commonly considered 'soft'[21–23], shear moduli of our

substrates ranged from 0.1 kPa, mechanically resembling the softest tissues in the body

including peripheral nerve tissue[24], to 50 kPa, which is already stiffer than most soft tissues

and organs[25] (substrates used: 0.1, 1, 10, 50 kPa shear modulus; corresponding to ~0.3, 3,

30, 150 kPa Young's modulus, Supplementary Fig. 1).

FBR-induced scarring is particularly detrimental to electrical neural interfaces, such as those

implanted in nerves. We therefore initially focused on this tissue. Nerve fibroblasts cultured

on substrates of varying stiffness for 6 days retained a spherical morphology on soft gels

with shear moduli of ~0.1-1 kPa, while cell spreading significantly increased on stiffer

substrates with shear moduli of 10-50 kPa (Fig. 1b) (p = 1.2e-7, one-way ANOVA). Adhesion

to the substrate via focal adhesions (Fig. 1c) and proliferation (Supplementary Fig. 2)

showed similar significant increases with substrate stiffness (adhesion p = 5.2e-9,

proliferation p = 0.0023). These observed increases in cell spreading, adhesion, and

proliferation are consistent with a fibroblast FBR-like phenotype[26].

Fibroblasts in FBR and other fibrotic processes typically differentiate into myofibroblasts –

which are characterised by the expression of alpha smooth muscle actin (αSMA) and high

extracellular matrix production[27]. Exposure to the non-physiological high stiffness of 50 kPa

significantly increased the synthesis of both αSMA and the extracellular matrix protein

collagen I – a primary component of the FBR capsule (Fig. 1d-f) (collagen p = 1.4e-26,

αSMA p = 5.3e-26, one-way ANOVAs). Fibronectin - a different extracellular matrix protein –

was present in nerve fibroblast cultures but was largely independent of substrate stiffness

(Supplementary Fig. 2). Our results on primary nerve fibroblasts are consistent with previous

studies of fibroblast populations from other tissues reporting that fibroblasts transition into a

myofibroblast phenotype at high substrate stiffnesses[27,28].

Macrophages showed similar functional changes on substrates stiffer than their physiological

host tissue. Similar to nerve fibroblasts, cell spreading, adhesion, and proliferation rates

were significantly increased on stiffer if compared to softer substrates (Fig 2a-c,

Supplementary Fig. 3) (spreading p = 9.8e-8, adhesion p = 0.009, proliferation p = 0.007,

one-way ANOVA), indicating macrophage activation.

RNA sequencing of macrophages three days post-plating showed a switch in gene

expression patterns, particularly in inflammation-related genes, between cells cultured on

substrates as soft as or softer than healthy nerve tissue (0.1 – 1 kPa) and cells cultured on

substrates stiffer than nerves (10 – 50 kPa) (Fig. 2d). These transcriptional differences were

consistent with a switch in phenotype from pro-inflammatory M1 on softer substrates to the

scar production-driving M2 phenotype on stiffer substrates. On stiff substrates, we found

downregulation of proinflammatory genes such as interleukin 1 beta (*il1b*) (p = 1.4e-6, FDR

adjusted p-value) and prostaglandin E synthase (*ptgs2*) (p = 9.5e-6), while M2-associated

genes such as arginase (*arg1*) (p = 0.002) and peroxisome proliferator-activated receptor-γ

(*ppar*γ) (p = 0.007) were upregulated if compared to soft substrates. This switch to a

macrophage M2 activation profile is typically associated with tissue regeneration and

fibrosis[29,30]. Together, our *in vitro* experiments indicated that a substrate stiffness above that

of the host tissue may lead to fibrosis, a hallmark of FBR.

Having confirmed that both primary macrophages and nerve fibroblasts assume an FBR-like

phenotype when exposed to materials that are stiffer than their host tissues, we sought to

test if materials mechanically matched to these tissues may alleviate FBR at the cellular

level *in vivo* in rat models. While it is often difficult or impractical to fabricate and use

implants made entirely from extremely soft materials because of fabrication and handling

challenges, stiff materials can be masked from cells underneath a thick enough layer of a

softer material[31–33]. Hence, we designed silicone rubber implants with a shear modulus of ~

200 kPa, which we coated with a 100 µm thick layer of a soft material (Fig. 3a). The

structural mechanical properties of these implants, such as bending stiffness, are dominated

by the much thicker ~200 kPa silicone rubber and are thus largely independent of the

coatings. However, at the cellular level, the thin coatings will "stealthen" the underlying

stiffer substrate from the adjacent cells (see Methods for details)[31–33].

The coatings consisted of either soft 0.2 kPa polyacrylamide (PAA_0.2kPa), 2kPa silicone

(PDMS_2kPa), or 20 kPa polyacrylamide (PAA_20kPa). One group of implants remained

non-coated (PDMS_200kPa) (Supplementary Fig. 4). We also benchmarked the

performance of our soft-coated implants against currently used clinical strategies, exploiting

devices impregnated with chemical repressors of inflammatory reactions such as

glucocorticoids[15,34], by including a group of implants coated with a ~100 µm thick

dexamethasone-impregnated silicone of ~ 200 kPa (Dex)[15].

These devices were implanted first into the subcutaneous space of rats, a common location

for medical implants such as pulse generators[35] and biosensors[17], facing the underlying

striated muscle. Three months post-implantation, a time point by which acute inflammation

due to implantation has resolved and chronic responses to implanted materials have settled

in, FBR was significantly reduced around the implants with soft coatings if compared to the

stiffer materials as revealed by immunohistochemistry (Fig. 3b). The intensities of markers

for myofibroblasts (αSMA), collagen I, and macrophages (CD68) were significantly lower in

tissues surrounding soft materials (αSMA $p = 0.005$, collagen $p = 6.0e\text{-}4$, CD68 $p = 3.4e\text{-}5$,

one-way ANOVA) (Fig. 3c). The reduction in FBR around soft implant surfaces was similar to

that observed in dexamethasone-treated implants ($p > 0.05$ for all three stains, Bonferroni-

corrected Student's t-tests). Also capsule thickness, a measure of fibroblast proliferation

around the implant and of the severity of FBR, was significantly decreased around implants

with soft coatings of $G \leq 20$kPa (Fig. 3d, Supplementary Fig. 6) ($p = 0.006$, one-way

ANOVA). Like our *in vitro* results, the extracellular matrix protein fibronectin did not vary

significantly across groups (Supplementary Fig. 5) ($p = 0.14$, one-way ANOVA).

Principal component analysis of the analysed FBR markers showed that all three soft

coatings clustered together and were distinct from the stiffest coating (Fig. 3e), suggesting

that coatings with a shear modulus of up to ~20 kPa, which is similar to muscle tissue

stiffness[31,36], ameliorated FBR to subcutaneous implants. These results indicated that FBR

can be minimized by coating implant surfaces with a material whose stiffness does not

exceed that of the surrounding tissue.

To test if the suppression of FBR by implants with soft coatings is a tissue type-specific

phenomenon or if it is more generally applicable, we then implanted nerve conduits with or

without soft coatings as those described above in a rat model of nerve injury (Fig. 4a) (for

details on sciatic nerve transection see Methods). Similar to the subcutaneous implants,

intensity of markers for myofibroblasts (αSMA) and activated macrophages (CD68) were

significantly decreased in tissues exposed to a soft coating compared to the non-coated

control implants (Fig. 4b, c) (αSMA $p = 0.002$, CD68 $p = 0.007$, one-way ANOVAs). Collagen

I also showed a similar trend, although differences were not statistically significant (Fig. 4b,

c) ($p = 0.19$, one-way ANOVA), while capsules became significantly thinner around softer

materials (Fig. 4d) ($p = 0.0008$, one-way ANOVA). The decrease in the cellular components

of FBR around soft implant surfaces was also similar to that of dexamethasone-treated

implants (for all soft-coated implants compared to Dex: $p > 0.05$, Bonferroni-corrected

Student's t-tests, Fig. 4b, c), indicating that soft coatings of implants may indeed represent a

general approach to alleviate FBR to biomedical implants irrespective of the type of host

tissue.

Principal component analysis of the analysed FBR markers revealed that, as in the

subcutaneous model, the softer implants were closer to the implants treated with

dexamethasone, suggesting that the softest coatings ameliorated FBR most. In contrast to

the subcutaneous model, however, in nerves only the two softest coatings ($G = 0.2$ kPa and

2 kPa) clustered together and were distinct from the stiffer materials of $G = 20$ kPa and 200

kPa (Fig. 4f). Because nerves are softer than subcutaneous tissue, with a stiffness on the

order of ~1 kPa[24], our results confirmed that FBR may indeed be minimized by implant

coatings at least as soft as the surrounding host tissue.

While soft-coated implants exhibited similar anti-FBR properties as dexamethasone-treated

materials, glucocorticoids such as dexamethasone are not only anti-inflammatory but also

anti-proliferative. Consequently, neuronal regeneration was significantly reduced in

dexamethasone-doped nerve implants if compared to implants with soft coatings (Fig. 4b, e,

Supplementary Fig. 7) (p = 0.003, one-way ANOVA). Hence, our data showed that soft

coatings of implants not only suppress inflammation and FBR but also permit regeneration –

in contrast to currently exploited devices relying on the anti-inflammatory properties of

glucocorticoids.

In FBR and fibrosis, the secretion of dense networks of extracellular matrix rich in

components such as collagen I leads to an increase in the stiffness of the tissue surrounding

the implant[37,38]. To further corroborate the suppression of FBR in tissues surrounding

implants with soft coatings, we used *ex vivo* atomic force microscopy to measure the

apparent elastic moduli of tissues exposed to the different implants (Fig. 4f). With a median

reduced apparent elastic modulus K ~ 1200 Pa, tissue around the stiffest conduits showed a

significant degree of stiffening compared to tissue around all soft-coated and

dexamethasone-treated implants with K ~ 150 Pa (p < 0.001 relative to all soft-coated and

dex-treated groups, Dunnett's multiple comparison test), which were indistinguishable from

each other (p = 0.70; Bonferroni-adjusted Student's t-test) (Fig 4g), adding further evidence

that soft implant coatings minimised the development of FBR.

Both our *in vivo* and *in vitro* experiments indicated that different implant coatings

considerably impacted the onset and extent of FBR. However, the different materials used in

this study might not only differ in their mechanical properties but also in their ability to bind

proteins. Protein adsorption – an initial and critical step in FBR – can vary between materials

and lead to differences in FBR severity[39]. Hence, we next tested if protein adsorption

depended on the type of material using a bicinchoninic acid (BCA) assay. We found no

differences in protein adsorption across our different surfaces (Supplementary Fig. 8) (p =

0.954, one-way ANOVA), suggesting that FBR to implants stiffer than the host tissue was

indeed initiated by a direct, mechanosensitive response of cells rather than indirectly via

alterations in protein adsorption.

To further corroborate that cellular mechanotransduction – the conversion of mechanical

cues into biochemical signals – was involved in FBR to implants stiffer than the host tissue,

we investigated the cellular distribution of the transcriptional regulator YAP in tissue

surrounding implants after 3 months. In many systems, YAP is majorly involved in

mechanotransduction[40]. On soft substrates, YAP is usually excluded from the nucleus, while

on stiffer substrates YAP enters the nucleus, leading to mechanically driven changes in gene

expression[41]. This effect has been observed *in vitro* in several cell types including

fibroblasts[42] as well as *in vivo*[43]. Immunohistochemical stains indeed revealed a significantly

lower nuclear localisation of YAP in tissues exposed to softer coatings if compared to stiffer

coatings in both implant types (Fig. 5) (subcutaneous $p = 0.01$, nerve $p = 0.001$, one-way

ANOVAs), confirming that cells in the vicinity of medical implants sense and respond to the

stiffness of the implant material.

Discussion

As in previous *in vitro* studies of similar cell systems, primary bone marrow-derived

macrophages and peripheral nerve tissue-derived fibroblasts investigated in this study

responded to the stiffness of their environment[17,44–47]. Our results link this cellular

mechanosensitivity to a key problem in medical implants: FBR. Contact with materials stiffer

than native tissue led to trans-differentiation of fibroblasts into myofibroblasts, and

macrophages became activated and took on an M2-like phenotype, driving tissue generation

an thus leading to thicker fibrotic capsules. This effect was similar for two different soft

materials: polyacrylamide and PDMS, and it occurred irrespective of implant design and the

location of implantation, indicating a very robust response of host tissues to implant stiffness.

Collectively, our results show that a mechanical mismatch between implant material and

host tissue stiffness may drive FBR at the cellular level. In nerves – a tissue with a stiffness

on the order of ~1kPa[24] – coatings of 2kPa and 0.2 kPa were most effective in minimising

FBR (Fig. 4f), while in the subcutaneous space – a tissue with a stiffness of approximately

12 kPa[31,36] –all coatings not exceeding 20 kPa were similarly effective (Fig 3e). Our data are

consistent with recent observations that ultra-soft implants can reduce FBR compared to

stiffer counterparts[17,19], and they define the upper limit of implant stiffness: softening an

implant surface to at least match the stiffness of its host tissue resulted in maximum

reduction of mechanically triggered FBR. Additionally, by using implants with similar

structural mechanical properties and various thin soft coatings, we showed that this

threshold of FBR is determined at the cellular level and not a result of the mechanical

mismatch between tissue and the whole implant as generally thought[20–22].

Mechanotransduction – the process by which cells translate mechanical cues into

biochemical responses – plays a key role in many cellular processes[48]. Cells constantly

probe their mechanical environment by applying contractile forces. This activates

downstream signalling pathways – which have yet to be fully characterised – leading to

changes in gene expression and cell function. Mechanotransduction has recently been

associated with inflammation[17] and fibrosis[19] *in vitro*. Here, we provide direct evidence for an

involvement of cellular mechanotransduction in the regulation of immune cell and connective

tissue cell function *in vivo.*

The transcription factor yes-associated protein (YAP) is a key downstream mediator in many

mechanotransduction pathways[40,41]. Its substrate stiffness-dependent translocation into the

nucleus is a useful marker to identify systems in which mechanotransduction is playing an

active a role[40–43]. We observed that, in tissue surrounding an implant, YAP's cellular

distribution is affected by implant stiffness *in vivo*. While softer materials have been used in

the past to decrease tissue damage around implants and to increase their

biocompatibility[20,49–51], our results provide a first direct link between *in vivo* cellular

mechanotransduction and FBR.

Current medical implants offer a powerful tool for the treatment of a number of clinical

conditions. However, long term stability of implants often remains limited by FBR, particularly

of those actively interacting with the host's environment such as electrical neural interfaces.

Corticosteroid drugs such as dexamethasone offer a viable strategy to control FBR in certain

situations[34]. However, their anti-inflammatory effect also greatly interferes with regeneration

of surrounding tissue[15], making them ill-suited for use in regenerative implants. As shown

here, coatings at least as soft as the host tissue offer an effective strategy to minimise FBR

without impacting surrounding tissue function or sacrificing the bulk mechanical properties of

the implant itself.

Medical implants are usually prepared from materials compatible with miniaturisation,

surgical handling, and advanced 3D design. These materials are much stiffer than their

biological host tissues. Tissue-level soft coatings offer a number of advantages as FBR-

minimising components of medical implants. The coatings' dimensions and compatibility with

existing microfabrication techniques make this technology potentially easy to apply to many

implant designs, which may facilitate translation to the clinic. Moreover, the FBR-reducing

effects are linked to the mechanical – and not chemical – properties of the coating materials,

providing great flexibility in material choice for different implant designs and applications.

Hence, the optimization of the mechanical surface properties of medical implants, in addition

to that of their chemical and electrical properties, will likely greatly contribute to long-term

stability of these devices in the future.

Materials and Methods

Polyacrylamide cell culture substrates.

Polyacrylamide hydrogels were prepared two days prior to the plating of any cells, using a

protocol previously described[52]. 19 mm diameter glass coverslips were cleaned by alternate

dipping in ddH$_2$O and EtOH, and covered in 0.1N NaOH (VWR, E584) for 5 min. NaOH was

removed, and coverslips were functionalised with 150 μl of APTMS (3-

Aminopropyltrimethoxysilane; Sigma, 281778) solution for 2.5 min, followed by thorough

rinsing in water. Coverslips were finally allowed to sit in a glutaraldehyde 0.5% (v/v) solution

(G6257, Sigma) in ddH$_2$O (15230089, Fisher Scientific) for 30 min at RT.

Polyacrylamide premixes were prepared by mixing of acrylamide (40\% w/w; A4058, Sigma),

bis-acrylamide (2%; BP1404-250; Fisher Scientific), and hydroxy-acrylamide (97%; 697931;

Sigma) solutions (177:100:23 ratio). A volume of PBS (D8537, Sigma) was added to the

premix to achieve gels of a particular stiffness (Supplementary Table 1). This final gel mix

was degassed under a vacuum for 10 min.

To initiate polymerisation, 5 μl of ammonium persulfate solution (0.1 g/ml in ddH$_2$O; Sigma,

215589) and 1.5 μl of TEMED (N,N,N´,N´-tetramethylethylenediamine; 15524-010,

Invitrogen) were added to 500 μl of gel mixes. 8 μl drops of mix were placed on the treated

surface of 19 mm diameter coverslips, and covered with a 22 mm diameter glass coverslip

(previously treated with a RainX hydrophobic coating – Rain Repellent Krako Car Care

International Ltd, UK).

The gels were allowed to swell in PBS overnight, allowing any remaining monomers and

unreacted crosslinkers to leach out. 22 mm diameter coverslips were then removed to reveal

the hydroxyacrylamide gels bound to 19 mm coverslips. Some of the gels were examined at

this point under AFM to ensure their stiffness matched the expected values. The rest of the

gels were sterilised under UV light for 1 hour, and functionalised with PDL (Poly-D-lysine;

100 μg/ml in PBS; P6407, Sigma) at room temperature overnight. Prior to cell plating, gels

were placed in culture medium for 30 min to allow medium to fill them, and prevent cell

culture medium from being diluted when cells were added.

Polyacrylamide substrates were prepared in the range of 0.1 kPa to 50 kPa. This covered

the range of tissue stiffnesses typically found in the body (with 50 kPa being stiffer than most

soft tissues and organs[25]). This was also the range of stiffnesses we could reliably achieve

using the same polymer : cross-linker ratio (Supplementary Table 1).

In vitro **assay.** *Nerve fibroblasts.* Cultures were prepared from postnatal day 1 to 5 Sprague

Dawley rat (Charles River UK) sciatic nerves. Using a variation of the procedure previously

described[53]. All animal procedures carried out were in compliance with the United Kingdom

Animals (Scientific Procedure) Act of 1986 and institutional guidelines.

Sciatic nerves of 10 - 20 animals were dissected out using sterilised microscissors and fine

forceps, and were kept in chilled HBSS (14170-112, Invitrogen) to stabilise the pH and

osmotic environment. To dissociate the tissue, nerves were transferred to a 2 ml

collagenase solution (2 mg/ml; C9407, Sigma) and incubated for 30 min at 37 ºC, after which

2 ml of trypsin (1 mg/ml; T0303, Sigma) was added (20 min, 37 ºC incubation). Finally, 2 ml

of deoxyribonuclease (0.1 mg/ml; D5025, Sigma) was added and, after a brief incubation

period (2 min), the cells were centrifuged (4 min, 1000 rpm). The supernatant was removed,

and the cell pellet was re-suspended in 2 ml of triturating solution (containing 10 mg/ml

bovine serum albumin [A7906, Sigma], 0.5 mg/ml trypsin inhibitor [10109886001, Roche],

0.02 mg/ml deoxyribonuclease).

To isolate the population of nerve fibroblasts from the dissociated nerves, the cells were

centrifuged and re-suspended in 0.5 ml of DPBS/BSA (Dulbecco's phosphate-buffered

saline [14190-094, Invitrogen] supplemented with 5 mg/ml bovine serum albumin) and 50 μl

of 50nm-magnetic-bead antibodies against rat/mouse CD90.1 (Thy1.1) (Miltenyi Biotec, 120-

094-523) and incubated for 15 min at RT. While nerve fibroblasts are less well studied than

other cell types, they are known to express CD90.1, while other common nerve cell types do

not[54]. This made CD90.1 a good choice for selectively isolating this cell population. Cells

were centrifuged, re-suspended in 2 ml of chilled DPBS/BSA, and run through a column

equipped with a magnetic separator (MiniMACS Separator; Miltenyi Biotec, 130-042-102).

Once the buffer had finished running through the column, and the flow-through collected, the

column was removed from the magnetic separator, and the magnetically-labelled cells were

flushed out with chilled DPBS/BSA. Finally, the positive fraction (nerve fibroblasts) were

centrifuged and the cell pellet re-suspended in DMEM (11320-033, Invitrogen) supplemented

with a further 4 mM of glutamine (25030032, Invitrogen), 100 mg/ml foetal calf serum (FCS,

Invitrogen) and an antibiotic-antimycotic agent (15240-062, Invitrogen). The cells were

plated on polyacrylamide substrates at a density of 10,000 cells/cm^2. While these 50nm

beads remain adhered to the cells of the positive fraction, they are not known to lead to lead

to changes in cell behaviour.

Bone marrow-derived macrophages. Macrophages were derived from adult rat bone marrow

hematopoietic stem cells as previously described[55]. Adult Sprague Dawley rats (Charles

River UK) were sacrificed by exposure to a rising concentration of CO_2. The femurs were

dissected out and broken open using sterile scissors. Bone marrow contained within the

femurs was washed out with chilled DPBS (14190-094, Invitrogen) and collected. The cell

suspension was centrifuged for 10 min at 1000 rpm. The supernatant was discarded and the

cells were re-suspended in BMDM (the same supplemented DMEM used for nerve

fibroblasts, further supplemented with macrophage colony stimulating factor [400-28,

Peprotech; 50 ng/ml]). Cells were counted in a hemocytometer and seeded on 100 x 15 mm

uncoated petri dishes (Sigma, P5731) at a density of 5,000 cells/cm^2. The dishes were

supplemented with further medium after 3 days of culture at 37 ºC.

Hematopoietic stem cells differentiate into macrophages in the presence of macrophage

colony stimulating factor present in BMDM. After 6 days to allow differentiation of

Hematopoietic stem cells differentiate into macrophages, the medium in the dishes was

removed to dispose of any cells which had not attached to the substrate. The remaining cells

were washed with warm DPBS followed by CellStripper solution (Corning, 25-056-CI). Cells

were incubated in CellStripper for 5 min at 37 ºC to detach them from the substrate. The cell

suspension was collected and an equal volume of BMDM was added to inactivate the

CellStripper solution. Cells were then centrifuged at 1000 rpm for 10 min and the

supernatant was removed. Upon re-suspension in BMDM and counting, cells were plated

onto polyacrylamide substrates at a density of 10,000 cells/cm^2.

Immunocytochemistry.

Cell stains were carried out 6 days after plating on polyacrylamide substrates. At this point in

time, warm paraformaldehyde solution (40 mg/ml in PBS) was added to the cells for 15 min

at room temperature. The fixative solution was washed off with PBS (3 washes, 10 min per

wash). To improve antibody specificity cells were incubated for 30 min at room temperature

in a blocking solution consisting of 0.03% v/v Triton X-100 (Sigma, T8787) and 3% v/v

bovine serum albumin (Sigma, A9418) in PBS. Primary antibodies (in blocking solution) were

then added to cells and incubated overnight at 4 °C. Further details regarding antibody

concentrations can be found in Supplementary Table 2.

Excess primary antibodies were washed off using PBS (3 washes, 10 min). Secondary

antibodies in blocking solution were incubated on the cells for 2 hr at room temperature.

Following two washes with PBS and a wash with non-saline Tris-buffered solution, Fluorsave

mounting agent (Millipore, 345789) was added to sections to preserve fluorescence before

gels were placed onto glass slides and stored at 4 °C prior to imaging.

Imaging of stained cells on polyacrylamide substrates was carried out using a confocal

microscope (Leica TCS SP5). For every condition 3 images were taken at random sites

within each gel with a 20X objective. The nuclear stain was used as a guide to ensure cells

were present in the field of view when pictures were taken. Gain and exposure settings for

each channel used were maintained constant between imaging sessions and across

different stains.

Cell counts were performed by hand in the Image-J software package (v1.48, National

Institutes of Health, USA). Contrast of images was modified prior to analysis. For

morphological stains, one image of high stiffness (50 kPa) and one of low stiffness (0.1 kPa)

were opened and their contrast modified to an equal degree until a satisfactory pattern of

stain was achieved in both. This contrast modification was then applied to all images of the

same batch of stained gels. For cell-type specific stains such as alpha-smooth muscle actin

this same contrast modification was carried out using negative and positive control stains.

Cells were counted, or the area stained was designated, by hand. Statistical analysis and

data plotting was carried out using MATLAB (Mathworks, R2016b). Box plots used to display

data consist of a box containing the 25^{th} to 75^{th} percentile range of data (the interquartile

range), an inner box mark indicating the median value, and whiskers containing most of the

remaining data points. Outliers, defined as data points further away from the 25^{th} or 75^{th}

percentile than 1.5 times the interquartile range, are presented as circles. Box plots with

overlaid scatter plots do not depict these outliers, as these can be observed in the scatter

plot.

RNA sequencing.

RNA sequencing was performed in parallel on n = 4 biological replicates. RNA extraction

was carried out at day 3 of culture on polyacrylamide substrates using an RNeasy Plus

Micro Kit (Qiagen, 74034). This time point (different to the 6 day time point used in

immunocytochemistry experiments) was chosen as it was the point at which cells were

beginning to show major morphological differences across conditions, while minimising the

contribution of potential changes in gene expression due to other effects - such as increased

proliferation rates and subsequent increases in cell density seen on stiff substrates. Prior to

and at regular intervals during the extraction procedure, work surfaces and pipettes were

cleaned with RNase Zap decontamination solution (ThermoFisher, AM9780) to inactivate

RNases and prevent sample RNA degradation. To collect the cells, each coverslip was

briefly washed in PBS and lifted out of the solution using forceps. The gels onto which the

cells were attached were gently scraped off from the coverslips using a sterile steel blade

and placed in RLT lysis buffer plus (Qiagen). The samples in buffer were then moved to

QIAshredder tubes (Qiagen, 79654) and centrifuged in a microcentrifuge (MSE, mistral

1000) for 2 min at 8,000g. Instructions provided by the kit manufacturer were then followed

to extract cellular RNA, which was collected and stored at -80°C.

RNA quantification and integrity analysis were carried out on all samples prior to library

preparation. Using an RNA 6000 Pico Kit (Agilent, 5067-1513), samples concentration and

integrity was analysed using an Agilent 2100 Bioanalyzer. No samples with an RNA integrity

number <7 were used. Library preparation was thereafter carried out using an Ovation RNA-

Seq System V2 kit (NuGen, 7102-32), following manufacturer instructions. Samples were

finally submitted for sequencing in an Illumina HiSeq 2500 system.

Illumina read data files were run through a bioinformatics pipeline and aligned with the

Rattus norvegicus genome (Ensembl Rnor_6.0). Fold changes and p-values were calculated

for each gene between each experimental group and a control group (consisting of the

combined 0.1 kPa and 1 kPa conditions). Genes expressed were filtered to produce lists of

differentially expressed genes (DEGs). Defined by a minimum of 2-fold change in

expression, a base expression above 3 normalised counts, and an adjusted p-value below

0.05. RNAseq data have been deposited in the ArrayExpress database at EMBL-EBI

(https://www.ebi.ac.uk/arrayexpress/experiments/E-MTAB-7900) under accession number E-

MTAB-7900. Code to create the figures displaying RNAseq results is available in the

following GitHub repository: https://github.com/CTR-BFX/2019-Carnicer-Lombarte.

Implant fabrication.

Nerve conduits. Moulds of the conduit implants were designed in 3D-CAD software

(AutoCAD, Autodesk Inc) and 3D printed in PLA (polylactic acid) plastic using a MakerGear

M2 3D printer (MakerGear). The moulds were covered in Sylgard 184 PDMS (Dow Corning),

and were placed in an oven at 65°C overnight. The 3D printed mould was removed from the

cured PDMS, producing a negative pattern of the conduit implants. The surface of the PDMS

negative moulds was activated using oxygen plasma (Diener plasma etcher) for 25 seconds

at 30 W, and 0.8 mbar chamber pressure. PDMS moulds were then functionalised using

Trichloro(1H,1H,2H,2H-perfluorooctyl)silane (Sigma, 448931). A few drops of silane were

placed on a glass petri dish and into a desiccator together with the PDMS moulds. The

desiccator was pumped down into a vacuum, and functionalisation was allowed to take place

overnight. The resulting layer of silane prevented any new PDMS cured on these moulds

from binding to them, allowing for the casting of the PDMS conduits from these negative

moulds.

To cast the conduits, flat petri dishes with raised edges were prepared. These edges were

produced through layering multiple layers of insulation PVC tape, until a thickness of 0.6 mm

was achieved. The functionalised PDMS negative moulds were coated with a thick layer of

Sylgard 184 PDMS and placed on top of these dishes. The raised edges of the dishes

created a 0.6 mm thick layer of Sylgard 184 PDMS below the moulds, which would become

part of the conduits after curing. The moulds and dishes were placed in an oven at 65°C

overnight.

The freshly-cured layer of PDMS was carefully peeled from the moulds and trimmed to the

appropriate dimensions with a steel blade. The resulting PDMS implants were functionalised

with an additional layer of silicone/polyacrylamide before rolling into conduits. To roll into

conduits, the edges of the implants were brought together and carefully secured with

insulation PVC tape. The edges were covered with RTV PDMS (SA03073, Farnell), which

was allowed to cure overnight. An additional layer of RTV was then added and allowed to

cure before the conduits were stored in PBS and sterilised under UV prior to implantation.

The resulting conduit had a length of 7 mm, an internal diameter of 1.5 mm, and a wall

thickness of 0.6 mm. Supplementary Fig. 9 summarises the conduit fabrication protocol.

Subcutaneous implants. A 3 mm thick layer of Sylgard 184 PDMS was cast and cured

overnight at 65 ºC. This was then trimmed using a steel blade into 5 x 5 mm blocks. Each

block then was functionalised with a coating. Four blocks – one for each of the 4 stiffness-

controlled conditions – were combined into one 10 x 10 mm implant and stuck together using

RTV silicone. The sides of each of the four component blocks were notched to later be able

to identify them. Dexamethasone-doped implants remained as 5 x 5 mm blocks, and were

not combined with other implants. Implants were stored in PBS and sterilised under UV prior

to implantation.

Coatings. To produce dexamethasone-doped silicone implants (Dex), Sylgard 184 PDMS

was doped with 10 mg/ml of dexamethasone and spin-coated into 100 µm-thick films. The

dexamethasone-doped films were cut into appropriately-sized rectangles. A small amount of

RTV PDMS was spread over an implant and a dexamethasone-doped PDMS rectangle was

placed on top. After allowing the RTV to cure overnight, the dexamethasone-doped film was

further trimmed to match the shape of the underlying PDMS, and the PDMS conduitwas

rolled as described above.

Soft silicone coatings (PDMS_2kPa) were prepared from a mix of NuSil 8100 (Polymer

System Technology, GEL-8100) and Sylgard 184 (99% to 1% w/w, respectively). An implant

was thoroughly cleaned with ethanol and ddH$_2$O (15230089, Fisher Scientific) and dried with

nitrogen gas, followed by the application of a 9 µl drop of the soft silicone mix to its surface.

This drop was spread out to ensure that the entire inner surface of the implant was

completely covered. The implant was then transferred to an oven and baked at 65 °C for one

week. This long curing time was a necessary step to remove traces of non-cured PDMS.

Polyacrylamide coatings (PAA_0.2kPa and PAA_20kPa) were grafted onto Sylgard 184

PDMS implants following a published protocol[56].Glass coverslips were cleaned by alternate

dipping in ddH$_2$O and EtOH. PDMS implants were thoroughly cleaned with methanol, dried

with nitrogen gas, and covered with a benzophenone solution 10% w/w in EtOH (Sigma,

B9300) for 2 min at room temperature. Benzophenone was removed and

conduits/subcutaneous implants cleaned with methanol and dried with nitrogen gas.

Polyacrylamide hydrogel mixes were prepared by combining acrylamide and bisacrylamide

solutions at a 2:1 ratio. The mixes were combined with PBS to achieve the desired stiffness,

as described in Supplementary Table 1. To initiate the polymerisation of the gel mix, 5 µl of

APS solution (0.1 g/ml in ddH$_2$O) and 1.5 µl of TEMED were added to 500 µl of gel mixes. A

9 µl drop of the gel mix was then transferred to a PDMS implant, which had been previously

soaked in 10% (w/w) benzophenone solution in ethanol. The drops were spread out by

covering with a clean glass coverslip. Implants were then quickly transferred under a 12

J/cm^2 UV lamp for 10 min (SUSS MicroTec MJB4). After the 10 min of UV exposure, glass

coverslips were removed and polyacrylamide-PDMS composites were placed in PBS for a

further 30 min. The polyacrylamide coating was kept hydrated with PBS at all times until

implantation.

Stiff silicone implants (PDMS_200kPa) were not coated with anything, leaving the surface of

the Sylgard 184 implant exposed to the tissue. While the absence of a coating resulted in

slightly larger diameter conduits for this group, this was unlikely to have an impact on the

nerve tissue. Conduits were implanted into a nerve gap injury which was later filled with

nerve tissue as part of normal tissue regeneration (and not wrapped around a pre-existing

nerve).

In vivo **implantation.**

All experimental procedures were performed in accordance with the UK Animals (Scientific

Procedures) Act 1986. Surgical procedures were carried out under aseptic conditions. ~250

g Lewis rats (Charles River UK) were housed in groups of 5 and provided *ad libitum* access

to food and water for a minimum of 7 days prior to surgical procedures. Immediately prior to

all surgical procedures, animals received an injectable dose of the non-steroidal anti-

inflammatory drug meloxicam (1.5 mg/ml, subcutaneous). Anaesthesia was induced and

maintained with isoflurane delivered via a facemask. Body temperature was monitored via a

rectal probe and maintained at 37 °C using a thermal blanket.

Nerve conduits. Biceps femoris and vastus lateralis muscles of the right leg of the animals

were approached dorsally and separated to expose the septum through which the sciatic

nerve travels. The sciatic nerve trifurcation point was located and followed 2 mm proximal.

This site was used as a landmark to achieve consistent location of injury and implantation.

The nerve was cleanly transected at this location using scissors and the conduit was

positioned between the two resulting nerve stumps, leaving a 5 mm long empty gap within

the conduit between the stumps. The epineurium of each nerve stump was sutured to the

silicone tube using 9/0 nylon sutures (Ethicon). Each animal received only one conduit, with

a single type of coating.

Subcutaneous implants. An incision was done dorsally over the right leg of an animal

(approximately above the femur). The skin was separated from the underlying muscle fascia

using blunt forceps to create a tunnel from the site of incision towards the midline of the

animal. The implant was fed through this tunnel and placed ~1 cm away from the midline,

with the coating facing the muscle fascia. Each animal received one subcutaneous implant;

either a composite of all four stiffnesses or a dexamethasone-containing implant. This was

done to prevent any dexamethasone leached from the implant from interfering with the FBR

of all other conditions.

All animals were allowed to recover following implantation. A further dose of meloxicam was

given orally the day after surgery. 3 months post-implantation, animals were sacrificed by

exposure to a rising concentration of CO_2 or, if AFM measurements were to be carried out,

by anaesthetic overdose (see below)and the tissue collected.

Immunohistochemistry.

All tissue was fixed prior to processing and staining by immersion in paraformaldehyde

solution (40 mg/ml in PBS) overnight at 4 °C. Samples which required sectioning were then

transferred to a sucrose solution (30% w/w in PBS; S0389, Sigma) for cryoprotection. They

were kept in this solution for a minimum of 16 hr at 4 °C, and otherwise stored until further

processing. Cryopreserved samples were embedded in optimal cutting temperature

compound (Tissue-Tek, 4583), which was frozen and mounted on a cryostat (CM3050 S,

Leica). 12 μm - thick sections were cut from the samples at a cutting temperature of -20 °C.

Sections were placed on glass slides and allowed to dry at room temperature overnight

before storage at -20 °C until stained.

Sections ready to be stained were washed in a Triton X-100 0.1% v/v solution in PBS to

allow for permeabilisation. These and all further washes were performed three times for 10

min. To minimise non-specific antibody binding, sections were incubated in a blocking buffer,

consisting of tris-buffered saline containing 0.03% v/v Triton X-100 and 10% v/v donkey

serum (Millipore, s30-100ml). After blocking for 1 hr at room temperature, primary antibodies

(in 10% blocking buffer v/v in PBS) were added to sections (further details in Supplementary

Table 2). Sections were covered with paraffin film to prevent drying and were incubated in

primary antibodies overnight at 4 °C.

Sections were washed in PBS-Triton solution to remove excess primary antibodies, and then

incubated in secondary antibodies in the same solution as primaries for 2 hr at room

temperature. Secondary antibodies were finally washed off with two PBS washes followed

by a non-saline Tris-buffered solution (T6066, Sigma). Fluorsave mounting agent (Millipore,

345789) was added to sections to preserve fluorescence before encasing with a glass

coverslip and storing at 4 °C prior to imaging.

Imaging of stained nerve tissue was carried out using a confocal microscope (Leica TCS

SP5). Image files were exported and processed for analysis in Image-J software package

(v1.48, National Institutes of Health, USA). Stain intensity profiles of FBR capsules was

carried out through a combination of custom Matlab and Fiji scripts. The edge of the nerve

capsule was delineated by the user and aligned by the scripts. An intensity profile (intensity

vs. depth into the nerve) of the each stain was obtained. The average intensity from the

edge of the nerve to a depth of 25 µm was calculated and provided as a ratio to the same

intensity of the PDMS_200kPa group. The only exception were CD68 stains, were a depth of

50 µm was instead chosen as macrophages were found to mostly locate deeper into the

tissue than other markers. Capsule thickness was analysed using a Matlab script, after its

edge was marked by hand based on the αSMA stain. Principal component analysis of FBR

was done over the combination of αSMA, collagen I, CD68 stains and capsule thickness.

For this analysis capsule thickness in dexamethasone group was set as 0. All values were

normalised and missing values substituted for the mean of the group (10 of 100 values in

subcutaneous samples, 3 of 82 values in nerves). Axon density was analysed in an

automated fashion using a Fiji script over 3 randomly chosen 100 x 100 µm boxes for every

image. This was done 5 mm distal to the point of conduit implantation to minimise any

effects from the conduits on regeneration, as this could result in a non-uniform axon

distribution. Statistical analysis and data plotting was carried out using MATLAB (Mathworks,

R2016b).

BCA protein adsorption assay

Adsorption of proteins to the surface of materials used in *in vivo* experiments was

determined using a BCA assay. Blocks of polyacrylamide hydrogel or silicone rubber were

prepared with dimensions 5 x 5 x 2 mm. Blocks were soaked in 10 mg/ml foetal calf serum

(FCS, Invitrogen) for 2 hours at 37 ºC. The blocks were then removed and placed in 50 mM

ammonium bicarbonate solution for a further two hours at room temperature to extract

adsorbed proteins. A bicinchoninic acid (BCA) assay (ThermoFisher, 23225) was used to

quantify protein content following manufacturer specifications. Absorbance of the assay was

measured using a FLUOstar Omega microplate reader (BMG Labtech) at 570 nm, and

compared to that of a protein standard.

Atomic force microscopy.

Sample elasticity was determined via atomic force microscopy (AFM) as previously

described[57]. Indentation measurements using a cantilever probe were taken on samples

placed on an inverted optical microscope (Axio Observer.A1, Carl Zeiss Ltd.) using a JPK

Nanowizard Cellhesion 200 AFM (JPK Instruments AG). Tipless silicon cantilevers (Arrow-

TL1; NanoSensors) with a spring constant of ~0.02 N/m were used in experiments were

tissue stiffness was measured. Material characterisation made use of either these or stiffer

cantilevers (SICON-TL-20, spring constant ~0.29 N/m, AppNano; TL-FM-10, spring constant

~2.8 N/m, Nanosensors; spring constant value was measured for each individual cantilever

via the thermal noise method[58]). Each cantilever had a polystyrene bead (~37 μm diameter

for tissue, ~20μm for stiffer materials; Microparticles GmbH) glued (ultraviolet curing, Loctite)

prior to all measurements. Choice of cantilever spring constant and bead diameter was

taken to ensure high measurement sensitivity for a given indentation depth given the

mechanical properties of the sample.

Tissue preparation. Lewis rats (Charles River UK) were sacrificed by overdose of euthatal

(pentobarbitone) administered intraperitoneally, followed by neck dislocation. Euthatal was

combined at a 1:1 v/v ratio with lidocaine anaelgesic and delivered at a total dose of 3 ml/kg

of bodyweight. Further processing of tissue was carried out within 1 - 2 hr of animal sacrifice,

and all AFM measurements were completed within 5 hr to minimise tissue degradation. This

sacrificial method was chosen instead of rising CO_2 concentration, as changes in tissue

stiffness as a consequence of changes in tissue pH can occur with the latter[59].

To dissect out the sciatic nerve, the dorsal side of the hindlegs was exposed and skin

removed. Biceps femoris and vastus lateralis muscles were separated to expose the septum

through which the sciatic nerve travels. The nerve was dissected out and transected just

below the trifurcation point, and 1 cm above it. The nerve was then transferred to a dish

containing mammalian physiological saline previously described by others[60] (121 mM NaCl,

5 mM KCl, 1 mM $MgCl_2$, 1 mM $CaCl_2$, 0.4 mM NaH_2PO_4, 23.8 mM $NaHCO_3$, 5.6 mM

glucose). Mammalian physiological saline was prepared freshly prior to the experiment. To

establish a pH of 7.3, a gas mixture of 95% CO_2 and 5% O_2 was bubbled through the

solution.

For naïve nerve measurements, under a dissection microscope, blood vessels and excess

tissue surrounding the nerve were removed, and the nerve stumps were trimmed off with a

steel blade. The remaining nerve was then cut into several fragments for mounting and

sectioning. Nerve fragments were embedded in warm 4% w/w low melting point agarose

(A9539, Sigma) in PBS. Agarose was allowed to cool and harden for a few minutes before

trimming into blocks containing the nerve fragments. Blocks were stuck to a steel stage with

cyanoacrylate glue (Super Glue, Loctite) and transferred to a chamber filled with chilled

mammalian physiological saline. The blocks were cut into 500 µm thick sections in a

vibrating microtome. Nerve sections were transferred to mammalian physiological saline

solution containing the live stain fluoromyelin (1:250 v/v in mammalian physiological saline;

Invitrogen, F34651) and incubated for 1 hr at room temperature to stain the myelin

surrounding axons. This allowed the endoneurial compartment to be identified and later

probed via AFM. Sections were mounted onto 35 mm plastic dishes (Z707651, Sigma). The

sections were gently deposited onto two strips of cyanoacrylate glue which adhered to the

agarose on which the tissue was embedded. Dishes were filled with room temperature

mammalian phosphate buffer and transferred to the inverted microscope to perform the

measurements.

For nerve FBR capsules and epineurium measurements, implanted conduits were extracted

from rats 3 months post-implantation with regenerated sciatic nerves still within them. Under

a dissection microscope, fibrotic tissue covering the outside of conduits was removed. A cut

was done along the length of the conduit, and the regenerated nerve fragment within was

carefully removed. The nerve fragment was embedded on its side on a shallow bed of 4%

w/w low melting point agarose (Sigma), and submerged in mammalian physiological saline.

Finally, AFM measurements of the side of the nerve were carried out.

Material preparation. The stiffness of polyacrylamide hydrogel and silicone rubber implants

and substrates was checked for every manufactured batch by AFM. Implants and substrates

were all cleaned by immersion in PBS overnight. These were then transferred to 35 mm

plastic dishes and fixed in place using a small amount of vaseline petroleum jelly

(28908.290, VWR). Dishes were transferred to the inverted microscope to perform AFM

measurements.

Indentation experiments. Petri dishes containing the samples to be analysed were placed on

a motorised xy stage, which allowed movement of the sample relative to the AFM cantilever.

A CCD camera (The Imaging Source GmbH) was used to image and track the position of the

cantilever above the sample. This setup was used to locate and define an area of interest on

the sample on which AFM measurements were taken. A custom python script broke down

this area into 20 x 20 μm squares, inside which a single measurement was taken. The

motorised stage was moved as measurements were taken to perform a raster scan of the

area of interest.

For each elasticity measurement, the cantilever probe was lowered onto the surface of the

sample at a speed of 10 μm/s. Upon contact and indentation of the sample, the probe

continued to be lowered until a force of 10 nN was reached (usually equivalent to an

indentation depth δ of 1 to 5 μm). The probe was then retracted, the sample moved, and a

measurement repeated at a different location.

The force-distance measurements taken by the AFM were translated into elasticity values

using the Hertz model[61] using a previously described custom[62] MATLAB (Mathworks,

R2008a) script for every indentation of the sample. The cantilever and polystyrene bead

probe on the sample was modelled as a sphere and a half space, and used to calculate the

apparent reduced elastic modulus *K*.

$$F = \frac{4}{3} K R^{\frac{1}{2}} \delta^{\frac{3}{2}}$$

697   With *F* being the force applied and R the radius of the polystyrene bead. Elasticity was

698   calculated at an indentation depth δ of 2 μm. The reduced elastic modulus may be further

699   transformed into other elastic moduli, including Young's modulus (*E*)[62] and Shear modulus

700   (*G*). A Poisson ratio ν of polyacrylamide was set to 0.48[63], while for PDMS a value of 0.499

701   was used[64].

$$K = \frac{E}{1 - v^2}$$

$$G = \frac{E}{2(1 + v)}$$

References

1. Salatino, J. W., Ludwig, K. A., Kozai, T. D. Y. & Purcell, E. K. Glial responses to implanted electrodes

in the brain. *Nat. Biomed. Eng.* **1**, 862–877 (2017).

2. Spearman, B. S. *et al.* Tissue-Engineered Peripheral Nerve Interfaces. *Adv. Funct. Mater.* **28**,

1701713 (2018).

3. Kenneth Ward, W. A Review of the Foreign-body Response to Subcutaneously-implanted Devices:

The Role of Macrophages and Cytokines in Biofouling and Fibrosis. *J. Diabetes Sci. Technol. Online*

2, 768–777 (2008).

4. Veiseh, O., Tang, B. C., Whitehead, K. A., Anderson, D. G. & Langer, R. Managing diabetes with

nanomedicine: challenges and opportunities. *Nat. Rev. Drug Discov.* **14**, 45–57 (2015).

5. Anderson, J. M., Rodriguez, A. & Chang, D. T. Foreign body reaction to biomaterials. *Semin.*

Immunol. **20**, 86–100 (2008).

6. Bryers, J. D., Giachelli, C. M. & Ratner, B. D. Engineering biomaterials to integrate and heal: The

biocompatibility paradigm shifts. *Biotechnol. Bioeng.* **109**, 1898–1911 (2012).

7. Brindley, G. S., Polkey, C. E. & Rushton, D. N. Sacral anterior root stimulators for bladder control

in paraplegia. *Paraplegia* **20**, 365–381 (1982).

8. Anderson, W. S. & Lenz, F. A. Surgery Insight: deep brain stimulation for movement disorders.

Nat. Rev. Neurol. **2**, 310–320 (2006).

9. Proctor, C. M. *et al.* Electrophoretic drug delivery for seizure control. *Sci. Adv.* **4**, (2018).

10.   Feiner, R. *et al.* Engineered hybrid cardiac patches with multifunctional electronics for online

monitoring and regulation of tissue function. *Nat. Mater.* **15**, 679–685 (2016).

11.   Khodagholy, D. *et al.* NeuroGrid: recording action potentials from the surface of the brain.

Nat. Neurosci. **18**, 310–315 (2015).

12.   Yang, X. *et al.* Bioinspired neuron-like electronics. *Nat. Mater.* 1 (2019) doi:10.1038/s41563-

019-0292-9.

13.   Doloff, J. C. *et al.* Colony stimulating factor-1 receptor is a central component of the foreign

body response to biomaterial implants in rodents and non-human primates. *Nat. Mater.* **16**, 671–

680 (2017).

14.   Xie, X. *et al.* Reduction of measurement noise in a continuous glucose monitor by coating the

sensor with a zwitterionic polymer. *Nat. Biomed. Eng.* **2**, 894–906 (2018).

15.   FitzGerald, J. J. Suppression of scarring in peripheral nerve implants by drug elution. *J. Neural*

Eng. **13**, 026006 (2016).

16.   Nguyen, J. K. *et al.* Mechanically-compliant intracortical implants reduce the

neuroinflammatory response. *J. Neural Eng.* **11**, 056014 (2014).

17.   Moshayedi, P. *et al.* The relationship between glial cell mechanosensitivity and foreign body

reactions in the central nervous system. *Biomaterials* **35**, 3919–3925 (2014).

18.   Jansen, L. E. *et al.* Zwitterionic PEG-PC hydrogels modulate the foreign body response in a

modulus-dependent manner. *Biomacromolecules* **19**, 2880–2888 (2018).

19.   Noskovicova, N. *et al.* Suppression of the fibrotic encapsulation of silicone implants by

inhibiting the mechanical activation of pro-fibrotic TGF-β. *Nat. Biomed. Eng.* 1–20 (2021)

doi:10.1038/s41551-021-00722-z.

20.   Lecomte, A., Descamps, E. & Bergaud, C. A review on mechanical considerations for

chronically-implanted neural probes. *J. Neural Eng.* **15**, 031001 (2018).

21.   Minev, I. R. *et al.* Electronic dura mater for long-term multimodal neural interfaces. *Science*

347, 159–163 (2015).

22.   Lacour, S. P., Courtine, G. & Guck, J. Materials and technologies for soft implantable

neuroprostheses. *Nat. Rev. Mater.* **1**, 16063 (2016).

23.   Capogrosso, M. *et al.* Advantages of soft subdural implants for the delivery of

electrochemical neuromodulation therapies to the spinal cord. *J. Neural Eng.* **15**, 026024 (2018).

24.   Carnicer-Lombarte, A., Barone, D. G., Fawcett, J. & Franze, K. Regenerative capacity of neural

tissue scales with changes in tissue mechanics post injury. 2022.12.12.517822 Preprint at

https://doi.org/10.1101/2022.12.12.517822 (2022).

25.   Cox, T. R. & Erler, J. T. Remodeling and homeostasis of the extracellular matrix: implications

for fibrotic diseases and cancer. *Dis. Model. Mech.* **4**, 165–178 (2011).

26.   Damanik, F. F. R., Rothuizen, T. C., van Blitterswijk, C., Rotmans, J. I. & Moroni, L. Towards an

in vitro model mimicking the foreign body response: tailoring the surface properties of

biomaterials to modulate extracellular matrix. *Sci. Rep.* **4**, 6325 (2014).

27.   Hinz, B. *et al.* The Myofibroblast. *Am. J. Pathol.* **170**, 1807–1816 (2007).

28.   Santoro, R. *et al.* Activation of human aortic valve interstitial cells by local stiffness involves

YAP-dependent transcriptional signaling. *Biomaterials* **181**, 268–279 (2018).

29.   Brown, B. N., Ratner, B. D., Goodman, S. B., Amar, S. & Badylak, S. F. Macrophage

polarization: An opportunity for improved outcomes in biomaterials and regenerative medicine.

Biomaterials **33**, 3792–3802 (2012).

30.   Hesketh, M., Sahin, K. B., West, Z. E. & Murray, R. Z. Macrophage Phenotypes Regulate Scar

Formation and Chronic Wound Healing. *Int. J. Mol. Sci.* **18**, (2017).

31.   Engler, A. J., Sen, S., Sweeney, H. L. & Discher, D. E. Matrix Elasticity Directs Stem Cell

Lineage Specification. *Cell* **126**, 677–689 (2006).

32.   Kuo, C.-H. R., Xian, J., Brenton, J. D., Franze, K. & Sivaniah, E. Complex Stiffness Gradient

Substrates for Studying Mechanotactic Cell Migration. *Adv. Mater.* **24**, 6059–6064 (2012).

33.   Choi, Y. S. *et al.* The alignment and fusion assembly of adipose-derived stem cells on

mechanically patterned matrices. *Biomaterials* **33**, 6943–6951 (2012).

34.   Mond, H. G., Helland, J. R., Stokes, K., Bornzin, G. A. & McVENES, R. The Electrode-Tissue

Interface: The Revolutionary Role of Steroid-Elution. *Pacing Clin. Electrophysiol.* **37**, 1232–1249

(2014).

35.   Bardy, G. H. *et al.* An Entirely Subcutaneous Implantable Cardioverter–Defibrillator. *N. Engl.*

J. Med. **363**, 36–44 (2010).

36.   Engler, A. J. *et al.* Myotubes differentiate optimally on substrates with tissue-like stiffness:

pathological implications for soft or stiff microenvironments. *J. Cell Biol.* **166**, 877–887 (2004).

37.   Georges, P. C. & Janmey, P. A. Cell type-specific response to growth on soft materials. *J.*

Appl. Physiol. **98**, 1547–1553 (2005).

38.   Swift, J. *et al.* Nuclear Lamin-A Scales with Tissue Stiffness and Enhances Matrix-Directed

Differentiation. *Science* **341**, 1240104 (2013).

39.   Swartzlander, M. D. *et al.* Linking the foreign body response and protein adsorption to PEG-

based hydrogels using proteomics. *Biomaterials* **41**, 26–36 (2015).

40.   Dupont, S. *et al.* Role of YAP/TAZ in mechanotransduction. *Nature* **474**, 179–183 (2011).

41.   Elosegui-Artola, A. *et al.* Force Triggers YAP Nuclear Entry by Regulating Transport across

Nuclear Pores. *Cell* **171**, 1397-1410.e14 (2017).

42.   Calvo, F. *et al.* Mechanotransduction and YAP-dependent matrix remodelling is required for

the generation and maintenance of cancer-associated fibroblasts. *Nat. Cell Biol.* **15**, 637–646

(2013).

43.   Pocaterra, A. *et al.* F-actin dynamics regulates mammalian organ growth and cell fate

maintenance. *J. Hepatol.* (2019) doi:10.1016/j.jhep.2019.02.022.

44.   Discher, D. E., Janmey, P. & Wang, Y. Tissue Cells Feel and Respond to the Stiffness of Their

Substrate. *Science* **310**, 1139–1143 (2005).

45.   Trepat, X. *et al.* Universal physical responses to stretch in the living cell. *Nature* **447**, 592–

595 (2007).

46.   Wirtz, D., Konstantopoulos, K. & Searson, P. C. The physics of cancer: the role of physical

interactions and mechanical forces in metastasis. *Nat. Rev. Cancer* **11**, 512–522 (2011).

47.   Discher, D. *et al.* Biomechanics: Cell Research and Applications for the Next Decade. *Ann.*

Biomed. Eng. **37**, 847 (2009).

48.   Iskratsch, T., Wolfenson, H. & Sheetz, M. P. Appreciating force and shape — the rise of

mechanotransduction in cell biology. *Nat. Rev. Mol. Cell Biol.* **15**, 825–833 (2014).

49.   Lee, H., Bellamkonda, R. V., Sun, W. & Levenston, M. E. Biomechanical analysis of silicon

microelectrode-induced strain in the brain. *J. Neural Eng.* **2**, 81–89 (2005).

50.   Takeuchi, S., Ziegler, D., Yoshida, Y., Mabuchi, K. & Suzuki, T. Parylene flexible neural probes

integrated with microfluidic channels. *Lab. Chip* **5**, 519–523 (2005).

51.   Subbaroyan, J., Martin, D. C. & Kipke, D. R. A finite-element model of the mechanical effects

of implantable microelectrodes in the cerebral cortex. *J. Neural Eng.* **2**, 103–113 (2005).

52.   Moshayedi, P. *et al.* Mechanosensitivity of astrocytes on optimized polyacrylamide gels

analyzed by quantitative morphometry. *J. Phys. Condens. Matter* **22**, 194114 (2010).

53.   Brockes, J. P., Fields, K. L. & Raff, M. C. Studies on cultured rat Schwann cells. I.

Establishment of purified populations from cultures of peripheral nerve. *Brain Res.* **165**, 105–118

(1979).

54.   Richard, L., Védrenne, N., Vallat, J.-M. & Funalot, B. Characterization of Endoneurial

Fibroblast-like Cells from Human and Rat Peripheral Nerves. *J. Histochem. Cytochem.* **62**, 424–435

(2014).

55.   Lynn, A. D. & Bryant, S. J. Phenotypic Changes in Bone Marrow Derived Murine Macrophages

cultured on PEG-based Hydrogels and Activated by Lipopolysaccharide. *Acta Biomater.* **7**, 123–

132 (2011).

56.   Yuk, H., Zhang, T., Parada, G. A., Liu, X. & Zhao, X. Skin-inspired hydrogel–elastomer hybrids

with robust interfaces and functional microstructures. *Nat. Commun.* **7**, 12028 (2016).

57.   Koser, D. E., Moeendarbary, E., Hanne, J., Kuerten, S. & Franze, K. CNS Cell Distribution and

Axon Orientation Determine Local Spinal Cord Mechanical Properties. *Biophys. J.* **108**, 2137–2147

(2015).

58.   Hutter, J. & Bechhoefer, J. Calibration of Atomic-Force Microscope Tips. *Rev. Sci. Instrum.* **64**,

1868–1873 (1993).

59.   Holtzmann, K. *et al.* Brain tissue stiffness is a sensitive marker for acidosis. *J. Neurosci.*

Methods **271**, 50–54 (2016).

60.   Brown, R. *et al.* Activity-dependent degeneration of axotomized neuromuscular synapses in

WldS mice. *Neuroscience* **290**, 300–320 (2015).

61.   Hertz, H. Ueber die Berührung fester elastischer Körper. *J. Für Reine Angew. Math.* **92**, 156–

171 (1882).

62.   Gautier, H. O. B. *et al.* Chapter 12 - Atomic force microscopy-based force measurements on

animal cells and tissues. in *Methods in Cell Biology* (ed. Paluch, E. K.) vol. 125 211–235 (Academic

Press, 2015).

63.   Boudou, T., Ohayon, J., Picart, C. & Tracqui, P. An extended relationship for the

characterization of Young's modulus and Poisson's ratio of tunable polyacrylamide gels.

Biorheology **43**, 721–728 (2006).

64.   Johnston, I. D., McCluskey, D. K., Tan, C. K. L. & Tracey, M. C. Mechanical characterization of

bulk Sylgard 184 for microfluidics and microengineering. *J. Micromechanics Microengineering* **24**,

035017 (2014).

65.   Turco, M. Y. *et al.* Trophoblast organoids as a model for maternal–fetal interactions during

human placentation. *Nature* **564**, 263–267 (2018).

Acknowledgements

The authors would like to thank Jessica Kwok for technical support and advice. Part of the

RNA-Seq work was performed with the Genomics and Transcriptomics Core, which is

funded by the UK Medical Research Council (MRC) Metabolic Disease Unit

(MRC_MC_UU_12012/5) and a Wellcome Trust Major Award (208363/Z/17/Z), and

guidance from Marcella Ma, whom the authors wish to thank. This work was furthermore

supported by the UK Medical Research Council (MRC) and the Sackler Foundation (doctoral

training grant RG70550 to ACL), the UK Wellcome Trust (Translational Medicine and

Therapeutics PhD Programme Fellowship 109511/Z/15/Z to DGB), the Centre for

Trophoblast Research (MP and RSH), the Whitaker International Scholars Program (ALR),

the European Commission's Horizon 2020 (Marie Sklodowska-Curie Fellowship 797506 to

ALR), the Bertarelli Foundation (SPL), the European Research Council (Consolidator Award

772426 to KF), the UK Biotechnology and Biological Sciences Research Council (Research

Grant BB/N006402/1 to KF), the UK Medical Research Council (Career Development Award

G1100312/1 to KF), and the Alexander von Humboldt Foundation (Alexander von Humboldt

Professorship to KF).

Fig 1 | Substrates with a stiffness above that of tissue trigger fibrosis *in vitro*. a,

Maximum intensity projections of *z*-stack confocal images of nerve fibroblasts at 6 DIV (days

in vitro) cultured on polyacrylamide substrates of various stiffness (50, 10, 1 and 0.1 kPa

shear modulus), stained for cytoskeleton (actin) and focal adhesion (vinculin) markers. Cell

morphologies significantly changed on non-physiologically stiff (shear modulus of 50 kPa)

substrates. Scale bar: 30 μm. **b,c**, Box plots of fibroblast cell area (**b**) and focal adhesion

area (**c**). *n* = number of cells. **d**, Images of fibroblasts stained for myofibroblast markers

αSMA (magenta) and collagen I (green) show an increase in fibrotic phenotype on 50 kPa

gels. Cell nuclei stained with DAPI (blue) Scale bar: 60 μm. **e**,**f**, Box plots of relative stain

intensities for collagen I (**e**) and αSMA (**f**). *n* = number of cells. Box plot characteristics

described in Methods. All statistical comparisons done via one-way ANOVA followed by

Dunnett's multiple comparisons test comparing to the 50 kPa condition. All experiments

performed 3 - 4 times.

Fig 2 | Substrates with a stiffness above that of native tissue trigger macrophage

activation and changes in inflammatory profile *in vitro*. a, Maximum intensity projections

of *z*-stack confocal images of bone marrow-derived macrophages at 6 DIV (days *in vitro*)

cultured on polyacrylamide substrates of various stiffness (50, 10, 1 and 0.1 kPa shear

modulus), stained for cytoskeleton (actin) and focal adhesion (vinculin) markers. Cell

morphologies significantly changed on non-physiologically stiff (50 kPa) substrates. Scale

bar: 30 μm. **b**,**c**, Boxplots of macrophage cell area (**b**) and focal adhesion area (**c**). *n* =

number of cells. All statistical comparisons done via one-way ANOVA followed by Dunnett's

multiple comparisons test comparing to the 50 kPa condition. Box plot characteristics

described in Methods. **d**, Heatmap of changes in inflammatory differentially expressed gene

(DEG) expression profile of macrophages at 3 DIV detected in RNAseq (expression values

represented as base-2 log fold change of counts, with respect to the average across all

groups, as previously used[65]). Changes in markers such as *arg1, pparg, il1b,* and *ptgs2*

indicate a switch to an M2-like scar production-driving phenotype of macrophages grown on

high stiffness substrates. Four samples analysed for each substrate stiffness condition**.**

Fig 3 | Coatings at least as soft as the host tissue significantly reduce foreign body reaction to subcutaneous implants 3 months post-implantation *in vivo.* **a**, Diagram of implant location and structure. Blue square represents area shown in images in **b**. **b**, *Z*-stack confocal images of subcutaneous tissue in response to implants of 200 kPa shear modulus silicone PDMS (PDMS_200kPa), or to implants coated with 20 kPa polyacrylamide hydrogel (PAA_20kPa), 2 kPa PDMS (PDMS_2kPa), 0.2 kPa polyacrylamide (PAA_0.2kPa), or PDMS impregnated with 10 mg/ml of the anti-inflammatory drug dexamethasone (Dex). Tissue is fluorescently labelled for myofibroblasts (αSMA, magenta), extracellular matrix components (collagen I, yellow), and macrophages (CD68, white). Approximate edges of implant are indicated by dashed white lines. All images show DAPI stains of nuclei (blue). Scale bar: 100 μm. **c**, Plot of stain intensities. **d**, Plot of fibrotic capsule thickness. Quantification of thickness in Dex group absent as dexamethasone impeded formation of a structured boundary between tissue and implant. For all plots: bars represent mean, dots represent individual animals. *N* = 5 rats. Statistical comparisons carried out via one-way ANOVA followed by Dunnett's multiple comparisons test comparing groups to the PDMS_200kPa control condition. **e**, Principal component analysis of quantified FBR components (αSMA, collagen I, CD68, and capsule thickness). Samples of the same implant stiffness are grouped within a colour-coded envelope. All implants at or below the stiffness of subcutaneous muscle tissue (PAA_20kPa, PDMS_2kPa, PAA_0.2kPa) grouped together away from the highest stiffness PDMS_200kPa. This clustering occurred in the direction of the Dex group, indicating that all three soft coatings considerably alleviate FBR.

Fig 4 | Coatings at least as soft as host tissue significantly reduce foreign body reaction to nerve conduits 3 months post-implantation *in vivo.* **a**, Schematic of implant location and structure. Implants had an internal diameter of 1.5 mm. Blue square represents area shown in images in **b**. **b**, *Z*-stack confocal images of sciatic nerve tissue regenerated through conduits of 200 kPa shear modulus silicone PDMS (PDMS_200kPa), or conduits coated with 20 kPa polyacrylamide hydrogel (PAA_20kPa), 2 kPa PDMS (PDMS_2kPa), 0.2kPa polyacrylamide (PAA_0.2kPa), or PDMS impregnated with 10 mg/ml dexamethasone (Dex). Approximate edges of implants are indicated by dotted white lines. Tissue is fluorescently labelled for axons (β3 tubulin, green), myofibroblasts (αSMA, magenta), extracellular matrix components (collagen I, yellow), and macrophages (CD68, white). All images are stained for nuclei (DAPI, blue). Images of non-operated naïve nerves are also included for comparison (epineurium). Softer coatings reduced cell activation and fibrotic capsule thickness while permitting nerve regeneration. Dex-treatment, however, abolished not only the fibrotic capsule but also nerve regeneration. Scale bar: 100 μm. **c**, Plot of relative stain intensities. **e**, Plot of axon density in nerves 5 mm downstream of implantation site. **d**, Plot of fibrotic capsule thickness. Quantification of thickness in Dex group absent as dexamethasone impeded formation of a structured boundary between tissue and implant. For all plots: bars represent mean, dots represent individual animals. N = 3 to 6 rats. **f**, Principal component analysis of quantified FBR components (αSMA, collagen I, CD68, and capsule thickness). Samples of the same stiffness condition are grouped within a colour-coded envelope. The implants of or below nerve tissue stiffness (PDMS_2kPa, PAA_0.2kPa) grouped together, away from the higher stiffnesses PAA_20kPa and PDMS_200kPa, and in the direction of the anti-inflammatory Dex group, indicating that the softest PDMS_2kPa and PAA_0.2kPa most efficiently alleviated FBR **g**, Diagram of *ex vivo* AFM setup for nerve tissue stiffness measurements. **h**, Box and scatter plot of tissue stiffness values for tissue in proximity to the implants with various coatings, showing a significant stiffening of tissue around implants with a stiff surface. Tissue stiffness was similar around PDMS_2kPa,

PAA_0.2kPa, and Dex-treated implants ($p > 0.05$). n = number of measurements.

Measurements taken on N = 3 to 6 rat nerves; measurements taken from the same animal

are depicted with the same colour. All statistical comparisons carried out via one-way

ANOVA followed by Dunnett's multiple comparisons test comparing groups to the

PDMS_200kPa control condition. Bonferroni-corrected Student's t-test used for comparisons

to Dex group. Box plot characteristics described in Methods.

Fig 5 | Reduction in foreign body reaction *in vivo* correlates with exclusion of the mechanosensitive transcriptional regulator YAP from nuclei in tissues surrounding soft-coated implants. **a-b**, Confocal images of subcutaneous (**a**) and nerve tissue (**b**) stained for the transcriptional regulator YAP and nuclei (DAPI). Tissue was exposed to implants of 200 kPa shear modulus silicone PDMS (PDMS_200kPa), or to implants coated with 20 kPa polyacrylamide hydrogel (PAA_20kPa), 2 kPa PDMS (PDMS_2kPa), or 0.2 kPa polyacrylamide (PAA_0.2kPa), for 3 months. YAP preferentially localised into nuclei of cells in contact with stiff but not with soft-coated implants, indicating a mechanosensitive process. Nuclei delineated by dashed white lines. Scale bars: 10 μm. **c,d**, Plots of relative nuclear YAP intensities. Bars represent mean, dots represent individual animals. $N = 5$ rats (**c**) and $N = 3$ to 5 rats (**d**). All statistical comparisons carried out via one-way ANOVA followed by Dunnett's multiple comparisons test comparing groups to the PDMS_200kPa condition.

973   **Supplementary Figure 1.** Plot of AFM-based stiffness measurements of polyacrylamide

974   substrates used in *in vitro* experiments (Fig. 1-2). N=5 gels per condition. Values per gel

975   represented by red circles; bars represent mean value. Stiffness values given in shear

976   modulus (G) and Young's modulus (E), based on a Poisson ratio of polyacrylamide gels of

977   0.48 [63].

Supplementary Figure 2. Fibroblast proliferation and fibronectin production as a function of substrate stiffness. a, Z-stack confocal images and quantification of nerve fibroblasts at 6 DIV cultured on polyacrylamide substrates of various stiffness (50, 10, 1 and 0.1 kPa shear modulus), stained for the proliferation marker Ki67, and the nuclear marker DAPI. Cells with overlapping DAPI and Ki67 stain (white arrowheads) are considered to be proliferating. Scale bar: 50 μm. N=4 cultures. Plot represents values for individual cultures

(red circles) and mean of all cultures (bar). **b,** Z-stack confocal images and quantification

(box plots) of nerve macrophages stained for the extracellular protein fibronectin, as well as

nuclei (DAPI). Scale bar: 60 μm. n=number of cells. Box plot characteristics described in

Methods. All statistical comparisons done via one-way ANOVA followed by Dunnett's

multiple comparisons test comparing to the 50 kPa condition. *, $p<0.05$; **, $p<0.01$, n.s, not

significant ($p>0.05$).

Supplementary Figure 3. Macrophage proliferation as a function of substrate stiffness. Immunostaining and quantification of proliferating macrophages, stained for the marker Ki67, as well as the nuclear marker DAPI. Cells with overlapping DAPI and Ki67 stain (white arrowheads) are considered proliferating. Scale bar: 50 μm. N=3 cultures. Plot represents values for individual cultures (red circles) and mean of all cultures (bar). All statistical comparisons done via one-way ANOVA followed by Dunnett's multiple comparisons test comparing to the 50 kPa condition. **, p<0.01; ***, p<0.001; n.s, not significant (p>0.05).

1001

1002 **Supplementary Figure 4. Stiffness measurements of materials used in *in vivo***

1003 **experiments.** Stiffness values given in terms of (**a**) shear modulus (*G*) and (**b**) Young's

1004 modulus (*E*), based on a Poisson ratio of 0.48 for polyacrylamide gels[63] and of 0.499 for

1005 silicone[64]. . n=number of measurements. Box plot characteristics described in Methods.

1006

Supplementary Figure 5. a,c, Fibronectin production *in vivo* is independent of implant

stiffness. Z-stack confocal images of the FBR capsule developed over 3 months in

response to coated implants in (**a**) subcutaneous tissue and (**b**) sciatic nerve, stained for

fibronectin (yellow) and nuclei (DAPI, blue). Scale bars: 100 μm. **c,d**, Quantification of

fibronectin stain intensity (values represented by red circles; mean represented by bar). All

statistical comparisons carried out via one-way ANOVA followed by Dunnett's multiple

comparisons test comparing groups to the PDMS_200kPa control condition. Epineurium

condition not included in statistical analysis. n.s, not significant (p>0.05).

1015

1016

1017

1018

1019

1020 Supplementary Figure 6. Masson's trichrome (MT) and H&E stained sections of FBR

1021 tissue developed around subcutaneous implants after 3 months of implantation.

Muscle and fascia visible at the bottom of images (red mass and blue collagen layer directly

above it in MT stain). Stains reveal differences in tissue structure and composition of FBR

capsules. Capsules around PDMS_200kPa are formed by a collagen-dense layer (black

arrowheads), which is absent in all other conditions. PDMS_200kPa also presents a thicker

layer of connective tissue separating the implant from muscle and fascia compared to all

other conditions, indicative of a more intense FBR. Scale bar: 150 μm.

1028

1029

1030

Supplementary Figure 7. Dexamethasone impedes nerve regeneration. Z-stack

confocal images of sciatic nerves exposed to implants of controlled stiffness (cross-

sections), 3 months post-implantation. Cross-sections were taken 5 mm downstream of the

point where the nerve was transected and the conduit was implanted. Axons stained in

green (β3 tubulin), nuclei in blue (DAPI). Axon stains show a large decrease in axon density

in nerves exposed to dexamethasone (Dex), while axon density is similar in all conditions

with materials of controlled stiffness. Quantification of axon density in implanted nerves was

carried out at this point of the nerve, downstream of the implantation site, and its

quantification is shown in Figure 4e. Scale bar: 100 μm.

1040

1041

Supplementary Figure 8. Protein adsorption assay. *In vitro* protein adsorption to

materials of controlled stiffness used in *in vivo* implantation, following two-hour incubation in

serum. N=5 samples of material per condition. Values per gel represented by red circles;

bars represent mean value. No difference was observed in protein adsorption between all

four materials. Statistical comparison done using one-way ANOVA ($p = 0.954$). n.s, not

significant.

1048

1049

Supplementary Figure 9. Nerve conduit fabrication protocol. Sheets of PDMS with

overhangs are produced on a chamber formed by a silanized PDMS mould, petri dish and

PVC tape. The resulting PDMS sheets were then coated on one of their surfaces with a

material of specific stiffness, or kept uncoated for the stiff PDMS condition. **a.** For PAA

hydrogel coatings, the PDMS surface was functionalised with benzophenone, and hydrogels

were crosslinked under UV light. Red colouring has been added to PAA hydrogels in the

image for easier visualisation. **b.** For soft silicone coatings, a drop of soft silicone mix was

spread over the surface of the PDMS sheet, and baked at 65 ºC for one week. Blue

colouring has been added to the soft silicone in the image for easier visualisation **c.** For

coatings containing dexamethasone, a small drop of RTV PDMS glue was spread over the

surface of the PDMS sheet, and a thin sheet of PDMS containing dexamethasone laid down

on top. The glue was allowed to set overnight. RTV glue and dex-containing PDMS are false

coloured in image for easier visualisation. PDMS sheets were then rolled into conduits, and

sealed to keep their shape using RTV PDMS glue applied to the overhangs. After allowing

the glue to set overnight, conduits were UV sterilised and implanted into rat sciatic nerves.

1065

1066

Polyacrylamide mix to PBS ratio	Group
Cell culture substrates	
0.106	0.1 kPa
0.15	1 kPa
0.30	10 kPa
1	50 kPa
Nerve conduit / subcutaneous implant	
0.15	PAA_0.2kPa
1	PAA_20kPa

1067

1068 **Supplementary Table 1. PAA protocols.** Polyacrylamide hydrogel mixes used to produce

1069 the substrates and coatings of various stiffnesses. Note the polyacrylamide mixes used for

1070 cell culture experiments and for implants are slightly different (see Methods section).

1071

Antibody	Dilution	Source	Code
Primary antibodies			
Rabbit anti-beta Tubulin	1:200	Abcam	ab6046
Rabbit anti-Collagen I	1:500	Abcam	ab34710
Rabbit anti-Fibronectin	1:100	Abcam	ab2413
Rabbit anti-Ki67	1:100	Abcam	ab15580
Mouse anti-Vinculin	1:100	Abcam	ab18058
Mouse anti-CD68	1:100	Serotec	MCA341R
Mouse anti-αSMA	1:100	Abcam	ab7817
Guinea pig anti-YAP1	1:500	Abcam	ab195987
Phalloidin-Alexa fluor 488	1:40	ThermoFisher	a12379
Secondary antibodies			
Alexa Fluor donkey anti-mouse 555	1:1,000	Invitrogen	ab150106
Alexa Fluor donkey anti-rabbit 488	1:1,000	Invitrogen	ab150073
Alexa Fluor donkey anti-mouse 488	1:400	Abcam	ab150185
Hoechst-33342 nuclear stain	1:10,000	Sigma	14533

1072

1073 **Supplementary Table 2.** Antibodies used in immunocytochemistry and

1074 immunohistochemistry experiments.

1075