In-depth profiling of calcite precipitation by environmental bacteria reveals

fundamental mechanistic differences with relevance to application

Bianca J. Reeksting[1], Timothy D. Hoffmann[1], Linzhen Tan[2], Kevin Paine[2] and Susanne

Gebhard[1]*

[1]Department of Biology and Biochemistry, Milner Centre for Evolution, and [2]BRE Centre for

Innovative Construction Materials, University of Bath, Claverton Down, Bath, BA2 7AY,

United Kingdom

Running title: Calcite precipitation by environmental bacteria

Key words: ureolysis, self-healing concrete, microbial-induced calcite precipitation, *Bacillus*

*Author for correspondence. Tel: +44 (0) 1225-386421 Email: s.gebhard@bath.ac.uk

ORIGINALITY-SIGNIFICANCE STATEMENT

Biomineralisation triggered by bacteria is important in the natural environment but also has many applications in industry, civil and geotechnical engineering. The diversity of biomineralization capability of environmental bacteria is, however, not well understood and the full potential for exploitation might therefore remain underestimated. This study surveyed environmental bacteria for their ability to precipitate calcium carbonate minerals and investigated both the mechanism and the resulting crystals. We show that while urease activity leads to the fastest precipitation, it is by no means essential. Importantly, the same quantities of calcium carbonate are produced by non-ureolytic bacteria, and the resulting crystals appear to have larger volumes and more organic components, which is likely beneficial in specific applications. This study also compares the performance of both precipitation mechanisms in a self-healing concrete application, with non-ureolytic bacteria delivering the more robust results. To our knowledge, this is the first systematic study into the fundamental differences in biomineralization between environmental bacteria and provides important information for the design of bacteria-based engineering solutions.

SUMMARY

Microbial-induced calcite precipitation (MICP) has not only helped to shape our planet's geological features, but is also a promising technology to address environmental concerns in civil engineering applications. However, limited understanding of the biomineralization capacity of environmental bacteria impedes application. We therefore surveyed the environment for different mechanisms of precipitation across bacteria. The most fundamental difference was ureolytic ability, where urease-positive bacteria caused rapid, widespread increases in pH, while non-ureolytic strains produced such changes slowly and locally. These pH shifts correlated well with patterns of precipitation on solid media. Strikingly, while both mechanisms led to high levels of precipitation, we observed clear differences in the precipitate. Ureolytic bacteria produced homogenous, inorganic fine

crystals, whereas the crystals of non-ureolytic strains were larger with a mixed

organic/inorganic composition. When representative strains were tested in application for

crack healing in cement mortars, non-ureolytic bacteria gave robust results, while ureolytic

strains showed more variation. This may be explained by our observation that urease activity

varied between growth conditions, or by the different nature and therefore material

performance of the precipitate. Our results shed light on the breadth of biomineralization

activity among environmental bacteria, an important step towards the rational design of

bacteria-based engineering solutions.

INTRODUCTION

Environmental protests worldwide have highlighted a growing demand for action on the

threat of climate change. Human activity has greatly contributed to global warming, currently

causing an estimated 0.2°C increase per decade due to past and ongoing emissions

(Intergovernmental panel on climate change (IPCC) 2018 report). There is a clear need to

reduce our carbon dioxide (CO_2) emissions as well as to find novel ways in which we can

consume CO_2 as a means of decreasing overall levels. Geological sequestration of CO_2

from large point source emitters into carbonate minerals, such as dolomite and limestone, is

an emerging technology that could mitigate increasing CO_2 concentrations (Mitchell *et al.*,

2010). Microorganisms can act as biomediators to enhance carbon capture (Mitchell *et al.*,

2010) by microbial induced calcite precipitation (MICP). This process leads to precipitation of

CO_2 as calcium carbonate ($CaCO_3$) as a result of microbial metabolism and has been

occurring on a geological scale for more than 2.5 billion years (Altermann *et al.*, 2006). The

formation by microbes of mineral carbonate structures, termed microbialites, is mediated by

a large diversity of microorganisms, often working together in a consortium (Wilmeth *et al.*,

2018). Indeed, cyanobacteria in association with heterotrophic bacteria are thought to be the

principal contributors to the production of carbonate rocks during almost 70% of Earth's

history (3.5-0.5 Ga) (Altermann *et al.*, 2006).

The success of MICP in biological engineering of the environment has led to the

investigation of its potential for exploitation in other areas. These areas include

bioremediation of heavy-metal contaminated soils via immobilisation of metals in precipitates

(Achal *et al.*, 2011; Ceci *et al.*, 2018), or wastewater treatment using this technology to

remove excess calcium. Geotechnical engineering represents another area of interest,

where MICP can improve soil properties by precipitating $CaCO_3$ to bind sand particles

together. Utilizing MICP in the construction industry is another rapidly emerging field. The

production and maintenance of concrete bears heavy environmental and economic costs,

with cement production contributing up to 5-8 % of global anthropogenic CO_2 emissions

(Huntzinger and Eatmon, 2009; Souto-Martinez *et al.*, 2018). Moreover, reinforced concrete

structures face durability issues caused by cracking and subsequent ingress of water and

ions, such as chlorides. This leads to corrosion of internal steel reinforcement and eventual

structural failure. MICP can seal such cracks in concrete and reduce permeability to

damaging substances, thereby extending the lifespan of structures and reducing the

environmental burden caused by construction of replacement structures. This broad range of

applications necessitates an understanding of how bacteria precipitate calcite and what the

factors are that may limit their performance.

Most bacteria are capable of MICP under suitable conditions (Boquet *et al.*, 1973), with key

factors such as calcium concentration, concentration of dissolved inorganic carbon (DIC),

pH, and availability of crystal nucleation sites affecting precipitation (Hammes and

Verstraete, 2002). Bacterial metabolism results in an increase in both pH and DIC (through

aerobic or anaerobic oxidation of organic compounds), and changes in solution chemistry

(Power *et al.*, 2011). This can lead to the oversaturation of Ca^{2+} and CO_3^{2-} ions to facilitate

the formation of calcium carbonate precipitates (Power *et al.*, 2011). The negatively charged

cell surfaces of bacteria further promote precipitation by attracting calcium ions and acting as

nucleation sites for crystal formation (Zhu *et al.*, 2016).

To date, the majority of studies of MICP have focussed on ureolytic bacteria (Zhu *et al.*,

2016). These are associated with high rates of $CaCO_3$ precipitation (Mitchell *et al.*, 2010),

caused by hydrolysis of urea ($CO(NH_2)_2$) to ammonia (NH_3) and carbonic acid (H_2CO_3)

(Mitchell *et al.*, 2010). The reaction of ammonia with water to ammonium (NH_4^+) and

hydroxide ions (OH^-) causes an upshift in pH, while carbonic acid dissociates to generate

bicarbonate (HCO_3^-). In the presence of calcium, this leads to the formation of a calcium

carbonate ($CaCO_3$) precipitate (Equations 1 and 2).

$$CO(NH_2)_2 + 2H_2O \rightarrow 2NH_4^+ + CO_3^{2-} \qquad (1)$$

$$Ca^{2+} + CO_3^{2-} \rightarrow CaCO_3 \text{ (s)} \qquad (2)$$

Ureolytic MICP has been used in a range of applications. Positive outcomes were obtained

in the improvement of soil properties, however non-uniform rates of precipitation throughout

the samples led to varying results (Zhao *et al.*, 2014). In addition, the requirement for

injection of the healing agent into the ground created problems where the rapid precipitation

initiated by urease activity caused clogging at the injection site (Cheng and Cord-Ruwisch,

2014). In other applications, such as crack sealing in cementitious materials, ureolytic MICP

has been shown to promote healing (Bang *et al.*, 2010; Wang *et al.*, 2012). However,

because of the dependency of the reaction on enzymatic activity, factors such as low

temperature markedly decreased the efficiency of the reaction (Wang *et al.*, 2017). In

addition, ureolytic MICP requires the presence of urea, which may not always be feasible to

provide, and the release of ammonia could contribute to environmental nitrogen loading

(Jonkers *et al.*, 2010).

To work around the challenges associated with ureolytic bacteria, the use of other metabolic

pathways needs consideration. The high efficiency of ureolytic MICP has resulted in the

assumption that non-ureolytic pathways cannot yield similarly high levels of precipitation and

are thus an inferior strategy to achieve precipitation. This has limited our understanding of

alternative pathways, and the factors affecting efficient calcite precipitation in non-ureolytic

bacteria are not clear. Studies on self-healing concrete using alkaliphilic non-ureolytic

bacteria, such as *Bacillus pseudofirmus* and *Bacillus cohnii*, have shown great promise and

have led to similar levels of self-healing at the laboratory scale as ureolytic bacteria (Sharma

et al., 2017; Alazhari *et al.*, 2018). To fully assess the potential of MICP for industrial and

environmental use, detailed understanding of the microorganism, mechanism of

precipitation, and application is therefore important.

Most studies of MICP have focussed on a small number of species and have thus restricted

our understanding of the mechanisms of precipitation across bacteria. In addition, many

previous studies have been primarily application-driven and have not always explored the

deeper workings of how the bacteria precipitate minerals and what influences this ability. To

build a strong basis on which to develop our understanding of MICP, we here took a broad

view and surveyed in detail the ability of environmental bacteria to precipitate calcite.

Focussing on bacteria that could grow in the alkaline conditions typical of high-calcium

environments, we assessed the prevalence of MICP capability in environmental bacteria,

their mechanisms of precipitation and resulting crystal morphologies as well as their

suitability for application in self-healing concrete. Our study provides an understanding of the

environmental potential for MICP, which is not only relevant to geomicrobiology but will

facilitate a more design-based approach to industrial application of MICP.

RESULTS AND DISCUSSION

Calcite precipitation ability of environmental isolates

To gain a broader understanding of the capability of bacteria to precipitate calcium

carbonate, we first performed a survey of a range of environments. In this, we focussed on

sites expected to be calcium-rich, such as exposed limestone, caves and soils in areas with

a limestone bedrock within the southwestern United Kingdom. Our isolation strategy targeted

spore-forming bacteria, as their stress tolerance makes them more universally useful in

potential applications. Moreover, as many of the high-calcium environments are in the

alkaline pH range, we specifically sought for isolates that tolerate such conditions.

Interestingly, the majority (89 %) of colonies obtained during primary isolations had visible

crystal formation on the surface, indicative of biomineralization. This supports previous

observations that this is a common trait among bacteria (Boquet *et al.*, 1973). Of 74 isolates

able to grow at pH 9, 31 displayed some growth at pH 10 on 0.25x B4 minimal medium and

were chosen for further characterisation.

Preliminary identification based on partial sequencing of the 16S rDNA assigned all of the

isolates into Bacillales (Fig. 1). The selection of spore-formers by heat-treatment can

account for the prevalence of Bacillales, with most isolates grouping within the *Bacillus*

genus. The predominant species represented were *Bacillus licheniformis* and *Bacillus*

muralis. *Sporosarcina pasteurii* was included in the analyses as it represents the paradigm

organism for industrial application of calcite precipitation. Interestingly, five of our isolates

grouped within the same clade as *S. pasteurii* (Fig. 1)*.*

Mechanistic differences in calcite precipitation between isolates

The isolation strategy, with the exception of looking for alkali-tolerant spore formers, was

unbiased for particular metabolic properties of the bacteria. A key feature of many known

calcite precipitators is ureolysis, which leads to a rapid pH change in the environment due to

the release of ammonia and subsequent production of OH$^-$. We therefore tested each of our

isolates for their ability to cleave urea, which is visible as a pink colour change in test broth

containing urea and phenol red (Fig. 2 and Fig. S2). Five out of the 31 isolates taken

forward for further characterisation were ureolytic. Two of these ureolytic isolates (CG4_2

and CG6_1) were most closely related to *B. muralis* whilst two others (CG7_2 and CG7_3)

were identified as *Lysinibacillus fusiformis*. The final isolate (EM1) was identified as

Psychrobacillus psychrodurans and was most closely related to *S. pasteurii*. With the

exception of CG4_2 and CG6_1, the other ureolytic isolates formed a monophyletic clade

with the strongly ureolytic *S. pasteurii* (Fig. 1).

To determine the effects of ureolysis and the associated pH change on crystal formation, we

repeated the experiment on solid media. Non-ureolytic strains showed only small changes in

pH, as indicated by local colour changes in the immediate vicinity of the bacterial colony, due

to general metabolic activity (Fig. 2, isolate RC1_1; Fig. S2). In contrast, a rapid and wide-

spread increase in pH was apparent in the model ureolytic bacterium *S. pasteurii*. Indeed, an

increase in pH as indicated by a colour change from orange to pink was visible as early as 1

h after inoculation of the plate with *S. pasteurii*, and the pH of the entire plate was alkaline by

24 h (Fig. 2). Similarly, the closely related ureolytic isolate CG7_3 caused a rapid increase in

pH, although the rate of pH change was slightly slower than seen in *S. pasteurii* (Fig. 2). The

same behaviour was observed for isolate EM1 (Fig. S2).

We next investigated the patterns of calcium carbonate precipitation on the same agar plates

and found that crystal formation correlated well with pH changes within the media. In non-

ureolytic strains, crystals were visible only on the surface of the colony, corresponding to the

observed localised pH change (Fig. 3A). In contrast, with ureolytic strains crystal

precipitation reflected the global pH change and occurred throughout the media (Fig. 3B).

The precipitation of calcium carbonate crystals throughout the media was likely due to a

change in the saturation kinetics in the media, resulting from the rapid increase in pH caused

by the urease-mediated release of ammonia from urea. Indeed, when urea was omitted for

isolate CG7_3, only the localised pH changes associated with non-ureolytic isolates was

seen (Fig. S3). In addition, crystals were only visible on the surface of the colony when urea

was omitted (Fig. S4), indicating that there are mechanistic differences in calcite precipitation

under ureolytic and non-ureolytic conditions.

Interestingly, two isolates that had tested positive for ureolysis in the test broth, CG6_1 and

CG4_2, did not produce the characteristic rapid rise in pH and associated crystal

precipitation when grown on solid media (Fig. 2 and S2). A possible explanation for this

discrepancy might be that in these isolates, urease activity is inducible in response to a cue

that was present in test broth, but not in the solid media. The main difference between the

two media was the content of nitrogen, which was very low in urease test broth (0.01 % (w/v)

yeast extract, 2 % (w/v) urea), but high in the solid media (0.2 % (w/v) yeast extract, 0.5 %

(w/v) peptone, 1 % (w/v) Lab-Lemco powder, 2 % (w/v) urea). Nitrogen metabolism and

urease production are tightly controlled in bacteria (Mobley and Hausinger, 1989). One

mechanism of regulation of urease is by repression of activity in the presence of ammonia-

or nitrogen-rich compounds and derepression of synthesis when nitrogen levels are low

(Mobley and Hausinger, 1989). We therefore tested to see whether nitrogen levels in the

media were having an effect on urease activity in these strains. Isolate CG6_1 was grown in

the presence of urea in media with either low (0.02 % yeast extract, 0.0125 % peptone, 2 %

urea) or high (0.2 % yeast extract, 0.125 % peptone, 2 % urea) nitrogen content, and urease

activity was quantified (Fig. 4A). Urease activity in CG6_1 was high when grown in low

nitrogen conditions, whilst significantly lower levels were detected in high nitrogen

conditions. This suggests that urease is only active in CG6_1 when the nitrogen supply is

limited. This is clearly a distinct type of behaviour from that seen in CG7_3 and *S. pasteurii*,

which both utilise urea rapidly regardless of the nitrogen composition of the media (Fig. 2).

However, while the overall urease activity of CG7_3 appeared similar to that of *S. pasteurii*

on solid media (Fig. 2), this isolate can grow well in the absence of urea (Fig. S3 and S4),

while *S. pasteurii* cannot. This suggests that CG7_3 may also be able to control the

expression of its urease genes, with urea acting directly as an inducer of urease activity. We

therefore tested the activity of whole cells grown in low and high nitrogen conditions as

before, but also compared cells grown in the presence and absence of urea (Fig. 4B). When

CG7_3 was grown in the absence of urea, it displayed medium urease activity under low

nitrogen conditions, which was further repressed by high nitrogen conditions. However,

when cells were grown in the presence of urea, urease activity was high regardless of

nitrogen conditions. Therefore, while urease activity in CG7_3 did show a partial response to

nitrogen limitation, this was overcome by incubation with urea, which clearly acted as the

main inducer and may be the preferred nitrogen source for this bacterium under the chosen

growth conditions. Taken together, our results indicate that there is a continuum of ureolytic

activity in environmental bacteria and that this, as seen above (Fig. 2-3), will have an impact

on crystal formation and biomineralization by different isolates.

Effect of ureolysis on crystal formation

Having established that crystal formation on solid media is very different between ureolytic

and non-ureolytic strains and that there are notable variations in ureolytic activity between

environmental isolates, we wanted to understand how ureolysis influences crystal formation

in more detail. To investigate this, we studied the kinetics of precipitation in our set of

isolates. Growing isolates in liquid culture with calcium over several days allowed us to

monitor the rates and total amounts of precipitate formed and correlate this to bacterial

growth and global pH changes. Growth of ureolytic isolates caused rapid alkalinisation of the

media, reaching pH 9 within two days, the first time point assayed. This resulted in complete

precipitation of the available calcium in the media on the same time-scale, with no further

change observed in two weeks of incubation (Fig. 5A and Fig. S5, *S. pasteurii*). Growth of

non-ureolytic bacteria caused a more gradual increase in pH, approaching pH 9 only in the

second week of incubation (Fig. 5B and Fig. S5). Precipitation of calcium in the media was

also more gradual, although both ureolytic and non-ureolytic isolates attained the maximum

theoretical levels of precipitation by the end of the first week. Strikingly, we observed

noticeable differences in cell numbers over the experimental period. Viable cell counts

decreased dramatically in ureolytic isolates and were undetectable within two days (Fig. 5A),

likely due to high ammonia concentrations in the media of these isolates resulting from the

cleavage of urea. Alternatively, these cells may have been encased by calcium carbonate,

preventing their further growth and division. In contrast, for non-ureolytic isolates cell

numbers gradually increased, before declining again over prolonged incubation (Fig. 5B).

These differences in viability over time between ureolytic and non-ureolytic bacteria may

have implications for application and should especially be considered in cases where the

continued presence of viable cells will be required for multiple cycles of precipitation.

Considering that the total amount of precipitate was similar in ureolytic and non-ureolytic

isolates, we next investigated whether the differences in the speed of precipitation had any

effects on the resulting crystals. As an initial observation, the precipitate recovered from

ureolytic strains was a much finer powder than that recovered from non-ureolytic strains.

EDX analyses of the different precipitates confirmed that all crystals tested were composed

of calcium carbonate (Fig. S6). However, further investigation using SEM revealed that the

crystal morphology differed between ureolytic and non-ureolytic strains (Fig. 5). When

precipitation was rapid, such as in ureolytic strains CG7_3 (Fig.5) and *S. pasteurii* (Fig. S5

and Fig S7), inorganic, homogenous crystals were produced. Non-ureolytic strains such as

MM1_1 that precipitated calcium carbonate more slowly produced crystals containing

significant proportions of bacterial cells and appeared more "organic" in nature (Fig. 5B).

Similarly, under these conditions CG4_2 and CG6_1 displayed the gradual increases in pH

(Fig. S5) and more organic precipitate characteristic of non-ureolytic strains (Fig. S7).

Considering that the assay conditions used for this experiment were high nitrogen, it can be

expected that urease activity was repressed under these conditions and resulted in strains

behaving like non-ureolytic strains. This differing appearance of precipitates in ureolytic

versus non-ureolytic conditions was consistently observed across all isolates tested in this

assay (Fig. S5 and Fig. S7). These results show that the differences in ureolytic activity

across our environmental isolates not only affected the kinetics of biomineralization, but also

had a clear impact on the crystal morphologies in the resulting precipitate.

Profound effects of urease activity on precipitation of calcium carbonate

To exclude that the observed differences in calcium carbonate precipitation were simply due

to strain-to-strain variation among our isolates, we exploited the fact that CG7_3 was

capable of switching between ureolytic and non-ureolytic states depending on the availability

of urea (Fig. 2 and Fig. S3). This allowed us to directly investigate the impact of ureolysis on

biomineralization in a single strain. When CG7_3 was grown in the absence of urea, there

was a gradual rise in pH and calcium carbonate precipitation as seen in non-ureolytic strains

(Fig. 6A). In contrast, in broths supplemented with urea we observed the rapid rise in pH and

associated calcium carbonate precipitation characteristic of the ureolytic strains studied

above (Fig. 6B). Viable cell counts also dropped dramatically in CG7_3 utilising urea (Fig.

6B), whereas in the absence of urea CG7_3 cell numbers remained relatively stable over the

first 10 days and declined by 13 days, likely due to prolonged nutrient depletion. SEM

analysis of the precipitates over the time-course of the study confirmed our previous

observations (Fig. 5) that urease activity was correlated with the rapid precipitation of

homogenous, inorganic crystals (Fig. 6B). When assessed over time, we noticed that the

initial precipitate consisted of the spherical calcium carbonate, typical of the polymorph

vaterite, followed by the eventual conversion into the rhombohedral morphology associated

with calcite, the more stable polymorph (Fig. 6B and Fig. S8-S9). In comparison, in the

absence of urea CG7_3 precipitated calcium carbonate more gradually, and these

precipitates were very organic in appearance (Fig. 6A and Fig. S8-S9). Moreover, these

'organic' crystals were often much larger than the inorganic spheres produced in the

presence of urea, likely due to aggregation via interspersed bacterial cells. As these

experiments were all performed on the same bacterial isolate, our observations are a direct

reflection of the effects of urease activity on calcite precipitation. Although both pathways

produced similar quantities of precipitate, there were major differences in precipitate

morphologies, number of viable bacteria and pH of the bulk phase. To our knowledge, this is

the first systematic study into the fundamental differences in biomineralization between

different environmental bacteria. Both ureolytic and non-ureolytic bacteria are currently being

developed for a range of industrial applications (DeJong *et al.*, 2010). The findings reported

here may therefore offer a key step towards a rational design approach to choosing which

mechanism of biomineralization is better suited to specific industrial applications.

Industrial relevance of different calcite precipitation strategies

To test if the differences in biomineralization mechanism translate to an applied setting, we

next assessed the performance of ureolytic and non-ureolytic strains in self-healing concrete

applications, using cement mortars as our test system. We produced spores for each strain,

which were then encapsulated in light-weight aggregate before casting them in mortars,

together with yeast extract and calcium nitrate, as well as urea in the case of ureolytic

strains, to provide nutrients for bacterial growth and sufficient calcium for biomineralization.

Mortars were cured and then cracked under three-point bending to obtain a target crack

width of 500 µM. The self-healing process was subsequently monitored over 8 weeks.

Autogenous healing, which occurs to some degree due to cement hydration, was seen in

control mortars that lacked any bacterial spores (Fig. 7 and Fig. 8). This healing was mostly

observed along the top edge of the crack and rarely extended down the sides of the mortar

prism. Mortars containing either ureolytic or non-ureolytic bacteria also displayed crack

healing, and this generally extended across the top as well as down the sides of the crack

(Fig. 7 and Fig. 8). However, healing in mortars containing ureolytic bacteria was less

regular than seen with non-ureolytic strains, with the sides of cracks not consistently sealing

(Fig. 8).

The key aim of bacteria-induced self-healing of concrete is to re-establish water tightness of

the structure to prevent water ingress and subsequent corrosion of steel reinforcement.

While visual inspection allowed an initial assessment of the healing process, we next sought

to test water tightness of our mortars using water flow tests following eight weeks of healing.

Recovery of water tightness in mortars containing only the standard cement mix, with no

nutrients or additional calcium showed variable recovery of water tightness, generally close

to 40 % (Fig. 9, 'Reference'). Control mortars containing yeast extract and calcium nitrate,

but without bacterial spores, showed much higher recovery (averaging 87-95 %). This

recovery is likely because of a combination of autogenous healing and possible presence of

environmental bacteria, which may be able to utilise the yeast extract and thus contribute to

precipitation. As the mortars were not made or kept in a sterile fashion to more closely reflect

industrial application, contamination with such environmental bacteria must be considered

likely. The mortars containing non-ureolytic bacteria showed a strikingly consistent recovery

in water tightness, leading to near complete resistance to water flow, with all specimens

healing to over 90 % and many reaching close to 100% (Fig. 9). Interestingly, while mortars

containing ureolytic bacteria also showed good restoration of water tightness, there was

more variation in the degree of healing obtained. EM1 performed as well as the non-ureolytic

strains, but CG7_3 showed lower overall recovery values (mean 87 %) that were similar to

the controls lacking encapsulated bacteria. This discrepancy in results may reflect the

variability in ureolytic activity in these strains. Given the clear dependence on growth

conditions in some strains described above, it is difficult to predict the degree of ureolytic

ability displayed in cement mortars. An alternative explanation may be that the rapid

precipitation and small crystal size observed in ureolytic isolates does not reliably lead to

retention of the precipitate within the crack and may thus not perform as reliably in self-

healing as the larger aggregates with organic components of the non-ureolytic strains. It will

be interesting to investigate the details of material performance following healing with both

types of bacteria to fully understand the implications of the different mechanisms of

precipitation.

CONCLUDING REMARKS

The environment represents a large reservoir of potential in terms of exploiting bacteria for

commercial use of MICP. There have been numerous studies on MICP for varying

applications, however, most of these have been restricted to the use of a single or small

number of species and were very application specific. This limits our understanding of

precipitation capabilities of environmental bacteria more generally. In order to establish a

stronger knowledge base to facilitate new and specialised technical applications we

surveyed the ability of environmental bacteria to precipitate calcite. We found that the

majority of isolates were capable of biomineralization, in line with previous results (Boquet *et*

al., 1973). This is most likely due to their ability, through metabolic processes, to create a

microenvironment around the cell that aids in the precipitation process. The electronegative

nature of their cell surface facilitates crystal deposition on the surface (Schultze-Lam *et al.*,

1996), making precipitation more favourable. Our detailed characterisation of

biomineralization by our set of isolates, however, revealed fundamental differences in the

way in which different bacteria precipitate calcium carbonate.

Ureolytic bacteria rapidly precipitate calcium carbonate, having led to ureolysis becoming

one of the main pathways used in MICP applications to date. However, in our study, only 16

% of isolates were able to cleave urea, and even amongst these there was a marked

diversity in ureolytic activity. Differences in how isolates regulate urease activity were seen,

with some responding to low nitrogen levels whilst others responded to urea as a primary

inducer. This was in striking contrast to the constitutive high urease activity of *S. pasteuri*,

one of the most frequently utilised MICP-capable bacteria to date (Stocks-Fischer *et al.*,

1999; Tobler *et al.*, 2011; Zhu *et al.*, 2016). The performance of ureolytic bacteria will

therefore depend on the precise conditions encountered in their environment, and this

should be carefully considered when choosing the bacterial species for a given application.

The importance of this point is further emphasised by our finding that ureolysis affected

crystal formation both in terms of kinetics and in the morphology of the precipitate.

The majority of our isolates precipitated calcium carbonate without possessing ureolytic

activity. In contrast to initial expectations that this mechanism may lead to the formation of

low amounts of precipitate, we found that all of our isolates were capable of precipitating the

total amount of calcium supplied in the growth media, although this process took more time

with non-ureolytic strains. Importantly, we showed that the precipitate formed by the non-

ureolytic bacteria consisted of larger, mixed organic/inorganic crystals. This was in good

agreement with our initial observation that precipitation in these bacteria on solid media only

occurred on top of the colony and therefore likely involved the physical presence of cells.

The mixed nature of the precipitate means that for the same amount of calcium being used,

a larger volume of precipitate can be formed. This could present a major advantage in

industrial application where often only a limited amount of calcium is available to fill a

relatively large space, such as in self-healing concrete.

When we tested the performance of our isolates in self-healing of cracked cement mortars,

we found that, indeed, non-ureolytic bacteria caused a more consistent recovery of water

tightness and more complete healing. The ureolytic bacteria tested showed less consistency

in performance, although one strain gave similar results to the non-ureolytic isolates. It is

difficult to ascertain whether these inconsistencies in behaviour are due to differences in

ureolytic activity in the applied setting or are a consequence of the purely inorganic

precipitate formed by ureolytic strains. It seems plausible that the supply of yeast extract as

part of the cement mix will lead to a low-nitrogen environment conducive to urease gene

expression, and the presence of urea should ensure activity in those strains that are urea-

responsive. While further experimentation is needed to determine the precise conditions

encountered by the bacteria within hardened cement mortars as well as the material

properties of the precipitate formed, in applications where nutritional supply is hard to

control, the use of non-ureolytic bacteria may give more robust and reliable performance.

Self-healing concrete of course only represents one of many potential applications of MICP

and each application will have its own challenges. For example, in spray-on applications

such as restoration of existing structures and historic buildings, the rapid precipitation of

large amounts of precipitate through ureolysis may be advantageous. In contrast, during soil

stabilisation where bacteria and their substrates are pumped into the ground, rapid rates of

ureolysis could result in premature precipitation and lead to blockages at the injection site as

has been reported (Cheng and Cord-Ruwisch, 2014). In this case, it would be more

beneficial to use microbes that are non-ureolytic, or that switch to ureolysis at a later time

point, as seen in our isolates that responded to low environmental nitrogen.

In summary, most bacteria have the ability to precipitate calcium carbonate given the right

conditions, and the most suitable bacteria to use will be application dependent. While most

previous studies have focussed on one or two isolates, we here show for the first time the

plethora of MICP activities and capabilities the environment has to offer as a 'talent pool' that

can offer bespoke solutions to many different applications. MICP-based technologies may

offer solutions to problems caused by a rising global population and may even be used to

mitigate global warming. The increasing demand for infrastructure, as well as the need to

engineer land on which to build it, results in an increase in CO_2 emissions and release of

harmful chemicals into the environment (DeJong *et al.*, 2010). MICP can reduce this

environmental burden by producing buildings that are more durable, prolonging the life of

existing buildings, and improving soil properties without the use of toxic and hazardous

chemical additives. Moreover, technologies that actively remove CO_2 from the environment

and sequestrate it in harmless or even useful minerals such as calcite will be critical in

meeting zero emission goals in the future.

EXPERIMENTAL PROCEDURES

Bacterial isolates and growth

Sample collection was from six locations across the United Kingdom including limestone

caves and immature calcareous soils (Mendip Hills, England), soil, rock and limestone caves

(Bath, England), soil and rock scrapings (Monmouthshire, Wales) and soil and scrapings

from marine rock in two locations in Cornwall (Mount's Bay and Falmouth). Samples were

stored at 4°C until use. Of each sample, 0.5 g was re-suspended in 1 ml sterile saline

solution (0.85% (w/v) NaCl) and heated to 80°C for 20 minutes to enrich for spore-formers.

Selection for alkali-tolerant bacteria was carried out by plating 100 µl of this suspension onto

$0.25\times$ B4 medium (1 g l^{-1} yeast extract, 12 g l^{-1} Trizma base, 1.25 g l^{-1} glucose, 2.5 g l^{-1}

calcium acetate (Ca(OAc)$_2$), 15 g l^{-1} agar) adjusted with NaOH to pH 9. Glucose and

Ca(OAc)$_2$ were filter-sterilised and added after autoclaving. Individual colonies with unique

colony morphology were re-streaked onto $0.25\times$ B4 medium buffered with 75 mM CHES, 75

mM CAPS, adjusted with NaOH to pH 10. Strains capable of growth at pH 10 and with

visible crystals on the colony or in the surrounding agar were selected for further

characterisation. Single colonies were inoculated in lysogeny broth (LB; 10 g l^{-1} tryptone, 5 g

l^{-1} yeast extract, 10 g l^{-1} NaCl) and grown overnight, before storage at -80 °C in a 25% (w/v)

glycerol solution. Isolates were subsequently maintained on LB agar.

Sporosarcina pasteurii DSM33 was included as a reference organism and maintained on LB

agar supplemented with 20 g l^{-1} urea (filter-sterilized, added after autoclaving). All bacterial

cultures were grown at 30 °C, and liquid cultures were agitated at 150 rpm. Growth of liquid

cultures was monitored spectrophotometrically by optical density at 600 nm wavelength

(OD$_{600}$) in cuvettes of 1 cm light path length. Representative isolates showing the best

characteristics were deposited into the DSMZ collection (Deutsche Sammlung von

Mikroorganismen und Zellkulturen GmbH, Germany) as follows*: DSM XX (RC1_1), DSM

XX (PD1_1), DSM XX (EM1), DSM XX (CG7_3), DSM XX (CG7_2), DSM XX (CG6_1), DSM

XX (CG4_2), and DSM XX (MM1_1).

*Note to reviewers: The DSM numbers have not yet been issued but will be available by the

time the manuscript has been through the review process.

Identification of isolates and phylogenetic analysis

The 16S rDNA gene fragment was amplified using the 27F (5'-

AGAGTTTGATCMTGGCTCAG-3') and 1492R (5'-TACCTTGTTACGACTT- 3') primers

(Lane, 1991). Amplification was performed in a total volume of 25 µl containing 12.5 µl of 2x

OneTaq Mastermix (New England Biolabs, NEB), 9.9 µl of nuclease-free H$_2$O, 2.4 % (v/v)

DMSO, 0.2 µM of each primer and 1 µl of an overnight culture as template. Reaction

conditions were as follows: initial denaturation at 94 °C for 5 min followed by 30 cycles

consisting of denaturation at 94°C for 30 sec, annealing at 45° C for 30 sec, and extension

at 68 °C for 2 min. Final extension was at 68°C for 5 min. For enzymatic clean-up, 2 µl of

EXO-SAP (100 U shrimp alkaline phosphatase (Thermo Scientific), 100 U Exonuclease I

(Thermo Scientific), and 895 µl nuclease-free H$_2$O) was added to every 5 µl of PCR product

and the reaction was incubated at 37°C for 15 min before enzyme inactivation at 80°C for 15

min. Sequencing of PCR products was carried out using the chain termination method

(Eurofins Genomics, Germany). In the case of strains where direct sequencing of the PCR

product was unsuccessful, 16S rDNA fragments were first cloned into the Topo® vector

according to manufacturer's instructions (TOPO TA Cloning® Kit, Invitrogen). Sequencing of

the resulting plasmids was performed using the M13 forward primer (5'-

CCCAGTCACGACGTTGTAAAACG-3'). Bioedit (Hall, 1999) was used to assemble

sequences obtained from forward and reverse sequencing reactions. Sequences were

compared against the non-redundant GenBank nucleotide collection using BLASTN

(http://www.ncbi.nlm.nih.gov). For phylogenetic analyses, the 16S rDNA sequences of

nearest relatives for each strain according to BLASTN analysis, as well as of

Sporosarcina pasteurii DSM 33 were obtained from GenBank, and evolutionary analyses

were carried out in MEGA 7.0 (Kumar *et al.*, 2016). Sequences were aligned using

MUSCLE, and conserved blocks were selected from these multiple alignments using

GBlocks (Castresana, 2000). Phylogenetic trees were constructed using the maximum

likelihood (ML) method based on the Tamura-Nei model (Tamura and Nei, 1993). Bootstrap

values were inferred from 1000 replicates and partitions reproduced in less than 50 %

bootstrap replicates were collapsed.

Analysis of calcium carbonate precipitation

Spatial distribution of calcite precipitation and pH changes was assessed by spotting 20 µl of

an overnight culture (OD_{600} adjusted to 1) onto nutrient agar (Oxoid, 23 g l^{-1}) supplemented

with phenol red (0.025 g l^{-1}) and $Ca(OAc)_2$ (2.5 g l^{-1} or 10 g l^{-1}), with or without urea (20 g l^{-1}).

Physical appearance of plates and crystals were recorded photographically at 1 hr, 3 hr, 5

hr, 24 hr, and 48 hr.

Rate of mineral precipitation over time was determined by inoculating (1:1000) 150 ml LB

broth supplemented with 10 g l^{-1} $Ca(OAc)_2$ from overnight cultures and monitoring viable cell

numbers, pH, and insoluble calcium precipitated over time. Viable cells were determined as

colony-forming units (CFU) by the plate count method. pH was recorded from aliquots of the

culture using a pH electrode (Jenway 924 030, Cole-Parmer, Staffordshire UK) coupled to a

pH meter (Jenway 3510 pH Meter). Insoluble precipitate was recovered by centrifugation

($975 \times g$, 2 minutes at room temperature (RT)) and washed three times in 50 ml distilled

water to remove planktonic cells and culture medium before oven drying at 50 °C for 48

hours. Morphology of dried precipitates was examined at accelerating voltages ranging from

10 to 20 kV by scanning electron microscopy (SEM; JSM 6480LV, JEOL, Welwyn, UK)

equipped with an energy dispersive x-ray (EDX) analyser for elemental analysis.

Representative samples were prepared by spreading dried precipitate on double-sided

carbon tape placed on aluminium stubs. For EDX, samples were placed under vacuum

overnight before analysis. For imaging, samples were gold-coated by sputtering for 3 min at

RT. Samples imaged with field emission electron microscopy (FE-SEM; JSM-6301F cold

field emission SEM, JEOL) were prepared in a similar manner as for SEM but coated in

Chromium to a thickness of 20 nM and examined at 5 kV.

Urease activity

Qualitative urease activity of bacterial isolates was determined using urease test broth (0.1 g

l^{-1} yeast extract, 20 g l^{-1} urea, 0.01 g l^{-1} phenol red, 0.67 mM KH_2PO_4, 0.67 mM Na_2HPO_4 (pH

6.8±0.2). Test broth (2 ml) was inoculated with 100 µl of an overnight culture grown in LB

and incubated at 30 °C for up to 5 days. A urease-positive reaction was characterised by a

change in colour from yellow/orange to pink.

For quantitative urease measurements in whole cells, cultures were grown at 30 °C with

agitation (150 rpm). Overnight cultures (20 µl, LB broth) were used to inoculate 25 ml (1:500)

low nitrogen (0.2 g l^{-1} yeast extract, 0.125 g l^{-1} peptone, 2.5 g l^{-1} NaCl) and standard media

(2 g l^{-1} yeast extract, 1.25 g l^{-1} peptone, 2.5 g l^{-1} NaCl) broths. Where pre-induction by urea

was required, broths were supplemented with urea (20 g l^{-1}). Cultures were grown (for 24 hr)

and cells were harvested from 1 ml of culture by centrifugation (8000 $x\ g$, 2 min). Cells were

resuspended in 1 volume 0.1 M potassium phosphate buffer (pH 8.0), and OD_{600} was

recorded. Depending on the urease activities of individual strains, dilutions of cells were

made to ensure the activity was within the linear range of the assay. These dilutions were

recorded and accounted for during OD normalisation. Urease activity was determined

according to the phenol-hypochlorite method (Natarajan, 1995) and adapted from (Achal *et*

al., 2009) for whole cells. The reaction mix volumes were multiplied by the number of time-

points in the assay to allow one larger volume mix to be prepared. Per time point, individual

reactions contained 75 µl cell suspension, 300 µl 0.1 M potassium phosphate buffer (pH 8.0)

and 750 µl 0.1 M urea solution. The mixture was incubated at 30°C and 1 ml aliquots were

removed at 0, 30, 60, 90 and 120 min. At each time point, the reaction was stopped by

adding 300 µl phenol nitroprusside and 300 µl alkaline hypochlorite. Final colour was

developed at 37 °C for 25 min and absorbance was measured at 625 nm. Ammonium

chloride (25-2500 µM) solutions were used to produce a standard curve (Fig. S1). One unit

of activity was defined as the release of 1 µM of ammonia per minute, per OD (U OD^{-1} ml^{-1}).

Endospore production

Endospores of bacterial strains were prepared by inoculating 150 ml LB broth (1:1000) from

an overnight culture grown at 30°C with shaking (150 rpm). This culture was again grown

overnight and then cells were harvested by centrifugation (3200 $\times$ *g*, 10 min at RT) and

resuspended in 750 ml Difco sporulation medium (DSM; 8 g l^{-1} nutrient broth (Oxoid), 13.41

mM KCl, 0.49 mM $MgSO_4$, adjusted to pH 7.6 with NaOH. Prior to use 1mM $Ca(NO_3)_2$, 0.01

mM $MnCl_2$, and 1µM $FeSO_4$ were added from a filter-sterilised stock solution (Sonenshein *et*

al., 1974). Cultures were grown with agitation (150 rpm) at 30 °C for at least 48 hours before

sporulation was assessed using phase contrast microscopy. When the majority of cells

contained phase-bright endospores, cells were pelleted by centrifugation (3200 $\times$ *g*, 10 min

at RT) and washed thrice in 10 mM Tris-HCl (pH 9) followed by 30 min treatment with

chlorohexidine digluconate (0.3 mg ml^{-1}) to kill vegetative cells. Washing was repeated as

before and spore pellets were snap-frozen in liquid nitrogen and freeze-dried under vacuum

overnight.

Preparation of mortar samples

Mortar prisms (65 mm × 40 mm × 40 mm) were comprised of two layers. The first contained

(per 3 prisms): 253.3 g sand conforming to BS EN 196-1, 92 g Portland limestone cement

(CEM II A-L 32.5R), 46 g water, 1 g yeast extract, 4.55 g calcium nitrate, 3.54 g aerated

concrete granules. Mortars containing ureolytic bacteria also contained urea (3.68 g per 3

prisms). Spores (2.1×10^{10} cfu) were resuspended in 1 ml dH_2O and imbibed into the

aerated concrete granules before drying and sealing with polyvinyl acetate (PVA, 30%

(w/w)). After approximately 3 hours, the second, top layer was cast. The second layer

contained standard cement mortar (Per 3 prisms: 276g standard sand, 92 g cement, 46 g

water). Reference specimens were cast in two layers but only contained standard cement

mortar. Specimens remained at room temperature for 24-48 hours before demoulding and

subsequent curing for 28 days submersed in tap water. After curing, specimens were oven

dried at 50 °C for 24 hours. The top third of the prism was wrapped with carbon fibre

reinforced polymer strips to enable generation of a crack of controlled width. A notch (1.5

mm deep) was sawn at mid-span to serve as a crack initiation point. Specimens were

cracked by three-point bending using a 30 kN Instron static testing frame. A crack mouth

opening displacement (CMOD) gauge was used to measurement crack width. Load was

applied to maintain a crack growth of 25 μm per minute, and loading was stopped when the

crack width was predicted to be 500 μm wide after load removal. A marker pen was used to

indicate specific crack sections to enable monitoring of the crack at the same site. Following

cracking, prisms were placed in tanks, open to the atmosphere and filled with tap water to 1

cm below the top of the mortars, and were incubated at room temperature for two months.

Visualisation of crack healing was monitored using a Leica M205C light microscope, and

images were taken of freshly cracked mortars and after 1, 4, and 8 weeks of healing.

Water permeability tests

Water flow rate before cracking, after cracking, and after 8 weeks of healing was determined to monitor effects of cracking and healing on water permeability in mortars as described previously (Lee and Ryou, 2016). The instrument used was based on RILEM test method II.4 (RILEM, 1987). The bottom of a 10 ml measuring cylinder (0.2 ml graduation) was removed and a 40 mm PVC pipe with 15 mm depth was fixed to the bottom. This was sealed onto the mortar with glue. This cylinder was filled with water and the time it took to drop from initial height h_1 to a final height h_2 was recorded. The total height was either 78.5 mm or, in the case of samples with low permeability, the height to which the water level had dropped after 30 min. The permeability coefficient was calculated according to Equation 3 (Lee and Ryou, 2016).

$$k = \frac{aL}{At} ln\left[\frac{h_1}{h_2}\right], \tag{3}$$

where k = water permeability coefficient (cm/s); a = cross-sectional area of the cylinder (1.77 cm^2); L = thickness of specimen (4 cm); A = cross-sectional area of the specimen which equals the cross-sectional area of acrylic plate (10.18 cm^2); t = time (s); h_1 = initial water head (12.4 cm); h_2 = final water head (cm). The percentage of crack healing was calculated as follows:

$$\text{Healing percentage (\%)} = \frac{(k_0 - k_t)}{k_0} \times 100 \tag{4}$$

where k_0 = initial water permeability after cracking, k_t = water permeability at healing time t.

ACKNOWLEDGEMENTS

The authors would like to acknowledge the Engineering and Physical Sciences Research Council (EPSRC; EP/PO2081X/1) and industrial collaborators/partners for funding the

Resilient Materials for Life (RM4L) project. TDH was supported by a University of Bath

Research Studentship Award. We thank technical staff in the Department of Architecture and

Civil Engineering and the Department of Biology and Biochemistry for key support. We

further thank Dr Philip Fletcher and Diane Lednitzky of the Material and Chemical

Characterisation Facility (MC^2) at University of Bath (https://doi.org/10.15125/mx6j-3r54) for

their assistance with microscopy.

REFERENCES

Achal, V., Mukherjee, A., Basu, P.C., and Reddy, M.S. (2009) Lactose mother liquor as an alternative nutrient source for microbial concrete production by *Sporosarcina pasteurii*. *J Ind Microbiol Biotechnol* **36**: 433–438.

Achal, V., Pan, X., and Zhang, D. (2011) Remediation of copper-contaminated soil by *Kocuria flava* CR1 , based on microbially induced calcite precipitation. *Ecol Eng* **37**: 1601–1605.

Alazhari, M., Sharma, T., Heath, A., Cooper, R., and Paine, K. (2018) Application of expanded perlite encapsulated bacteria and growth media for self-healing concrete. *Constr Build Mater* **160**: 610–619.

Altermann, W., Kazmierczak, J., Oren, A., and Wright, D.T. (2006) Cyanobacterial calcification and its rock-building potential during 3.5 billion years of Earth history. *Geobiology* **4**: 147–166.

Bang, S.S., Lippert, J.J., Yerra, U., Mulukutla, S., and Ramakrishnan, V. (2010) Microbial calcite , a bio-based smart nanomaterial in concrete remediation. *Int J Smart Nano Mater* **1**: 28–39.

Boquet, E., Boronat, A., and Ramos-Cormenzana, A. (1973) Production of Calcite (Calcium Carbonate) Crystals by Soil Bacteria is a General Phenomenon. *Nature* **246**: 527–529.

Castresana, J. (2000) Selection of Conserved Blocks from Multiple Alignments for Their Use in Phylogenetic Analysis. *Mol Biol Evol* **17**: 540–552.

Ceci, A., Pinzari, F., Riccardi, C., Maggi, O., Pierro, L., Papini, M.P., et al. (2018) Metabolic synergies in the biotransformation of organic and metallic toxic compounds by a saprotrophic soil fungus. *Environ Biotechnol* **102**: 1019–1033.

Cheng, L. and Cord-Ruwisch, R. (2014) Upscaling Effects of Soil Improvement by Microbially Induced Calcite Precipitation by Surface Percolation. *Geomicrobiol J* **31**: 396–406.

DeJong, J.T., Mortensen, B.M., Martinez, B.C., and Nelson, D.C. (2010) Bio-mediated soil improvement. *Ecol Eng* **36**: 197–210.

Hall, T. (1999) Bioedit: a user-friendly biological sequence alignment editor and analysis program for Windows 95/98/NT. *Nucleic Acids Symp Ser* **41**: 95–98.

Hammes, F. and Verstraete, W. (2002) Key roles of pH and calcium metabolism in microbial

carbonate precipitation. *Rev Environ Sci Biotechnol* **1**: 3–7.

Huntzinger, D.N. and Eatmon, T.D. (2009) A life-cycle assessment of Portland cement
manufacturing : comparing the traditional process with alternative technologies. *J Clean*
Prod **17**: 668–675.

Jonkers, H.M., Thijssen, A., Muyzer, G., Copuroglu, O., and Schlangen, E. (2010)
Application of bacteria as self-healing agent for the development of sustainable
concrete. *Ecol Eng* **36**: 230–235.

Kumar, S., Stecher, G., and Tamura, K. (2016) MEGA7 : Molecular Evolutionary Genetics
Analysis Version 7 . 0 for Bigger Datasets Brief communication. *Mol Biol Evol* **33**:
1870–1874.

Lane, D. (1991) 16S/23S rRNA sequencing. In, Stackebrandt,E. and Goodfellow,M. (eds),
Nucleic acid techniques in bacterial systematics. John Wiley and Sons, pp. 115–175.

Lee, Y.S. and Ryou, J.S. (2016) Crack healing performance of PVA-coated granules made
of cement, CSA, and Na2CO3 in the cement matrix. *Materials (Basel)* **9**: 555–575.

Mitchell, A.C., Dideriksen, K., Spangler, L.H., Cunningham, A.B., and Gerlach, R. (2010)
Microbially Enhanced Carbon Capture and Storage by Mineral-Trapping and Solubility-
Trapping. *Environ Sci Technol* **44**: 5270–5276.

Mobley, H.L.T. and Hausinger, R.P. (1989) Microbial Ureases : Significance , Regulation ,
and Molecular Characterization. *Microbiol Rev* **53**: 85–108.

Natarajan, K.R. (1995) Kinetic Study of the Enzyme Urease from Dolichos biflorus. *J Chem*
Educ **72**: 556–557.

Power, I.M., Wilson, S.A., Small, D.P., Dipple, G.M., Wan, W., and Southam, G. (2011)
Microbially Mediated Mineral Carbonation : Roles of Phototrophy and Heterotrophy.
Environ Sci Technol **45**: 9061–9068.

RILEM (1987) Measurement of Water Absorption Under Low Pressure. RILEM Test Method
No. 11.4.

Schultze-Lam, S., Fortin, D., Davis, B.S., and Beveridge, T.J. (1996) Mineralization of
bacterial surfaces. *Chem Geol* **132**: 171–181.

Sharma, T.K., Alazhari, M., Heath, A., Paine, K., and Cooper, R.M. (2017) Alkaliphilic
Bacillus species show potential application in concrete crack repair by virtue of rapid
spore production and germination then extracellular calcite formation. *J Appl Microbiol*
122: 1233–1244.

Sonenshein, A.L., Cami, B., Brevet, J., and Cote, R. (1974) Isolation and Characterization of
Rifampin-Resistant and Streptolydigin-Resistant Mutants of *Bacillus subtilis* with Altered
Sporulation Properties. *J Bacteriol* **120**: 253–265.

Souto-Martinez, A., Arehart, J.H., and Srubar III, W. V (2018) Energy & Buildings Cradle-to-
gate CO_2 emissions vs . *in situ* CO_2 sequestration of structural concrete elements.
Energy Build **167**: 301–311.

Stocks-Fischer, S., Galinat, J.K., and Bang, S.S. (1999) Microbiological precipitation of
$CaCO_3$. *Soil Biol Biochem* **31**: 1563–1571.

Tamura, K. and Nei, M. (1993) Estimation of the Number of Nucleotide Substitutions in the
Control Region of Mitochondrial DNA in Humans and. *Mol Biol Evol* **10**: 512–526.

Tobler, D.J., Cuthbert, M.O., Greswell, R.B., Riley, M.S., Renshaw, J.C., Handley-Sidhu, S.,
and Phoenix, V.R. (2011) Comparison of rates of ureolysis between *Sporosarcina*

pasteurii and an indigenous groundwater community under conditions required to
precipitate large volumes of calcite. *Geochim Cosmochim Acta* **75**: 3290–3301.

Wang, J., De Belie, N., and Verstraete, W. (2012) Diatomaceous earth as a protective
vehicle for bacteria applied for self-healing concrete. *Biotechnol Methods* **39**: 567–577.

Wang, J., Jonkers, H.M., Boon, N., and De Belie, N. (2017) *Bacillus sphaericus* LMG 22257
is physiologically suitable for self-healing concrete. *Appl Microbiol Biotechnol* **101**:
5101–5114.

Wilmeth, D.T., Johnson, H.A., Stamps, B.W., Berelson, W.M., Stevenson, B.S., Nunn, H.S.,
et al. (2018) Environmental and Biological Influences on Carbonate Precipitation Within
Hot Spring Microbial Mats in Little Hot Creek, CA. *Front Microbiol* **9**: 1–13.

Zhao, Q., Li, L., Asce, M., Li, C., Li, M., Amini, F., et al. (2014) Factors Affecting
Improvement of Engineering Properties of MICP-Treated Soil Catalyzed by Bacteria
and Urease. *J Mater Civ Eng* **26**: 1–10.

Zhu, T., Dittrich, M., and Dittrich, M. (2016) Carbonate Precipitation through Microbial
Activities in Natural environment , and Their Potential in Biotechnology : A Review.
Front Bioeng Biotechnol **4**: 1–21.

FIGURE LEGENDS

Figure 1. Phylogenetic analysis of selected calcite-precipitating isolates and their

closest relatives. Yellow boxes, non-ureolytic isolates; orange boxes, isolates with inducible

ureolytic activity; pink boxes, isolates that utilize urea as a primary nitrogen source; unfilled

boxes, unknown ureolytic ability. The ureolytic potential of closest relatives is not shown.

Accession numbers are indicated in parentheses. The percentage of trees in which

associated taxa clustered together is shown next to the branches (1000 bootstraps).

Figure 2. Diversity in ureolytic activity across environmental isolates. *Left*, urease test

broth inoculated with the strains indicated to the left. *Right*, nutrient agar plates

supplemented with phenol red, calcium acetate, and urea were inoculated in the centre with

suspensions of the same strains. Pink shading indicates the pH change caused by ammonia

release from ureolytic activity.

Figure 3. Crystal formation correlates with pH changes in non-ureolytic and ureolytic

bacteria. (A) Non-ureolytic isolate PD1_1 shows localised crystals on the bacterial colony.

(B) Ureolytic *S. pasteurii* demonstrates crystal precipitation throughout the media,

corresponding to pH changes that occur throughout the media. Arrows indicate $CaCO_3$

crystals.

Figure 4. Regulation of urease activity by environmental nitrogen and urea. Isolates

722 CG6_1 (A) and CG7_3 (B) cells were grown in high or low nitrogen conditions in the

723 presence (+) or absence (-) of urea. Error bars represent standard deviation from 2-3

724 biological reps with 1-2 technical reps each. Significance was tested using an unpaired t-test

725 (A) and one-way ANOVA followed by unpaired t-test (B). *, $P < 0.05$, ***, $P < 0.001$ and ****, P

726 < 0.0001.

Figure 5. Calcite precipitation kinetics and crystal morphology in ureolytic CG7_3 and

non-ureolytic MM1_1. The ureolytic strain CG7_3 (A) and the non-ureolytic MM1_1 (B)

were grown in LB medium supplemented with urea (20 g l^{-1}) and $Ca(OAc)_2$ (10 g l^{-1}) and

precipitation of insoluble calcium carbonate (bars, g l^{-1}), pH changes (circles) and changes in

cell number (boxes, CFU ml^{-1}) were monitored over time (days). Maximum theoretical level

of precipitation is indicated (dotted line). *Right,* electron micrographs of representative

precipitate taken at day 9.

Figure 6. Comparison of ureolytic and non-ureolytic mechanisms of calcite

precipitation in CG7_3. The ureolytic strain CG7_3 was grown in LB medium

supplemented with $Ca(OAc)_2$ (10 g l^{-1}) in the absence (A) and presence (B) of urea (20 g l^{-1}).

Precipitation of insoluble calcium carbonate (bars, g l^{-1}), pH changes (circles) and changes

in cell number (boxes, CFU ml^{-1}) were monitored over time (days). Maximum theoretical

level of precipitation is indicated (dotted line). *Right,* electron micrographs of representative

precipitate taken at days 3 and 13.

Figure 7. Crack closure in control mortars and mortars containing non-ureolytic

bacteria. Cracks in mortar specimens are shown immediately post-cracking and after 8

weeks of healing. Cracks were marked with black pen to allow the same region to be

monitored over time. Two independent regions along the top of the mortar were monitored

per sample. Side views show the cracks down both sides of the mortar at 8 weeks. *White*

arrows, complete crack closure. *Black arrows*, incomplete crack closure.

Figure 8. Crack closure in control mortars and mortars containing ureolytic bacteria.

Cracks in mortar specimens are shown immediately post-cracking and after 8 weeks of

healing. Cracks were marked with black pen to allow the same region to be monitored over

time. Two independent regions along the top of the mortar were monitored per sample. Side

views show the cracks down both sides of the mortar at 8 weeks. *White arrows*, complete

crack closure. *Black arrows*, incomplete crack closure.

Figure 9. Recovery of water tightness in mortars after two months of bacteria-based

self-healing. Water flow through mortars containing ureolytic (CG7_3, EM1) or non-ureolytic

(MM1_1, RC1_1) bacteria was determined immediately after cracking and following 8 weeks

of healing. Reference mortars contained no additives; Control mortars contained yeast

extract and calcium nitrate, but no bacteria. Recovery of water tightness was determined as

a percentage relative to the freshly cracked specimen (0%: no change in water flow, 100%:

complete inhibition of water flow). Data is shown for four specimens per condition from two

separate cracking/healing experiments.

Figure 1. Phylogenetic analysis of selected calcite-precipitating isolates and their closest relatives. Yellow boxes, non-ureolytic isolates; orange boxes, isolates with inducible ureolytic activity; pink boxes, isolates that utilize urea as a primary nitrogen source; unfilled boxes, unknown ureolytic ability. The ureolytic potential of closest relatives is not shown. Accession numbers are indicated in parentheses. The percentage of trees in which associated taxa clustered together is shown next to the branches (1000 bootstraps).

Figure 2. Diversity in ureolytic activity across environmental isolates. *Left*, urease test broth inoculated with the strains indicated to the left. *Right*, nutrient agar plates supplemented with phenol red, calcium acetate, and urea were inoculated in the centre with suspensions of the same strains. Pink shading indicates the pH change caused by ammonia release from ureolytic activity.

Figure 3. Crystal formation correlates with pH changes in non-ureolytic and ureolytic bacteria. (A) Non-ureolytic isolate PD1_1 shows localised crystals on the bacterial colony. (B) Ureolytic *S. pasteurii* demonstrates crystal precipitation throughout the media, corresponding to pH changes that occur throughout the media. Arrows indicate $CaCO_3$ crystals.

Figure 4. Regulation of urease activity by environmental nitrogen and urea. Isolates CG6_1 (A) and CG7_3 (B) cells were grown in high or low nitrogen conditions in the presence (+) or absence (-) of urea. Error bars represent standard deviation from 2-3 biological reps with 1-2 technical reps each. Significance was tested using an unpaired t-test (A) and one-way ANOVA followed by unpaired t-test (B). *, $P<0.05$, ***, $P<0.001$ and ****, $P<0.0001$.

Figure 5. Calcite precipitation kinetics and crystal morphology in ureolytic CG7_3 and non-ureolytic MM1_1. The ureolytic strain CG7_3 (A) and the non-ureolytic MM1_1 (B) were grown in LB medium supplemented with urea (20 g l⁻¹) and Ca(OAc)₂ (10 g l⁻¹) and precipitation of insoluble calcium carbonate (bars, g l⁻¹), pH changes (circles) and changes in cell number (boxes, CFU ml⁻¹) were monitored over time (days). Maximum theoretical level of precipitation is indicated (dotted line). *Right,* electron micrographs of representative precipitate taken at day 9.

Figure 6. Comparison of ureolytic and non-ureolytic mechanisms of calcite precipitation in CG7_3. The ureolytic strain CG7_3 was grown in LB medium supplemented with Ca(OAc)$_2$ (10 g l^{-1}) in the absence (A) and presence (B) of urea (20 g l^{-1}). Precipitation of insoluble calcium carbonate (bars, g l^{-1}), pH changes (circles) and changes in cell number (boxes, CFU ml^{-1}) were monitored over time (days). Maximum theoretical level of precipitation is indicated (dotted line). *Right,* electron micrographs of representative precipitate taken at days 3 and 13.

Figure 7. Crack closure in control mortars and mortars containing non-ureolytic bacteria. Cracks in mortar specimens are shown immediately post-cracking and after 8 weeks of healing. Cracks were marked with black pen to allow the same region to be monitored over time. Two independent regions along the top of the mortar were monitored per sample. Side views show the cracks down both sides of the mortar at 8 weeks. *White arrows*, complete crack closure. *Black arrows*, incomplete crack closure.

Figure 8. Crack closure in control mortars and mortars containing ureolytic bacteria. Cracks in mortar specimens are shown immediately post-cracking and after 8 weeks of healing. Cracks were marked with black pen to allow the same region to be monitored over time. Two independent regions along the top of the mortar were monitored per sample. Side views show the cracks down both sides of the mortar at 8 weeks. *White arrows*, complete crack closure. *Black arrows*, incomplete crack closure.

Figure 9. Recovery of water tightness in mortars after two months of bacteria-based self-healing. Water flow through mortars containing ureolytic (CG7_3, EM1) or non-ureolytic (MM1_1, RC1_1) bacteria was determined immediately after cracking and following 8 weeks of healing. Reference mortars contained no additives; Control mortars contained yeast extract and calcium nitrate, but no bacteria. Recovery of water tightness was determined as a percentage relative to the freshly cracked specimen (0%: no change in water flow, 100%: complete inhibition of water flow). Data is shown for four specimens per condition from two separate cracking/healing experiments.

Figure S1. Ammonium chloride concentration vs absorbance standard curve. Ammonium chloride (25-2500 µM) solutions were used as standards to quantify the change in absorbance at 625 nm wavelength (A_{625}) observed using phenol-hypochlorite as described in methods. The linear fit of ammonium chloride concentration versus absorbance used to calculate unknown concentrations is shown by the equation and dashed line.

Figure S2. Diversity in ureolytic activity across environmental isolates. *Left*, urease test broth inoculated with the strains indicated to the left. *Right*, nutrient agar plates supplemented with phenol red, calcium acetate, and urea were inoculated in the centre with suspensions of the same strains. Pink shading indicates the pH change caused by ammonia release from ureolytic activity. MM1_1, although non-ureolytic, caused changes in pH likely due to a stress response to urea which resulted in swarming.

Figure S3. No pH changes are seen in ureolytic isolates when urea is excluded from the media. Nutrient agar plates supplemented with phenol red and calcium acetate were inoculated in the centre with suspensions of the same strains. Only local pH changes characteristic of normal metabolism are seen.

Figure S4. Comparison of crystal localisation in ureolytic strain CG7_3 without (A) and with (B) urea. Ureolytic bacteria precipitate crystals locally in the absence of urea, similar to what is seen in non-ureolytic strains. Arrows indicate $CaCO_3$ crystals.

Figure S5. Calcite precipitation kinetics in ureolytic and non-ureolytic isolates. Isolates were grown in LB medium supplemented with urea (20 g l^{-1}) and CaAoc (10 g l^{-1}) and precipitation of insoluble calcium carbonate (bars, g l^{-1}), pH changes (circles) and changes in cell number (boxes, CFU ml^{-1}) were monitored over time (days).

Figure S6. EDX analyses of precipitates produced by environmental bacteria. *Left,* the position on the precipitate where EDX was conducted (purple boxes). *Centre*, corresponding EDX spectra are shown, with the three peaks of main components labelled below. *Right,* elemental analysis indicating that the three main components (%) of the precipitate where carbon (C), oxygen (O), and calcium (Ca). Minor elements were excluded from the summary tables.

Figure S7. Crystal morphology in ureolytic and non-ureolytic isolates. Isolates were grown in LB medium supplemented with urea (20 g l^{-1}) and Ca(OAc)$_2$ (10 g l^{-1}) and electron micrographs of representative precipitates were taken between days 9-15. Strain names and their ureolytic potential are stated above.

Figure S8. Comparison of crystal morphology in CG7_3 grown in the absence and presence of urea. The ureolytic strain CG7_3 was grown in LB medium supplemented with Ca(OAc)$_2$ (10 g l^{-1}) in the absence (A) and presence (B) of urea (20 g l^{-1}). Electron micrographs of precipitate were taken at days 1,3, 6 and 13. The top panel of each series represents a low magnification view, the bottom panel a high magnification close-up.

Figure S9. Comparison of ureolytic and non-ureolytic mechanisms of calcite precipitation in CG7_3. Ureolytic strain CG7_3 was grown in LB medium supplemented with Ca(OAc)$_2$ (10 g l^{-1}) in the absence (A) and presence (B) of urea (20 g l^{-1}). Precipitation of insoluble calcium carbonate (bars, g l^{-1}), pH changes (circles) and changes in cell number (boxes, CFU ml^{-1}) were monitored over time (days). *Right,* electron micrographs of representative precipitate taken at days 2, 7, 10 and 13.