Resolving heterogeneity of targeted lipid nanoparticles through solution-based biophysical analyses

Hannah C. Geisler[1], Hannah C. Safford[1], Ajay S. Thatte[1], Marshall S. Padilla[1], Elisa Battistini[1], Hannah M. Yamagata[1], Violet M. Ullman[1], Alex Chan[1], Benjamin E. Nachod[1], Anushka Agrawal[1], Maxwell B. Watkins[2], Jesse B. Hopkins[2], Andrew Tsourkas[1], Kushol Gupta[3*], and Michael J. Mitchell[1,4-8*]

[1]Department of Bioengineering, University of Pennsylvania, Philadelphia, PA, USA.
[2]The Biophysics Collaborative Access Team (BioCAT), Department of Physics, Illinois Institute of Technology, Chicago, IL 60616, USA
[3]Department of Biochemistry and Biophysics, Perelman School of Medicine, University of Pennsylvania, Philadelphia, PA 19104, USA
[4]Penn Institute for RNA Innovation, University of Pennsylvania, Philadelphia, PA, USA.
[5]Abramson Cancer Center, Perelman School of Medicine, University of Pennsylvania, Philadelphia, PA, USA.
[6]Institute for Immunology, Perelman School of Medicine, University of Pennsylvania, Philadelphia, PA, USA.
[7]Cardiovascular Institute, Perelman School of Medicine, University of Pennsylvania, Philadelphia, PA, USA.
[8]Institute for Regenerative Medicine, Perelman School of Medicine, University of Pennsylvania, Philadelphia, PA, USA.

*Co-Corresponding authors: kgupta@pennmedicine.upenn.edu; mjmitch@seas.upenn.edu

CORRESPONDING AUTHORS

*Michael J. Mitchell
Associate Professor
Department of Bioengineering
University of Pennsylvania
25 N 38th St
Suite 1014
Philadelphia, PA 19104, USA
Email: mjmitch@seas.upenn.edu

*Kushol Gupta
Research Assistant Professor
Department of Biochemistry and Biophysics
University of Pennsylvania
422 Curie Blvd.
901C Stellar-Chance Building
Philadelphia, PA 19104, USA
Email: kgupta@pennmedicine.upenn.edu

ABSTRACT

Targeted lipid nanoparticles (tLNPs) represent the next frontier in nucleic acid therapeutics, enabling cell-specific delivery through covalent attachment of targeting ligands that drive receptor-mediated uptake. tLNPs are particularly promising for pregnancy-associated applications where precise on-target delivery is required to minimize maternal toxicity and protect fetal health. Yet, their rational design is limited by an incomplete understanding of how tLNP physicochemical properties influence biological performance. Conventional LNPs already exhibit pronounced heterogeneity in size, composition, and RNA loading, which is further amplified in tLNPs by variability in ligand attachment and surface density. Because traditional analytical methods report only ensemble-averaged properties, the nanoscale diversity of tLNPs remains unresolved. Here, we find that tLNP functional behavior is governed by previously inaccessible, structurally distinct tLNP subpopulations that are not captured by bulk measurements. We utilize asymmetric flow field-flow fractionation integrated with in-line UV spectral analysis, light scattering, and synchrotron small-angle X-ray scattering (AF4-UV-DLS-MALS-SAXS) to resolve ligand-dependent tLNP subpopulations that differ in size, shape, composition, and relative abundance. We find that protein conjugation preserves the internal lipid–RNA nanostructure of base LNPs but substantially increases particle heterogeneity, particularly for larger and multivalent targeting ligands. Despite increased heterogeneity, tLNPs functionalized with higher-avidity ligands achieve more effective targeted placental RNA delivery in mice, suggesting that binding avidity can offset the functional consequences of polydispersity. Chemometric SAXS analyses reveal that only SAXS-resolved tLNP subpopulations, not ensemble-averaged parameters, correlate with targeted placental transfection in vivo, whereas bulk-derived physicochemical metrics more strongly associate with nonspecific hepatic delivery. Together, this work harnesses a separation-coupled biophysical platform to resolve previously inaccessible tLNP subpopulations and demonstrates that subpopulation nanoscale structure, rather than bulk-averaged properties, dictates targeted RNA delivery. These insights provide a mechanistic foundation for rational engineering of next-generation precision targeted RNA LNP therapeutics.

1 **MAIN TEXT**
2 **INTRODUCTION**
3
Targeted lipid nanoparticles (tLNPs) are central to the advancement of precision nucleic acid
therapeutics, enabling precise, cell-specific RNA delivery while minimizing systemic toxicity[1–3].
tLNPs are commonly generated through chemical ligation of protein targeting ligands to the LNP
surface, facilitating receptor-mediated endocytosis of LNPs by specific cell types. Despite their
promise, the rational design of tLNPs remains limited by an incomplete understanding of how
tLNP physicochemical properties govern biological behavior. The base LNPs from which tLNPs
are derived exhibit substantial heterogeneity in size, composition, and RNA loading[4–7], and
subsequent protein functionalization steps introduce additional variability in protein attachment
and surface density, yielding complex product mixtures whose true nanoscale diversity remains
unresolved[8] (**Fig. 1a**). Consequently, the inability to directly resolve and quantify tLNP
physicochemical complexity has emerged as a fundamental barrier to the design and deployment
of targeted nucleic acid delivery platforms for in vivo applications that demand strict cell specificity,
such as chimeric antigen receptor (CAR) T cell therapies[9–11], gene editing strategies[12–15], and
gene therapies for obstetric complications[16–18].
18
Common practices for (i) confirming successful protein functionalization and (ii) characterizing
tLNP products rely upon bulk ensemble-average measurement, such as dynamic light scattering
(DLS) and plate-based assays (BCA, fluorescent protein quantification). Traditionally, increases
in LNP hydrodynamic radius (R_h) measured by DLS has been interpreted as evidence of
successful protein functionalization, while plate-based assays provide an estimate of the total
protein incorporated into the final tLNP product. However, these approaches lack the resolution
required to characterize heterogeneous tLNP populations[19,20]. For example, DLS cannot resolve
subpopulations within polydisperse samples[21,22], and calculated R_h measurements
disproportionately reflect larger species[23]. Moreover, DLS assumes that particles are perfectly
spherical, despite recent evidence that LNPs adopt ellipsoidal geometries in solution[24]. Similarly,
plate-based protein quantification assays yield only bulk, ensemble-averaged measurements and
cannot report on particle-level variability in ligand loading or spatial distribution[25,26]. Finally, none
of these protein-detection methods report on internal LNP structure. Thus, existing analytical
strategies obscure the true nanoscale structural and compositional landscape of tLNP
formulations, limiting direct establishment of predictive structure–function relationships between
protein functionalization patterns and biological outcomes.
35
Here, we leverage emerging solution-phase, "plug-and-play" orthogonal biophysical technologies
to resolve the nanoscale architecture and compositional heterogeneity of tLNPs functionalized
with a panel of protein targeting ligands differing in size and valency. Recent advances in
separation-coupled biophysical platforms, including the integration of asymmetric flow field-flow
fractionation (AF4) with synchrotron small-angle X-ray scattering (SAXS), have enabled
nanoscale structural resolution of proteins[27,28] and, more recently, mRNA LNPs[21,22,29–31]. However,
these approaches have not been systematically applied to tLNPs, where protein functionalization
introduces additional layers of compositional and structural heterogeneity, nor have they been
extensively used to directly link tLNP physicochemical features to biological targeting capacity. In
this work, we integrate AF4 with in-line UV–Vis detection, dynamic light scattering (DLS), multi-
angle light scattering (MALS), and SAXS (AF4-UV-DLS-MALS-SAXS) to characterize tLNPs in
solution. This approach enables separation-resolved analysis of co-existing particle populations
and provides complementary measurements of composition (UV–Vis), hydrodynamic size (R_h,
from DLS), molar mass and radius of gyration (M_w and R_g, from MALS), and nanoscale structure
(SAXS). Through chemometric analysis of both UV–Vis spectra and SAXS scattering profiles, we
demonstrate orthogonal resolution of previously inaccessible, distinct tLNP subpopulations and

quantify their relative abundance, size, and structural features. Batch SAXS measurements
establish that protein conjugation preserves the internal lipid–RNA organization of LNPs, while
separation-coupled analyses uncover substantial surface-driven structural heterogeneity that is
not accessible to ensemble methods. This integrated approach thus enables direct resolution of
distinct tLNP subpopulations and their structural descriptors, including R_g, maximum dimension
(D_{max}), and particle morphology.
58
We further demonstrate the functional relevance of this biophysical framework by evaluating
relationships between tLNP physicochemical properties and RNA transfection in a murine model
of pregnancy, a setting where maternal–fetal safety constraints are exceptionally stringent and
effective therapeutic options for obstetric complications remain scarce[32,33]. By evaluating tLNP-
mediated RNA delivery in vitro in placental cells and in vivo in pregnant and nonpregnant mice,
we find that SAXS-resolved tLNP subpopulations show stronger correlation with targeted
placental RNA delivery than ensemble-averaged measurements, whereas ensemble-averaged
parameters instead predict nonspecific hepatic transfection and inflammatory responses.
Together, this work demonstrates a separation-coupled, solution-based biophysical framework to
resolve functionally relevant tLNP subpopulations, define their nanoscale structure, and link these
features to biological outcomes, thereby enabling subpopulation-level structure–function
relationships to guide the rational design of precision RNA tLNP therapeutics for pregnancy
complications and other highly cell-specific in vivo applications.
72
RESULTS
Heterogeneity of tLNPs is unresolved by traditional bulk measurements
LNPs were formulated via chaotic mixing of an organic lipid phase and an aqueous mRNA phase
using polydimethylsiloxane microfluidic devices[34,35]. The base LNP was formulated using the
placenta-tropic Lipid A4[36]. LNPs were formulated encapsulating firefly luciferase (FLuc)
messenger RNA (mRNA) and were subsequently functionalized with one of four targeting proteins
(nanobody, DARPin, F(ab')$_2$ fragments, or antibody) via strain-promoted azide-alkyne
cycloaddition (SPAAC) chemistry as previously described[37–39] (**Supplementary Fig. 1).** All protein
targeting moieties were directed against the epidermal growth factor receptor (EGFR), a receptor
highly expressed in both murine and human placental tissue[38,40].
83
First, traditional LNP characterization techniques, including dynamic light scattering (DLS),
electrophoretic light scattering, and plate-based fluorescent assays were employed to evaluate
LNP physicochemical properties. The base, nontargeted (NT) LNP had a hydrodynamic radius
(R_h) of ~45 nm, a polydispersity index (PDI) of ~0.3, and a neutral ζ-potential around ~10 mV (**Fig.
1b-d, Supplementary Table 1**). As expected, protein functionalization resulted in an increase in
R_h accompanied by changes in ζ-potential. Protein functionalization did not influence LNP PDI as
measured by DLS. Functionalization with smaller protein ligands (nanobody and DARPin)
increased R_h by ~5-6 nm, whereas larger protein ligands (F(ab')$_2$ and antibody) produced greater
increases in R_h (~24–35 nm). DARPin and F(ab')$_2$ tLNPs exhibited reduced but still positive ζ-
potential, while nanobody and antibody tLNPs displayed net negative ζ-potential values. Results
from a potassium cyanide (KCN)-mediated protein quantification assay confirmed that no protein
was present in solution in NT LNPs. All tLNPs had bulk protein concentrations ranging from ~10–
15 ng μL^{-1} (**Fig. 1e**). Changes in physicochemical properties, including R_h and ζ-potential, in
combination with results from the KCN-mediated protein quantification assay, indicated that all
tLNP groups were successfully functionalized with their respective protein. Protein
functionalization did not impact LNP encapsulation efficiency or mRNA concentration. All LNPs
had encapsulation efficiencies ranging from ~95–99%, mRNA concentrations ranging from ~30–
45 ng μL^{-1}, and LNP particle concentrations ranging from ~10^{11}–10^{12} particles per ml (**Fig. 1f-h**).
102

Finally, all tLNPs showed enhanced mRNA delivery relative to NT LNPs when screened in EGFR+
A431 control cells (**Fig. 1i**), further validating successful protein functionalization. Protein addition
did not introduce any detectable cytotoxicity, as none of the LNP formulations exhibited toxicity
across a range of mRNA doses (**Fig. 1j**). In stability studies, all LNPs maintained consistent size
distributions for approximately ten days at 4°C in aqueous buffer before measurable changes
were detected by DLS (**Fig. 1k**). Notably, NT LNPs displayed pronounced increases in size over
time, consistent with aggregation, whereas tLNPs exhibited smaller shifts in hydrodynamic radius,
suggesting improved colloidal stability.
111
Evidence for heterogeneity in tLNPs by SEC-MALS and AUC
Because conventional characterization methods provide limited insight into LNP composition and
structural heterogeneity, size-exclusion chromatography with multi-angle light scattering (SEC-
MALS) was applied to confirm composition of NT LNPs and to probe changes in apparent size
following protein functionalization. While DLS assumes sphericity, MALS, when coupled with UV
and refractive index (RI) detection, provides greater quantitative information on LNP composition,
mass, and spatial extent[41]. Moreover, pairing MALS with SEC enables elution-resolved
determination of physicochemical properties, allowing interrogation of heterogenous systems that
conventional SEC or DLS alone cannot access[42].
121
UV chromatograms from SEC provide the relative abundance of species eluting over the course
of the separation, with each sample displaying a predominant peak between 22–30 min
corresponding to the bulk LNP population (**Supplementary Fig. 2a-g**). Molar mass (M_w) profiles
and nucleic acid fraction were determined leveraging 18-angle light scattering and RI detection,
with UV measurements corrected for LNP Mie scattering as previously described[41]. Conjugate
analysis enabled determination of mRNA concentration in NT LNPs, confirming the expected two-
component lipid-RNA composition (~58 MDa total, ~2% RNA mass) (**Supplementary Fig. 2a-b**).
However, because tLNPs incorporate a third material component (protein), the standard two-
component conjugate model cannot be applied, preventing direct measurement of RNA content.
131
Assuming ~90 sites of conjugation on a base NT LNP of ~58 MDa, added protein mass of
anywhere between 1.4 to 13.5 MDa could be expected, comprising anywhere from 2% to 19% of
the total protein mass fraction (**Supplementary Table 2**). Mass profiles of NT LNPs displayed
sloping molar masses, ranging from ~50 to ~100 MDa across the elution peak (**Supplementary
Fig. 2a**), consistent with the inherent polydispersity of NT LNPs. Comparison of chromatographic
profiles showed that tLNPs eluted earlier than NT LNPs (**Supplementary Fig. 2c**), indicating
increased apparent LNP size after protein functionalization. Using mass-averaged *dn/dc* values
assuming 100% protein-conjugation, tLNPs mass profiles were calculated and found to be
comparable to NT LNPs (**Supplementary Fig. 2d-g**); discrete subpopulations were not evident.
The observed broad, sloped mass profiles across the unimodal elution peaks of all LNPs suggests
substantial heterogeneity that chromatography alone cannot fully resolve. This substantial
heterogeneity was further substantiated by sedimentation/flotation velocity analytical
ultracentrifugation (SV/FV-AUC) (**Supplemental Fig. 3a-c**), which was applied to determine
whether these apparent subpopulations could be separated by their density properties. Although
SV-AUC showed small increases in sedimentation coefficients for tLNPs relative to NT LNPs
(**Supplementary Fig. 3d**), these shifts did not correspond to discrete, resolvable species,
indicating that SV-AUC also lacked the resolution needed to fully deconvolve tLNP heterogeneity.
149
150 **Batch SAXS reveals conserved internal structure with increased tLNP structural variability**
151 Traditional batch SAXS measurements were made to assess tLNP internal structure via their
152 Bragg peak features, and to determine whether protein functionalization affects internal structure.

153 Although protein attachment is generally assumed not to influence internal lipid–RNA
154 arrangement, this has not, to our knowledge, been directly demonstrated.
155
The SAXS scattering profiles of mRNA-loaded LNPs are distinguished by a characteristic first-
order Bragg peak at scattering vectors where (q) $\approx$ 0.1–0.15 Å^{-1} (d $\approx$ 41.9–62.8 Å), reflecting a
highly ordered internal lattice arising from RNA–lipid interactions[43,44] (**Fig 2a, Supplementary**
Fig. 4a-**b**). The Bragg region of each scattering profile was analyzed using multi-Lorentzian peak
fitting[45], which separates the sharp internal-ordering signal from disorder on larger length scales.
This approach enabled quantitative extraction of peak width (full width at half maximum, FWHM),
peak intensity (I_p), and integrated area[45–47] (**Supplementary Table 3**). NT LNPs exhibited a first-
order Bragg peak at q $\approx$ 0.12 Å^{-1}, whereas tLNPs displayed similar peaks at q $\approx$ 0.11 Å^{-1},
consistent with the characteristic lattice spacing of lipid–RNA packing (**Fig. 2b**). The FWHM of
the Lorentzian fit serves as a measure of structural coherence: narrower peaks correspond to
well-defined ordering, whereas broader peaks correspond to more disordered correlations[48].
Across all formulations, the Bragg peaks remained narrow, indicating preservation of internal
structure following protein functionalization. Specifically, NT LNPs exhibited a FWHM of ~0.045 ±
0.002, while nanobody, DARPin, F(ab')$_2$, and antibody tLNPs showed FWHMs of ~0.038 ± 0.004,
~0.039 ± 0.001, ~0.038 ± 0.004, and ~0.038 ± 0.001, respectively. The comparison of the area of
the two respective Lorentzian peaks in the fit provides a relative measure of the proportion of
order to disorder in the internal structure. In all cases except the antibody tLNP sample, these
proportions are similar. The proportion of disorder is more pronounced in the antibody tLNP
formulation, however, it is not clear how much of this is due to elevated heterogeneity.
175
While Bragg peak features remain well conserved throughout the samples, the lower-q Porod
region of the scattering profiles showed marked differences when superposed[47] (**Supplementary**
Fig. 4c). Although the Porod regime is sensitive to interfacial characteristics and surface
heterogeneity, in ensemble-averaged batch SAXS these features reflect convolution of
heterogeneous particle populations and therefore cannot be unambiguously assigned to specific
structural species. As such, robust interpretation of these parameters is limited in batch
measurements by sample heterogeneity.
183
AF4-UV-DLS-MALS-SAXS resolves ligand-dependent tLNP polydispersity and
compositional heterogeneity
To better resolve and study tLNP subpopulations, an analytical platform comprised of AF4
separation in-line with multiple modalities of biophysical analysis was applied: (i) in-line UV-Vis
diode array detection, (ii) DLS, (iii) MALS, and (iv) synchrotron SAXS (**Supplementary Fig. 5).**
This AF4-UV-DLS-MALS-SAXS approach leverages the high-flux, low-q capabilities of an
advanced synchrotron source with the superior size resolution of AF4, enabling hydrodynamic
separation and structural analysis to be performed in-line[21]. While SEC-SAXS has been used to
characterize LNP systems[24], AF4-SAXS has more recently emerged as a powerful approach for
resolving the structural features of standard mRNA LNP formulations[21,29–31,49]. Because SEC
separation is constrained by pore accessibility, LNPs and higher-mass assemblies are expected
to elute near the void volume with limited resolution. In contrast, AF4 separates particles based
on diffusion under an applied crossflow, enabling size-resolved analysis of nanoparticle-scale
species without the exclusion limitations inherent to SEC. Building on these recent advances, the
present work represents, to our knowledge, the first application of integrated AF4-UV-DLS-MALS-
SAXS for real-time, in-line characterization of complex tLNP formulations. AF4 provides gentle,
size-based fractionation, while UV-Vis, DLS, MALS, and SAXS collectively report compositional,
hydrodynamic, and structural parameters across eluting fractions. Integrating all four modalities
of analysis in-line enables a comprehensive view with orthogonal validation of tLNP heterogeneity
in solution otherwise inaccessible to individual measures and bulk measurements.

204
AF4–UV fractograms provided substantially greater resolving power than SEC, revealing complex
elution behavior across all LNP formulations. All samples exhibited a dominant peak between
~28–32 min corresponding to the primary LNP population, accompanied by wavelength-
dependent variations indicative of compositional heterogeneity. UV–Vis heat maps showed strong
absorbance at 210 nm across all samples, consistent with lipid-dominated absorbance and
scattering, along with a narrower feature at 260 nm associated with encapsulated RNA **(Fig. 2c)**.
Absorbance at 280 nm increased progressively from NT LNPs to antibody-functionalized tLNPs,
reflecting increasing protein incorporation. Analysis of the 260 nm trace revealed a bimodal RNA-
associated peak for NT LNPs, suggesting the presence of at least two RNA-enriched
subpopulations **(Fig. 2d–f)**, whereas tLNPs exhibited broader, asymmetric, and largely unimodal
profiles consistent with overlapping species. Correspondingly, the 260:280 absorbance ratio
decreased systematically from NT to antibody tLNPs, consistent with increasing protein content
(Fig. 2g). Together, these wavelength-dependent changes indicate that the AF4 elution profiles
contain overlapping LNP populations that differ not only in size, but also in RNA-to-protein
composition, motivating subsequent chemometric decomposition of both the UV–Vis and SAXS
datasets.
221
To more rigorously resolve these overlapping contributions, multivariate chemometric analysis
was applied to the full AF4–UV diode array dataset (**Supplementary Fig. 6**). Singular value
decomposition (SVD)[50] and evolving factor analysis (EFA)[51] indicated the presence of
compositionally distinct components within each fractogram, exceeding what could be inferred
from individual wavelength traces alone. Multivariate curve resolution (MCR-ALS) decomposed
the data into resolved concentration profiles and corresponding UV–Vis spectra, enabling
separation of lipid-dominated, RNA-associated, and protein-associated components across the
elution time domain. These results confirm that NT LNPs contain at least two RNA-enriched
populations with distinct elution behavior, while protein-functionalized tLNPs display broader,
partially overlapping populations characterized by increased protein contribution and reduced
RNA-to-protein ratios. Although RNA and protein together comprise a minor fraction of total LNP
mass, their strong and spectrally distinct UV absorbance enables robust resolution by multivariate
analysis. Absolute absorbance intensities, particularly at shorter wavelengths, may be influenced
by lipid-derived UV Mie scattering and should therefore be interpreted in terms of relative optical
contributions rather than direct mass fraction. Importantly, these UV-derived components define
the compositional heterogeneity present across the AF4 elution window and provide the basis for
interpreting the SAXS-resolved components as occurrences of overlapping LNP populations that
differ in RNA and protein content.
240
Elution behavior and variations in R_h by in-line DLS and R_g and mass by MALS were consistent
with the compositional heterogeneity identified by UV chemometric analysis, indicating that the
overlapping RNA- and protein-associated populations also differ in hydrodynamic size and mass.
In contrast to SEC, where larger species co-elute near the exclusion limit, AF4 separates particles
based on diffusion, such that larger species elute later. Accordingly, three of four tLNP
formulations eluted later than NT LNPs, consistent with increased particle sizes (**Fig. 2e**).
Nanobody and DARPin tLNPs showed modest R_h increases but clear increases in R_g and molar
mass (M_w), consistent with their relatively small (<20 kDa) protein ligands (**Fig. 2f,h-j,**
Supplementary Fig. 7). In contrast, F(ab')$_2$ and antibody tLNPs exhibited continuous increases
in R_h across the elution peak, reflecting substantial heterogeneity and access to size regimes that
would be partially excluded in SEC-based separations. Antibody tLNPs displayed an R_h plateau
followed by a secondary increase, suggesting a more uniform subpopulation followed by a larger,
potentially aggregated population. F(ab')$_2$ tLNPs exhibited the broadest size distribution, with R_h
values spanning ~30–70 nm. All tLNPs contained minor populations of large particles, providing

a tractable explanation for why bulk DLS measurements yield overestimated hydrodynamic radii
relative to the R_h distributions observed across AF4 fractograms. Consistent with these size
distributions, MALS-derived R_g and molar mass increased substantially across all tLNPs (**Fig. 2i-**
j). DARPin and F(ab')$_2$ tLNPs exhibited mass increases of ~50 MDa, while nanobody and antibody
tLNPs increased by ~100 MDa (**Fig. 2j**). Steep, sloping R_h and mass trajectories, combined with
broad asymmetric elution peaks, suggest that F(ab')$_2$ and antibody tLNPs exhibit the greatest
polydispersity, corroborated by M_w/M_n values (**Fig. 2k**). In-line DLS and AF4-MALS derived
physicochemical parameters are summarized in **Supplementary Table 4**.
263
Taken together, the AF4–UV data indicate that multiple LNP populations with distinct RNA-to-
protein composition co-elute within the main fractogram peak. This compositional heterogeneity
provides a direct rationale for subsequent SAXS chemometric decomposition, as the ensemble
scattering signal arises from these overlapping populations. In this framework, UV chemometrics
resolves compositional contributions across the elution window, while SAXS chemometrics
resolves the corresponding structural contributions. Although baseline resolution is not achieved,
AF4-MALS provides substantially improved separation of heterogeneous mixtures compared to
SEC-MALS and DLS alone. Together, these data indicate that AF4-resolved tLNP heterogeneity
is manifested across composition, size, and mass, enabling linkage of compositional variability to
structural heterogeneity that is obscured in ensemble-averaged measurements.
274
SAXS component analysis reveals distinct structural tLNP subpopulations
As indicated by UV and light scattering analyses (**Fig. 2**), the AF4 elution profiles showed broad
multimodal peaks for all formulations (**Fig. 3a**), reflecting overlapping LNP populations that differ
in RNA and protein content and that cannot be resolved by elution time alone. Differences in peak
width and shape were consistent with the hydrodynamic heterogeneity observed with in-line light
scattering, with F(ab')$_2$ and antibody tLNPs exhibiting the broadest and most asymmetric elution
profiles. To resolve structural subpopulations contributing to the SAXS signal across the AF4
elution window, we performed component analysis using SVD and EFA as implemented in
REGALS[52,53]. SVD was first used to estimate the number of statistically significant scattering
components present; this analysis indicated that the SAXS signal cannot be adequately described
by a single particle population. EFA then identified the elution boundaries over which each
component contributed measurably to the total scattering, thereby identifying partially overlapping
populations contributing to the scattering signal. Finally, component profiles were extracted to
obtain physically consistent scattering curves for each subpopulation[53]. This approach enabled
robust separation of overlapping signals and yielded physically consistent SAXS profiles
corresponding to co-existing LNP subpopulations rather than purely mathematical
decompositions. In this framework, UV chemometrics and light scattering analysis define
compositional heterogeneity across the elution window, while SAXS chemometrics resolves the
corresponding structural heterogeneity arising from the same AF4-resolved populations.
294
EFA identified evolving scattering contributions across each elution peak (**Fig. 3b**). In the selected
ranges, all formulations exhibited at least two evolving populations, except for F(ab')$_2$ LNPs, which
exhibited three evolving subpopulations, which is consistent with the increased compositional and
structural heterogeneity inferred from UV and light scattering measurements. The EFA-defined
regions were broader for DARPin, F(ab')$_2$, and antibody tLNPs, consistent with greater size and
mass heterogeneity. SVD quantified the number of statistically significant scattering components
present in each dataset (**Fig. 3c**). In all samples, the first component (C1) dominated the signal,
indicating one principal structural population. All LNP formulations showed non-negligible
secondary components (C2), and for F(ab')$_2$ tLNPs, a non-negligible third component (C3),
suggesting the presence of minor but distinct structural contributors in all formulations.
305

The volatility of ratio (V_r) metric was then used to substantiate the statistical uniqueness of the SAXS data (**Fig. 3d, Supplementary Fig. 8**). The V_r parameter reports the variability in the ratio of scattering intensity between two profiles, quantifies differences between scattering profiles across the q-range selected, and is advantageous relative to other methods of profile comparison, especially in regimes of weaker signals[54]. In V_r matrices, lower V_r values (yellow) represent more similar profiles and higher V_r values (red) represent more distinct curves. V_r matrices of tLNPs revealed structurally distinct scattering profiles between the first, second, and third components (C1-C3), supporting the interpretation that these components represent distinct scattering subpopulations rather than numerical artifacts. These results support that the resolved components are statistically independent and non-redundant, rather than arising from overfitting of the SAXS data. Higher V_r values observed for F(ab')$_2$ and antibody tLNPs reflect comparatively increased differences when compared to the components of the other particles.

V_r matrices provided additional insight into structural differences among the resolved SAXS components. For NT LNPs, C1 most closely resembled the peak-averaged scattering profile, indicating that it is most consistent with the dominant structural contribution. In contrast, for nanobody, DARPin, and antibody tLNPs, the C2 showed the closest correspondence to the average profile, suggesting a shift in the dominant structural contribution following protein functionalization, indicating that the relative contribution of LNP subpopulations shifts with ligand incorporation. F(ab')$_2$ tLNPs exhibited the greatest heterogeneity: C3 best matched the peak-averaged profile, followed by the C2, while C1 was the most structurally distinct.

Across all extracted component scattering profiles (**Fig. 3e–h**), Bragg features were not sharply defined. This is likely due to peak broadening and sample dilution inherent to the in-line AF4-SAXS workflow and does not indicate a loss of internal lipid–RNA ordering, which was supported by batch SAXS measurements. Instead, the REGALS-derived profiles emphasize differences in the low-q and mid-q regions, reflecting variations in particle size and polydispersity among components, where low-q differences primarily reflect size and mass distribution, and mid-q differences reflect internal structural organization. These differences were most pronounced for F(ab')$_2$ and antibody tLNPs, reinforcing the conclusion that larger targeting ligands produce broader distributions of nanoparticle morphologies.

The high-q region of each SAXS profile was then analyzed using Porod scaling to probe short-length-scale density correlations. In contrast to ensemble-averaged batch SAXS, where Porod behavior reflects convolution of heterogeneous populations, AF4- and SVD-resolved profiles enabled interpretation of Porod scaling at the subpopulation level (**Supplementary Table 5**). Porod exponents for all LNP formulations fall predominantly in the range where m ≈ 3.0–3.8, consistent with compact particles exhibiting surface-fractal scattering rather than ideal Porod behavior. This is consistent with rough or diffuse interfaces, which would be expected due to lipid heterogeneity, heterogenous RNA–lipid organization within LNP interiors, and heterogenous protein functionalization. No formulation displays sustained mass-fractal behavior, although isolated SVD-resolved components approach m ≈ 2.5, consistent with locally disordered internal domains rather than globally fractal particles.

Determination of model-independent structural parameters of distinct tLNP subpopulations

Having resolved the principal scattering components for each formulation, we next quantified the underlying structural properties for these subpopulations. Classical Guinier analysis, which directly ascertains the particle radius of gyration (R_g) from the lowest q regime of recorded scattering, is often challenging for LNPs because their large real-space dimensions typically require low measurable q that is inaccessible in standard experimental configurations[24,55,56]. As a

result, most LNP SAXS datasets lack a true Guinier region and may not always provide reliable
R_g values depending on q-range and sample heterogeneity. However, the low-q coverage
afforded by this AF4-SAXS experimental configuration enabled Guinier analysis for components
that satisfied standard linearity criteria. Importantly, these Guinier analyses were performed on
component-resolved SAXS profiles, reducing the impact of population heterogeneity that typically
obscures low-q behavior in ensemble measurements. By combining AF4 separation with SAXS
component analysis, these measurements enable structural parameters to be assigned to
subpopulations that would otherwise be obscured in ensemble-averaged scattering data.
365
For NT, nanobody, and DARPin LNPs, both C1 and C2 components produced linear Guinier
regions (**Fig. 4a**). For NT LNPs, C1 yielded an R_g of 132.4 ± 18.4 Å, while C2 exhibited a larger
R_g of 284.6 ± 8.6 Å (**Supplementary Table 6**). Nanobody tLNP C1 and C2 had R_g values of 188.6
± 8.0 Å and 219.9 ± 13.4 Å, respectively, and DARPin tLNPs produced comparable R_g values of
175.9 ± 11.6 Å and 177.3 ± 7.7 Å. For the $F(ab')_2$ and antibody tLNPs, only C3 and C2,
respectively, had measurable Guinier regions; additional components could not be analyzed by
Guinier methods due to their large size or the absence of a well-defined low-q linear regime within
the measured range. The $F(ab')_2$ tLNP C3 component yielded an R_g of 190.4 ± 18.1 Å, while the
antibody tLNP C2 exhibited an R_g of 232.9 ± 18.4 Å. The observed increases in R_g are consistent
with both larger particle dimensions and broader mass distributions in protein-functionalized
LNPs. These differences in R_g across subpopulations are consistent with the presence of
structurally distinct subpopulations identified by SAXS chemometric analysis and with
compositional heterogeneity inferred from UV and light scattering measurements.
379
The P(r) function represents the distribution of all intraparticle distances and is used to extract the
real-space size parameters R_g and the maximum dimension (D_{max}), providing complementary,
global size estimates that are less sensitive to limitations in Guinier analysis and provide a more
complete description of particle size distributions[56]. NT, nanobody, and DARPin LNPs exhibited
more compact, unimodal P(r) curves, consistent with smaller ellipsoids (**Fig. 4b-d**). $F(ab')_2$ and
antibody tLNPs displayed broader P(r) profiles with longer maximum dimensions, consistent with
greater structural heterogeneity. All parameters derived from Guinier analysis and P(r) analysis
using GNOM are summarized in **Supplementary Table 6**.
388
We also calculated a shape factor (D_{max}/R_g) for each component (**Fig. 4e, Supplementary Table
7**), where ideal spheres have values of 2.58 and prolate ellipsoids have values of 3.0[24,57]. NT
LNPs exhibited shape factors consistent with ellipsoidal geometries, in agreement with previous
reports of LNP morphology[24,58]. In contrast, tLNPs trended downward in shape factor with
increasing ligand size, approaching more isotropic values. This shift may reflect preferential
protein decoration on the elongated axes of ellipsoidal particles, effectively "rounding" their
apparent shape by evening out surface mass distribution. Finally, the algorithm density from
solution scattering (DENSS) can be applied to LNP SAXS data to generate low-resolution electron
density reconstructions consistent with the scattering data[58] (**Fig. 4f-j**). Consistent with trends
observed in P(r) analyses and previous reports of shape, NT LNPs were anisotropic ellipsoids.
To define length, width, and height independent of the arbitrary initial orientation of DENSS
reconstructions[59], density maps were aligned to their principal axes prior to dimensional analysis.
Determined dimensions from DENSS showed that tLNPs varied substantially in their
reconstructed dimensions across subpopulations (**Supplementary Table 8**). Relative to NT
LNPs, all targeted formulations exhibited measurable shifts in one or more principal axes,
consistent with ligand-dependent differences in particle morphology. Larger ligands ($F(ab')_2$ and
antibody) were associated with components exhibiting greater size variability, with some
becoming more elongated while others approached more isotropic, sphere-like dimensions,

consistent with increased structural heterogeneity inferred from SAXS component analysis and
the previous changes observed in the shape factor.
409
Biophysical-biological correlations identify structural subpopulations governing tLNP
targeting to the placenta
Designing effective tLNP nucleic acid delivery systems requires parameters that reliably predict
delivery outcomes, yet such predictors remain largely undefined due to limited analytical
resolution. To determine whether high-resolution biophysical measurements can fill this gap, we
evaluated our tLNP library in vitro in immortalized placental cells and in vivo in pregnant mice and
nonpregnant mice. All targeting ligands used in this study were anti-human EGFR proteins.
Because human and mouse EGFR differ in their binding interfaces, the anti-EGFR protein ligands
used in this work display negligible affinity for endogenous mouse EGFR, except in tissues with
extremely high receptor density[60]. The placenta, which expresses abundant EGFR and is directly
exposed to maternal circulation[38,61,62], therefore represents the primary tissue in which ligand-
receptor engagement would be expected. This design ensured a model where pregnancy-specific
targeting could be cleanly resolved from baseline biodistribution.
423
When screened in human placental trophoblasts, antibody tLNPs showed the greatest early (1 h,
4 h timepoints) cellular accumulation compared to NT LNPs and all other tLNP groups (**Fig. 5a-**
b, Supplementary Fig. 9). By 24 h, antibody tLNP accumulation remained significantly more
enriched than NT LNPs, however both F(ab')$_2$ and antibody tLNPs produced significantly higher
mCherry expression relative to the NT control (**Fig. 5c-d**). LNPs were then formulated with FLuc
mRNA and injected intravenously into gestational day E16 pregnant and nonpregnant mice and
luminescence was analyzed 6h later (**Fig. 5e-f, Supplementary Figs. 10-12**). In pregnant mice,
NT LNPs delivered luciferase mRNA primarily to the liver and spleen (**Fig. g-h**), whereas all tLNPs
showed significantly reduced hepatic and splenic delivery relative to NT LNPs. F(ab')$_2$ tLNPs
exhibited significantly enhanced luciferase expression in the placenta compared to NT LNPs,
consistent with in vitro performance. Antibody tLNPs demonstrated enhanced placental mRNA
delivery compared to PBS treated mice but did not reach statistical significance compared to NT
LNPs. None of the formulations showed detectable fetal transfection, consistent with previous
reports (**Fig 5i-j**). Overall luminescence in the major organs was higher in nonpregnant mice than
pregnant mice (**Fig. 5k-m**). In nonpregnant mice, all formulations localized predominantly to the
liver and spleen as expected. Luminescence signals in the liver were comparable across groups,
except for antibody tLNPs, which showed reduced hepatic delivery relative to NT LNPs. No
significant differences were observed between NT LNPs and tLNPs in the liver or spleen,
consistent with the diminished contribution of ligand-mediated selectivity in the absence of EGFR-
rich placental tissue.
444
We next correlated measured physicochemical parameters with luminescence outputs using
Spearman analysis, defining $|r| > 0.6$ as a medium-to-strong association (**Fig. 5n-q,**
Supplementary Table 9). Placental luminescence showed a strong positive correlation with the
area under the curve (AUC) of the batch SAXS Bragg peak, R_h determined by in-line DLS, and
R_g and mass determined by MALS (**Fig. 5n**). In contrast, batch SAXS peak intensity (I_p), AF4-
MALS PDI, and the 260:280 UV-Vis ratio exhibited strong negative correlations. Notably,
benchtop protein quantification measurements did not correlate with placental delivery, indicating
that simple estimates of total ligand content fail to capture functionally relevant ligand decoration.
SAXS-determined R_g and D_{max} of C1 correlated positively with placental luminescence, whereas
the C1 shape factor correlated negatively, suggesting that a specific, perhaps more isotropic,
subpopulation within the tLNP population contributes most strongly to placental targeting. These
in vivo correlations were corroborated by in vitro measurements of tLNP binding affinity
(**Supplementary Fig. 13a-b, Supplementary Fig. 14**) and inhibition of receptor-mediated

endocytosis (**Supplementary Fig. 13c**), followed by biophysical correlation analysis
(**Supplementary Fig. 13d-f, Supplementary Table 10**). Consistent with in vivo placental
targeting, SAXS-determined R_g, $D_{max,}$ and the shape factor of C1 showed the strongest correlation
with tLNP binding to EGFR-expressing placental cells, and both C1 and C2 parameters correlated
with inhibition of tLNP-mediated mRNA delivery upon EGFR blockade.

In pregnant mice, hepatic luminescence correlated positively with standard DLS-derived PDI and
batch SAXS peak intensity (I_p) and negatively with standard DLS-derived R_h, peak full width half
maximum (FWHM) and in-line DLS-derived R_h (**Fig. 5o**). SAXS-derived R_g and D_{max} of the
average profile also correlated positively with hepatic delivery, and the average shape factor
correlated negatively, indicating that nonspecific liver delivery is influenced by parameters of the
global particle properties rather than by parameters of specific subpopulations. In nonpregnant
mice, hepatic luminescence correlated positively with batch SAXS I_p and the 260:280 ratio and
negatively with batch SAXS AUC, in-line DLS R_h, and MALS-derived R_g and mass (**Fig 5p**).
Luminescence also showed negative correlations with SAXS-derived average-population R_g and
C1 D_{max}, and positive correlations with the shape factors of both the average and C1 populations.
Collectively, these trends support a coherent model: in pregnant mice, the EGFR-rich placenta
enables ligand-mediated targeting, whereas in nonpregnant mice, all LNP subpopulations,
including ligand-decorated species, default to hepatic accumulation and subsequent transfection.
These findings further suggest that residual nonspecific liver delivery is dictated primarily by bulk
physicochemical properties rather than by discrete structural subpopulations (**Fig. 5q**).

Biophysical-toxicological correlations reveal bulk LNP populations and tLNP
subpopulations drive differential acute cytokine responses
We next evaluated whether biophysical parameters were associated with systemic toxicity by
measuring serum cytokines (C3a, TNF, IFN-γ, IL-6) and liver enzymes (ALT, AST) in pregnant
(**Fig. 6a**) and nonpregnant (**Fig. 6b**) mice. In pregnant mice, nanobody tLNPs elicited significantly
elevated C3a levels compared to PBS controls, indicating complement activation. Antibody tLNPs
increased TNF and IL-6 and significantly elevated IFN-γ, whereas NT LNPs and DARPin tLNPs
produced significantly higher AST levels compared to PBS. Notably, F(ab')$_2$ tLNPs demonstrated
the most favorable toxicity profile in pregnant mice, with AST levels significantly lower than NT
LNPs and no significant increases in any cytokine observed. In nonpregnant mice, nanobody,
DARPin, and F(ab')$_2$ tLNPs produced significantly higher C3a levels compared to PBS.
Nanobody, F(ab')$_2$, and antibody tLNPs significantly elevated TNF relative to PBS, with F(ab')$_2$,
and antibody tLNPs exceeding NT LNP levels. Antibody tLNPs further induced higher TNF levels
compared to F(ab')$_2$ tLNPs. DARPin, F(ab')$_2$, and antibody tLNPs all showed significantly
increased IFN-γ levels compared to both PBS and NT LNP treated mice, and antibody tLNPs
produced the highest IFN-γ induction among all tLNP formulations. Antibody tLNPs additionally
elevated AST relative to both PBS and F(ab')$_2$ tLNPs. No significant differences in ALT were
observed in either pregnant or nonpregnant mice.

When the Spearman correlation was applied to cytokine data, several consistent structure–toxicity
relationships emerged (**Fig. 6c-g, Supplementary Tables 11-12**). In pregnant mice, cytokine
induction (C3a, TNF, and IFN-γ) correlated predominantly with subpopulation-specific features,
including positive correlations with SAXS-derived R_g and D_{max} of C1 components and negative
correlations with their shape factors (**Fig. 6c-d**). Notably, while C1 most strongly correlated with
placental luminescence, C3a levels correlated with C2, suggesting the potential existence of a
secondary ligand-engaging subpopulation that activates the complement cascade. In addition,
TNF correlated negatively with the 260:280 ratio, and TNF, IFN-γ, and AST positively correlated
with C1 parameters, suggesting that the structurally defined targeted subpopulation responsible
for placental RNA delivery also contributes to acute cytokine induction. In contrast, IL-6 in

pregnant mice had strong correlation with average R_g, D_{max}, and shape factor (**Fig. 6e**), which is
in agreement with hepatic luminescence correlations, indicating that the classic IL-6 responses
often associated with LNP delivery are likely associated with global, ensemble-averaged
nanoparticle properties.

The structure-toxicity correlation landscape shifted markedly in nonpregnant mice (**Fig. 6f-g**). TNF
again showed positive correlation with C1 parameters and negative correlation with the 260:280
ratio, consistent with LNP-mediated mRNA delivery by the C1 subpopulation. However, IL-6
switched polarity relative to pregnancy, now correlating positively with the R_g and D_{max} of C1 rather
than with bulk parameters, indicating a switch from global nanoparticle-driven IL-6 production to
subpopulation-specific delivery in the liver. C3a and IFN-γ displayed mixed correlations involving
both individual component and average profiles, reflecting contributions again from both targeted
subpopulations and the averaged population. Features derived from Lorentzian analysis of SAXS
profiles and AF4-MALS measurements also contributed to cytokine associations: batch SAXS I_p
remained negatively correlated with cytokine production across pregnant and nonpregnant mice,
FWHM lost its pregnancy-specific positive correlation with IL-6, and both in-line DLS R_h and
MALS-derived R_g and mass showed stronger positive correlations in nonpregnant mice.

DISCUSSION
Despite rapid advances in targeted RNA delivery, the rational engineering of tLNP systems has
remained constrained by the lack of analytical tools capable of resolving the structural
heterogeneity that shapes in vivo performance.[20] In this work, we move beyond ensemble-
averaged characterization by integrating AF4-UV-DLS-MALS-SAXS with component-resolved
scattering analysis to dissect how ligand attachment reshapes LNP structure, polydispersity,
morphology, and functional performance at the subpopulation level, providing enhanced
resolution of features that are not accessible by ensemble-averaged methods. This approach
enables parallel resolution of compositional heterogeneity (UV chemometrics and light scattering)
and structural heterogeneity (SAXS component analysis) across the same AF4-resolved
populations.

We find that protein conjugation does not substantially perturb the internal lipid-RNA
nanostructure of LNPs but instead remodels their external architecture. Although ligand
attachment is generally assumed to leave internal organization intact, this assumption has not
previously been directly verified. The preservation of internal order across all tLNPs is consistent
with functional differences that arise from changes in external surface composition and geometry
rather than from disruption of core assembly. At the same time, ligand attachment dramatically
amplifies the intrinsic heterogeneity of LNP formulations, particularly for larger and multivalent
proteins. While conventional bulk techniques, such as DLS and SEC-MALS, yield only ensemble-
averaged descriptors, AF4-UV-DLS-MALS-SAXS resolves overlapping ligand-dependent tLNP
subpopulations with distinct mass, size, and structural features, establishing population-level
heterogeneity as a defining consequence of protein functionalization.

A central finding of this work is that ligand decoration remodels LNP geometry, shifting particles
from prolate ellipsoid towards increasingly isotropic morphologies as ligand size increases.
Leveraging the extended low-q range afforded by our AF4-UV-DLS-MALS-SAXS experimental
configuration, we perform Guinier and P(r) analyses that are often challenging for LNPs due to
insufficient q-range[54,55] which enables reliable extraction of R_g, D_{max}, and shape factor for
individual fraction-resolved tLNP subpopulations. Analysis of the resulting shape factor (D_{max}/R_g),
as defined in the main text, reveals a ligand-size–dependent reduction in particle anisotropy,
suggestive of preferential ligand decoration along the elongated axes of the nanoparticle. This
hypothesis aligns with the broader concept that LNP elongation may facilitate cell-surface

interactions[63–65] and that changes in LNP morphology impact RNA delivery[66,67]; protein decoration
on these axes could reorganize apparent external morphology and enhance target-cell
engagement[68]. DENSS reconstructions further support these findings, showing that tLNPs differ
from NT LNPs through expansions or contractions along one or more axes, with larger ligands
producing greater inter-component variability and, in some cases, more isotropic density
envelopes. Our results suggest a mechanistic model in which ligand attachment not only
increases particle size but also reshapes external nanoparticle morphology, generating
structurally distinct subpopulations, each of which contributes differently to biological targeting
and LNP-mediated RNA delivery.

A second, critical finding of this study is that tLNP functional behavior is driven by biophysically
defined tLNP subpopulations rather than by bulk-average LNP properties, as revealed by
correlations between subpopulation-resolved biophysical parameters and biological outcomes.
To our knowledge, this represents the first demonstration that only specific, structurally defined
tLNP subpopulations, not ensemble-average properties, correlate with in vivo targeted mRNA
delivery. Specifically, targeted placental mRNA delivery correlates most strongly with the R_g, D_{max},
and shape factor of C1 components, whereas ensemble-averaged parameters instead predict
nonspecific hepatic transfection. Cytokine induction follows a similar pattern in pregnant mice:
TNF and IFN-γ track with C1 population features, whereas IL-6 correlates with ensemble-
averaged values. When the placental target is absent, mRNA delivery and cytokine correlations
shift toward a mixture of individual components and bulk metrics, reflecting simultaneous
contributions from ligand-decorated populations and the global LNP population. These results
indicate that targeted delivery is likely mediated primarily by one or more structurally and
compositionally defined subpopulations rather than by the entire heterogeneous ensemble. This
interpretation is consistent with the intrinsic inefficiency of LNP formulations, in which only a
fraction of LNPs encapsulate RNA[19,69], and only a subset of those are successfully decorated with
targeting ligands[70]. Therefore, the biologically active tLNP species (those containing both RNA
and protein ligand) are likely a small subset within the bulk formulation. These findings point to a
clear next step for the field: the fractionation and isolation of discrete tLNP subpopulations to
directly interrogate their functional contributions. Enriching or purifying these subpopulations may
significantly improve therapeutic performance and reduce off-target effects, marking a conceptual
shift from bulk formulation optimization toward subpopulation-level nanoparticle engineering.

An important implication of this subpopulation-driven framework is that increased structural
heterogeneity does not necessarily preclude effective targeting, as exemplified by the superior
performance of F(ab')$_2$ tLNPs. In pregnant mice, F(ab')$_2$ tLNPs result in the highest placental
luminescence with minimal toxicity. This disparity likely reflects the unique advantages of avidity:
F(ab')$_2$ and antibody ligands possess dual binding sites and lower K_d values than monovalent
nanobody and DARPin ligands. Avidity is multiplicative rather than additive, and may partially
compensate for structural heterogeneity by increasing the probability of receptor engagement and
subsequent endocytosis[71]. This principle is consistent with principles observed in biological
systems such as viral capsids, which rely on probabilistic multivalent interactions to overcome
stochastic barriers during nuclear entry[72]. Our findings therefore suggest that ligand avidity may
be a key mechanism enabling tLNPs to function effectively despite their pronounced
polydispersity.

Collectively, this work is, to our knowledge, the first to reveal that the functional behavior of tLNPs
is not governed by ensemble-averaged properties but instead by distinct, structural
subpopulations that have historically remained analytically inaccessible. While separation-
coupled, solution-phase biophysical platforms have been applied to mRNA LNPs, here we extend
this integrated approach to tLNP systems, enabling the first direct resolution of functionally

relevant tLNP subpopulations and, further, the first correlation of their nanoscale structure to in vivo targeting performance. We anticipate that the AF4-UV-DLS-MALS-SAXS platform and subsequent chemometric analyses used in this work will inform a mechanistic, data-driven framework to guide future improvements in rational tLNP engineering. Importantly, this framework is developed and validated in the context of pregnancy, a uniquely stringent physiological setting in which therapeutic choices for pregnancy complications remain scare and safety constraints render systemic delivery approaches poorly suited[16,32,33]. Under these conditions, therapeutic efficacy is unlikely to scale with bulk-average biodistribution and will demand tLNP engineering at the subpopulation level to achieve exceptional targeting precision. More broadly, this work addresses a critical gap in nanotechnology and drug delivery research, where mechanistic structure–activity relationships for diseases and therapeutic contexts unique to women's health have remained largely underexplored. By resolving tLNP heterogeneity at the subpopulation level and linking defined structural features to in vivo outcomes, this work enables the generation of high-quality, interpretable datasets that move beyond bulk descriptors. Importantly, such datasets are well suited for integration with machine-learning and AI-driven optimization strategies, which will enable the derivation of predictive design rules for targeted delivery systems. Together, these findings establish that identifying, enriching, and engineering functionally competent tLNP subpopulations will be essential for the development of next-generation precision tLNP-mediated RNA therapeutics not only in pregnancy and women's health, but also other therapeutic settings where targeting accuracy is non-negotiable.

 MAIN TEXT FIGURES

Figure 1. Heterogeneity of targeted LNPs (tLNPs) is unresolved by traditional bulk measurements. (**a**) Schematic depicting polydispersity intrinsic to base LNPs, where the addition of targeting ligands further amplifies this heterogeneity, resulting in a product space of infinite combinations. This image was created with BioRender.com. LNP physicochemical characteristics

including (**b**) R_h and (**c**) PDI determined via DLS, (**d**) ζ-potential calculated via electrophoretic light
scattering, (**e**) apparent protein concentration determined via a potassium cyanide (KCN) assay,
(**f**) encapsulation efficiency and (**g**) mRNA concentration determined by a RiboGreen assay, and
(**h**) LNP particle concentration determined via DLS. (**i–j**) NT LNPs and tLNPs containing FLuc
mRNA were incubated with A431 cells at a dose of 25 ng of mRNA per 25,000 cells. (**i**) Luciferase
mRNA delivery and (**j**) cell viability in A431 cells 24 h after treatment with nontargeted (NT) LNPs
or anti-EGFR tLNPs. Normalized luciferase expression was quantified by normalizing to cells
treated with NT LNPs. Percent cell viability for each treatment condition was normalized to
untreated cells. (**k**) Stability of LNPs stored at 4°C in aqueous buffer for 28 days. Measurements
are reported mean ± SD from n = 3 technical replicates for (**a–g**), **(k)** and n = 5 biological replicates
for (**i–j**). One-way ANOVA with post hoc Student's t-tests using the Holm–Sídak correction for
multiple comparisons was used to compare luminescence in (**i**) across treatment group.

Figure 2. AF4-UV-DLS-MALS-SAXS resolves tLNP ligand-dependent polydispersity and compositional heterogeneity. (**a**) SAXS profiles of NT LNPs and tLNPs, showing the characteristic Bragg peak feature associated with internal lipid–RNA organization. (**b**) Fitting of

the Bragg peak feature using a multiple-Lorentz model where red is the first-order Bragg peak fit,
green represents higher-order particle disorder and blue is the cumulative fit of the two features.
(**c**) In-line AF4-UV-Vis contour maps (200–300 nm) depicting wavelength-resolved absorbance
of LNPs during separation. The 260 nm absorbance signal is characteristic of encapsulated RNA,
enabling identification of RNA-containing LNP populations across the AF4 elution profile.
Overlapping spectral features indicate the presence of multiple co-eluting populations with distinct
compositional profiles, motivating subsequent chemometric deconvolution. (**d**) Absorbance at 260
nm (RNA-associated signal) and 280 nm (protein-associated signal) from (**c**) plotted against the
corresponding 260:280 ratio for each LNP formulation. Deviations in the 260:280 ratio across
elution time indicate heterogeneity in RNA and protein content, suggesting the presence of
compositionally distinct subpopulations that cannot be resolved by bulk measurements alone.
These data were further subjected to chemometric analysis (see **Supplemental Figure 6**). The
determined (**e**) R_h profiles derived from in-line DLS and (**f**) molar mass profiles derived from MALS
analysis for NT LNPs (beige) and tLNPs (colors) overlaid with UV fractograms from in-line AF4
separation. (**g**) Peak 260:280 ratios from (**d**), shown for comparison across LNP groups. (**h**) In-
line DLS R_h and MALS-derived (**i**) mass, (**j**) radius of gyration, and (**k**) polydispersity plotted for
comparison across LNP groups. Measurements are reported mean ± standard error for (**h–k).**

Figure 3. SAXS component analysis reveals discrete tLNP subspecies. (**a**) SAXS elution profiles of NT LNPs and tLNPs. Dotted boxes indicate the main LNP elution region, expanded in (**b**). Evolving factor analysis (EFA) (**b**) applied to AF4-SAXS data, highlighting frames

corresponding to discrete evolving species (C1–C3) within each formulation. The resolved components correspond to distinct LNP subpopulations that differ in size and internal organization and a third component (when present) reflecting a minor population of highly heterogeneous or higher-mass particles. The temporal evolution of EFA-selected frames across the elution peak indicates that these components arise from partially overlapping populations that co-elute but differ in hydrodynamic size and composition. (**c**) Singular value decomposition (SVD) of SAXS datasets, indicating the number of independent signals present in each formulation. The presence of multiple significant singular values indicates that the SAXS signal cannot be described by a single particle population, necessitating decomposition into independent scattering components. (**d**) Volatility of ratio (V_r) analysis used to assess the statistical uniqueness of deconvoluted component subpopulations relative to the ensemble-averaged population. (**e-h**) Regularized alternating least squares (REGALS) deconvolutions of SAXS data yields component-resolved scattering profiles. Shown are the (**e**) ensemble-averaged SAXS profile over the elution peak, and the REGALS-derived scattering profiles for the (**f**) C1, (**g**) C2, and (**h**) C3 subpopulations. These structural components are consistent with compositionally distinct populations inferred from UV-based chemometric analysis, linking RNA-associated heterogeneity to differences in particle size and morphology. Together, these analyses demonstrate that the ensemble SAXS signal arises from multiple, structurally distinct tLNP subpopulations that can be resolved and interpreted through chemometric decomposition.

691
Figure 4. Determination of model-independent structural parameters of distinct tLNP subspecies. (**a**) Guinier analyses with corresponding residuals for SVD-resolved C1 and C2 components of NT LNPs and tLNPs, with the exception of F(ab')$_2$ tLNPs, where only C3 is shown.

White regions indicate components for which Guinier analysis failed due to large size ($q_{min}R_g >$
1.3). (**b**) P(r) analyses normalized by I(0) for the average profile and individual components (C1–
C3) for NT LNPs and tLNPs. (**c**) Radius of gyration (R_g) and (**d**) maximum dimension (D_{max}) of the
average profile and individual components derived from GNOM analysis for NT LNPs and tLNPs.
Blank regions denote populations where GNOM analysis was invalid ($q_{min}D_{max} > 4$). (**e**) LNP shape
factor calculated as D_{max}/R_g, where values of ~2.58 and ~3.0 correspond to spherical and prolate
ellipsoid geometries, respectively. DENSS ab initio electron density reconstructions from the AF4-
UV-DLS-MALS-SAXS profiles for (**f**) NT LNPs, (**g**) nanobody tLNPs, (**h**) DAPRin tLNPs, (**i**),
F(ab')$_2$ tLNPs, and (**j**) antibody tLNPs.

Figure 5. Targeted mRNA delivery to the placenta is driven by tLNP structural subspecies.
(**a-d**) DiR-labeled NT LNPs and tLNPs containing mCherry mRNA were incubated with placental

BeWo b30 trophoblasts at a dose of 150 ng of mRNA per 150,000 cells. After (**a**) 1 h, (**b**) 4 h, and
(**c**) 24 h, cellular accumulation was quantified. After (**d**) 24 h, mCherry expression was also
quantified. Normalized DiR and mCherry MFI was calculated by normalizing to cells treated with
NT LNPs. (**e–m**) NT LNPs and tLNPs containing FLuc mRNA were administered intravenously
via retroorbital injection into pregnant and nonpregnant mice at a dose of 12 µg mRNA per mouse.
After 6 h, mice were euthanized, and major organs were dissected. For pregnant mice,
luminescence imaging of (**e**) livers and spleens and (**f**) placentas and fetuses were performed via
an *in vivo* imaging system (IVIS). Luminescence from (**e-f**) was quantified via region of interest
(ROI) analysis to obtain luminescence flux in the (**g**) liver, (**h**) spleen, (**i**) placentas, and (**j**) fetuses
of pregnant mice. For nonpregnant mice, luminescence imaging of (**k**) livers and spleens was
performed. Luminescence from (**k**) was quantified via region of interest (ROI) analysis to obtain
luminescence flux in the (**m**) liver and (**m**) spleen of nonpregnant mice. Signal is reported mean
± SD from n = 3 biological replicates for (**a–d**) and n = 4 biological replicates for (**e–m**). One-way
ANOVA with post hoc Student's t-tests using the Holm–Sídak correction for multiple comparisons
was used to compare fluorescence in for (**a–d**) and luminescence in (**g–h, l–m**) across treatment
groups. Nested one-way ANOVA with post hoc Student's t-tests using the Holm–Sídak correction
for multiple comparisons was used to compare luminescence in (**i–j**) across treatment groups.
(**n–q**) Spearman correlations for (**n**) placental, (**o**) pregnant hepatic, and (**p**) nonpregnant hepatic
luminescence values using the physicochemical parameters from traditional characterization
methods, static SAXS analyses, and AF4-UV-DLS-MALS-SAXS analyses. (**q**) Heatmap
representing the entire dataset. For Spearman correlation graphs, dotted lines represent r = –0.6
and 0.6.
728

 Figure 6. tLNP bulk populations and subspecies drive differential acute cytokine
 responses. (**a-b**) NT LNPs and tLNPs containing FLuc mRNA were administered intravenously
 via retroorbital injection into pregnant and nonpregnant mice at a dose of 12 µg mRNA per mouse.

After 6 h, mice were euthanized, and serum was collected. Serum levels of C3a, TNF, IFN-γ, IL-6, ALT, and AST were quantified in (**a**) pregnant and (**b**) nonpregnant mice via ELISA. Measurements are reported mean ± SD from $n = 3–4$ biological replicates. One-way ANOVA with post hoc Student's t-tests using the Holm–Sídak correction for multiple comparisons was used to compare cytokine levels across treatment groups. (**c–e**) Spearman correlations for (**c**) TNF, (**d**) IFN-γ, and (**e**) IL-6 serum levels in pregnant (top) and nonpregnant (bottom) mice using the physicochemical parameters from traditional characterization methods, static SAXS analyses, and AF4-UV-DLS-MALS-SAXS analyses. (**f**) Heatmap representing the entire dataset. For Spearman correlation graphs, dotted lines represent $r = –0.6$ and 0.6.

METHODS

Materials

Cholesterol was purchased from Sigma Aldrich. The remaining lipid excipients were purchased from Avanti Polar Lipids. Anti-human EGFR antibody (Cetuximab biosimilar) was purchased from Bioxcell. FLuc and mCherry mRNA with N^1-methylpseudouridine modifications was purchased from TriLink Biotechnologies. DiR, 10X PBS (pH 7.4), enzymatic digestion kits, EDTA (pH 8.0), Sytox Blue, and dialysis cassettes were purchased from Thermo Fisher Scientific. Citrate buffer was purchased from Teknova. Dulbecco's Modified Eagle Medium (DMEM), Opti-MEM Reduced Serum Medium, fetal bovine serum (FBS), and penicillin-streptomycin (P/S) were purchased from Gibco. 96-well and 48-well plates were purchased from Corning. Dynasore, bafilomycin A1, amiloride, wortmannin, cytochalasin D, and methyl-beta-cyclodextrin small molecule inhibitors were purchased from Sigma Aldrich. Erlotinib small molecule inhibitor was purchased from Cayman Chemical. The Luciferase Reporter 1000 Assay System and CellTiter-Glo Luminescent Assay System were purchased from Promega. D-Luciferin Potassium Salt was purchased from Regis Technologies.

Protein modification

Anti-EGFR nanobodies (9G8)[73] and DARPins (E01)[74] were expressed and purified using the previously described sortase-tag expressed protein ligation system (STEPL)[75]. To generate expression plasmids, gBlocks for either 9G8 or E01 were inserted into a pSTEPL backbone between NdeI and AgeI restriction sites using In-Fusion Cloning (Takara Bio USA). Proteins were expressed in T7 Express Competent E. coli (C2566, New England Biolabs) and purified with a single DBCO handle attached to the C-terminal via STEPL. Proteins were further purified via size exclusion chromatography on a Superdex™ 75 Increase 10/300 GL Column (Cytiva). Protein concentration was determined via BCA assay. The purified nanobody and DARPin proteins were stored at -20°C for later use.

Anti-EGFR cetuximab antibody was cleaved into F(ab')$_2$ fragments using a ficin enzymatic digestion kit and purified using a Protein A column (Thermo Fisher Scientific). Whole antibodies and F(ab')$_2$ fragments were functionalized with DBCO via a reaction with a 20-fold molar excess of TFP-PEG(4)-DBCO (Thermo Fisher Scientific) in anhydrous DMSO for 2 h at 25°C. Unreacted TFP-PEG(4)-DBCO was removed using Zeba Dye and Biotin Removal spin columns (Thermo Fisher Scientific). Final protein concentration was measured using a Qubit Protein Quantification Assay (Thermo Fisher Scientific). The purified DBCO-labeled antibodies were stored at 4°C for later use.

tLNP formulation

tLNPs containing lipid A4 were formulated as previously described[38]. Lipid excipients were dissolved in ethanol to form the organic phase using the following molar ratio: ionizable lipid A4 (35 mol.%), DOPE (16 mol.%), cholesterol (46.5 mol.%), C14-PEG2000 (2.1 mol.%), and DSPE-PEG2000-azide (0.4 mol.%). mRNA was dissolved in citrate buffer (pH 3) to form the aqueous phase. LNPs were formulated at a weight ratio 10:1 of ionizable lipid to RNA with a volume ratio of organic phase to aqueous phase of 1:3. The organic and aqueous phases were loaded into glass syringes (Hamilton) and attached to a Pump 33 DDS syringe pump (Harvard Apparatus). The two phases were pushed through a custom soft lithography-patterned polydimethylsiloxane (PDMS) herringbone microfluidic chip, fabricated as described in our previous study[35]. The organic and aqueous phases were injected at a flow rate of 0.6 ml min^{-1} and 1.8 ml min^{-1}, respectively. Empty LNPs were prepared in the same manner, but with an aqueous phase containing citrate buffer and no mRNA. For in vitro flow cytometry studies, LNPs were labeled with 1.0 mol.% DiR before loading into dialysis cassettes. For remaining studies, LNPs were

792 loaded directly into dialysis cassettes. LNPs were dialyzed against 1X PBS (pH 7.4) for 2 h in
793 cassettes with a 20kDa molecular weight cutoff filter (Thermo Fisher Scientific). Non-targeted
794 LNPs were stored at 4°C for later use.
795
To functionalize LNPs with protein, DBCO-labeled proteins were added to LNPs at a 1:200 ratio
of DBCO-protein to lipid-anchored PEG-azide and incubated for 18 h at 25°C with gentle shaking.
tLNPs were purified from residual, unbound protein using size exclusion chromatography. Briefly,
a column was packed with Sepharose CL-6B (Sigma Aldrich) and rinsed with 1X PBS (pH 7.4) to
clear ethanol from the system. tLNPs were passed through the column and collected in a 96-well
plate. All fractions containing mRNA were pooled and concentrated using 100kDa filters (Sigma
Aldrich). The final tLNP solution was stored at 4°C for later use.
803
DLS
LNP R_h, PDI, and particle concentration were determined via dynamic light scattering (DLS)
measurements with a DynaPro Plate Reader III (Wyatt Technology) using a cumulants model.
LNPs were diluted 15-fold in 1X PBS (pH 7.4) and loaded into a 384-well Aurora plate (Wyatt
Technology). The plate was centrifuged at 300g for 1 min and then loaded onto the plate reader.
Size is reported as intensity-weighted averages from n = 3 independent measurements per
sample and data are expressed as the mean ± SD, where SD was calculated with the following
formula: $SD = \sqrt{PDI} \times radius$.
812
813 **ζ-potential**
814 ζ-potential was determined via electrophoretic light scattering (ELS) measurements on a
815 Zetasizer Nano (Malvern Instruments). LNPs were diluted 50-fold in ultrapure water and then
816 transferred to disposable folded capillary cells (Malvern Instruments). For each sample, n = 3
817 measurements with n = 5 runs were recorded.
818
Fluorescent protein quantification
Protein content of tLNPs was estimated using the CBQCA Protein Quantitation Kit according to
the manufacturer's instructions (Thermo Fisher Scientific). BSA standards and LNP samples were
prepared in 0.1 M sodium borate containing 0.1% (v/v) Triton X-100 and then transferred to a
black 96-well plate. 20 mM KCN and 40 mM ATTO-TAG CBQCA reagent were added to the
standards and samples to a total reaction volume of 100 μL at the ratios specified in the
manufacturer's instructions. The plate was shaken at 300 rpm for 1 h at 25°C and fluorescence
was read at an excitation wavelength of 465 nm and an emission wavelength of 550 nm. LNP
protein content was estimated by first subtracting the base fluorescence from an LNP with no
protein and then comparing with a standard curve fitted using univariate least-squares linear
regression.
830
LNP encapsulation
Relative encapsulation efficiency and encapsulated RNA concentration were determined using a
Quant-iT RiboGreen assay (Thermo Fisher Scientific). Each LNP formulation was diluted 80X in
either 1X tris-EDTA (TE) buffer (Thermo Fisher Scientific) or 1X TE buffer containing 0.1% (v/v)
Triton X-100 (Sigma Aldrich). LNPs were shaken at 300 rpm for 10 min at 25°C to facilitate particle
lysis and then transferred to a black 96-well plate. A standard curve was prepared according to
the manufacturer's instructions. RiboGreen fluorescent detection reagent was added to each well
at a 1:1 (v/v) ratio per the manufacturer's instructions. After incubation for 5 min at 25°C, the
fluorescence intensity was read on an Infinite 200 Pro plate reader (Tecan) at an excitation
wavelength of 480 nm and an emission wavelength of 520 nm. Encapsulation efficiency was
calculated as (B-A)/B X 100%, where A is the measured RNA content in TE buffer and B is the
measured RNA content in Triton X-100. mRNA concentrations of LNP formulations were

estimated by comparison with a standard curve fitted using univariate least-squares linear
regression.
845
Size-exclusion chromatography in-line with multiangle light scattering (SEC-MALS)
SEC-MALS experiments were performed on 100 µL injections of ~10^{12} particles/mL samples at
0.5 ml/min at room temperature in 1x PBS buffer using a TOSOH TSKgel G6000PWXL-CP SEC
column (7.8 mm × 300 mm, 13-µm particle size; Millipore Sigma). Absolute molar mass was
determined in-line using multi-angle light scattering from the column eluent at 18 angles using a
DAWN-HELEOS II MALS detector (Waters/Wyatt Technology Corp.) operating at 658 nm. Eluent
concentration was recorded using an in-line Optilab T-rEX Interferometric Refractometer
(Waters/Wyatt Technology Corp.). The online MALS detectors were normalized for counting
efficiency using BSA monomer peak data from separate experiment on a Superose 6 10/300
column in the same running buffer.
856
For compositional analysis of the base nontargeted mRNA-LNP, data acquisition and analysis
were performed as previously described[24] using the LNP Analysis Module in the ASTRA™ 8.2.2
software (Waters/Wyatt Technology Corp.). To obtain accurate concentration data from the online
260 nm UV absorbance signal, empty LNP samples were also prepared using the microfluidic
devices with lipid compositions and concentrations matching the LNP-mRNA samples. The empty
LNP samples were measured with the same method as the LNP-mRNA samples, and the results
from the empty samples were used to generate experimentally derived UV scattering correction
profiles with the ASTRA LNP Analysis Module as previously described[41]. The scattering correction
profiles were then applied non-destructively to the data collected for the corresponding LNP-
mRNA samples.
867
For mass determination of protein-labeled mRNA LNP particles, the weight-averaged molar
masses of species within defined chromatographic peaks were calculated using the ASTRA
software version 8.2.2 (Waters/Wyatt Technology Corp.), by construction of Debye plots ($KC/R\theta$
versus $\sin^2[\theta/2]$) at one second data intervals. The weight-averaged molar mass was then
calculated at each point of the chromatographic trace from the Debye plot intercept, and an overall
average molar mass was calculated by weighted averaging across the peak. A mass-averaged
dn/dc for the composite particle was calculated using the compositional analyses of the base
mRNA-LNP performed and the calculated number of surface azide attachment sites per particle,
assuming 100% labelling efficiency, yielding calculated *dn/dc* figures ranging from 0.160–0.165
mL/g. These derived properties are provided in **Supplementary Table 2**.
878
Synchrotron batch small angle X-ray scattering (SAXS)
Batch SAXS data were collected at beamline 16-ID (LiX) of the National Synchrotron Light Source
II (Upton, NY)[76]. SAXS/WAXS data were simultaneously collected at a wavelength of 0.89 Å,
yielded accessible scattering angle where 0.006 < q < 3.0 Å^{-1}, where q is the momentum transfer,
defined as $q = 4\pi\frac{\sin(\theta)}{\lambda}$, where λ is the X-ray wavelength and *2θ* is the scattering angle; data to
q<0.5 Å^{-1} were used in subsequent analyses. 60 µL of sample at a particle concentration of ~10^{12}
particles / mL were examined. Samples in dialysis matched 1x PBS (pH 7.4) were loaded into a
1-mm capillary for ten 1-s X-ray exposures.
887
Sedimentation velocity analytical ultracentrifugation (SV-AUC)
Sedimentation velocity analytical ultracentrifugation experiments were performed at 20°C with an
Optima™ analytical ultracentrifuge (Beckman-Coulter) and a TiAn50 rotor with two-channel
charcoal-filled Epon centerpieces and sapphire windows, using both absorbance and interference
optics. Data were collected in 1x PBS with detection at 260 & 280 nm, as well as interference

optics. Complete sedimentation velocity profiles were recorded every 30 seconds at 20,000 rpm
and 20°C. Data were fit using a least-squares *g*(s)* model as implemented in the program
SEDFIT[77].
896
Synchrotron AF4-UV-DLS-MALS-SAXS
Data were collected at the BioCAT beamline (18ID) at the Advanced Photon Source at Argonne
National Labs (Argonne, IL)[78]. SAXS data were simultaneously collected at a wavelength of 1.033
Å (12.0 keV), yielded accessible scattering angle where 0.0025 < q < 0.413 Å^{-1}, where q is the
momentum transfer, defined as $q = 4\pi\frac{\sin(\theta)}{\lambda}$, where λ is the X-ray wavelength and 2θ is the
scattering angle; data to q < 0.2 Å^{-1} were used in subsequent analyses. 100 µL of LNP at a particle
concentration of ~10^{12} particles were injected and eluted isocratically from an Eclipse^{TM} NEON
field flow fractionation (AF4) instrument with dilution control module using a variable-height short
channel with a 275 µm spacer and a 10 kDa regenerated cellulose membrane (Wyatt
Technology), connected to a 1260 Infinity II HPLC system with a G711A quaternary pump and a
G7167A multisampler (Agilent Technologies). A DAWN^{TM} HELEOS II MALS instrument with an
integrated WyattQELS^{TM} DLS detector (Wyatt Technology), an Optilab^{TM} T-rEX differential
refractometer (Wyatt Technology), and a G7165A UV-Vis multi-wavelength UV-Vis detector
(Agilent Technologies) were used for online detection. 1X PBS (pH 7.4) was used as the mobile
phase. Sample injection volumes were 55–150 µL. The AF4 system was controlled by VISION
3.2.0 software (Wyatt Technology). AF4 method parameters: 2.5 mL min^{-1} channel flow and 0.5
mL min^{-1} detector flow (corresponding to a 5-fold concentration enhancement from the dilution
control module), 0.2 mL min^{-1} inject flow. Focusing was at 1.0 mL min^{-1} with a 25% focus position
for 14 min. Cross flow was ramped from 0 to 1.0 mL min^{-1} in the first minute of the method, and
then kept constant at 1.0 mL min^{-1} throughout focusing and the initial 5 min of the elution step,
followed by an exponential gradient of 1.0–0.04 mL min^{-1} over 30 min after which the crossflow
was kept constant at 0.04 mL min^{-1} for 10 min before being turned off. Eluent from the AF4, after
flowing through the UV, MALS-DLS and RI detectors, was flown through the SAXS flow cell. The
flow cell consists of a 1.0 mm ID quartz capillary with ~20 µm walls. A coflowing buffer sheath is
used to separate sample from the capillary walls, helping prevent radiation damage[79]. Scattering
intensity was recorded using an EIGER2 XE 9M (Dectris) detector which was placed 3.714 m
from the sample using0.15 s X-ray exposures taken at 1 second intervals over the entire elution
and data was reduced to 1D scattering profiles using BioXTAS RAW 2.3.0[80]. Plots of intensity
from the forward scatter closely correlated to in-line UV and refractive index (RI) measurements.
926
In-line Absorbance Analyses: In-line diode-array spectral data was collected at eight wavelengths
(4 nm bandpass) between 210-300 nm across 3634 time points. Chemical spectral and
concentration profiles were resolved using Multivariate Curve Resolution – Alternating Least
Squares (MCR-ALS) implemented via the pyMCR library[81]. All chemometric analyses were
performed in Python 3.10 using the Anaconda distribution on Ubuntu Linux, using *NumPy*,
pandas, *SciPy*, *scikit-learn*, *pyMCR*, and *matplotlib*. Data handling used *NumPy* and *pandas*. Prior
to multivariate analysis, chromatographic matrices were converted into sample × wavelength and
wavelength × sample representations. No baseline subtraction or smoothing was applied unless
specified. To determine the intrinsic dimensionality of each chromatographic dataset, singular
value decomposition (SVD) was applied[50]. Singular values were normalized to the first singular
value, and components with normalized singular values above 0.03 were retained as significant.
The resulting SVD rank serves as an upper bound on the number of chemically meaningful
species. To refine the chemical rank, Evolving Factor Analysis (EFA)[51] was applied in both forward
and backward directions. At each step, SVD was performed on growing (forward) or shrinking
(backward) subsets of the chromatogram. A component was considered active if its normalized
evolving singular value exceeded 0.03 at any point. The final chemical rank was defined as the

minimum of SVD rank, forward EFA rank, and backward EFA rank. PCA[51,82] was used to obtain
initial spectral estimates, with the number of components equal to chemical rank plus one (to
model baseline contributions). Alternating least-squares iterations were solved under non-
negativity constraints on both concentration and spectral profiles. The first MCR component was
assigned to protein absorbance and the second to RNA, based on UV–Vis characteristics.
Normalized concentration profiles were computed, and RNA-to-protein ratios were determined
pointwise to assess component co-elution and relative abundance across the chromatographic
time domain. Gaussian models containing one, two, or three components were fit to the major
protein elution peak using nonlinear least-squares optimization. Model selection was performed
using the Akaike Information Criterion (AIC), with the lowest AIC indicating the best model.
Residuals and fit diagnostics were recorded for all candidate models.

In-line MALS/DLS Analyses: Prior to LNP sample injections in the AF4-MALS component, the
membrane was conditioned by injecting 100 µL of a 4 mg mL^{-1} bovine serum albumin (BSA
Fraction V) standard (Wyatt Technology). The system performance was checked by injecting and
analyzing a triplicate of 25 µL of the same BSA standard using the BSA short channel AF4 method
built into the VISION 3.2.0 software. The online MALS detectors were calibrated at 90° scattering
angle and the remaining detector angles normalized to the response at 90° using the BSA
monomer peak data. Data acquisition and analysis were performed using ASTRA^{TM} 8.2.1
software (Wyatt Technology). Masses were calculated using the mass-averaged *dn/dc* values in
Supplementary Table 2.

SAXS analyses
Analysis of the AF4-SAXS datasets was performed using the BioXTAS RAW program[80,83]. Buffer-
subtracted profiles were analyzed by SVD and the ranges of overlapping peak data were
determined using EFA as implemented in REGALS[52,84]. The determined peak windows were used
to identify the basis vectors for each component and the corresponding SAXS profiles were
calculated. When manually fitting the pair distribution function P(r), the maximum diameter of the
particle (D$_{max}$) was incrementally adjusted in GNOM[85] as implemented in RAW to maximize the
total estimate and χ^2 figures, to minimize the discrepancy between the fit and the experimental
data to a q$_{max}$ of 0.1 Å^{-1} and to optimize the visual qualities of the distribution profile.

Deconvolution of the primary Bragg peaks in SAXS were using multiple Lorentz fits[45] as
implemented in the program Origin (OriginLab Corporation):

$$y = y_0 + \frac{2 \times area}{\pi} \times \frac{width}{4(x - x_c)^2 + width^2}$$

where y$_0$ is an offset and was set to the X-ray baseline. x$_c$ is a center of function and corresponds
to the center of the SAXS peak.

The high-q region of each SAXS profile was analyzed using Porod scaling to probe short-length-
scale density correlations. In the Porod regime, the scattered intensity follows a power-law
dependence, $I(q) \sim q^{-m}$, where the Porod exponent m reflects interfacial and internal density
fluctuations at length scales smaller than the overall particle size. Ideal compact particles with
sharp interfaces exhibit classical Porod behavior ($m = 4$), whereas deviations toward lower values
indicate increasing structural heterogeneity. Exponents in the range $3 < m < 4$ are associated
with surface-fractal scattering arising from rough or diffuse interfaces, while values $1 < m <$
3 correspond to mass-fractal scattering from internally disordered structures[86–88]. Porod
exponents were determined by linear fitting of $\log I(q)$ versus $\log q$ over the experimentally

accessible high-q range using ScÅtter[89]. Fits were applied consistently across all datasets,
including batch measurements, elution-resolved, and component-resolved profiles obtained by
singular value decomposition (SVD). The resulting exponents were used to classify particle
structural behavior without assuming idealized geometries.
996
DENSS[90] was used to calculate the ab initio electron density map directly from the GNOM output.
In total, 20 reconstructions of electron density were performed in slow mode with default
parameters and subsequently averaged and refined. Reconstructions were visualized using the
PyMOL 2.5.2 Molecular Graphics System (Schrödinger) with five contour levels of density
rendered with the following colors: 15σ, red; 10σ, green; 5σ, cyan; 2.5σ, blue; −0.7σ, blue. To
determine size parameters, DENSS density maps were converted to pseudo-atomic PDB format
using the vol2pdb utility from the Situs package[59].
1004
Cell culture
A431 cells were kindly provided by Dr. Andrew Tsourkas (University of Pennsylvania). BeWo b30
cells were kindly provided by Dr. Dogeun Huh (University of Pennsylvania) with permission from
Dr. Alan Schwartz (Washington University in St. Louis). BeWo b30 cells and A431 cells were
cultured in Dulbecco's Modified Eagle Medium (DMEM) supplemented with 10% fetal bovine
serum (FBS) and 1% penicillin-streptomycin (P/S) and maintained at 37ºC and 5% CO_2.

In vitro transfection studies
For luminescence assays, A431 cells were plated at a density of 25,000 cells/well in 100 μL
DMEM in tissue-culture treated 96-well plates and then left to adhere overnight. DMEM was
aspirated and replaced with Opti-MEM Reduced Serum Medium. Cells were then treated with
LNPs encapsulating FLuc mRNA at a dose of 25 ng of mRNA per well. After 24 h, media was
removed, and cells were incubated with 0.1% Triton-X for 3 min. 100 μL of luciferase assay
substrate (Promega) was then added to each well, and cells were left to incubate at room
temperature for 5 min. Luminescence was detected using an Infinite 200 Pro plate reader (Tecan).
Normalized luciferase expression for each tLNP treatment group was quantified by normalizing
to cells treated with non-targeted LNPs.
1021
For flow cytometry studies, BeWo b30 cells were plated at a density of 150,000 cells/well in 200
μL DMEM in tissue-culture treated 48-well plates and then left to adhere overnight. DMEM was
aspirated and replaced with Opti-MEM Reduced Serum Medium. Cells were then treated with
DiR-labeled LNPs encapsulating mCherry mRNA at a dose of 150 ng of mRNA per well. After 1
h, 4 h, or 24 h, media was removed, and cells were washed with 1X PBS (pH 7.4) containing 2
mM EDTA. Cells were then resuspended 1X PBS-EDTA containing 0.125% (v/v) Sytox Blue.
Single cell suspensions were analyzed via flow cytometry for DiR and mCherry fluorescence using
a BD LSR II flow cytometer equipped with violet, blue, green and red lasers. For each sample, at
least 10,000 events within the singlet gate were collected. Data analysis was performed using
FlowJo version 10.9 (Becton Dickinson). Normalized DiR or mCherry median fluorescent intensity
(MFI) for each treatment group was quantified by normalizing to cells treated with non-targeted
LNPs at each time point.
1034
In vitro endocytosis studies
BeWo b30 cells were plated at a density of 25,000 cells/well in 100 μL DMEM in tissue-culture
treated 96-well plates and then left to adhere overnight. Cells were treated with small molecule
endocytosis inhibitors dissolved in DMSO for 30 min. at the following concentrations: dynasore
(100 μM), amiloride (2 mM), methyl-beta-cyclodextrin (5 mM), and erlotinib (200 μM). Cell media
was then aspirated and replaced with Opti-MEM Reduced Serum Medium. Cells were then
treated with LNPs encapsulating FLuc mRNA at a dose of 25 ng of mRNA per well. Control cells

were treated with DMSO alone (no inhibitor) followed by LNPs. After 24 h, luciferase expression
was evaluated using a Luciferase Reporter 1000 Assay System. Cell viability was evaluated using
a CellTiter-Glo Luminescent Assay System. To calculate toxicity, each group was normalized to
BeWo b30 cells treated with DMSO containing no inhibitor followed by treatment with LNPs. To
calculate relative luminescence, each group was first normalized to BeWo b30 cells treated with
DMSO containing no inhibitor and then normalized to each group's estimated toxicity value to
account for potential decreases in luminescence due to DMSO-mediated toxicity.
1049
Animal experiments
All animal use was in accordance with the guidelines and approval from the University of
Pennsylvania's Institutional Animal Care and Use Committee (IACUC, protocol #806540). Female
and male C57BL/6 mice (8-12 weeks old, approximately 20 g average weight) were purchased
from the Jackson Laboratory. Time-dated pregnancies were achieved by housing two females
and one male all at least 8–12 weeks of age together in one cage overnight and separating the
male the next morning. Consistent with the breeding scheme established by Jackson Laboratory,
separation was deemed to be gestational day E0. Mice were housed in a vivarium with a 12 h
light–dark cycle and were provided with food and water ad libitum. Vivarium temperature was
maintained between 20 and 24 °C and humidity was maintained between 40 and 70%.
1060
In vivo biodistribution studies
LNPs encapsulating FLuc mRNA were administered to non-pregnant and gestational day E16
pregnant mice via retroorbital injection at a dose of 12 µg mRNA per mouse. After 6 h, mice
received an intraperitoneal injection of *D*-luciferin potassium salt at a dose of 150 mg kg^{-1}. After 5
min, blood was collected by retroorbital bleeding in Microtainer blood collection tubes containing
serum separator gel (BD Biosciences). Mice were then euthanized with CO_2 and the heart, lung,
liver, kidneys, spleen, and uterus were removed. In pregnant mice, the uteruses were dissected
to remove the fetuses and placentas. Luminescence imaging of the organs was performed using
an in vivo imaging system (IVIS; PerkinElmer). Luminescence flux was quantified using the Living
Image Software 4.7.3 (PerkinElmer) by placing rectangular regions of interest (ROIs) on organ
images, keeping the same ROI sizes among each organ. Collected blood was allowed to clot for
2 h at room temperature and then centrifuged for 20 min at 2000 g. Serum was removed,
aliquoted, and stored at -20 °C for later use. Mouse Quantikine ELISA kits (R&D systems) were
used to evaluate C3a, IL-6, TNF, and IFN-γ levels in serum per the manufacturer's instructions.
Colorimetric assay kits (Cayman Chemical) were used to evaluate ALT and AST levels in serum
per the manufacturer's instructions.
1077
Statistical analysis
All statistical analysis was performed in GraphPad Prism version 10.6.0. All tests of significance
were performed at a significance level of α = 0.05. Ordinary (one technical replicate per biological
replicate) or nested (multiple technical replicates per biological replicate) one-way ANOVAs with
post hoc Student's t-tests using the Holm–Šídák correction for multiple comparisons were used
to compare responses across treatment groups. Each fetus or placenta from one mouse was
considered a technical replicate. Two-sided ordinary two-way ANOVAs with post hoc Student's t-
tests using the Holm–Šídák correction for multiple comparisons were used to compare responses
across treatment groups and gestational days or mouse cohorts (nonpregnant versus pregnant).
All data are presented as the mean ± standard deviation (SD) with the exact number of replicates
reported in the figure legends. All samples had at least *n* = 3 biological replicates, and no statistical
methods were used to predetermine sample size. Investigators were not blinded during outcome
assessment or data analysis.

DATA AVAILABILITY

All data supporting the findings of this study are available within the paper and Supplementary Information. The SEC-MALS, SAXS, and AF4-UV-DLS-MALS-SAXS raw and analyzed data are available from Zenodo. Source data are provided with this paper.

ACKNOWLEDGEMENTS

The authors acknowledge and thank the Penn Cytomics and Cell Sorting Core (RRID: SCR_022376). The LiX beamline is part of the Center for Biomolecular Structure (CBMS), which is supported by the Department of Energy Office of Biological and Environmental Research (KP1605010). As part of NSLS-II, a national user facility at Brookhaven National Laboratory, work performed at the CBMS is supported in part by the US Department of Energy, Office of Science, Office of Basic Energy Sciences Program under contract number DE-SC0012704. This research was performed on an APS beam time award from the Advanced Photon Source, a U.S. Department of Energy (DOE) Office of Science user facility operated for the DOE Office of Science by Argonne National Laboratory under Contract No. DE-AC02-06CH11357. BioCAT was supported by grant P30 GM138395 from the National Institute of General Medical Sciences of the National Institutes of Health. K.G. acknowledges support from the Johnson Research Foundation. M.J.M. acknowledges support from an NSF CAREER Award (no. CBET-2145491) and a Burroughs Wellcome Fund Career Award at the Scientific Interface. H.C.G, H.C.S., A.S.T., H.M.Y, and A.A. were supported by National Science Foundation Graduate Research Fellowships (Award 1845298). The content is solely the responsibility of the authors and does not necessarily reflect the official views of the National Institute of General Medical Sciences or the National Institutes of Health.

AUTHOR CONTRIBUTIONS

H.C.G., M.S.P., M.B.W., J.B.H., and K.G. conceived and designed the experiments. H.C.G., H.C.S., A.S.T., M.S.P., E.B., H.M.Y., V.M.U., A.C., B.E.N., A.A., M.B.W., J.B.H., and K.G. performed the experiments. H.C.G., M.B.W., J.B.H., and K.G. analyzed the data. H.C.G., K.G., and M.J.M wrote and edited the manuscript. A.T., K.G., and M.J.M. funded the experiments. All authors discussed the results and approved the final version of the manuscript for submission.

COMPETING INTERESTS

H.C.G., H.C.S., and M.J.M. have filed a patent application related to this study. The remaining authors declare no competing interests.

REFERENCES

1. Mitchell, M. J. *et al.* Engineering precision nanoparticles for drug delivery. *Nat Rev Drug Discov* **20**, 101–124 (2021).
2. Hou, X., Zaks, T., Langer, R. & Dong, Y. Lipid nanoparticles for mRNA delivery. *Nat Rev Mater* **6**, 1078–1094 (2021).
3. Huang, X. *et al.* The landscape of mRNA nanomedicine. *Nat Med* **28**, 2273–2287 (2022).
4. Li, S. *et al.* Single-Particle Spectroscopic Chromatography Reveals Heterogeneous RNA Loading and Size Correlations in Lipid Nanoparticles. *ACS Nano* **18**, 15729–15743 (2024).
5. Vaidya, A. *et al.* Analytical Characterization of Heterogeneities in mRNA-Lipid Nanoparticles Using Sucrose Density Gradient Ultracentrifugation. *Anal. Chem.* **96**, 5570–5579 (2024).
6. Bepperling, A. & Richter, G. Determination of mRNA copy number in degradable lipid nanoparticles via density contrast analytical ultracentrifugation. *Eur Biophys J* **52**, 393–400 (2023).
7. Kamanzi, A. *et al.* Single-particle multi-parametric microscopy reveals structural, size, and payload heterogeneity in mRNA-loaded lipid nanoparticles. 2025.10.17.683130 Preprint at https://doi.org/10.1101/2025.10.17.683130 (2025).
8. Guyon, L., Groo, A.-C. & Malzert-Fréon, A. Relevant Physicochemical Methods to Functionalize, Purify, and Characterize Surface-Decorated Lipid-Based Nanocarriers. *Mol. Pharmaceutics* **18**, 44–64 (2021).
9. Yan Ang, M. J., E. Metzloff, A., S. Thatte, A. & J. Mitchell, M. Lipid nanoparticles for engineering next generation CAR T cell immunotherapy. *Nanoscale Horizons* https://doi.org/10.1039/D5NH00432B (2026) doi:10.1039/D5NH00432B.
10. Hunter, T. L. *et al.* In vivo CAR T cell generation to treat cancer and autoimmune disease. *Science* **388**, 1311–1317 (2025).
11. Billingsley, M. M. *et al.* In Vivo mRNA CAR T Cell Engineering via Targeted Ionizable Lipid Nanoparticles with Extrahepatic Tropism. *Small* **20**, 2304378 (2024).
12. Rosenblum, D. *et al.* CRISPR-Cas9 genome editing using targeted lipid nanoparticles for cancer therapy. *Science Advances* **6**, eabc9450 (2020).
13. Han, J. P. *et al.* In vivo delivery of CRISPR-Cas9 using lipid nanoparticles enables antithrombin gene editing for sustainable hemophilia A and B therapy. *Science Advances* **8**, eabj6901 (2022).
14. Finn, J. D. *et al.* A Single Administration of CRISPR/Cas9 Lipid Nanoparticles Achieves Robust and Persistent In Vivo Genome Editing. *Cell Reports* **22**, 2227–2235 (2018).
15. Shi, D., Toyonaga, S. & Anderson, D. G. *In Vivo* RNA Delivery to Hematopoietic Stem and Progenitor Cells *via* Targeted Lipid Nanoparticles. *Nano Lett.* **23**, 2938–2944 (2023).
16. Swingle, K. L., Ricciardi, A. S., Peranteau, W. H. & Mitchell, M. J. Delivery technologies for women's health applications. *Nat Rev Bioeng* **1**, 408–425 (2023).
17. Swingle, K. L. *et al.* Placenta-tropic VEGF mRNA lipid nanoparticles ameliorate murine pre-eclampsia. *Nature* **637**, 412–421 (2025).
18. Pritchard, N., Kaitu'u-Lino, T., Harris, L., Tong, S. & Hannan, N. Nanoparticles in pregnancy: the next frontier in reproductive therapeutics. *Hum Reprod Update* **27**, 280–304 (2021).
19. Sych, T. *et al.* High-throughput measurement of the content and properties of nano-sized bioparticles with single-particle profiler. *Nat Biotechnol* **42**, 587–590 (2024).
20. Hallan, S. S., Sguizzato, M., Esposito, E. & Cortesi, R. Challenges in the Physical Characterization of Lipid Nanoparticles. *Pharmaceutics* **13**, 549 (2021).
21. Graewert, M. A. *et al.* Quantitative size-resolved characterization of mRNA nanoparticles by in-line coupling of asymmetrical-flow field-flow fractionation with small angle X-ray scattering. *Sci Rep* **13**, 15764 (2023).

22. Börjesdotter, A.-M. *et al.* Lipid nanoparticle properties explored using online asymmetric flow
field-flow fractionation coupled with small angle X-ray scattering: Beyond average
characterisation. *International Journal of Pharmaceutics* **668**, 124940 (2025).
23. Nogueira, S. S. *et al.* Analytical techniques for the characterization of nanoparticles for
mRNA delivery. *European Journal of Pharmaceutics and Biopharmaceutics* **198**, 114235
(2024).
24. Padilla, M. S. *et al.* Elucidating lipid nanoparticle properties and structure through
biophysical analyses. *Nat Biotechnol* 1–14 (2025) doi:10.1038/s41587-025-02855-x.
25. Menon, I., Zaroudi, M., Zhang, Y., Aisenbrey, E. & Hui, L. Fabrication of active targeting lipid
nanoparticles: Challenges and perspectives. *Materials Today Advances* **16**, 100299 (2022).
26. Sapsford, K. E. *et al.* Functionalizing Nanoparticles with Biological Molecules: Developing
Chemistries that Facilitate Nanotechnology. *Chem. Rev.* **113**, 1904–2074 (2013).
27. Bolinsson, H., Söderberg, C., Herranz-Trillo, F., Wahlgren, M. & Nilsson, L. Realizing the
AF4-UV-SAXS on-line coupling on protein and antibodies using high flux synchrotron
radiation at the CoSAXS beamline, MAX IV. *Anal Bioanal Chem* **415**, 6237–6246 (2023).
28. Da Vela, S. *et al.* AF4-to-SAXS: expanded characterization of nanoparticles and proteins at
the P12 BioSAXS beamline. *J Synchrotron Rad* **32**, 971–985 (2025).
29. Kolb, B. *et al.* Advanced Quality and Comparability Assessment of mRNA-Loaded Lipid
Nanoparticles: Absolute Size Distribution Profiles and Structure from AF4-Coupled Light and
X-ray Scattering Measurements. *Anal. Chem.* **98**, 5271–5283 (2026).
30. Sanchez-Fernandez, A. *et al.* Structural heterogeneity in mRNA-LNP subpopulations
revealed by AF4-SAXS: implications for cargo loading and cell transfection.
2026.01.16.699683 Preprint at https://doi.org/10.64898/2026.01.16.699683 (2026).
31. Bittrich, E. *et al.* Structural Profiling of Lipid Nanoparticles at Sub-10 nm Resolution via
Online AF4 Coupled to SAXS and SANS. Preprint at https://doi.org/10.26434/chemrxiv-
2025-6mtt8-v2 (2025).
32. Chappell, L. C., Cluver, C. A., Kingdom, J. & Tong, S. Pre-eclampsia. *The Lancet* **398**, 341–
354 (2021).
33. Geisler, H. C., Safford, H. C. & Mitchell, M. J. Rational Design of Nanomedicine for
Placental Disorders: Birthing a New Era in Women's Reproductive Health. *Small* **n/a**,
2300852.
34. Chen, D. *et al.* Rapid Discovery of Potent siRNA-Containing Lipid Nanoparticles Enabled by
Controlled Microfluidic Formulation. *J. Am. Chem. Soc.* **134**, 6948–6951 (2012).
35. Shepherd, S. J. *et al.* Scalable mRNA and siRNA Lipid Nanoparticle Production Using a
Parallelized Microfluidic Device. *Nano Lett.* **21**, 5671–5680 (2021).
36. Swingle, K. L. *et al.* Ionizable Lipid Nanoparticles for In Vivo mRNA Delivery to the Placenta
during Pregnancy. *J. Am. Chem. Soc.* **145**, 4691–4706 (2023).
37. Agard, N. J., Prescher, J. A. & Bertozzi, C. R. A Strain-Promoted [3 + 2] Azide−Alkyne
Cycloaddition for Covalent Modification of Biomolecules in Living Systems. *J. Am. Chem.*
Soc. **126**, 15046–15047 (2004).
38. Geisler, H. C. *et al.* EGFR-targeted ionizable lipid nanoparticles enhance *in vivo* mRNA
delivery to the placenta. *Journal of Controlled Release* **371**, 455–469 (2024).
39. Geisler, H. C., Battistini, E., Thatte, A. S., Padilla, M. S. & Mitchell, M. J. Preparation of
targeted lipid nanoparticles for precision nucleic acid delivery. *Nat Protoc* 1–36 (2026)
doi:10.1038/s41596-025-01330-w.
40. Uhlén, M. *et al.* Tissue-based map of the human proteome. *Science* **347**, 1260419 (2015).
41. Jia, X. *et al.* Enabling online determination of the size-dependent RNA content of lipid
nanoparticle-based RNA formulations. *Journal of Chromatography B* **1186**, 123015 (2021).
42. Some, D., Amartely, H., Tsadok, A. & Lebendiker, M. Characterization of Proteins by Size-
Exclusion Chromatography Coupled to Multi-Angle Light Scattering (SEC-MALS). *Journal of*
Visualized Experiments https://doi.org/10.3791/59615 (2019) doi:10.3791/59615.

43. Bragg, W. H. & Bragg, W. L. The reflection of X-rays by crystals. *Proc. A* **88**, 428–438
(1913).
44. Carrasco, M. J. *et al.* Ionization and structural properties of mRNA lipid nanoparticles
influence expression in intramuscular and intravascular administration. *Commun Biol* **4**, 956
(2021).
45. Hammel, M. *et al.* Correlating the Structure and Gene Silencing Activity of Oligonucleotide-
Loaded Lipid Nanoparticles Using Small-Angle X-ray Scattering. *ACS Nano* **17**, 11454–
11465 (2023).
46. Thompson, P., Cox, D. E. & Hastings, J. B. Rietveld refinement of Debye–Scherrer
synchrotron X-ray data from Al2O3. *J Appl Cryst* **20**, 79–83 (1987).
47. Wilhelmy, C. *et al.* Direct structural investigation of pH responsiveness in mRNA lipid
nanoparticles: Refining paradigms. *Journal of Controlled Release* **384**, 113848 (2025).
48. Koizumi, R., Li, B.-X. & Lavrentovich, O. D. Effect of Crowding Agent Polyethylene Glycol on
Lyotropic Chromonic Liquid Crystal Phases of Disodium Cromoglycate. *Crystals* **9**, 160
(2019).
49. Börjesdotter, A.-M. *et al.* Lipid nanoparticle properties explored using online asymmetric flow
field-flow fractionation coupled with small angle X-ray scattering: Beyond average
characterisation. *International Journal of Pharmaceutics* **668**, 124940 (2025).
50. Golub, G. H. & Reinsch, C. Singular Value Decomposition and Least Squares Solutions. in
Linear Algebra (eds Wilkinson, J. H., Reinsch, C. & Bauer, F. L.) 134–151 (Springer, Berlin,
Heidelberg, 1971). doi:10.1007/978-3-662-39778-7_10.
51. Malinowski, E. R. *Factor Analysis in Chemistry, 3rd Edition | Wiley*. (Wiley, 2002).
52. Meisburger, S. P. *et al.* Domain Movements upon Activation of Phenylalanine Hydroxylase
Characterized by Crystallography and Chromatography-Coupled Small-Angle X-ray
Scattering. *J. Am. Chem. Soc.* **138**, 6506–6516 (2016).
53. Meisburger, S. P., Xu, D. & Ando, N. REGALS: a general method to deconvolve X-ray
scattering data from evolving mixtures. *IUCrJ* **8**, 225–237 (2021).
54. Hura, G. L. *et al.* Comprehensive macromolecular conformations mapped by quantitative
SAXS analyses. *Nat Methods* **10**, 453–454 (2013).
55. Hammouda, B. A new Guinier–Porod model. *J Appl Crystallogr* **43**, 716–719 (2010).
56. Jeffries, C. M. *et al.* Small-angle X-ray and neutron scattering. *Nat Rev Methods Primers* **1**,
70 (2021).
57. [11] Small-angle x-ray scattering. in *Methods in Enzymology* vol. 61 148–249 (Academic
Press, 1979).
58. Dao, H. M. *et al.* Characterization of mRNA Lipid Nanoparticles by Electron Density
Mapping Reconstruction: X-ray Scattering with Density from Solution Scattering (DENSS)
Algorithm. *Pharm Res* **41**, 501–512 (2024).
59. Wriggers, W. Conventions and workflows for using Situs. *Acta Cryst D* **68**, 344–351 (2012).
60. Sihver, W. *et al.* Radiolabeled Cetuximab Conjugates for EGFR Targeted Cancer
Diagnostics and Therapy. *Pharmaceuticals* **7**, 311–338 (2014).
61. Marsh, B. & Blelloch, R. Single nuclei RNA-seq of mouse placental labyrinth development.
eLife **9**, e60266 (2020).
62. Clemente, L. & Bird, I. M. The epidermal growth factor receptor in healthy pregnancy and
preeclampsia. *Journal of Molecular Endocrinology* **70**, e220105 (2023).
63. Geng, Y. *et al.* Shape effects of filaments versus spherical particles in flow and drug
delivery. *Nature Nanotech* **2**, 249–255 (2007).
64. Zhu, M. *et al.* Physicochemical Properties Determine Nanomaterial Cellular Uptake,
Transport, and Fate. *Acc. Chem. Res.* **46**, 622–631 (2013).
65. Huang, K. *et al.* Size-Dependent Localization and Penetration of Ultrasmall Gold
Nanoparticles in Cancer Cells, Multicellular Spheroids, and Tumors in Vivo. *ACS Nano* **6**,
4483–4493 (2012).

66. Patel, S. *et al.* Naturally-occurring cholesterol analogues in lipid nanoparticles induce
polymorphic shape and enhance intracellular delivery of mRNA. *Nat Commun* **11**, 983
(2020).
67. Champion, J. A. & Mitragotri, S. Role of target geometry in phagocytosis. *Proceedings of the*
National Academy of Sciences **103**, 4930–4934 (2006).
68. Choi, Y. *et al.* Controlled spatial characteristics of ligands on nanoparticles: Determinant of
cellular functions. *Journal of Controlled Release* **360**, 672–686 (2023).
69. Li, S. *et al.* Payload distribution and capacity of mRNA lipid nanoparticles. *Nat Commun* **13**,
5561 (2022).
70. Elias, D. R., Poloukhtine, A., Popik, V. & Tsourkas, A. Effect of ligand density, receptor
density, and nanoparticle size on cell targeting. *Nanomedicine: Nanotechnology, Biology*
and Medicine **9**, 194–201 (2013).
71. Kiessling, L. L., Gestwicki, J. E. & Strong, L. E. Synthetic Multivalent Ligands as Probes of
Signal Transduction. *Angewandte Chemie International Edition* **45**, 2348–2368 (2006).
72. Mammen, M., Choi, S.-K. & Whitesides, G. M. Polyvalent Interactions in Biological Systems:
Implications for Design and Use of Multivalent Ligands and Inhibitors. *Angewandte Chemie*
International Edition **37**, 2754–2794 (1998).
73. Roovers, R. C. *et al.* Efficient inhibition of EGFR signaling and of tumour growth by
antagonistic anti-EFGR Nanobodies. *Cancer Immunol Immunother* **56**, 303–317 (2007).
74. Steiner, D., Forrer, P. & Plückthun, A. Efficient selection of DARPins with sub-nanomolar
affinities using SRP phage display. *J Mol Biol* **382**, 1211–1227 (2008).
75. Chan, A. *et al.* Cytosolic Delivery of Small Protein Scaffolds Enables Efficient Inhibition of
Ras and Myc. *Mol. Pharmaceutics* **19**, 1104–1116 (2022).
76. Yang, L. *et al.* Solution scattering at the Life Science X-ray Scattering (LiX) beamline. *J*
Synchrotron Rad **27**, 804–812 (2020).
77. Schuck, P. Size-Distribution Analysis of Macromolecules by Sedimentation Velocity
Ultracentrifugation and Lamm Equation Modeling. *Biophysical Journal* **78**, 1606–1619
(2000).
78. Fischetti, R. *et al.* The BioCAT undulator beamline 18ID: a facility for biological non-
crystalline diffraction and X-ray absorption spectroscopy at the Advanced Photon Source. *J*
Synchrotron Rad **11**, 399–405 (2004).
79. Kirby, N. *et al.* Improved radiation dose efficiency in solution SAXS using a sheath flow
sample environment. *Acta Crystallogr D Struct Biol* **72**, 1254–1266 (2016).
80. Hopkins, J. B. BioXTAS RAW 2: new developments for a free open-source program for
small-angle scattering data reduction and analysis. *J Appl Cryst* **57**, 194–208 (2024).
81. Camp, C. H. pyMCR: A Python Library for MultivariateCurve Resolution Analysis with
Alternating Regression (MCR-AR). *J Res Natl Inst Stand Technol* **124**, 1–10 (2019).
82. Tauler, R. Multivariate curve resolution applied to second order data. *Chemometrics and*
Intelligent Laboratory Systems **30**, 133–146 (1995).
83. Hopkins, J. B., Gillilan, R. E. & Skou, S. BioXTAS RAW: improvements to a free open-
source program for small-angle X-ray scattering data reduction and analysis. *J Appl Cryst*
50, 1545–1553 (2017).
84. Meisburger, S. P., Xu, D. & Ando, N. REGALS: a general method to deconvolve X-ray
scattering data from evolving mixtures. *IUCrJ* **8**, 225–237 (2021).
85. Svergun, D. I. Determination of the regularization parameter in indirect-transform methods
using perceptual criteria. *Journal of Applied Crystallography* **25**, 495–503 (1992).
86. Feigin, L. A. & Svergun, D. I. *Structure Analysis by Small-Angle X-Ray and Neutron*
Scattering. (Springer US, Boston, MA, 1987). doi:10.1007/978-1-4757-6624-0.
87. Schmidt, P. W. Small-angle scattering studies of disordered, porous and fractal systems. *J*
Appl Cryst **24**, 414–435 (1991).

88. Hammouda, B. Solvation characteristics of a model water-soluble polymer. *Journal of*
Polymer Science Part B: Polymer Physics **44**, 3195–3199 (2006).
89. Rambo, R. P. & Tainer, J. A. Accurate assessment of mass, models and resolution by
small-angle scattering. *Nature* **496**, 477–481 (2013).
90. Grant, T. D. Ab initio electron density determination directly from solution scattering data.
Nat Methods **15**, 191–193 (2018).
1334