Binding Structures, Mechanical Properties, and Effects on Cellular Behaviors of Extracellular Matrix Proteins on Biomembranes

Veronica Ivanovskaya[1,2,3], Jessica Ruffing[2,4], Minh D. Phan[1,2,5,*]

1 Center for Neutron Research, National Institute of Standards and Technology, Gaithersburg, MD, USA
2 Research Reactor, University of Missouri, Columbia, MO, USA
3 Department of Materials Science, Johns Hopkins University, Baltimore, MD, USA
4 Department of Chemical and Biomedical Engineering, University of Missouri, Columbia, MO, USA
5 Center for Neutron Science, Chemical and Biomolecular Engineering, University of Delaware, Newark, DE, USA

* phanmd@missouri.edu

Abstract

Extracellular matrix (ECM) proteins assemble to form a heterogeneous connective scaffold that supports cells. Physical interactions between cells and the matrix regulate cellular behaviors and influence subsequent tissue construction. However, there is a lack of fundamental understanding regarding the contributions of individual native ECM proteins to the matrix. This gap arises from the need for nanoscopic characterization, which operates on a much smaller length scale than typical assessments in cell and tissue cultures, as well as in tissue reconstruction and clinical implantation. This study aims to systematically investigate how individual ECM proteins affect lipid membranes structurally and mechanically, and how these influences regulate cell migration. Results from Langmuir isotherm analysis, X-ray reflectivity measurements, and cell scratch assays demonstrate that strong collagen adsorption on the membrane surface disrupts lipid packing. However, its rigid network provides a sturdy scaffold for cell adhesion, thereby enhancing cell attachment and promoting cell migration. In contrast, elastin has a minimal structural or mechanical impact on the membrane during both adsorption and compression, but it benefits cells by facilitating migration and reducing the risk of infection. Fibronectin, on the other hand, exhibits complex mechanical responses to compression, characterized by significant structural rearrangements that occur during adsorption. This strong interaction with the membrane can result in excessively high adhesion forces, ultimately limiting cell motility. These findings lay the foundation for the design of artificial scaffolds that can manipulate cellular responses, a critical step toward advancing regenerative medicine and tissue engineering.

Significance

Fabricating extracellular matrix (ECM) scaffolds from cells offers advantages over traditional approaches, such as decellularized tissues, which face donor limitations, and artificial scaffolds, which may hinder cellular communication. However, the slow

harvesting process of cell-derived ECM has limited its clinical applications. This research is part of a larger mission to engineer ECM prescaffolds on lipid carriers tailored to cell requirements, enhancing ECM production and regulating cell behavior. The first step involves systematically analyzing the structural and mechanical effects of ECM on lipid membranes and how these effects regulate cellular behavior. This work confirms distinct characteristics of ECM proteins, advancing fundamental understanding of cell-matrix interactions and paving the way for scaffold engineering.

Introduction

Regenerative medicine focuses on restoring the functionality of lost or damaged tissues by helping the body heal. This field includes gene therapy, cell therapy, specialized drug delivery, and tissue engineering, which use various natural and synthetic materials. Tissue engineering often employs scaffolds, platforms for tissue formation, that can be implanted in the body. Effective scaffolds must be biocompatible, biodegradable, highly porous, and possess adequate mechanical properties to support cell adhesion and growth [1]. Currently, scaffold options include premade porous scaffolds, hydrogel scaffolds, decellularized extracellular matrices and cell-derived extracellular matrices [2]. Pre-made porous scaffolds, while diverse in material, often use artificial polymers that possibly hinder cellular communication [3,4]. Decellularized extracellular matrix scaffolds provide the most native-like environment, but require organ donors, making them challenging to produce. Cell-derived extracellular matrix sheets do not depend on organ donors but have limited applications due to their long production timelines. Ultimately, while various scaffolds exist, extracellular matrix sheets have greater potential to replicate the native extracellular matrix required for effective cell growth once optimized matrix secretion efficiency is achieved.

The extracellular matrix (ECM) is a network of proteins, glycosaminoglycans (GAGs), and proteoglycans synthesized within cells and released through exocytosis [5,6] primarily composed of collagen, elastin, fibronectin, and laminin, with variation in composition among various cell and tissue types [7]. Often described as the glue that connects cells, ECM plays a vital role in cell differentiation, adhesion, and migration, while also regulating the mechanical properties of a cell's environment [8]. The outermost layer of the ECM, the interstitial matrix, contains structural proteins such as collagen types I to III, elastin, and additional proteoglycans [7,9]. These collagens are hydrophobic, stiff, rod-shaped proteins that resist mechanical stress, accounting for about 30% of the total protein mass of the body [7]. Collagen I is essential for providing mechanical strength and stability to the ECM [10], and is deposited at higher concentrations in tissues that need stiffness, such as cartilage and bone. Cells rely on mechanical stimuli from the ECM through mechanotransduction to sense their environment, which affects their migration and adhesion [11]. Elastin, another hydrophobic structural protein found in the interstitial matrix, is characterized as a randomly coiled structure with some covalent crosslinking of hydrophilic lysine residues, giving it amphiphilic properties. As an elastic natural polymer, it provides low stiffness, high extensibility, and efficient storage of elastic energy in the ECM [12]. Elastin is abundant in soft, elastic tissues, including the vascular system, lungs, skin, and bladder. It contributes to biological processes such as migration signaling, cell proliferation, adhesion, and growth [13]. Studies suggest that elastin can improve the fibrillogenesis of collagen I [14] and that fibronectin accelerates the deposition of these two proteins [15,16]. A large dimeric glycoprotein (230-270 kDa), fibronectin serves as a transition molecule, meaning it can be found in both the interstitial matrix and the basement membrane, the lowest layer of the ECM, which consists mainly of laminins, collagen IV, nidogens, and heparan sulfate proteoglycans [17]. Fibronectin, possessing

multiple binding domains connected by cysteine disulfide bonds [18], acts as a
regulatory protein, binding to growth factors, other proteins, and itself in response to
cytoskeletal tensile forces [19]. The protein naturally prefers a folded state when
suspended in solution, but will unfold upon electrostatic interactions [20, 21] or under
mechanical forces [22, 23]. Fibronectin organizes the interstitial matrix through
signaling, adhesion, migration, and morphogenesis, and regulates mechanical properties
similarly to collagen. Its assembly is influenced by the basement membrane, which
anchors ECM proteins with transmembrane proteins that facilitate mechanical and
chemical signaling with cells [24–26].

These native polymers are commonly incorporated into hydrogels and other types of
scaffolds to mimic the ECM. However, the composition of the extracellular environment
evolves over time and is much more complex than that of current scaffolds, making the
development of accurate platforms challenging [7, 27]. ECM secreted by confluent cells
possesses the desired level of sophistication [27]. However, producing it is a slow process
that cannot be optimized without methods to manipulate the resulting matrix and its
modifications. The restructuring of the ECM occurs in response to environmental
stimuli, involving the synthesis or degradation of various molecules to alter its
mechanical and/or chemical properties. Despite significant variations in the mechanical
properties and structures of proteins within the ECM, predicting how restructuring will
occur is difficult due to the overlapping functions of these proteins.

By understanding the mechanical contributions of individual proteins to the ECM,
we can create optimized scaffolds. This can be achieved by supplementing the ECM
with molecular components and manipulating modifications alongside cellular responses.
With this knowledge, growing cells can be supplemented with lipid nanoparticles
containing specific prescaffold native ECM proteins, which would serve as instructions
to direct the cells' ECM secretion. The most prevalent ECM proteins – collagen, elastin,
and fibronectin – exhibit unique mechanical properties, making them suitable for
developing diverse instructions. In this study, our objective is to assess the structures
and mechanical effects of individual ECM proteins on lipid membranes using Langmuir
isotherms and X-ray reflectivity, and to examine these influences on cellular migration
through scratch-assay experiments. The results demonstrate the distinct protein
adsorption, structural, and mechanical behaviors of individual ECM proteins, as well as
the advantages of formulating ECM prescaffolds on lipid membranes, rather than free,
native forms of these proteins in solution, when examining cell proliferation, migration,
and susceptibility to infection.

Materials and Methods

Lipid Monolayer Preparation

14:0 1,2-dimyristoyl-sn-glycero-3-phosphocholine (DMPC) and 14:0
1,2-dimyristoyl-sn-glycero-3-phospho-L-serine (DMPS) lipids obtained from Avanti
Polar Lipids (Alabaster, AL) were used to create a negatively charged lipid monolayer
for the characterization of lipid-protein interactions. DMPC and DMPS were mixed
together at a 4:1 mole ratio and dissolved in a mixture of chloroform and methanol at a
5:1 volume ratio to achieve a 1 mg/mL concentration solution that would then be used
with elastin from bovine neck ligament purchased from Sigma Aldrich (St. Louis, MO)
and human plasma fibronectin from Thermo Fisher Scientific (Carlsbad, CA). This
mixture was selected to create a negatively charged surface, facilitating protein
adsorption and the unfolding of ECM proteins onto the lipid platform [21]. In order to
work with rat type I collagen from Sigma Aldrich (St. Louis, MO), plant cholesterol was
also obtained from Avanti Polar Lipids (Alabaster, AL) and added to a DMPC:DMPS

mixture at a 25 mol% to promote protein association, based on our previous findings [28]. Lipid monolayers were formed using an asymmetric film compression 32.8 x 9.7 cm^2 Langmuir trough system (KSV NIMA 302 M; Biolin Scientific, UK) that was thoroughly cleaned prior to each use by wiping with non-sterile cleanroom wipers soaked in chloroform or ethanol (for Teflon surfaces), and rinsed with MilliQ water. Any remaining water on the trough or barriers was aspirated. The value of surface pressure (Π), calculated from the difference between the bare buffer surface tension and the film-covered surface tension, was monitored by a Wilhelmy plate that hung from a high precision microbalance as given by,

$$\Pi = \gamma_o - \gamma, \tag{1}$$

where γ_o is the surface tension of the air-water interface and γ is the surface tension in the presence of a monolayer film. The platinum Wilhelmy plate was blowtorched to remove any residual solvent, protein, or lipid. The trough was then placed in its plexiglass box with two Kapton windows on an active antivibration table within an X-ray reflectometer (D8 Advance; Bruker, Germany). The trough was filled with a filtered 0.05 M Tris-HCl buffer at pH 7.2, ensuring the liquid level rose above the edges to form a positive meniscus and allowing full contact with the barriers and the Wilhelmy plate. The working surface was cleaned by first closing the barriers, then using gentle aspiration to remove surface contaminants until the compression and expansion of the barriers maintained a constant pressure. To form the monolayer, the lipid mixture was tapped onto the buffer surface in small drops using a Hamilton syringe. The system was given ten minutes for the organic solvents to evaporate and for the monolayers to stabilize before the Π-A isotherms were recorded at a constant compression rate of 2 mm/min.

Mechanical Properties

In order to assess two-dimensional elastic packing interactions within the lipid monolayer, monolayer compressibility C_s was calculated using,

$$C_s = (\frac{-1}{A_\Pi}) \times (\frac{dA}{d\Pi}), \tag{2}$$

where Π is the surface pressure, and A_Π is the molecular area at the calculated Π. Data was collected at 1-second sample intervals. The resulting Langmuir isotherm data were then extracted prior to film collapse and averaged across repeated experiments. Further analysis uses the reciprocal of monolayer compressibility, the elastic modulus of the area compressibility (C_s^{-1}), allowing for quantitative comparison with bilayer lipid systems. The higher modulus indicates the film's greater resistance to area compression, providing insight into the interfacial elasticity arising from lipid-lipid and lipid-protein interactions [28–31]. This method is typically used for amphiphilic molecules, including surfactants, lipids, and polymers, but it can also be applied to less amphiphilic molecules, such as proteins, as long as these molecules are attached to a free-standing platform on the water's surface. Data points nearest to half- and whole-integer values were selected, isolated, and smoothed using LOESS, a nonparametric method that does not require prior trend assumptions, revealing unique trends.

ECM Protein Adsorption Assays and Compression Isotherms

Each of the three proteins was diluted in filtered Tris-HCl buffer and adjusted to various concentrations and pH values. The protein solutions were prepared with final concentrations of 2.9 μg/mL elastin (pH 8.8), 5.69 μg/mL collagen supplemented with

2–3 drops of acetic acid as per the manufacturer's recommendation, and 17.6 μg/mL 136
fibronectin for a 1:5 protein to lipid ratio. These solutions were vortexed prior to use 137
and deposited after the lipid monolayer had been compressed to 12.5 mN/m. This was 138
held constant for 15 minutes to equilibrate the monolayer structure, then switched to 139
fixed surface area (stopped the barriers) while monitoring surface pressure changes. 140
Without disturbing the surface or increasing the surface pressure by more than 0.15 141
mN/m, 1 mL of the individual protein was injected beneath the film by carefully sliding 142
the needle beneath the barriers. The proteins were allowed to adsorb, and changes in 143
surface pressure corresponding to protein adsorption were recorded over 24-72 hours. To 144
minimize evaporation during longer studies, a small dish containing buffer-damped 145
Kimwipes was kept within the plexibox to maintain humidity. The evaporation level 146
was confirmed by X-ray reflectivity, with less than 50 μm change in the water surface 147
position over 65 hours, resulting in less than 0.5 mN/m change in the surface pressure. 148
For the compression isotherms, after protein deposition, the barriers were set to 149
compress at 0.5 mm/min, and the Langmuir isotherm profiles were recorded until lipid 150
film collapse. 151

X-ray Reflectometry 152

X-ray reflectometry (XRR) measurements were performed at a wavelength of $\lambda = 1.54$ 153
Å from a Cu Kα source, using a vertical goniometer and a horizontal sample geometry, 154
on an undisturbed liquid surface. A parallel incident beam was produced by a Göbel 155
mirror and used two slits to define the size of the incident beam and reduce its vertical 156
divergence. Intensity was measured as a function of momentum transfer (q_z), 157

$$q_z = (4sin\theta)/\lambda \tag{3}$$

where λ and θ are the wavelength and incident angle, respectively. Reflectivity was 158
measured over a range of q_z values, allowing determination of thickness and density 159
changes within the protein-lipid layers. X-ray scattering length density (SLD) is a 160
product of $r_e \times \rho$, where r_e is the classical electron radius (2.814×10^{-5} Å) and ρ is the 161
electron density. The X-ray SLD profiles perpendicular to the reflecting interface were 162
acquired from reflectivity data curve fits. In this work, XRR scans were performed on 163
the bare lipid membrane at 12.5 mN/m before and after protein deposition, and after a 164
minimum of 15 hours when the adsorption reached equilibrium. The protein-bound lipid 165
films were then further compressed to pressures of 20 mN/m and 30 mN/m, and XRR 166
was measured accordingly. The data were then analyzed using amoeba and chi-squared 167
fittings in LSFit and DREAM fitting in Refl1D to obtain error ranges. Analysis was 168
performed using a two-layer model, which was later replaced with a more sophisticated 169
three-layer model once it became unrepresentative of the observed protein adsorption 170
system. 171

Scratch Assays 172

HDFn cells obtained from American Type Culture Collection (ATCC) were cultured in 173
accordance with the vendor's recommendations with Fibroblast Basal Media 174
(FBM)(Manassas, VA) from ATCC and supplemented with a Serum Free Fibroblast 175
Growth Kit (Manassas, VA) from ATCC. Passaging was performed every 3 days to 176
provide cells with sufficient nutrients and space to continue proliferating. HDFn cells 177
were passaged four times and seeded into 12-well culture plates at a density of 178
2,500–5,000 cells/cm^2, with 2 mL of growth medium added per well. Each well had a 179
horizontal line drawn to reference during scratching. Lipid monolayers were prepared in 180
previously explained methods with 14:0 1,2-dimyristoyl-sn-glycero-3-phosphocholine 181

(DMPC) and 14:0 1,2-dimyristoyl-sn-glycero-3-phospho-L-serine (DMPS), and plant 182
cholesterol obtained from Avanti Polar Lipids (Alabaster, AL). Elastin from bovine neck 183
ligament purchased from Sigma Aldrich (St. Louis, MO), human plasma fibronectin 184
from Thermo Fisher Scientific (Carlsbad, CA), and rat type I collagen from Sigma 185
Aldrich (St. Louis, MO) were individually adsorbed onto the lipid membranes as 186
previously explained to create an ECM scaffold. Lipid membranes act as carriers of 187
native ECM proteins to cells [32]. Varying experimental conditions were assigned to 188
each well. The protein–lipid mixture was added to achieve a final concentration of 20% 189
(400 µL per well). Conditions were diluted to achieve 10 μg of added protein, with and 190
without vesicles. Cells were grown to 90-100% confluence in media without 191
supplementation from a growth kit. Once grown, a vertical scratch was made using a 192
200 μl pipette tip. Images at 10x magnification were taken from the zeroth to the 193
fifty-fourth hour, with the first hour at 3-hour increments and the remaining hours at 194
6-hour increments. Migration analysis was performed in ImageJ by outlining each 195
scratch with the polygon tool and measuring the scratch area in μm using the measure 196
tool. MATLAB code was developed to extract pixels in the RGB color model with 197
values [195, 255, 0] with a tolerance of 0.3, and to produce a grayscale image or a mask 198
of pixels in this range. The pixels in the mask were compared to the total number of 199
pixels to yield the amount of infection within the cells (Image processing using 200
MATLAB is described in S4, and scratch assay images at selective hours are provided in 201
S5, Supplemental Information). 202

Results 203

Two-Dimensional Lipid Film Characterization 204

Characterizing the lipid monolayers establishes a reference point for evaluating how 205
ECM proteins influence lipid packing and the resulting mechanical behavior. Langmuir 206
isotherms provide a two-dimensional description of the lipid film, capturing not only its 207
mechanical response but also the thermodynamics associated with phase transitions. 208
Upon compression, the monolayer progresses from a highly disordered gaseous phase to 209
more densely packed liquid and solid phases. The Π-A isotherms in Figure S1 210
(Supplemental Information) illustrate how DMPS and cholesterol interact with DMPC. 211
Moreover, the Langmuir setup (Fig. 1A) enables analysis of the thermodynamics of 212
mixing in multicomponent systems via their packing characteristics, the mechanical and 213
rheological properties of the films through their resistance to compression, and the use 214
of a precisely controlled film surface area or packing density for adsorption experiments 215
and surface scattering measurements. 216

Protein Adsorption Assays 217

Adsorption assays provide insight into protein-lipid interactions, allowing observation of 218
parameters such as protein binding affinity, lipid film adsorption capacity, and 219
adsorption kinetics. Figure 1B shows the adsorption assays of each ECM protein as a 220
function of surface pressure change that took place after injection. Collagen adsorption 221
occurs instantaneously, increasing surface pressure by 3.1 mN/m, followed by a sharp 222
decline to 0.4 mN/m. The adsorption curve gradually rises back to its maximum surface 223
pressure, then mildly decreases again, forming a broad peak over 12.5 hours and 224
plateauing thereafter. Elastin exhibits steady adsorption for 40 hours, with a slow 225
increase in surface pressure by only 1.2 mN/m. Fibronectin's adsorption curve followed 226
a sigmoidal trend, reaching saturation at approximately 65 hours with a total surface 227
pressure change of 5.5 mN/m. Note that the adsorption kinetics obtained from the 228

Langmuir apparatus may take longer than similar experiments where both lipid vesicles and proteins are dispersed in solution [21], because it not only depends on lipid-protein interactions but also on the amphiphilicity of proteins that drives them to the water surface.

Figure 1. (A) Langmuir apparatus schematic. (B) Adsorption (Π vs time) of individual proteins to their respective lipid films. The blue curve represents collagen, the yellow represents elastin, and the red represents fibronectin. Mechanical response of individual lipid-adsorbed proteins (C) collagen, (D) elastin, and (E) fibronectin systems to compressive forces. The curves were smoothed using LOESS to track trends without losing data accuracy.

Protein Influence on Lipid Packing and Mechanical Properties

Interfacial elasticity is commonly used to characterize lipids, but can also be applied to other amphiphilic molecules forming a free-standing film or adhering to a platform at the water's surface. The versatility of this method enables the mechanical properties of a wide range of materials to be determined, including ECM proteins, whose mechanical properties are vital for regulating cellular mechanical behavior. As shown in Figure 1C, collagen's deposit slowly increases elastic modulus beginning at 64.4 mN/m, and rising to 81.9 mN/m at a surface pressure of 35 mN/m. During compression, the addition of collagen lowers the initial elastic modulus of the collagen-coated membrane and slows its increase as surface pressure increases, as compared to the pure membrane modulus; however, beyond 35 mN/m, the system significantly stiffens, exhibiting a 160% increase in elastic modulus and reaching a peak value of 255 mN/m at a surface pressure of 42 mN/m. The latter behavior is expected to be dominated by collagen's intrinsic rigidity. In contrast, the mere introduction of elastin does not change the elastic modulus of the lipid system significantly (Fig. 1D). Once compression begins, the overall system shows an increase in elastic modulus to 10 mN/m, but at a surface pressure of 30 mN/m, it triggers an amplified collapse and a decrease in stiffness, a characteristic expected of elastin. The compression of fibronectin, similar to that of collagen, softens the lipid film during the 17.8-25.8 mN/m surface pressure range as indicated by the two local minima and elastic modulus of 30 mN/m (Fig. 1E). The fibronectin-coated membrane stiffens

sharply above 30 mN/m, delaying the collapsing surface pressure by 7.4 mN/m. Both elastin and fibronectin increase the elastic modulus by only 14% from just a pure lipid film with maximum moduli of 91 mN/m.

X-ray Reflectometry of Individual Protein Systems

X-ray reflectometry (XRR) complements the characterization of the protein–lipid system along the third dimension, the z-axis, by recording the intensity of X-rays reflected from individual layers within a free-standing film. Due to the specific atomic composition of lipid molecules, XRR can differentiate between headgroup and tail regions and can detect structural rearrangements following protein adsorption. XRR data were acquired before protein addition, immediately after protein injection, and once protein adsorption had reached equilibrium. Subsequently, the protein-covered lipid films were compressed to surface pressures of 20 and 30 mN/m, and XRR was recorded at each pressure. Two-layer model X-ray scattering length density (SLD) profiles were evaluated against those of the pristine lipid membrane to determine how protein binding alters membrane architecture. When the two-layer fit no longer adequately represented the measured profiles, a three-layer model was employed instead. In the X-ray SLD depth profiles, z = 0 is defined at the midpoint of the lipid headgroup region; negative z values correspond to the protein and subphase side, while positive z values extend toward the lipid tails and air.

Figure 2. (A) X-ray reflectivity data for the lipid membranes before (black) and immediately following (red) collagen deposit, after adsorption (blue), and further compressing at 20 mN/m (green) and 30 mN/m (purple) surface pressures. The lines were generated using an iterative procedure and are the best fits, resulting in (B) the corresponding X-ray scattering length density (SLD) profiles.

At the time of deposition, the collagen-coated membrane (red profile, Fig. 2A) exhibits an oscillation fringe shifted toward lower q_z values and a higher reflectivity compared to the bare membrane (black, Fig. 2A). This corresponds to an increase in both thickness and material density in the lipid headgroup region (red, Fig. 2B), consistent with the adsorption assay results. After allowing additional time for adsorption and equilibration (blue, Fig. 2A), the oscillation fringe in the XRR curve shifts slightly further toward lower q_z, indicating a further increase in overall sample thickness. The corresponding fit suggests that collagen molecules migrate into the region between the head and tail groups, which is reflected by an additional increase in thickness combined with a decrease in the material density of the headgroup region, as well as a reduced tail-region thickness due to packing disruptions (blue, Fig. 2B). Once

compression begins (green and purple, Fig. 2A), the oscillation fringes move further to lower q_z, and the reflectivity diminishes much more rapidly than in the earlier stages, indicating increased interfacial roughness and layer thickness, along with a potential decrease in packing density within the layers. The fitted models corroborate this by showing reduced X-ray SLDs and a pronounced rise in interfacial roughness, which together imply disrupted packing in both the headgroup and tail regions (green and purple, Fig. 2B).

Figure 3. (A) X-ray reflectivity before (black), immediately following elastin deposit (red), after adsorption (blue), and further compressing at 20 mN/m (green) and 30 mN/m (purple) surface pressures. The lines were generated using an iterative procedure and are the best fits, resulting in (B) the corresponding X-ray scattering length density (SLD) profiles.

Upon elastin deposition (red, 3A), the XRR profile shifts slightly toward lower q_z values without notable changes in reflectivity, indicating an increase in the overall sample thickness. The corresponding fit (red, 3B) verifies that the headgroup thickness increases, while the lipid head–tail interfacial roughness decreases slightly, consistent with non-disruptive interactions between elastin molecules and the headgroup region, thereby promoting packing uniformity. This non-disruptive interaction is further evident at the adsorption equilibrium, where both the XRR profile and the fitted model are nearly indistinguishable from those of the bare membrane. Under compression, the XRR profile shifts further toward lower q_z, reflecting a further increase in total thickness (green and purple, 3A). The corresponding fitted models resolve more detailed structural changes: the headgroup thickness and interfacial roughnesses increase, whereas the tail thickness remains constant, implying that elastin is incorporated into the lipid head region and extends to the head–tail interface (green, 3B). By the end of compression, both head and tail thicknesses increase, while the two interfacial roughnesses decrease, pointing to improved layer-by-layer packing uniformity. The non-disruptive behavior of elastin is further underscored by the X-ray SLD values of the head and tail regions, which remain unchanged throughout compression.

Similar to collagen, fibronectin interacts strongly with the lipid monolayer and drives pronounced alterations in membrane structure. Immediately after injection, the XRR profile (red, Fig. 4A) exhibits nearly the same fringe position as the bare membrane but with a modest increase in reflectivity, consistent with a higher material density. The corresponding fit (red, Fig. 4B) indicates that the X-ray SLD of both the head and tail regions increases, with a slight thickening of the headgroup layer and a small reduction in the tail thickness, while the overall thickness and roughness of the film remain essentially unchanged. At adsorption equilibrium, the XRR profile (blue, Fig. 4A)

Figure 4. (A) X-ray reflectivity before (black), immediately following fibronectin deposit (red), adsorption equilibrium (blue), and further compressing at 20 mN/m (green) and 30 mN/m (purple) surface pressures). The lines were generated using an iterative procedure and are the best fits, resulting in (B) the corresponding X-ray scattering length density (SLD) profiles.

displays a further, though small, increase in reflectivity intensity together with the loss of the oscillatory fringe. This suggests a rise in average material density and either a diminished SLD contrast between layers or an increase in interfacial roughness on the scale of the layer thickness. The fit (blue, Fig. 4B) supports the latter interpretation, showing that FN is located between the head and tail regions and induces substantial disorder in the tail layer.

Upon compression (green, Fig. 4A), the reflectivity intensity rises again, and the oscillatory fringe reappears, implying a further increase in material density. In addition, the adsorbed FN molecules reorganize, likely enhancing the SLD contrast between adjacent layers. The fitted model (green, Fig. 4B) indicates a partial recovery of the membrane architecture from the disruption observed at adsorption equilibrium. The headgroup SLD increases, while both its thickness and interfacial roughness decrease, consistent with FN molecules occupying voids in the headgroup region and thereby increasing its density. Conversely, the tail SLD decreases to a value close to that of the pristine membrane, while its thickness increases markedly, suggesting that FN redistributes toward the headgroup region and allows the lipid tails to repack more normally under compression. Additional compression causes a further shift of the fringe toward lower q_z values (purple, Fig. 4A), corresponding to an increase in both tail thickness and SLD, as reflected in the fitted model (purple, Fig. 4B).

Cellular Migration and Infection Assessment by Scratch Assays

After characterizing the structural and mechanical properties of the deposited ECM proteins, we used the same formulations in liposome systems to examine their influence on cellular behavior. We conducted *in vitro* experiments with human neonatal dermal fibroblasts (HDFn), which are key contributors to tissue repair. Scratch assays are commonly employed in wound-healing research to monitor cell migration under various treatment conditions. Following tissue injury, secreted cytokines recruit fibroblasts from surrounding regions [21,33]. During this process, fibroblasts become activated and move toward the damaged area, in parallel with the accumulation of ECM proteins [34,35]. In our experiments, we applied ECM protein-coated liposomes and free soluble ECM proteins to the wounded area as treatments. Figure 5A presents a schematic of the

	X-ray SLD$_{head}$[†]	σ_{head} (Å)	t_{head} (Å)	X-ray SLD$_{tail}$[†]	σ_{tail} (Å)	t_{tail} (Å)
Before COL	11.68	5.0	6.9	9.01	7.2	10.2
COL Injection	12.98	3.0	8.6	10.15	5.3	10.6
COL Equilibrium	12.19	2.9	10.7	9.83	6.0	7.2
COL 20 mN/m	10.86	6.6	8.2	7.58	7.5	10.1
COL 30 mN/m	10.78	7.0	9.3	6.97	8.1	10.9
Before ELAS	11.07	5.3	6.6	8.37	7.2	9.7
ELAS Injection	11.07	4.7	7.5	8.37	7.2	9.7
ELAS Equilibrium	11.07	5.3	6.5	8.37	7.2	9.7
ELAS 20 mN/m	11.07	5.9	9.6	8.37	8.2	9.7
ELAS 30 mN/m	11.07	5.1	11.4	8.37	7.9	10.6
Before FN	11.52	2.5	8.2	8.69	5.7	9.9
FN Injection	12.34	2.9	8.9	9.64	5.8	9.7
FN Equilibrium	13.62	3.0	9.4	10.23	6.7	8.3
FN 20 mN/m	14.60	2.5	7.9	8.21	4.3	11.2
FN 30 mN/m	14.09	4.1	8.0	10.73	6.5	14.5

Table 1. Summary of X-ray fitting parameters. [†] $\times 10^{-6}/\text{Å}^2$

scratch, which is partitioned into two halves within a single well. Figure 5B and C depict the temporal progression of wound closure by cell migration through representative images at 0 and 54 hours, and also show the emergence of bacterial contamination (bright neon dots) observed at the conclusion of the scratch assay (Fig. 5C). The two control samples consisted of: 1) Tris-HCl buffer only without liposomes and ECM proteins, and 2) a liposome solution without ECM proteins (Fig. S5, Supplemental Information).

Free collagen and collagen-coated liposomes drive comparable cell migration for roughly the first 30 hours. After this point, migration in the free collagen group slows and plateaus at 70% wound closure, whereas cells in the collagen-coated liposome group continue to migrate, ultimately reaching 89% coverage (Fig. 5D). In contrast, free elastin initially supports a migration rate similar to that of elastin-coated liposomes for the first 7 hours, then induces a faster migration over the following 21 hours before decelerating and ending at 82% coverage. Treatment with elastin-coated liposomes, however, enhances migration beginning around hour 28, resulting in 89% wound closure by the end of the assay (Fig. 5E). Analogous to the collagen results, free fibronectin and fibronectin-coated liposomes elicit similar migration rates during the first 15 hours. Thereafter, migration with free fibronectin slows and plateaus at 65% healing, while cells in the fibronectin-coated liposome group continue to migrate and achieve 83% closure by the end of the experiment (Fig. 5F). Relative to buffer-only and free liposome conditions, the ranking of final closure from most to least complete is as follows: elastin-coated liposomes (89%) $\simeq$ collagen-coated liposomes (89%) > buffer only (85%) > fibronectin-coated liposomes (83%) $\simeq$ free elastin (83%) > unmodified liposome (78.5%) > free collagen (70%) > free fibronectin (65%). These data underscore two key points: (1) free collagen and fibronectin do not interact sufficiently with cells to effectively enhance cell migration; and (2) liposomes coated with ECM proteins generally stimulate cell migration more effectively than either uncoated liposomes or the corresponding free proteins.

The pattern of bacterial infection rates varies with treatment conditions; nonetheless, the overall trend underscores liposomes' role in limiting infection. In culture medium supplemented with free collagen, infection remains relatively low until approximately hour 30, then rises to a maximum of 0.6% and a minimum of 0.45%, before increasing again thereafter (Fig. 5G). When collagen-coated liposomes are applied, infection stays between 0.13–0.3% before climbing to 0.48% at the conclusion of the experiment.

Figure 5. Evaluation of cell migration and infection rates in collagen, elastin, and fibronectin formulations. The scratch was performed at hour 0 and monitored for 54 hours. Each well plate contributed two data points for the upper and lower halves of the scratch. The shadows represent the actual upper and lower data points, while the central lines represent the average value of the well plate. (B) Cell scratch at 0 h. (C) Cell scratch at 54 h. Neon spherical cells indicate infected or dead cells directly captured by the light microscope. Quantification of the scratch area over time to model (D) cell migration and (G) infection rate in collagen alone (black) and collagen-coated liposomes (red). Likewise, (E) cell migration and (H) infection rates were measured under conditions with elastin alone (black) and elastin-coated liposomes (red). Similarly, (F) cellular migration and (I) infection development were evaluated for fibronectin alone (black) and fibronectin-coated liposomes (red).

Treatment with free elastin leads to infection peaking at 0.8% at hour 37, then declining to 0.4% and subsequently rising again to 0.56% by the end of the assay (Fig. 5H). In contrast, elastin-coated liposomes maintain infection levels of 0.1–0.28%. Free fibronectin treatment results in contamination reaching 1.5% at the end of the assay, whereas fibronectin-coated liposomes keep contamination between 0.2–0.35% throughout (Fig. 5I). Relative to the two control conditions, the progression from lowest to highest infection at the end of the assays is: elastin-coated liposome (0.17%) < fibronectin-coated liposome (0.24%) < buffer alone (0.35%) < unmodified liposome (0.44%) < collagen-coated liposome (0.49%) < free elastin (0.56%) < free collagen (0.58%) < free fibronectin (1.5%). These findings indicate that liposomes themselves do not necessarily reduce infection, but rather serve as a platform on which ECM proteins, such as elastin and fibronectin, can unfold, making the membrane surface less permissive to infection. In contrast, ECM proteins in solution—particularly collagen and fibronectin—not only fail to interact effectively with cells and their secreted matrix to facilitate migration, but also actively increase infection.

Discussion

Individual Protein-Lipid Interactions

To develop an instructive scaffold environment, the ECM proteins employed are key to guiding cell behavior. Different mechanical properties and interactions of these proteins can be tailored to different mini-scaffold recipes to promote desired cell responses, whether that be growth and healing or cell differentiation. Prior to fabricating this pre-designed platform, the mechanoproperties of these proteins must first be characterized and understood to determine the most effective protein composition blends. The three proteins discussed in this study have been shown to possess different adsorption and mechanical behaviors and continue to differ in their binary and tertiary systems. The combined results from the interfacial elastic modulus, adsorption assays, X-ray reflectivity profiles, and cell scratch assays shed light on each protein's unique role in the extracellular matrix and help to define their future application in mini-scaffolds.

Figure 6. Schematic Representation of (A) collagen, (B) elastin, and (C) fibronectin proteins' adsorption mechanisms in response to compressive forces. These models were determined using the adsorption assays and X-ray reflectivity profiles.

Among these proteins, collagen is one of the most well-studied ECM proteins in terms of mechanical behavior and structure, and thus this characterization serves to validate and refine the collagen-lipid monolayer interaction model (Fig 6A). After spontaneous integration between the head and tail groups of the lipid, the start of compression showed a minor softening of the system (Fig. 1C). This protein, as discussed previously, significantly contributes to the strength and stability of the ECM, which collagen's compression curve corroborates. This, however, appears to contradict the observed softening of the monolayer; the notable rise in elastic modulus at 35 mN/m surface pressure, however, supports literature findings. Collagen's rigid rod structure allows the protein to possess high compressive stiffness and fracture resistance [36]. Instead, as compression begins, the proteins move and puncture through the monolayer, disrupting it, as indicated by increased roughness and decreased SLD (Table 1). The lipid monolayer eventually reassembles at 35 mN/m, at which point proteins can no longer rearrange and take up the compressive load imposed by the moving barriers (Fig. 1C). The residual sample at the bottom of the trough is most likely the lipid-protein

sample that sank after disruption (Fig. S2A, Supplemental Information).   422

Elastin, whose primary recorded mechanical function is to store elastic energy,   423
interacts much more passively with the lipid monolayer. The protein adsorbs more   424
slowly than collagen and interacts with the head groups, only moving between the head   425
and tail groups in response to compressive force, as evident by the changes in thickness 426
and roughness of the headgroup layer (Fig 6B). Given the lack of residual protein in the 427
trough between experiments, it is apparent that elastin is fully adsorbed onto the lipid   428
film, allowing it to be aspirated along with the monolayer. This full incorporation of the 429
protein with the lipid system is similar to that of collagen before compression, where   430
collagen's rigidity causes further disruption, but elastin's mechanical properties don't 431
modify lipid film behavior while a compressive force is applied (Fig. 1D). The   432
elastin-monolayer and pure monolayer systems collapse at the same pressure,   433
demonstrating that the addition of elastin to the monolayer increases elastic modulus   434
with no new mechanical behavior. This increase in modulus is due to an increase in the   435
volume of material resisting compression, but the protein's energy storage and elasticity 436
cannot be observed during compression. After the collapse of the system, the elastic   437
modulus drop is far higher than that of the lipid control, showcasing elastin's   438
"amplification" effect and energy storage as the protein permits greater folding and   439
softens the membrane more.   440

As the only basement membrane protein out of the three studied, fibronectin showed   441
a drastically different adsorption and interaction mechanism with the lipid monolayer   442
(Fig 6C). At a slower rate than collagen (Fig. 1B), fibronectin adsorbs onto the lipid,   443
settling between the head and tail groups, as indicated by dramatic increases in SLD of   444
both head and tail layers (Table 1). In solution, fibronectin adopts a compact folded   445
conformation, but upon adsorption it unfolds, enabling greater FN-FN binding [37].   446
Over time, the protein begins to form a network, weighing down the protein-bound   447
monolayer and increasing the SLD and thicknesses of the head and tail group layers, as   448
recorded in the x-ray reflectivity profiles (Fig. 4C and Table 1). Once compression   449
begins in response to the mechanical stimulus, the protein network continues to   450
assemble, dragging the monolayer downward. This result aligns with earlier reports   451
showing that fibronectin can trigger vesicle budding upon binding to giant unilamellar   452
vesicles [38]. As the film bulges inward, changes in roughness (Table 1) and the drop in 453
elastic modulus (Fig. 1E) can be attributed to this mechanical interaction. The greater   454
the compressive force, the greater the lipid film bulges, and eventually the lipid-protein 455
bubbles drop to the bottom of the trough. This process is revealed by the first local   456
minima in the compression curve (Fig. 1E) and in the protein-lipid remnants at the   457
bottom of the trough (Fig. S2B, Supplemental Information). Breaks in the monolayer   458
soften the system, and the monolayer stiffens only once the lipids reassemble into an   459
uninterrupted film. For the rest of the compression, the remaining fibronectin network   460
resists the compressive load applied to the system, stiffening it until a delayed collapse 461
from the loss of material, suggesting fibronectin's minor mechanical function in the   462
ECM.   463

Influences on Cellular Behaviors   464

The adsorption behavior and the structural and mechanical properties arising from   465
protein–lipid interactions significantly influence the cellular responses observed in the 466
scratch assay. Presentation of extracellular matrix (ECM) proteins on liposomes alters   467
both migration dynamics and infection susceptibility compared to protein-only   468
conditions. These findings suggest that not only protein identity, but also the   469
mechanical and structural context in which proteins are presented, play a critical role in 470
regulating cell behavior.   471

When introduced alone, these ECM proteins either exert minimal influence (elastin)   472

or markedly inhibit cell migration (fibronectin and collagen). This is likely due to ineffective interactions with cells, which in turn diminish cellular motility. Notably, despite elastin and collagen possessing contrasting mechanical characteristics, their liposome-bound forms both enhance cell migration. The soft, elastic behavior of elastin at membrane interfaces aligns with the mechanical properties of skin cells, thereby facilitating fibroblast uptake during migration. Collagen on liposomes assembles in a more regulated manner [28], which improves fibroblast attachment during migration, whereas free collagen can spontaneously form large fibrils in solution, ultimately impeding cell movement. Treatment with fibronectin-coated liposomes slightly reduces the cell migration rate compared with the control. As a basement membrane protein, fibronectin exhibits a strong interaction with the lipid membrane and causes disruption (Fig. 4). When cells encounter fibronectin, its interaction with integrins can generate adhesion forces that can be excessively strong, thereby constraining cell motility [39].

The fluid and compliant nature of the lipid interface likely enabled dynamic ligand presentation, facilitating continuous adhesion turnover, which is necessary for efficient cell migration [40]. Enhanced migration in liposome-associated conditions may therefore result from optimized adhesion strength. Excessively strong adhesion can restrict movement, whereas insufficient adhesion limits traction generation [39]. The lipid-supported ECM proteins may provide an intermediate mechanical environment that promotes integrin engagement while maintaining adhesion plasticity, allowing cells to reorganize attachments and migrate more effectively across the wound area [41].

In addition to promoting migration, ECM proteins coated liposomes substantially reduce bacterial contamination across all three ECM systems. This observation is consistent with studies by Lee et al. and Chabria et al., where they similarly showed that stretched fibronectin can make the membrane surface less favorable for bacterial colonization, particularly Staphylococcus aureus (S. aureus), a frequent cause of opportunistic skin infections that can result in tissue damage [21, 42]. Another possible explanation is that altered protein conformation or spatial organization on lipid vesicles, which apply for all three ECM proteins, limits accessibility of viral binding sites or reduces receptor clustering required for efficient internalization [43]. Although our control group using unmodified liposomes did not exhibit a significant reduction in infection, earlier studies have demonstrated the antibacterial activity and infection-treating capabilities of liposomes [41, 44]. Together, these results demonstrate that protein–lipid interactions modulate both mechanical signaling and pathogen susceptibility in cultured cells. The ability to engineer ECM scaffolds through lipid platforms may provide a strategy to simultaneously enhance tissue regeneration while limiting infection risk, highlighting potential applications in wound healing, biomaterial coatings, and therapeutic delivery systems.

Conclusions

In conclusion, our study systematically examined individual ECM proteins, examining how they structurally and mechanically affect lipid membranes and regulate cell migration. These proteins display distinct behaviors. Strong collagen adsorption on the membrane surface disrupts lipid packing, while its intrinsic rigidity yields an elastic modulus that is markedly higher than that of elastin or fibronectin. This stiff collagen network can form a robust scaffold for cell adhesion when its assembly is directed by the membrane, thereby enhancing cell attachment and promoting cell migration. In contrast, elastin exerts minimal structural or mechanical influence on the membrane during both adsorption and compression, yet it benefits cells by promoting migration and reducing infection. Fibronectin, on the other hand, exhibits complex mechanical responses to compression, associated with pronounced structural rearrangements

initiated during adsorption. This strong interaction with the membrane, together with its specific binding to integrins on the cell surface, can generate excessively high adhesion forces that ultimately restrict cell motility.

The ratios of these proteins will later be tuned in the mixture to enhance cell growth, migration, and healing based on their mechanical behavior and interprotein interactions. Collagen is stiff in compression and provides the structural foundation for the ECM, while elastin, the other interstitial matrix protein, amplifies the mechanical properties of the ECM proteins by acting as a connecting molecule. Fibronectin, as a protein that interacts with both cell receptors and interstitial proteins, forms large networks and is more responsive to external stresses, but it cannot provide mechanical stability. These findings provide a better understanding of how the ECM interacts mechanically with itself, enabling us to begin manipulating and hastening ECM secretion. Additionally, knowledge of these proteins' interactions and additive capabilities can enable the production of a strategically designed native scaffold and various materials tailored for specific biomedical applications.

Author Contributions

M.D.P. designed the research. V.I. carried out Langmuir isotherms, protein adsorption assays, and performed interfacial elastic calculations. V.I. and J.R. performed and analyzed scratch assays. V.I. and M.D.P. carried out X-ray reflectivity experiments. M.D.P. analyzed and modeled X-ray data. V.I, J.R., and M.D.P wrote the article.

Acknowledgments

Support for M.D.P. was provided through the Midscale RI:1 program of the NSF, Award DMR-1935956. Support for V.I. was provided by the Center for High Resolution Neutron Scattering, a partnership between the National Institute of Standards and Technology and the National Science Foundation under Agreement No. DMR-2010792. This research was also partially supported by funds from the University of Missouri Research Reactor through the Nuclear Science Career Academy Summer 2025 Internship Program. We thank Dr. Sushil Satija for the help in setting up the X-ray instrument at the NIST Center for Neutron Research (NCNR). Additionally, V.I. thanks Julie Borchers, Donna Kalteyer, and Juscelino Leao for their support during the SURF 2024 Internship program at NCNR. We are deeply grateful for the assistance in cell experiments from Dr. Taixing Cui's lab at Mizzou's Dalton Cardiovascular Research Center, particularly Dr. Yixiao Liu and Dr. Jianxin Yan. The commercial products used in this study were referenced only to adequately specify the experimental procedure. Such identification of commercial products is not intended to imply recommendation or endorsement by the National Institute of Standards and Technology, nor is it intended to imply that the identified products are necessarily the best available for the purpose.

References

1. Mohsen Hosseinkhani, Davood Mehrabani, Mohammad Hassan Karimfar, Salar Bakhtiyari, Amir Manafi, and Reza Shirazi. Tissue engineered scaffolds in regenerative medicine. *World journal of plastic surgery*, 3(1):3, 2014.

2. BP Chan and KW Leong. Scaffolding in tissue engineering: general approaches and tissue-specific considerations. *European spine journal*, 17:467–479, 2008.

3. Joon Pio Hong, Joanneke Maitz, and Matthias Mörgelin. Comparison of cell-scaffold interactions in a biological and a synthetic wound matrix. *International Wound Journal*, 22(1):e70108, 2025.

4. Thomas Lee Jenkins and Dianne Little. Synthetic scaffolds for musculoskeletal tissue engineering: cellular responses to fiber parameters. *NPJ Regenerative medicine*, 4(1):15, 2019.

5. Hector Capella-Monsonís, Stephen Badylak, and Marley Dewey. Extracellular matrix bioscaffolds: Structure-function. In *Handbook of the Extracellular Matrix: Biologically-Derived Materials*, pages 1–22. Springer, 2023.

6. Tania Rozario and Douglas W DeSimone. The extracellular matrix in development and morphogenesis: a dynamic view. *Developmental biology*, 341(1):126–140, 2010.

7. Nikos K Karamanos, Achilleas D Theocharis, Zoi Piperigkou, Dimitra Manou, Alberto Passi, Spyros S Skandalis, Demitrios H Vynios, Véronique Orian-Rousseau, Sylvie Ricard-Blum, Christian EH Schmelzer, et al. A guide to the composition and functions of the extracellular matrix. *The FEBS journal*, 288(24):6850–6912, 2021.

8. Jaspreet K Kular, Shouvik Basu, and Ram I Sharma. The extracellular matrix: Structure, composition, age-related differences, tools for analysis and applications for tissue engineering. *Journal of tissue engineering*, 5:2041731414557112, 2014.

9. Anna Zhou, Jie Qu, Min Liu, and Patrick Tso. The role of interstitial matrix and the lymphatic system in gastrointestinal lipid and lipoprotein metabolism. *Frontiers in physiology*, 11:4, 2020.

10. Kristopher E Kubow, Radmila Vukmirovic, Lin Zhe, Enrico Klotzsch, Michael L Smith, Delphine Gourdon, Sheila Luna, and Viola Vogel. Mechanical forces regulate the interactions of fibronectin and collagen i in extracellular matrix. *Nature communications*, 6(1):8026, 2015.

11. Fabiana Martino, Ana R Perestrelo, Vladimír Vinarský, Stefania Pagliari, and Giancarlo Forte. Cellular mechanotransduction: from tension to function. *Frontiers in physiology*, 9:824, 2018.

12. Hanna Trebacz and Angelika Barzycka. Mechanical properties and functions of elastin: an overview. *Biomolecules*, 13(3):574, 2023.

13. Amandine Scandolera, Ludivine Odoul, Stéphanie Salesse, Alexandre Guillot, Sébastien Blaise, Charlotte Kawecki, Pascal Maurice, Hassan El Btaouri, Béatrice Romier-Crouzet, Laurent Martiny, et al. The elastin receptor complex: a unique matricellular receptor with high anti-tumoral potential. *Frontiers in pharmacology*, 7:32, 2016.

14. Nelda Vazquez-Portalatin, Alba Alfonso-Garcia, Julie C Liu, Laura Marcu, and Alyssa Panitch. Physical, biomechanical, and optical characterization of collagen and elastin blend hydrogels. *Annals of biomedical engineering*, 48:2924–2935, 2020.

15. Daniele Pezzoli, Joseph Di Paolo, Heena Kumra, Giulia Fois, Gabriele Candiani, Dieter P Reinhardt, and Diego Mantovani. Fibronectin promotes elastin deposition, elasticity and mechanical strength in cellularised collagen-based scaffolds. *Biomaterials*, 180:130–142, 2018.

16. Jeffrey A Paten, Cassandra L Martin, Jamil T Wanis, Seyed Mohammad Siadat, Amanda M Figueroa-Navedo, Jeffrey W Ruberti, and Leila F Deravi. Molecular interactions between collagen and fibronectin: a reciprocal relationship that regulates de novo fibrillogenesis. *Chem*, 5(8):2126–2145, 2019.

17. Ambra Pozzi, Peter D Yurchenco, and Renato V Iozzo. The nature and biology of basement membranes. *Matrix Biology*, 57:1–11, 2017.

18. Christian Frantz, Kathleen M Stewart, and Valerie M Weaver. The extracellular matrix at a glance. *Journal of cell science*, 123(24):4195–4200, 2010.

19. Mateusz K Bieniek, Virginia Llopis-Hernandez, Katie Douglas, Manuel Salmeron-Sanchez, and Christian D Lorenz. Minor chemistry changes alter surface hydration to control fibronectin adsorption and assembly into nanofibrils. *Advanced Theory and Simulations*, 2(12):1900169, 2019.

20. Seungkuk Ahn, Leila F Deravi, Sung-Jin Park, Borna E Dabiri, Joon-Seop Kim, Kevin Kit Parker, and Kwanwoo Shin. Self-organizing large-scale extracellular-matrix protein networks. *Advanced materials*, 27(18):2838–2845, 2015.

21. Keel Yong Lee, Huong Thanh Nguyen, Agustina Setiawati, So-Jung Nam, Minyoung Kim, Il-Gyu Ko, Won Hee Jung, Kevin K Parker, Chang-Ju Kim, and Kwanwoo Shin. An extracellular matrix-liposome composite, a novel extracellular matrix delivery system for accelerated tissue regeneration. *Advanced healthcare materials*, 11(4):2101599, 2022.

22. Leila F Deravi, Tianxiang Su, Jeffrey A Paten, Jeffrey W Ruberti, Katia Bertoldi, and Kevin Kit Parker. Differential contributions of conformation extension and domain unfolding to properties of fibronectin nanotextiles. *Nano letters*, 12(11):5587–5592, 2012.

23. Christophe O Chantre, Patrick H Campbell, Holly M Golecki, Adrian T Buganza, Andrew K Capulli, Leila F Deravi, Stephanie Dauth, Sean P Sheehy, Jeffrey A Paten, Karl Gledhill, et al. Production-scale fibronectin nanofibers promote wound closure and tissue repair in a dermal mouse model. *Biomaterials*, 166:96–108, 2018.

24. Lewis J et al. Alberts B, Johnson A. *Molecular biology of the cell*. Garland Science, Boca Raton, FL, 4 edition, March 2002. Integrins.

25. Karl E Kadler, Adele Hill, and Elizabeth G Canty-Laird. Collagen fibrillogenesis: fibronectin, integrins, and minor collagens as organizers and nucleators. *Current opinion in cell biology*, 20(5):495–501, 2008.

26. Jiaoyang Lu, Andrew D Doyle, Yoshinari Shinsato, Shaohe Wang, Molly A Bodendorfer, Minhua Zheng, and Kenneth M Yamada. Basement membrane regulates fibronectin organization using sliding focal adhesions driven by a contractile winch. *Developmental Cell*, 52(5):631–646, 2020.

27. Ulrich Blache, Molly M Stevens, and Eileen Gentleman. Harnessing the secreted extracellular matrix to engineer tissues. *Nature biomedical engineering*, 4(4):357–363, 2020.

28. Minh D Phan, Keel Yong Lee, Jumi Lee, Sushil K Satija, and Kwanwoo Shin. The effect of cholesterol on membrane binding and self-assembly of collagen fibrils. *Langmuir*, 36(26):7259–7267, 2020.

29. Minh Dinh Phan and Kwanwoo Shin. Effects of cardiolipin on membrane morphology: a langmuir monolayer study. *Biophysical journal*, 108(8):1977–1986, 2015.

30. Kiet G Pham, Benjamin R Thompson, Minh Phan, Frank Heinrich, Yun Liu, Tingting Wang, Ken K Qian, and Norman J Wagner. Shear and dilatational rheology and interfacial structure of a monoclonal antibody adsorbed at the air–liquid interface. *Langmuir*, 41(45):30102–30115, 2025.

31. Benjamin R Thompson, Kiet G Pham, Minh D Phan, Pablo Sanchez-Puga, Philipp Gutfreund, Tingting Wang, Ken K Qian, Frank Heinrich, Yun Liu, and Norman J Wagner. Competitive adsorption of monoclonal antibodies and nonionic surfactants at the air–water interface. *ACS Applied Materials & Interfaces*, 17(28):40116–40128, 2025.

32. Minh D Phan, Olena I Korotych, Nathan G Brady, Madeline M Davis, Sushil K Satija, John F Ankner, and Barry D Bruce. X-ray and neutron reflectivity studies of styrene-maleic acid copolymer interactions with galactolipid-containing monolayers. *Langmuir*, 36(14):3970–3980, 2020.

33. Wing S To and Kim S Midwood. Plasma and cellular fibronectin: distinct and independent functions during tissue repair. *Fibrogenesis & tissue repair*, 4(1):21, 2011.

34. Lauren E Tracy, Raquel A Minasian, and EJ Caterson. Extracellular matrix and dermal fibroblast function in the healing wound. *Advances in wound care*, 5(3):119–136, 2016.

35. Richard AF Clark, Joan M Lanigan, Patricia DellaPelle, Eleanor Manseau, Harold F Dvorak, and Robert B Colvin. Fibronectin and fibrin provide a provisional matrix for epidermal cell migration during wound reepithelialization. *Journal of Investigative Dermatology*, 79(5):264–269, 1982.

36. Anne M Römgens, Corrinus C Van Donkelaar, and Keita Ito. Contribution of collagen fibers to the compressive stiffness of cartilaginous tissues. *Biomechanics and modeling in mechanobiology*, 12(6):1221–1231, 2013.

37. Lisa M Maurer, Wenjiang Ma, and Deane F Mosher. Dynamic structure of plasma fibronectin. *Critical reviews in biochemistry and molecular biology*, 51(4):213–227, 2016.

38. Keel Yong Lee, Huong Thanh Nguyen, Sungwoo Jeong, Kevin Kit Parker, and Kwanwoo Shin. Extracellular matrix-coated vesicles as a biomimetic model of membranematrix interplay. *Small Methods*, page e01785, 2025.

39. Dennis E Discher, Paul Janmey, and Yu-li Wang. Tissue cells feel and respond to the stiffness of their substrate. *Science*, 310(5751):1139–1143, 2005.

40. Elisabetta Ada Cavalcanti-Adam, Tova Volberg, Alexandre Micoulet, Horst Kessler, Benjamin Geiger, and Joachim Pius Spatz. Cell spreading and focal adhesion dynamics are regulated by spacing of integrin ligands. *Biophysical journal*, 92(8):2964–2974, 2007.

41. Y Wang. Liposome as a delivery system for the treatment of biofilm-mediated infections. *Journal of applied microbiology*, 131(6):2626–2639, 2021.

42. Mamta Chabria, Samuel Hertig, Michael L Smith, and Viola Vogel. Stretching fibronectin fibres disrupts binding of bacterial adhesins by physically destroying an epitope. *Nature communications*, 1(1):135, 2010.

43. Judith M. White. Integrins as virus receptors. *Current Biology*, 3(9):596–599, 1993.

44. Gang Shu, Dan Xu, Wei Zhang, Xiaoling Zhao, Haohuan Li, Funeng Xu, Lizi Yin, Xi Peng, Hualin Fu, Li-Jen Chang, et al. Preparation of shikonin liposome and evaluation of its in vitro antibacterial and in vivo infected wound healing activity. *Phytomedicine*, 99:154035, 2022.