1 **Synthesis of extracellular stable gold nanoparticles by *Cupriavidus metallidurans* CH34 cells**
2 **(revision)**

3

4 Francisco Montero-Silva

5

6 Laboratorio de Microbiología Molecular y Biotecnología Ambiental, Departamento de Química,
7 Universidad Técnica Federico Santa María, Valparaíso, Chile.

8

9

10 Abstract

11

12 The biogenic synthesis of metallic nanoparticles is of increasing interest. In this report, synthesis of gold
 13 nanoparticles by the model heavy metal-resistant strain *Cupriavidus metallidurans* CH34 and *Escherichia*
 14 *coli* strain MG1655 was studied. For the synthesis of AuNPs, bacterial cells and secretomes were
 15 incubated with Au(III) ions, revealing that only CH34 cells can produce dispersions of AuNPs.
 16 Comparative bioinformatic analysis of proteomes from both strains showed potential CH34 proteins that
 17 may be electron donors during reduction of extracellular Au(III) ions and for the biosynthesis of gold
 18 nuggets in nature. Powder X-ray diffraction demonstrated that biogenic AuNPs are composed of face-
 19 centered cubic gold with a crystallinity biased towards {111} planes. Transmission electron microscopy
 20 images showed that AuNPs morphology was dominated by triangular and decahedral nanostructures.
 21 EDX and FT-IR spectra showed the presence of sulfur and vibrations associated to the biogenic AuNPs.
 22 Based on these results, and analyses of previous genomic and proteomic data, a mechanism for
 23 extracellular gold reduction and synthesis of AuNPs by strain CH34 is proposed. Average AuNPs
 24 diameter was obtained by nanoparticle tracking analysis, dynamic light scattering and analysis of electron
 25 microscopy images. DLS studies showed that biogenic AuNPs colloids are stable after exposure to
 26 ultrasound, high ionic strength and extreme pH conditions, and revealed the presence of basic groups
 27 associated to the AuNPs surface. Electrophoretic and dynamic light scattering indicated that biogenic
 28 dispersions of AuNPs are stabilized by a steric mechanism. The AuNPs produced by *C. metallidurans*
 29 CH34 are not cytotoxic towards bacterial cells, in contrast to biogenic AgNPs. These stable non-toxic
 30 biogenic AuNPs have potential clinical applications including development of topic delivery formulations
 31 and optical biosensors.

32

33 Keywords

34

35 *Cupriavidus metallidurans* CH34, protein mediated gold reduction, gold nanoparticles, biogenic AuNPs,
 36 extracellular nanoparticles.

1 Introduction

38

39 The need for cost-effective eco-friendly synthesis of metallic nanoparticles has established new
40 methods to replace the chemical synthesis. The biogenic synthesis of nanoparticles is of increasing
41 interest. Bacteria are versatile biocatalysts for detoxification and biotransformation of heavy metals and
42 aromatic compounds [1–8]. Microbial systems have been selected for synthesis of nanoparticles due to
43 their detoxification mechanisms of metallic ions through extracellular or intracellular reduction. Biogenic
44 synthesis of metallic nanoparticles by diverse microorganisms has been described [9, 10]. Accordingly,
45 synthesis of gold nanoparticles by *Pseudomonas*, *Shewanella* and *Streptomyces* strains has been reported
46 [11–15].

47 *C. metallidurans* is a model heavy metal-resistant bacterium that harbours gene clusters enabling
48 detoxification of diverse heavy metal ions and complexes [1, 2, 16, 17]. Interestingly, *C. metallidurans* is
49 also involved in the biogeochemical cycle of gold. Presence of *C. metallidurans* cells in biofilms that
50 covered the surface of gold grains has been reported [18, 19]. Transcriptomic analysis suggested that
51 oxidative stress and heavy metal resistances genes including an Au-specific operon were involved in Au
52 reduction by *C. metallidurans* [19]. Recently, formation of gold nanoparticle and microparticle aggregates
53 onto the surface *C. metallidurans* biofilms has been reported [20].

54 The aim of this study was to obtain a stable dispersion of AuNPs by *C. metallidurans* CH34 cells.
55 Bacterial cultures were fractionated and exposed to a gold aqueous solution. Using this procedure
56 extracellular dispersions of NPs were obtained. The biogenic colloid of dispersed AuNPs was
57 characterized by surface plasmon spectroscopy, dynamic and electrophoretic light scattering and
58 nanoparticle tracking analysis. Solid state AuNPs were characterized by powder X-ray diffraction, Fourier
59 transform infrared spectroscopy and TEM. Stability of the colloid was characterized by electrophoretic
60 and dynamic light scattering. A synthesis mechanism is proposed. Finally, cytotoxic effect of the biogenic
61 gold NPs on bacterial growth was evaluated.

62

2 Experimental

64

2.1 Materials

66

67 Solid H₂AuCl₄·3 H₂O (99.9% purity) was obtained from Sigma Aldrich (Saint Louis, MO, USA).
68 NaCl, NaOH and KCl were obtained from Merck (Darmstadt, Germany). Beef extract and yeast extract
69 were acquired from Becton Dickinson (Cockeysville, MD, USA) and agar solid medium was obtained
70 from Merck (Darmstadt, Germany). Biogenic AgNPs (40 nm average diameter) were recovered from
71 fungal *Fusarium oxysporum* filtrates [13].

72

2.2 Biosynthesis of gold nanoparticles

74

75 *C. metallidurans* CH34 [21] and *E. coli* MG1655 [22] were grown in a low ionic strength
76 medium with meat extract (20 g L⁻¹) and yeast extract (20 g L⁻¹) [23]. Biogenic synthesis of gold

nanoparticles was done according to methods A and B [13], with modifications (Fig. 1S). Method A evaluates the effect of bacterial biomass on the biogenic synthesis of AuNPs, and method B evaluates the effect of bacterial extracellular medium on the gold reduction process. In method A, biomass (40 mL) was directly exposed to a gold solution achieving a final concentration of 2 mM. In method B, bacterial biomass was used to obtain bacterial filtrates that were exposed to a gold solution (2 mM). In both methods, cell cultures grown until stationary phase were used as starting bacterial biomass. For method A, cells were collected by centrifugation and washed 3 times with doubly deionized water. Cell pellet was suspended in doubly deionized water and diluted up to a concentration of 3.3×10^9 CFU mL⁻¹. The bacterial suspension was exposed to AuCl₄⁻ (2 mM) and then incubated during 96 h in darkness without shaking at 30° C. The HAuCl₄ stock solution (40 mM) was previously adjusted to pH 7 with NaOH. To recover the biogenic colloid, the bacterial suspension was centrifuged at $5,000 \times g$ during 10 min and supernatant was filtered using a 0.45 µm pore size nitrocellulose membrane. The dispersion of biogenic AuNPs was recovered in the permeate fraction. For method B, cells from a stationary phase bacterial culture were collected by centrifugation and washed 3 times with doubly deionized water. Cell pellet was suspended in doubly deionized water and diluted up to a concentration of 6×10^9 CFU mL⁻¹. To obtain the bacterial secretome, biomass was incubated during 3 days in flasks with shaking (150 rpm) at 30° C. Cells were centrifuged at $5,000 \times g$ during 10 min and the supernatant was recovered and filtered using a 0.2 µm pore size nitrocellulose membrane. The bacterial secretomes were recovered [24] and incubated with AuCl₄⁻ (2 mM) during 96 h in darkness without shaking at 30° C.

2.3 Characterization of biogenic gold nanoparticles

The UV-visible absorbance spectra of gold nanoparticles were obtained at room temperature with an Agilent 8453 spectrophotometer equipped with a diode array (Palo Alto, CA, USA). Hydrodynamic diameter (Z-Ave) and dispersion index (PdI) of the biogenic dispersions were determined by dynamic light scattering (DLS) measurements, and zeta-potentials (ζ-potentials) were measured by electrophoretic light scattering using a ZetaSizer Nano ZS instrument (Malvern, Worcestershire, UK). Additional particles size distributions and concentration were determined by nanoparticle tracking analysis (NTA) technology using a NanoSight LM20 device (Amesbury, UK). In all cases, temperature was fixed at 25° C and 1 mM KCl solution was used as dissolvent. Morphology and size distribution of the biogenic AuNPs was observed by transmission electron microscopy. Images were obtained using a Carl Zeiss (Libra) transmission electron microscope (TEM) operating at 120 keV and analyzed using software ImageJ 1.47v. To obtain the images, one drop of biogenic AuNPs was deposited on a carbon-coated parlodion film supported in 300 mesh copper grids (Ted Pella, Redding, CA, USA). For EDX measurements, biogenic AuNPs were extensively washed with MilliQ water, concentrated by centrifugation, and deposited on a carbon grid. Spectra were acquired with a Carl Zeiss, EVO MA-10 device. Solid state characterization was done to powder samples of the biogenic AuNPs. To obtain the powder samples, colloidal dispersions of biogenic AuNPs were centrifuged at $20,000 \times g$ during 20 min and then washed 3 times with MilliQ water. The resulting sediment containing the biogenic AuNPs was lyophilized and then analyzed by powder X-ray diffraction (XRD) and Fourier transform infrared (FT-IR) spectrometry. Powder XRD

spectra were obtained in a Shimadzu XRD 6000 diffractometer using Cu K α radiation (1.5406 Å) operating at 30 mA and 40 kV. Scan speed was 0.02 degree min⁻¹ and time constant was 2 s. FT-IR spectra of powder samples were recorded using a Bomem MB spectrometer in the 4,000-400 cm⁻¹ frequency range using an attenuated total reflectance mode. A total of 250 scans and a resolution of 4 cm⁻¹ were employed to obtain each spectrum. Concentrations of gold and silver in the nanoparticles dispersions were determined by inductively coupled plasma (ICP) Perkin Elmer Optima 3000 DV spectrometry.

2.4 Cytotoxic activity assays

The cytotoxic effect of biogenic AuNPs and Ag nanoparticles on *E. coli* MG1655 cells was evaluated by minimal inhibition concentration (MIC) measurements. MIC of biogenic nanoparticles was determined by the microdilution method [25]. The liquid medium used in these assays contained meat extract (5 g L⁻¹) and yeast extract (5 g L⁻¹) and was inoculated to a final bacterial concentration of 5 × 10⁵ CFU mL⁻¹. Aliquots of bacterial cultures were exposed to equivalent concentrations of gold and silver NPs obtained by serial dilutions of the colloids. The initial concentration of both Au and Ag nanoparticles was 14.5 µg mL⁻¹. MIC was defined as the minimum concentration of nanoparticles that inhibit the bacterial growth in liquid medium after an incubation period of 16 h at 37° C. The effect of gold and silver nanoparticles on bacterial growth was visually analyzed on agar plates. Solid medium contained meat extract (5 g L⁻¹), yeast extract (5 g L⁻¹) and agar (15 g L⁻¹). Agar plates (85 mm diameter) were seeded with an aliquot (100 µL) of 1 × 10⁸ CFU mL⁻¹ of MG1655 cells and exposed to AuNPs and AgNPs. The nanoparticle dispersions were serially diluted and drops containing 20 µL of each dilution were poured onto the previously seeded solid medium. Agar plates were incubated during 16 h at 37° C.

3 Results

3.1 Biogenic synthesis of gold nanoparticles

After 96 h in darkness, supernatant of strain CH34 cell culture developed a purple color indicating the production of an extracellular dispersion of biogenic AuNPs (Fig. 1a). No viable cells were detectable after the biosynthesis process, whilst cell viability of CH34 cultures without Au(III) ions remained constant. In contrast to *C. metallidurans* CH34, development of a purple color in supernatant of *E. coli* MG1655 cells was not detected and accumulation of a dark sediment was observed (Fig. 1a). Viable *E. coli* cells were not detected after incubation with Au(III) ions, whereas cell viability of control cultures without Au(III) ions remained constant.

The reduction of Au(III) ions and production of biogenic AuNPs by the secretomes of strains CH34 and MG1655 was studied. Incubation of both bacterial secretomes with Au(III) ions did not developed a purple color and appearance of an insoluble yellow gold complex was observed (not shown).

3.2 Characterization of biogenic AuNPs in colloidal state

The visible spectrum of supernatants of CH34 cultures obtained after incubation with Au(III) ions showed a maximum absorbance peak at a wavelength of 536 nm (Fig. 1b). No absorbance was detected in supernatants of *E. coli* MG1655 cells (Fig. 1b) and secretomes of both strains. These results indicate that under these conditions only CH34 cells are capable to produce extracellular dispersions of biogenic AuNPs.

The biogenic colloid obtained with CH34 cells was characterized by light scattering measurements. Dynamic and electrophoretic light scattering measurements indicated that the AuNPs dispersion presents a Z-Ave of 126.4 nm (Fig. 2a) with an associated zeta-potential of -0.25 ± 3 mV. Additional measurements using NTA technology correlated well with previous DLS results. Mean diameter of the biogenic colloid was 124 nm, with a mode of 78 nm and the presence of minor populations of 302 nm and 405 nm (Fig. 2b, video in Supplemental information). Concentration of biogenic AuNPs diluted 4 times with 1 mM KCl and reported by NTA was 4.19×10^9 particles mL⁻¹. Therefore, the biogenic colloid has a concentration of 1.68×10^9 particles mL⁻¹.

Stability of the biogenic AuNPs colloid after exposure to ultrasound, extreme pH conditions and elevated ionic strength was evaluated by DLS measurements (Table 1). Hydrodynamic diameter of control samples was 126.4 nm with associated PdI of 0.284. Ultrasound treatment did not affect size distribution the colloid, with associated Z-Ave and PdI values of 124.9 nm and 0.279, respectively. Stability of the colloid was also evaluated in the presence of highly acidic (pH 1) and alkaline (pH 10) conditions. The presence of an acidic environment reduced Z-Ave from 126.4 nm to 114.6 nm, whilst an alkaline environment increased Z-Ave to 135.3 nm. In both cases, PdI of the colloid increased to 0.33. Finally, presence of elevated ionic strength (500 mM NaCl) showed no-effect on size distribution, with associated Z-Ave and PdI values of 127.5 nm and 0.286, respectively.

3.3 Characterization of biogenic AuNPs in solid state

The degree of crystallinity of the biogenic gold nanoparticles was determined by powder X-ray diffraction measurements. XRD spectrum showed Bragg's reflection peaks at positions $2\theta = 38.1^\circ, 44.3^\circ, 64.6^\circ, 77.5^\circ$ and 81.7° (Fig. 3a). Position of the reflection peaks can be associated to diffraction planes (111), (200), (220), (311) and (222) of the crystalline unit cell of elemental gold as seen in the 04-0784 file of the JCPDS database. The all odd or all even Miller index values of the diffraction planes indicate that the biogenic gold nanoparticles have a face-centered cubic (*fcc*) crystalline structure. The calculated lattice constant (*a*) using the distance value (*d*) associated to the {220} diffraction planes was estimated to be 4.1 Å. This value agrees with standard report value from JCPDS (*a* = 4.1 Å), confirming that biogenic AuNPs synthesized by strain CH34 are composed of elemental gold. Predominant diffraction plane present in the sample was also determined. Ratio of the intensity peaks (200), (220), (311) and (222) with respect to (111) are lower than ratio of the intensity reported in the standard JCPDS gold sample (0.25 versus 0.52, 0.18 versus 0.32, 0.14 versus 0.36, and 0.04 versus 0.12, respectively). This analysis indicates that the crystallographic structure of AuNPs synthesized by strain CH34 is dominated by {111} diffraction planes.

The morphology and size distribution of the biogenic AuNPs were studied by transmission

electron microscopy. Morphology of the biogenic AuNPs was dominated by decahedral and triangular nanostructures (Fig. 3b). The metallic core of biogenic AuNPs showed diameters ≥ 10 nm, with 85% of the particles showing a diameter between 20 and 60 nm. Few truncated triangular nanoplates with a diameter ≥ 70 nm were also observed. Mean of the frequency distribution was 37.1 ± 15.5 nm. Further analysis of TEM images showed that perimeter of all nanoparticles was surrounded by a layer of non-metallic material with a width of ~ 4.5 nm (Fig. 3b (Inset)). These structures could be organic capping ligands adsorbed on the surface of the biogenic AuNPs.

Energy-dispersive X-ray analysis of biogenic AuNPs showed the presence of sulfur atoms associated to AuNPs (Fig. 4a). Afterwards, the chemical nature of the biogenic AuNPs was characterized by FT-IR spectroscopy (Fig. 4b). Absorbance spectrum of the biogenic AuNPs showed several peaks that correlate with molecular vibrations of functional groups from proteins; therefore, biogenic AuNPs spectrum was analyzed based on the FT-IR spectrum of bovine serum albumin [26]. The broad band between 3700 and 3000 cm^{-1} corresponds to vibrations of water molecules and protein functional groups. The higher peak at 3450 cm^{-1} corresponds to OH... stretching vibrations of residual H_2O ($\nu_{\text{O-H}}$). The following absorption bands at lower energy correspond with amide A group of vibrations. These are the stretching vibrational modes of N-H group of the peptide bonds ($\nu_{\text{N-H}}$; 3290 cm^{-1} and $\nu_{\text{N-H}}$; 3100 cm^{-1}). The absorption band between 3000 and 2800 cm^{-1} corresponds with stretching vibrations of C-H groups. The broad band between 1600 and 1700 cm^{-1} corresponds with molecular vibrations of amide I group. This group includes stretching modes of hydrogen bond acceptor ($\nu_{\text{C=O}}$; 1675, 1665 and 1630 cm^{-1}) and hydrogen bond non-acceptor ($\nu_{\text{C=O}}$; 1695 cm^{-1}) molecular vibrations associated to C=O group of peptide bonds. The absorption band between 1600 and 1500 cm^{-1} corresponds with molecular vibrations of amide II group. This group includes bending modes of the hydrogen bond acceptor ($\delta_{\text{N-H}}$; 1550 and 1520 cm^{-1}) and hydrogen bond non acceptor ($\delta_{\text{N-H}}$; ≈ 1500 cm^{-1}) molecular vibrations associated to N-H group of peptide bonds. A similar absorbance pattern has been described when albumin is adsorbed onto chemically synthesized AuNPs [27, 28]. The absorption band between 1400 and 1360 cm^{-1} corresponds with symmetric stretch ($\nu_{\text{COO}^-}^s$) of the carboxylate groups of Asp and Glu residues. This global data suggests that dispersions of biogenic AuNPs synthesized by strain CH34 are covered by a layer of proteins.

3.4 Effect of biogenic AuNPs on bacterial growth

The effect of biogenic gold and silver NPs on bacterial cell growth was compared. Microdilution method indicated that biogenic AuNPs did not affect the growth of *E. coli* MG1655 cultures, while biogenic AgNPs showed a MIC of 0.45 $\mu\text{g mL}^{-1}$ (Fig. 5). This value is in agreement with previous reports [10, 29, 30]. Similar results were observed with biogenic Au and Ag nanoparticles on solid growth medium. These results indicate that biogenic AuNPs synthesized by *C. metallidurans* strain CH34 do not affect growth of *E. coli* MG1655. Therefore, these biogenic AuNPs are not cytotoxic for *E. coli* cells.

236 4 Discussion

237

238 In this study, stable dispersions of AuNPs were produced after reduction of Au(III) ions by *C.*
239 *metallidurans* CH34 cells. Production of biogenic metallic nanoparticles occurred by redox agents
240 allocated in the cellular biomass. Exposure of *C. metallidurans* CH34 and *E. coli* MG1655 secretomes to
241 Au(III) ions did not produce AuNPs dispersions. Therefore, under these experimental conditions both
242 strains do not secrete enzymes or compounds to the extracellular medium that allow reduction of Au(III)
243 ions with concomitant generation of biogenic AuNPs dispersion. Reduction of Au(III) ions by *E. coli* cells
244 has been reported, but AuNPs aggregate onto bacterial cells and do not generate extracellular dispersions
245 [31]. Production of extracellular AuNPs by cyanobacterium *Plectonema boryanum* UTEX485 cells has
246 been described [32].

247 These results indicate that the mechanism of Au(III) reduction during the biogenic synthesis of
248 extracellular dispersions of AuNPs implies oxidation of molecules that are produced by strain CH34 and
249 are absent in strain MG1655. It is propose that reduction of Au(III) ions and production of extracellular
250 dispersions of AuNPs is mediated by oxidation of macromolecules that are located in the cellular
251 membranes or periplasm of CH34 cells and are absent in MG1655 cells. Accordingly, a comparative
252 bioinformatic analysis of both genomes indicated that, in contrast to strain MG1655, *C. metallidurans*
253 CH34 possess a *cop* gene cluster located within the megaplasmid pMOL30 that encodes periplasmic and
254 outer membrane sulfur rich proteins that contain a significant number of methionine (Met) and cysteine
255 (Cys) residues (CopA 36 Met/1 Cys, CopB 51 Met, CopC 7 Met, CopK 9 Met, CopJ 4 Met/2 Cys) (Fig.
256 6). Moreover, proteomic studies of strain CH34 demonstrated the constitutive expression of the
257 periplasmic protein CopK and the outer membrane bound protein CopB [33], showing that these proteins
258 are highly expressed in cells of *C. metallidurans* CH34.

259 Thus, during biogenic synthesis experiments, the presence of Cop sulfur rich proteins located at
260 the membranes and periplasm of CH34 cells might allow direct interaction between the sulfur atoms of
261 methionine and cysteine residues and the diffusive Au(III) ions present in the extracellular space. In this
262 manner, it is proposed that extracellular Au(III) ions oxidize the sulfur atom of the methionine residues
263 into methionine-sulfoxide. This event has been described for methionine residues from ribonuclease A
264 and glycyl-D,L-methionine dipeptide, with concomitant production of Au(0) [34–36]. In addition, Au(III)
265 ions may oxidize cysteine to cystine, and subsequently to sulfonic acid [37, 38]. After interaction, the
266 reduced gold atoms might return to the medium and generate nucleation centers that finally evolve into
267 extracellular AuNPs dispersions (Fig. 6). Moreover, under physiological conditions, redox cycling
268 enzymes such as Met sulfoxide reductases might reduce and recover the functionality of oxidized
269 sulphur containing residues. Therefore, this analysis suggests that Met residues of CopA and CopB are
270 especially involved in the reduction of gold ions to produce biogenic extracellular AuNPs; and that a
271 redox cycling process of these residues, probably mediated by Met sulfoxide reductases, is involved in
272 the biochemical synthesis of gold nuggets in nature [19].

273 Analysis of electron microscopy images showed that nanoparticles morphology was dominated
274 by decahedral and triangular structures. Origin of these structures may occur by interaction of ultra-small
275 tetrahedral nanoparticles [39-41]. Tetrahedral morphology becomes unstable when nanoparticles reach

diameters close to 10 nm. Then, interaction of five tetrahedral units lowers down the surface area allowing formation of decahedral structures [39] (Fig. 3b and Fig. 6). On the other hand, presence of major triangular nanoplates has been attributed to a slow kinetic process during nanoparticles formation [42]. After long periods, interaction of decahedra like structures serve as nucleation centers that finally evolve into triangular and truncated triangular structures. It is propose that the synthesis mechanism of biogenic AuNPs involves an initial step where small tetrahedral nanoparticles are generated. The interaction of small tetrahedral units evolves into decahedral structures. As observed by TEM, one population of these decahedral structures may serve as nucleation centers for the subsequent biosynthesis of triangular nanoplates and other population might evolve up to reach diameters close to 50 nm.

Analysis of XRD spectrum showed a bias towards {111} diffraction planes. This non-ideal behavior may be attributed to morphological properties of decahedral and triangular nanoparticles observed by TEM. Decahedral structures are formed by interaction of five tetrahedral particles bounded by its lower energy {111} twin planes [39, 41]. Also the major faces of triangular and triangular like nanoplates present a {111} crystallite structure [40, 43, 44]. As the surface area of these nanostructures is dominated by {111} diffraction planes, it is propose that morphology of the biogenic AuNPs contains the information that enhanced the signal of (111) diffraction plane, leading to a XRD spectrum dominated by {111} diffraction planes as described above.

Comparison of size distribution of the biogenic AuNPs obtained by light scattering measurements using two different technologies showed similar results. Dynamic light scattering measurements indicated that Z-Ave was 126.4 nm, whilst NTA indicated that mean diameter of the distribution was 124 nm. These results do not correlate with size distribution deduced from TEM images (average diameter of 37.1 nm). The difference between diameters determined by TEM and light scattering technologies can be explained by the characteristics of each technique. Size distributions obtained from TEM images are proportional to the length of the nanoparticles and do not include the width of capping ligands adsorbed onto AuNPs surface. Also, size distributions obtained from TEM images reflect the results from the analysis of AuNPs samples that are in a solid static state. In contrast, size distributions obtained from DLS and NTA measurements are proportional to the volume of the nanoparticles and represent the accumulation of multiple measurements obtained from a nanoparticles population in dynamic state. Size distributions obtained by these light scattering technologies reveal intermolecular interactions between AuNPs dispersions that leads to multiple equilibriums and are finally detected as an average of major sized nanoparticles complexes [28, 45-47]. Therefore, size distributions of colloids obtained by DLS and NTA contain information about interacting and non-interacting nanoparticles, and detect small amounts of larger nanoparticles that are outside the normal distribution and are not captured in TEM images [48].

The stability of the biogenic AuNPs colloid was determined by exposure to ultrasound, extreme pH conditions and elevated ionic strength by DLS measurements. Ultrasound fuses non-functionalized AuNPs into worm like units with concomitant increment in Z-Ave and PdI [49]. Exposure to prolonged sonication periods did not change Z-Ave nor PdI values, indicating that the biogenic colloid is not sensitive to ultrasound perturbation by the protective effect of a layer of capping ligands that cover the surface of the particles. Further Z-Ave determinations after exposure to extreme pH conditions indicated

that the biogenic colloid endures the chemical perturbation of acidic and alkaline environments and reveals the presence of basic functional groups located at the surface of the nanoparticles. Exposure to an acidic environment reduced the hydrodynamic diameter and increased PDI of the colloid. It is proposed that low pH conditions generate a re-distribution of the interacting nanoparticles population. Protonation of basic groups of the capping ligands increase electrostatic repulsion of at least one fraction of the interacting nanoparticles. This process probably generates a novel group of non-interacting nanoparticles that splits the population distribution and is detected as a reduction in Z-Ave and an increment in the PDI of the colloid. On the other hand, alkaline environment increased both Z-Ave and PDI of the colloid. Deprotonation of basic groups might reduce the electrostatic repulsion of at least one fraction of the interacting nanoparticles. This process would generate a group of highly-interacting nanoparticles that splits the former population distribution and is detected as an increment in both Z-Ave and PDI of the biogenic colloid. The presence of high concentrations of NaCl did not alter size distribution of the colloid. This result demonstrates that biogenic AuNPs do not flocculate nor aggregate in the presence elevated ionic strength conditions, and indicates that biogenic AuNPs colloids obtained with *C. metallidurans* CH34 cells would remain stable even under physiological conditions (150 mM NaCl).

The stability mechanism of the biogenic colloid was studied by electrophoretic and DLS measurements in the presence and absence of ionic strength. Elevated absolute ζ -potential values (≥ 30 mV) are indicative of electrostatic repulsion between nanoparticles and therefore to the stability of the colloid mediated by an electrostatic repulsion mechanism [50]. In this case, presence of ionic strength shields the electrostatic repulsion between the particles, and induces flocculation and increment in Z-Ave of the colloid. The ζ -potential of biogenic AuNPs synthesized by strain CH34 was ~ 0 mV (-0.25 ± 3 mV), and Z-Ave did not change in presence of 500 mM NaCl (Table 1). These results indicate that the biogenic colloid is not stabilized by electrostatic repulsion forces and suggests that the stability mechanism is based on a steric repulsion between the capping ligands of the nanoparticles. Stabilization by steric repulsion mechanism indicates that elevated molecular weight ligands are adsorbed onto the surface of the biogenic AuNPs [28, 51], and supports FT-IR results that reveal the presence of functional groups of proteins.

5 Conclusions

Stable colloidal dispersions of AuNPs were obtained after incubation of *C. metallidurans* CH34 cells with Au(III). Potential CH34 proteins such as CopA, CopB or CopK may act as electron donors for the reduction of Au(III) ions during the biosynthesis process, and a mechanism for the production of extracellular AuNPs by strain CH34 was proposed.

Average diameter of the biogenic AuNPs in colloidal state obtained from light scattering measurements (DLS and NTA) was four times higher than diameter of the biogenic AuNPs in solid state obtained from analysis of TEM images. This comparison shows that the size distributions obtained from analyses of nanoparticles in colloidal and solid state are not comparable.

The biogenic colloid is stable under chemical and physical perturbations, which is useful for potential applications. Clinical applications include the topical delivery of bioactive compounds that may

356 interact with the protein layer of the nanoparticles and the development of colorimetric biosensors that
357 require colloidal probes with elevated stability and absorptivity.

358

359 References

360

- 361 1 Monchy, S., Benotmane, M.A., Janssen, P., *et al.*: 'Plasmids pMOL28 and pMOL30 of
362 *Cupriavidus metallidurans* are specialized in the maximal viable response to heavy metals', *J.*
363 *Bacteriol.*, 2007, **189**, pp. 7417–7425.
- 364 2 Rojas, L.A., Yáñez, C., González, M., Lobos, S., Smalla, K., Seeger, M.: 'Characterization of the
365 metabolically modified heavy metal-resistant *Cupriavidus metallidurans* strain MSR33 generated
366 for mercury bioremediation', *PLoS One*, 2011, **6**, p. e17555.
- 367 3 Altimira, F., Yáñez, C., Bravo, G., González, M., Rojas, L.A., Seeger, M.: 'Characterization of
368 copper-resistant bacteria and bacterial communities from copper-polluted agricultural soils of
369 central Chile', *BMC Microbiol.*, 2012, **12**, p. 193.
- 370 4 Chirino, B., Strahsburger, E., Agulló, L., González, M., Seeger, M.: 'Genomic and functional
371 analyses of the 2-aminophenol catabolic pathway and partial conversion of its substrate into
372 picolinic acid in *Burkholderia xenovorans* LB400', *PLoS One*, 2013, **8**, p. e75746.
- 373 5 Ramanathan, R., Field, M.R., O'Mullane, A.P., Smooker, P.M., Bhargava, S.K., Bansal, V.:
374 'Aqueous phase synthesis of copper nanoparticles: a link between heavy metal resistance and
375 nanoparticle synthesis ability in bacterial systems', *Nanoscale*, 2013, **5**, pp. 2300–2306.
- 376 6 Okamoto, A., Kalathil, S., Deng, X., Hashimoto, K., Nakamura, R., Nealson, K.H.: 'Cell-secreted
377 flavins bound to membrane cytochromes dictate electron transfer reactions to surfaces with
378 diverse charge and pH', *Sci. Rep.*, 2014, **4**, p. 5628.
- 379 7 Fuentes, S., Méndez, V., Aguila, P., Seeger, M.: 'Bioremediation of petroleum hydrocarbons:
380 catabolic genes, microbial communities, and applications', *Appl. Microbiol. Biotechnol.*, 2014,
381 **98**, pp. 4781–4794.
- 382 8 Fuentes, S., Barra, B., Caporaso, J.G., Seeger, M.: 'From rare to dominant: a fine-tuned soil
383 bacterial bloom during petroleum hydrocarbon bioremediation', *Appl. Environ. Microbiol.*, 2016,
384 **82**, pp. 888–896.
- 385 9 Durán, N., Marcato, P.D., Durán, M., Yadav, A., Gade, A., Rai, M.: 'Mechanistic aspects in the
386 biogenic synthesis of extracellular metal nanoparticles by peptides, bacteria, fungi, and plants',
387 *Appl. Microbiol. Biotechnol.*, 2011, **90**, pp. 1609–1624.
- 388 10 Rai, M., Birla, S., Ingle, A.P., *et al.*: 'Nanosilver: an inorganic nanoparticle with myriad potential
389 applications', *Nanotechnol. Rev.*, 2014, **3**, pp. 281–309.
- 390 11 Kashefi, K., Tor, J.M., Nevin, K.P., Lovley, D.R.: 'Reductive precipitation of gold by
391 dissimilatory Fe(III)-reducing Bacteria and Archaea', *Appl. Environ. Microbiol.*, 2001, **67**, pp.
392 3275–3279.
- 393 12 Karthikeyan, S., Beveridge, T.J.: '*Pseudomonas aeruginosa* biofilms react with and precipitate
394 toxic soluble gold', *Environ. Microbiol.*, 2002, **4**, pp. 667–675.
- 395 13 Durán, N., Marcato, P.D., Alves, O.L., Souza, G.I.H. De, Esposito, E.: 'Mechanistic aspects of

396 biosynthesis of silver nanoparticles by several *Fusarium oxysporum* strains', *J. Nanobiotechnol.*,
397 2005, **3**, p. 8.

398 14 Thakkar, K.N., Mhatre, S.S., Parikh, R.Y.: 'Biological synthesis of metallic nanoparticles',
399 *Nanomedicine*, 2010, **6**, pp. 257–262.

400 15 Derakhshan, F.K., Dehnad, A., Salouti, M.: 'Extracellular biosynthesis of gold nanoparticles by
401 metal resistance bacteria: *Streptomyces griseus*', *Synth React Inorg Met -Org Chem*, 2012, **42**, pp.
402 868–871.

403 16 Nies, D.H.: 'Efflux-mediated heavy metal resistance in prokaryotes', *FEMS Microbiol. Rev.*,
404 2003, **27**, pp. 313–339.

405 17 Taghavi, S., Lesaulnier, C., Monchy, S., Wattiez, R., Mergeay, M., van der Lelie, D.: 'Lead(II)
406 resistance in *Cupriavidus metallidurans* CH34: interplay between plasmid and chromosomally-
407 located functions', *Antonie Van Leeuwenhoek*, 2009, **96**, pp. 171–182.

408 18 Reith, F., Etschmann, B., Grosse, C., *et al.*: 'Mechanisms of gold biomineralization in the
409 bacterium *Cupriavidus metallidurans*', *Proc. Natl. Acad. Sci.*, 2009, **106**, pp. 17757–17762.

410 19 Reith, F., Rogers, S.L., McPhail, D., Webb, D.: 'Biomineralization of gold: biofilms on
411 bacterioform gold', *Science*, 2006, **313**, pp. 233–236.

412 20 Fairbrother, L., Etschmann, B., Brugger, J., Shapter, J., Southam, G., Reith, F.:
413 'Biomineralization of gold in biofilms of *Cupriavidus metallidurans*', *Environ. Sci. Technol.*,
414 2013, **47**, pp. 2628–2635.

415 21 Mergeay, M., Nies, D., Schlegel, H.G., Gerits, J., Charles, P., Van Gijsegem, F.: '*Alcaligenes*
416 *eutrophus* CH34 is a facultative chemolithotroph with plasmid-bound resistance to heavy metals',
417 *J. Bacteriol.*, 1985, **162**, pp. 328–334.

418 22 Baba, T., Ara, T., Hasegawa, M., *et al.*: 'Construction of *Escherichia coli* K-12 in-frame, single-
419 gene knockout mutants: the Keio collection', *Mol. Syst. Biol.*, 2006, **2**, p. 2006.0008.

420 23 Parra, C., Montero-Silva, F., Henríquez, R., *et al.*: 'Suppressing bacterial interaction with copper
421 surfaces through graphene and hexagonal-boron nitride coatings', *ACS Appl. Mater. Interfaces*,
422 2015, **7**, pp. 6430–6437.

423 24 Song, C., Kumar, A., Saleh, M.: 'Bioinformatic comparison of bacterial secretomes', *Genomics*
424 *Proteomics Bioinformatics*, 2009, **7**, pp. 37–46.

425 25 Wiegand, I., Hilpert, K., Hancock, R.E.W.: 'Agar and broth dilution methods to determine the
426 minimal inhibitory concentration (MIC) of antimicrobial substances', *Nat. Protoc.*, 2008, **3**, pp.
427 163–175.

428 26 Grdadolnik, J., Maréchal, Y.: 'Bovine serum albumin observed by infrared spectrometry. I.
429 Methodology, structural investigation, and water uptake', *Biopolymers*, 2001, **62**, pp. 40–53.

430 27 Tsai, D.-H., Delrio, F.W., Keene, A.M., *et al.*: 'Adsorption and conformation of serum albumin
431 protein on gold nanoparticles investigated using dimensional measurements and *in situ*
432 spectroscopic methods', *Langmuir*, 2011, **27**, pp. 2464–2477.

433 28 Shi, X., Li, D., Xie, J., Wang, S., Wu, Z., Chen, H.: 'Spectroscopic investigation of the
434 interactions between gold nanoparticles and bovine serum albumin', *Chinese Sci. Bull.*, 2012, **57**,
435 pp. 1109–1115.

- 436 29 Marcato, P.D., Durán, M., Huber, S.C., *et al.*: 'Biogenic silver nanoparticles and its antifungal
437 activity as a new topical transungual drug', *J. Nano Res.*, 2012, **20**, pp. 99–107.
- 438 30 Huang, J., Zhan, G., Zheng, B., *et al.*: 'Biogenic silver nanoparticles by Cacumen Platycladi
439 extract: synthesis, formation mechanism, and antibacterial activity', *Ind. Eng. Chem. Res.*, 2011,
440 **50**, pp. 9095–9106.
- 441 31 Du, L., Jiang, H., Liu, X., Wang, E.: 'Biosynthesis of gold nanoparticles assisted by *Escherichia*
442 *coli* DH5a and its application on direct electrochemistry of hemoglobin', *Electrochem. commun.*,
443 2007, **9**, pp. 1165–1170.
- 444 32 Lengke, M.F., Ravel, B., Fleet, M.E., Wanger, G., Gordon, R.A., Southam, G.: 'Mechanisms of
445 gold bioaccumulation by filamentous cyanobacteria from gold(III)-chloride complex', *Environ.*
446 *Sci. Technol.*, 2006, **40**, pp. 6304–6309.
- 447 33 Monchy S, Benotmane M a., Wattiez R, van Aelst S, Auquier V, Borremans B, et al:
448 'Transcriptomic and proteomic analyses of the pMOL30-encoded copper resistance in
449 *Cupriavidus metallidurans* strain CH34'. *Microbiology* 2006, **152**, pp. 1765–1776.
- 450 34 Isab, A., Sadler, P.: 'Reactions of gold(III) ions with ribonuclease A and methionine derivatives
451 in aqueous solution', *Biochim. Biophys. Acta*, 1977, **492**, pp. 322–330.
- 452 35 Glišić, B.Đ., Rychlewska, U., Djuran, M.I.: 'Reactions and structural characterization of gold(III)
453 complexes with amino acids, peptides and proteins', *Dalt. Trans.*, 2012, **41**, pp. 6887–6901.
- 454 36 Glišić, B.D., Rajkovic, S., Stanic, Z.D., Djuran, M.I.: 'A spectroscopic and electrochemical
455 investigation of the oxidation pathway of glycyl-D,L-methionine and its N-acetyl derivative
456 induced by gold(III)', *Gold Bull.*, 2011, **44**, pp. 91–98.
- 457 37 Shaw III, C.F., Cancro, M.P., Witkiewicz, P.L.: 'Gold (III) oxidation of disulfides in aqueous
458 solution', *Inorg. Chem.*, 1980, **19**, pp. 3198–3201.
- 459 38 Witkiewicz, P.L., Shaw, C.F.: 'Oxidative cleavage of peptide and protein disulphide bonds by
460 gold(III): a mechanism for gold toxicity', *J. Chem. Soc. Chem. Commun.*, 1981, pp. 1111–1114.
- 461 39 Johnson, C.L., Snoeck, E., Ezcurdia, M., *et al.*: 'Effects of elastic anisotropy on strain
462 distributions in decahedral gold nanoparticles', *Nat. Mater.*, 2008, **7**, pp. 120–124.
- 463 40 Sun, J., Guan, M., Shang, T., Gao, C., Xu, Z.: 'Synthesis and optical properties of triangular gold
464 nanoplates with controllable edge length', *Sci. China Chem.*, 2010, **53**, pp. 2033–2038.
- 465 41 Walsh, M.J., Yoshida, K., Kuwabara, A., Pay, M.L., Gai, P.L., Boyes, E.D.: 'On the structural
466 origin of the catalytic properties of inherently strained ultrasmall decahedral gold nanoparticles',
467 *Nano Lett.*, 2012, **12**, pp. 2027–2031.
- 468 42 Mukherjee, P., Roy, M., Mandal, B.P., *et al.*: 'Synthesis of uniform gold nanoparticles using non-
469 pathogenic bio-control agent: evolution of morphology from nano-spheres to triangular
470 nanoprisms', *J. Colloid Interface Sci.*, 2012, **367**, pp. 148–152.
- 471 43 Chen, S., Carroll, D.L.: 'Synthesis and characterization of truncated triangular silver nanoplates',
472 *Nano Lett.*, 2002, **2**, pp. 1003–1007.
- 473 44 Montes, M.O., Mayoral, A., Deepak, F.L., *et al.*: 'Anisotropic gold nanoparticles and gold plates
474 biosynthesis using alfalfa extracts', *J. Nanoparticle Res.*, 2011, **13**, pp. 3113–3121.
- 475 45 Filipe, V., Hawe, A., Jiskoot, W.: 'Critical evaluation of nanoparticle tracking analysis (NTA) by

476 NanoSight for the measurement of nanoparticles and protein aggregates', *Pharm. Res.*, 2010, **27**,
477 pp. 796–810.

478 46 Doane, T., Burda, C.: 'Nanoparticle mediated non-covalent drug delivery', *Adv. Drug Deliv. Rev.*,
479 2012, **65**, pp. 607–621.

480 47 Fu, C., Yang, H., Wang, M., Xiong, H., Yu, S.: 'Serum albumin adsorbed on Au nanoparticles:
481 structural changes over time induced by S–Au interaction', *Chem. Commun.*, 2015, **51**, pp. 3634–
482 3636.

483 48 Brar, S.K., Verma, M.: 'Measurement of nanoparticles by light-scattering techniques', *Trends*
484 *Anal. Chem.*, 2011, **30**, pp. 4–17.

485 49 Radziuk, D., Grigoriev, D., Zhang, W., Su, D., Möhwald, H., Shchukin, D.: 'Ultrasound-assisted
486 fusion of preformed gold nanoparticles', *J. Phys. Chem. C*, 2010, **114**, pp. 1835–1843.

487 50 Doane, T.L., Chuang, C.-H., Hill, R.J., Burda, C.: 'Nanoparticle ζ -potentials', *Acc. Chem. Res.*,
488 2012, **45**, pp. 317–326.

489 51 El Badawy, A.M., Luxton, T.P., Silva, R.G., Scheckel, K.G., Suidan, M.T., Tolaymat, T.M.:
490 'Impact of environmental conditions (pH, ionic strength, and electrolyte type) on the surface
491 charge and aggregation of silver nanoparticles suspensions', *Environ. Sci. Technol.*, 2010, **44**, pp.
492 1260–1266.

493

494

495

496

497

498 **Table 1 Dynamic light scattering measurements of biogenic AuNPs dispersions produced by *C.***
 499 ***metallidurans* CH34 after exposure to ultrasound, extreme pH and elevated ionic strength (average**
 500 **of 3 measurements)**

Experimental condition	Z-Ave (d.nm)	PdI
Control	126.4	0.284
Ultrasound	124.9	0.279
pH 1	114.6	0.332
pH 10	135.3	0.334
NaCl (500 mM)	127.5	0.286

501

502 **Fig. 1 Optical properties of gold nanoparticles synthesized by bacteria.** (a) Reduction of AuCl_4^- by *C.*
503 *metallidurans* CH34 (left) and *E. coli* MG1655 cells (right). (b) Visible spectra of the aqueous fractions
504 obtained from *C. metallidurans* CH34 and *E. coli* MG1655 supernatants.

505

506 **Fig. 2 Comparison of size distributions of gold nanoparticles synthesized by *C. metallidurans* CH34**
507 **obtained by light scattering measurements.** (a) Size distribution obtained by dynamic light scattering
508 (DLS) measurements. Reported Z-Ave of 126.4 nm and PdI of 0.284 (b) Size distribution and particles
509 concentration obtained by nanoparticle tracking analysis (NTA). Reported mean of 124 nm, mode of 78
510 nm and SD of 88 nm.

511

512 **Fig. 3 Physical properties of biogenic gold nanoparticles synthesized by *C. metallidurans* CH34.** (a)
513 Powder X-ray diffraction spectrum. (b) Size frequency distribution and morphology of the AuNPs
514 determined by analysis of TEM images (n=142). Mean of 37.1 with SD of 15.5 nm. Inset: representative
515 field of biogenic AuNPs.

516

517 **Fig. 4 Chemical characterization of biogenic AuNPs synthesized by *C. metallidurans* CH34.** (a) EDX
518 spectrum of biogenic AuNPs. (b) FT-IR spectrum of biogenic nanoparticles (straight line), and bovine
519 serum albumin adapted from [26] (dotted line).

520

521 **Fig. 5 Minimal inhibitory concentration of AuNPs on planktonic cultures of *E. coli* MG1655.** a,
522 AuNPs produced by *C. metallidurans* CH34 b, AgNPs produced by *Fusarium oxysporum*. nd: no growth
523 detected. Inset: growth of *E. coli* MG1655 cells on agar plates after exposure to an equivalent amount of
524 NPs.

525

526 **Fig. 6 Proposed mechanism for the reduction of Au(III) ions by *C. metallidurans* CH34 cells and**
527 **subsequent formation of extracellular dispersions of AuNPs.**

528

529

530

531 **Fig. 1S Workflow of cell culture fractionation.**

532

533 **Interactive media S1. Video showing light dispersion and Brownian motion of biogenic AuNPs**
534 **synthesized by *C. metallidurans* CH34 cells.**

cell culture

H₂O

biomass

Method A

96 h

secretome

Method B