Helical Fibrillar Microstructure of Tendon using Serial Block-Face SEM and a Mechanical Model for Interfibrillar Load Transfer

Babak N. Safa^{1,2}, John M. Peloquin¹, Jessica R. Natriello¹,
Jeffrey L. Caplan^{3,4}, and Dawn M. Elliott^{1*}

¹Department of Biomedical Engineering, University of Delaware, Newark, DE, United States

²Department of Mechanical Engineering, University of Delaware, Newark, DE, United States

³Department of Plant and Soil Sciences, University of Delaware, Newark, DE, United States

⁴Delaware Biotechnology Institute, University of Delaware, Newark, DE, United States

***Corresponding author:**

Dawn M. Elliott
University of Delaware
161 Colburn Lab,
150 Academy Street,
Newark, DE 19716
(delliott@udel.edu, T(302)-831-1295)

(Word count: ~3900)

Abstract

Tendon's hierarchical structure allows for load transfer between its
 35 fibrillar elements at multiple length scales. Tendon microstructure is particularly
 important, because it includes the cells and their surrounding collagen fibrils,
 where mechanical interactions can have potentially important physiological and
 pathological contributions. However, the three-dimensional microstructure and
 the mechanisms of load transfer in that length scale are not known. It has been
 40 postulated that interfibrillar matrix shear or direct load transfer via the
 fusion/branching of small fibrils are responsible for load transfer, but the
 significance of these mechanisms is still unclear. Alternatively, the helical
 fibrils that occur at the microstructural scale in tendon may also mediate load
 transfer, however, these structures are not well studied due to the lack of a
 45 three-dimensional visualization of tendon microstructure. In this study, we used
 serial block-face scanning electron microscopy (SBF-SEM) to investigate the
 three-dimensional microstructure of fibrils in rat tail tendon. We found that
 tendon fibrils have a complex architecture with many helically wrapped fibrils.
 We studied the mechanical implications of these helical structures using finite
 50 element modeling and found that frictional contact between helical fibrils can
 induce load transfer even in the absence of matrix bonding or fibril
 fusion/branching. This study is significant in that it provides a three-
 dimensional view of the tendon microstructure and suggests friction between
 helically wrapped fibrils as a mechanism for load transfer, which is an
 55 important aspect of tendon biomechanics. [Word count 232/250]

Keywords: SBF-SEM, Collagen fibril, Tendon, Friction, Stress mechanics

Introduction

60 Tendon's hierarchical structure allows for load transfer between its
fibrillar elements across multiple length scales (Kastelic et al., 1978; Pensalfini
et al., 2014; Screen et al., 2005), which results in remarkable capabilities to
withstand stress and endure repetitive loading (Snedeker and Foolen, 2017). The
microscale structure and function are particularly important, because this is the
65 scale where the cells and their surrounding collagen fibrils interface, and these
mechanical interactions can have important physiological and pathological
contributions. In particular, there is evidence of microscale sliding and shear
load transfer that is highly likely to represent sliding between fibrils at small
strains (less than 2%) and at larger strains this microscale sliding is
70 nonrecoverable, indicating tissue damage (Lee et al., 2017; Screen et al., 2005;
Szczesny and Elliott, 2014a). However, the underlying mechanisms of load
transfer between tendon fibrils are still unknown. Tendon fibrils are collagenous
structures (diameter ~100 nm) that are the building blocks of tendon
microstructure (Kannus, 2000). The fibrils are responsible for supporting
75 external mechanical loading. Interfibrillar matrix molecules such as
glycosaminoglycan chains (GAG) have been postulated to be responsible for
load transfer between fibrils (Ahmadzadeh et al., 2013; Redaelli et al., 2003);
however, removal of a wide range of extracellular matrix components, including
GAG, does not affect the mechanical response (Szczesny et al., 2017), or has

minimal consequences (Fessel and Snedeker, 2009). It is not likely that the load transfer in tendon is solely, or majorly, mediated via interfibrillar matrix. Thus, the microscale architecture of the collagen fibrous network itself is likely to have a role in mediating load transfer.

Serial block-face scanning electron microscopy (SBF-SEM) makes it possible to visualize the 3D microscale architecture of tissue in great detail, and to reveal the fibrillar architecture with several mechanical implications (Pingel et al., 2014; Starborg et al., 2013). SBF-SEM is an advanced electron microscopy technique that takes sequential SEM images of the cross-section of tissue; these images combine to provide a three-dimensional view of the microstructure (Hashimoto et al., 2016; Starborg et al., 2013). Using SBF-SEM with a short scan depth (8.7 μm), our group showed that there is a small fibril angular dispersion and that the fusion/branching of small fibrils might be responsible for interfibrillar load transfer (Szczeny et al., 2017, 2014). Longer scan depths ($\sim 100 \mu\text{m}$) showed that fibril fusion/branching and fibril ends also exist in tendons (Svensson et al., 2017), and that helical fibril patterns form in microscale during tendon development in juvenile tail tendons (Kalson et al., 2015; Starborg and Kadler, 2015). The existence of helical fibrils in collagen microscale and nanoscale was shown using two-dimensional light, atomic force, electron, and X-ray scattering microscopy in tendons and other collagenous tissues (Altraud et al., 1987; Bozec et al., 2007; Folkhard et al., 1987; Franchi et al., 2010; Kalson et al., 2012; Lillie et al., 1977; Orgel et al., 2006; Reed et al.,

1956; Vidal, 2003); however, these two-dimensional visualizations do not provide the three-dimensional structure.

Experimental observations and finite element (FE) modeling suggest that helical structures in tendon may have significant mechanical effects. The rotation and high Poisson's ratio observed during tendon's axial loading have been attributed to such structures (Buchanan et al., 2017; Reese et al., 2010; Thorpe et al., 2013). Furthermore, some FE models have studied the groups of helical fibrils by combining the fibrils with interfibrillar matrix in a mesh to produce the nonlinear stress response of fascicles (Carniel et al., 2019; Reese et al., 2010). Despite the potential of helical fibril organization to affect tendon's microscale mechanics, little is known about individual groups of helically wrapped fibrils and their mechanical implications. We hypothesized that helical wrapping can induce frictional load transfer between fibrils, allowing for mechanical interfibrillar load transfer without an intermediate matrix. This would imply that friction between helically wrapped fibrils can contribute to load transfer, in addition to interfibrillar matrix shear and fibril fusion/branching.

The scope of this contribution was to visualize the three-dimensional fibril organization of rat tail tendon and to study the potential of interfibrillar friction within helically wrapped groups of fibrils to serve as a mechanism for load transfer. First, we visualized the microstructure of tendon in three dimensions using SBF-SEM. We found a complex network, with many helically

wrapped fibrils. These observations informed the second part of this study, in which we used finite element (FE) analysis to test the hypothesis that frictional contact between helically wrapped fibrils can transfer stress (load) between fibrils without a need for a mediating matrix. This study elucidates new aspects of tendon microstructure, providing a detailed image of fibril tortuosity, fusion/branching, and organization into helical groups. Importantly, our results establish interfibrillar friction as a new mechanism for interfibrillar load transfer, among the several proposed load transfer mechanisms in the field, advancing our knowledge about microscale structure–mechanics relationships.

Methods

Serial block-face SEM imaging

A tail tendon fascicle from a three-month-old male Sprague-Dawley rat was dissected as previously described (Safa et al., 2017), and used for SBF-SEM imaging. To prepare for imaging, the fascicle was placed in PBS for 8 hours to equilibrate and then soaked overnight at 4°C in a solution of 2% glutaraldehyde and 2% paraformaldehyde in 0.1 M sodium cacodylate buffer. The sample was subsequently stained and resin-embedded, according to established techniques (Starborg et al., 2013).

The transverse cross-section was scanned in series under 1.78 kV in low-vacuum pressure with three microseconds dwelling time using an Apreo VolumeScope (Thermo Fisher Scientific, Waltham MA). After the end of the

scanning of each section, a 200 nm layer of the block's face was removed by means of a mechanical slicer and the scanning was repeated. The in-plane resolution of the scans was 10 nm/pixel with 432 slices that covers a total volume of (20.27 $\mu\text{m} \times 16.74 \mu\text{m} \times 86.20 \mu\text{m}$), where the third dimension is measured along the fascicle's axial direction.

Segmentation and data analysis

The SEM images were smoothed using a Gaussian blur filter and a representative subset of fibrils were manually segmented through the entire 3D image stack (Fig. 1A). Only fibrils that spanned the entire image stack, as many fibrils did not entirely fit in the scanned volume or some fibrils were otherwise discontinuous, were used for analysis ($n = 42$ fibrils). The segmentation was done using Seg3D (seg3d.org). Since the axial distance between subsequent images was small (200 nm) the fibrils appear as semi-circular spots that move in-plane allowing for the fibrils to be inspected and tracked through the image stack (Fig. 1A-C).

To confirm that the manually segmented fibrils were a representative selection of all the fibrils, we segmented all fibrils in each of ten equally spaced 2D sections by thresholding (ImageJ, imagej.nih.gov). The distribution of fibril diameter was calculated and compared to that of the manual 3D fibril segmentations (Fig. 1D and E). The distributions matched, confirming that the manually segmented fibrils were a representative sample. The manual 3D fibril segmentations were used for all subsequent analysis.

To determine the variation in fibril diameter along the length, we calculated the normalized diameter of each fibril in each section in the image stack. The normalized diameter for a fibril at section i is defined as

$$\bar{d}(z_i) = \frac{d(z_i)}{\tilde{d}}, \quad (1)$$

170 where z_i is the scan depth, $d(z_i) = \sqrt{4A_i/\pi}$ is the diameter of the fibril, A_i is the cross-sectional area of the fibril, and $\tilde{d}$ is the median of $d(z_i)$ across all sections (Fig. 1C). To quantify the complexity of the fibrillar network, we calculated the percent tortuosity for each fibril as

$$\tau = \left(\frac{\sum_{i=1}^{N-1} s_i}{l_0} - 1 \right) \times 100; \quad (2)$$

here, l_0 is the end-to-end distance of the fibrils, and s_i is the distance between
175 fibril centroids in adjacent sections, and N is the number of sections (Fig. 1C). Approximately half of the segmented fibrils ($n = 20$) were in helical groups; for these fibrils we calculated the pitch (λ) by dividing the total scan depth (86.20 μm) by the number of turns in the helices.

Statistics

180 The variation in diameter along the length was tested by calculating, for each section, the 95% confidence interval of normalized diameter (Eq. 1) across the fibrils in that section. To test the correlation between fibril diameter and tortuosity, we conducted a linear regression analysis between $\tilde{d}$ and τ for the

fibrils in the helical groups and others, separately, using Pearson's correlation
 185 method. Statistical significance was defined as $p < 0.05$.

Finite element analysis of helical fibril structures

Helical wrapping of fibrils around each other was a commonly observed
 feature, and we hypothesized that this helical wrapping may provide
 interfibrillar load transfer. To study this, we developed a three-dimensional
 190 finite element (FE) model of a pair of helical fibrils in contact (Fig. 1F and G)
 using FEBio software (FEBio2.8 febio.org) (Maas et al., 2012). The fibril
 diameter was taken to be 200 nm, and according to our observations from SBF-
 SEM, the helix pitch was set at 40 μm . The entire model included three full
 fibril revolutions (i.e., $L = 3\lambda$ where L is the total length). The boundary
 195 condition was set as that each fibril had one free-end. In one fibril, the opposite
 end was anchored; in the other fibril, it was set to move to create 8% axial strain
 (Fig. 1F). The value of 8% was selected from experimental data as the
 maximum tissue strain that fibrils may experience prior to failure (Lee et al.,
 2017).

200 We used an isotropic compressible neo-Hookean constitutive relation for
 the fibrils (Bonet and Wood, 1997; Maas et al., 2019):

$$\Psi(I_1, J) = \frac{E}{4(1+\nu)}(I_1 - 3) - \frac{E}{2(1+\nu)} \ln J + \frac{E\nu}{2(1+\nu)(1-2\nu)} (\ln J)^2. \quad (3)$$

Where, Ψ is the strain energy, I_1 is the first invariant of the right Cauchy-Green
 strain tensor and J is the Jacobian of deformation; E is the Young's modulus,

and ν is the Poisson's ratio. The model parameters were set as $E = 1$ GPa, $\nu =$
 205 0.2. The friction parameter between fibrils was set as $\mu = 0.5$, and the helix
 pitch was set as $\lambda = 40$ μm .

To solve the frictional contact problem between the fibrils we employed
 the penalty method regularized with an augmented Lagrangian scheme that has
 been implemented in FEBio (Zimmerman and Ateshian, 2018). In the initial
 210 configuration the fibrils were in contact along the entire length. We used a mesh
 consisting of 20,160 hexahedral trilinear elements and 23,478 nodes based on a
 mesh sensitivity analysis (Fig 1G). To improve the stability of the contact
 algorithm we used a frictionless external cylindrical sheath with a weak
 modulus (10% of fibril modulus) to prevent separation in the intermediate steps
 215 of the iterative FE solver. The sheath was highly effective in increasing the
 stability of the model, and did not alter the final solutions. This was confirmed
 by using different moduli for the sheath between 0.1% and 1000% of the fibril
 modulus; the same mechanical response was produced in each case.

The reaction force at the anchored end of the fixed fibril was divided by
 220 the cross sectional area and used as the measure for load transfer. To assess the
 sensitivity of the load transfer, we performed a one-at-a-time parametric
 sensitivity analysis by varying the model parameters in a range according to the
 reported values in the literature for fibril properties that are summarize in Table
 1 (Chung et al., 2013; Gautieri et al., 2011; Liu et al., 2016; Minary-Jolandan
 225 and Yu, 2009; Szczesny and Elliott, 2014a; Wells et al., 2015; Wenger et al.,

2007; Yang et al., 2012). Since the experimental data for frictional coefficient of
fibril-on-fibril is not available, we used an estimated range ($0 < \mu < 2$) based
on AFM indentation tests (Chung et al., 2013). We studied the following cases
by changing one parameter at a time: $E = 0.1$ to 10 GPa, $\nu = 0$ to 0.4 , $\mu =$
230 0 to 2 , $\lambda = 20$ to 80 μm .

To evaluate the spatial distribution of the induced stress and deformation
in the fibrils we plotted axial stress and we also plotted the normalized
displacement ($\bar{u}$) relative to the mid-section of each fibril along the axial
direction. We defined normalized displacement as

$$\bar{u}(z) = \frac{1}{\lambda} \left(u(z) - u\left(\frac{L}{2}\right) \right). \quad 4)$$

235 Here, $u(z)$ is the axial displacement at position z along the fibril length.

Results

Microstructure of fibrils and SBF-SEM

To describe the microstructure of tendon, we segmented fibrils from the
SBF-SEM images in three-dimensions. The segmentation indicated that
240 although the fibrils are mostly axially-aligned, they create a complex network
around the cells (Fig. 2A). From the manually segmented fibrils we quantified
the fibril diameter throughout the scan depth (Eq. 1) and the percent tortuosity
(Eq. 2). As expected, the fibrils' diameter did not vary along the fibril length
(Fig. 2B), which is consistent with previous findings (Svensson et al., 2017).

Note that the normalized fibril diameter (Eq. 1) was not significantly different than one across the scan depth (Fig 2B). This observation supports the use of a single median diameter value assigned to each fibril for correlation with the tortuosity. We quantified the % tortuosity (τ) of each segmented fibril (Eq. 2), and calculated its correlation with the median diameter of the fibrils. This showed that for all of the fibrils, τ was small ($< 1\%$) and for the fibrils in helical groups tortuosity was correlated with diameter ($r = -0.59, p < 0.05$), where for the other fibrils it was the same across the diameter sizes ($r = 0.12, p = 0.616$) (Fig. 2C). As a result, the smaller fibrils in helical groups are more likely to have higher tortuosity, and thus have a more complex structure. For the tortuosity analysis, one fibril that made a right-angle turn and passed through the cell membrane (Fig. 3C, discussed below) was not included in the correlation.

We made several isolated structural observations that have potential mechanical implications: tapered fibril end (Fig. 3A and Supplementary Video 1), fibril fusion/branching (Fig. 3B and Supplementary Video 2), and one fibril that wrapped around the cells (Fig. 3C and Supplementary Video 3). For the tapered fibril end, in the last $\sim 4 \mu\text{m}$ of the fibril length (scan depth of $38\text{-}42 \mu\text{m}$) a reduction in fibril diameter was evident, where the fibril gradually fades away in the image sequence when approaching from the deeper scanned layers (Fig. 3A). At the fusion/branching site, a small fibril merges with a larger one, and in the subsequent scanned images the larger resulting fibril branches into two

distinct ones. The fusion/branching site approximately spanned 6 μm , where at least two fibrils were not distinguishable (Fig. 3B). Another interesting feature was one fibril that made almost a full turn around the cells (Fig. 3C). These features were interesting but were isolated observations in the dataset.

When looking at the axial view of the fibrils, we observed several helical structures (Fig. 4 and Supplementary Video 4). In particular, many fibrils locally wrapped around each other, which contained two, three, or more fibrils with both left and right-handed helical configuration (Fig. 4 and Supplementary Video 5). Almost 50% (20 out of 42 fibril) of the fibrils that we segmented were in helical groups, although the sampling was not purely random. Of these helical fibrils, 13 fibrils had a right-handed twist and 7 were left-handed (Fig. 4B). These fibrils made an average of 2.2 ± 1.4 turns around each other along the scan-length (Fig. 4C), that also corresponds to an overall $\sim 39 \pm 18 \mu\text{m}$ helical pitch (λ , the axial length of one full turn as described in Fig. 1F).

Finite element simulations of the helical fibrils

We used a finite element model to test our hypothesis that frictional contact between helically wrapped fibrils can transfer stress (load) between fibrils without a need for a mediating matrix. The stress transfer was proportional to the fibril's tensile modulus (Fig. 5A). Further parametric studies indicated that there is no change to the transferred stress with a change in Poisson's ratio (ν) (Fig. 5B). As expected, the transferred load increased with

an increase of frictional coefficient (μ) (Fig. 5C). Our results show that the load transfer decreased with an increase in pitch (λ) (Fig. 5D).

To evaluate the spatial distribution of stress and deformation along the length of each fibril and its dependence on the friction coefficient, we plotted the axial stress and axial displacement ($\bar{u}$, Eq. 4) at the end of loading (Fig. 6). The fibril stress was zero with no friction ($\mu = 0$, Fig. 6B) and it increased with higher friction coefficient (Fig. 6C and D). The axial stress varied linearly along the length of the fibril, increasing with distance from the free boundary and the stress in each fibril was the mirror image of the stress in the other one (Fig. 6A-D), which is in accordance with the static equilibrium condition. Similarly, for the fibril deformation, in the zero friction case, there was no axial deformation, hence the fibrils slid freely (Fig. 6E). When friction was increased, the induced deformation also increased, showing a plateau at the free ends indicating no strain, which confirms the stress-free boundary condition imposed on the model (Fig. 6F and G).

Discussion

In this study, we visualized the microscale structure of tendon fibrils in three dimensions using serial block-face scanning electron microscopy (SBF-SEM) and studied the mechanical implications of helical fibrils as a mechanism for interfibrillar load transfer using FE analysis. We found that tendon fibrils are not purely parallel structures and there are many helical fibrils that wrap around

each other and in groups. Our FE analysis indicated that, in addition to other
 310 potential mechanisms of load transfer (interfibrillar matrix and fusion/branching
 of smaller fibrils), the helical fibrils can also mediate load transfer through
 frictional mechanical contact.

Microstructure of fibrils and SBF-SEM

We observed helical structures that twisted around each other (Fig. 4).
 315 The existence of helical fibrils was previously reported (Bozec et al., 2007;
 Orgel et al., 2006), and were suggested to be left-handed (Franchi et al., 2010);
 however, our findings showed a similar number of the left-handed and right-
 handed helical fibrils (Fig. 4B). The formation of the helical structure has been
 explained based on a fibripositor model of fibril assembly (Kadler et al., 1996;
 320 Kalson et al., 2015) and the helicity of subfibrillar structures (Bozec et al.,
 2007). The helical fibril structures explain the rotation of tendon in tension
 (Buchanan et al., 2017). Additionally, they have been used as an explanation for
 the macro-scale mechanical behavior of tendon, in particular for the low
 stiffness at small deformations and the large tensile Poisson's ratio (Reese et al.,
 325 2010; Thorpe et al., 2013). The grouping of fibrils into helices can mediate load
 transfer by inducing frictional contact between fibrils during axial loading.

We observed some interesting but isolated features that can have
 implications for load transfer and loading on cells. For load transfer, we
 observed a tapered fibril end and fusion/branching, which agree with previous
 330 findings (Svensson et al., 2017), with the difference that the tapered end in this

study was observed in a “straight” fibril in contrast to the hairpin shape in the previous study. As previously suggested by Szczesny and co-workers (Szczesny et al., 2017), an instance of fusion/branching, such as the one described above, could mediate load transfer between fibrils via direct physical connection. A free fibril end like the tapered end can also mediate load transfer by allowing microscale sliding and shear stress, which is a well-documented phenomenon in experimental studies (Lee et al., 2017; Szczesny and Elliott, 2014a; Thorpe et al., 2013). Additionally, we observed a fibril that wrapped around the cells, which indicates that during an axial loading, lateral compression can be exerted on the cells affecting tendon mechanotransduction (Lavagnino et al., 2015).

The fibril structure assessment was subject to some limitations. The SBF-SEM technique generates large 3D datasets and segmentation is consequently difficult compared to 2D SEM, creating practical limitations in data collection and analysis (Svensson et al., 2017). Although we consequently chose to do in-depth manual segmentation for only one sample, we performed several scans of additional fascicles, and these scans showed similar structural features. Additionally, although the helical fibrils were easily observed and represented approximately half of the total fibrils in the image sequence, future work using 3D automated segmentation will be needed to calculate the frequency of helical fibril. A separate limitation is that our observations only included a region near the tenocytes, and other regions further away from the cells might have a different structure. Furthermore, we only scanned the tail tendon, which is a

low-stress tendon; further investigation is needed to confirm the existence of helical fibril groups in other tendons.

355 **Finite element simulations of the helical fibrils**

Interfibrillar load transfer by friction in a helical contact does not require interfibrillar matrix bonding, but the sum of its contribution over many fibrils and its relative magnitude in comparison to other load transfer mechanisms such as chemical bonding remains unknown. Here, the estimated magnitude of the transferred fibril stress ($\sim 0.2 - 4$ MPa) was low compared to the ultimate stress of the fibrils—typically in the range of 90 MPa (Liu et al., 2016). The large variation in mechanical parameters of fibrils (Table 1) and the unknown accumulation among hundreds of fibrils hinders accurate calculation of the total load transferred in situ by the interfibrillar friction mechanism. Of particular importance, the fibril-on-fibril friction coefficient is unavailable. Thus, more experimental measurements of single fibrils and groups of fibrils are needed for more accurate estimations.

The variations in fibril stress transfer and displacement observed in the parametric FE sensitivity analysis make physical sense (Fig. 6). In particular, the dependence of transferred stress with modulus and frictional coefficient are expected based on Hooke's law and Coulomb's friction law, respectively, and they were shown using our FE model (Fig. 5A and C). Note, however, that while this studies used the relatively simplified model of friction contact, additional mechanisms, such as hydrodynamic friction, molecular asperity, and

nonlinear dependence of friction coefficient to normal traction and other nano- and micro-scale tribological effects may be at interplay to induce load transfer between and within fibrils in the physiological system (Bhushan, 1999; Eyre et al., 2008; Sutcliffe et al., 1978; Ward et al., 2015). The decrease in reaction force by increasing the pitch of the helix, which is shown in Fig. 5D, can be explained by a reduction in lateral compression (normal force) on the fibrils as the pitch angle decreases and the fibrils become more parallel. The lack of dependence on Poisson's ratio was an unexpected observation that might be due to the high aspect ratio of the fibril's geometry or due to the isotropy of the constitutive relation (Fig. 5B). Large Poisson's ratio in tension ($\nu \sim 2$) have been reported for individual fibrils (Wells et al., 2015), which is greater than the isotropic limit of $\nu = 0.5$. To include Poisson's ratio's effect on the interfibrillar load transfer, anisotropy of the isolated fibril material may be needed to be incorporated. The curves in Fig. 5 were not smooth, which is potentially related to the nature of frictional contact that can switch between slip and stick conditions and cause jitter (imagine moving heavy house furniture on ceramic), however the trends are clear, and this does not affect the outcome of the sensitivity analysis.

Interfibrillar friction causes a gradient of axial stress in the fibril. In the simulated cases (Fig 6), the spatial distribution of stress variation and deformation match the distributions of stress and deformation based on established shear-lag theories as applied to tendon fibrils (Szczesny and Elliott,

2014b). To further put this study in the context of prior research on theory of wire ropes, it should be mentioned that, unlike helical ropes such as elevator and bridge cables, which are continuous strands with only a small and local effect of friction (Costello, 1997; Jiang et al., 1999); in tissue, experimental observations demonstrate significant microscale sliding that mediates load transfer. Therefore, while there remains open questions regarding the physical existence and frequency of free fibril ends in mature tendon (Provenzano and Vanderby, 2006; Svensson et al., 2017), experimental tensile data suggests there are “effective” free fibril ends that allow microscale sliding (Szczesny et al., 2015). It is possible that fibril ends may exist in the form of tapered ends (such as Fig. 3A) or as physically weak links along the fibril length that can act as an “effective end” due to its high compliance (Veres et al., 2014). Further investigations are required to explore these microstructures and their contribution to interfibrillar sliding and shear load transfer. Regardless of how the effective fibril ends occur, the experimental evidence of microscale sliding and shear load transfer supports our FE model based on friction and its inherent boundary condition assumption for free fibril ends.

In conclusion, we used SBF-SEM to visualize the three-dimensional microscale tendon structure of the fibrillar network, and used FE analysis to demonstrate that helically arranged fibrils can have the mechanical function of frictional interfibrillar load transfer. Interfibrillar friction should be considered as another potential mechanism for interfibrillar load transfer, in addition to the

previously postulated mechanisms of interfibrillar matrix shear and direct load
 420 transfer through fibril junctions. This study shows that a combined approach of
 SBF-SEM imaging and FE modeling is a powerful tool to study structure-
 mechanics relationships in tendon microstructure.

Conflict of interest

The authors do not have any conflict of interests to disclose.

Acknowledgments

We would like to acknowledge Bioimaging center in the Delaware
 Biotechnology Institute (DBI) and the Thermo Fisher Scientific Company for
 SBF-SEM imaging. The funding for this study was made available from NIH-
 NIBIB grant R01-EB002425. Microscopy access was supported by grants from
 430 the NIH-NIGMS (P20 GM103446), the NSF (IIA-1301765) and the State of
 Delaware. The content is solely the responsibility of the authors and does not
 necessarily represent the official views of the NIH.

Appendix: Supplementary dataset

The image stack for SBF-SEM images are available at (Safa et al., 2019).

References

Ahmadzadeh, H., Connizzo, B.K., Freedman, B.R., Soslowsky, L.J., Shenoy,
 V.B., 2013. Determining the contribution of glycosaminoglycans to tendon
 mechanical properties with a modified shear-lag model. J. Biomech. 46,

2497–503.

- 440 Altraud, W., Daniela, F., Hristm Ann, C., Erner, W., Eercken, G., Knörzer, E.,
Koch, M.H.J.J., Mosler, E., Emetschek-Gansler, H.N., Nemetschek, T.,
Folkhard, W., Koch, M.H.J.J., Geercken, W., Knörzer, E., Mosler, E.,
Nemetschek-Gansler, H., Nemetschek, T., 1987. Twisted Fibrils are a
Structural Principle in the Assembly of Interstitial Collagens, Chordae
445 Tendineae Included. *Z. Naturforsch* 42, 1303–1306.
- Bhushan, B., 1999. *Handbook of micro/nanotribology*. CRC Press.
- Bonet, J., Wood, R.D., 1997. *Nonlinear Continuum Mechanics for Finite
Element Analysis*. Cambridge University Press.
- Bozec, L., van der Heijden, G., Horton, M., 2007. Collagen fibrils: nanoscale
450 ropes. *Biophys. J.* 92, 70–5.
- Buchanan, K.A., Lakes, R.S., Vanderby, R., 2017. Chiral behavior in rat tail
tendon fascicles. *J. Biomech.* 64, 206–211.
- Carniel, T.A., Klahr, B., Fancello, E.A., 2019. On multiscale boundary
conditions in the computational homogenization of an RVE of tendon
455 fascicles. *J. Mech. Behav. Biomed. Mater.* 91, 131–138.
- Chung, K.H., Chen, A.K., Anderton, C.R., Bhadriraju, K., Plant, A.L., Bush,
B.G., Cook, R.F., Delrio, F.W., 2013. Frictional properties of native and
functionalized type i collagen thin films. *Appl. Phys. Lett.* 103, 143703.
- Costello, G.A., 1997. *Theory of Wire Rope*, Mechanical Engineering Series.
460 Springer New York, New York, NY.

Eyre, D.R., Weis, M.A., Wu, J.-J., 2008. Advances in collagen cross-link analysis. *Methods* 45, 65–74.

Fessel, G., Snedeker, J.G., 2009. Evidence against proteoglycan mediated collagen fibril load transmission and dynamic viscoelasticity in tendon. *Matrix Biol.* 28, 503–10.

Folkhard, W., Koch, M.H.J., Geercken, W., Knörzer, E., Mosler, E., Nemetschek-Gansler, H., Nemetschek, T., 1987. Twisted fibrils are a structural principle in the assembly of interstitial collagens, chordae tendineae included. *Zeitschrift fur Naturforsch. - Sect. C J. Biosci.* 42, 1303–1306.

Franchi, M., Ottani, V., Stagni, R., Ruggeri, A., 2010. Tendon and ligament fibrillar crimps give rise to left-handed helices of collagen fibrils in both planar and helical crimps. *J. Anat.* 216, 301–309.

Gautieri, A., Vesentini, S., Redaelli, A., Buehler, M.J., 2011. Hierarchical structure and nanomechanics of collagen microfibrils from the atomistic scale up. *Nano Lett.* 11, 757–766.

Hashimoto, T., Thompson, G.E., Zhou, X., Withers, P.J., 2016. 3D imaging by serial block face scanning electron microscopy for materials science using ultramicrotomy. *Ultramicroscopy* 163, 6–18.

Jiang, W.G., Yao, M.S., Walton, J.M., 1999. A concise finite element model for simple straight wire rope strand. *Int. J. Mech. Sci.* 41, 143–161.

Kadler, K.E., Holmes, D.F., Trotter, J.A., Chapman, J.A., 1996. Collagen fibril

formation. *Biochem. J* 316, 1–11.

Kalson, N.S., Lu, Y., Taylor, S.H., Starborg, T., Holmes, D.F., Kadler, K.E.,

485 2015. A structure-based extracellular matrix expansion mechanism of
fibrous tissue growth. *Elife* 4.

Kalson, N.S., Malone, P.S.C., Bradley, R.S., Withers, P.J., Lees, V.C., 2012.

Fibre bundles in the human extensor carpi ulnaris tendon are arranged in a
spiral. *J. Hand Surg. (European Vol.* 37, 550–554.

490 Kannus, P., 2000. Structure of the tendon connective tissue. *Scand. J. Med. Sci.*
Sport. 10, 312–320.

Kastelic, J., Galeski, A., Baer, E., 1978. The Multicomposite Structure of
Tendon. *Connect. Tissue Res.* 6, 11–23.

Lavagnino, M., Wall, M.E., Little, D., Banes, A.J., Guilak, F., Arnoczky, S.P.,

495 2015. Tendon mechanobiology: Current knowledge and future research
opportunities. *J. Orthop. Res.* 33, 813–22.

Lee, A.H., Szczesny, S.E., Santare, M.H., Elliott, D.M., 2017. Investigating
mechanisms of tendon damage by measuring multi-scale recovery
following tensile loading. *Acta Biomater.* 57, 363–372.

500 Lillie, J.H., MacCallum, D.K., Scaletta, L.J., Occhino, J.C., 1977. Collagen
structure: Evidence for a helical organization of the collagen fibril. *J.*
Ultrasructure Res. 58, 134–143.

Liu, Y., Ballarini, R., Eppell, S.J., 2016. Tension tests on mammalian collagen
fibrils. *Interface Focus* 6, 20150080.

- 505 Maas, S., Rawlins, D., Weiss, J.A., Ateshian, G.A., 2019. FEBio Manual 2.8
[WWW Document]. URL https://help.febio.org/FEBio/FEBio_um_2_8/
(accessed 10.4.19).
- Maas, S.A., Ellis, B.J., Ateshian, G.A., Weiss, J.A., 2012. FEBio: Finite
Elements for Biomechanics. *J. Biomech. Eng.* 134, 011005.
- 510 Minary-Jolandan, M., Yu, M.F., 2009. Nanomechanical heterogeneity in the
gap and overlap regions of type I collagen fibrils with implications for bone
heterogeneity. *Biomacromolecules* 10, 2565–2570.
- Orgel, J.P.R.O., Irving, T.C., Miller, A., Wess, T.J., 2006. Microfibrillar
structure of type I collagen in situ. *Proc. Natl. Acad. Sci.* 103, 9001–9005.
- 515 Pensalfini, M., Duenwald-Kuehl, S., Kondratko-Mitnacht, J., Lakes, R.,
Vanderby, R., 2014. Evaluation of global load sharing and shear-lag models
to describe mechanical behavior in partially lacerated tendons. *J. Biomech.*
Eng. 136, 091006.
- Pingel, J., Lu, Y., Starborg, T., Fredberg, U., Langberg, H., Nedergaard, A.,
520 Weis, M., Eyre, D., Kjaer, M., Kadler, K.E., 2014. 3-D ultrastructure and
collagen composition of healthy and overloaded human tendon: evidence of
tenocyte and matrix buckling. *J. Anat.* 224, 548–555.
- Provenzano, P.P., Vanderby, R., 2006. Collagen fibril morphology and
organization: Implications for force transmission in ligament and tendon.
525 *Matrix Biol.* 25, 71–84.
- Redaelli, A., Vesentini, S., Soncini, M., Veres, S.P., Mantero, S., Monteverchi,

F.M., 2003. Possible role of decorin glycosaminoglycans in fibril to fibril force transfer in relative mature tendons—a computational study from molecular to microstructural level. *J. Biomech.* 36, 1555–1569.

530 Reed, R., Wood, M.J., Keech, M.K., 1956. Helical Nature of the Collagen Fibril. *Nature* 177, 697–699.

Reese, S.P., Maas, S.A., Weiss, J.A., 2010. Micromechanical models of helical superstructures in ligament and tendon fibers predict large Poisson’s ratios. *J. Biomech.* 43, 1394–400.

535 Safa, B.N., Meadows, K.D., Szczesny, S.E., Elliott, D.M., 2017. Exposure to buffer solution alters tendon hydration and mechanics. *J. Biomech.* 61, 18–25.

Safa, B.N., Peloquin, J.M., Natriello, J.R., Caplan, J.L., Elliott, D.M., 2019. Cross-sectional serial block-face images of rat tail tendon fascicle.

540 Screen, H.R.C., Shelton, J.C., Chhaya, V.H., Kayser, M. V., Bader, D.L., Lee, D.A., 2005. The Influence of Noncollagenous Matrix Components on the Micromechanical Environment of Tendon Fascicles. *Ann. Biomed. Eng.* 33, 1090–1099.

Snedeker, J.G., Foolen, J., 2017. Tendon injury and repair – A perspective on the basic mechanisms of tendon disease and future clinical therapy. *Acta Biomater.*

Starborg, T., Kadler, K.E., 2015. Serial block face-scanning electron microscopy: A tool for studying embryonic development at the cell-matrix

interface. Birth Defects Res. Part C - Embryo Today Rev. 105, 9–18.

- 550 Starborg, T., Kalson, N.S., Lu, Y., Mironov, A., Cootes, T.F., Holmes, D.F.,
Kadler, K.E., 2013. Using transmission electron microscopy and 3View to
determine collagen fibril size and three-dimensional organization. Nat.
Protoc. 8, 1433–1448.
- Sutcliffe, M.J., Taylor, S.R., Cameron, A., 1978. Molecular asperity theory of
555 boundary friction. Wear 51, 181–192.
- Svensson, R.B., Herchenhan, A., Starborg, T., Larsen, M., Kadler, K.E.,
Qvortrup, K., Magnusson, S.P., Peter Magnusson, S., Magnusson, S.P.,
2017. Evidence of structurally continuous collagen fibrils in tendons. Acta
Biomater. 50, 293–301.
- 560 Szczesny, S.E., Caplan, J.L., Pedersen, P., Elliott, D.M., 2015. Quantification of
Interfibrillar Shear Stress in Aligned Soft Collagenous Tissues via Notch
Tension Testing. Sci. Rep. 5, 14649.
- Szczesny, S.E., Edelstein, R.S., Elliott, D.M., 2014. DTAF dye concentrations
commonly used to measure microscale deformations in biological tissues
565 alter tissue mechanics. PLoS One 9, e99588.
- Szczesny, S.E., Elliott, D.M., 2014a. Interfibrillar shear stress is the loading
mechanism of collagen fibrils in tendon. Acta Biomater. 10, 2582–2590.
- Szczesny, S.E., Elliott, D.M., 2014b. Incorporating plasticity of the interfibrillar
matrix in shear lag models is necessary to replicate the multiscale
570 mechanics of tendon fascicles. J. Mech. Behav. Biomed. Mater. 40, 325–

338.

Szczesny, S.E., Fetchko, K.L., Dodge, G.R., Elliott, D.M., 2017. Evidence that interfibrillar load transfer in tendon is supported by small diameter fibrils and not extrafibrillar tissue components. *J. Orthop. Res.* 35, 2127–2134.

575 Thorpe, C.T., Klemm, C., Riley, G.P., Birch, H.L., Clegg, P.D., Screen, H.R.C., 2013. Helical sub-structures in energy-storing tendons provide a possible mechanism for efficient energy storage and return. *Acta Biomater.* 9, 7948–7956.

Veres, S.P., Harrison, J.M., Lee, J.M., 2014. Mechanically overloading collagen 580 fibrils uncoils collagen molecules, placing them in a stable, denatured state. *Matrix Biol.*

Vidal, B. de C., 2003. Image analysis of tendon helical superstructure using interference and polarized light microscopy. *Micron* 34, 423–432.

Ward, A., Hilitski, F., Schwenger, W., Welch, D., Lau, A.W.C., Vitelli, V., 585 Mahadevan, L., Dogic, Z., 2015. Solid friction between soft filaments. *Nat. Mater.* 14, 583–588.

Wells, H.C., Sizeland, K.H., Kaye, H.R., Kirby, N., Hawley, A., Mudie, S.T., Haverkamp, R.G., 2015. Poisson's ratio of collagen fibrils measured by small angle X-ray scattering of strained bovine pericardium. *J. Appl. Phys.* 590 117, 184905.

Wenger, M.P.E., Bozec, L., Horton, M.A., Mesquida, P., 2007. Mechanical properties of collagen fibrils. *Biophys. J.* 93, 1255–63.

Yang, L., van der Werf, K.O., Dijkstra, P.J., Feijen, J., Bennink, M.L., 2012.

Micromechanical analysis of native and cross-linked collagen type I fibrils

595 supports the existence of microfibrils. J. Mech. Behav. Biomed. Mater. 6,
148–158.

Zimmerman, B.K., Ateshian, G.A., 2018. A Surface-to-Surface Finite Element

Algorithm for Large Deformation Frictional Contact in febio. J. Biomech.

Eng. 140, 081013.

600

Table 1

Table 1: Collagen fibril mechanical properties: Young's modulus (E), Poisson's ratio (ν), frictional coefficient (μ) in tendon unless otherwise noted.

E (GPa)	ν	μ	Method	Tissue	Ref.
0.1 – 10	0 – 0.4	0 – 2	-	Rat tail	Current study's range
0.326 ± 0.112	-	-	Tensile test MEMS	Rat patellar	(Liu et al., 2016)
0.6 ± 0.2	-	-	Tensile test AFM	Bovine Achilles	(Yang et al., 2012)
0.3 – 1.2	-	-	Atomistic modeling	-	(Gautieri et al., 2011)
1.6 ± 0.4	-	-	Shear-lag curve fitting	Rat tail	(Szczesny and Elliott, 2014)
1.2 – 2.2	-	-	Indentation AFM	Bovine Achilles	(Minary-Jolandan and Yu, 2009)
3.75 – 11.5	0 – 0.5	-	Indentation AFM	Rat tail	(Wenger et al., 2007)
-	2.1 ± 0.7	-	X-ray diffraction	Bovine pericardium	(Wells et al., 2015)
-	-	~ 0.4	Indentation AFM	Collagen film	(Chung et al., 2013)

Figure 1

Figure 1: (A) Representative SEM image and in-plane segmentation (scale bar = 5 μm), (B) SBF-SEM imaging process showing sequential stacks of images and a schematic fibril label (dotted orange line) along the tendon length, (C) schematics of fibrils with large (left) and low (right) tortuosity that shows the cross-sectional area (A_i) of fibrils throughout the scan depth and the incremental distance (s_i) between the center of the fibrils. (D) By comparing the distribution and (E) cumulative distribution function (CDF) of the diameter using the averaged 2D automatic segmentation of all fibrils (blue) and the 3D manual segmentation of a subset of 42 fibrils (red), it is evident that the manually segmented fibrils are a representative of the full fibril population. (F) For the finite element analysis a model with three full turns is used ($L = 3\lambda$). The boundary condition is that one fibril (blue) is anchored (left), while the other fibril (red) is pulled in the axial direction (arrow, right) to a deformation of $\Delta L = L\varepsilon$. (G) The mesh used for the finite element simulations shows that the fibrils were initially in contact throughout the length

Figure 2

Figure 2: (A) Lateral view of the three dimensional segmentation along the scan length with cell nuclei. Although the fibrils are primarily axially oriented, they have a complex three-dimensional network. (B) the 95% confidence interval (highlighted in pink) of the normalized diameter ($\bar{d}$, Eq. 1) contains the unity value throughout the scan depth with less than 5% variation, which indicates that the diameter of the fibrils does not change along the scan depth. (C) Percent-tortuosity (τ , Eq. 2) was calculated as a measure of the complexity of the fibrillar structure for the fibrils in helical groups (marked with blue squares) and the other fibrils (marked with red circles) separately. The helical fibril tortuosity was correlated with the diameter, with the small diameter fibrils being more tortuous, however, tortuosity was uniform for the other fibrils.

Figure 3

Figure 3: Three interesting but isolated structural features were observed: (A) tapered fibril end (B) fibril fusion/branching and (C) a helical fibril that wrapped around cells (only the nuclei are shown). For each feature, the first row includes the 3D segmentation, and the second row shows the segmentation mask overlaid on the SEM section image (dashed red box). In (A) and (B) scale bar = 1 μm , for (C) scale bar = 5 μm .

Figure 4

Figure 4: Many helical structures were observed in the axial view of the fibrils that are evident in the figures (A) with and (B) without the cell nuclei. The helical fibril groups have both left (marked with + ccw curve) and right-handed (marked with – cw curve) twist. (C) Shows three examples of the groups of twisting fibrils with pitch ranging from 20 μm to 86 μm .

Figure 5

Figure 5: Finite element analysis of stress transfer due to friction between helically grouped fibrils. Base material properties $E = 1$ GPa, $\nu = 0.2$, $\mu = 0.5$, $\lambda = 40 \mu m$. The transferred stress (A) increases with fibril modulus E , and (B) is insensitive to Poisson's ratio ν , (C) increases with frictional coefficient μ , and (D) decreases with increasing helix pitch λ .

Figure 6

Figure 6: Finite element simulation of two helically wrapped fibrils. (A) Axial stress distribution in the fibrils for the undeformed (top) and deformed (bottom) states for $\mu = 0.5$. The geometrical scale is compacted 10 times in the axial direction for clarity. (B–D) Stress along the length of the fibrils, and (E–G) normalized displacement ($\bar{u}$, Eq. 4) along the length of the fibrils for various choices of friction coefficient μ . With no friction ($\mu = 0$) there was no σ or $\bar{u}$ (B, E). As the frictional coefficient increases, the stress and the deformation increases for $\mu = 0.5$ (C, F) and for $\mu = 2$ (D, G). The model parameters are $E = 1$ GPa, $\nu = 0.2$, $\lambda = 40$ μm .